

REPORT DOCUMENTATION PAGE

Form Approved
OMB No. 0704-0188

2

AD-A250 166



Not estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and reviewing the information, and completing and reviewing this collection of information. Send comments regarding this burden estimate or any aspect of this collection of information, including suggestions for reducing the burden, to Washington Headquarters Service, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.

2. REPORT DATE
April 1992

3. REPORT TYPE AND DATES COVERED
Technical Rept. (Interim) 9/1/91-8/30/92

4. TITLE AND SUBTITLE

Electronic Structure of Fullerene Tubules

5. FUNDING NUMBERS

C: N00014-92-WX-24183
PE: 0601153N
PR: RR013-01-01
RR022-03-02
TA: 4131062-03
WU: 61-3932-02

6. AUTHOR(S)

J.W. Mintmire, D.H. Robertson, B.I. Dunlap,
R.C. Mowrey, D.W. Brenner, and C.T. White

7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES)

Naval Research Laboratory
Washington, DC 20375-5000
(Code 6170, D.L. Venezky)

8. PERFORMING ORGANIZATION REPORT NUMBER

Technical Report #4

9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)

Office of Naval Research
800 N. Quincy Street
Arlington, VA 22217-5000
(Code 1113PS, P.P. Schmidt)

10. SPONSORING/MONITORING AGENCY REPORT NUMBER

11. SUPPLEMENTARY NOTES

In press in Materials Research Society Proc. No. 247 (1992)

12a. DISTRIBUTION / AVAILABILITY STATEMENT

This document has been approved for public release and sale; its distribution is unlimited.

12b. DISTRIBUTION CODE

DTIC
ELECTE
MAYO 4 1992
S D D

13. ABSTRACT (Maximum 200 words)

Recent reports suggest that graphitic tubules with diameters on the order of fullerene diameters have been synthesized. Such small-diameter tubules should have electronic properties related to those of two-dimensional graphite. We demonstrate by comparison with results from a first principles, self-consistent, all electron Gaussian-orbital based local-density functional approach that an all-valence tight-binding model can be expected to give a reasonable description of the electronic states of these tubules. In analyzing both high-symmetry tubules and lower-symmetry chiral tubules, we see that a relatively high carrier density could be expected for many of these structures.

14. SUBJECT TERMS

Fullerene, tubule, electronic structure

15. NUMBER OF PAGES

16. PRICE CODE

17. SECURITY CLASSIFICATION OF REPORT

Unclassified

18. SECURITY CLASSIFICATION OF THIS PAGE

Unclassified

19. SECURITY CLASSIFICATION OF ABSTRACT

Unclassified

20. LIMITATION OF ABSTRACT

OFFICE OF NAVAL RESEARCH

CONTRACT # N00014-92-WX-24183

R&T Code 4131062

Technical Report No. 4

Electronic structure of fullerene tubules

by

J.W. Mintmire, D.H. Robertson, B.I. Dunlap,
R.C. Mowrey, D.W. Brenner, and C.T. White

In press, *Electrical, Optical, and Magnetic Properties of Organic Solid State Materials*, Eds., L. Y. Chiang, A. F. Garito, and D. J. Sandman, MRS Symposia Proceedings No. 247 (Materials Research Society, Pittsburgh, PA, 1992).

Code 6170, Chemistry Division
U.S. Naval Research Laboratory
Washington, DC 20375-5000

April 15, 1992

Accession For	
NTIS CRA&I	<input checked="" type="checkbox"/>
DTIC TAB	<input type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	
By	
Distribution /	
Availability	
Dist	Availability Special
A-1	

Reproduction in whole or in part is permitted for any purpose of the United States Government

This document has been approved for public release and sale; its distribution is unlimited.

92 4 29 128

92-11870



Electronic Structure of Fullerene Tubules

J. W. MINTMIRE, D. H. ROBERTSON, B. I. DUNLAP, R. C. MOWREY,
D. W. BRENNER, and C. T. WHITE
Naval Research Laboratory, Washington, DC 20375-5000

ABSTRACT

Recent reports suggest that graphitic tubules with diameters on the order of fullerene diameters have been synthesized. Such small-diameter tubules should have electronic properties related to those of two-dimensional graphite. We demonstrate by comparison with results from a first-principles, self-consistent, all-electron Gaussian-orbital based local-density functional approach that an all-valence tight-binding model can be expected to give a reasonable description of the electronic states of these tubules. In analyzing both high-symmetry tubules and lower-symmetry chiral tubules, we see that a relatively high carrier density could be expected for many of these structures.

INTRODUCTION

Recent developments in synthetic techniques have allowed the synthesis of macroscopic amounts of the all-carbon fullerenes C_{60} and C_{70} , [1] and the availability of these materials has led in turn to an explosive increase in research efforts concentrating on understanding the fullerenes. Several workers have speculated on the possibility of obtaining small-diameter all-carbon tubules with transverse dimensions on the scale of the molecular fullerenes. [2-4] Work on carbon fibers [5,6] has demonstrated that tubular graphitic filaments can be synthesized with filament diameters as small as 10 nm. Recently, Wang and Buseck [3] have reported observations of elongated ellipsoidal structures in transmission electron microscopy images of fullerene materials, which were interpreted as larger all-carbon fullerene cages containing roughly 130 carbons. Chai, *et al.* [4] have discussed the possibility that fullerenes containing multiple metal atoms may be extended prototubular structures such as those seen by Wang and Buseck. Iijima [7] has presented preliminary work that suggests that graphitic tubules with diameters as small as 2.2 nm can be produced using an arc-discharge evaporation method similar to that used for fullerene synthesis, with small carbon needles grown on one of the electrodes.

Herein is a preliminary report of our work analyzing the electronic structure of fullerene tubules. First we present results for the electronic structure of a high-symmetry fullerene tubule using a first-principles, self-consistent, all-electron Gaussian-orbital based local-density functional approach. We then compare results we obtain for the same tubule using a valence tight-binding approach, and find that the full-valence tight-binding approach can give a reasonable description of the one-electron energy levels with appropriate parameterization. We finally examine a sample chiral tubule similar to those suggested by Iijima's work, and discuss how the electronic states should affect the properties of these materials.

TUBULE STRUCTURE

As noted by previous workers, a model for a graphitic tubule is that of rolling up a single layer of graphite in its honeycomb lattice into a cylindrical tubule with constant diameter. We can thus visualize the graphitic tubule as a conformal mapping of the two-dimensional honeycomb lattice (depicted in Figure 1) to the surface of a cylinder.

We can then see directly by inspection of Figure 1 that the proper periodic boundary conditions can only be satisfied if the circumference of the cylinder maps to one of the Bravais lattice vectors for the graphite sheet. Thus each real lattice vector of the two-dimensional hexagonal lattice (the Bravais lattice for the honeycomb) defines a different way of rolling up the sheet into a tubule. The point group symmetry of the honeycomb lattice will make many of these equivalent, however, so truly unique tubules are only generated using a one-sixth irreducible wedge of the Bravais lattice.




Figure 1. Two-dimensional graphite lattice structure. Line segments OA and OB represent two lattice translation vectors for the hexagonal lattice.

Furthermore all tubules generated by such a conformal mapping must have translational periodicity. In our conformal mapping, we choose a real lattice vector (although not necessarily a primitive lattice vector) to map to the circumference of the tubule. The perpendicular direction then maps to the tubule axis. Consider the primitive reciprocal lattice vectors of the two-dimensional hexagonal lattice. These vectors are by construction each perpendicular to one of the primitive real lattice vectors. The perpendicular to a real lattice vector is then proportional to within a scalar constant to an integer multiple of the primitive reciprocal lattice vectors. For the hexagonal lattice there exist real lattice vectors also proportional to the primitive reciprocal lattice vectors to within a scalar constant; therefore we will always be able to find a real lattice translation vector that maps to the tubule axis direction. Thus all such tubules must have translational periodicity.

The base fullerene, C_{60} , has a soccer-ball structure (a truncated icosahedron) formed from 12 pentagons and 20 hexagons. [8-11] Experimental evidence [9,12] implies that the larger fullerene, C_{70} , has a D_{5h} structure that can be constructed by orienting the C_{60} along one of its C_5 axes, and then inserting 5 new hexagons by equatorially adding a planar ring of 10 carbon atoms while simultaneously rotating the two caps with respect to each other. As discussed by several workers, an extended structure can be formed by continuing to add such rings, each one rotated one-half full turn from the last. The transverse dimensions of this tubule are consistent with the ellipsoidal structures having a cross-section diameter of ~ 0.7 nm—roughly that of the diameter of C_{60} —observed by Wang and Buseck. In terms of a conformal mapping of a graphite sheet, this tubule structure is generated by mapping the line segment OA in Figure 1 to the circumference of the tubule.

ELECTRONIC STRUCTURE RESULTS

We have calculated the electronic structure of an infinitely long tubule using a first-principles, all-electron, self-consistent local-density functional (LDF) method originally developed to treat chain polymers [13] and recently adapted for helical symmetry. [14] This method calculates the total energy and the electronic structure using local Gaussian-type orbitals within a one-dimensional band structure approach. Our structure was generated by a planar ring of 10 carbon atoms with D_{5h} symmetry arranged in 5 pairs; the distance between interior members of adjacent pairs was fixed at 0.284 nm, twice the nearest-neighbor separation typical of fullerenes and other graphitic systems. The tubule structure was generated with a screw operation having a twist of π radians and a translational shift




Figure 2. LDF (left) and valence tight-binding band structure and density-of-states (right, DOS is per carbon atom) for high-symmetry fullerene tubule. Note that the Fermi level is given by the dotted line denoted ϵ_F for the LDF results and is defined at zero energy for the tight-binding results. DOS value at right-hand side of figure would be 0.8 eV^{-1} .

of 0.123 nm chosen to yield nearest-neighbor separations between rings equal to the in-ring values. The one-electron states are Bloch functions generated by repeated application of the screw operation, and belong to irreducible representations of the screw symmetry group with a dimensionless analog of the wave vector, k . In the calculations we used 20 evenly-spaced points in the one-dimensional Brillouin zone ($-\pi < k \leq \pi$) and a carbon 7s3p Gaussian basis set.

We depict our calculated LDF valence band structure in the left-hand side of Figure 2. Because all of the operations of the C_{5v} point group commute with the screw-symmetry space group, we label all bands according to the 4 irreducible representations of the C_{5v} group: the rotationally-invariant a_1 and a_2 representations, and the doubly-degenerate e_1 and e_2 representations. Assignment of each calculated state to the appropriate symmetry then allows us to interpolate the bands to the resolution depicted in the figure. For this lattice structure we find the tubule is a metal, with the a_1 bands and a_2 bands crossing at a position in the Brillouin zone roughly 2/3 of the width of the half-Brillouin zone from the origin. The Fermi level, ϵ_F , coincides with this crossing.

We have also examined the use of an all-valence tight-binding model to calculate the electronic structure of larger tubule structures. We use a Slater-Koster parameterization [15] of the carbon valence states which we have parameterized [16,17] to earlier LDF band structure calculations [13] on polyacetylene. Within the notation of Ref. 15 our tight-binding parameters are given by $V_{ss\sigma} = -4.76 \text{ eV}$, $V_{sp\sigma} = 4.33 \text{ eV}$, $V_{pp\sigma} = 4.37 \text{ eV}$, and $V_{pp\pi} = -2.77 \text{ eV}$. We choose the diagonal term for the carbon p orbital, $\epsilon_p = 0$ which results in the s diagonal term of $\epsilon_s = -6.0 \text{ eV}$. We see that this tight-binding model reproduces the LDF band structures qualitatively quite well. We note in the density-of-states that around the Fermi level this system behaves roughly as a metal with a nearly constant density-of-states. In other work [18] several of us have discussed the possibility that particular fullerene structures may have advantages over other conjugated carbon structures such as polyacetylene and over larger-diameter graphitic tubules. First, the coupling between electronic states and lattice should be such that no gap is introduced at ϵ_F from Peierls distortion forces. [19] Second, a small diameter of the tubule should lead to an marked enhancement of carrier density in the tubule relative to that in normal

graphitic systems.

Iijima [7] has recently reported the preparation of graphitic tubules with diameters down to 2.2 nm. He interprets his electron diffraction data for these tubules as suggesting a range of tubule structures, including one example with one spiral rotation around the tubule axis giving an offset of three hexagons. Using the tight-binding model, we have examined a sample tubule which is generated by mapping the line segment OB in Figure 1 to the circumference of the tubule. This structure can be described as a $6 \times 222/7$ helix, with 6 carbons per motif and 222 motifs and 7 helical turns over one translational period, with a diameter of ~ 2.5 nm. The tight-binding electronic structure and density-of-states of this tubule are depicted in Figure 3.

The dominant characteristic of the band structure in Figure 3 is the rapid oscillatory behavior of the energy levels as a function of wave vector. This wave vector k is defined in terms of the phase shift of the local functions that comprise the Bloch functions for the delocalized states. The oscillatory behavior arises from hopping matrix elements between motifs which are close in real space but separated by a turn of the helix; the relative phase of these two functions thus oscillates rapidly as a function of k leading to the observed behavior.

We note that the density-of-states is becoming markedly more like graphite than that for the smaller-diameter tubule described above. We see that this structure is also metallic (*i.e.*, no gap at ϵ_F) although this condition is not universally true for all helical structures. In addition, although this system also has a metallic density-of-states at ϵ_F , the magnitude has been reduced by roughly a factor of 4 compared to the smaller tubule. This factor, in conjunction with an increased volume per carbon atom, should lead to a reduction in the effective carrier density of roughly an order of magnitude compared to that expected for the smaller tubule.




Figure 3. Valence tight-binding electronic band structure and density-of-states (per carbon atom) for $6 \times 222/7$ helix graphitic tubule. DOS scale is the same as in Figure 2.

SUMMARY

We have presented results for the electronic structure of a high-symmetry fullerene tubule using a first-principles, self-consistent, all-electron Gaussian-orbital based local-density functional approach. Comparing these results for the high-symmetry tubule with a Slater-Koster tight-binding model, we find that the approach can give an reasonable

description of the electronic states with appropriate parameterization. We examined a tubule similar to those suggested by Iijima's work, and find that although closer in character to graphite than the smaller tubule, it can still have a metallic density-of-states at the Fermi level. In analyzing these example tubules we see that a relatively high carrier density could be expected for many of these structures.

ACKNOWLEDGEMENTS

This work was supported in part by the U.S. Office of Naval Research. Computational support for this project was provided in part by a grant of computer resources from the Naval Research Laboratory. One of us (DHR) acknowledges a NRC/NRL Postdoctoral Research Associateship.

REFERENCES

1. W. Krätschmer, L. D. Lamb, K. Fostiropoulos, and D. R. Huffman, *Chem. Phys. Lett.* **170**, 167 (1990), *Nature* **347**, 354 (1990).
2. M. Dresselhaus and G. F. Dresselhaus, private communication.
3. S. Wang and P. R. Buseck, *Chem. Phys. Lett.* **181**, 1 (1991).
4. Y. Chai, T. Guo, C. Jin, R. E. Haufler, L. P. F. Chibante, J. Fure, L. Wang, J. M. Alford, and R. E. Smalley, *J. Phys. Chem.* **95**, 7564 (1991).
5. G. G. Tibbetts, *J. Crystal Growth* **66**, 632 (1984).
6. J. S. Speck, M. Endo, and M. S. Dresselhaus, *J. Crystal Growth* **94**, 834 (1989).
7. S. Iijima, *Nature* **354**, 56 (1991).
8. H. W. Kroto, J. R. Heath, S. C. O'Brien, R. F. Curl, and R. E. Smalley, *Nature* **318**, 162 (1985).
9. R. Taylor, J. P. Hare, A. K. Abdul-Sada, and H. W. Kroto, *J. Chem. Soc., Chem. Commun.*, 1423 (1990).
10. R. D. Johnson, G. Meijer, and D. S. Bethune, *J. Am. Chem. Soc.* **112**, 8983 (1990).
11. H. Ajie, M. M. Alvarez, S. J. Anz, R. D. Beck, F. Diederich, K. Fostiropoulos, D. R. Huffman, W. Krätschmer, Y. Rubin, K. E. Schriver, D. Sensharma, and R. L. Whetten, *J. Phys. Chem.* **94**, 8630 (1990).
12. R. D. Johnson, G. Meijer, J. R. Salem, and D. S. Bethune, *J. Am. Chem. Soc.* **113**, 3619 (1991).
13. J. W. Mintmire and C. T. White, *Phys. Rev. Lett.* **50**, 101 (1983); *Phys. Rev. B* **28**, 3283 (1983).
14. J. W. Mintmire, in *Density Functional Methods in Chemistry*, (Eds., J. Labanowski and J. Andzelm), pp. 125-138, Springer-Verlag (1991).
15. J. C. Slater and G. F. Koster, *Phys. Rev.* **94**, 1498 (1954).
16. M. L. Elert, J. W. Mintmire, and C. T. White, *J. Phys. (Paris), Colloq.* **44**, C3-451 (1983).
17. M. L. Elert, C. T. White, and J. W. Mintmire, *Mol. Cryst. Liq. Cryst.* **125**, 329 (1985).
18. J. W. Mintmire, B. I. Dunlap, and C. T. White, unpublished.
19. R. E. Peierls, *Quantum Theory of Solids* (Oxford Univ. Press, New York, 1955), p. 108.

Technical Report Distribution List: J.W. Mintmire
NRL Code 6170

Office of Naval Research Chemistry Division, Code 1113 800 North Quincy Street Arlington, VA 22217-5000	. . . 2 copies
Dr. James S. Murday Chemistry Division, Code 6100 Naval Research Laboratory Washington, DC 20375-5000	. . . 1 copy
Dr. Robert Green, Director Chemistry Division, Code 385 Naval Air Weapons Center Weapons Division China Lake, CA 93555-6001	. . . 1 copy
Dr. Elek Lindner Naval Command, Control and Ocean Surveillance Center RDT&E Division San Diego, CA 92152-5000	. . . 1 copy
Dr. Bernard E. Douda Crane Division Naval Surface Warfare Center Crane, IN 47522-5000	. . . 1 copy
Dr. Richard W. Drisko Naval Civil Engineering Laboratory Code L52 Port Hueneme, CA 93043	. . . 1 copy
Dr. Harold H. Singerman Naval Surface Warfare Center Carderock Division Detachment Annapolis, MD 21402-1198	. . . 1 copy
Dr. Eugene C. Fischer Code 2840 Naval Surface Warfare Center Carderock Division Detachment Annapolis, MD 21402-1198	. . . 1 copy
Defense Technical Information Center Building 5, Cameron Station Alexandria, VA 22314	. . . 2 copies

3STRACT DISTRIBUTION LIST

Professor Rodney J. Bartlett
Chemistry and Physics Department
University of Florida
362 Williamson Hall
Gainesville, FL 32611-2085

Professor Max Berkowitz
Department of Chemistry
University of North Carolina
Chapel Hill, North Carolina 27514

Professor Elliot R. Bernstein
Department of Chemistry
Colorado State University
Fort Collins, Colorado 80523

Doctor David Chandler
Department of Chemistry
University of California, Berkeley
Berkeley CA 94720

Professor Mostafa El-Sayed
Department of Chemistry
University of California, Los Angeles
Los Angeles, California 90024

Professor Jonathan G. Harris
Department of Chemical Engineering
Massachusetts Institute of Technology
Cambridge, MA 02139

Professor Purusottam Jena
Physics Department
Virginia Commonwealth University
Richmond, VA 23284-2000

Professor Jurgen Kreuzer
Department of Physics
Dalhousie University
Halifax, Nova Scotia B3H 3J5
Canada

Dr. Mark Maroncelli
Department of Chemistry
The Pennsylvania State University
152 Davey Laboratory
University Park, PA 16802

Professor Craig C. Martens
Department of Chemistry
University of California, Irvine
Irvine, CA 92717

Dr. T. Pavlopoulos
Naval Ocean Systems Center
Code 521
San Diego, California 92152-5000

Professor Laura Philips
Department of Chemistry
Cornell University
Ithaca, New York 14853

Professor Geraldine Richmond
Department of Chemistry
University of Oregon
Eugene, Oregon 97403

Professor Deanne Snavely
Department of Chemistry
Bowling Green State University
Bowling Green, Ohio 43402

Dr. David L. Venezky
Surface Chemistry Branch
Chemistry Division
Naval Research Laboratory
Washington DC 20375-5000

Professor Gregory A. Voth
University of Pennsylvania
Department of Chemistry
Philadelphia PA 19104-6323

Professor S. E. Webber
Department of Chemistry
The University of Texas at Austin
Austin, Texas 78712-1167

Professor Michael Zerner
Department of Chemistry
The University of Florida
Gainesville, FL 32611