

2

AD-A261 720



TECHNICAL REPORT
NATICK/TR-93/019

AD _____

ALTERNATING CURRENT (AC) IMPEDANCE TESTING OF COATED TRAYCANS

By
Kurt Lawson
John Beavers

CORTEST COLUMBUS TECHNOLOGIES
COLUMBUS, OHIO 42325

January 1993

FINAL REPORT
JULY 1991 to JANUARY 1993

S DTIC
ELECTE
MAR 05 1993 **D**
E

93-04677

Approved for Public Release; Distribution Unlimited

Prepared for
UNITED STATES ARMY NATICK
RESEARCH, DEVELOPMENT AND ENGINEERING CENTER
NATICK, MA 01760-5000

FOOD ENGINEERING DIRECTORATE

93 3 4 049

DISCLAIMERS

The findings contained in this report are not to be construed as an official Department of the Army position unless so designated by other authorized documents.

Citation of trade names in this report does not constitute an official endorsement or approval of the use of such items.

DESTRUCTION NOTICE

For Classified Documents:

Follow the procedures in DoD 5200.22-M, Industrial Security Manual, Section II-19 or DoD 5200.1-R, Information Security Program Regulation, Chapter IX.

For Unclassified/Limited Distribution Documents:

Destroy by any method that prevents disclosure of contents or reconstruction of the document.

REPORT DOCUMENTATION PAGE			Form Approved OMB No. 0704-0188	
Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.				
1. AGENCY USE ONLY (Leave blank)	2. REPORT DATE January 1993	3. REPORT TYPE AND DATES COVERED Final July 1991 - January 1993		
4. TITLE AND SUBTITLE Alternating Current (AC) Impedance Testing of Coated Traycans			5. FUNDING NUMBERS OMA FR 728012.19 WU 9315746523000	
6. AUTHOR(S) Mr. Kurt Lawson Mr. John Beavers			8. PERFORMING ORGANIZATION REPORT NUMBER	
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) Cortest Columbus Technologies 2704 Sandburg Blvd Columbus, OH 42325			10. SPONSORING / MONITORING AGENCY REPORT NUMBER NATICK/TR-93/019	
9. SPONSORING / MONITORING AGENCY NAME(S) AND ADDRESS(ES) U.S. Army Natick RD&E Center ATTN: SAINC-WIS Kansas Street Natick, MA 01760-5018			10. SPONSORING / MONITORING AGENCY REPORT NUMBER	
11. SUPPLEMENTARY NOTES				
12a. DISTRIBUTION / AVAILABILITY STATEMENT Approved for public release; distribution unlimited			12b. DISTRIBUTION CODE	
13. ABSTRACT (Maximum 200 words) <p>This is the final report on Cortest Columbus Technologies' program entitled "AC Impedance Testing of Coated Traycans", performed under Contract DAAK60-90-1301. The overall objective of the program was to evaluate the relative resistance of several candidate coatings prior to retorting to a solution containing NaCl and citric acid (simulating saline, acidic food product) at ambient temperature. An additional objective of the program was to perform an initial assessment of the applicability of the AC impedance technique as a quality assurance technique for traycan coatings. The performance of the coatings was evaluated by means of an Electrochemical Impedance Spectroscopy (EIS) technique, also referred to as AC impedance.</p> <p>The EIS technique was found to be a sensitive technique for measuring coating degradation on the traycans. Of the coatings analyzed, the VMC coating, in general was found to be the best performer, followed closely by DMS and VMS. The control coating as found to be the poorest coating, of the coatings analyzed. No measurable effect of forming the corners of traycans on coating performance was found in the study. The EIS technique is promising for quality control but further research is needed to optimize the analysis time and simplify the test technique.</p>				
14. SUBJECT TERMS Traycan Corrosion Resistance Electrochemical Impedance Spectroscopy			15. NUMBER OF PAGES 33	
14. SUBJECT TERMS Tinplating Corrosion Test and Evaluation			16. PRICE CODE	
14. SUBJECT TERMS AC Impedance Tin-free Steel Coatings			16. PRICE CODE	
17. SECURITY CLASSIFICATION OF REPORT Unclassified	18. SECURITY CLASSIFICATION OF THIS PAGE Unclassified	19. SECURITY CLASSIFICATION OF ABSTRACT Unclassified	20. LIMITATION OF ABSTRACT SAR	

TABLE OF CONTENTS

	<u>Page</u>
FIGURES	iv
TABLES	v
INTRODUCTION.....	1
PROCEDURE	1
RESULTS	4
DISCUSSION	5
CONCLUSIONS	6
REFERENCE	8
APPENDIX	9
Figures	9
DISTRIBUTION LIST.....	25

Accession For	
NTIS CRA&I	<input checked="" type="checkbox"/>
DTIC TAB	<input type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	
By	
Distribution /	
Availability Codes	
Dist	Avail and/or Special
A-1	

DTIC QUALITY INSPECTED 1

LIST OF FIGURES

	Page
Figure A-1. Bode Plot For VMC Coating After 430 Hours of Exposure	10
Figure A-2. Bode Plot For VMC Coating After 1872 Hours of Exposure	11
Figure A-3. Bode Plot for Control Coating after 1872 Hours Exposure	12
Figure A-4. Total Resistance as a Function of Time for Control Coating (1). A and C were Corner Compartments, B was the Center Compartment	13
Figure A-5. Total Resistance as a Function of Time for Control Coating (2). A and C were Corner Compartments, B was the Center Compartment.....	14
Figure A-6. Total Resistance as a Function of Time for Control Coating (3). A and C were Corner Compartments, B was the Center Compartment.....	15
Figure A-7. Total Resistance as a Function of Time for RMS (1) Coating. A and C were Corner Compartments, B was The Center Compartment	16
Figure A-8. Total Resistance as a Function of Time for VMS (1) Coating. A and C were Corner Compartments, B was The Center Compartment	17
Figure A-9. Total Resistance as a Function of Time for VMS (2) Coating. A and C were Corner Compartments, B was The Center Compartment	18
Figure A-10. Total Resistance as a Function of Time for Abraded VMS Coating. A and C were Corner Compartments, B was The Center Compartment.....	19
Figure A-11. Total Resistance as a Function of Time for VMC (1) Coating. A and C were Corner Compartments, B was The Center Compartment	20
Figure A-12. Total Resistance as a Function of Time for DMS (1) Coating. A and C were Corner Compartments, B was The Center Compartment	21
Figure A-13. Total Resistance for Various Coatings after 500 Hours Exposure	22
Figure A-14. Total Resistance for Various Coatings after 1000 Hours Exposure	23
Figure A-15. Total Resistance for Various Coatings after 1500 Hours Exposure	24

LIST OF TABLES

	Page
Table 1. Coated Traycans Tested	2
Table 2. Summary of Tests	3

AC IMPEDANCE TESTING OF COATED TRAYCANS

INTRODUCTION

This is the final report on Cortest Columbus Technologies' program entitled "AC Impedance Testing of Coated Traycans", performed under Natick Contract DAAK60-90-1301. The overall objective of the program was to evaluate the relative resistance of several candidate coatings prior to retorting to a solution containing NaCl and citric acid (simulating a saline acidic food product) using the AC impedance technique. An additional objective of the program was to perform an initial assessment of the applicability of the AC impedance technique as a quality assurance technique for the traycan coatings.

PROCEDURE

a. Apparatus. The apparatus used by Cortest Columbus consists of a frequency response analyzer used in conjunction with a potentiostat connected to a microcomputer for data analysis and plotting. For the Natick contract, the test cell consisted of a traycan partitioned into three areas by means of dividers and foam gaskets to represent different configurations of the traycan surface. The test areas were filled with a three per cent solution of NaCl in deionized water adjusted to a pH of 4-5 to simulate a saline, acidic, aggressive food environment such as a tomato paste. The temperature was ambient and conditions were aerobic. The cell was covered with plastic film wrap to control evaporation (losses were made up with deionized water). There were seven traycan cells set up for testing at one time.

b. Coatings Studied. The coatings studied were the four variables considered in the Natick Traycan Improvement Program plus the current traycan. They represented the four candidate coatings applied on 0.75 tinplate traycans and the current traycan made of coated tin-free steel as the control. A detailed description of the coating variables is shown in Table 1. For

Table 1. Coated Traycans Tested

Designation	Exterior Coat	Base Coat	Interior Coat
1. Dexter Matte Sheet (DMS)*	Aluminum Vinyl	Epoxy Phenolic	Aluminum Vinyl
2. Reliance Matte Sheet (RMS)*	Aluminum Epoxy	Clear Epoxy	Aluminum Vinyl
3. Valspar Matte Sheet (VMS)*	Clear Epoxy	Clear Vinyl	Aluminum Vinyl-High Solids
4. Valspar Matte Coil (VMC)*	Clear Epoxy	Clear Epoxy	Aluminum Vinyl-High Solids
5. Valspar over Tin Free Steel (Control-Ctr)	Clear Epoxy	Clear Epoxy	White Vinyl

*Tin Plate Substrate - 90 lb per base box Electrolytic Tin Plate, Matte Finish, 0.75/0.35 tin weights.

identification purposes, candidate coatings were designated as Dexter Midland Matte Sheet (DMS), Reliance Matte Sheet (RMS), Valspar Matte Sheet (VMS) and Valspar Matte Coil (VMC). The control was designated as CTR.

c. Testing sequence was as follows:

(1) The first test run of cells consisted of duplicates of CTR and VMS coatings and one each of DMS, VMC and RMS coatings. After 1200 hours, this run was interrupted to allow setting up two different cells (Run #2, Table 2). CTR-1, VMS-2, and RMS coatings were terminated to provide space for Run #2 coating tests.

(2) The second test run of shorter duration, 500 hours, was conducted on a third control (CTR-3), and an abraded VMS to determine the effect of slight surface mechanical damage. A new control was also tested in this run, but was dropped from the program as the corrosion resistance was inferior.

(3) The remaining four of the original runs, CTR, VMS, DMS, and VMC continued to be tested for a total of 1900 hours. Table 2 outlines the test sequence:

Table 2. Summary of Tests

<u>Run #</u>	<u>Coating</u>	<u>Duration of Test, Hours</u>
1	CTR-1	1200
	CTR-2	"
	VMS-1	"
	VMS-2	"
	RMS	"
	DMS	"
	VMC	"
2	New Control*	500
	VMS-Abraded	500

CTR-3

Run #1 continued

VMS-1	1900	Total
CTR-2	1900	
DMS	1900	
VMC	1900	

* Dropped from program due to poor performance.

d. AC Impedance.

Test Technique.

A series of small AC voltages, less than 20 millivolts, were applied to the coated specimen by means of a platinum counter electrode. Using the potentiostat, the frequency response analyzer analyzed the correspondent lead or lag angle (phase shift, similar to power factor) and the AC impedance (similar to DC resistance) at each frequency of applied AC voltage. The computer was fed these data and calculated the impedance or resistance at each frequency and plotted these data for each exposure time being measured. This is called a Bode plot (Figure 1). Polarization or total resistance was obtained from the Bode plot by determining the impedance values for each measurement at the low frequency limit as shown in Figure 1. These data were plotted versus time in Figures 4-12 and for each coating in Figures 13-15 for 500, 1000 and 1500 hour exposure periods.

RESULTS

a. Bode Plots. Figures 1-3 represent the Bode plots after 430 and 1872 hours on two coatings tested. A Bode plot is a graph of the log of Z, the impedance or AC resistance versus the log of the frequency at which each measurement was made. The phase angle was also plotted versus frequency in

Figures 1-3. However, these plots were not used for making the final conclusions. As stated under "Procedure", the total system resistance, the low frequency limit for the polarization resistance, Z , was obtained for each Bode plot representing a specific coating and exposure time. This extrapolation procedure is illustrated in Figure 1.

b. Total Polarization Resistance versus Time Plots. These data are shown in Figures 4-12 and are obtained from Bode plots. These plots show the change in total resistance (corresponding to corrosion resistance) with exposure time for each coating.

c. Total Resistance versus Coating Type after 500, 1000, and 1500 Hours Exposure, Figures 13-15, respectively, illustrate these data after the three time periods. These data were obtained from the plots of total resistance versus time.

DISCUSSION

The objective of the investigation was to measure the overall performance of each coating by means of measuring the overall corrosion resistance versus time using the AC Impedance technique. In order to simplify the program, details obtained using this technique such as the Nyquist plots and phase angle versus frequency, which are useful in analyzing sub-components of the total resistance, are not included or considered herein. These subcomponents are solution, substrate, and pore resistance. Since the total resistance of the system to corrosion is the primary quantity of interest, only this information was used to reach the conclusions.

The results that lead to the following conclusions were the total resistance versus time plots (Figures 4-12) and the comparison of the resistance of the coatings tested after various exposures times (Figure 13-15). These data show that the VMC coating consistently exhibited the best preretort corrosion resistance of the coatings evaluated, exhibiting high

resistance values throughout the testing. A fall in resistance versus time is indicative of coating degradation. VMC exhibited only a slight decrease in resistance after 1500 hours of exposure. The DMS and VMS coating also performed well in the testing. The resistance of the DMS coating after 500 hours was comparable to that of the VMC coating, but the DMS coating degraded somewhat faster than the VMC coating thereafter. The VMS coating exhibited somewhat lower resistances than the VMC or DMS coatings and slowly degraded over the testing period. The remaining coatings, RMS and Control, exhibited lower performance than any of the tested coatings with Control showing the most rapid degradation. As anticipated, the abraded VMS coating exhibited very low resistances, demonstrating the expected values for a completely failed coating. For any of the coatings, comparison of the data for the three compartments indicates that there was no measurable effect of formed corners on coating performance.

VMC was considered by Central States Can Co., Massillon, Ohio to be the best of the coating candidates except for poor adhesion at formed corners of the traycan body. The next best, DMS, did not exhibit poor adhesion at the formed traycan corners.

CONCLUSIONS

(1) The AC Impedance technique was found to be a sensitive technique for measuring coating degradation on traycans.

(2) Of the coatings analyzed, the VMC coating was found to be the best performer, followed closely by the DMS and the VMS coatings. These conclusions approximated those reached in the Ross report¹.

(3) The Control coating was found to be the poorest coating, of the coatings analyzed.

(4) No measurable effect of forming the corners of the traycans on coating performance was found in the study. As mentioned above, VMC was reported to have poorer adhesion at the formed corners of the traycan body when compared to DMS.

(5) The AC Impedance technique is promising for quality control but further research is needed to optimize the analysis time and simplify the test technique.

It should be cautioned that the preceding conclusions are based on the long-term ambient temperature exposures and do not consider blistering or coating degradation associated with the high temperature thermal process to which filled and sealed traycans are subjected.

REFERENCE

1. Ross, Jeanne M. Evaluation of Half Steam Tray, Tinplate vs Tin-free steel, Phase I, Technical Report TR-91/030 U.S. Army Natick RD&E Center, FED, Nov 90

APPENDIX

Figures




Fig. A-1. Bode Plot for VMC Coating After 430 Hours of Exposure




Fig. A-2. Bode Plot for VMC Coating After 1872 Hours of Exposure




Fig. A-3. Bode Plot for Control Coating After 1872 Hours of Exposure




Fig. A-4. Total Resistance as a Function of Time for Control Coating (CTR 1). A and C were Corner Compartments, B was the Center Compartment.




Fig. A-5. Total Resistance as a Function of Time for Control Coating (CTR 2). A and C were Corner Compartments, B was the Center Compartment.




Fig. A-6. Total Resistance as a Function of Time for Control Coating (CTR 3). A and C were Corner Compartments, B was the Center Compartment.




Fig. A-7. Total Resistance as a Function of Time for RMS Coating 1. A and C were Corner Compartments, B was the Center Compartment.




Fig. A-8. Total Resistance as a Function of Time for VMS Coating 1. A and C were Corner Compartments, B was the Center Compartment.




Fig. A-9. Total Resistance as a Function of Time for VMS Coating 2. A and C were Corner Compartments, B was the Center Compartment.




Fig. A-10. Total Resistance as a Function of Time for Abraded VMS Coating. A and C were Corner Compartments, B was the Center Compartment.




Fig. A-11. Total Resistance as a Function of Time for VMC Coating 1. A and C were Corner Compartments, B was the Center Compartment.




Fig. A-12. Total Resistance as a Function of Time for DMS Coating 1. A and C were Corner Compartments, B was the Center Compartment.




Fig. A-13. Total Resistance for Various Coatings after 500 Hours of Exposure.




Fig. A-14. Total Resistance for Various Coatings after 1000 Hours of Exposure.




Fig. A-15. Total Resistance for Various Coatings after 1500 Hours of Exposure.

DISTRIBUTION LIST

	NO. OF COPIES
Administrator Defense Technical Information Center Alexandria, VA 22314	2
Technical Library U.S. Army Natick Research, Development and Engineering Center Natick, MA 01760-5000	4
Commander U.S. Army Natick Research, Development and Engineering Center ATTN: SATNC-WIS (George Dittmeier) Natick, MA 01760-5018	70
DOD Joint Technical Staff U.S. Army Natick Research, Development and Engineering Center ATTN: SATNC-TAA/SATNC-TAF/SATNC-TAD/ SATNC-TAN/SATNC-TAM Natick, MA 01760-5000	5
Special Assistant for DoD Food Program U.S. Army Natick Research, Development and Engineering Center ATTN: SATNC-WIS Natick, MA 01760-5018	1
Commander U.S. Army Troop Support Command ATTN: AMSIR-E 4300 Goodfellow Boulevard St. Louis, MO 63120-1798	1
Commander U.S. Army Test and Evaluation Command ATTN: AMSTE-EV-S Aberdeen Proving Ground, MD 21005-5055	1
HQDA DCSLOG ATTN: DALO-TST Washington, DC 20310-2300	1

DISTRIBUTION LIST (CONT'D)

HQDA OTSG ATTN: DASG-DEB Rm 617, Bldg 5, Skyline Place 5111 Leesburg Pike Falls Church, VA 22041-3258	1
Commandant U.S. Army Quartermaster Center and School (Provisional) ATTN: ATSM-CDT/AMISM-SFM-FM Fort Lee, VA 23801	2
Commandant U.S. Army Troop Support Agency ATTN: DALO-TAF/DALO-HS Fort Lee, VA 23801	2
Commander Defense Personnel Support Center ATTN: DPSC-HQ/DPSC-HS 2800 South 20th Street Philadelphia, PA 19101-8419	2
United States Department of Agriculture ATTN: USDA/AMS P.O. Box 96456 Washington, DC 44648-0642	1
Mr. Dave Blizzard Central States Can Company 700 16th St., S.E. Massillon, OH 44648-0642	5
David Dee, COL (Ret) Executive Secretary R&DA for Military Food and Packaging Systems, Inc 16607 Blanco Road, Suite 305 San Antonio, TX 78232	1
Commander U.S. Army Health Services Command ATTN: HSVS-F Fort Sam Houston, TX 78234-6000	1