

AD-A265 451

FR21998-19



15 May 1993

2

FATIGUE IN SINGLE CRYSTAL NICKEL SUPERALLOYS
Technical Progress Report

Daniel P. DeLuca
Principal Investigator

Charles Annis
Program Manager



P.O. Box 109600
West Palm Beach, FL 33410-9600
(407)796-6565

Government Engines and Space Propulsion

SDTIC
ELECTE
JUN 04 1993
S A D

15 May, 1993

Period of performance
16 April 1993 through 15 May 1993

Contract N00014-91-C-0124

Prepared for:
Dr. A. K. Vasudevan, Scientific Officer
Code 1222



This document has been approved
for public release and sale; its
distribution is unlimited.

Office of Naval Research
Department of the Navy
800 N. Quincy Street
Arlington, Va 22217-5000

93-12561



93 6 03 070

I. Introduction and Program Objective

This program investigates the seemingly unusual behavior of single crystal airfoil materials. The fatigue initiation processes in single crystal (SC) materials are significantly more complicated and involved than fatigue initiation and subsequent behavior of a (single) macrocrack in conventional, isotropic, materials. To understand these differences it is helpful to review the evolution of high temperature airfoils.

Characteristics of Single Crystal Materials

Modern gas turbine flight propulsion systems employ single crystal materials for turbine airfoil applications because of their superior performance in resisting creep, oxidation, and thermal mechanical fatigue (TMF). These properties have been achieved by composition and alloying, of course, but also by appropriate crystal orientation and associated anisotropy.

Early aeroengine turbine blade and vane materials were conventionally cast, equiaxed alloys, such as IN100 and Rene'80. This changed in the late 1960s with the introduction of directionally-solidified (DS) MAR-M200+Hf airfoils. The DS process produces a $\langle 001 \rangle$ crystallographic orientation, which in superalloys exhibits excellent strain controlled fatigue resistance due to its low elastic modulus. The absence of transverse grain boundaries, a 60% reduction in longitudinal modulus compared with equiaxed grains, and its corresponding improved resistance to thermal fatigue and creep, permitted significant increases in allowable metal temperatures and blade stresses. Still further progress was achieved in the mid-1970s with the development of single crystal airfoils¹.

The first such material, PWA 1480, has a considerably simpler composition than preceding cast nickel blade alloys because, in the absence of grain boundaries, no grain boundary strengthening elements are required. Deleting these grain boundary strengtheners, which are also melting point depressants, increased the incipient melt temperature. This, in turn, allowed nearly complete γ' solutioning during heat treatment and thus a reduction in dendritic segregation. The absence of grain boundaries, the opportunity for full solution heat treatment, and the minimal post-heat treat dendritic segregation, result in significantly improved properties as compared with conventionally cast or directionally solidified alloys. Single crystal castings also share with DS alloys the $\langle 001 \rangle$ crystal orientation, along with the benefits of the resulting low modulus in the longitudinal direction.

Pratt & Whitney has developed numerous single crystal materials. Like most, PWA 1480 and PWA 1484 are γ' strengthened cast mono grain nickel superalloys based on the Ni-Cr-Al system. The bulk of the microstructure consists of approximately 60% by volume of cuboidal γ' precipitates in a γ matrix. The precipitate ranges from 0.35 to 0.5 microns and is an ordered Face Centered Cubic (FCC) nickel aluminide compound. The macrostructure of these materials is characterized by parallel continuous primary dendrites spanning the casting without interruption in the direction of solidification. Secondary dendrite arms (perpendicular to solidification) define

¹ Gell, M., D. N. Duhi, and A. F. Giamei, 1980, "The Development of Single Crystal Superalloy Turbine Blades," *Superalloys 1980*, proceedings of the Fourth International Symposium on Superalloys, American Society for Metals, Metal Park, Ohio, pp. 205-214

A-1		
-----	--	--

the interdendritic spacing. Solidification for both primary and secondary dendrite arms proceeds in $\langle 001 \rangle$ type crystallographic directions. Undissolved eutectic pools and associated microporosity reside throughout the interdendritic areas. These features act as microstructural discontinuities, and often exert a controlling influence on the fatigue initiation behavior of the alloy. Also, since the eutectics are structurally dissimilar from the surrounding matrix their fracture characteristics will differ.

Single Crystal Fatigue

The fatigue process in single crystal airfoil materials is a remarkably complex and interesting process. In cast single crystal nickel alloys, two basic fracture modes, crystallographic and non-crystallographic, are seen in combination. They occur in varying proportions depending upon temperature and stress state. Crystallographic orientation with respect to applied load also affects the proportion of each and influences the specific crystallographic planes and slip directions involved. Mixed mode fracture is observed under monotonic as well as cyclic conditions.

Single crystal turbine blades are cast such that the radial axis of the component is essentially coincident with the $\langle 001 \rangle$ crystallographic direction which is the direction of solidification. Crystallographic fracture is usually seen as either octahedral along multiple (111) planes or under certain circumstances as (001) cleavage along cubic planes.

Non-crystallographic fracture is also observed. Low temperatures favor crystallographic fracture. At higher temperatures, in the 427C range, small amounts of non-crystallographic propagation have the appearance of transgranular fatigue in a related fine grain equiaxed alloy. Under some conditions, this propagation changes almost immediately to the highly crystallographic mode along (111) shear planes, frequently exhibiting prominent striations emanating from the fatigue origin and continuing to failure in overstress. Under other conditions the non-crystallographic behavior can continue until tensile failure occurs. At intermediate temperatures (around 760C) non-crystallographic propagation is more pronounced and may continue until tensile overload along (111) planes occurs, or may transition to subcritical crystallographic propagation. At 982C, propagation is almost entirely non-crystallographic, similar to transgranular propagation in a polycrystal.

Damage Catalogue

This program will identify and compile descriptions of the fracture morphologies observed in SC airfoil materials under various combinations of temperature and stress associated with advanced Navy aeropropulsion systems. We will suggest fatigue mechanisms for these morphologies and catalogue them as unique damage *states*. Most testing will be accomplished under ancillary funding, and therefore be available to this effort at no cost. The work is organized into four tasks, which are described in the following paragraphs.

II. Program Organization

The program is structured into four tasks, three technical and one reporting. The individual tasks are outlined here.

Task 100 - Micromechanical Characterization

This task will define the mechanisms of damage accumulation for the various types of fracture observed in single crystal alloys. These fracture characteristics will be used to establish a series of Damage States which represent the fatigue damage process. The basis for this investigation will be detailed fractographic assessment of failed laboratory specimens generated in concurrent programs. Emphasis will be on specifically identifying the micromechanical damage mechanisms, relating them to a damage state, and determining the conditions required to transition to an alternate state.

Task 200 - Analytical Parameter Development

This task will extend current methods of fatigue and fracture mechanics analysis to account for microstructural complexities inherent in single crystal alloys. This will be accomplished through the development of flexible correlative parameters which can be used to evaluate the crack growth characteristics of a particular damage state. The proposed analyses will consider the finite element and the hybrid Surface-Integral and Finite Element (SAFE) methods to describe the micromechanics of crack propagation.

Task 300 - Probabilistic Modeling

This task will model the accumulation of fatigue damage in single crystal alloys as a Markov process. The probabilities of damage progressing between the damage states defined in Task 100 will be evaluated for input into the Markov model. The relationship between these transition probabilities and fatigue life will then be exploited to establish a model with comprehensive life predictive capabilities.

Task 400 - Reporting

Running concurrently with the analytical portions of the program, this task will inform the Navy Program Manager and Contracting Officer of the technical and fiscal status of the program through R&D status reports.

III. Technical Progress

During the previous reporting period we reassessed our rationale for applying the Markov Paradigm, a statistical technique, to the fatigue and fracture process in single crystals. Our research into the micromechanics of fracture in these materials has greatly enhanced our knowledge of the fracture process. A probabilistic system is especially desirable in the absence of detailed knowledge of the physical processes controlling the events in question. We now can look upon these alloys with a greater appreciation of the underlying physics than we possess for many of our more conventional alloys. Consequently we have shifted the emphasis of our investigation to the underlying mechanisms controlling material behavior. The relationship of a microstructure to macroproperties was the original vision of the Navy Program Monitor.

The ability to predict the relationships between input energy, state energy (a function of composition) and fracture mode (determining fatigue crack growth rate) is fundamental to a micro-mechanically based life prediction system. In addition, it can represent a powerful tool in the hands of the alloy developer.

In January we described an experimental microstructure to enhance the damage tolerance of PWA 1480. The microstructure is characterized by a duplex γ' precipitate structure. The microstructure retains the fine cuboidal precipitate with an additional, larger "barrier" precipitate array. The solidification kinetics associated with the development of the duplex structure would be expected to result in a compositional difference in the fine precipitate compared to a microstructure of only the fine precipitate. We hypothesized that this compositional variation could result in microscopic fracture mode transition, a "state energy" induced transition. We have subsequently observed just such a transition and are in the process of determining the nature of the assumed compositional differences. Thin foil Transmission Electron Microscope (TEM) specimens have been produced from the baseline and modified microstructures and compositional data is being analyzed. The intent is to correlate superlattice composition with microscopic fracture mode. The compositional information could be used in an atomic simulator to determine if changes in anti phase boundary energy could account for the fracture mode transition. This information may result in a more intelligent approach to alloy design and life prediction.

A comprehensive report of work performed to date is being prepared.

IV. Current Problems

No technical problems have been encountered during the reporting period.

REPORT DOCUMENTATION PAGE		1. REPORT NO. FR2198-19	2.	3. Recipient's Accession No.
4. Title and Subtitle FATIGUE IN SINGLE CRYSTAL NICKEL SUPERALLOYS Technical Progress Report		5. Report Date 15 May, 1993		
7. Author(s) Charles Annis		6. Performing Organization Report No. FR2198-19		
9. Performing Organization Name and Address United Technologies Pratt & Whitney P. O. Box 109600 West Palm Beach, FL 33410-9600		10. Project/Task/Work Unit No.		
		11. Contract(G) or Grant(G) No. (C) N00014-91-C-0124 (G)		
12. Sponsoring Organization Name and Address Office of Naval Research Department of the Navy 800 N. Quincy Street Arlington, VA 22217-5000		13. Type of Report & Period Covered Monthly 04/16/93 - 05/15/93		
13. Supplementary Notes		14.		
16. Abstract (Limit 200 words) This program investigates the seemingly unusual behavior of single crystal airfoil materials. The fatigue initiation processes in single crystal (SC) materials are significantly more complicated and involved than fatigue initiation and subsequent behavior of a (single) macrocrack in conventional, isotropic, materials. To understand these differences is the major goal of this project.				
17. Document Analysis a. Descriptors Fatigue, Fracture, Single Crystal, PWA 1480, PWA 1484 b. Identifiers/Open-Ended Terms c. COSATI Field/Group				
18. Availability Statement Unlimited		19. Security Class (This Report) Unclassified		21. No. of Pages 5
		20. Security Class (This Page)		22. Price