		1 0	ISTRIBUTION	STATEMENT A
AD-A265 841	*.	-	Approved for Distribution	public releases u Unlimited
RT DQCU	MENTATION	PAGE		
T. REPORT SECURITY CLASSIFICATION	1b. RESTRICTIVE	MARKINGS		
SECURITY CLASSIFICATION AUTHORITY HERE LELT	DISTRIBUTION	AVAILABILITY	OF REPORT	
DONE STATION / DOWNGRADING SCIENCE (11) 19 1003	unlimit	ted		
PERFORMING ORGANIZATION REPORT NUMERICS)	5. MONITORING	ORGANIZATION	REPORT NUMB	ER(S)
Technical Report #53	ONR NO	0014 -89- J-	1225	
NAME OF PERFORMING ORGANIZATION 65. OFFICE SYMBOL	78. NAME OF MO	ONITORING O	GANIZATION	
University of Southern (" appicable)	nee:	OF NAMES	Decements	
	75. ADDRESS (Cit	y, State, and 2	Research	
University of Southern Mississippi	Chemis	try Divisi	on Starst	
uepartment of Polymer Science Hattiesburg, MS 39406-0076	Arling	rtn Quincy ton. VA	Street 22217-5000	
NAME OF FUNDING/SPONSORING Bb. OFFICE SYMBOL	9. PROCUREMEN	T INSTRUMENT	IDENTIFICATION	NUMBER
ORGANIZATION (If applicable) Office of Naval Research				
c ADDRESS (City, State, and ZIP Code)	10. SOURCE OF I	UNDING NUM	BERS	
Chemistry Division	PROGRAM	PROJECT	TASK	WORK UNIT
800 North Quincy Street Arlington VA 22217-5000	ELEMIENT NO.	NO.		
ATTING CON, VA 22217-5000				
2 PERSONAL AUTHOR(S)		and Ny:0		
C. G. Johnson, L. J. Mathias	LA DATE OF REM		the owned by the	
Technical FROM 6-1-92 to 5-31-92	3 93-6-	7 7	in, Day) - 13. Pl	
6. SUPPLEMENTARY NOTATION				
Submitted for Publication				
7. COSATI CODES 18. SUBJECT TERMS	(Continue on revers	e if necessary	and identify by	block number)
FIELD GROUP SUB-GROUP				
		+ 10 ¹ 0 minute 1 1 1 1 1 1 1		
9 ABSTRACT ' A series of copolymers was prepar	red from 11-a	minoundec	anoic and	12-
aminododecanoic acids by melt-condensation	at 210 °C in se	aled tubes	under vacu	ium.
Mole percentages of hylon 12 monomer were	9 U, 15, 35, 50, Jabaliat amino	acide areili	na 700 % in abies through	une the
Gebriel synthesis (only the 1-1 cooplymer was	enriched with n	itrogen-15)	. Solid-state	¹³ C
(at 100.6 MHz) and ¹⁵ N $(at 20.3 MHz)$ N	IMR spectrosc	opy, differ	ential scan	ning
anterior sida ande se alla differenciar an	nd infrared sp	ectroscopy	were used	d to
calonmetry, wide-angle x-ray dimaction, an	IN APP	nowed a sm	ooth shift of	f the
calonmetry, wide-angle x-ray dimaction, an characterize the copolymers. Solid-state ¹⁵ N N	vmH spectra sr			
calonimetry, wide-angle x-ray diffraction, ar characterize the copolymers. Solid-state ¹⁵ N N main peak position from 84 ppm for α -nylon	11 to 89 ppm	for y-nylor	1 12 for the	as-
catorimetry, wide-angle x-ray diffraction, ar characterize the copolymers. Solid-state ¹⁵ N N main peak position from 84 ppm for α -nylon prepared copolymers. Similar behavior was s	11 to 89 ppm een for amide	for γ-nylor V and VI π	1 12 for the nodes which	as- are
catorimetry, wide-angle x-ray dimaction, ar characterize the copolymers. Solid-state ¹⁵ N N main peak position from 84 ppm for α -nylon prepared copolymers. Similar behavior was s sensitive the α - and γ -crystal forms. Carbon-1	NMH spectra sr 11 to 89 ppm een for amide 3 NMR T, mea	for γ-nylor V and VI n surements	n 12 for the nodes which showed that	as- are the
calorimetry, wide-angle x-ray diffraction, ar characterize the copolymers. Solid-state ¹⁵ N N main peak position from 84 ppm for α -nylon prepared copolymers. Similar behavior was s sensitive the α - and γ -crystal forms. Carbon-1 most mobile sample was the 65:35 nvlon 11-c	NMH spectra sr 11 to 89 ppm een for amide 3 NMR T, mea o-12 polymer.	for γ-nylor V and VI π surements	12 for the nodes which showed the	as- are the
catorimetry, wide-angle x-ray dimaction, ar characterize the copolymers. Solid-state ¹⁵ N N main peak position from 84 ppm for α -nylon prepared copolymers. Similar behavior was s sensitive the α - and γ -crystal forms. Carbon-1 most mobile sample was the 65:35 nylon 11-c	11 to 89 ppm een for amide 3 NMR T ₁ mea o-12 polymer.	for y-nylor V and VI m surements	12 for the lodes which showed the fication	as- are the
Calorimetry, wide-angle x-ray dimaction, an characterize the copolymers. Solid-state ¹⁵ N M main peak position from 84 ppm for α-nylon prepared copolymers. Similar behavior was s sensitive the α- and γ-crystal forms. Carbon-1. most mobile sample was the 65:35 nvlon 11-c DISTRIBUTION / AVAILABILITY OF ABSTRACT	11 to 89 ppm een for amide 3 NMR T, mea 0-12 polymer.	for y-nylor V and VI m surements ECUNITY CLASS	1 12 for the nodes which showed the ification	as- are the
Calorimetry, wide-angle x-ray diffraction, an characterize the copolymers. Solid-state ¹⁵ N M main peak position from 84 ppm for α-nylon prepared copolymers. Similar behavior was s sensitive the α- and γ-crystal forms. Carbon-1 most mobile sample was the 65:35 nylon 11-c 20 DISTRIBUTION / AVAILABILITY OF ABSTRACT 20 DISTRIBUTION / AVAILABILITY OF ABSTRACT 20 DISTRIBUTION / AVAILABILITY OF ABSTRACT 20 NAME OF RESPONSIBLE INDIVIDUAL 20 J. Mathias	AMH spectra sr 11 to 89 ppm een for amide 3 NMR T ₁ mea 0-12 polymer. 21 ABSTRACT SI 225 TELEPHONE 601-266-4	for y-nylor V and VI m surements ECUNITY CLASS (include Area C 871	1 12 for the nodes which showed the ification ode) 22c Offic	as- are the

.

SYNTHESIS AND CHARACTERIZATION OF COPOLYMERS OF NYLON 11 AND NYLON 12

C. Gregory Johnson and Lon J. Mathias"

University of Southern Mississippi Department of Polymer Science Southern Station Box 10076 Hattiesburg, MS 39406-0076

ABSTRACT

.

A series of copolymers was prepared from 11-aminoundecanoic and 12aminododecanoic acids by melt-condensation at 210 °C in sealed tubes under vacuum. Mole percentages of nylon 12 monomer were 0, 15, 35, 50, 65, 85, and 100 % in the feed. The amide group was labelled using ¹⁵N-labelled amino acids available through the Gabriel synthesis (only the 1:1 copolymer was enriched with nitrogen-15). Solid-state ¹³C (at 100.6 MHz) and ¹⁵N (at 20.3 MHz) NMR spectroscopy, differential scanning calorimetry, wide-angle x-ray diffraction, and infrared spectroscopy were used to characterize the copolymers. Solid-state ¹⁵N NMR spectra showed a smooth shift of the main peak position from 84 ppm for α -nylon 11 to 89 ppm for γ -nylon 12 for the asprepared copolymers. Similar behavior was seen for amide V and VI modes which are sensitive the α - and y-crystal forms. Carbon-13 NMR T, measurements showed that the most mobile sample was the 65:35 nylon 11-co-12 polymer. An annealed, solution-cast film of the 50:50 copolymer afforded material with a T_{IN} value of 349 s, similar to annealed nylon 11 and nylon 12 homopolymers. Melting point and heat of fusion depressions were observed for the copolymer series with the 65 mol-% nylon 12 copolymer having the lowest % crystallinity and T_m at 148 °C. Solid-state NMR

93 6 15 095



measurements indicated that the α -crystal form dominates as the stable polymorph up to 65 mol-% nylon 12 in as-polymerized samples, then the γ -phase predominates. The WAXS pattern for the 65 mol-% nylon 12 sample shows a sharp peak at 20 = 21.3, ove:lapping a broad peak centered at 20 = 21.0. This is consistent with the spacing seen for γ -nylon 12. The 1:1 copolymer was shown to be polymorphic, like the homopolymers, with an γ -like phase formed upon solvent casting, and an α -like phase dominating for aspolymerized material and precipitated flakes.

Introduction

Copolymers in general provide opportunities for developing new materials with tailored properties. The synthesis of copolymers requires the determination of reactivity ratios,^{1,2} which in turn allow controlled modification of polymer properties such as solubility of rigid-rod polymers,^{3,4,5} the effect of ionizable groups on ion binding,⁶ the isomorphic behavior of biodegradable copolyesters,^{7,8,9,10} the placement of otherwise intractable functionalities in a tractable backbone,¹¹ and the modification of commercially available polymers to enhance their blend behavior.¹²

Our interest in random copolymers stems from investigations of semi-crystalline polyamides^{13,14,15} using solid-state NMR to determine types of crystal phases present. Many random copolyamides are isomorphic and are able to crystallize despite a mismatch of repeat unit lengths. The crystallinity developed is different than the traditional type. For example, differential scanning calorimetry generally underestimates the amount of crystallinity due to the lack of characterization of the isomorphic crystalline phase that has a heat of fusion different from the parent homopolymers. WAXS and density

measurements give improved measures of overall crystallinity, although they are also limited in sensitivity in terms of evaluating crystallite size and perfection since each method sees the polymer on a different level of organization.

Nylon 11 crystallizes into the α -phase from the melt while nylon 12 adopts the γ phase. In the α -phase, the polymer chains are arranged in an anti-parallel manner with the amide units coplanar with the zig-zag methylene segments, while the γ -phase chains are packed parallel to each other with the amide units twisted from the plane of the aliphatic segments by ca 60°. Our experience with solid-state NMR in characterizing nylon homopolymers suggested that such a molecular level probe of polymer chain packing behavior might provide insight into isomorphic crystallinity in nylon copolymers such as those obtainable from polycondensation of the amino acid monomers for nylons 11 and 12.

EXPERIMENTAL

Solvents were reagent grade and used as received. The amino acids were purchased from Aldrich Chemical Company and recrystallized from boiling, deionized water three times before use. The ¹⁵N-labelled amino acids were prepared in several steps using ¹abelled potassium phthalimide, 11-bromoundecanoic acid,¹⁴ and 12bromododecanoic acid.¹⁵

Mixtures of the amino acids were sealed under vacuum in glass tubes and P_{0r} polymerized at 210 °C for 4 h using a Wood's metal[®] bath as a constant temperature medium. The following mole percentages of amino acids (C₁₁:C₁₂) were used with the sample designation given in parentheses: 100:0 (PA-1), 85:15 (PA-2), 65:35 (PA-3),

and Carry a second on a

D,

Y Codes

Special

50:50 (PA-4), 35:65 (PA-5), 15:85 (PA-6), and 0:100 (PA-7). The colorless polymer plugs were carefully removed from the glass tubes after cooling. Thin films of the aspolymerized polymers removed from the glass tubing were used for FTIR measurements.

A sample of PA-4 was dissolved in a mixture of 2,2,2-trifluoroethanol (TFE) and methylene chloride (3:2 by volume), cast onto glass and the solvent allowed to evaporate (PA-4CF). Another portion of the PA-4 solution was precipitated into rapidly stirring diethyl ether, collected, and dried (PA-4PF). PA-4CF and PA-4PF were annealed under vacuum at 115 °C for 2 days, and designated PA-4CA and PA-4PA, respectively.

Differential scanning calorimetry measurements were made using a Perkin-Elmer DSC-7 equipped with a microcomputer. The instrument was calibrated immediately prior to use with tin and indium standards. Data were collected at 10 °C/min in aluminum pans. FTIR spectra (as-polymerized thin films) were obtained using a Bruker IFS-88 at a resolution of 0.5 cm⁻¹ (64 scans per sample). Wide-angle X-ray diffraction data were obtained using a Siemens XPD-700P polymer diffraction system equipped with a twodimensional, position sensitive, area detector, and background corrected using the GADDS[™] software package.

Solid-state NMR spectra were obtained using a Bruker MSL-200 for ¹⁵N operating at 20.287 MHz and a Bruker MSL-400 for ¹³C operating at 100.614 MHz. The parameters used to collect the spectra are shown in Table 1. Samples were placed in fused zirconia rotors and spun with dry air. Spin-lattice relaxation data were collected using the method developed by Torchia.¹⁶

Parameter	¹³ C	¹⁵ N
¹ H 90°-pulse	ύ. σ μs	5.7 μs
X 90°-pulse	5.3 μs	5.6 μs
contact pulse	1.0 ms	1.0 ms
ringdown delay	14 µs	30 µs
acquisition time	45 ms	68 ms
recycle delay	3 s	5 s
spinning rate	5 kHz	3 kHz
# of scans	400 - 800	20 - 40 k
data size	8 kbytes	8 kbytes
time domain size	4 kbytes	2 kbytes
sweep width	300 ppm	600 ppm
stator diameter	4 mm	7 mm

Table 1. NMR Spectrometer Acquisition Parameters

Results and Discussion

A single report¹⁷ on the synthesis of nylon 11-co-12 appears in the literature in which a 1:1 copolymer was prepared by reaction of 11-aminoundecanoic acid with laurolactam under melt conditions at 250 °C. Solution ¹³C NMR results suggested that no resolution of the carbonyl carbons could be obtained due to the similarity in length of the carbon monomer framework. No other characterization data for this copolymer was given. Our attempts at repeating this procedure mostly gave nylon 11 highly plasticized with the 12-carbon lactam. No copolymer was ever achieved under conditions similar to those listed in the reference.

Other reports^{16,19} of A-B type nylon copolymers describe syntheses, characterization, and physical properties. Almost all of the copolyamides were reported to be essentially random. Melting point depressions and decreases in crystallinity were observed and increases in % elongation were seen with a concomitant decrease in modulus. However, many of the reports did not cover the full range of copolymer compositions.

The copolymers obtained from polymerization of the 11- and 12-carbon amino acids were expected to be random since the starting monomers possess similar structures and end-group reactivities. The monomer melting points are a few degrees apart and homopolymers are readily obtained from each under conditions similar to those used for copolymer synthesis. The polymer plugs obtained were very tough and required careful cutting with a razor blade. While the two homopolymers were not readily soluble in the TFE-CH₂Cl₂ mixture, all of the copolymers were. The solution ¹³C NMR spectrum (not shown here) of the 1:1 copolymer showed a single carbonyl peak at 176.9 ppm. This is in agreement with the single peak observed by Kricheidorf for his polymer, although he used fluorosulfonic acid as solvent.¹⁷ However, our solution NMR experiments on the sample obtained from 11-amincundecanoic acid and laurolactam showed peaks for both lactam and homopolymer nyion 11. The DSC results showed a melting endotherm for lactam and a slightly depressed T_m for nylon 11, but no obvious T_m for copolymer. Based on these results, we chose to use the commercially available amino acids for "opolymer synthesis rather than attempting further reactions with the lactam.

Thermal Analysis

The thermal data for the copolymer series is shown in Table 2, while the T_m and % crystallinities (based on ΔH data) are plotted in Figure 1 for homopolymers and samples PA-1 through PA-7. It is clear that the melting points decrease with increasing comonomer content on moving away from the homopolymers with a minimum near 65 mol-% nylon 12 units. This is also where the estimated percent crystallinity reaches its minimum for the as-prepared samples. The percent crystallinity was calculated after the manner of Garner and Fasulo²⁰ using the ΔH_r of the pure homopolymers.

SAMPLE	∆H (J/g)	onset T _m (°C)	T ₀ (°C)	% cryst.
PA-1	54	183	45	24
PA-2	39	175	43	22
PA-3	38	160	37	17
PA-4	34	152	43	17
PA-5	31	148	42	14
PA-6	46	163	41	20
PA-7	65	171	41	30
PA-4CF	65	146	42	29
PA-4PF	50	148	42	22
PA-4CA	75	146	ò	33
PA-4PA	55	151	b	24

 Table 2.
 Nylon 11-co-12 thermal data^a for all as-obtained and several treated samples

* - data averaged over three samples for first runs; % crystallinity calculated according to the method used for hylon 6-co-12²⁰

^b - no glass transition temperature observed for these samples on the first run

We speculate that, as the amount of comonomer increases, the less perfect and/or the smaller the crystallites become, causing a depression in the melting points. No multiple melting peaks were observed by DSC, suggesting that separate domains of homopolymer segments did not form. However, the thermograms of the homopolymers and copolymers showed a melting endotherm superimposed on a crystallization exotherm, suggesting the melting of the less-perfect crystallites followed by simultaneous formation and melting of more perfect crystalline domains.²¹ On the second and third DSC runs, no crystallization exotherms were observed as has been reported for nylons 6-co-8 and 6-co-12 at compositions up to 30 mol-% nylon 8 and nylon 12, respectively,^{19c} and for 1:1 nylons 6-co-11, 6-co-12, 7-co-11, and 7-co-12.²² Interestingly, the second and third run T_m's were only slightly reduced from the first run, although the Δ H and % crystallinity were reduced. It is clear that regardless of the <u>amount</u> of crystallinity inferred by the DSC data, the nature of the chain conformations and the type of crystalline packing that exists cannot be determined by thermal analysis.

Solid-State NMR

The solid-state ¹³C CP/MAS and CPT1 NMR spectra of the copolymers (aliphatic regions only) are shown in Figure 2. The CP/MAS spectra contain peaks for both amorphous and crystalline domains, while the CPT1 spectra show only crystalline domain peaks. Examination of the spectra suggests that there is a smooth transition in peak positions going from PA-1, 100 mol-% nylon 11, to PA-7, 100 mol-% nylon 12. The chemical shift data from the CPT1 spectra are contained in Table 3. Nylon 11 crystallizes into the α -phase from the melt and nylon 12 into the y-phase. Each has its own particular

8

;

İ

chain conformations in extended chain crystallites,²³ and solid-state NMR is sensitive to these differences.

and a second						
SAMPLE	со	C _N	C _a	C _{AT}	C _p	NHiª
PA-1	173.7	42.5	35.8	33.4	27.5	85.2
PA-2	173.5	42.3	35.8	33.4	27.5	85.8
PA-3	173.6	41.5	35.8	33.3	27.4	86.3
PA-4	173.6	41.0	36.2	33.2	27.4	86.9
PA-5	173.4	40.2	35.9	33.4	31.0	85.9
PA-6	173.2	39.5	35.8	33.5	30 2	88.1
PA-7	173.3	39.6	35.9	33.5	30.2	88.9
PA-4CF	173.1	39.7	36.8	33.6	30.3	88.9
PA-4PF	173.5	40.1	35.9	33.3	28.0	87.0
PA-4CA	173.2	39.6	36.7	23.5	30.6	88.9
PA-4PA	173.5	40.8	36.4	33.3	27.7	86.9
PA-4PF	173.9	40.5	36.9	30.9	d	87.1
PA-4 (sol)°	176.9	40.6	37.3	30.0	27.4	•

 Table 3.
 Nylon 11-co-12 polymer chemical shift values from CPT1 spectra

* - data taken from CP/MAS NMR experiments for both natural-abundance and isotopically enriched samples

^b - data taken from HP/MAS experiments for both ¹³C and ¹⁵N

e - data collected for as-polymerized PA-4 in a mixture of TFE and CH2Cl2 at 75.465 MHz

^d - peak not observed

- data not collected

As we have described for nylon 7,²⁴ the carbon beta to the carbonyl (C_f) appears at 28 ppm in α -crystallites due to shielding effects of the oxygen atom in the carbonyl group. Others have seen similar behavior for nylon 6 polymorphs and have reported²⁵

that the C_p peak in γ -crystallites appears near 30 ppm. Similarly, the carbon alpha to the nitrogen atom (C_N) appears near 43 ppm in α -crystals, while it is near 39 ppm in γ -crystals.

For the CPT1 spectra, the C_p peak at 27.5 ppm for PA-1 becomes less pronounced as the amount of comonomer is increased, appearing near 30.2 ppm for PA-5 through PA-7. Similarly, C_N moves from 42.5 ppm for PA-1 to 39.6 ppm for PA-7, consistent with a change from the α -phase to the γ -phase. This can be rationalized in terms of diminishing amounts of one type of crystalline phase in favor of the other. That is, as the amount of 12-aminododecanoic acid is increased in the monomer feed, the more the crystallites look like nylon 12 γ -phase crystallites. This can be seen more readily by examining the CPT1 chemical shifts of C_N which are plotted in Figure 3 against mol-% 12-aminododecanoic acid. The plot is nearly linear between the α -phase peak at 42.5 ppm and γ -phase peak at 39.5 ppm. Interestingly, the chemical shift of the C_{AT} peak at about 33.4 ppm remains fairly constant over the composition range, even though the two homopolymers contain different numbers of molecules per unit cell and crystallize into different unit cells.²³

The solid-state ¹⁵N CP/MAS NMR spectra are contained in Figure 4 and the chemical shift values are plotted in Figure 3. The spectra consist of overlapping peaks for the amorphous and crystalline domains. The α -phase peak appears at 84 ppm and that of the γ -phase at 89 ppm, with the broad amorphous peak centered rear 86 to 87 ppm. It is clear the spectrum of **PA-7** (pure nylon 12) consists of a sharp peak near 89 ppm overlapping a broad resonance at 86. The low level of crystallinity developed in **PA**-

1 (approximately 24 % by DSC), however, does not allow as-ready observation of crystalline and amorphous peaks. We know from previous work^{13,14,15} with isotopically enriched polymer samples (which allow phase-selective observation of the amorphous and crystalline contributions) that low levels of crystallinity can make clear separation of the peaks difficult. None-the-less, even such apparently broad peaks can indicate the dominate crystal phase by main peak position and/or overall shape. There is a clear, continuous change in ¹⁵N peak position from α -form for nylon 11 to γ -form for nylon 12.

19

Spin-Lattice Relaxation

The ¹³C T₁ values for the copolymer series are contained in Table 4. The magnetization decay of the carbons (and the nitrogen) could be fit to multiple exponentials consistent with the behavior of semi-crystalline polymers with well-separated domains of differing mobilities (T₁ values differing by at least an order of magnitude). This is very different from glassy polymers that give multiple relaxation times of the same order of magnitude.²⁸ We believe the biezponetial behavior corresponds to amorphous phases with short relaxation times and ordered phases with longer times.

The T₁ behavior at first glance does not appear to follow a trend with respect to copolymer content. We propose that, at low comonomer contents, the small number of defects (mismatched repeat unit lengths) along the polymer backbones allow crystallization to occur more easily than in the homopolymer containing no defects as reflected by the increased T₁ values for the 15 mol-% copolymers (PA-2 and PA-6). As more defects are incorporated in the polymer backbone, however, the ability to form highly regular domains is diminished, decreasing the T₁ values below those of the

homopolymers. The all-trans carbons (C_{AT}) have the longest T₁ values of all the carbons except for the 50:50 copolymer. This suggests that the carbons are able to pack in ordered zig-zag arrays with little perturbation. The chemical shift for C_{AT} peak changes very little throughout the composition range indicating that gauche defects are not disrupting the planar zig-zag regions. Most likely the defects are associated with the methylenes attached directly to the amide units, allowing the middle of the hydrocarbon chains to assume the preferred all-trans conformation. The low T₁ values for C_a and C_p support this as do their chemical shifts which change with composition suggesting that conformational changes take place at these carbons.

SAMPLE	C _N	C _a	C _{at}	C _β			
PA-1	0.7	0.7	0.8	0.4			
	8.6	6.5	10.2	6.0			
PA-2	0.8	0.6	0.9	0.4			
	6.5	9.3	12.3	7.4			
PA-3	0.2	0.3	0.8	0.3			
	3.0	2.5	5.5	2.8			
PA-4	0.6	0.5	0.6	0.3			
	5.8	2.2	3.2	3.0			
PA-5	0.6	0.4	0.8	0.3			
	5.8	2.4	5.3	2.8			
PA-6	0.7	0.7	1.3	0.4			
	9.1	12.9	14.1	5.1			
PA-7	0.5	0.7	1.0	0.3			
	4.6	8.2	8.9	5.4			

Table 4. Nvion 11-co-12 carbon-13 spin-lattice relaxation values (s)

FTIR Analysis

Table 5²⁷ lists the FTIR bands between 1500 and 400 cm⁻¹ while the spectra in this region are shown in Figure 5. Due to the thickness of the as-polymerized films, it was not possible to obtain accurate peak positions above 1500 cm⁻¹. Several prominent features can be seen that are common to all the spectra such as methylene scissoring (ca 1400) and twisting (ca 1300), the amide III (ca 1250), V (ca 690), and VI (ca 580) modes, and fundamental CH₂ rocking (ca 720).

PA-1 has three distinct bands in the scissoring region at 1468, 1456, and 1437 cm¹ which persist in the copolymers up to **PA-6** for which the lower frequency band becomes a shoulder. Copolymers more like α -nylon 11 have three bands in this region and the copolymers more like γ -nylon 12 have two bands, similar to behavior seen for nylon 12 samples with different amounts of α - and γ -phases.²⁷⁴ Three bands also appear in the twisting region near 1373, 1355, and 1339 cm⁻¹. However, the latter two bands are hardly discernable in **PA-5** and all of the bands shift to lower frequencies in **PA-6** and **PA-7**. The region of the amide III mode coupled to CH₂ wagging contains multiple bands that vary with composition. Samples **PA-1** through **PA-4** have bands near 1298 and 1278 cm⁻¹ that shift to 1289 and 1271 cm⁻¹ in the remaining copolymers. The amide III band (probably the band near 1270) is the most intense band in this region and is least sharp for the copolymer with the overall lowest carbon T₁ values, **PA-5**. The copolymers on either end of the composition range have low intensity but observable shoulders at slightly higher frequencies of the band near 1245 cm⁻¹, which is invariant over the composition range. The C-C skeletal bands (ca 1100 cm⁻¹) do not change from **PA-1** to **PA-7**.

Assignment	PA-7	PA-A	PA-5	PA-4	PA-3	PA-2	PA-1
	1468	1466	1467	1467	1466	1467	1468
	(2.02)	(3.16)	(3.48)	(1.11)	(2.11)	(1.54)	(3.31)
	1457	1457	1456	1457	1457	1456	1457
CH,	(1.57)	(2.69)	(3.07)	(0.76)	(1.90)	(1.20)	(2.24)
scissoning	1437	1437	1436	1437	1436	1437	1437
	(1.49)	(2.61)	(2.96)	(0.70)	(1.82)	(1.12)	(2.02)
		1419	1421	1419	1420	1419	1419
		(1.86)	(2.18)	(0.53)	(1.58)	(1.04)	(1.87)
			1372	1371	1371	1373	1373
			(2.38)	(0.58)	(1.65)	(1.05)	(1.78)
	1369	1369					
	(1.26)	(2.15)					
				1353	1355	1356	1354
Сн,				(0.51)	(1.54)	(1.00)	(1.65)
twisting	1342	1344					
	(1.12)	(1.83)					
			1338	1338	1338	1339	1340
			(1.89)	(0.46)	(1.44)	(0.96)	(1.55)
	1308	1307	1305	1309	1310	1309	1310
	(1.07)	(1.72)	(1.68)	(0.44)	(1.42)	(0.93)	(1.46)
				1298	1298	1298	1298
				(0.46)	(1.44)	(0.97)	(1.55)
	1266	1289	1287				
	(1.17)	(1.91)	(2.05)				
				1277	1278	1278	1280
				(0.56)	(1.64)	(1.08)	(1.85)
amide III	1270	1271	1273				
CH, wassing	(1.25)	(2.07)	(2.24)				
					1262	1262	1262
					(1.52)	(0.99)	(1.62)
	1244	1245	1245	1246	1247	1244	1244
2	(1.16)	(1.87)	(2.01)	(0.50)	(1.53)	(1.01)	(1.70)
	1222	1223	1225	1225	1225	1225	1224
	(1.07)	(1.68)	(1.82)	(0.46)	(1.46)	(1.02)	(1.74)

 Table 5.
 Nylon 11-cc-12 FTIR bands (with relative intensities) observed for the region between 1500 and 400 cm⁻¹

				_	وجنبيهم ومعرف المتعادين		والمستجربة والمستركب فتعرف ومرور المتحفظ ومرجو ويعتمها والمحرورة فتترج
11 99 (1.26)	11 99 (0.85)	11 95 (1.21)	1200 (0.33)				
1192 (1.13)	1193 (0.84)	11 93 (1.23)	1194 (0.34)	1194 (1.46)	1193 (1.40)	1193 (0.81)	
1161 (1.18)	1161 (0.83)	1160 (1.20)	11 60 (0.35)	1:61 (1.58)	1161 (1.63)	1161 (1.05)	splitting of arnide III and
1125 (1.13)	1124	1123 (1.10)	1123 (0,29)	1122 (1.31)	1123 (1.27)	1122 (0.96)	motions
	1107	1108 (0.84)	1109	11 09 (1.03)	1110	1110	
1083	1081	1081	1081	1084	((0.01)	
1059	1059	1061	10 63	1085	1085	1064	
1025	1025	1027	1028	1028	1026	1028	
(0.68)	(0.71)	(0.82)	(0.17)	(0.92)	(0.95)	(0.79)	
					1011 (0.89)	1011 (0.76)	
997 (0.88)	997 (0.72)	997 (0.72)	994 (0.17)				CONH
				960 (0.90)	962 (0.90)	962 (0.76)	vibrations
974 (0.86)		972 (0.82)	973 (0.17)				
967 (0.85)	967 (0.71)						
937 (0.96)	938 (0.74)	940 (0.85)	942 (0.19)	944 (0.99)	946 (1.02)	946 (0.81)	
					905 (0.82)	905 (0.70)	
722 (1.90)	722 (1.10)	721 (1.62)	722 (0.60)	722 (2.55)	723 (2.28)	723 (1.31)	fundamental CH ₂ rocking
687 (1.44)	689 (0.93)	691 (1.24)	69 2 (0.37)	sh			
626 (1.02)	625 (0.78)	626 (0.98)	624 (0.25)	627 (1.21)	628 (1.19)	626 (0.86)	amide V
583 (1.16)	565 (0.82)	58 8 (1.01)	592 (0.26)	583 (1.19)	593 (1.09)	59 2 (0.84)	
545 (0.95)	542 (0.75)	540 (0.83)	540 (0.20)	538 (1.02)	538 (1.03)	538 (0.80)	emide VI

The CONH skeletal motion bands between 1084 and 905 cm⁻¹ are well-defined in all of the copolymers except PA-5. The pattern of bands changes at this composition point also. The fundamental rocking mode for methylenes appears constant over the copolymer series. The bands for amide V and VI show changes which correspond to the changes seen in the NMR spectra. The amide V peak, which consists of two bands near 690 and 628 cm⁻¹, shifts from 687 to a weak shoulder in PA-1 to PA-5, respectively, and is absent in the remaining two spectra of copolymers high in nylon 12 content. The lower frequency band remains near 628 but decreases in relative intensity with increasing nylon 12 content. Two bands associated with the amide VI mode shift over the copolymer composition range. For PA-1, a peak appears at 583 shifting to 592 for PA-7 and decreasing in relative intensity, which suggests that there is a shift from the α -phase to the γ -phase. The second band at 545 cm⁻¹ for PA-1 moves to lower frequencies on increasing the rylon 12 content, ending at 538 cm⁻¹ for PA-7.

X-Ray Analysis

The wide-angle X-ray diffraction patterns for the copolymer series confirm the complimentary nature of structural analysis with techniques that observe different levels of organization. The NMR and FTIR data provide molecular level information which, for crystalline domains, indicates the conformation and packing of repeat unit segments. X-ray, on the other hand, sees arrays of molecular segments that correspond to higher levels of organization built up from the molecular to the microscopic level. It is often the case that contributions from one of the domains present may make observation of the others difficult. For example, the broad amorphous peak in the ¹⁵N NMR spectra of PA-1

(Figure 4) masks the α -crystal peak which is clearly seen as a pair of peaks at 20 values of 20.2 and 22.8 in the X-ray diffraction pattern (Figure 6). These are typical values for α -crystallites.²⁸

The strong NMR peaks for the y-form of nylon 12 (PA-7, Figures 2 and 4) are consistent with the strong, relatively narrow X-ray peak seen for this sample at a value $(2\theta = 21.3)$ characteristic for y-crystallites. The X-ray patterns for the mostly-y copolymers (by NMR and IR), PA-6 and PA-5, are virtually identical to that of PA-7. However, the pattern for PA-4 is almost the same in peak width and position (28 = 21.4), yet NMR and IR indicate weak α or some intermediate form with a mixture of weak α and γ peaks. Even more surprising are the broad X-ray peak for PA-3 and the intermediate pair of peaks (20 = 20.6 and 22.1) for PA-2. The NMR and IR data are consistent with strong a-content for both. We believe this is indicative of less-ordered crystallites for the copolymers as the compositions move away from the two extremes, a change which is more easily seen for the a-form samples (because it normally gives two, widely separated peaks in the X-ray pattern) than for the γ samples which display a single X-ray peak which overlays the broad peak of the pseudo-hexagonal or mesomorphic peak that occurs in many guenched or disordered nylon samples.²⁹ The combination of spectral and Xray data give a good qualitative picture of the molecular and microscopic order in these as-polymerized copolymer samples. The additional question of what effect sample treatment has on the type and degree of ordered phase present is also well determined by this combination of methods as illustrated for the ¹⁵N-labelled 1:1 copolymer (PA-4) below.

¹⁵N-Enriched 1:1 Copolymer: Sample Treatment Effects

The polymorphism of homopolyamides has been repeatedly demonstrated but the question remains of polymorphic crystallinity in random copolyamides. Sample history and treatment affect the type and amount of crystallinity, even to the point of almost completely generating the thermodynamically less-stable of the crystal forms available to a given polyamide.^{14,15} We subjected an isotopically enriched 50 mol-% nylon 11 sample, PA-4, to different chemical and thermal treatments to evaluate their affect on crystallinity. The copolymer sample was prepared from a 1:1 mixture of 50 mol-% isotopically-enriched amino acids to give a 50 mol-% nylon 11 copolymer (PA-4) with 50 % total ¹⁵N enrichment. The ¹⁵N-labelled samples were given no treatment (as-polymerized, PA-4); dissolved in 2,2,2-trifluoroethanol and methylene chloride (3:2 by volume) and cast on a glass plate (PA-4CF); precipitated from the mixture into diethyl ether, collected and dried (PA-4PF); and the latter two annealed separately under vacuum in sealed glass tubes at 115 $^{\circ}$ C for 12 h (PA-4CA and PA-4PA, respectively).

The ¹³C and ¹⁵N solid-state NMR spectra are shown in Figures 7 and 8, respectively, while the X-ray diffraction patterns of the five samples are given in Figure 9. The chemical shift values for both ¹³C and ¹⁵N spectra are included in Table 3, while the thermal data are contained in Table 2. In Figure 7, the samples cast onto glass and simply dried (PA-4CF) or annealed at 115 °C (PA-4CA) show peaks characteristic of the γ -crystal form. In fact, the ¹⁵N NMR peaks at 89 ppm (Figure 8) confirm this as do the sharp X-ray peaks at 29 = 21.3. Solvent casting onto glass plates is clearly an effective method for inducing highly ordered γ -crystals into copolymers of nylons 11 and 12.

Also interesting is the behavior displayed by the other three samples (PA-4, PA-4PF and PA-4PA) whose spectra and diffraction patterns are given in the upper, middle and bottom traces of Figures 7, 8 and 9. The ¹³C peaks appear to indicate α-form crystallites in all three samples and the chemical shifts listed in Table 3 support this. In fact, neither the ¹⁵N CPT1 traces nor the X-ray diffraction patterns confirm this. Instead, both suggest disordered structures based on broad peaks centered at the amorphous positions, with the ¹⁵N NMR peaks showing virtually no shoulder at 84 ppm as seen for the PA-1 through PA-3 spectra in Figure 4. However, it should be remembered that the CPT1 method (right-hand set of peaks in Figures 7 and 8) selectively observes crystalline, or at least more rigid, domains. The samples may contain chains packed in a pseudohexagonal crystalline array which gives a ¹⁵N peak position similar to that of the amorphous phase as well as the mesomorphic form and the high-temperature δ-crystals of nylon 11.¹⁴

Let us now consider the effects of different treatments on the spin-lattice relaxation values of PA-4 samples (see Table 6). The precipitated sample has the overall lowest values with annealing having very little affect on the carbon T_1 values. However, the T_{1N} value nearly doubles and a component with a very short T_1 appears on annealing. The increase in the nitrogen T_1 values with little change in the carbon values on annealing suggests that for this sample, ordering occurs near the amide units with little change in the hydrocarbon segments. The ¹⁵N CPT1 peak shape also narrows for this sample on annealing (from 5.6 ppm wide at half height to 4.8 ppm), and the main peak shifts upfield from 87.2 to 86.4 ppm.

The cast sample (PA-4CF) has the longest carbon T_1 values of those presented here, indicating that solvent casting forms a highly ordered phase that is thermally stable. Annealing increases this order, as reflected by the T_1 values for the carbons immediately adjacent to the amide group and for the amide nitrogen itself. Again, the amide order dominates and the hydrocarbon segments are less ordered.

SAMPLE	C _N	C _a	C _{AT}	C _β	NHª
PA-4CF	1.7 v.3	0.3 2.5	0.4 20.3	0.4 4.1	0.1 6.8 112.9
PA-4PF	0.5 2.5	0.3 1.5	0.7 3.8	0.3 1.6	3.0 22.6
PA-4CA	0.8 12.5	0.9 15.9	1.2 13.3	0.3 4.2	1.6 39.4 349.4
PA-4PA	0.3 1.4	0.3 2.4	0.8 4.3	0.3 1.7	0.3 5.9 42.8

 Table 6.
 PA-4 carbon-12 and nitrogen-15 spin-lattice relaxation values (s)

^a - compare to T_{1N} values for nylon 11:¹⁴ quenched sample; 2.3 s / 13.4 s, and annealed sample; 4.9 s / 68.1 s, and for nylon 12:¹⁵ quenched sample; 3.0 s / 34.0 s, and annealed sample; 20.0 s / 314.0 s.

The high degree of order for the cast film sample (especially after annealing), indicated by the sharpness of the γ -form ¹⁵N NMR peak at 89.1 and the very long T_{1N} values, is consistent with the DSC Δ H value measured: it was the highest of any of the samples examined here despite the fact that the T_m did not change. Two observations are important to make here. First, despite the fact that the 1:1 copolymer should be

ţ

highly disordered due to random monomer sequences, sample treatment can induce a very high degree of order. Second, once an ordered phase is formed (at least for nylons 11, 12 and their copolymers), annealing does <u>not</u> cause transformation to other, supposedly more stable, phases. In fact, annealing actually <u>increases</u> the order in the existing ordered domains as indicated by narrowing of the ¹⁵N NMR peak and the X-ray diffraction pattern, and a doubling of the T_{1N} value.

Conclusions

The nylon 11-co-12 series prepared here shows the expected melting point depression (for as-polymerized samples) with the lowest T_m and percent crystallinity belonging to PA-5, the 65 mol-% nylon 12 copolymer. This is also the copolymer with the overall lowest carbon T, values. From solid-state NMR ¹³C and ¹⁵N line shapes and positions, the crystalline phase that dominates up to 65 mol-% nylon 12 is the α -phase. The γ -phase is present in copolymers with higher nylon 12 mol-%. Several bands in the FTIR spectra reflect a similar trend. The pattern of bands in the amide III region changes noticeably at PA-5 as do the CONH skeletal motion bands.

The ¹⁵N-labelled 1:1 copolymer (PA-4) was shown to be polymorphic in nature. As-polymerized and precipitated flakes possessed an ordered phase with α -like characteristics in the NMR and IR spectra but which appears to be pseudohexagonal by X-ray. A strong γ -like phase was observed in the solvent cast sample. Neither phase for PA-4 could be transformed into the other by annealing, which actually increased the degree of existing order.

Overall, it is clear that sample history and composition are both important in determining the degree and type of crystallinity and/or order in nylon copolymers. Vital to observation and understanding of molecular and microscopic behavior is the use of a combination of analytical methods which "see" different functional groups (amides versus methylene chains), backbone segments and conformations, and arrays of segments and polymer chains in crystallographic domains.

References

- 1. Muthiah, J.; Mathias, L. J. J. Polym. Sci., Polym. Chem. Ed. 1991, 29, 29.
- 2. Nair, C. P. R. Macromolecules 1993, 26, 47.
- 3. Arai, M.; Cassidy, P. E.; Farley, J. M. Macromolecules 1989, 22, 989.
- 4. Evers, R. C.; Dnag, T. D.; Moore, R. D. J. Polym. Sci., Polym. Chem. Ed. 1993, 29, 121.
- 5. Gaudiana, R. A.; Sinta, R. F. J. Polym. Sci., Polym. Chem. Ed. 1991, 29, 45.
- 6. McCormick, C. L.; Elliot, D. L. Macromolecules 1986, 19, 542.
- 7. Feng, X. D.; Voong, S. T.; Song, C. X.; Chen, W. Y. J. Polym. Sci., Polym. Lett. Ed. 1983, 21, 593.
- 8. Kricheldorf, H. R.; Mang, T.; Jonté, J. M. Macromolecules 1984, 17, 2173.
- 9. Mitomo, H.; Barham, P. J.; Keller, A. Polym. J. 1987, 19, 1241.
- 10. Kamiya, N.; Sakurai, M.; Inoue, Y.; Chûjô, R. Macromolecules 24, 3888 (1991).
- 11. Yu, L; Chen, M.; Dalton, L. R. J. Polym. Sci., Polym. Chem. Ed. 1991, 29, 127.
- 12. Buchanan, C. M.; Gedon, S. C.; White, A. W.; Wood, M. D. *Macromolecules* 1992, *25*, 7373.
- 1C. Powell, D. G.; Mathias, L. J. J. Am. Chem. Soc. 1990, 112, 669.

- 14. Mathias, L. J.; Powell, D. G.; Autran, J.-P.; Porter, R. S. *Macromolecules* 1990, *23*, 963.
- 15. Mathias, L. J.; Johnson, C. G. Macromolecules 1991, 24, 6114.
- 16. D. A. Torchia, J. Magn. Reson., 30, 613 (1978).
- 17. Kricheldorf, H. S.; Hull, W. E. J. Polym. Sci., Polym. Chem. Ed. 1978, 16, 2253.
- (a) Kobayyashi, F.; Matsuya, K. J. Polym. Sci., Part A 1963, 1, 111. (b) Hybart, F. J.; Pepper, B. J. Appl. Polym. Sci. 1969, 13, 2643. (c) Kubota, H.; Nowell, J. B. J. Appl. Polym. Sci. 1975, 19, 1521. (d) Goodman, I.; Kehayoglou, A. H. E. Polym. J. 1983, 19, 321. (e) Kehayoglou, A. H.; Arvanitoyannis, I. Eur. Polym. J. 1990, 26, 261. (f) Gonsalves, K. E.; Chen, X. Polym. Commun. 1990, 31, 312. (g) Coutin, B.; Sekiguchi, H.; Prieto, A.; Munoz-Guerra, S. Makromol. Chem. 1991, 192, 21.
- 19. (a) Kricheldorf, H. R.; Leppert, E.; Schilling, G. Makromol. Chem. 1975, 176, 81.
 (b) Kricheldorf, H. R.; Schilling, G. Makromol. Chem. 1976, 177, 607. (c) Kricheldorf, H. R.; Hull, W. E. J. Macromol. Sci.-Chem. 1977, A11, 2281. (d) Kricheldorf, H. R.; Coutin, B.; Sekiguchi, H. J. Polym. Sci., Polym. Chem. Ed. 1982, 20, 2353. (e) Kricheldorf, H. R.; Joshi, S. V.; Hull, W. E. J. Polym. Sci., Polym. Chem. Ed. 1982, 20, 2791.
- 20. Garner, D. P.; Fasulo, P. D. J. Appl. Polym. Sci. 1988, 35, 495.
- 21. Xenopoulos, A.; Wunderlich, B. J. Polym. Sci., Polym. Phys. Ed. 1990, 28, 2271.
- 22. Johnson, C. G.; Mathias, L. J., manuscript submitted for publication in *Polymer Comm*.
- 23. Puffr, R.; Kubának, V. Lactam-Based Polyamides; CRC Press: Boca Raton, FA, Vol. 1, 1992.
- 24. Johnson, C. G.; Mathias, L. J. Polymer, in press.
- 25. Hatfield, G. R.; Glans, J. H.; Hammond, W. B. Macromolecules 1990, 23, 1654.
- 26. Schaffer, J.; Sefcik, M. D.; Stejskal, E. O.; McKay, R. A.; Dixon, W. T.; Cais, R. E. Macromolecules 1984, 17, 1107.
- 27. (a) Ishikawa, T.; Nagai, S.; Kasai, N. J. Polym. Sci., Polym. Phys. Ed. 1980, 18, 291. (b) Matsubara, I.; Otoh, Y.; Shinomiya, M. Polym. Letts. 1966, 4, 47.
- 28. Hiramatsu, N.; Haraguchi, K.; Hirakawa, S. Jpn. J. Appl. Phys. 1983, 22, 335.

29. Kim, K. G.; Newman, B. A.; Scheinbeim, J. I. J. Polym. Sci., Polym. Phys. Ed. 1985, 23, 2477.

List of Figures

- Figure 1. Plot of T_m onset (dotted line, left axis) and calculated % crystallinity (solid line, right axis) versus mol-% nylon 12 monomer in the copolymers.
- Figure 2. Aliphatic regions of the solid-state ¹³C NMR spectra for the copolymers; CP/MAS traces on the left, CPT1 traces on the right.
- Figure 3. Plot of ¹⁵N CP/MAS chemical shifts (solid line, left axis) and C_N ¹³C CPT1 chemical shifts (dotted line, right axis) versus mol-% nylon 12 monomer.
- Figure 4. ¹⁵N CP/MAS spectra of nylon 11-co-12 as-polymerized samples PA-1 through PA-7.
- Figure 5. FTIR spectra (1500-400 cm⁻¹ region) for the as-polymerized copolymers.
- Figure 6. Wide-angle X-ray diffraction patterns for the as-polymerized copolymers.
- Figure 7. ¹³C solid-state NMR spectra of 1:1 copolymer with different sample histories; CP/MAS spectra on the left and CPT1 on the right.
- Figure 8. ¹⁵N solid-state NMR spectra of 1:1 copolymer with different sample histories; CP/MAS spectra on the left and CPT1 on the right.
- Figure 9. X-ray diffraction patterns for the five PA-4 samples.





Johnson, Fig 2







Tibon - - -



Talian Rr. 1



1- A. 7



r Ø

1

.



-1 - 9