

AD-A275 178



REPORT DOCUMENTATION PAGE			Form Approved OMB No. 0704-0188
<small>Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.</small>			
1. AGENCY USE ONLY (Leave blank)	2. REPORT DATE 14 OCT 93	3. REPORT TYPE AND DATES COVERED Technical Report, 01 JUN 93 - 31 AUG 93	
4. TITLE AND SUBTITLE Crystallization of silver chromate from ethanol via salt metathesis reactions of solubilized precursors		5. FUNDING NUMBERS	
6. AUTHOR(S) Kenneth M. Doxsee		8. PERFORMING ORGANIZATION REPORT NUMBER Technical Report No. 7	
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) Department of Chemistry University of Oregon Eugene, OR 97403		10. SPONSORING/MONITORING AGENCY REPORT NUMBER	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) Dr. Harold E. Guard Office of Naval Research 800 North Quincy Street Arlington, VA 22217-5000		10. SPONSORING/MONITORING AGENCY REPORT NUMBER	
11. SUPPLEMENTARY NOTES			
12a. DISTRIBUTION/AVAILABILITY STATEMENT This document has been approved for public release and sale; its distribution is unlimited.		12b. DISTRIBUTION CODE	
13. ABSTRACT (Maximum 200 words) Admixture of aqueous solutions of silver nitrate and potassium chromate results in immediate precipitation of silver chromate as a red-brown microcrystalline powder, while addition of aqueous silver nitrate solution to a solution of potassium chromate/18-crown-6 in ethanol gives a bright-red precipitate. X-ray powder diffraction shows both materials to be orthorhombic silver chromate. The ethanol-derived sample displays broader diffraction peaks, suggesting smaller crystallite size. Scanning electron microscopy confirms this. The ethanol-derived sample appears amorphous, while the aqueous sample displays well-faceted crystallites approximately 0.5 - 1 micron in size.			
14. SUBJECT TERMS Nonaqueous crystallization; complexation-mediated crystallization		15. NUMBER OF PAGES 2	
17. SECURITY CLASSIFICATION OF REPORT Unclassified		16. PRICE CODE N/A	
18. SECURITY CLASSIFICATION OF THIS PAGE Unclassified	19. SECURITY CLASSIFICATION OF ABSTRACT Unclassified	20. LIMITATION OF ABSTRACT UL	

OFFICE OF NAVAL RESEARCH

Grant N00014-91-J-1731

R&T Code 413p010---03

Technical Report No. 7

Crystallization of silver chromate from ethanol via salt metathesis reactions of solubilized precursors

by

Kenneth M. Doxsee

Interim Technical Report

Department of Chemistry
University of Oregon
Eugene, OR 97403

October 14, 1993

Reproduction in whole or in part is permitted for
any purpose of the United States Government

This document has been approved for public release
and sale; its distribution is unlimited.

Accession For	
NTIS CRA&I	<input checked="" type="checkbox"/>
DTIC TAB	<input checked="" type="checkbox"/>
Unannounced	<input checked="" type="checkbox"/>
Justification	
By	
Distribution /	
Availability Codes	
Dist	Avail and/or Special
A-1	

DTIC QUALITY INSPECTED 2

94 2 01 07 8

3p8

94-03269



Experimental

Two samples of silver chromate (Ag_2CrO_4) were prepared by admixture of solutions of AgNO_3 and K_2CrO_4 :

Sample A: AgNO_3 solution in water added dropwise to solution of K_2CrO_4 in water, resulting in immediate precipitation of a red-brown powder. This was isolated by filtration and washed with water, then ethanol, then diethyl ether, affording the Ag_2CrO_4 as a brown powder in high yield.

Sample B: AgNO_3 dissolved in 0.5 mL water, then diluted with 4 mL ethanol and added dropwise to a solution of K_2CrO_4 in ethanol (6 mL) containing 3 equivalents of 18-crown-6, resulting in immediate precipitation of a red powder. This was isolated by filtration and washed with ethanol, then water, then ethanol, then diethyl ether, affording the Ag_2CrO_4 as a red powder in high yield.. (Note that K_2CrO_4 appears completely insoluble in ethanol in the absence of 18-crown-6.)

Each sample was examined by x-ray powder diffraction and shown to be the (known) orthorhombic phase of Ag_2CrO_4 . Each appeared crystalline; however, sample A (prepared from water) appeared to be composed of significantly larger crystallites, as evidenced by sharper lines in the powder diffraction pattern.

Scanning electron microscopy confirmed this observation: Sample A was comprised entirely of apparently well-faceted crystallites approximately 0.5 - 1 micron in size, while sample B displayed no clearly identifiable crystallites, being composed instead of aggregates of visually amorphous (but, recall, still crystalline as shown by x-ray powder diffraction) material.

Discussion

Silver chromate serves an important role as a cathode material for nonaqueous-electrolyte batteries. It has also appeared in the patent literature as an alkene polymerization catalyst, as a potential optical recording material, and as a component in anti-fouling agents. It is generally prepared by a simple metathesis reaction between, e.g., potassium chromate and silver nitrate. Such metathesis reactions are universally carried out in aqueous solution, as the precursors display negligible solubility in nonaqueous solvents. We have found that use of 18-crown-6 as a complexing agent allows preparation of solutions of potassium chromate in ethanol. Dropwise addition of ethanolic silver nitrate (containing a few percent water in order to solubilize the silver salt) to such an ethanolic solution of solubilized potassium chromate results in immediate precipitation of silver chromate which, as demonstrated by visual inspection (color of the bulk sample), X-ray powder diffraction, and electron microscopy, is of significantly smaller crystallite size than silver chromate prepared from aqueous solution. The ability to effect such a significant alteration in crystallite size simply through alteration of crystallization medium, made possible through application of our technique of complexation-mediated crystallization, may prove of profound importance in, e.g., the area of semiconductor nanoparticle technology.