REPORT DOCUMENTATION PAGE		Form App OMB No. 0	Form Approved OMB No. 0704-018	
Public reporting burden for this collection of inf existing data sources, gathering and maintainin burden estimate or any other aspect of this coll Directorate for Information and Reports, 1215 J Paperwork Reduction Project (0704-0188), Was	iormation is estimated to average 1 hour pend the data needed, and completing and rev ection information, including suggestions effers on Davis Highway, Suite 1204, Arling shington, DC 20503.	response, including the time for reviewin iewing the collection of information. Send or reducing this burden, to Washington H ton, VA 22202-4302, and to the Office of f	g instructions, searching I comments regarding this eadquarters Services, Management and Budget,	
1. AGENCY USE ONLY (Leave blank)	2. REPORT DATE February 1994	3. REPORT TYPE AND D	ATES COVERED	
4. TITLE AND SUBTITLE		5. FUNDING NUMBERS		
CATHODIC PROTECTION SYSTEM INSPECTION VI				
6. AUTHOR(S)				
Jim Jenkins				
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESSE(S)		8. PERFORMING ORGAN	8. PERFORMING ORGANIZATION REPORT	
Naval Facilities Engineering Service Center Port Hueneme, CA 93043-4328		TDS-2003-SHR	TDS-2003-SHR	
9. SPONSORING/MONITORING AGEN	NCY NAMERS AND ADDRESSES ELECTE IAN 1 3 1995	10. SPONSORING/MONITO NUMBER	RING AGENCY REPORT	
11. SUPPLEMENTARY NOTES	G			
12a. DISTRIBUTION/AVAILABILITY	STATEMENT	12b. DISTRIBUTION CODE		
Approved for public releas	e; distribution is unlimited.			
13. ABSTRACT (Meximum 200 words)	· · · · · · · · · · · · · · · · · · ·		t I	
If the cathodic protection syste condition of the protected struct need for physical inspection of	m is periodically inspected and cture can be inferred from the c f the protected structure.	maintained to provide continuc athodic protection system recon Ju	ous protection, the Image: The second seco	
B		B	y istribution /	
		Availability Codes		
19950112 0	09 serie que	D INPA ENCHANNED S	ist Avail and/or Special	
				
14. SUBJECT TERMS			15. NUMBER OF PAGES	
Cathodic protection system, rect	mers, inspection vi		16. PRICE CODE	
17. SECURITY CLASSIFICATION OF REPORT Unclassified	18. SECURITY CLASSIFICATION OF THIS PAGE Unclassified	19. SECURITY CLASSIFICATION OF ABSTRACT Unclassified	20. LIMITATION OF ABSTRACT UL	
NSN 7540-01-280-5500			Standard Form 298 (Rev. 2-89)	



CATHODIC PROTECTION SYSTEM INSPECTION VI

When a cathodic protection system is working properly, corrosion of the protected structure is virtually nil. However, when the cathodic protection system is not working properly, the corrosion of the structure proceeds at a rate up to the normal corrosion rate of an unprotected structure. If the cathodic protection system is periodically inspected and maintained to provide continuous protection, the condition of the protected structure can be inferred from the cathodic protection system records without the need for physical inspection of the protected structure. Thus, the high cost of inspecting buried or submerged structure surfaces can be avoided if the cathodic protection system is properly inspected and maintained.

The requirements for scheduled inspection of cathodic protection systems are given in Chapter 8 of Naval Facilities Engineering Command MO-306 "Maintenance and Operation of Cathodic Protection Systems." Each individual cathodic protection system should be inspected according to these requirements. The requirements are:

Monthly:

• Inspect rectifiers.

Quarterly:

• Measure structure to electrolyte potentials.

Annually:

• Inspect submerged anodes (waterfront structures and water tanks) for consumption.

• Inspect test stations for mechanical damage.

INSPECTION PROCEDURES

The procedures for monthly inspection of cathodic protection system rectifiers were described in NFESC Techdata Sheet (TDS) (2002-SHR) and are described in more detail in MO-306. As in all inspection programs, proper record keeping is vital. NAVFAC Form 11014-74B should be used to record the results of these monthly rectifier inspections.

The structure to electrolyte potential is the key measurement in determining proper operation of cathodic protection systems. Procedures for performing these measurements were outlined in NCEL TDS 93-04 and are described in more detail in MO-306. For buried structures, structure-to-electrolyte potentials should be taken at a minimum of four points within the system with one of these points being the least negative point measured in previous surveys. Assistance in establishing these test points can be obtained from the corrosion control coordinator at your geographical Engineering Field Division or Activity, from the Cathodic Protection System Center of Expertise, or from the Naval Facilities Engineering Service Center. The structure to electrolyte potential readings should be recorded on NAVFAC Form 11014-74A.

For waterfront structures, the structure-toelectrolyte potential should also be measured quarterly at a minimum of four points in the system. These measurements should be recorded on NAVFAC Form 10014-74A.

For water tanks with internal cathodic protection systems, the system usually includes a "permanent" reference electrode in the tank. The structure-to-electrolyte potential should be measured monthly during the inspection of the rectifier using the "permanent" reference electrode and recorded on NAVFAC Form 11014-74B. The performance of the "permanent" reference electrode can be checked by comparing it with a portable reference electrode of known accuracy. This is usually performed in conjunction with the annual inspection of the tank anodes as described below.

Submerged anodes on waterfront structures and water tanks are visually inspected for consumption. If the anode is suspended, it can usually be retrieved for inspection. In this case, the easiest way of determining anode consumption in most instances is to weigh the anode and compare the weight with the original anode weight and the weight measures during previous inspections. If the remaining weight of the anode is less than that required for another year of operation, it should be replaced. When the anodes are mounted directly to the structure, or cannot be retrieved for topside inspection, divers can be used to inspect the anodes for consumption. In this case, the diver should measure the anode (length, width and thickness) to determine anode consumption.

The inspection of test stations is primarily a visual inspection for broken wires, loose contacts, and corrosion of conductors or connectors.

In addition to the minimum requirements described above, it is good practice to perform additional inspections. Whenever a buried structure is excavated for repair or in conjunction with other work, the surface of the structure should be inspected for evidence of corrosion and, if coated, for coating deterioration. If a water tank is emptied for any reason, the interior should likewise be inspected for evidence of corrosion or coating deterioration.

Good record keeping is the key to any inspection and maintenance program. In addition to the required records (Forms 11014-74A and 11014-74B), records of leaks and required maintenance on the buried or submerged systems, as well as repairs and maintenance required on the cathodic protection system should be maintained. Current drawings of underground utility systems, waterfront structures, and water tanks, as well as current drawings of the cathodic protection systems are also vital to a good overall inspection and maintenance program.

NFESC CONTACTS

Mr. Jim Jenkins, Code ESC63 (Waterfront Materials Division) Comm: (805) 982-4797, DSN: 551-4797 FAX: (805) 982-985-1197

or

Mr. Pete Tafoya, Code ESC101 (Command Support & Technology Office) Comm: (805) 982-1342, DSN: 551-1342

or

Answering Machine Comm: (805) 982-4070; DSN: 551-4070

DEPARTMENT OF THE NAVY

COMMANDING OFFICER NFESC 560 CENTER DRIVE PORT HUENEME CA 93043-4328

-

OFFICIAL BUSINESS NFESC 5110/1 (10/93)