

# REPORT DOCUMENTATION PAGE

Form Approved  
OMB No. 0704-0188

Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.

<b>1. AGENCY USE ONLY (Leave blank)</b>	<b>2. REPORT DATE</b> 16-3-98	<b>3. REPORT TYPE AND DATES COVERED</b> Technical Report	
<b>4. TITLE AND SUBTITLE</b> Facile Reactions for the Preparation of [(Me <sub>3</sub> CCH <sub>2</sub> ) <sub>2</sub> GaNH <sub>2</sub> ] <sub>2</sub> and of GaN		<b>5. FUNDING NUMBERS</b> Grant: N00014-96-1-0483  R&T Code: 4135002	
<b>6. AUTHOR(S)</b> O. T. Beachley, Jr., John C. Pazik and Matthew J. Noble		<b>8. PERFORMING ORGANIZATION REPORT NUMBER</b>  Technical Report No. 50	
<b>7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES)</b> Department of Chemistry State University of New York at Buffalo Natural Sciences Complex Buffalo, NY 14260-3000		<b>10. SPONSORING / MONITORING AGENCY REPORT NUMBER</b>  n/a	
<b>9. SPONSORING / MONITORING AGENCY NAME(S) AND ADDRESS(ES)</b> Office of Naval Research 800 N. Quincy Street Arlington, VA 22217-5000		<b>11. SUPPLEMENTARY NOTES</b>  Accepted for publication - Organometallics	
<b>12a. DISTRIBUTION / AVAILABILITY STATEMENT</b> This document has been approved for public release and sale; its distribution is unlimited. Reproduction in whole or in part is permitted for any purpose of the United States government.		<b>12b. DISTRIBUTION CODE</b>  n/a	
<b>13. ABSTRACT (Maximum 200 words)</b> Four reactions of neopentylgallium compounds with ammonia have been investigated. The dihydronaphthalene derivative C <sub>10</sub> H <sub>8</sub> [Ga(CH <sub>2</sub> CMe <sub>3</sub> ) <sub>2</sub> ] <sub>2</sub> ·2NaCl has been observed to react with anhydrous ammonia at low temperature (-78°C) to form (Me <sub>3</sub> CCH <sub>2</sub> ) <sub>2</sub> GaNH <sub>2</sub> , dihydronaphthalene (C <sub>10</sub> H <sub>10</sub> ) and NaCl whereas the related elimination reaction between Ga(CH <sub>2</sub> CMe <sub>3</sub> ) <sub>3</sub> and NH <sub>3</sub> occurred at 140 - 150 °C. The new compound (Me <sub>3</sub> CCH <sub>2</sub> ) <sub>2</sub> GaNH <sub>2</sub> also was prepared by reacting Ga(CH <sub>2</sub> CMe <sub>3</sub> ) <sub>2</sub> Cl with sodium in liquid ammonia at -70 °C. Bisneopentylgallium amide was fully characterized and exists as a dimer at room temperature in benzene solution. Neopentylgallium(I) [Ga(CH <sub>2</sub> CMe <sub>3</sub> ) <sub>n</sub> ] has been observed also to react with NH <sub>3</sub> at 460 - 480 °C to form GaN(s), CMe <sub>4</sub> and H <sub>2</sub> .			
<b>14. SUBJECT TERMS</b> Organogallium compounds, elimination reactions, gallium nitride			<b>15. NUMBER OF PAGES</b> 10
			<b>16. PRICE CODE</b> n/a
<b>17. SECURITY CLASSIFICATION OF REPORT</b> Unclassified	<b>18. SECURITY CLASSIFICATION OF THIS PAGE</b> Unclassified	<b>19. SECURITY CLASSIFICATION OF ABSTRACT</b> Unclassified	<b>20. LIMITATION OF ABSTRACT</b> UL

19980318 066

OFFICE OF NAVAL RESEARCH  
Contract N-00014-96-1-0483  
R&T Code 4135002  
TECHNICAL REPORT NO. 50

Facile Reactions for the Preparation of  $[(\text{Me}_3\text{CCH}_2)_2\text{GaNH}_2]_2$   
and of GaN

by

O. T. Beachley, Jr.\*, John C. Pazik and Matthew J. Noble

Prepared for Publication  
in  
Organometallics

State University of New York at Buffalo  
Department of Chemistry  
Buffalo, New York 14260-3000

16 March 1998

Reproduction in whole or in part is permitted for  
any purpose of the United States Government

\*This document has been approved for public release  
and sale; its distribution is unlimited

# Facile Reactions for the Preparation of $[(\text{Me}_3\text{CCH}_2)_2\text{GaNH}_2]_2$ and of GaN

by

O. T. Beachley, Jr.\* , John C. Pazik and Matthew J. Noble  
Department of Chemistry  
State University of New York at Buffalo  
Buffalo, NY 14260-3000


## Abstract

Four reactions of neopentylgallium compounds with ammonia have been investigated. The dihydronaphthalene derivative  $\text{C}_{10}\text{H}_8[\text{Ga}(\text{CH}_2\text{CMe}_3)_2]_2 \cdot 2\text{NaCl}$  has been observed to react with anhydrous ammonia at low temperature ( $-78^\circ\text{C}$ ) to form  $(\text{Me}_3\text{CCH}_2)_2\text{GaNH}_2$ , dihydronaphthalene ( $\text{C}_{10}\text{H}_{10}$ ) and NaCl whereas the related elimination reaction between  $\text{Ga}(\text{CH}_2\text{CMe}_3)_3$  and  $\text{NH}_3$  occurred at  $140 - 150^\circ\text{C}$ . The new compound  $(\text{Me}_3\text{CCH}_2)_2\text{GaNH}_2$  also was prepared by reacting  $\text{Ga}(\text{CH}_2\text{CMe}_3)_2\text{Cl}$  with sodium in liquid ammonia at  $-70^\circ\text{C}$ . Bisneopentylgallium amide was fully characterized and exists as a dimer at room temperature in benzene solution. Neopentylgallium(I)  $[\text{Ga}(\text{CH}_2\text{CMe}_3)]_n$  has been observed also to react with  $\text{NH}_3$  at  $460 - 480^\circ\text{C}$  to form  $\text{GaN}_{(g)}$ ,  $\text{CMe}_4$  and  $\text{H}_2$ .

---


Low oxidation state gallium clusters<sup>1</sup>  $[\text{Ga}(\text{CH}_2\text{CMe}_3)]_n$  ( $n = 6 - 12$ ) have been prepared by the reduction of dineopentylgallium chloride by using either sodium or lithium with naphthalene in THF solution. When the reagents were combined at  $-78^\circ\text{C}$ , a yellow dihydronaphthalene gallium(III) derivative  $\text{C}_{10}\text{H}_8[\text{Ga}(\text{CH}_2\text{CMe}_3)_2]_2 \cdot 2\text{MCl}$  ( $\text{M} = \text{Li}, \text{Na}$ ) was formed. Upon warming to room temperature, this intermediate was converted to gallium(I) clusters  $(\text{GaR})_n$  ( $n = 6 - 12$ ),  $\text{GaR}_3$  and  $\text{MCl}$ . We have investigated the reaction of this yellow dihydronaphthalene gallium(III) intermediate  $\text{C}_{10}\text{H}_8[\text{Ga}(\text{CH}_2\text{CMe}_3)_2]_2 \cdot 2\text{NaCl}$  with anhydrous ammonia because of our interest in the reactions of gallium compounds which have two different organic substituents.<sup>2,3,4</sup> The reactivity of this dihydronaphthalene derivative with ammonia was compared, in turn, with that for  $\text{Ga}(\text{CH}_2\text{CMe}_3)_3$ . Two additional reactions of organogallium compounds are also reported: (1) the reaction of the low oxidation state gallium cluster  $[\text{Ga}(\text{CH}_2\text{CMe}_3)]_n$  with ammonia and (2) the reaction of  $\text{Ga}(\text{CH}_2\text{CMe}_3)_2\text{Cl}$  with sodium in liquid ammonia.

The yellow gallium(III) derivative of dihydronaphthalene  $\text{C}_{10}\text{H}_8[\text{Ga}(\text{CH}_2\text{CMe}_3)_2]_2 \cdot 2\text{NaCl}$  reacts with anhydrous ammonia at  $-78^\circ\text{C}$  to form  $(\text{Me}_3\text{CCH}_2)_2\text{GaNh}_2$ ,  $\text{C}_{10}\text{H}_{10}$  and  $\text{NaCl}$  in high yields (Eq 1). Hydrogen was not formed. Initially, the reaction mixture had



an intense golden-yellow color, which would be indicative of the dihydronaphthalene intermediate as an ammonia adduct. As the reaction mixture was stirred for 18 h at  $-78^\circ\text{C}$ , the yellow color disappeared and a colorless solution and a colorless precipitate ( $\text{NaCl}$ ) formed. The solution never became brown, a color which would be indicative of the presence of the gallium(I) compound<sup>1</sup>  $[\text{Ga}(\text{CH}_2\text{CMe}_3)]_n$ , a product from the decomposition of  $\text{C}_{10}\text{H}_8[\text{Ga}(\text{CH}_2\text{CMe}_3)_2]_2$ . Filtration of the final product mixture and removal of the solvent led to the isolation and subsequent identification of  $(\text{Me}_3\text{CCH}_2)_2\text{GaNh}_2$ ,  $\text{C}_{10}\text{H}_{10}$

and NaCl. All observations confirm the occurrence of a very facile elimination reaction between the dihydronaphthalene gallium(III) intermediate and ammonia and indicate the absence of an oxidation-reduction reaction. In comparison the elimination reaction between  $\text{Ga}(\text{CH}_2\text{CMe}_3)_3$  and ammonia required heating at 140-150 °C for 4 days in a sealed tube to effect the formation of  $(\text{Me}_3\text{CCH}_2)_2\text{GaNH}_2$  and  $\text{CMe}_4$  (Eq 2) in nearly quantitative yields.



Thus, this elimination reaction occurs at ~200 °C above the temperature needed for the reaction between the yellow dihydronaphthalene intermediate<sup>1</sup> and ammonia. The latter is known to decompose to  $\text{Ga}(\text{CH}_2\text{CMe}_3)_3$ ,  $[\text{Ga}(\text{CH}_2\text{CMe}_3)]_n$  and  $\text{C}_{10}\text{H}_8$  but  $(\text{Me}_3\text{CCH}_2)_2\text{GaNH}_2$  cannot have been formed by way of the initial decomposition of  $\text{C}_{10}\text{H}_8[\text{Ga}(\text{CH}_2\text{CMe}_3)_2]_2$  and the subsequent elimination reaction of  $\text{Ga}(\text{CH}_2\text{CMe}_3)_3$  with ammonia.


Neopentylgallium(I)  $[\text{Ga}(\text{CH}_2\text{CMe}_3)]_n$  reacted with anhydrous ammonia in a sealed-tube but only at temperatures in the range of 460 - 480 °C. After 24 h the products were separated and identified as  $\text{CMe}_4$ ,  $\text{H}_2$  and  $\text{GaN}_{(6)}$  with yields of 86, 70 and 88%, respectively, as based on Eq 3. Neopentane was identified by its characteristic <sup>1</sup>H NMR



spectrum whereas  $\text{H}_2$  was identified by its typical properties in the vacuum line. The shiny black solid remaining in the tube was identified as GaN (hexagonal) by its X-ray powder pattern and ESCA spectrum. The ESCA spectrum confirmed the presence of gallium, nitrogen, carbon and oxygen. However, an elemental analysis of the shiny black solid revealed very low carbon contamination, 1.24 % C and 0.69 % H. It is of interest to note that when  $\text{GaN}_{(6)}$  is prepared from  $\text{GaMe}_3$  and  $\text{NH}_3$ , temperatures in the range of ~1000 °C

are needed.<sup>5</sup> Thus, the lower temperatures used for the reaction of the gallium(I) compound with ammonia might reflect a significant relationship between the low oxidation state and intermediates in the pathway for the formation of group 13 - 15 materials.

The reaction between  $\text{Ga}(\text{CH}_2\text{CMe}_3)_2\text{Cl}$  and sodium in liquid ammonia also was studied. Addition of a stoichiometric quantity of  $\text{Ga}(\text{CH}_2\text{CMe}_3)_2\text{Cl}$  dissolved in ammonia at  $-70^\circ\text{C}$  to the deep blue solution formed between sodium and liquid ammonia resulted in the formation of a colorless solution and a heavy colorless precipitate. Subsequent use of the vacuum line revealed the formation of slightly less than one half mol of hydrogen gas per mol of  $\text{Ga}(\text{CH}_2\text{CMe}_3)_2\text{Cl}$ . Thus, the following balanced equation (Eq 4) describes the



reaction.

The compound  $(\text{Me}_3\text{CCH}_2)_2\text{GaNH}_2$  was fully characterized by its melting point,  $^1\text{H}$  NMR and IR spectra, C and H analyses and a cryoscopic molecular weight study in benzene solution. All data are consistent with the presence of a dimer in solution and in the solid state with a melting point of  $58.0 - 60.5^\circ\text{C}$ . The corresponding methyl derivative<sup>6</sup>  $\text{Me}_2\text{GaNH}_2$  exists as a trimer with a higher melting point ( $100-101.5^\circ\text{C}$ ).

### Experimental Section

All compounds described in this investigation were very sensitive to oxygen and moisture and were manipulated by using standard vacuum line techniques or under a purified argon atmosphere in a Vacuum Atmospheres drybox equipped with a Dry Train. All solvents were purified before use. Elemental analyses were performed by E+R Microanalytical Laboratories, Corona, NY. Infrared spectra of samples as Nujol mulls between CsI plates were recorded by means of a Perkin Elmer 683 spectrometer. The  $^1\text{H}$

NMR spectra were recorded at 300 MHz by using a Varian Gemini 300 spectrometer. All samples for NMR spectra were contained in flame-sealed NMR tubes. Chemical shifts are reported in  $\delta$  (ppm) and are referenced to tetramethylsilane (TMS) as  $\delta = 0.00$  ppm and benzene as  $\delta = 7.15$  ppm. X-ray photoelectron spectra were recorded by using a Perkin Elmer Physical Electronics (PHI) Model 5100 ESCA spectrometer with a Mg  $K_{\alpha 1,2}$  X-ray source (1253.6 eV) with a 180 degree hemispherical detector. The spectrometer was calibrated to the Ag  $3d_{5/2}$  peak at 367.9 eV. Spectra were collected at an angle of  $45^\circ$ . The identity of elements at the surface were evaluated qualitatively with low resolution spectra (89.45 eV) whereas high resolution spectra (35.75 eV) were used to establish the binding energies and peak areas for quantitative analysis. X-ray powder diffraction data were recorded by using a Siemens D-500 X-ray diffractometer with Cu  $K_{\alpha}$  radiation. Melting points were observed in a Mel-Temp by using flame-sealed capillaries. Molecular weights were measured cryoscopically in benzene by using an instrument similar to that described by Shriver and Drezdson.<sup>7</sup>

**Reaction of  $C_{10}H_8[Ga(CH_2CMe_3)_2]_2 \cdot 2NaCl$  with Anhydrous  $NH_3$ .** The yellow gallium(III) dihydronaphthalene derivative  $C_{10}H_8[Ga(CH_2CMe_3)_2]_2 \cdot 2NaCl$  was prepared in THF at  $-78^\circ C$  as previously described<sup>1</sup> by using sodium metal (0.067 g, 2.9 mmol), naphthalene (0.380 g, 2.97 mmol) and  $Ga(CH_2CMe_3)_2Cl$  (0.721 g, 2.91 mmol). Then, excess dry  $NH_3$  was added to the flask by vacuum distillation. Initially, the solution had an intense yellow color. As the solution was stirred at  $-78^\circ$  for 18 h, the color disappeared and a colorless solution and a colorless precipitate formed. Pressure measurements at  $-196^\circ C$  on the vacuum line confirmed the absence of any noncondenseable gas. The THF and excess  $NH_3$  were removed by vacuum distillation. The remaining reaction products were subjected to dynamic vacuum for 40 h. The products which were volatile at room temperature were collected in a  $-196^\circ C$  trap and identified by  $^1H$  NMR spectroscopy as dihydronaphthalene with very small amounts of naphthalene and other unidentified impurities. Extraction of the nonvolatile products with pentane through a

glass frit separated NaCl (0.168 g, 2.88 mmol, 99.0 % yield based on Na) from a pentane soluble colorless solid. Sublimation of this solid at 55 °C led to the isolation and identification of  $(\text{Me}_3\text{CCH}_2)_2\text{GaNH}_2$  (0.344 g, 1.51 mmol, 52 % yield based on Na).  $(\text{Me}_3\text{CCH}_2)_2\text{GaNH}_2$ . Mp: 51.8 - 54.0 °C.  $^1\text{H NMR}$  ( $\text{C}_6\text{D}_6$ ):  $\delta$  1.10 (s, 9.3H,  $-\text{CH}_3$ ), 0.63 (s, 2.2H,  $-\text{CH}_2-$ ), 0.34 (s, br, 1.0H,  $-\text{NH}_2$ ). IR (Nujol mull,  $\text{cm}^{-1}$ ): 3870 (vw), 3400(m), 3325 (m), 3295 (vw), 3205 (w, br), 2735 (w), 2705 (m), 2400 (vw), 2370 (vw), 2280 (vw), 2270 (vw), 2100 (vw), 2010 (vw), 1982 (vw), 1650 (w), 1565 (w), 1355 (s), 1230 (s), 1133 (m), 1099 (s), 1013 (m), 997 (s), 930 (m), 908 (w), 846 (m), 800 (s), 743 (s), 700 (s), 628 (s), 590 (m), 574 (m), 520 (w), 455 (sh), 435 (vs), 382 (m), 328 (w), 288 (m), 245 (w).

**Reaction of  $\text{Ga}(\text{CH}_2\text{CMe}_3)_3$  with  $\text{NH}_3$  at 140 - 150 °C.** A break-seal tube was charged with  $\text{Ga}(\text{CH}_2\text{CMe}_3)_3$  (1.42 g, 5.02 mmol) and purified  $\text{NH}_3$  (5.03 mmol) and then sealed by fusion. The tube was heated at 140 - 150 °C for 4 d in a tube furnace and then opened. Noncondensable gas ( $-196$  °C) was absent. The volatile products were separated, weighed (0.384 g) and the neopentane was identified by  $^1\text{H NMR}$  spectroscopy. The colorless solid remaining in the tube was sublimed at 60 - 80 °C and identified as  $(\text{Me}_3\text{CCH}_2)_2\text{GaNH}_2$  (0.996 g, 4.37 mmol, 87.3 % yield based on  $\text{Ga}(\text{CH}_2\text{CMe}_3)_3$ ).  $(\text{Me}_3\text{CCH}_2)_2\text{GaNH}_2$ . Mp: 58.8 - 60.8 °C. Cryoscopic molecular weight, benzene solution, formula weight 228.03 (observed molality, observed mol wt, association): 0.0796, 490, 2.15; 0.0562, 477, 2.09; 0.0284, 499, 2.19. The  $^1\text{H NMR}$  and IR spectra were identical to that described above.

**Reaction of  $[\text{Ga}(\text{CH}_2\text{CMe}_3)]_n$  with Ammonia.** A break-seal tube was charged with 0.440 g of  $[\text{Ga}(\text{CH}_2\text{CMe}_3)]_n$  (3.13 mmol) and then 3.44 mmol of  $\text{NH}_3$  was added by vacuum distillation. The tube was sealed by fusion and heated for 1 d at 460 - 480 °C. As reaction occurred, the contents of the tube changed from dark reddish brown to light gray, to yellow gray and finally to shiny black. The tube was cooled to  $-196$  °C, opened and the noncondensable gas was transferred and measured by using a Toepler



pump-gas burette assembly (2.20 mmol, 70.3 % based on Eq 3). The volatile, condensable material (0.195 g) was transferred by vacuum distillation to a small weighed trap. The  $^1\text{H}$  NMR spectrum of these volatile compounds in  $\text{C}_6\text{D}_6$  identified neopentane ( $\text{CMe}_4$ ,  $\delta$  0.99, 86 % yield based on Eq 3). The nonvolatile, shiny black solid was scraped out of the reaction tube in the dry box, ground into a fine powder and washed with 50 mL of pentane. This crystalline phase was identified as GaN (0.232 g, 2.77 mmol, 88.5 % based on Eq 3). **GaN**. X-ray powder diffraction (d spacings in Å): 2.76, 2.58, 2.44, 1.89, 1.60, 1.46, 1.37 (Lit.<sup>8</sup> for hexagonal GaN: 2.76, 2.59, 2.43, 1.88, 1.59, 1.46, 1.38). ESCA (Binding energy, eV; corrected to  $\text{C}_{1s}$ ):  $\text{Ga}_{3d_{3/2}}$  20.3,  $\text{Ga}_{2p_{3/2}}$  1119.5,  $\text{N}_{1s}$  398.3,  $\text{C}_{1s}$  285.0,  $\text{O}_{1s}$  531.7. (Lit.<sup>9</sup> for hexagonal GaN:  $\text{Ga}_{3d_{3/2}}$  19.8,  $\text{Ga}_{2p_{3/2}}$  1124.1,  $\text{N}_{1s}$  397.0,  $\text{C}_{1s}$  285.0,  $\text{O}_{1s}$  531.9). Surface ratio from ESCA (Ga:N): 1.32:1.00. Anal. for GaN: Found: C, 1.24; H, 0.69.

**Reaction of  $\text{Ga}(\text{CH}_2\text{CMe}_3)_2\text{Cl}$  with Sodium in Liquid Ammonia.** A Solv-seal flask was charged with 0.027 g of Na (1.2 mmol) and then connected with an  $80^\circ$  elbow to another flask which contained 0.290 g of  $\text{Ga}(\text{CH}_2\text{CMe}_3)_2\text{Cl}$  (1.17 mmol). Then liquid ammonia (25 mL) which had been previously dried by stirring over sodium at  $-70^\circ\text{C}$  was vacuum distilled onto the fresh sodium metal and stirred for 0.5 h to form a deep blue solution. After a small amount of ammonia was distilled onto the  $\text{Ga}(\text{CH}_2\text{CMe}_3)_2\text{Cl}$  to form a solution, the reagents were combined. The dark blue solution immediately turned light blue. More ammonia was distilled back into the flask which originally contained the  $\text{Ga}(\text{CH}_2\text{CMe}_3)_2\text{Cl}$  in order to ensure the quantitative transfer of the reagent. The final solution was colorless and contained a colorless precipitate. After the mixture was stirred for 1 h at  $-70^\circ\text{C}$ , the noncondensable gas was measured at  $-196^\circ\text{C}$  with a Toepler pump - gas burette assembly (0.458 mmol  $\text{H}_2$ ). The ammonia was removed and the products were extracted with pentane to separate NaCl (0.068 g, 1.2 mmol, 100 % yield) from  $(\text{Me}_3\text{CCH}_2)_2\text{GaN}\text{H}_2$  which was identified by its melting point,  $^1\text{H}$  NMR and IR spectra and partial elemental analysis.  $(\text{Me}_3\text{CCH}_2)_2\text{GaN}\text{H}_2$ . Mp:  $58.0 - 60.5^\circ\text{C}$ . Anal.

Calcd. for  $C_{10}H_{24}GaN$ : C, 52.56; H, 10.61. Found: C, 52.83; H 10.85. The  $^1H$  NMR and IR spectra were identical to that described above.

**Acknowledgment.** This work was supported in part by the Office of Naval Research. We are especially grateful for the help of Professor Rossman F. Giese, University at Buffalo for the X-ray powder diffraction studies which were used to identify GaN and of Professor Joseph A. Gardella, Jr. and Ms. Norma L. Hernandez de Gatica, University at Buffalo for recording and evaluating the ESCA spectral data.

## References

1. Beachley, O. T., Jr.; Pazik, J. C.; Noble, M. J. *Organometallics* **1994**, *13*, 2885.
2. Beachley, O. T., Jr.; Royster, T. L., Jr.; Arhar, J. R.; Rheingold; A. L.  
*Organometallics* **1993**, *12*, 1976.
3. Beachley, O. T., Jr.; Rosenblum, D. B.; Churchill, M. R.; Lake, C. H.; Toomey, L.  
M. *Organometallics* **1996**, *15*, 3653.
4. Beachley, O. T., Jr.; Maloney, J. P.; Rogers, R. D. *Organometallics* **1997**, *16*, 3267.
5. (a) Addamiano, A. J. *J. Electrochem. Soc.* **1961**, *108*, 1072. (b) Munir, Z. A.;  
Searcy, A. W. *J. Chem. Phys.* **1965**, *42*, 4223. (c) Pichugin, I. G.; Searcy, D. A.  
*Inorg. Mater.* **1970**, *6*, 1732. (d) Isherwood, B. J.; Wickenden, D. K. *J. Mater. Sci.*  
**1970**, *5*, 869; (e) Ejder, E. *J. Cryst. Growth* **1974**, *22*, 44. (f) Ogino, T.; Aoki, M.  
*J. Appl. Phys.* **1979**, *18*, 1049.
6. Coates, G. E. *J. Chem. Soc.* **1951**, 2003.
7. Shriver, D. F.; Drezdson, M. A. *The Manipulation of Air Sensitive Compounds*;  
McGraw-Hill: New York, 1968; p 38.
8. *JCPDS Powder Diffraction File Search Manual* ; International Center for Diffraction  
Data: Swarthmore, PA.; Card 2-1078.
9. (a) Gann, R. G.; Geib, K. M.; Wilmsen, C. W.; Costello, J.; Hrychowain, G.; Zeto,  
R. J. *J. Appl. Phys.* **1988**, *63*, 506. (b) Wagner, C. D.; Riggs, W. M.; Davis, L. E.;  
Moulder, S. F. *Handbook of X-Ray Photoelectron Spectroscopy*; Muilenberg, G. E.,  
Physical Electronics: Eden Prairie, MN, **1979**; (c) Murty, P. S.; Bhaskara Rao, S. V.

N.; Sharma, S. K.; Grampurohit, S. V. *Current Sci.* **1982**, *51*, 468.

## TECHNICAL REPORT DISTRIBUTION LIST - GENERAL

Office of Naval Research Chemistry Division, ONR 331 800 North Quincy Street Arlington, Virginia 22217-5660	(1)*	Dr. Richard W. Drisko Naval Facilities & Engineering Service Center Code L52 Port Hueneme, CA 93043	(1)
Defense Technical Information Center (2) 8725 John J. Kingman Rd., #0744 Fort Belvoir, VA 22060-6217		Dr. Eugene C. Fischer Code 2840 Naval Surface Warfare Center Carderock Division Detachment Annapolis, MD 21402-1198	(1)
Dr. James S. Murday Chemistry Division, Code 6100 Naval Research Laboratory Washington, D.C. 20375-5320	(1)		
Dr. John Fischer, Director Chemistry Division, C0235 Naval Air Weapons Center Weapons Division China Lake, CA 93555-6001	(1)		
Dr. Peter Seligman Naval Command, Control and Ocean Surveillance Center RDT&E Division San Diego, CA 92152-5000	(1)		

\* Number of copies to forward