

REPORT DOCUMENTATION PAGE

Form Approved
OMB No. 0704-0188

Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.

1. AGENCY USE ONLY (Leave blank)	2. REPORT DATE 22 Jan 98	3. REPORT TYPE AND DATES COVERED Final Conference 01 Aug 96 to 31 Jul 97
----------------------------------	-----------------------------	---

4. TITLE AND SUBTITLE Scale-up Equipment for Nanosize Particle Synthesis	5. FUNDING NUMBERS F49620-96-1-0427
---	--

6. AUTHOR(S) Dr Gary L Messing	AFRL-SR-BL-TR-98
-----------------------------------	------------------

7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) The Pennsylvania State University 110 Technology Center Bldg University park PA 168002-7000	0294 N
---	--------

9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) AFOSR/NA 110 Duncan Ave. Suite B115 Bolling AFB, DC	10. SPONSORING/MONITORING AGENCY REPORT NUMBER NA
--	--

11. SUPPLEMENTARY NOTES

12a. DISTRIBUTION AVAILABILITY STATEMENT Unlimited	12b. DISTRIBUTION CODE 19980410 056
---	--

13. ABSTRACT (Maximum 200 words)


The goal of the ARPA/AFOSR supported research program is to establish a scientific foundation for the low cost preparation of bulk single crystal quality materials by templated grain growth (TGG); a process in which solid phase epitaxy is used to initiate solid state grain growth of a specific orientation in a polycrystalline matrix. We are investigating two classes of TGG: surface TGG in which a single crystal is contacted with a dense, polycrystalline ceramic and in situ TGG in which anisometric particles are uniformly dispersed and oriented in a polycrystalline matrix. The matrix must be fully dense and consist of sub-100 nm scale grains for TGG to work. Bi4Ti3O12 and Sr2Nb2O7 have been selected because of the need for high temperature piezoelectrics. These materials can be poled only when they are highly oriented materials.

We are also studying TGG for the low cost preparation of bulk single crystal quality BaTiO3 and (Ba1-xSrx)TiO3. This process is designed to provide large single crystals at considerably less expense than top-seeded solution grown BaTiO3 which cost on the order of \$5000 per crystal (Sanders Inc., Nashua, New Hampshire). Ultimately, such crystals are attractive for photorefractive applications including optical storage, phase conjugate mirrors, and multiple-wave mixing.

14. SUBJECT TERMS	15. NUMBER OF PAGES 2
	16. PRICE CODE

17. SECURITY CLASSIFICATION OF REPORT UNCLASSIFIED	18. SECURITY CLASSIFICATION OF THIS PAGE UNCLASSIFIED	19. SECURITY CLASSIFICATION OF ABSTRACT UNCLASSIFIED	20. LIMITATION OF ABSTRACT UL
---	--	---	----------------------------------

PENNSSTATE



(814) 865-2262
Fax: (814) 865-2326
messing@ems.psu.edu

Gary L. Messing, Director
Intercollege Materials Research Lab.

The Pennsylvania State University
202 Materials Research Laboratory
University Park, PA 16802-4801

January 22, 1998

Dr. Alexander Pechenik
AFOSR/NA
110 Duncan Avenue Room B115
Bolling AFB, DC 20332-8080

Dear Dr. Pechenik:

Enclosed please find the Final Technical Report for Grant No. F49620-96-1-0427, "Scale-up Equipment for Nano-size Particle Synthesis by Spray Pyrolysis."

Best regards,



Gary L. Messing

GLM/wb

cc: R. Killoren

Final Technical Report

"Scale-up Equipment for Nanosize Particle Synthesis by Spray Pyrolysis"

AFOSR Contract F49620-94-1-0427
Dr. Alexander Pechenik, Project Monitor

We purchased a PSD52 Laboratory Spray Dryer for Closed Circuit Operation from APV Anhydro Separation Technologies. The equipment operates at 350°C using nitrogen gas with an outlet temperature of 100°C. Both aqueous and non-aqueous systems can be used in this system. This allows for organic solvent based systems to be used. Organic solvents can be recovered in an activated carbon assembly. For water drying, the drying capacity is 4 kg/h whereas acetone is 21 kg/h.

The system was delivered in November 1997 and will be installed in January 1998. However, it will be used for powder synthesis in the following DOD projects:

ARPA/AFOSR Supported Program

Grant #49620-94-1-0428, P.I.s G. L. Messing and S. Trolier-McKinstry
Grant #DAAH04-95-1-0484, P.I. G. L. Messing

The goal of the ARPA/AFOSR supported research program is to establish a scientific foundation for the low cost preparation of bulk single crystal quality materials by templated grain growth (TGG); a process in which solid phase epitaxy is used to initiate solid state grain growth of a specific orientation in a polycrystalline matrix. We are investigating two classes of TGG; surface TGG in which a single crystal is contacted with a dense, polycrystalline ceramic and *in situ* TGG in which anisometric particles are uniformly dispersed and oriented in a polycrystalline matrix. The matrix must be fully dense and consist of sub-100 nm scale grains for TGG to work. $\text{Bi}_4\text{Ti}_3\text{O}_{12}$ and $\text{Sr}_2\text{Nb}_2\text{O}_7$ have been selected because of the need for high temperature piezoelectrics. These materials can be poled only when they are highly oriented materials.

We are also studying TGG for the low cost preparation of bulk single crystal quality BaTiO_3 and $(\text{Ba}_{1-x}\text{Sr}_x)\text{TiO}_3$. This process is designed to provide large single crystals at considerably less expense than top-seeded solution grown BaTiO_3 which cost on the order of \$5000 per crystal (Sanders Inc., Nashua, New Hampshire). Ultimately, such crystals are attractive for photorefractive applications including optical storage, phase conjugate mirrors, and multiple-wave mixing.

A key component of these projects is the availability of substantial quantities of high purity, nanosize powders with controlled stoichiometry. While nanosize BaTiO_3 powder is commercially available it requires doping to achieve the desired dielectric properties. There is no commercial source for nanosize $\text{Bi}_4\text{Ti}_3\text{O}_{12}$, $\text{Sr}_2\text{Nb}_2\text{O}_7$ and $(\text{Ba}_{1-x}\text{Sr}_x)\text{TiO}_3$ powder. While we have developed processes for the synthesis of such powders, our SP processes are scale-limited. The ability to produce a kilogram of nanosize powder of these compositions and doped versions of these powders will have a profound effect on the project by allowing more effort to be spent on obtaining dense and submicrometer scale microstructures, grain growth studies and characterization. Also, a much larger range of compositions can be evaluated.

ARPA/ONR Supported Program

Grant #N00014-93-1-0502, P.I.s G. L. Messing and S. Trolier-McKinstry

The goal of this project is to produce oriented PMN-PT by *in situ* templated grain growth (TGG). Because of the high degree of texture possible by TGG we will be able to determine, for the first time, whether or not it is possible to achieve large strain actuators in polycrystalline ceramics.

PMN-PT is chosen as the primary material for investigation instead of PZN-PT due to the stability of the perovskite crystal structure. PZN-PT powder, on the other hand, when heated above $\sim 500^{\circ}\text{C}$, tends to decompose into a pyrochlore structure. Since the ceramic processing techniques enable excellent control of compositional homogeneity, preparation of oriented PMN-PT ceramics near the morphotropic phase boundary should be easier to produce than by single crystal growth techniques, where the high PT content is problematic in terms of uniformity.

Our overall goal is to produce a fine-grained (i.e., $< 5\ \mu\text{m}$), textured PMN-PT. Based on our earlier successes with textured $\text{Sr}_2\text{Nb}_2\text{O}_7$ we know that we can refine the grain size by using a larger number of smaller seed particles to induce texture development. The acicular template particles seem to be particularly attractive for this purpose because they have diameters of $< 100\ \text{nm}$ and aspect ratios of > 10 . To obtain fine-grained PMN-PT it may be necessary to use a high concentration of PT particles and thus, to achieve the target PMN-PT phase composition, will require compositional compensation of the matrix powder.

We have extensive experience at MRL in producing PMN and PMN-PT powders and ceramics. The formation of perovskite PMN is extremely sensitive to preparation conditions whereas PMN-PT can be produced by the columbite mixed oxide approach. Likewise, solution synthesis of perovskite PMN-PT is well documented. In this program, however, fine grain size is critical for both TGG and for the final component. Thus, we will use a chemical synthesis approach so we can sinter at a lower temperature and achieve fine grain size for templated grain growth.

The new spray pyrolysis system will allow further preparation of nanosize PMN, PMN-PT, PZN and PZT powders. Such fine powders are essential for the development of textured piezoelectrics by templated grain growth. This work will commence in March 1998.