

US Army Corps of Engineers Construction Engineering Research Laboratory



CERL Technical Report 99/37 May 1999

Robotic Underwater Corrosion Inspection/Assessment of Sheet Pile Along Two Rivers at Cleveland, Ohio

Cuyahoga River Bulkhead Study: Phase 2 Report

Charles P. Marsh Robert Weber James B. Bushman James Klempir Brian A. Temple

The objectives of this study were to (1) perform a quantitative underwater corrosion inspection and assessment of sheet pile along the Cuyahoga River at Cleveland and (2) use the measured material thicknesses and corrosion rates to predict a probable future range of sheet pile thickness. The work was conducted in response to The Water Resources Development Act of 1996, Section 438, which directs the Army to project the cost of repairing and/or replacing all sheet pile along the Cuyahoga River.

This Phase 2 work was a follow-on condition assessment, conducted by the U.S. Army Construction Engineering Research Laboratory (CERL), using a remotely controlled submersible robotic inspection system in conjunction with conventional handheld acoustic thickness probes. Data were collected from 12 sites over a period of 1 week. Based on the data sample collected during the limited time frame of the study, a bounded,



steady-state projection of future sheet pile condition was made for each site. Because corrosion rates correlate directly to the degree of zebra mussel infestation, these condition projections may be too conservative if zebra mussel infestation proceeds significantly faster than assumed in this study.

USER EVALUATION OF REPORT

REFERENCE: USACERL Technical Report 99/37, Robotic Underwater Corrosion Inspection/Assessment of Sheet Pile Along Two Rivers at Cleveland, Ohio Cuyahoga River Bulkhead Study: Phase 2 Report

Please take a few minutes to answer the questions below, tear out this sheet, and return it to USACERL. As user of this report, your customer comments will provide USACERL with information essential for improving future reports.

1. Does this report satisfy a need? (Comment on purpose, related project, or other area of interest for which report will be used.)

2. How, specifically, is the report being used? (Information source, design data or procedure, management procedure, source of ideas, etc.)

3. Has the information in this report led to any quantitative savings as far as manhours/contract dollars saved, operating costs avoided, efficiencies achieved, etc.? If so, please elaborate.

4. What is your evaluation of this report in the following areas?

a.	Presentation:
b.	Completeness:
c.	Easy to Understand:
d.	Easy to Implement:
e.	Adequate Reference Material:
f.	Relates to Area of Interest:
g.	Did the report meet your expectations?
h.	Does the report raise unanswered questions?

i. General Comments. (Indicate what you think should be changed to make this report and future reports of this type more responsive to your needs, more usable, improve readability, etc.)

5. If you would like to be contacted by the personnel who prepared this report to raise specific questions or discuss the topic, please fill in the following information.

Name:

Telephone Number:

Organization Address:

6. Please mail the completed form to:

Department of the Army CONSTRUCTION ENGINEERING RESEARCH LABORATORY ATTN: CECER-TR-I P.O. Box 9005 Champaign, IL 61826-9005

REPORT DOCUMENTATION PAGE

Form Approved OMB No. 0704-0188

Public reporting burden for this collection of in gathering and maintaining the data needed, a collection of information, including suggestion Davis Highway, Suite 1204, Arlington, VA 222	nformation is estimated to average 1 hour per n and completing and reviewing the collection of i is for reducing this burden, to Washington Head 02-4302, and to the Office of Management and	esponse, including the time for re- nformation. Send comments reg- iquarters Services, Directorate for Budget, Paperwork Reduction Pr	eviewing instructions, s arding this burden esti or information Operatio roject (0704-0188), Wa	earching existing data sources, mate or any other aspect of this ns and Reports, 1215 Jefferson Ishington, DC 20503.						
1. AGENCY USE ONLY (Leave Blank)	2. REPORT DATE May 1999	3. REPORT TYPE AND DATE Final	SCOVERED							
4. TITLE AND SUBTITLE Robotic Underwater Corrosion Rivers at Cleveland, Ohio Cu	5. FUNDING NUMBE MIPR W81FU68	RS								
6. AUTHOR(S) Charles P. Marsh, Rober Webe Temple	er, James B. Bushman, James Kle	mpir, and Brian A.	·							
7. PERFORMING ORGANIZATION NAME(S	S) AND ADDRESS(ES)		8. PERFORMING O	RGANIZATION						
U.S. Army Construction Engine	eering Research Laboratory (CER	L)	REPORT NUMBE	К						
P.O. Box 9005 Champaign, IL 61826-9005	P.O. Box 9005 Champaign, IL 61826-9005									
9. SPONSORING / MONITORING AGENCY U.S. Army Corps of Engineers ATTN: CELRD-PE-EE 1776 Niagra Street Buffalo, NY 14207-3199	SPONSORING / MONITORING AGENCY NAME(S) AND ADDRESS(ES) 10. SPONSORING / MONITORING U.S. Army Corps of Engineers District, Buffalo AGENCY REPORT NUMBER ATTN: CELRD-PE-EE 1776 Niagra Street Buffalo, NY 14207-3199 Image: Comparison of the street									
11. SUPPLEMENTARY NOTES	<u></u>									
Copies are available from the N Royal Road, Springfield, VA 2	National Technical Information Se 2161.	rvice, 5285 Port								
12a. DISTRIBUTION / AVAILABILITY STATI	EMENT		12b. DISTRIBUTION	CODE						
Approved for public release, di	stribution is unlimited.									
 13. ABSTRACT (Maximum 200 words) The objectives of this study we along the Cuyahoga River at C probable future range of sheet p Act of 1996, Section 438, whice Cuyahoga River. This Phase 2 work was a follow Laboratory (CERL), using a real hand-held acoustic thickness pp collected during the limited tim made for each site. Because coprojections may be too conserved. 	tre to (1) perform a quantitative un leveland and (2) use the measured pile thickness. The work was con the directs the Army to project the word condition assessment, condu- motely controlled submersible rob robes. Data were collected from 1 he frame of the study, a bounded, so prosion rates correlate directly to vative if zebra mussel infestation p	derwater corrosion insp material thicknesses ar ducted in response to TI cost of repairing and/or cted by the U.S. Army C ootic inspection system i 2 sites over a period of steady-state projection of the degree of zebra mus roceeds significantly far	bection and asses ad corrosion rate he Water Resour- replacing all she Construction Eng in conjunction w 1 week. Based of future sheet pi ssel infestation, to ster than assume	essment of sheet pile s to predict a ces Development eet pile along the ineering Re-search ith conventional on the data sample le condition was hese condition d in this study.						
				•						
14. SUBJECT TERMS			.	15. NUMBER OF PAGES 136						
Fury corrosion	bulkhead robotic inspection		sheet pile	16. PRICE CODE						
17. SECURITY CLASSIFICATION OF REPORT	18. SECURITY CLASSIFICATION OF THIS PAGE	19. SECURITY CLASSIFICAT OF ABSTRACT	ION	20. LIMITATION OF ABSTRACT						
Unclassified	Unclassified	Unclassified	1	SAR						
NSN 7540-01-280-5500			Standard	Form 298 (Rev. 2-89)						

298-102

Foreword

This investigation was conducted for U.S. Army Engineer District Buffalo under Military Interdepartmental Purchase Request (MIPR) W81EU681485194, "Cuyahoga Bulkheads Inspection," dated 12 June 1998. The technical monitor was Teofilo D. Valerio, CELRD-PE-EE.

The work was performed by the Materials and Structures Branch (CF-M) of the Facilities Division (CF), U.S. Army Construction Engineering Research Laboratory (CERL). The CERL Principal Investigator was Dr. Charles P. Marsh. Robert Weber was the Associate Investigator, and James Klempir and Brian A. Temple were student contractors for the project. Dr. Ilker R. Adiguzel is Chief, CECER-CF-M, and L. Michael Golish is Chief, CECER-CF. The technical editor was Gordon L. Cohen, Information Technology Laboratory – CERL.

The Director of CERL is Dr. Michael J. O'Connor.

Contents

SF	2981
Fo	reword2
1	Introduction 7 Background 7 Objectives 8 Approach 8 Mode of Technology Transfer 8 Units of Weight and Measure 9
2	Degradation Mechanisms of Sheet Pile13
3	Sheet Pile Thickness Measurements15
4	Corrosion Rate Measurements19
5	Video Inspection of Sheet Pile
6	Discussion26
7	Summary and Recommendations35
	Summary
Re	ferences
Fig	jures37
Ар	pendix A: Sites Referenced in Sheet Pile Thickness and Corrosion Rate Measurements45
Ар	pendix B: Sheet Pile Thickness Measurements71
Ар	pendix C: Sheet Pile Corrosion Rate Measurements83
Ар	pendix D: Resistivity and Water Chemistry Data92
Dis	stribution

List of Figures and Tables

Figures

Figure 1. Map of test site locations.	11
Figure 2. General principle of corrosion	14
Figure 3. The Fury robot	17
Figure 4. Use of the hand-held acoustic sensor	18
Figure 5. McGyver measuring device.	18
Figure 6. Onsite probe for corrosion rate measurement.	19
Figure 7. Waterline video capture of sheet pile at Site 1	23
Figure 8. Video capture of Site 1 at 10 ft below waterline	25
Figure 9. Video capture of Site 1 at 25 ft below waterline	25
Figure 10. Site 1 projected thickness over time	28
Figure 11. Site 2 thickness projected over time.	29
Figure 12. Site 3 web thickness projected over time.	.29
Figure 13. Site 4 flange thickness projected over time.	.30
Figure 14. Site 5 web thickness projected over time.	.30
Figure 15. Site 5 flange thickness projected over time.	.31
Figure 16. Site 6 web thickness projected over time.	.31
Figure 17. Site 7 web thickness projected over time.	.32
Figure 18. Site 8 web thickness projected over time.	.32
Figure 19. Site 9 flange thickness projected over time.	.33
Figure 20. Site 10 flange thickness projected over time.	.33
Figure 21. Site 11 flange thickness projected over time.	.34
Figure 22. Site 12 web thickness projected over time.	.34
Figure 23. Site 1 thickness measurements	.38
Figure 24. Site 2 thickness measurements	.38
Figure 25. Site 3 thickness measurements	.39
Figure 26. Site 4 thickness measurements	.39
Figure 27. Site 5 thickness measurements	.40
Figure 28. Site 6 thickness measurements	.40
Figure 29. Site 7 thickness measurements	.41

Figure 30. Site 8 thickness measurements	41
Figure 31. Site 9 thickness measurements	42
Figure 32. Site 10 thickness measurements	42
Figure 33. Site 11 thickness measurements.	43
Figure 34. Site 12 thickness measurements	43
Figure 35: Corrosion process showing anodic and cathodic current	84
Figure 36. Coal storage at Site 4, the Mid-Continental Coke and Coal property	89
Figure 37. Polarization resistance testing device	89
Figure 38. Fury robot entering the water on the back flange of the sheet pile	91
Figure 39. Fury nearly submerged, taking measurements on the front flange of sheet pile.	91

Tables

Table 1. Corrosion rate analysis data	21
Table 2. Life-cycle projection table for the sheet pile.	27
Table 3. Estimated dates of construction by site.	28
Table 4. Site 1 thickness measurements	71
Table 5. Site 2 thickness measurements	72
Table 6. Site 3 thickness measurements	73
Table 7. Site 4 thickness measurements	74
Table 8. Site 5 thickness measurements	75
Table 9. Site 6 thickness measurements	76
Table 10. Site 7 thickness measurements	77
Table 11. Site 8 thickness measurements.	78
Table 12. Site 9 thickness measurements	79
Table 13. Site 10 thickness measurements	
Table 14. Site 11 thickness measurements	
Table 15. Site 12 thickness measurements	82

1 Introduction

Background

The Cuyahoga and Old Rivers in Cleveland, OH, are important industrial and recreational waterways that provide access through Lake Erie to the Great Lakes and the St. Lawrence River. Along both banks of the Cuyahoga and Old Rivers is steel sheet pile bulkheads that were first installed in the 1940s and 1950s. The failure of any portion of this sheet pile would have serious economic and environmental impact, and would also present a public safety hazard. The responsibility for this sheet pile rests with the landowners, but a recent federal law — *The Water Resources Development Act of 1996* (Public Law 104-303, Section 438, "Cuyahoga River, Ohio" [12 October 1996]) — mandates that the Army develop estimates for the cost of repairing and/or replacing all sheet pile bulkhead along these waterfronts in Cleveland. To develop such estimates, the Army must first determine the current condition of this sheet pile.

A Phase 1 study of the subject infrastructure (URS Greiner, Inc. 1998) was conducted using the systematic, engineering-based visual condition assessment approach detailed in CERL Technical Report REMR-OM-9/ADA231916 (Greimann, Lowell, and James Stecker, *Maintenance and Repair of Steel Pile Structures*, December 1990). Phase 2 of the study was a follow-on condition assessment, conducted by the U.S. Army Construction Engineering Research Laboratory (CERL) and is documented in this report. In the Phase 2 study, underwater thickness measurements were made using a remotely controlled submersible robotic system called *Fury* (Marsh, Siddique, and Hock 1997). Additionally, corrosion rate measurements were taken at selected sites to provide a basis for predicting bulkhead conditions at any given time during the sheet pile life-cycle. Inherent in this inspection and assessment capability are the following advantages:

- more accurate cost estimation for repair or replacement
- better quantitative basis for prioritizing maintenance and repair (M&R) projects
- improved life-cycle utilization of the infrastructure
- improved ability to prevent or mitigate potential economic, environmental, and public safety hazards that may arise from sheet pile failure.

Objectives

The objectives of this study were to (1) perform a quantitative underwater corrosion inspection and assessment of sheet pile at specific sites selected by the sponsor of the work and (2) use the measured material thicknesses and corrosion rates to predict a probable future range of sheet pile thickness.

Approach

Twelve sites along the Cuyahoga and Old Rivers were selected for study (Figure 1) and prioritized by engineering personnel from Army Engineer District Buffalo, NY, with input from the Executive Director of the Flats Oxbow Association of Cleveland, an organization representing area riverfront businesses and property owners. These sites were specified in order to focus the study on stretches of sheet pile that appeared to range in condition from medium-good to medium-poor, which are the most difficult to accurately assess by visual inspection alone.

The Fury robotic system was used in the field at Cleveland for one work week to take underwater ultrasonic thickness measurements. Then, a corrosion engineer certified by the National Association of Corrosion Engineers (NACE) was employed to take localized corrosion rate measurements. By applying the localized corrosion rate to the current thickness measurements, the future material thickness at any future point in the sheet pile life cycle could be projected. To help further refine the corrosion life prediction, other critical measurements were also taken. These included soil-side resistivity measurements (where applicable and where access was obtainable), and water pH, dissolved oxygen, total dissolved solids, hardness, chlorides, sulfides, and sulfates.

Mode of Technology Transfer

The results of this study will be combined with the Phase 1 study (URS Greiner, Inc. 1998) by Buffalo District to meet the requirements of PL 104-303, Section 438.

Operational experience with Fury gained by CERL during this field study will be incorporated into future refinements of the system, enhancing the robot and condition inspection methodologies to promote adoption of this dual-use technology for additional Corps-specific applications.

Units of Weight and Measure

U.S. standard units of measure are used throughout this report. A table of conversion factors for Standard International (SI) units is provided below.

SI conversion factors							
1 in.	=	2.54 cm					
1 ft	=	0.305 m					
1 yd	=	0.9144 m					
1 sq in.	=	6.452 cm²					
1 sq ft	=	0.093 m²					
1 sq yd	=	0.836 m²					
1 cu in.	=	16.39 cm³					
1 cu ft	=	0.028 m ³					
1 cu yd	=	0.764 m ³					
1 gal	=	3.78 L					
1 lb	=	0.453 kg					
1 kip	=	453 kg					
1 psi	=	6.89 kPa					
°F	=	(°C x 1.8) + 32					



Figure 1. Map of test site locations.

--

.

.

• • •

2 Degradation Mechanisms of Sheet Pile

In an aqueous environment, the corrosion of steel is the result of a naturally occurring electrochemical process (Figure 2). If metal is in contact with such electrolytes as water or moist soil, variations in potential difference are formed due to factors such as local variations in retained stress from manufacturing, alloying elements and phase distribution, coating efficiency, and dissolved oxygen distribution. The potential difference creates small local cells that act like batteries. At anodic areas, dissolution of the metal occurs, producing ferrous ions and electrons as follows:

 $Fe \rightarrow Fe^{++} + 2e^{-}$

On the other hand, at cathodic areas, electrons are consumed as shown below, depending on the electrolyte conditions:

$$2H^+ + 2e^- \rightarrow H_2$$
 and/or $\frac{1}{2}O_2 + H_2O + 2e^- \rightarrow 2(OH)^-$

While steel goes into solution at the anodes as ferrous ion, where there is sufficient oxygen available, this metal will be rapidly converted to insoluble hydrated ferric oxides that deposit on the surface as rust.

$$Fe^{++} + 2(OH)^- \rightarrow Fe(OH)_2$$

 2 Fe(OH)₂ + $\frac{1}{2}$ O₂ + H₂O \rightarrow 2Fe(OH)₃



Figure 2. General principle of corrosion.

In the Cuyahoga and Old Rivers, the regular passage of river traffic serves to provide a sufficient supply of dissolved oxygen to allow the oxidation process to continue more or less uniformly as general corrosion. On the soil side of the sheet pile, soil resistivity determines how easily corrosion currents flow in the soil. The corrosion current is directly proportional to the amount of metal lost. The lower the resistance (i.e., soil resistivity), the greater the rate of corrosion and metal loss.

An additional factor affecting the degradation of the sheet pile is the presence of zebra mussels. The infestation at the time of this work appeared to be well advanced in Lake Erie,^{*} but decreased the farther inland the designated site was located. Although the mechanism is not yet fully understood, recent experience with inland waterway infestation by zebra mussels indicates an accelerated corrosion rate compared to the corrosion rate without zebra mussels (Claudi and Mackie 1994; Race and Kelly 1996).

As observed at the Corps of Engineers' Cleveland Area Office.

3 Sheet Pile Thickness Measurements

From 24 - 28 August 1998, the inspection team^{*} conducted sheet pile thickness measurements. Twelve sites, detailed in Appendix A, were chosen by the Buffalo District as indicative of the condition of sheet pile along the Cuyahoga and Old Rivers. Thickness measurements were taken by three methods.

The Fury robot was the primary means of data acquisition. Originally designed for thickness measurements in underground storage tanks, adaptation of Fury for this application was novel and cost effective. Figure 3 shows the robot, which consists of permanent magnetic wheels, bump sensors, steering head, and cleaning head with ultrasonic transducers. Not shown, in addition, are a TestPro Infometric Data Processor for the thickness measurement transducer and a control console.

Hand-held acoustic sensors were the primary backup method for thickness measurements. A Panametrics 5 MHz ultrasonic transducer with an Epoch III Model 2300 Data Processor were used to make the measurements. The transducer is attached to a pole and the pole is used to hold the sensor against the sheet pile while measuring. Figure 4 shows the method of use for the hand held sensor.

An additional backup device nicknamed "McGyver" was used to take acoustic measurements. Difficulties maintaining adequate pressure at increasing depths with the hand-held device led to the use of the McGyver, which is a wooden platform with a spring-loaded transducer holder that attaches to the steel sheet pile using permanent magnets. The Panametrics transducer system was used with the McGyver platform. Figure 5 illustrates the implementation of McGyver for sheet pile measurements.

The acquired data from the 12 surveyed sites were entered into a spreadsheet and plotted. The results from each site are plotted on a graph. The location of

^{*} Consisting of personnel from CERL (Dr. Charles Marsh, Mr. Robert Weber, Dr. Aaron Averbuch, Mr. Brian Temple) and Buffalo District (Mr. Dennis Rimer).

each site is given in Appendix A, the data tables are in Appendix B, and the plots are provided under "Figures" immediately following the body text.

Before every ultrasonic thickness measurement considerable surface preparation and scraping was necessary. Before the hand-held and McGyver measurements, and supplemental to the Fury surface preparation/scraping system, a hand-held scraper was used. This scraper was a 6 in. square of 0.25 in. thick steel plate with a sharpened edge welded to 0.5 in. threaded pipe at an angle of approximately 20 degrees. Vigorous scraping to depth was accomplished by adding sections of pipe as needed. The corrosion scale proved to be relatively thick and very adherent.



Figure 3. The Fury robot.



Figure 4. Use of the hand-held acoustic sensor.



Figure 5. McGyver measuring device.

4 Corrosion Rate Measurements

From the 24 - 28 August 1998, a NACE-certified corrosion engineer was employed to take localized corrosion measurements at the 12 sites where sheet pile thickness was measured. Corrosion rates were measured using the equipment shown in Figure 6, used in conjunction with data analysis software^{*}.

The polarization resistance technique was used to rapidly estimate of the corrosion rate of metal in a solution. In this technique, cell current readings are taken during a very short, slow sweep of the potential. The sweep used in this study was from -20 to +20 mV relative to open circuit potential of the test surface, commonly called " $E_{Open Circuit}$ " (E_{cc}). Over this range, the current vs voltage curve is generally linear. A linear fit of the data to a standard model yields an estimate of the polarization resistance (R_p) that is then used to calculate the corrosion current (I_{corr}). Using the corrosion current, the corresponding mass loss or corrosion rate of the sheet pile at the test site is then determined (Appendix C).



Figure 6. Onsite probe for corrosion rate measurement.

Gamry CMS 100 Electrochemical Corrosion Testing software and hardware installed on a Gateway P5/133 computer operating under Windows 95.

There are numerous advantages to using the polarization resistance technique. Polarization resistance experiments run very quickly. The scan in a polarization resistance experiment does not appreciably polarize the sample. This minimizes changes in the surface of the sample caused by the test itself, which is especially important for long-term monitoring. Furthermore, this technique facilitates rerunning the scans when data acquisition during a particular test was disturbed by external sources. There are a couple of disadvantages to using the polarization resistance technique. The corrosion rate calculation requires the tester to provide kinetic parameters (Beta slopes) that must be estimated or obtained from another type of experiment. In this test, the Beta slope value used for both the anodic and cathodic slopes was 120 mV/Decade. This value is the one most commonly used in aqueous electrolytes and is well accepted as a very close approximation of the actual slope(s) in the Cuyahoga River water environment. Under laboratory conditions, the result of a polarization resistance calculation may be somewhat less accurate than the corrosion rate calculated from Tafel data. Unfortunately, Tafel tests require considerably longer time to run (typically more than 1 hour), and any change in condition during this test will distort or even completely invalidate the results. During this study, a number of Tafel scans were attempted but each time external noise from passing ships, spurious electrical signals, etc., significantly distorted the data and no analysis could be made of the data obtained during any of these scans. Analysis of the curve can yield the corrosion potential, corrosion current, and corrosion penetration rate.

ASTM Standard G-59, *Practice for Conducting Potentiodynamic Polarization Re*sistance Measurements, contains additional useful information about polarization resistance measurements. Details of the measurement procedure and the polarization resistance plots are given in Appendix C.

A total of 31 polarization resistance (PR) and 5 Tafel scans were performed on submerged portions of the steel sheet pile along the Cuyahoga River. These scans were conducted at 10 different sites that corresponded to locations where ultrasonic thickness measurements were obtained.

As noted, none of the Tafel scans provided accurate, useful data. However, 23 of the 31 polarization resistance scans were completed successfully and provided meaningful results for the current *in-situ* corrosion rates occurring on the sheet pile water-side surfaces. A summary of the corrosion rate data is given in Table 1.

Site	Ecorr	r Icorr Rp Corrosion Rat		Corrosion Rate	Corrosion Rate
	(-mV)	(Amps/cm2)	(Ohms/cm2)	(mils/Year)	(inches/Year)
1	365.3	1.48E-06	1.76E+04	1.844	0.001844
2	637.6	2.58E-06	1.01E+04	3.215	0.003215
2	605.4	9.67E-11	2.70E+08	0	0
2	640.4	1.04E-05	2.50E+03	12.98	0.01298
Near 2	410.4	3.91E-03	6.66E+00	27.067	0.027067
Near 2	509	4.18E-05	6.24E+02	51.982	0.051982
Near 2	601.8	1.29E-05	2.02E+03	16.052	0.016052
3	404.7	3.42E-05	7.62E+02	1.082	0.001082
3	426.2	5.24E-06	4.97E+03	6.522	0.006522
3	601.8	2.79E-05	9.34E+02	34.75	0.03475
4	384.6	8.63E-06	3.02E+03	10.744	0.010744
4	573.7	1.53E-05	1.71E+03	18.977	0.018977
4	584.7	4.07E-06	6.40E+03	5.071	0.005071
5	353.5	3.21E-06	8.13E+03	3.992	0.003992
6	621.6	2.44E-06	1.07E+04	3.043	0.003043
6	508	6.52E-06	4.00E+03	8.113	0.008113
7	541	1.74E-06	1.50E+04	0.055	0.000055
7	550.6	8.77E-06	2.97E+03	10.92	0.01092
8	432.2	8.81E-06	2.96E+03	10.963	0.010963
11	553.4	3.85E-06	6.77E+03	4.795	0.004795
12	676.9	6.49E-06	4.01E+03	8.086	0.008086
12	589.9	1.40E-06	1.87E+04	1.739	0.001739
12	588	1.35E-06	1.94E+04	1.675	0.001675
Minimum	353.5	9.67E-11	6.66E+00	0	0
Maximum	676.9	3.91E-03	2.70E+08	51.98	0.05198
Average	527.64	3.21E-04	2.16E+07	11.83	0.01183
Std. Dev.	98.47	8.14E-04	5.62E+07	12.56	0.01256

Table 1. Corrosion rate analysis data.

In addition, resistivities were measured for both water and soil. The water resistivity was found to be 1010 ohm-cm. The soil resistivity was measured using the Werner 4-pin method with intermediate values inferred using the Barnes layering technique. Appendix D contains full details of measured values. At both the 5 ft and 10 ft depth, a value of 5050 ohm-cm was found. This is considered only moderately corrosive, especially when compared to the water side. Additional water chemistry data from the Ohio Environmental Protection Agency are included in Appendix D.



5 Video Inspection of Sheet Pile

While thickness and corrosion rate measurements were being performed, a videotape of the condition of the sheet pile below the water surface was recorded at 1 ft intervals. Although the Cuyahoga's lack of water clarity made filming difficult, a field-adapted device fitted to the front of the camera allowed for some marginally useful video footage to be taken. Both visible-color and infrared cameras were used. Figures 7, 8, and 9 show screen images of the captured video. Aside from indicating the degree of zebra mussel infestation, video or still images have considerably less utility for inspection and assessment compared to thickness and corrosion rate measurements.



Figure 7. Waterline video capture of sheet pile at Site 1.



Figure 8. Video capture of Site 1 at 10 ft below waterline.



Figure 9. Video capture of Site 1 at 25 ft below waterline.

6 Discussion

The data acquired from the 12 surveyed sites were entered into a spreadsheet and plotted. The results from each site are plotted on a graph, with the data tables and plots included as attachments to this document.

Different thickness values measured at a specific depth do not necessarily represent error or anomaly. It is more likely that the measurements were taken at different horizontal locations at the same depth, and in fact represent actual different wall thicknesses.

Although this work was the first time Fury was adapted for *in-situ* corrosion assessment of sheet pile, the cost was still comparable to a four-person dive crew. With the experience gained in dealing with tough, adherent scale and very cloudy water, and with further technical adaptations of the Fury system for this application, it seems certain that the cost of robotic inspection and assessment can be driven significantly lower.

Zebra mussels are present in Lake Erie, but they were not found in great numbers at any site surveyed except for Site 12. Since Site 12 is closest to Lake Erie, a reasonable conjecture is that the encroachment of zebra mussels will proceed inland, assuming adequate initial environmental conditions for growth and reproduction. Although the rate of this migration is unknown, it is likely to adversely affect the corrosion rate of installed sheet pile. Experience at Black Rock Lock in Buffalo, NY, suggests that zebra mussels increase the corrosion rate by a factor of 5 compared to the rate in noninfested water. On the plus side, as filter feeders, the Zebra mussels are likely to have a positive effect on the clarity of Cuyahoga River water. It seems prudent therefore, to verify both the encroachment patterns and accelerated corrosion rates before considering available options for control.

It can reasonably be assumed that the water-side corrosion will typically dominate over soil-side corrosion with respect to the sheet pile deterioration.

Based on the data from all 23 polarization resistance scans, the average corrosion rate measured was slightly less than 12 mils per year with a standard deviation of 12.5 mils per year. Given the 500 mil thickness of the sheet pile typically used along the river, time to perforation of the pile due to water-side corrosion would typically occur approximately 40 years after installation.

However, the variation in the rates measured suggests that locations with more aggressive environments could experience failure much sooner. Given the relatively few measurements and the inherent and unavoidable uncertainties associated with the polarization resistance technique, no single measured value alone should be considered as an accurate value. Instead, taken together, a corrosion rate of 11.8 mils per year should be considered as representative river-wide.

On a structures and/or planning basis, the time to perforation may not be of greatest concern. Table 2 summarizes the results of projecting the time needed to reach 50, 30, and 10 percent of the original thickness for the 12 sites. A consistent and ongoing rate of 11.8 mils per year is assumed for all sites. An average of the current measured thicknesses is used as a starting value for each site. The maximum and minimum values are the result of starting with a thickness of plus or minus one standard deviation. Figures 10 - 22 follow the same approach, but instead represent a continuous presentation of the corrosion process. Table 3 gives estimated dates of sheet pile construction for each measurement site.

Sito	Type of Sheet	Ave. Thick	STD	50% Max	50% Min	50%	30% Max	30% Min	30% ∆ve	10% Max	10% Min	10% Ave
One	pile	(in)	(in)	(yrs)	(yrs)	(yrs)	(yrs)	(yrs)	(yrs)	(yrs)	(yrs)	(yrs)
1	Cold	0.3533	0.1	20.33	0.33	10.33	30.33	10.3	20.3	40.33	20.3	30.3
2	Cold	0.379	0.04	16.9	8.9	12.9	26.9	18.9	22.9	36.9	28.9	32.9
3-Web	Hot	0.28	0.094	18.65	0	9.25	26.15	7.35	16.8	33.65	14.9	24.3
4-Flange	Hot	0.32	0.092	16.2	0	7	26.2	7.8	17	36.2	17.8	27
5-Web	Hot	0.233	0.119	16.45	0	4.55	23.95	0.15	12.1	31.45	7.65	19.6
5-Flange	Hot	0.39	0.007	14.7	13.3	14	24.7	23.3	24	34.7	33.3	34
6-Web	Hot	0.251	0.054	11.75	0.95	6.35	19.25	8.45	13.9	26.75	16	21.4
7-Web	Hot	0.306	0.043	16.15	7.55	11.85	23.65	15.1	19.4	31.15	22.6	26.9
8-Web	Hot	0.306	0.048	16.65	7.05	11.85	24.15	14.6	19.4	31.65	22.1	26.9
9-Flange	Hot	0.301	0.118	16.9	0	5.1	26.9	3.3	15.1	36.9	13.3	25.1
10-Flange	Hot	0.32	0.075	14.5	0	7	24.5	9.5	17	34.5	19.5	27
11-Flange	Hot	0.234	0.109	9.3	0	0	19.3	0	8.4	29.3	7.5	18.4

Table 2. Life-cycle projection table for the sheet pile.

1940s	1950s	1960s	1970s	1980s	1990s			
Sites 2, 4, 9 Site 10 –1942 Sites 12,8 –1945 Site 5 –1948 Site 11 -1949	Site 7	Site 6	None	None	Sites 1,3-1990			
Note: Due to the lack of information, years for Sites 2, 4, 6, 7, and 9 have been estimated based on known ages of nearby bulkheads on the same property. [*] Site 2 appeared to be much more recent than 1940s.								

Table 3. Estimated dates of construction by site.

It must be remembered that while the land-side corrosion rates will usually be substantially lower than for water-side corrosion, site-specific factors may reverse this. For example, Site 4 has major subsidence behind the pile. Coal coke had been stored in the immediate area. This coal coke has extremely low resistivity and is probably acidic. The leaching of this material into the soil side backfill immediately behind the pile will substantially increase the land-side corrosion rate causing much earlier failure than at other sites.





^{*} Personal communication from Frank T. Lewandowski, 22 January 1999.



Figure 11. Site 2 thickness projected over time.



Figure 12. Site 3 web thickness projected over time.



Figure 13. Site 4 flange thickness projected over time.



Figure 14. Site 5 web thickness projected over time.



Figure 15. Site 5 flange thickness projected over time. Note: There were too few reliable measurements to determine a valid max/min range in this case.



Figure 16. Site 6 web thickness projected over time.











Figure 19. Site 9 flange thickness projected over time.






Figure 21. Site 11 flange thickness projected over time.





7 Summary and Recommendations

Summary

Thickness and corrosion rate measurements were made to obtain quantitative data pertaining to the current underwater condition of the sheet pile at 12 specified sites along the Cuyahoga and Old Rivers. Thickness measurements were made both by the Fury remotely controlled robotic inspection system and by manual acoustic sensing technology. Based on limited data samples collected in this study, a bounded, steady-state projection of future sheet pile condition was made for each site.

During this study zebra mussels were found along the river, with the largest populations located near the mouth of the river and Lake Erie. Because previous studies have indicated that there may be a positive linkage between corrosion rates and degree of zebra mussel infestation, the rate of corrosion measured in this study may accelerate if zebra mussel colonies move up river as anticipated. In such a case, the projected sheet pile thicknesses reported here would be too large, and any given percentage of original material thickness would be reached sooner than projected here.

Recommendations

Based on the results of this study, the following recommendations are offered:

- A structural analysis on reduced section modulus should be conducted to determine the overall average reduced thickness at which failure may reasonably be expected.
- Based on the projected time to failure, property owners should be notified in advance, and replacement should be scheduled before the bulkhead fails.
- Additional measurements should be made at the 12 sites in order to improve the statistical reliability of the current findings.
- The encroachment rate of zebra mussels into the Cuyahoga should be verified.
- Verify the linkage between zebra mussel infestation and accelerated corrosion rates before implementing control methods.

References

ASTM Standard G-59, Practice for Conducting Potentiodynamic Polarization Resistance Measurements.

Barnes, H.E., Electrical Survey Detects Underground Rock, Pipeline Industry, April 1959.

- Chaker, Victor, "Simplified Method for the Electrical Soil Resistivity Measurement", Underground Corrosion Symposium, sponsored by ASTM Committee G-1, Williamsburg, VA, 26-27 November 1979. ASTM Publication Code Number 04-741000-27, Philadelphia, PA, 1981.
- Claudi, Renata and Gerald L. Mackie; Practical Manual for Zebra Mussel Monitoring and Control (CRC Press Inc., Boca Raton FL, 1994).
- Evans, Ulrick R., The Corrosion and Oxidation of Metals: Scientific Principles and Practical Applications. Edward Arnold Publishers Ltd, London, 1960.
- Greimann, Lowell, and James Strecker, *Maintenance and Repair of Steel Pile Structures*, CERL Technical Report (TR) REMR-OM-9 (U.S. Army Construction Engineering Research Laboratory, December 1990, ADA 231916).
- Marsh, Charles P., Amer Siddique, and Vincent F. Hock, "Fury: A Remote Underground Storage Tank Inspection/Assessment System," Proceedings of the 2d Tri-Service Environmental Technology Workshop, 10 – 12 June 1997, St. Louis, MO (U.S. Army Environmental Center).
- Public Law 104-303, The Water Resources Development Act of 1996, Section 438, "Cuyahoga River, Ohio" (12 October 1996).
- Race, Timothy D. and Mark A. Kelly, "Controlling Zebra Mussels with Coatings," Journal of Protective Coatings and Linings, Vol. 13, No. 12, Dec. 1996; pp60-72.
- URS Greiner, Inc., Phase 1 Report: Cuyahoga River Bulkhead Study, Cleveland, Ohio, Contract DACW49-96-D-005, Work Order #6 (Army Engineer District Buffalo, January 1998).
- Wenner, Frank, "A Method of Measuring Earth Resistivity," NBS Bulletin No. 12 (469), National Bureau of Standards.

Figures

The plots use the following lines to represent the original thickness of the sheet pile and the standard deviation limits of the measurements:

Original Thickness for the Flange or Web Measurements

Average Thickness for the Flange or Web Measurements

Standard Deviation Limits for Cold Rolled sheet Pile and the Flange Measurements for Hot Rolled Sheet Pile

Standard Deviation Limits for Hot Rolled Sheet Pile Web Measurements

Original and average thickness lines for hot rolled sheet pile are labeled as either flange or web measurements. For cold rolled sheet pile, the original web and flange thicknesses are equivalent.

CERL TR 99/37







Figure 24. Site 2 thickness measurements.



Figure 25. Site 3 thickness measurements.







Figure 27. Site 5 thickness measurements.







Figure 29. Site 7 thickness measurements.







Figure 31. Site 9 thickness measurements.







Figure 33. Site 11 thickness measurements.





Appendix A: Sites Referenced in Sheet Pile Thickness and Corrosion Rate Measurements

Note: Acoustic measurements were made by either the Panametric transducer or the transducer on the Fury robot.



Site 1 Location: Parks1/Parks 3, City of Cleveland Parks and Recreation, next to Frank Morrison and Son; just north of marker 540 on east shore.

Type of sheet pile: cold-rolled.



Measurements: Taken on the northeastern side approximately 40 ft upriver from water fountain. Measurements were taken on the flange and the web of the sheet pile.



Site 2 Location: Glazer 4/City of Cleveland 32 or City of Cleveland 31, approximately 400 ft south of Site 1 between markers 540 and 548 on east shore.

Type of sheet pile: cold-rolled.



Measurements: Taken from the first full sheet pile section down from the platform on the bulkhead. All measurements were taken on the flange of the sheet pile.



Site 3 Location: Cereal 1 / Cereal 2 or Cereal Food Processors 3, just north of marker 559 on the east shore.

Type of sheet pile: hot-rolled in front.



Measurements: Taken below the yellow triangle next to the 624A marker on the sheet pile, near the northwest corner of the grain loading tower. All measurements were taken on the flange of the hot-rolled sheet pile.

,



Site 4 Location: Mid-Continental Coal/Coke 2, halfway between markers 640 and 650 on the east shore.

Type of sheet pile: hot-rolled.



Measurements: Measurements taken close to the 650 sheet pile marker. Measurements were taken on the flange of the sheet pile by Fury and Panametrics. Panametrics measurements were also taken on the web.

•

. .

.



Site 5 Location: Erie RR 10/Sta Realty 2, on outcropping between markers 660 and 670, closer to 670 on west shore.

Type of sheet pile: hot-rolled.



Measurements: Two measurements were taken on the web by Panametrics. All other measurements were taken on the flange by Fury and Panametrics.



Site 6 Location: River Terminal 6, just north of marker 760 on southwest shore.

Type of sheet pile: hot-rolled.



Measurements: Measurements were taken on the back flange of the sheet pile by Fury. Panametrics measurements were taken on the web.



Site 7 Location: Carter 1, between Samsel Realty and Carter Peninsula; just south of marker 610 on the east shore.

Type of sheet pile: hot-rolled.



Measurements: Taken near station 610+00. Two measurements were taken on the flange of the sheet pile by Panametrics. All other measurements were taken by Fury and Panametrics on the web.



Site 8 Location: B&O RR 1/ Tower City 1, between Tower City and F.C. Southridge Corp.; between markers 620 and 630 on the north shore.

Type of sheet pile: hot-rolled.



Measurements: Measurements were taken on the flange of the sheet pile by Fury and Panametrics. Panametrics measurements were also taken on the web.



Site 9 Location: B&O RR 1/Mid-Continental 5, between markers 630 and 640, on east shore.

Type of sheet pile: hot-rolled.



Measurements: All measurements were taken on the flange by Panametrics.



Site 10 Location: Republic Steel 7/ LTV Steel 31, between 800 and 810 on the east shore.

Type of sheet pile: hot-rolled.



Measurements: Close to station 800+50, at front of Sun Oil terminal. All measurements were taken on the flange of the sheet pile by Fury and Panametrics.

.



Site 11 Location: B&O Railroad 7 / B&O Railroad 5, slightly east of marker 700 on the north shore.

Type of sheet pile: hot-rolled.



Measurements: All measurements were taken on the flange of the sheet pile by Fury and Panametrics.



·



Site 12 Location: Erie RR 6 / Ontario Stone 4, between markers 320 and 310 on the south shore.

Type of sheet pile: hot-rolled.



Measurements: Site near the end of the building. Measurements were taken on the web by Fury and Panametrics. One Panametrics measurement was taken on the flange. . . .

. . .

. . .

·

. .

· · ·
Appendix B: Sheet Pile Thickness Measurements

Site 1 measurements were taken on 24 - 26 August 1998. The water surface was approximately 72 inches from the top of the concrete deck surface. The sheet pile at this site was cold-rolled.

		e medearem					
Fury		Hand Held		Hand Held		Hand Held	
				Front Face		Short cable	e / side
Height	Thickness	Height	Thickness	Height	Thickness	Height	Thickness
(ft) -	(in)	(ft)	(in)	(ft)	(in)	(ft)	(in)
-1 1/2	0.438	1	0.25	3	0.5	0	0.42
-2 5/12	0.25	0	0.2	0	0.495	-1	0.48
-2 5/6	0.41	0	0.225	- 1/3	0.495	-1 1/2	0.44
-3 1/2	0.45	- 1/3	0.22	-2 1/2	0.48	-2 1/2	0.375
-3 1/2	0.462	- 2/3	0.302	-3	0.45		
-4	0.483	-1	0.28				
-4	0.48	-1	0.295				
-4 1/2	0.45	-1 1/3	0.32				
-5	0.435	-1 2/3	0.32				
-6	0.4	-2	0.25				:
-6	0.4	-2	0.25				
		-3	0.26				
		-3	0.285				
		-4	0.305			-	
		-5	0.275	Sum T (in)	2.42	Sum T (in)	1.715
		-7 1/2	0.267	Number P	5	Number P	4
				Average T		Average	
		-7 1/2	0.215	(in)	0.484	T (in)	0.42875
		-10	0.225				
		-12	0.335			Site 1 Tota	
		-13	0.26			Sum T (in)	14.132
Sum T (in)	4.658	Sum T (in)	5.339			Number P	40
						Average	
Number P	11	Number P	20			T (in)	0.3533
Average T		Average T					
(in)	0.423455	(in)	0.26695			STD =	0.0997862

Table 4. Site 1 thickness measurements

Sum T stands for the sum of all thickness measurements. Number P is the number of thickness measurements, and Average T is the average thickness.

Site 2 measurements were taken on the 25 and 28 August 1998. The water surface was approximately 137 in. from the top of the piles during the first set of measurements and 133 in. from the top of the piles during the second set. All height measurements have been normalized to the first day's height data. The sheet pile at this site was cold-rolled.

Table 5. Si	te 2 thickne	ess measur	rements.	· · · · · · · · · · · · · · · · · · ·			
Hand Held		Hand Held	2nd	Fury		Fury 2nd	
		Short Cable	9			,	
Height	Thickness	Height		Height	Thickness	; Heigh t	Thickness
(ft)	(in)	(ft)	Thickness (in)	(ft)	(in)	(ft)	(in)
4	0.375	1 2/3	0.375	4	0.323	- 1/3	0.362
0	0.37	- 1/3	0.4	0	0.341	- 1/2	0.321
- 1/3	0.377	- 2/3	0.41	-1	0.294	- 5/6	0.33
- 2/3	0.382	-1	0.395	-1 1/2	0.339	-1	0.41
-1	0.425	-1 1/3	0.415	-3	0.359	-1 1/6	0.334
-1	0.425	-1 2/3	0.4			-1 1/3	0.38
-1 1/3	0.397	-2	0.375			-1 1/2	0.375
-1 2/3	0.427	-2 1/3	0.41			-1 2/3	0.362
-2	0.455	-2 2/3	0.365			-1 5/6	0.369
-2 1/2	0.492	-3 1/3	0.42			-2	0.352
-3	0.465	-3 5/6	0.43			-2 1/6	0.362
-4	0.366					-2 1/3	0.365
-5	0.342					-25/6	0.36
-5	0.33					-3 1/3	0.395
-6	0.407					-35/6	0.342
-7	0.38					-4 1/3	0.38
-8	0.34					-45/6	0.4
-9	0.345					-5 1/3	0.374
-10	0.405					-55/6	0.388
-11	0.342					-6 1/3	0.4
						-65/6	0.389
						-8 1/3	0.43
						-85/6	0.44
						-91/3	0.28
		i.				-95/6	0.32
• • • • • • • • •	7047	••••••••••••••••••••••••••••••••••••••	4 005	0	1 050	Cum T (in)	0.22
	/.84/	Sum I (III)	4.390	Sumbor D	1.000	Sulli i (iii) Neimbor D	J.22 95
	20		11		5		20
Average I	0.00005	Average I	0 000545455	Average 1	0.0010	Average :	0.2600
(IN)	0.39235	(IN) ·	0.399545455	(11)	0.3312	(11)	0.3000
Number P	61	Sum T(in)	23.118	Ave T(in)	0.378984	STD=	0.04049

Site 3 measurements were taken on 25 August 1998. The water surface was approximately 49 in. from the top of the sheet pile, with measurements taken below the $\Delta 624A$ marker. There was severe pitting at this site. The sheet pile at this site was hot-rolled.

Table 6.	Site 3	thickness	measurements.
Table V.	JIE J	1110411033	incasurements.

Hand Held		Fury	
Height	Thickness	Height	Thickness
(ft)	(in)	(ft)	(in)
3	0.352	- 1/2	0.322
0	0.365	-1	0.21
		-3	0.152
Sum T (in)	0.717	Sum T (in)	0.684
Number P	2	Number P	3
Average T		Average T	
(in)	0.3585	(in)	0.228
		Site 3 Tota	
		Sum T (in)	1.401
		Number P	5
		Average T	
		(in)	0.2802
		STD Web	0.09415

Sum T stands for the sum of all thickness measurements. Number P is the number of thickness measurements, and Average T is the average thickness.

Site 4 measurements were taken on 25 and 27 August 1998. The water surface was approximately 66 in. from the top of the sheet pile. The sheet pile at this site was cold-rolled.

Hand Held		Fury		
Height	Thickness	Height	Thickness	
(ft)	(in)	(ft)	(in)	
3	0.5	-1 1/6	0.4	
3	0.345	-1 3/7	0.38	
0	0.255	-1 1/2	0.398	
- 1/3	0.415	-2	0.31	
- 1/2	0.41	-2	0.15	ĺ
- 2/3	0.225	-2	0.31	
- 5/6	0.412	-2 1/4	0.15	ĺ
-1	0.45	-2 1/4	0.25	
-1	0.245	-2 3/7	0.1	
-1 1/3	0.405	-2 3/7	0.38	
-1 2/3	0.315	-2 5/6	0.3	
-1 2/3	0.44	-3	0.32	
-2	0.445	-3	0.315	
-2	0.33	-3 1/2	0.24	
-2 1/2	0.345	-4 1/2	0.17	
-2 1/2	0.377	-4 1/2	0.318	
-3	0.335	-5 1/6	0.23	
		-5 5/12	0.32	
		-5 1/2	0.38	
		-7	0.26	
		-7 2/3	0.25	
Sum T (in)	6.249	Sum T (in)	5.931	
Number P	17	Number P	21	
Average T		Average T		
(in)	0.367588	(in)	0.282429	
		Site 4 Tota		
		Sum T (in)	12.18	
		Number P	38	
		Average T		
		(in)	0.320526	
		STD =	0.092468	

Table 7. Site 4 thickness measurements.

Sum T stands for the sum of all thickness measurements. Number P is the number of thickness measurements, and Average T is the average thickness.

Site 5 measurements were taken on 25 and 28 August 1998. The data from the 25th consisted of only one data point due to the scale. The water surface was approximately 66 in. from the top of the sheet pile. In addition there was heavy backside scale at this site. The sheet pile at this site was hot-rolled.

Table 8. Site 5 thickness measurements.							
Hand		Fury		Hand			
				Front Face			
Height	Thickness	Height	Thickness	Height	Thickness		
(ft)	(in)	(ft)	(in)	(ft)	(in)		
2	0.526	- 1/6	0.485	3	0.397		
0	0.521	- 5/6	0.126	2	0.387		
- 1/3	0.228	-1	0.107				
- 2/3	0.273	-1 1/6	0.132				
-1	0.293	-1 1/3	0.162				
-1 1/3	0.223	-1 1/2	0.17				
-1 2/3	0.218	-1 2/3	0.15				
-2	0.228	-1 5/6	0.123				
-2 1/2	0.307	-2	0.192				
-3	0.223	-2 1/2	0.426				
-3 1/2	0.208	-3	0.161				
-4	0.307	-3 1/2	0.121				
		-4	0.119				
		-4 1/2	0.164	ν.			
		-5	0.189				
		-5 1/2	0.133				
		-6	0.193				
		-6 1/2	0.34	_			
		-7	0.178	-			
		-7 1/2	0.38		•		
		-8	0.115				
Sum T (in)	3.555	Sum T (in)	4.166	Sum T (in)	0.784		
Number P	12	Number P	21	Number P	2		
Average T		Average T		Average T			
(in)	0.29625	(in)	0.198381	(in)	0.392		
Site 5 Tot	Web			Site 5 Tot	Flance		
Sile 5 Tol	7 701			Sum T (in)	0 784		
Number P	22			Number P	2		
	00			Averane T	2		
(in)	0 22307			(in)	0 392		
	0.20007				0.007071		
	0.11030			יוסיטן	0.00/0/1		

Sum T stands for the sum of all thickness measurements. Number P is the number of thickness measurements, and Average T is the average thickness.

Site 6 measurements were taken on 25 August 1998. The water surface was approximately 84 in. from the top of the sheet pile. The sheet pile at this site was hot-rolled.

Table 9. Site 6 thickness measurements.							
Hand		Hand		Fury			
Short Cable	e Side	Long Cable)				
Height	Thickness	Height	Thickness	Height	Thickness		
(ft)	(in)	(ft)	(in)	(ft)	(in)		
- 1/3	0.205	0	0.21	0	0.22		
- 2/3	0.215	- 1/2	0.225	- 1/2	0.225		
-1	0.205	- 4/7	0.25	- 3/5	0.25		
-1 1/3	0.21	-2 1/2	0.19	-2 1/6	0.21		
-1 2/3	0.215	-3	0.305	-2 1/2	0.3		
-1 1/3	0.335			-3	0.21		
-2	0.22			-3	0.34		
-2	0.284						
-6	0.357						
-7	0.34						
Sum T (in)	2.586	Sum T (in)	1.18	Sum T (in)	1.755		
Number P	10	Number P	5	Number P	7		
Average I	0.0500	Average I	0.000	Average I	0.050744		
(in)	0.2586	(in)	0.236	(in)	0.250714		
	[Site 6 Tot	Web				
		Sum T (in)	5.521				
		Number P	22				
		Average T					
		(in)	0.250955				
		STD Web	0.053933		•		

Sum T stands for the sum of all thickness measurements. Number P is the number of thickness measurements, and Average T is the average thickness.

Site 7 measurements were taken on 26 August 1998. The water surface was approximately 61 in. from the top of the sheet pile. The sheet pile at this site was hot-rolled.

Table 10. Si	te 7 thickne	ss measurer	nents.			
Hand		Fury		Hand		
				Front Face		
Height	Thickness	Height	Thickness	Height	Thickness	
(ft)	(in)	(ft)	(in)	(ft)	(in)	
5	0.335	- 1/6	0.335	5	0.465	
0	0.29	- 1/3	0.35			
0	0.27	- 1/2	0.3			
- 1/3	0.325	-2	0.325			
- 2/3	0.355	-2 1/2	0.285			
-1	0.35	-3	0.2			
-2	0.315	-4 1/2	0.25			
-2 1/2	0.275					
-3	0.34					
Sum T (in)	2.855	Sum T (in)	2.045	Sum T (in)	0.465	
Number P	9	Number P	7	Number P	1	
Average T	•	Average T		Average T		
(in)	0.317222	(in)	0.292143	(in)	0.465	
		Site 7 Tot	Web]		
		Sum T (in)	4.9			
		Number P	16			
-		Average T				
		(in)	0.30625			
		STD Web	0.042642			

Sum T stands for the sum of all thickness measurements. Number P is the number of thickness measurements, and Average T is the average thickness.

Site 8 measurements were taken on 25 August 1998. The water surface was approximately 65 in. from the top of the sheet pile. The sheet pile at this site was hot-rolled.

Table 11. Sit	Table 11. Site 8 thickness measurements.							
McGyver		Hand		Fury				
Side								
Height	Thickness	Height	Thickness	Height	Thickness			
(ft)	(in)	(ft)	(in)	(ft)	(in)			
0	0.377	- 2/3	0.297	0	0.348			
0	0.377			- 1/6	0.332			
-2	0.295			- 1/2	0.235			
-2	0.302			-1	0.24			
-2 1/2	0.282							
-3	0.282							
Sum T (in)	1.915	Sum T (in)	0.297	Sum T (in)	1.155			
Number P	6	Number P	1	Number P	4			
Average T		Average T		Average T				
(in)	0.319167	(in)	0.297	(in)	0.28875			
				Site 8 Tota				
				Sum T (in)	3.367			
				Number P	11			
				Average T				
				(in)	0.306091			
				STD Web	0.048259			

Sum T stands for the sum of all thickness measurements. Number P is the number of thickness measurements, and Average T is the average thickness.

Site 9 measurements were taken on 26 August 1998. The water surface was approximately 63 in. from the top of the sheet pile. The sheet pile at this site was hot-rolled.

Table	12.	Site	9	thickness	measurements.
-------	-----	------	---	-----------	---------------

McGyver w	/press	Fury	
Height	Thickness	Height	Thickness
(ft)	(in)	(ft)	(in)
3	0.395	3	0.39
-1 1/3	0.412	- 2/3	0.154
-3	0.312	- 5/6	0.09
-4 2/3	0.307	-1	0.095
-5 1/3	0.335	-1 1/2	0.369
		-2	0.45
		-2 1/2	0.4
		-3	0.222
		-3 1/2	0.276
Sum T (in)	1.761	Sum T (in)	2.446
Number P	5	Number P	9
Average T		Average T	
(in)	0.3522	(in)	0.271778
		Site 9 Tot	Flange
		Sum T (in)	4.207
		Number P	, 14
		Average T	
		(in)	0.3005
		STD FI	0.118466

Sum T stands for the sum of all thickness measurements. Number P is the number of thickness measurements, and Average T is the average thickness.

Site 10 measurements were taken on 26 August 1998. The water surface was approximately 98 in. from the top of the sheet pile. The surface was uneven and there were the beginnings of pitting corrosion. The sheet pile at this site was hot-rolled.

Hand Held		
Height	Thickness	
(ft)	(in)	
4	0.46	
0	0.345	
0	0.307	
- 1/3	0.267	
-1	0.28	
-2	0.262	
Sum T (in)	1.921	
Number P	6	
Average T		
(in)	0.320167	
Site 10 Tot	Flange	
Sum T (in)	1.921	•
Number P	6	
Average T		
(in)	0.320167	
STD FI	0.075056	

Table	13. Site	10 thickness	measurements.

Sum T stands for the sum of all thickness measurements. Number P is the number of thickness measurements, and Average T is the average thickness.

CERL TR 99/37

Site 11 measurements were taken on 27 August 1998. The water surface was approximately 72 in. from the top of the sheet pile. The surface was covered in a heavy coating of growth or scale and was very difficult to get clean. The sheet pile at this site was hot-rolled.

Fury		Hand Held	
Heiaht	Thickness	Height	Thickness
(ft)	(in)	(ft)	(in)
0	0.321	2	0.41
- 1/6	0.308	0	0.405
- 2/3	0.132	0	0.135
- 5/6	0.106	- 1/3	0.155
-1	0.112	- 2/3	0.16
-1 1/6	0.412	- 2/3	0.2
-1 1/2	0.367	-1	0.135
-1 2/3	0.135	-1 1/3	0.145
-2 1/2	0.338	-1 2/3	0.155
-3	0.17	-2	0.165
-4	0.31	-2 1/2	0.39
-4 1/2	0.28	-3	0.27
		-3 1/2	0.13
Sum T (in)	2.991	Sum T (in)	2.855
Number P	12	Number P	13
Average T		Average T	
(in)	0.24925	(in)	0.219615
		Site 11 Tot	Flange
		Sum T (in)	5.846
		Number P	25
		Average T	
		(in)	0.23384
		STD FI	0.108926

Table 14. Site 11 thickness measurements.

Sum T stands for the sum of all thickness measurements. Number P is the number of thickness measurements, and Average T is the average thickness.

Site 12 measurements were taken on 28 August 1998. The water surface was approximately 50 in. from the top of the sheet pile. The sheet pile at this site was hot-rolled.

.

папи пени		ruiy	
Height (ft) 2 0 - 1/3 - 2/3 -1	Thickness (in) 0.223 0.278 0.263 0.179	Height (ft) - 1/3 - 1/2 - 2/3 - 5/6 -1 -1 1/6 -1 1/3 -1 2/3 -2 -2 1/2 -3 -3 1/6 -3 1/2 -4	Thickness (in) 0.129 0.15 0.16 0.128 0.12 0.115 0.342 0.115 0.342 0.115 0.342 0.115 0.331 0.277 0.1236 0.325
Sum T (in) Number P Average T (in)	1.29 5 0.258	Sum T (in) Number P Average T (in)	2.5356 14 0.181114
		Site 12 Tot Sum T (in) Number P Average T (in) STD Web	Web 3.8256 19 0.201347 0.091268

Table 15. Site 12 thickness measurements. Hand Held Furv

Sum T stands for the sum of all thickness measurements. Number P is the number of thickness measurements, and Average T is the average thickness.

Appendix C: Sheet Pile Corrosion Rate Measurements

Definition of Current

A current value of (-)1.2 mA can mean different things to workers in different areas of electrochemistry. To an analytical electrochemist, it represents 1.2 mA of anodic current. To a corrosion scientist, it represents 1.2 mA of cathodic current. In the techniques used by the test equipment for this project, the corrosion convention for current was followed. Positive currents are anodic, resulting in an oxidation at the metal specimen under test.

Potential Values and Conventions Used in this Analysis

In this study, the equilibrium potential assumed by the metal in the absence of electrical connections to the metal is called the open circuit potential (E_{∞}) . The term corrosion potential (E_{corr}) was reserved for the potential at which no current flows, as determined by a numerical fit of current versus potential data. In an ideal case, the values for E_{∞} and E_{corr} will be identical. One reason the two voltages may differ is changes in the electrode surface during the scan. In this study, all potentials are specified or reported as the potential of the working electrode with respect to either the reference electrode or the open circuit potential. The former is always labeled as "vs E_{ref} " and the latter is labeled as "vs E_{∞} ". The equations used to convert from one form of potential to the other are:

$$E vs E_{oc} = (E vs E_{ref}) - E_{oc}$$
 [Eq C1]

$$E vs. E_{ref} = (E vs E_{oc}) + E_{oc}$$
 [Eq C2]

Regardless of whether potentials are versus E_{re} or versus E_{∞} , one sign convention is used. The more positive a potential, the more anodic it is. More anodic potentials tend to accelerate oxidation of a metal specimen.

Nearly all metal corrosion occurs via electrochemical reactions at the interface between the metal and an electrolyte solution. A thin film of moisture on a metal surface forms the electrolyte for atmospheric corrosion. Wet concrete is the electrolyte for reinforcing rod corrosion in bridges.

Corrosion normally occurs at a rate determined by equilibrium between opposing electrochemical reactions. The first is the anodic reaction, in which a metal is oxidized, releasing electrons into the metal. The other is the cathodic reaction, in which a solution species (often o_2 or H⁺) is reduced, removing electrons from the metal. When these two reactions are in equilibrium, the flow of electrons from each reaction is balanced, and no net electron flow (electronic current) occurs. The two reactions can take place on one metal or on two dissimilar metals (or metal sites) that are electrically connected.

Figure 35 diagrams this process. The vertical axis is potential and the horizontal axis is the logarithm of absolute current. The theoretical currents for the anodic and cathodic reactions are shown as straight lines. The curved line is the sum of the anodic and cathodic currents. It is the current that is measured when a sweeping scan of the potential of the metal is made. The sharp point in the curve results from the use of a logarithmic axis. It is actually the point where the current gets very small prior to changing sign.

The potential of the metal is the means by which the anodic and cathodic reactions are kept in balance (Figure 35).



Figure 35: Corrosion process showing anodic and cathodic current. It should be noted that the current from each half reaction depends on the electrochemical potential of the metal.

Suppose the anodic reaction releases too many electrons into the metal. Excess electrons shift the potential of the metal more negative, which slows the anodic reaction and speeds up the cathodic reaction. This counteracts the initial perturbation of the system.

In the system used in this study, the equilibrium potential assumed by the metal in the absence of electrical connections to the metal is called the open circuit potential (E_{x}).

The value of either the anodic or cathodic current at E_{∞} is called the corrosion current, I_{corr} . If we could measure I_{corr} , we could use it to calculate the corrosion rate of the metal. Unfortunately I_{corr} cannot be measured directly. However, it can be estimated using electrochemical techniques. In any real system, I_{corr} and corrosion rate are a function of many system variables including type of metal, solution composition, temperature, solution movement, metal history, and many others.

The above description of the corrosion process does not say anything about the state of the metal surface. In practice, many metals form an oxide layer on their surface as they corrode. If the oxide layer inhibits further corrosion, the metal is said to *passivate*. In some cases, local areas of the passive film break down, allowing significant metal corrosion to occur in a small area. This phenomenon is called *pitting corrosion*, or simply *pitting*.

Electrochemical Testing Techniques

Because corrosion occurs via electrochemical reactions, electrochemical techniques are ideal for the study of the corrosion processes. In electrochemical studies, a metal sample a few cm^2 in surface area is used to model the metal in a corroding system. The metal sample is immersed in a solution typical of the metal's environment in the system being studied. Additional electrodes are immersed in the solution, and all the electrodes are connected to a device called a potentiostat. A potentiostat allows the users to change the potential of the metal sample in a controlled manner.

With the exception of open circuit potential vs time and galvanic corrosion techniques, all the standard electrochemical analysis techniques utilized in this study use a potentiostat to perturb the equilibrium corrosion process. When the potential of a metal sample in solution is forced away from E_{∞} , it is referred to as *polarizing the sample*. The response (current or voltage) of the metal sample is measured as it is polarized. The response is used to develop a model of the sam-

ple's corrosion behavior. Both controlled potential (potentiostatic) and controlled current (galvanostatic) polarization is useful. When the polarization is done potentiostatically, current is measured, and when it is done galvanostatically, potential is measured. This discussion will concentrate on controlled potential methods, which see more common use.

Suppose we use the potentiostat to force the potential of a metal anodic (toward positive potentials) from EOC. In Figure 35, we are moving toward the top of the graph. This will increase the rate of the anodic reaction and decrease the rate of the cathodic reaction. Since the anodic and cathodic reactions are no longer balanced, a net current will flow from the electronic circuit into the metal sample. The sign of this current is positive by convention. The potentiostat accurately measures the current. If we take the potential far enough from E_{α} , the current from the cathodic reaction will be negligible, and the measured current will be a measure of the anodic current lie on top of each other at positive potentials. Conversely, at strongly negative potentials, the cathodic current dominates the cell current.

In some cases, as we vary the potential, we will first passivate the metal, then cause pitting corrosion. Analysis of a curve plotting the measured current versus time or potential may allow us to determine I_{corr} at E_{corr} , the tendency for passivation to occur, and the potential range over which pitting will occur.

The polarization resistance tests run in this study utilized Gamry CMS 100 Electrochemical corrosion testing software and hardware installed in a Gateway P5-133 computer operating under Windows 95. Each polarization resistance scan run during the field testing phase required the following operations:

- 1. Select test site and transport test equipment to site.
- 2. Placement of the counter electrode (CE) and reference electrode (RE) with current containment chamber on the water-side sheet pile surface at the desired test depth and orientation (Figure 37).
- 3. Connect wiring to/from the working electrode (WE = in this case the steel sheet pile), counter electrode ($CE = \frac{1}{4}$ " x 4" ceramic-coated titanium rod element) and reference electrode (RE = MC Miller Saturated Cu-CuSO₄ Reference Electrode) to the corresponding terminals on the Gamry Circuit Boards installed in the computer.
- 4. Start the "Gamry CMS100 Software" program.

- 5. The "Experiments" window created by the CMS100 provides a number of potentiostatic and potentiodynamic test alternatives. In this study, the "polarization Resistance Experiment" program was selected as the primary test module.
- 6. The program creates a "Setup" dialog box that becomes the active window and accepts changes in the experimental parameters.
- 7. The script then obtains the use of the potentiostat specified during Setup and opens a data file using the tester's entered Output name. In this study, all Tafel experiments were labeled "coetaf#xx.dta" while all polarization resistance (commonly called linear polarization) experiments were labeled either "coepr#xx.dta" or "coelp#xx.dta.
- 8. The file header information is written to the data file. This header information includes:
 - a. tags identifying possible analyses
 - b. the current time and date
 - c. a list of the setup parameters. This information is written to the file prior to data acquisition.

In all polarization resistance tests, the following test options were used:

Total Potential Band to be tested – (-)20 mV to (+)20 mV from " E_{corr} "

- potential test steps of 0.2 mV
- potential test time of 1 second per step
- test area of 180 cm²
- steel sheet pile faradaic consumption rate of 6 gm/cm³
- 15 second time conditioning only of test surface with <u>NO applied cur</u>rent or voltage.
- initial test setup stabilization period of 120 seconds or achievement of " E_{corr} " stability, as defined by a change of less than 0.1 mV/second for 5 consecutive readings, whichever occurs first.
- Inputting of any relevant test notes, such as test site location, sheet pile surface being tested, depth of probe below existing water level, etc.
- 9. The program can first condition the electrode by applying a fixed potential for a defined time period. It can establish a known surface state on the corrosion specimen. A plot of current versus time is displayed during this conditioning. For the *in situ* corrosion testing on this project, this procedure was set at 0 volts and thus was not used as it would distort the results.

- 10. The E_{∞} of the sheet pile surface directly under the probe containment chamber is measured.
 - a. If an initial delay is turned on in the setup, this step lasts for the time specified as the initial delay time, or until the E_{our} potential stabilizes. During this study, the delay maximum time was set to either 180 seconds or a stabilized potential was achieved as defined by three successive readings being within +/- 0.5 mV of each other.
 - b. A real-time plot of the measured sheet pile potential versus time is always displayed on the computer's display. The last potential measured after the initial delay criterion is met is recorded as E_{∞} .
- 11. The Polarization Resistance scan is then initiated. The potential of the sample is swept from the Initial $E(E_{x})$ to the Final E. Current readings at the above-specified 1 second time intervals are taken during the sweep.
 - a. The sweep is actually a staircase ramp. The sample is potentiostatic at the E_{∞} , a delay of one sample period occurs, and a reading of the current is taken.
 - b. The potential is then stepped by the mV value specified (0.2 mV in this study), a delay of one sample period (1 second in this study) occurs, and the next current reading is taken.
 - c. Stepping the potential, delaying and acquiring data points continues until the potential equals the final E. At each point the current range is automatically switched to the optimal range for the measured cell current.
 - d. IR-drop error compensation was used in each scan, correcting each potential for the measured IR drop of the preceding point.
 - e. A plot of log I vs E is displayed during the scan.
- 12. The data are written to the output file and the script cleans up and halts.
- 13. When the scan is over the cell is turned off, after which the next location can be tested.
- 14. The data are then analyzed by a separate program module which runs as a subroutine under Microsoft Excel. The program automatically evaluates the measured data in accordance with Stern-Geary equation (discussed in more detail in Section V of this report), and the graphs and data including corrosion rate (CorrRate) are displayed and printed out in the form shown in Figure 35.



Figure 36. Coal storage at Site 4, the Mid-Continental Coke and Coal property.



Figure 37. Polarization resistance testing device.



Figure 38. Fury robot entering the water on the back flange of the sheet pile.



Figure 39. Fury nearly submerged, taking measurements on the front flange of sheet pile.

Appendix D: Resistivity and Water Chemistry Data

	River		i						Hardness	N02-	NH3		
SURIOD	Mile	Uate	1 une	Comments	TEMP	ЪН	D.O.	COND.	as CACO3	NO3	Ą	TKN	SQT
Duy R@ W3rd St.	3.26	04-Sep-96	1118		27.5	7.3	5.2	1190	266	8.56	0.52	1.5	702
Duy R@ W3rd St.	3.26	10-Jul-96	1216		26.9	7.65	4.0	101	276	7.56	0.62	1.7	728
Juy R@ W3rd St.	3.26	20-Jun-96	1015	Ore Boat 20 Mins. Ago	23.3	7.6	8.7	650	177	2.66	0.37	1.1	392
Cuy R@ W3rd St.	3.26	29-Aug-96	1105		27.0	7.6	4.9	1070	257	7.64	0.40	0.5	644
Cuy R@ W3rd St.	3.26	20-Jul-96	1153		26.5	9.6	3.5	1150	250	6.83	0.61	1:7	684
Cuy R@ dst Columbus Ave.	1.46	04-Sep-96	1149		27.0	. 7.3	3.6	1175	269	7.54	0.53	1.4	690
Cuy R@ dst Columbus Ave.	1.46	04-Sep-96	1149		27.0	7.3	3.6	1175	269	7.35	0.55	1.5	694
Cuy R@ dst Columbus Ave.	1.46	10-Jul-96	1346		26.3	7.48	4.1	1017	274	7.31	0.71	1.7	710
Cuy R@ dst Columbus Ave.	1.46	20-Jun-96	0945	Freighter Two Hours Ago	24.0	7.54	3.75	640	173 ·	2.40	0.43	1.3	358
Cuy R@ dst Columbus Ave.	1.46	29-Aug-96	1129		27.0	7.5	2.7	1010	246	6.47	0.51	0.5	608
Cuy R@ dst Columbus Ave.	1.46	29-Aug-96	1129	CD Verified 10-1-96						6.53	0.54	0.6	610
Cuy R@ dst Columbus Ave.	1.46	30-Jul-96	1247	After Rain Started	25.0	7.4	4.1	1000	224	5.75	0.78	1.7	610
Cuy R@ dst Columbus Ave.	1.46	30-Jul-96	1247	After Rain Started	25.0	7.4	4.1	1000	222	5.65	0.75	1.6	608

Cuyahoga River Basin Water Quality Data for 1996 Survey Rewrite

US Army Corps of Engineers Cuyahoga River Sheet Pile Wenner 4-Pin In-Situ Soil Resistivity Data

Site Location	Pin Spacing (in Feet)	Meter Range	Measured Value	R (in Ohms)	<i>p =</i> Resistivity (in Ohm-Cm)	Barnes Layer Resistivity (5' to 10' Layer in Ohm- Cm)
CM#1	5	1	4.5	4.5	4,310	
CM#1	10	1	1.5	1.5	2,870	2,250
CM#2	5	10	1	10	9,580	
CM#2	10	1	5.5	5.5	10,530	12,222
CM#3	5	1	5.8	5.8	5,550	
CM#3	10	1	1.3	1.3	2,490	1,676
CM#4	5	0.1	5.5	0.55	530	
CM#4	10	1	2.3	2.3	4,400	Can Not Calculated by Barnes Method
CM#5	5	1	1.9	1.9	1,820	
CM#5	10	1	1.6	1.6	3,060	10,133
CM#6	5	10	1.45	14.5	13,880	
CM#6	10	1	6	6	11,490	10,235
CM#7	5	1	5.9	5.9	5,650	
CN1#7	10	0.1	8.8	0.88	1,690	1,034
CN1#8	5	1	3.9	3.9	3,730	
CM#8	10	1	1.1	1.1	2,110	1,532
CN1#11	5	10	1.9	19	18,190	
CM#11	10	1	3.7	3.7	7,090	4,595
CM#12	5	10	1.2	12	11,490	
CM#12	10	1	2.9	2.9	5,550	3,824
CM#12 - Boat	5	10	1.5	15	14,360	
CM#12 - Boat	10	1	2.5	2.5	4,790	3,000
Average of 0) to 5' Layer				8,099	
Average of 0) to 10' Layer				5,097	
Average of 5	5' to 10' Layer	•				5,050

Metal Con Referenc Country	Values L Scan Rate Scan Rate fetal Density trosion Rate hamber Size Electrode B, & B,	Jsed in Pro = -0.02 V to 0.0 = 58 grams/c = 6 gm/cm ³ = 3" x 9-1/2" ⁻ = MCM Mode = 1/4" Dia x 6 = 1/20 mV/De	gram and Analysis: 02 V: 0.02 mV/Sec: 1Second/Data Pt m ³ = 180 cm ² = 180 cm ² = 180 cm ² Long PMO Coated Ttanium Rod cade		Noite N		of Data Inclui	bata Only Data	
Test No.	File Name	Site Location	Description	Type of Test	Ecorr (-mV)	lcorr (Amps/cm ²)	Rp (ohm/cm ²)	Corrosion Rate (mm//ear)	Comment
2	coepr#2	CM Site #2	Same as Test #1 except 2' farther south on outer surface of Z pile	Linear Polarization	637.6	2.583E-06	1.009E+04	3.215	Very łow Corrosion Rate - Less Scatter
e.	coepr#3	CM Site #2	Same as Test #1 except Top of Test Camber 6" below HWL -	Linear Polarization	605.4	9.666E-11	2.696E+08	0.000	Nij Corrosion Rate - Low Data Scatter
4	coelp#4	Near CM Site #2	300' Southwest of Test #3, 2' below HVVL on Invert – Note corrosion rate calculation not valid - test run with are set at 1 cm2 divide rate of 4872 mpy by 180	Línear Polarization	410.4	3.913E-03	6.659E+00	27.067	Note Data Entry Error corrected per Description Note to provide 27 mpy corrosion rate
ى ع	coepr#4a	Near CM Site #2	Same as Test No. 4 except area corrected to 180 cm ² and test re-run	Linear Polarization	509.0	4.175E-05	6.241E+02	51.982	Corrected value and retest gives very similar results.
ω	coelp#5	Near CM Site #2	Near Test No. 5 except on 90° surface facing downstream 1' below HWL	Linear Polarization	601.8	1.289E-05	2.021E+03	16.052	Good Data and comparative to Test # 4 & 5. Note: Downstream face and deeper test should give lower corrupt
2	coelp#6	CM Site #2	Re-Run at Test Nos. 1 - 3 except on 900 Surface facing upstream 6" below HWL	Linear Polarization	640.4	1.042E-05	2.500E+03	12.980	Reasonable Values
				•					

Values Used in Program and Analysis: Values Used in Program and Analysis: Scan Rate = -0.02 V to 0.02 V; 0.02 mV/Sec; 15econd/Data Pr Metal Density = 58 grams/cm ³ Metal Density = 58 grams/cm ³ Chamber Size = 3" x 9-1/2" = 180 cm ² Chamber Size = 3" x 9-1/2" = 180 cm ² Reference Electrode = MCM Model RE-375 Saturated Cu-CuSO ₄ Counter Electrode = 1/4" Dia x 6" Long PMO Coated Tranium Rod	$D_a \in B_c = 120 \text{ mV/Decade}$
---	---------------------------------------

Electrochemical Corrosion Rate Analysis Cuyahoga River Sheet Pile

_			Electrochemic	iya rive al Corro	sion F	et Pile Rate Ana	lvsis		
							·		
G	coepr#7a	CM Site #8	Re-Run at Test No. 8 Same location and conditions	Linear Polarization	432.2	8.805E-06	2.959E+03	10.963	Good Data with low data scatter 1st run had abnormally low Ecorr
=	coelp#8a	CM Site #4	Re-Run of Test No. 10	Linear Polarization	384.6	8.630E-06	3.020E+03	10.744	Note reasonable Ecorr with low data scatter
12	coelp#9	CM Site #4	Same as #11 except on 90° Surface facing downstream 8' below HWL	Linear Polarization	573.7	1.526E-05	1.708E+03	18.977	Note reasonable Ecorr with low data scatter
ŧ	coelp#9a	CM Site #4	Same as #12	Linear Polarization	584.7	4.073E-06	6.398E+03	5.071	Note reasonable Ecorr with moderate data scatter and reasonable corrosion rate
5	coelp10a	CM Site #5	Same as Teet No. 14 (NOTE: Very old, thick and voluminous corrosion product but substantial steel still evident	Linear Polarization	353.5	3.206E-06	8.128E+03	3.992	Reasonable Values and moderate data scatter with reasonable Ecorr given heavy corrosion product on surface
16	coelp#11	CM Site #6	At LTV Steel Turning Basin - 2' below HWL on 90° Surface facing upstream	Linear Polarization	621.6	2.444E-06 [`]	1.066E+04	3.043	Note somewhat high Ecorr with moderate data scatter
17	coelp11a	CM Site #6	Rerun of Test No. 16	Linear Polarization	508.0	6.516E-06	3.999E+03	8.113	More Realistic Ecorr with slightly less data scatter
18	coelp#12	CM Site #7	At 150 Yards Upstream from Elev. RR Bridge, Z' Below HWL on 90o Surface facing Upstream	Linear Polarization	541.0	1.741E-06	1.497E+04	0.055	Data has moderate Scatter with somewhat high Ecorr - Renun
-19	coelp#13	CM Site #7	Same as Test No. 18 except 4' below HWL – Zebra Mussels prevented locating probe deeper	Linear Polarization	550.6	8.771E-06	2.971E+03	10.920	Data has less Scatter with reasonable Ecorr
8	coelp#14	CM Site #3	2' below HWL on 90° surface facing downstream	Linear Polarization	404.7	3.420E-05	7.618E+02	1.082	Data somewhat scattered initially and did not stabilize until 3 minutes after test initiation but did not seem to effect data

Ċ C 0 devii O

CERL TR 99/37

			Electrochemic	il Corro	sion F	tate Ana	alvsis		
8	coelp14b	CM Site #3	Rerun of Test Nos. 20 & 21	Linear Polarization	426.2	5.239E-06	4.974E+03	6.522	Data much smoother and Corr Rate seems realistic for area and test location
R	coelp#15	CM Site #3	Same location as Tests No. 20 thru 22 except probe at Mud Line	-inear Polarization	601.8	2.791E-05	9.336E +02	34.750	Note major potential difference between Ecorr at Test 20-22 and 23 with this value much more negative proving large macrocell with mud line being more active (anotic). Test results confirm this.
25	coelp16a	CM Site #1	Same as Test #24 - Rerun	Linear Polarization	365.3	1.481E-06	1.759E+04	1.844	Data is much smoother and results appear reasonable
21	coelp17a	CM Site #12	rerun of Test No. 26	-inear Polarization	676.9	6.494E-06	4.013E+03	8.086	Data much smoother and Corr Rate seems realistic for area and test location
8	coelp#18	CM Site #12	Same area as Test Nos. 26 & 27 except 1 ⁻ below HWL on 90° surface facing upstream	Linear Dolarization	589.8	1.397E-06	1.865E+04	1.739	Smooth Data and given lower Ecorr would produce lower corrosion rate (possibly reduced oxycen level)
R	coelp#19	CM Site #12	400' East of Test Nos. 26 thru 28 near ICOE Robotic Work Boat Test Location - 3' below HWL on 90o surface facing downstream	.İnear Olarization	588.0	1.345E-06	1.937E+04	1.675	Smooth data and good correlation of data with Test No. 27 & 28
31	coelp20a	CM Site #11	Re-Run of Test at same location as Tests No. 30	Linear Polarization	563.4	3.851E-06	6.766E+03	4.795	Data very smooth and Corr Rate seems realistic for area and test location
Minimum					353.50	9.666E-11	6.659E+00		
Maximun	٤				676.90	3.913E-03	2.696E+08	51.98	
Average					527.64	3.214E-04	2.157E+07	11.83	
Standarc	1 Deviativ	uo			QR 47	8 140E-04	K CHELOT	17 55	

Cuyahoga River Sheet Pile

			US Army Cuyaho Electrochemica	Corps (ga Rivel Il Corro:	of Engi r Sheet sion Ra	ineers t Pile ate Ana	lysis		
Metal Co Reference Count	(alues U Scan Rate Scan Rate Introsion Rate hamber Size Electrode B, & B,	Sed in Pro = -0.02 V to 0. = 58 grams/ = 58 grams/ = 58 grams/ = 58 grams/ = 58 grams/ = 58 grams/ = 112" = 112" = 112" = 120 mV/Di	Gram and Analysis 102 V. 0.02 mV/Sec: 1Second/Data Pt cm ³ = 180 cm ² = 180 c		NOTE III	This Set All dine	or Data Inc.	udes Only On Data	
Test No.	File Name	Site Location	Description	Type of Test	Ecorr (-mV)	lcorr (Amps/cm ²)	Rp (0hm/cm²)	Corrosion Rate (mm/Year)	Comment
	1 coepr#1	CM Site #2	At HWL on Invert at Big Bend 50' South of Fountain	Linear Polarization	569.4	7.59E-06	3.43E+03	-169.455	Not Valid - Negative Slope - Large Scatter to
	8 coelp#7	CM Site #8	On Tower City Side of River, Just downstream of turning basin, on 90o surface facing downstream, 1' below HML	Linear Polarization	234.2	-1.52E-05	-1.71E+03	-18.951	Not Valid - Negative Slope - Large Scatter to Data - Very low Ecorr
4	0 coelp#8	CM Site #4	At Coke Plant, Stored Coke Pile near major undermined area with several sink holes (site of TV camera shoot), using new magnetic hold probe located on invert 6" below HWL	Linear Polarization	144.0	-3.43E-06	-7.59E+03	4.276	<u>Not Valid</u> - Negative Slope - Large Scatter to Data - Very low Ecorr
÷	4 coelp#10	CM Site #5	At Cement Plant, on Invert at HVVL (NOTE: Very old, thick and voluminous corrosion product but substantial steel still evident	Linear Polarization	159.6	-2.57E-06	-1.01E+04	-0.081	<u>Not Valid</u> - Negative Slope - Large Scatter to Data - Very low Ecorr

CERL TR 99/37

			Electrochemica	Corros	sion Ra	te Anal	vsis		•
21	coelp14a	CM Site #3	Rerun of Test No. 20 - Note corrosion rate calculation not valid - test run with area set at 1 cm2 - Corrate on Graph recalculated to give Mils/Yr Result instead of mm/yr and revised area (divide by 25.4 and 180)	Linear Polarization	415.4	1.00E-03	2.60E+01	0.007	Not Valid - Wrong Test Area in data and analysis program could not accommodate distortion . see graph
54	coelp#16	CM Site #1	6" below HWL on outer face - could not go deeper here - during test, data tooked quite scattered - Reported data of 0.209 mm/y converted to mils/year by dividing value by 25.4	Linear Polarization	351.0	6.60E-06	3.95E+03	0.008	<u>Not Valid</u> - Large Scatterto Data
56	coelp#17	CM Site #12	6" below HWL on outer face	Linear Polarization	.545.4	1.02E-04	2.56E+02	126.800	<u>Not Valid</u> - Large Scatter to data - rate seems unusually high - will result
27	coelp17a	CM Site #12	rerun of Test No. 26	Linear Polarization	676.9	6.49E-06	4.01E+03	8.086	Data much smoother and Corr Rate seems realistic for area and test
30	coelp#20	CM Site #11	2' below HWL on 90° surface facing downstream	Linear ^D olarization	460.1	1.33E-04	1.97E+02	164.989	Not Valid –Extremely scattered data
					NOTE	This Set o	Data Inclu	des Only	

US Army Corps of Engineers Cuyahoga River Sheet Pile ctrochemical Corrosion Rate Analv

98

.

Invalid Linear Polarization Data

	Data	osion Comment Ite Comment Year)	A55 Slope - Large Scatter to Data	215 Very low Corrosion Rate Less Scatter	00 Nil Corrosion Rate - Low Data Scatter	Note Data Entry Error corrected per Description Note to provide 27 mpy corrosion rate	Corrected value and retest gives very similar results.
	cludes all L ng invalid D	Corrc Cm ²) Ra	+03 -169	+04 3.2	+08 0.0	+00 27.0	+02 51. 9
lysis	Data in Includi	Rp (Ohm/G	3.43E-	1.01E	2.70E-	9.66E	6.24E
ineers t Pile ate Ana	This Set of zation Data	lcorr (Amps/cm ²)	7.59E-06	2.58E-06	9.67E-11	3.91E-03	4.18E-05
of Eng Shee sion R	NOTE: Polari	Ecorr (-mV)	569.4	637.6	605.4	410.4	509.0
Corps c ga Rivel I Corros		Type of Test	Linear Polarization	Linear Polarization	Linear Polarization	Linear Polarization	Linear Polarization
US Army Cuyahoç Electrochemica	ram and Analysis 2 v: 0.02 m/vsec: 15econd/Data Pt 1 ³ = 180 cm ² = 180 cm ²	Description	At HWL on Invert at Big Bend 50' South of Fountain	Same as Test #1 except 2' farther south on outer surface of 2 pile	Same as Test #1 except Top of Test Camber 6" below HWL -	300' Southwest of Test #3, 2' below HVVL on Invert – Note corrosion rate calculation not valid - test run with are set at 1 cm2 – divide rate of 4872 mpy by 180	Same as Test No. 4 except area corrected to 180 cm ² and test re-run
	ed in Prog = -0.02 V to 0.0 = -0.02 V to 0.0 = = 5 gm/cm ³ = = 0.02 V to 0.0 = = 114" Dia v G	Site Location	CM Site #2	CM Site #2	CM Site #2	Near CM Site #2	Near CM Site #2
	Alues Us Scan Rate Scan Rate osion Rate osion Rate osion Rate B. & B.	File Name	coepr#1	coepr#2	coepr#3	coelp#4	coepr#4a
	Va Metal Corr Cha Cha Charter Counter	Test No.	-	2	e	4	2

			Electrochemica	ja river Corros	Sneet	Pile Ita Anal	veie		
							2002		
U	5 coelp#5	Near CM Site #2	Near Test No. 5 except on 90° surface facing downstream 1' below HWL	Linear Polarization	601.8	1.29E-05	2.02E+03	16.052	Good Data and comparative to Test # 4 & 5. Note: Downstream face and deeper test
Ľ	/ coelp#6	CM Site #2	Re-Run at Test Nos. 1 - 3 except on 90o Surface facing upstream 6" below HWL	Linear Polarization	640.4	1.04E-05	2.50E+03	12.980	Reasonable Values
3	8 coelp#7	CM Site #8	On Tower City Side of River, just downstream of turning basin, on 90o surface facing downstream, 1' below HWL	Linear Polarization	234.2	-1.52E-05	-1.71E+03	-18.951	Not Valid - Negative Slope - Large Scatter to Data - Very low Ecorr
0	coepr#7a	CM Site #8	Re-Run at Test No. 8 Same location and conditions	Linear Polarization	432.2	8.81E-06	2.96E+03	10.963	Good Data with low data scatter 1st run had abnormally low Ecorr
\$) coelp#8	CM Site #4	At Coke Plant, Stored Coke Pile near major undermined area with several sink holes (site of TV camera shoot), using new magnetic hold probe located on invert 6" below HWL	Linear Polarization	144.0	-3.43E-06	-7.59E+03	4.276	<u>Not Valid</u> - Negative Slope - Large Scatter to Data - Very low Ecorr
£	coelp#8a	CM Site #4	Re-Run of Test No. 10	Linear Polarization	384.6	8.63E-06	3.02E+03	10.744	Note reasonable Ecorr with low data scratter
4	coelp#9	CM Site #4	Same as #11 except on 90° Surface facing downstream 8' below HWL	Linear Polarization	573.7	1.53E-05	1.71E+03	18.977	Note reasonable Ecorr with low data scatter
£	3 coelp#9a	CM Site #4	Same as #12	Linear Polarization	584.7	4.07E-06	6.40E+03	5.071	Note reasonable Ecorr with moderate data scatter and reasonable corrosion rate
4	l coelp#10	CM Site #5	At Cernent Plant, on Invert at HWL (NOTE: Very old, thick and voluminous corrosion product but substantial steel still evident	Linear Polarization	159.6	-2.57E-06	-1.01E+04	-0.081	Not Valid - Negative Slope - Large Scatter to Data - Very low Ecorr

US Army Corps of Engineers

			US Army Cuyahoç Electrochemica	Corps c Ja River Corros	of Engi - Sheet sion Ra	neers Pile ate Anal	ysis		
	Ī								
15 coelp	o10a (CM Site #5	Same as Test No. 14 (NOTE: Very old, thick and voluminous corrosion product but substantial steel still evident	Linear	353.5	3.21E-06	8.13E+03	3.992	Reasonable Values and moderate data scatter with reasonable Ecorr given heavy corrosion product on surface
16 coelp	# 	CM Site #6	At LTV Steel Turning Basin - 2' below HWL on 90° Surface facing upstream	Linear Polarization	621.6	2.44E-06	1.07E+04	3.043	Note somewhat high Ecorr with moderate data scatter
17 coelp	o11a (CM Site #6	Rerun of Test No. 16	Linear Polarization	508.0	6.52E-06	4.00E+03	8.113	More Realistic Ecorr with slightly less data scatter
18 coelp	o#12 (CM Site #7	At 150 Yards Upstream from Elev. RR Bridge, 2' Below HWL on 90o Surface facing Upstream	Linear Polarization	541.0	1.74E-06	1.50E+04	0.055	Data has moderate Scatter with somewhat high Ecorr - Rerun
19 coelp	第13 (CM Site #7	Same as Test No. 18 except 4 below HVVL Zebra Mussels prevented locating probe deeper	Linear Polarization	550.6	8.77E-06	2.97E+03	10.920	Data has less Scatter with reasonable Ecorr
20 coelp	#14 	CM Site #3	2' below HWL on 90° surface facing downstream	Linear Polarization	404.7	3.42E-05	7.62E+02	1.082	Data somewhat scattered initially and did mot stabilize until 3 minutes after test initiation but did not seem to effect data
21 coelp	014a ((CM Site #3	Rerun of Test No. 20 – Note corrosion rate calculation not valid - test run with area set at 1 cm2 - CorrRate on Graph recalculated to give Mils/Yr Result instead of mm/yr and revised area (divide by 25.4 and 180)	Linear Polarization	415.4	1.00E-03	2.60E+01	0.007	Not Valid - Wrong Test Area in data and analysis program could not accommodate distortion - see graph
22 coelp	14b (CM Site #3	Rerun of Test Nos. 20 & 21	Linear Polarization	426.2	5.24E-06	4.97E+03	6.522	Data much smoother and Corr Rate seems realistic for area and test location

		cuyano Electrochemica	ja Kiver I Corros	- Sheet sion Ra	Pile ite Anal	ysis		
C	Site #3	Same location as Tests No. 20 thru 22 except probe at Mud Line	Linear Polarization	601.8	2.79E-05	9.34E+02	34.750	Note major potential difference between Ecorr at Test 20-22 and 23 with this value much more negative proving large macrocell with mud line being more active (anodic). Test results confirm this.
U 1	M Site #1	6" below HWL on outer face - could not go deeper here - during test, data looked quite scattered - Reported data of 0.209 mm/y converted to mils/year by dividing value by 25.4	Linear Polarization	351.0	6.60E-06	3.95E+03	0.008	<u>Not Valid</u> - Large Scatter to Data
0 1	M Site #1	Same as Test #24 - Rerun	Linear Polarization	365.3	1.48E-06	1.76E+04	1.844	Data is much smoother and results appear reasonable
51	M Site #12	6" below HWL on outer face	Linear Polarization	545.4	1.02E-04	2.56E+02	126.800	<u>Not Valid</u> - Large Scatter to data - rate seems unusually high - will rerun
0 1	M Site #12	rerun of Test No. 26	Linear Polarization	676.9	6.49E-06	4.01E+03	8.086	Data much smoother and Corr Rate seems realistic for area and test
	M Site #12	Same area as Test Nos. 26 & 27 except 1' below HWL on 90° surface facing upstream	Linear Polarization	589.9	1.40E-06	1.87E+04	1.739	Smooth Data and given lower Ecorr would produce lower corrosion rate (possibly reduced oxvoen level)

US Army Corps of Engineers

			US Army Cuyaho Electrochemica	Corps c ja River I Corros	of Engi Sheet sion Ra	neers Pile tte Anal	ysis		
Sč) coelp#19	CM Site #12	400' East of Test Nos. 26 thru 28 near COE Robotic Work Boat Test Location - 3' below HWL on 900 surface facing downstream	Linear Polarization	588.0	1.35E-06	1.94E+04	1.675	Smooth data and good correlation of data with Test No. 27 & 28
Ř) coelp#20	CM Site #11	2' below HWL on 90° surface facing downstream	Linear Polarization	460.1	1.33E-04	1.97E+02	164.989	Not Valid –Extremely scattered data
ñ	l coelp20a	CM Site #11	Re-Run of Test at same location as Tests No. 30	Linear Polarization	553.4	3.85E-06	6.77E+03	4.795	Data very smooth and Corr Rate seems realistic for area and test location

CERL TR 99/37

Pstat #1 Scan: -0.02 V to 0.02 V, 0.2 mV/s, 1 s/pt EOC: -0.562908 V Area: 180 cm2 Electrode: 6 gm/cm3, 58 g/equiv Conditioning: OFF Delay: ON, 1200 s IR Comp.: ON	NOTES	POLRES RESULTS Region = -20.1 mV to -13.3 mV BetaC = 120.0 mV/Decade BetaA = 120.0 mV/Decade Ecorr = -569.4 mV Icorr = -7.594E-06 A/cm2 Rp = -3.431EE-06 A/cm2 Rp = -3.435 mpy CorrRate = -9.455 mpy
Polarization Resistance 'coepr#1.dta' 8/24/1998-14:6:9 -0.013	Potential (V) vs Eoc 0 0 0 0 0 0 0 0 0 0 0 0 0 0 0 0 0 0 0	-0.020 -0.021 -0.021 -0.021 -0.026-06 0.0E+00 2.0E-06 4.0E-06 6.0E-06 8.0E-06 1.0E-05 1.4E-05 Current Density (Acm2)



Pstat #1 Scan: -0.02 V to 0.02 V, 0.2 mV/s, 1 s/pt EOC: -0.572948 V Area: 180 cm2 Electrode: 6 gm/cm3, 58 g/equiv Conditioning: OFF Detby: ON, 120 s IR Comp.: ON	same as coepr#1 except 6" below water	POLRES RESULTS Region = -20.1 mV to -11.6 mV BetaC = 120.0 mV/Decade BetaA = 120.0 mV/Decade Ecorr = -605.4 mV Icorr = 9.666E-11 A/cm2	corrRate = 0.000 mpy
Polarization Resistance 'coepr#3.dta' 8/24/1998-15:16:44	-0.013 -	-0.019	-5.0E-09 -4.0E-09 -3.0E-09 -2.0E-09 -1.0E-09 0.0E+00 1.0E-09 2.0E-09 3.0E-09 5.0E-09 Current Density (A/cm2)


Polarization Resistance 'coepr#4a.dta' 8/25/1998-12:37:18	Pstat #1 Scan: -0.02 V to 0.02 V, 0.2 mV/s, 1 s/pt EOC: -0.505151 V Area: 180 cm2 Electrode: 6 gm/cm3, 58 g/equiv Conditioning: OFF Delave ON 720.5	IR Comp.: ON	same as coepr#4 except area corrected to 180 cm2	POLRES RESULTS Region = -8.8 mV to 1.3 mV BetaC = 120.0 mV/Decade BetaA = 120.0 mV/Decade	Ecorr = -509.1 mV lcorr = 4.175E-05 Acm2 Rp = 6.241E+02 Ohm cm2 5 CorrRate = 51.982 mpy
	Polarization Resistance 'coepr#4a.dta' 8/25/1998-12:37:18		MAnd	Jon Mo	-05 -4.0E-05 -3.0E-05 -2.0E-05 -1.0E-05 0.0E+00 1.0E-05 2.0E-05 3.0E-05 4.0E-05 5.0E-0





Pstar #1 Scan: -0.02 V to 0.02 V, 0.2 mV/s, 1 s/pt EOC: -0.422124 V Area: 180 cm2 Electrode: 6 gm/cm3, 58 g/equiv Conditioning: OFF Delay: ON, 180 s IR Comp.: ON	NOTES Rerun of coelp#7 at CM#8 on Tower City Side, Same Conditions	POLRES RESULTS Region = -12.2 mV to -2.1 mV BetaC = 120.0 mV/Decade BetaA = 120.0 mV/Decade Ecorr = -432.2 mV Icorr = 8.805E-06 A/cm2 Rp = 2.959E+03 Ohm cm2 CorrRate = 10.963 mpy
	<u> </u>	2.0E-05
		1.5E-05
		1.0E-05
tance	~	5.0E-06
on Resis	Mond	0.0E+00
Jarizati 7a.dta' 8		-5.0E-06 Currer
Pc coepr#		-1.0E-05
		-1.5E-05
74 52		2.0E-05

























Pstat #1 Scan: -0.02 V to 0.02 V, 0.125 mV/s, 2 s/pt EOC: -0.423185 V Area: 180 cm2 Electrode: 6 gm/cm3, 58 g/equiv Conditioning: OFF Delay: ON, 300 s IR Comp.: ON	repeat of COELP#14 & 14a	POLRES RESULTS Region = -7.6 mV to 2.4 mV BetaC = 120.0 mV/Decade BetaA = 120.0 mV/Decade Ecorr = -426.2 mV Icorr = 5.239E-06 A/cm2 Rp = 4.974E+03 Ohm cm2 CorrRate = 6.522 mpy
		3.0E-05
		2.0E-05
:е):47:37		1.0E-05
n Resistanc	~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~	at Density (Acm2
Polarizatio p14b.dta' 8,		-1.0E-05 Currer
'coel		-2.0E-05
0.004	Potential (V) vs Eoc -0. -0. -0. -0. -0. -0. -0. -0. -0. -0.	-0.006 - -0.008



















USACERL DISTRIBUTION

Chief of Engineers ATTN: CEHEC-IM-LH (2) ATTN: CEHEC-IM-LP (2) ATTN: CECC-R ATTN: CECC-R ATTN: CERD-L ATTN: CERD-M ATTN: CECW-ET ATTN: CECW-EE

US Army Engr Div, Buffalo 14207 ATTN: CELRD-PE-EE (12)

Defense Tech Info Center 22304 ATTN: DTIC-O (2)

> 23 5/99