AEC-TIC (2)

ICL-DC-720088

**Julimited Release** 

MASTER Some Observations on the Formation of Surface Martensite in 304L Stainless Steel **DISTRIBUTION STATEMENT A** AT (29-1)-189 Approved for Public Release **Distribution Unlimited** -C. Ociagard 1973 **Reproduced From Best Available Copy** Sandie Laboratories 73)



DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

### This work was supported by the United States Atomic Energy Commission. Contract Number AT-(29-1)-789

#### Issued by Sandia Laboratories, a prime contractor to the United States Atomic Energy Commission

#### - NOTICE -

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the United States Atomic Energy Commission, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or essumes any legal lishility or responsibility for the eccurscy, completeness or usefulness of any information, apparenus, product or process disclosed, or represents that its use would not infringe privately owned rights.

Transfer the state of the second state of the

2

### SCL-DC-720088

## SOME OBSERVATIONS ON THE FORMATION OF SURFACE MARTENSITE IN 304L STAINLESS STEEL

B. C. Odegard Member of Technical Staff Sandia Laboratories Livermore, CA 94550

#### ABSTRACT

A surface martensite was observed in a 304L stainless steel. The morphological details as influenced by polishing techniques and thermal quenching are discussed. The quantity of martensite was found to be greatly amplified by the strain energy produced by mechanical polishing.

> NOTICE This report was prepared as an account of work sponsored by the United States Governmeut, Neither the United States nor the United States Atomic Easrry Commission, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or essumes any legal liability or responsibility for the accurscy, completeness or usefulness of any information, spparatus, product or process disclosed, or represents that its use would not infringe privately owned rights.

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

3

#### Introduction

A surface-related martensitic transformation has been observed in 18-8 type stainless steels [1,2] and in Fe-Ni alloys [3,4]. In each instance, the transformation was reported to occur spontaneously at temperatures well above the M<sub>s</sub> temperatures of the bulk material. This behavior has been interpreted [3,4] as arising from the inability of the surface to support a hydrostatic stress component. This stress is produced by the volume expansion accompanying the  $\gamma + \alpha'$  transformation. Kaufman et al [4] observed a decrease in the M<sub>s</sub> temperature in an Fe-30% Ni alloy of about 5 x 10<sup>-3</sup> K-atm<sup>-1</sup>. The absence of a hydrostatic stress therefore raises the M<sub>s</sub> temperature. Klosterman [3] describes the surface martensite formation at 5-30°C above that of the M<sub>s</sub> temperature for an Fe-30% Ni alloy.

In this investigation, two distinct morphologies of surface martensite were observed in an annealed 304L stainless steel. No temperature or strain excursions had occurred to prompt the transformation. The study was conducted to examine the morphology and quantity of martensite produced as influenced by the polishing technique. /

#### Experimental

The chemical analysis of the alloy was 0.026 percent C, 18.52 percent Cr, 8.75 percent Ni, 1.05 percent Mn and the balance Fe. Although the chemistry is within the allowable range for a 304L alloy, it is atypically low in the elements which are known austenite stabilizers. As a consequence, this alloy has an abnormally high propensity to form martensite. To provide

a measure of the instability of the austenite, the T<sub>o</sub> value was computed. T<sub>o</sub> is defined as the temperature above which martensite cannot thermodynamically form  $\int (i.e., \Delta G^{\gamma-\alpha'})$  is positive). This analysis has been described in the literature [5]. The alloy used in this study had a T<sub>o</sub> value of 321°C, 50°C higher than for a typical chemistry of 304L stainless steel.

The material had been forged at approximately 900°C followed by a full anneal to conform to a 206  $MN/m^2$  yield strength requirement.

### Results and Discussion

The microstructure of the as-received material after mechanically polishing and etching is shown in Figure 1. This is contrasted to the microstructure after exposure to -17°C for 45 minutes in Figure 2. Two distinct morphologies of martensite coexist with the austenite matrix: a platelet shaped (spearhead) martensite (position a) which favors nucleation and growth along annealing twin boundaries, consistent with the surface martensite in Fe-Ni-Cr reported by Breedis [6] and a massive-type martensite (position b) which exists intragranularly. Figures 3 and 4 show more clearly the result of the low temperature excursion on the two types of martensite. The existing platelets exhibited growth in both width and length as well as additional nucleation. The massive type exhibited no significant change. Additional exposures to -55°C created no further change in the phase quantities. The magnetic phase content as determined both before and after the low temperature exposures by a Severn indicator<sup>1</sup> and magnetometer

<sup>1</sup>Trademark of Severn Engineering Company, Inc., Annapolis, MD.

> met

was less than 0.5% present, although the quantity of martensite indicated by a linear analysis on Figure 2 was approximately 15%. The sample, in the condition indicated in Figure 2, was then inspected by X-ray diffraction to determine the martensite structure. A monochrometer was used to eliminate flucrescent radiation.  $\alpha'$ -martensite was detected, with one additional weak peak indicating a small quantity of  $\varepsilon$ -martensite.

To discern the martensite phase distribution, the specimen was electropolished to remove 50-75  $\mu$ m of the existing surface and then etched (Figures 6, 7). The microstructure both before and after the electropolishing procedure is shown in contrast in Figures 5 and 6. As noted, the platelets are almost nonexistent and the massive type has been significantly reduced. An X-ray diffraction scene das nable to detect any martensite. Exposures to -55°C (Figure 8) and color detectable change in the distribution or quantity of martensive in this electropolished sample.

Conclusions

1. The abnormally low austenite stabilized chemistry prompted the martensite transformation.

2. The martensite is concentrated at the surface and exists in two morphologies: (1) a plate-like morphology described as surface martensite which prefers annealing twin boundaries for nucleation and growth and (2) a "massive-type" morphology which nucleates intragranularly and is not significantly affected by thermal quenching. The diffraction experiments indicate that the structure of the martensite was predominantly the BCC type ( $\alpha$ '-martensite).

3. The observed quantity of martensite was greatly influenced by the strain energy imposed during mechanical polishing thus producing an erroneously high quantity compared to the bulk. (

The comments and advise of my colleagues A. W. Thompson, M. C. Nichols, and M. I. Baskes have been greatly appreciated during this study. Also, a special thanks to T. L. Bryant and R. E. Gorniak for their assistance in the metallography.





Figure 2. Exposed, ~17°C for 45 minutes



() }-





g





E Statist

# Figure 5. Mechanical polish, exposed to -17°C for 45 minutes

# Figure 6.

Electropolished to remove 50-75 microns



1

# Figure 7. Electropolished surface prior to any exposure



9

Exposed, -55°C for 30 minutes

#### References

- P. Bastien and G. Stora, Decomposition de Laustenite en Phase a Sous l'effet des Contraintes Latentes dans les Aciers Inoxydables du Type 18-8, *Comptes Rendus*, 244, 2613 (1957).
- R. Margerand, Etude Cristallographique de la Transformation Gamma+Alpha Provoquee par une Deformation Plastique dans les Aciers 18-8 Instables, *Metaux Corros. Industr.*, 37, 204 (1962).
- 3. J. A. Klostermann and W. G. Burgers, Surface Martensite in Iron-Nickel, Acta Met., 12,355-360 (1964).
- L. Kaufman, A. Leyenaar and J. S. Harvey, The Effect of Hydrostatic Pressure on the Potency of Martensitic Embryos, *Acta Met.*, 8, 270 (1960).
- L. Kaufman, The Free-Energy Changes Attending the Martensitic Transformation in the Iron-Chromium and Iron-Chromium-Nickel Systems, *Trans. AIME*, 215, 218 (1959).
- 6. J. F. Breedis, Trans. AIME, 230, 1583 (1964).