

OFFICE OF NAVAL RESEARCH

Grant or Contract N00014-96-1-0735

96PR05335-00

Technical Report No. 12

Study of Polydispersity of Grafted Poly(dimethylsiloxane) Surfaces Using Single
Molecule Atomic Force Microscopy

by

Sabah Al-Maawali, Jason E. Bemis, and Gilbert C. Walker

Prepared for publication in

in

DISTRIBUTION STATEMENT A
Approved for Public Release
Distribution Unlimited

J. Physical Chemistry

University of Pittsburgh
Department of Chemistry
Pittsburgh, PA

2000

Reproduction in whole or in part is permitted for any purpose of the
United States Government

This document has been approved for public release and sale;
its distribution is unlimited.

20010906 094

Man-made polymers synthesized by free radical or polycondensation mechanisms are known to produce a wide distribution of molecular weights and hence characteristic chain lengths [1-5]. A quantity called 'Polydispersity Index' (*PI*) has been used as a rough guide to understand the distribution of these molecular weights.

$$PI = \overline{M}_w / \overline{M}_n$$

where \overline{M}_w is the weight average molecular weight and \overline{M}_n is the number average molecular weight. A polymer is considered to be monodisperse if *PI* equals 1. Different analytical methods, such as gel permeation chromatography (GPC) and combinations of light scattering and vapor pressure osmometry, are analytical tools that have been traditionally used to study the distribution of these different molecular weights (polydispersity) of polymers in solution [1-4]. On the other hand, there are few direct methods for analyzing lengths of molecules at surfaces [1, 4]. Given the importance of polymer adsorption in technologies ranging from adhesion, lubrication, to biology and medicine [1], new methods for characterizing polydispersity at surfaces are of both practical and fundamental interest.

Single molecule studies using atomic force microscopy may be able to directly characterize such surface polydispersity and this paper aims to examine that potential. Apart from the usual contact adhesion observed in AFM, polymer distortions can be observed when a grafted polymer chain bridges to the AFM tip [6-12] as can be seen in Figure 1. The suggestion that this phenomenon could be used to study polymer polydispersity has been suggested by several authors, [7, 8, 10b, 11] but has not been explored in detail.

REPORT DOCUMENTATION PAGE

Form Approved
OMB No. 0704-0188

Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.

1. AGENCY USE ONLY (Leave blank)	2. REPORT DATE August, 2001	3. REPORT TYPE AND DATES COVERED Technical	
4. TITLE AND SUBTITLE Study of Polydispersity of Polymer Surfaces Using Single Molecule Atomic Force Microscopy		5. FUNDING NUMBERS N00014-96-0735	
6. AUTHOR(S) Al-Mawaali, S.; Bemis, J.; Walker, G. C.,			
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) University of Pittsburgh G-12 Chevron Science Center		8. PERFORMING ORGANIZATION REPORT NUMBER 00-1	
9. SPONSORING / MONITORING AGENCY NAME(S) AND ADDRESS(ES) Department of the Navy, Office of Naval Research 800 North Quincy Street, Arlington, VA 22217-5660		10. SPONSORING / MONITORING AGENCY REPORT NUMBER	
11. SUPPLEMENTARY NOTES			
12a. DISTRIBUTION / AVAILABILITY STATEMENT This document has been approved for public release and sale, its distribution is unlimited.		12b. DISTRIBUTION CODE	
13. ABSTRACT (Maximum 200 words) Single molecule atomic force microscopy (AFM) was used to study the statistical distribution of contour lengths (polydispersity) of polymer chains grafted to a surface. A poly(dimethylsiloxane) (PDMS) monolayer was grafted on a flat silicon substrate by covalently bonding Cl-terminated PDMS to an OH-silicon surface and characterized using contact angle measurements and ellipsometry, and single molecule AFM. A model for the single chain dynamics is presented. The statistical distributions of the polymer contour lengths were found to depend on concentration of the PDMS polymer used in the grafting solutions.			
14. SUBJECT TERMS		15. NUMBER OF PAGES 12	
		16. PRICE CODE	
17. SECURITY CLASSIFICATION OF REPORT Unclassified	18. SECURITY CLASSIFICATION OF THIS PAGE Unclassified	19. SECURITY CLASSIFICATION OF ABSTRACT Unclassified	20. LIMITATION OF ABSTRACT UL