NASA TECHNICAL NOTE

NASA TN D-3247



B063573 NASA TN D-3247 8

608743



DISTRIBUTION STATEMENT A Approved for Public Release Distribution Unlimited

INFLUENCE OF BORON ADDITIONS ON PHYSICAL AND MECHANICAL PROPERTIES OF ARC-MELTED TUNGSTEN AND TUNGSTEN - 1 PERCENT TANTALUM ALLOY

by Peter L. Raffo and William D. Klopp Lewis Research Center ₅ Cleveland, Ohio

20020320 230

,0

NATIONAL AERONAUTICS AND SPACE ADMINISTRATION . WASHINGTON, D. C. . FEBRUARY 1966

NASA TN D-3247

INFLUENCE OF BORON ADDITIONS ON PHYSICAL AND MECHANICAL

PROPERTIES OF ARC-MELTED TUNGSTEN AND

TUNGSTEN - 1 PERCENT TANTALUM ALLOY

By Peter L. Raffo and William D. Klopp

Lewis Research Center Cleveland, Ohio

NATIONAL AERONAUTICS AND SPACE ADMINISTRATION

INFLUENCE OF BORON ADDITIONS ON PHYSICAL AND MECHANICAL PROPERTIES

OF ARC-MELTED TUNGSTEN AND TUNGSTEN - 1 PERCENT TANTALUM ALLOY

by Peter L. Raffo and William D. Klopp

Lewis Research Center

SUMMARY

Start [WThe effects of boron additions on the physical and mechanical properties of arc-melted tungsten and a <u>tungsten</u> <u>1 percent tantalum</u> alloy were investigated.] Boron additions significantly refined the as-melted grain size of tungsten. The 1-hour recrystallization temperature was initially increased by small boron additions (approx. 0.0l atomic percent boron), after which it decreased continuously with increasing boron content. High-temperature tensile tests showed that the boron additions produced an initial rapid rise in strength followed by a leveling off of the strength-composition curve. Boron in solid solution was postulated to be the cause of the rapid increase in strength.

INTRODUCTION

The technology of arc-melted tungsten and its alloys has been limited by the lack of forgeability of the as-melted ingots. This deficiency has been ascribed in part to the relatively large columnar grain size of the ingots. This coarse structure must be broken down by extrusion prior to conventional forging and rolling operations (ref. 1). In addition, grain growth in arc-melted tungsten occurs very rapidly at the contemplated use temperatures (ref. 2), which are generally above 3500° F. Finding a method to refine the as-melted grain size of tungsten and stabilize it against subsequent grain growth at elevated temperatures thus seems desirable.

The most successful method of achieving fine as-melted grain sizes in tungsten appears to be alloying. Attempts at this procedure have resulted in some grain refinement by most of the alloy additions studied previously (refs. 3 to 5). [The most potent grain refiner for tungsten, however, appears to be boron. In addition, it has been demonstrated that as little as 0.005 atomic percent boron is sufficient to decrease the grain growth rate in tungsten by three orders of magnitude in the temperature range 3600° to 4200° F/(ref. 6).

The tungsten-rich end of the tungsten-boron phase diagram has been determined by Goldschmidt et al. (ref. 7) and is shown in figure 1. As can be seen, boron is estimated to have a small but finite solubility in tungsten, approximately 0.2 atomic percent at the eutectic temperature. The eutectic melts at



approximately 4700° F and contains 23 atomic percent boron.

Few attempts, however, appear to have been made to characterize fully tungsten-boron alloys with respect to both their fabricability and their subsequent mechanical properties. The present investigation was directed toward a study of the influence of boron in the range 0.01 to 7.8 atomic percent on these properties. In addition, two ternary tungsten-tantalum-boron (W-Ta-B) alloys were melted to investigate the secondary influence of a typical solid-solution strengthener on the W-B binary.) A portion of this work on both the W-B and the W-Ta-B alloys has appeared elsewhere (ref. 8).

EXPERIMENTAL PROCEDURE

med and al

pay starty

3

The alloy compositions are given in table I. They were prepared by vacuum consumable arc melting of pressed and sintered electrodes compacted from elemental tungsten, boron, and tantalum powders.) Details of these techniques are given in earlier reports (refs. 2, 6, and 8). The resulting ingots, measuring 2 or $2\frac{1}{2}$ inches in diameter were fabricated by extrusion, swaging, and rolling as shown in table I. The ingots were extruded either in a conventional hydraulic press or in the high-energy rate Dynapak. Extrusion temperatures varied from 2700° to 4180° F, and reduction ratios varied from 6 to 10 with a die angle of 120°. Some of the ingots were canned in 0.1-inch-thick molybdenum sheet.

Amount of boron		Interstitial analyses,			As-melted	As-melted	Extrusion	Reduction	Swaging conditions	
Atomic	Weight	(a)			hardness	size,	ature,	14010	Average	Reduction,
percent	(a)	Carbon	Nitrogen	Oxygen	(10-kg load)	cm	<u>о</u> й.		temper- ature, ^O F	percent
	Binary tungsten-boron alloys									
0.01	0.0005	3	11	11	360	0.100	3500	b ₈	2500	78
.03	.002	4	6	2	360	.100	3500	Ba d	2500	78
•10	.006	4	(c)	4	394	.085	3460		NC NC	ne I 70
.23	.015	3		4	409	.000	3700	d ₈	2300 No	ne ro
.59	.035	5	8	8	413	.038	3800	b,e ₈	2700	78
.67	.040	9	10	4	413	.037	4000	d,e ₈	2650	80
1.7	.099	4	(c)	5	380	f.007	4180	^d 6	Nc	ne
7.8	.456	(c)	(c)	(c)	590	(c)	3500	D10	No	ne
Ternary tungsten - 1 atomic percent tantalum - boron alloys										
0.22 1.11	0.013 .065	5 4	(c) (c)	3 3	400 380	(c) (c)	2700 4000	b ₈ d ₈	2500 2500	78 83

TABLE I. - CONSOLIDATION AND FABRICATION CONDITIONS

^aAnalysis on extruded or swaged rod.

^bDynapak extruded.

c_{Not determined.}

^dConventional hydraulic press extruded.

^eClad in 0.100-in.-thick molybdenum sheet.

^fDendritic structure; grain size represents size of dendritic cells.

All the alloys were satisfactorily extruded with the exception of tungsten -7.8 percent boron, which disintegrated during an attempt at Dynapak extrusion. (All compositions are given in atomic percentages.)

Annealing treatments for recrystallization studies at temperatures up to 3200° F were conducted in a hydrogen-atmosphere induction-heated tube furnace. Annealing treatments above 3200° F were conducted in a vacuum furnace (5×10^{-5} mm Hg) with a tantalum or tungsten resistance heater. Temperatures up to 3200° F were measured with a tungsten - tungsten-26 percent rhenium (W - W-26Re) thermocouple placed on the specimens and are believed accurate to $\pm10^{\circ}$ F. Temperatures above 3200° F were measured optically and are estimated to be accurate to $\pm25^{\circ}$ F. The fraction recrystallized was measured by point counting and the average grain diameter by a line intercept method.

Tensile and creep tests were performed in vacuum, and temperature was measured with a W - W-26Re thermocouple tied to the center of the gage length. The gage diameter was 0.14 or 0.16 inch, and the gage length was 1 inch. The crosshead speed was 0.005 inch per minute to yield and 0.05 inch per minute from yield to fracture. More complete details of the testing procedures are documented in reference 2.

3



(a) Tungsten - 0.01 atomic percent boron. X100.



(b) Tungsten - 0.03 atomic percent boron. X100.



(c) Tungsten - 0.25 atomic percent boron. X100.



Figure 2. - As-melted microstructures of binary alloys. Etchant, 3 percent hydrogen peroxide

RESULTS AND DISCUSSION

Ingot metallography. - Photomicrographs were taken of cross sections of slices from the tops of seven of the nine as-melted tungsten-boron alloy ingots (fig. 2). No precipitate was observed in the W - 0.0l percent B alloy (fig. 2(a)). In the alloy W - 0.03 percent B, a precipitate, presumably W_2B , was observed at the grain boundaries (fig. 2(b)). The specks within the grains in both alloys are etch pits and micropores. Increasing the boron content resulted in a general increase in the volume fraction of the boride phase (figs. 2(c) to (h)). The distribution of the phase, however, varied with boron content tent. In the W - 0.25 percent B alloy, the boride was present as a Widmanstätten precipitate within the grains (figs. 2(c) and (d)) in addition to the grain boundary film and round intragranular particles seen in the alloys containing 0.03 to 1.69 percent B. The microstructure of the W - 0.1 percent B alloy (not



(boiling) or lactic-nitric-hydrofluoric acid etch. Reduced approximately 30 percent in printing.

shown) was similar to that of the W - 0.25 percent B alloy. Increasing the boron content to 0.47 and 0.67 percent (figs. 2(e) and (f)) increased the amount of intergranular boride film and spherical intragranular boride particles, but no Widmanstätten precipitate was observable. Similar changes in the character of the boride have been noted by other investigators (ref. 7). At higher boron contents (1.7 and 7.8 percent B), dendritic structures were observed as shown in figures 2(g) and (h). In addition, in the W - 7.8 percent B alloy (fig. 2(h)), a pronounced fine interdendritic eutectic was visible at high magnifications in the dark phase.

From the W-B phase diagram (ref. 7) as reproduced in figure 1 (p. 2), alloys with greater than approximately 0.2 percent B (the maximum solubility of boron in tungsten) should show a eutectic phase, while alloys with compositions below this amount should not. The black phase at the grain boundaries in figures 2(e) and (f) corresponds to the expected eutectic, since the grain boundaries in these alloys are rounded and thus imply liquid contact during solidification. The round intragranular particles probably precipitated from the solid state because of a decreasing solubility of boron in tungsten at temperatures in the vicinity of the eutectic temperature and spheroidized after solidification of the eutectic.

With regard to the solid solubility limit, the present work shows that no precipitate was observed in the W - 0.0l percent B alloy at magnifications up to 1500, while a precipitate was observed at 0.03 percent B. The phase diagram in reference 7 gives the solubility at 1832° F as 0.1 percent. Although comparison of the present results with the phase diagram is not strictly valid since the cooling of the ingot occurs under nonequilibrium conditions, the present results do suggest that the microstructures are representative of a temperature lower than 1832° F or, more likely, that the solubility at temperatures in the vicinity of 1832° F is much lower than the 0.1 percent reported in ref - erence 7.

The intragranular boride in the W - 0.25 percent B alloy evidently precipitated entirely from the solid state and its Widmanstätten character suggests a lower temperature precipitation than the precipitation of boride in the higher boron content alloys. The Widmanstätten phase was observed in the W - 0.1 percent B alloy also but not in the W - 0.03 percent B alloy. In addition, a Widmanstätten phase was also observed in the W - 1 percent Ta - 0.22 percent B alloy (not shown in the figures). This type of precipitation thus appears to be a characteristic of alloys containing between about 0.03 and 0.25 percent B, which is approximately the solid solubility limit as determined in reference 7. The nature of this phase, its habit plane, and the temperature ranges where it precipitates, however, are not derivable from the limited observations made in this study.

Grain refinement in as-melted ingots. - The average ingot grain diameter is plotted in figure 3 as a function of boron content. Boron appreciably refined the as-melted grain size of tungsten. For example, 0.67 percent B decreased the grain size of unalloyed tungsten from 0.175 to 0.037 centimeter. At 1.7 percent B, an array of polyhedral grains was no longer observed, and the measured grain diameter was determined as the dendritic cell size.

The decrease in grain size with increasing boron content suggests that grain refinement occurred by "constitutional supercooling." Constitutional supercooling is a direct consequence of the difference in solubility of a given solute in the liquid and in the solid (refs. 9 and 10). It is found in those systems in which the liquidus temperature decreases with increasing solute content. Thus, in order for the solid to freeze, solute must be rejected to the liquid, and as this process is slower than the rate of heat extraction by the mold walls, the rate of advancement of the solid-liquid interface is slow. This process eventually leads to a reduced as-cast grain size. Solutes which have a low value of the distribution coefficient, that is, the ratio of the solubility in the solid to that in the liquid, thus tend to be effective grain refiners (ref. 10).

The maximum distribution coefficient for the W-B system was calculated from the phase diagram as 9.1×10⁻³. This value would result in a solute concentration in front of the solid-liquid interface of approximately 100 times



that of the bulk liquid and would be expected to produce a substantial decrease in the rate of the advance of the solid-liquid interface.

Further evidence for the mechanism of constitutional supercooling is the transition from a polyhedral to a dendritic mode of solidification at 1.7 percent B (fig. 2(g), p. 5). This transition has been found previously to be a feature of alloys which solidify by constitutional supercooling (ref. 11). During solidification, a large amount of solute occupies the region adjacent to the solid-liquid interface. At compositions where this buildup of solute is such that it becomes more and more difficult to diffuse this solute away from a planar solid-liquid interface, the interface breaks into the dendritic type and thus produces more surface area and, hence, a larger number of sites for the solute to reside.

Forgeability studies. - Cylinders measuring 3/4 inch in diameter and 5/8 inch high were spark-machined from selected W-B alloys and an ingot of unalloyed tungsten. They were heated to 2400° to 2800° F in hydrogen and rapidly transferred to a drop hammer, where they were deformed approximately 50 percent in two to four blows, with intermediate heating between blows. Photographs of the forged cyclinders are shown in figure 4. Forging by this technique could not be performed without the appearance of a large amount of edge cracking in the cylinders. The amount of cracking did not appear to be dependent upon temperature in the narrow range studied. The edge cracking was at a minimum for the W - 1.7 percent B alloy, which corresponded to the fine celled (0.007 cm) dendritic structure shown in figure 2(g)(p. 5). Metallographic examination of sections of the forged cylinders showed that the edge cracks were confined mainly to the surface. No forging experiments were performed on the W-Ta-B alloys.

If these results are combined with the extrusion data in table I(p. 3), [it] can be seen that there was no systematic dependence of the fabricability on $[e^{2}]$

7



(o) Forging pronout competature, 2100 Fr

Figure 4. - Upset forged cylinders of arc-melted tungsten and tungsten-boron alloys. Specimens shown 80 percent of full size.

boron content (0.01 to 1.7 percent B) or grain size.) The only instance where a lack of fabricability was noted was in the W - 7.8 percent B alloy, which disintegrated during an attempt at extrusion by the Dynapak method. This failure was probably due to the rapid input of energy in this process, which caused the temperature of the billet to exceed the eutectic temperature in the tungstenboron system and consequently melt along the grain boundaries. This conclusion was borne out by the observation of a glassy coating on the surface of the pieces remaining from this extrusion.

Recrystallization and grain growth - Samples of the W-B and W-Ta-B alloys which had been swaged approximately 60 to 80 percent after extrusion were annealed for 1 hour in the temperature range 2400° to 4200° F.) The samples were metallographically prepared, and hardness (10-kg load), grain size, and the fraction recrystallized were measured on each specimen. These data are given in table II.

The recrystallization temperature, ^S defined as the temperature at which the structure was 50 percent recrystallized in 1 hour, is plotted in figure 5 as a function of boron content for both binary W-B and ternary W-Ta-B alloys. Boron additions produced an initial rapid increase of the recrystallization temperature from an average value of 2700° F for unalloyed arc-melted tungsten of a similar percentage reduction (ref. 2) to 3140° F for the W - 0.01 percent B alloy. Increasing the boron content then produced a continuous decrease in the recrystallization temperature to 2630° F for the W - 0.67 percent B alloy. The recrystallization temperature for the W-Ta-B alloys behaved in a fashion similar to that of the binary W-B alloys. The recrystallization temperature decreased from 3000° F for a nonboron-containing W - 1 percent Ta alloy (unpublished data) to 2800° F for the alloy containing 1.11 percent B. The recrystallization

TABLE II. - RECRYSTALLIZATION OF TUNGSTEN-

BORON AND TUNGSTEN-TANTALUM-BORON ALLOYS

		· · · · · · · · · · · · · · · · · · ·							
Annealing condition		Fraction recrys-	Average grain	Vickers hardness					
Temper-	Temper- Time.		diameter, cm	(10-kg load)					
ature,	hr,								
Tungsten - 0.01 percent boron									
As swa	ared	0		503					
2900	lgeu 1	.02		488					
3000	1	.16		429 421					
3200	ī	1.00	0.0023	376					
	Tungsten - 0.03 percent boron								
As swa	iged	0		491					
2800		.05		465					
3100	Į	.69	0.0076	425					
3200		1.00	0.0036	423					
0.0.000	Tungs	1 - 0.2	percent	514					
2400	I l	ŏ		497					
2600	1			518					
2600	4	.19		512					
2600	6	.23		464					
2700	2	.05		499					
2700	3	.63		474					
2700	$\frac{4}{1/4}$.95		439 529					
2800	1/2	.91		442					
2800 3200	1	1.00	.0021						
Tungsten - 0.59 percent boron									
As swa	aged	0		504					
2600	1 1/4	0		468 546					
2700	1/2	.46		520					
2700	3/4	.60		478 460					
2700	1	1.00		446					
2800	1	1.00	0.0020	401					
3200	1	1.00	,0025						
	Tungs	ten - 0.6	7 percent	boron					
As swa 2600	aged			506 470					
2700	1/4	0 00		561					
2700	1/2 3/4	.28		532 446					
2700	1	.96		446					
2700	112	1.00	0.0017	444					
2800	ļ	1.00	.0020	397					
5200	1 ¹		1.0022						
0.22 percent boron									
As sw	aged	0		528					
2800	1 1	.17		483					
3000	1	1.00	0.0025	416					
	Tungsten - 1 percent tantalum - 1.11 percent boron								
As sw	aged	0		548					
2700	1	.02		498					
3000	ĺi	1.00	0.0027	429					
	1								



Figure 5. - Influence of boron on 1-hour recrystallization temperature of tungsten and a tungsten - 1 percent tantalum alloy. Average value for unalloyed tungsten from reference 2; average value for tungsten -1 atomic percent tantalum (no boron) from unpublished data.

Ttemperature of the W-Ta-B alloys was higher than that of similar binary W-B alloys, which reflected the effect of tantalum in solid solution.

Specimens of alloys of tungsten with 0.25, 0.59, and 0.67 percent boron were also annealed at 2700° F for times up to 4 hours.) The fraction recrystallized and hardness are plotted in figure 6 as functions of time. In figure 6(a), the resistance to recrystallization decreases as the boron content is increased from 0.25 to 0.67 percent boron.) In figure 6(b), maximum hardness is observed during the early stages of recrystallization. The maximum hardness is of the order of 4 to 10 percent greater than that for the as-swaged material. The initial increase in hardness on annealing at 2700° F) (fig. 6(b)) may be a strain aging phenomenon, involving the precipitation of fine boride particles on dislocations and/or subgrain boundaries. Such hardness maximums have been observed previously in relatively impure tungsten wire (ref. 12) and in ironmanganese alloys (ref. 13).

(The initial increase in recrystallization temperature at low boron contents is probably due to boron in solid solution.) Boron in solid solution in tungsten reduces the grain boundary migration rate of unalloyed tungsten by three orders of magnitude (ref. 6). This decrease in the grain boundary migration rate by dissolved solutes is similar to that observed in other alloy systems (refs. 14 and 15). Explaining the decrease in recrystallization temperature observed upon adding additional boron, however, requires that the nucleation aspect of recrystallization be considered. Leslie, Plecity, and Michalak (ref. 14), for example, found that an air-melted low-carbon steel (0.06 weight percent) had a faster rate of recrystallization than higher purity vacuum or zone melted iron. They attributed this fact to a greater number of nucleation sites in the lowcarbon steel, which could outweigh any decrease in the boundary migration rate caused by the higher solute content in the steel.







Figure 7. - Tungsten - 0.25 atomic percent boron annealed at 2700° F for 1 hour. Arrows point to recrystallized grains originating in vicinity of boride particles; X250. Reduced approximately 30 percent in printing.

In the case of the tungstenboron alloys, the observed borides had particle sizes ranging from 1 to 8 microns. During the deformation of these alloys, gross dislocation entanglements are believed to be formed in the vicinity of the boride particles in an effort to maintain strain continuity. Such dislocation entanglements near included particles have been observed in a variety of materials (refs. 16 and 17). This localized region of high strain energy may act as a preferred nucleation site for a recrystallized grain during subsequent annealing.

Metallographic studies conducted on the tungsten-boron alloys revealed the important feature shown in fig-

ure 7. Colonies of recrystallized grains clustered around two boride particles (see arrows) suggest that the grains were nucleated by the particle or in the region immediatley adjacent to it. English and Backofen (ref. 18) also observed a similar type of particle-nucleated recrystallization in hot-worked silicon iron. The large boride particles thus appear to be responsible for the decrease in recrystallization temperature by acting as preferred nucleation sites.

High-temperature tensile and creep studies./-High-temperature tensile data obtained on swaged and annealed alloys are given in tables III and IV, and plotted in figures 8 and 9. Most of the alloys were recrystallized by annealing at 3600° F for 1 hour prior to testing. The alloys of tungsten with 0.1 and 0.47 percent boron, however, recrystallized during extrusion and were evaluated in this condition.

Figure 8 shows the effect of temperature and boron content on the ultimate tensile strength of the binary W-B alloys. An initial rapid increase in strength as small amounts of boron were added was observed and was followed by a flattening of the strength-composition curves to an almost constant value at higher boron contents. The strength increase by the addition of 0.03 percent boron (the lowest boron content tested) was 50 percent at 2500° F, 47 percent at 3000° F, and 20 percent at 3500° F.

The addition of tantalum to selected W-B alloys produced additional strengthening (fig. 9). For example, the strength at 3500° F of a W - 0.22 percent B alloy (interpolated from the curve in fig. 8) was 13 800 psi. The addition of 1 percent tantalum increased the tensile strength to 18 600 psi. Increasing the boron content to 1.11 percent in the W - 1 percent Ta alloy did not appreciably alter the strength, in agreement with the trend observed in the binary alloys. In addition, the swaged W-Ta-B alloys which were tested at 3000° F had approximately the same strength as the annealed specimens. These alloys recrystallized during testing at 3000° F; the low resistance to recrys-

r						
ł	TABTE	TTT	_	HTCH_TEMPERATIRE	TENSTLE	PROPERTIES
۰.	TUDIE	• +•	_	UTGU-TERR DRVTOVE		111011111111

.

OF BINARY TUNGSTEN-BORON ALLOYS

Annealing condition		Test temper-	0.2 Percent offset wield	VV Ultimate tensile	Elon- gation,	Reduc- tion in	Average grain diameter.	
Temper- ature,	Time, hr	F	stress,	psi	percent	percent	cm	
^O F							(a)	
Tungsten - 0.03 percent boron								
3600	1	2500		31 500	28	>98	0.0097	
		3000 3500	12 520 5 530	20 650 11 520	48 42	>98 >98	.0097 .0097	
		LTu:	ngsten - 0.10) percent	boron	L		
As ext	ruded	2500	15 520	33 000	38	86		
		3000	8 170	21 620	76 79	>98		
			3 170	7 730	88	>98		
	Tungsten - 0.25 percent boron							
3600	1	2500	18 900	34 430	33	98	0.006	
		3000 3500	6 030 5 190	24 700 13 220	62 62	98 82	.006 .006	
Tungsten - 0.47 percent boron								
As ext	As extruded		17 000	36 900	36	73		
		3000 3500	6 520	27 500 15 900	61	98		
Tungsten - 0.59 percent boron								
3600	l	2500	13 090	32 100	31	86	0.0065	
		3000	8 110	25 300	50	94	.0065	
		3500	6 380	13 100	86	98	.0065	
Tungsten - 0.67 percent boron								
3600	1	2500	8 870	34 200	56	86	0.0054-	
		3000 3500	6 570	14 360	75 84	98	.0054	

^aGrain diameter measured on undeformed buttonhead of tensile specimens; value reported is an average of values for the three test temperatures.

TABLE IV. - HIGH-TEMPERATURE TENSILE PROPERTIES

Annealing condition		Test temper-	Yield stress,	Ultimate tensile	Elon- gation,	Reduc- tion in	Average grain	
Temper- ature, OF	Time, hr	o _F	psi	psi	percent	percent	cm	
די	ungstei	n - 1.0 p	percent	tantalum -	0.22 per	rcent bor	ron	
As swaged		2500 3000 3500	43 600 14 100 8 880	84 300 36 900 18 600	13 57 87	69 56 98	Wrought 0.0032	
Tungsten - 1.0 percent tantalum - 1.11 percent boron								
As swaged		2500 3000 3500	53 800 13 900 9 210	85 400 33 300 16 800	14 71 97	72 87 96	Wrought 0.0013 .0018	
Tungsten - 1.0 percent tantalum - 0.22 percent boron								
3200	l	2500 3000	24 400 14 420	55 600 37 900	31 60	79 53	0.0025 .0028	
Tungsten - 1.0 percent tantalum - 1.11 percent boron								
3600	1	2500 3000 3500 4000	20 600 16 000 9 320 5 610	50 000 36 500 18 300 9 420	50 79 87 147	78 87 94 97	0.0026 .0026 .0026 .0031	

OF TUNGSTEN-TANTALUM-BORON ALLOYS

tallization effected by large boron additions was thus substantiated. All the binary and ternary alloys exhibited high ductilities (see tables III and IV) at these temperatures, although there was no systematic variation with boron content.

Step load creep data were also obtained on four binary W-B alloys at 3500° F and at 2500°, 3000°, and 3500° F for the W - 1 percent Ta - 1.11 percent B alloy by use of the test methods described in reference 2. Figure 10 is a bar graph showing the interpolated stress at a linear creep rate of 10-6 second⁻¹ at 3500° F, which corresponds to a rupture life of approximately 50 hours (ref. 2). There was a large degree of scatter in the data, and the only trends which were observed were an initial rapid increase in strength at the 0.03 percent boron level (as also noted in the tensile results) and an apparent maximum in the creep strength at low boron levels.

Figure 11 illustrates the influence of temperature on the creep strength of the W - 1 percent Ta - 1.11 percent B alloy. The stress at a rupture life of 50 hours at 2500° F was estimated from the transient creep data (ref. 2) as no steady-state creep was observed at this temperature. The creep strength for the W-Ta-B alloy was slightly higher than any of the binary W-B alloys tested (see fig. 10). (The percentage increase in creep strength over that of unalloyed tungsten) for this W-Ta-B alloy (varied from 320 percent at 2500° F to) -- P K E har we have to all all

14



tested in recrystallized condition; unalloyed tungsten data from reference 2.







Figure 10. - Creep strength of tungsten-boron and tungsten-tantalum-boron alloys at 3500° F.



Figure 11. - Effect of temperature on creep strength of tungsten-tantalum-boron alloys.

80 percent at 3500° F.

An attempt was made to rationalize the nature of the initial rapid strengthening by the boron additions observed in the tensile and creep tests. There are three possibili-7 Pl8 (1) solid-solution strengthening, (2) ties: strengthening by a boride dispersion, or (3) strengthening by grain-size refinement. The latter effect has been noted in unalloyed tungsten (ref. 2) where the ultimate tensile strength varied by 40 percent for a grain-size change of twentyfold. The ultimate tensile strength of the W - 0.034 percent B alloy was thus compared with the strength of unalloyed tungsten of the same grain size from the plots in reference 2, and approximately 90 percent of the strengthening still remained unaccounted for. Recourse to possibility (1) or (2) must thus be made to explain the observations. Since the solid solubility of boron in tungsten is greater than 0.1 atomic percent at temperatures greater than 2500° F (fig. 1, p. 2), the probability that boron in solid solution contributed to the observed strength is higher than that boride precipitates contributed. Strengthening by boron in solid solution will thus be considered first.

Fleischer and Hibbard (ref. 19) examined the rate of solid-solution strengthening in various alloy systems by a comparison of the shear-modulus-compensated rate of alloy

TABLE V. - COMPARISON OF RATE OF ALLOY

STRENGTHENING IN VARIOUS MATERIALS

Alloy	Temper- ature, o _F	$\frac{l}{G} \left(\frac{d\tau}{dc} \right) $ (a)
Substitutional alloying elements in aluminum, copper, iron, and columbium (ref. 19)	Room	0.05 - 0.10
Interstitial carbon in iron, (ref. 19)	Room	5
Interstitial nitrogen in columbium (ref. 19)	Room	2
Tungsten-boron alloys (present investigation)	2500 3000 3500	0.85 .58 .19

^aValues of G determined from approximate relation $G = \frac{3}{8} E$, where E is Young's modulus (Young's modulus from ref. 22). Shear stress τ taken to be half the tensile stress.

strengthening $(1/G)(d\tau/dc)$, where G is the shear modulus, τ is the shear stress, and c is the atomic fraction of solute. An approximate value of $(1/G)(d\tau/dc)$ was obtained in the present work by assuming that a straight line relation existed between the strength of unalloyed tungsten and the strength of the W - 0.03 percent B alloy. This assumption would give the minimum rate of alloy strengthening (between these two points), since the real curve connecting these two points might be of some other form and hence have a larger initial slope. The values obtained are compared in table V with data for other alloy systems taken from reference 19. As noted in table V, the value of (1/G) $(d\tau/dc)$ for the W-B alloys decreases with increasing temperature, which suggests a decreased interaction of boron atoms with dislocations at elevated temperatures. Fleischer

and Hibbard (ref. 19) correlate the magnitude of $(1/G)(d\tau/dc)$ with the type of lattice distortion present in the lattice due to the solute atom. High values of $(1/G)(d\tau/dc)$ represent strengthening by tetragonal distortions induced by interstitials in solid solution, while low values suggest hemispherical distortions by substitutional atoms. The values of $(1/G)(d\tau/dc)$ for W-B alloys are intermediate between the typical values given by reference 19 for interstitial and substitutional solid solutions (table V). There is some doubt in the literature as to whether boron occupies an interstitial or substitutional site in body-centered-cubic metals (refs. 8 and 20). It has been suggested that the boron atom may occupy both sites simultaneously. This possibility might explain the intermediate value of $(1/G)(d\tau/dc)$ found in this investigation. Additional support for this proposition is found in reference 21 in which the data from this study are compared with data on binary tungsten-carbon alloys. Carbon has been definitely shown to be an interstitial in tungsten (ref. 8) and in contrast to the boron additions to produce an initial decrease in the strength of tungsten at 2500° to 4000° F. The initial rapid increase in strength with the boron additions thus is more suggestive of an interstitial-substitutional balance with the balance tending toward a substitutional solid solution.

In addition, there still remains the possibility that fine boride precipitates in the W - 0.03 percent B alloy may have contributed to the initial strengthening. Additions of boron of greater than about 0.25 percent, however, did not result in appreciable additional increases in strength. This lack of additional strengthening implies that the dispersion of boride existing in these alloys is not an effective strengthener and that the strength advantage of any of the tungsten-boron alloys over unalloyed tungsten is predominantly due to boron in solid solution.

CONCLUDING REMARKS

One of the main purposes for this work was to determine whether a distinct improvement in forgeability would result from grain refinement of arc-melted tungsten by boron additions. The limited studies performed showed that, although a significant amount of grain refinement of the ingot structure was effected by boron, an improvement in forgeability was not observed. It is possible that the presence of the brittle boride phase in these alloys negated the effect of the finer grain structure of the alloys and resulted in the insignificant improvements in forgeability.

CONCLUSIONS

In an investigation of the influence of boron additions on the physical and mechanical properties of arc-melted tungsten and tungsten - 1 percent tantalum alloy, the following conclusions were drawn:

1. Boron appreciably refines the as-melted grain size of arc-melted tungsten. This refinement has only a minor effect on ingot forgeability.

2. The grain refinement of tungsten by boron is due to "constitutional supercooling," which occurs because of the small distribution coefficient of boron in tungsten.

3. A boron addition of 0.0l atomic percent produced an initial rapid increase in the 1-hour recrystallization temperature. Additions of boron greater than this amount continuously decreased the recrystallization temperature because the boride particles acted as sites for nucleation of recrystallization.

4. Boron additions to arc-melted tungsten result in an initial rapid increase in the 2500° to 3500° F tensile strength followed by a leveling off of the strength-composition curve. The initial increase is presumably due to boron in solid solution. The distortion effect of boron in solid solution is intermediate between that of a substitutional and interstitial atom.

5. Tantalum additions to the binary tungsten-boron alloys raised the recrystallization temperature and increased the elevated temperature tensile and creep strength.

Lewis Research Center, National Aeronautics and Space Administration, Cleveland, Ohio, October 8, 1965.

REFERENCES

- 1. Barth, V. D.: The Fabrication of Tungsten. Rept. No. 115, Defense Metals Info. Center, Aug. 14, 1964.
- Klopp, William D.; and Raffo, Peter L.: Effect of Purity and Structure on Recrystallization, Grain Growth, Ductility, Tensile, and Creep Properties of Arc-Melted Tungsten. NASA TN D-2503, 1964.
- 3. Semchysen, M.; and Barr, R. Q.: Development of Tungsten-Base Alloys. Climax Molybdenum Co., June 20, 1961.
- 4. Carlson, R. G.: Grain Refinement and Workability of Some Tungsten-Base Alloys. Paper Presented at AIME Meeting, Detroit (Mich.), Oct. 23-26, 1961.
- 5. Semchysen, M.; and Barr, R. Q.: Molybdenum and Molybdenum Containing Refractory Alloys. Refractory Metals and Alloys, Intersci. Pub., Inc., 1961, pp. 283-316.
- 6. Raffo, Peter L.; and Hehemann, Robert F.: Grain Growth in Dilute Tungsten-Boron Alloys. NASA TN D-2649, 1965.
- 7. Goldschmidt, H. J.; Catherall, E. A.; Ham, W. M.; and Oliver, D. A.: Investigation Into the Tungsten-Rich Regions of the Binary Systems Tungsten-Carbon, Tungsten-Boron and Tungsten-Beryllium. Rept. No. ASD-TDR-62-25, pt. II, Birmingham Small Arms, Ltd., June 1963.
- 8. Raffo, Peter L.; Klopp, William D.; and Witzke, Walter R.: Mechanical Properties of Arc-Melted and Electron-Beam-Melted Tungsten-Base Alloys. NASA TN D-2561, 1965.
- 9. Form, G. W.; and Wallace, J. F.: General Principles of the Solidification of Metals. Mod. Castings, vol. 37, no. 4, Apr. 1960, pp. 145-156.
- 10. Wallace, John F.: Grain Refinement of Steels. J. Metals, vol. 15, no. 5, May 1963, pp. 372-376.
- 11. Morris, W.; Tiller, W. A.; Rutter, J. W.; and Winegard, W. C.: Conditions for Dendritic Growth in Alloys. Trans. ASM, vol. 47, 1955, pp. 463-472.
- 12. Lement, B. S.; Thomas, D. A.; Weissmann, S.; Owen, W. S.; and Hirsch, P. B.: Substructure and Mechanical Properties of Refractory Metals. Rept. No. ASD-TR-61-181, pt. II, Manlabs, Inc., Oct. 1962.
- 13. Austin, Charles R.; Luini, L. A.; and Lindsay, R. W.: Annealing Studies of Cold-Rolled Iron Binary Alloys. Trans. ASM, vol. 35, 1945, pp. 446-484.
- 14. Leslie, W. C.; Plecity, F. J.; and Michalak, J. T.: Recrystallization of Iron and Iron-Manganese Alloys. Trans. AIME, vol. 221, no. 4, Aug. 1961, pp. 691-700.

- 15. Gordon, Paul; and Vandermeer, R. A.: The Mechanism of Boundary Migration in Recrystallization. Trans. AIME, vol. 224, no. 5, Oct. 1962, pp. 917-928.
- 16. Lawley, A.; and Gaigher, H. L.: Dislocation Uncertainty in Relation to Observations on BCC Molybdenum. Appl. Phys. Letters, vol. 2, no. 7, Apr. 1, 1963, pp. 123-124.
- Barnby, J. T.; and Smith, E.: The Deformation of an Austenitic Steel Containing a Distribution of Coarse Precipitates. Acta Met., vol. 12, no. 12, Dec. 1964, pp. 1353-1358.
- 18. English, A. T.; and Backofen, W. A.: Recrystallization in Hot-Worked Silicon-Iron. Trans. AIME, vol. 230, no. 3, Apr. 1964, pp. 396-406.
- 19. Fleischer, R. L.; and Hibbard, W. R.: Solution Hardening. Vol. 1 of The Relation Between the Structure and Mechanical Properties of Metals, Nat. Phys. Lab., 1963, pp. 261-297.
- 20. Hayashi, Yasunori; and Sugeno, Takesi: Condition of Boron in Alpha-Iron. Phys. Soc. Japan J., vol. 19, no. 7, July 1964, p. 1251.
- 21. Raffo, Peter L.; and Klopp, William D.: Mechanical Properties of Solid-Solution and Carbide-Strengthened Arc-Melted Tungsten Alloys. NASA TN D-3248, 1966.
- 22. Armstrong, Phillip E.; and Brown, Harry L.: Dynamic Young's Modulus Measurements Above 1000^o C on Some Pure Polycrystalline Metals and Commercial Graphites. Trans. AIME, vol. 230, no. 4, Aug. 1964, pp. 962-966.

"The aeronautical and space activities of the United States shall be conducted so as to contribute . . . to the expansion of human knowledge of phenomena in the atmosphere and space. The Administration shall provide for the widest practicable and appropriate dissemination of information concerning its activities and the results thereof."

--- NATIONAL AERONAUTICS AND SPACE ACT OF 1958

NASA SCIENTIFIC AND TECHNICAL PUBLICATIONS

TECHNICAL REPORTS: Scientific and technical information considered important, complete, and a lasting contribution to existing knowledge.

TECHNICAL NOTES: Information less broad in scope but nevertheless of importance as a contribution to existing knowledge.

TECHNICAL MEMORANDUMS: Information receiving limited distribution because of preliminary data, security classification, or other reasons.

CONTRACTOR REPORTS: Technical information generated in connection with a NASA contract or grant and released under NASA auspices.

TECHNICAL TRANSLATIONS: Information published in a foreign language considered to merit NASA distribution in English.

TECHNICAL REPRINTS: Information derived from NASA activities and initially published in the form of journal articles.

SPECIAL PUBLICATIONS: Information derived from or of value to NASA activities but not necessarily reporting the results of individual NASA-programmed scientific efforts. Publications include conference proceedings, monographs, data compilations, handbooks, sourcebooks, and special bibliographies.

Details on the availability of these publications may be obtained from:

SCIENTIFIC AND TECHNICAL INFORMATION DIVISION

NATIONAL AERONAUTICS AND SPACE ADMINISTRATION

Washington, D.C. 20546