SMC-TR-03-09

AEROSPACE REPORT NO. TR-2002(8565)-7

# Thermomechanical Properties of Selected Space-Related Materials

30 September 2002

Prepared by

W. H. CHILDS Space Materials Laboratory Laboratory Operations

Edited by Tom Park and Sandra Gyetvay

Prepared for

SPACE AND MISSILE SYSTEMS CENTER AIR FORCE SPACE COMMAND 2430 E. El Segundo Boulevard Los Angeles Air Force Base, CA 90245

Engineering and Technology Group



APPROVED FOR PUBLIC RELEASE; DISTRIBUTION UNLIMITED

# 20030312 132

This report was submitted by The Aerospace Corporation, El Segundo, CA 90245-4691, under Contract No. F04701-00-C-0009 with the Space and Missile Systems Center, 2430 E. El Segundo Blvd., Los Angeles Air Force Base, CA 90245. It was reviewed and approved for The Aerospace Corporation by P. D. Fleischauer, Principal Director, Space Materials Laboratory. Michael Zambrana was the project officer for the Mission-Oriented Investigation and Experimentation (MOIE) program.

This report has been reviewed by the Public Affairs Office (PAS) and is releasable to the National Technical Information Service (NTIS). At NTIS, it will be available to the general public, including foreign nationals.

This technical report has been reviewed and is approved for publication. Publication of this report does not constitute Air Force approval of the report's findings or conclusions. It is published only for the exchange and stimulation of ideas.

wheen

Michael Zambrana SMC/AXE

|  |                             |                       | F                             | orm Approved   |  |
|--|-----------------------------|-----------------------|-------------------------------|--|--|
| REPORT DOCUMENTATION PAGE  |                             |                       | PAGE                          | OM   | 3 No. 0704-0188                                |
| Public reporting and maintaining the data needed, and completing and reviewing this collection of information. Send comments requiring this burden estimate or any other aspect of this<br>collection of information, including suggestions for reducing this burden to Department of Defense, Washington Headquarters Services, Directorate for Information Operations and<br>Reports (0704-0188), 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person<br>shall be subject to any penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number. PLEASE DO NOT RETURN YOUR FOR<br>TO THE ABOVE ADDRESS. |                             |                       |                               | earching existing data sources,<br>imate or any other aspect of this<br>for Information Operations and<br>any other provision of law, no person<br>ASE DO NOT RETURN YOUR FORM |  |
| 1. REPORT DATE (<br>30-09  | <b>DD-MM-YYYY)</b><br>-2002 | 2. REPORT TYPE        |                               | 3. DATES CO  | VERED (From - To)                              |
| 4. TITLE AND SUB   | TITLE                       |                       |                               | 5a. CONTRAC  | T NUMBER                                       |
| Thermomechanical Properties of Selected Space-Related Mate   |                             |                       | terials                       | 5b. GRANT N  | UMBER  |
|  |                             |                       |                               | 5c. PROGRAM  | LEMENT NUMBER                                  |
| 6. AUTHOR(S)   |                             |                       |                               | 5d. PROJECT  | NUMBER   |
| W. H. Childs   |                             |                       |                               | 5e. TASK NUI   | MBER   |
| Edited by Tom Pa   | ark and Sandra Gy           | etvay                 |                               | 5f. WORK UN  | IT NUMBER                                      |
| 7. PERFORMING C  | RGANIZATION NAI             | IE(S) AND ADDRESS(ES) |                               | 8. PERFORMI<br>REPORT N  | NG ORGANIZATION                                |
| The Aerospace C  | orporation                  |                       |                               |  |  |
| El Segundo, CA 9   | 00245-4691                  |                       |                               | T  | R-2002(8565)-7                                 |
| 9. SPONSORING /<br>Space and Missile   | MONITORING AGE              | NCY NAME(S) AND ADDR  | ESS(ES)                       | 10. SPONSOF  | WONITOR'S ACRONYM(S)<br>SMC                    |
| Air Force Space (  | Command                     |                       |                               | 11. SPONSOF  | MONITOR'S REPORT                               |
| Los Angeles Air  | Force Base, CA 90           | 245                   |                               | NUMBER(  | (S)  |
|  |                             | TEMENIT               |                               | 5  | SMC-TR-03-09                                   |
| Approved for put   | blic release; distrib       | ution unlimited.      |                               |  |  |
| 13. SUPPLEMENT   | ARY NOTES                   |                       |                               |  |  |
| 14. ABSTRACT   |                             |                       |                               |  |  |
| Room-temperature values for nine thermomechanical material properties of 130 space-related materials have been tabulated in this report. These data are essential for analyses to determine material response to pulsed radiation that relate to survivability assessments of space systems based on above- and below-ground nuclear weapons effects experiments. The nine properties tabulated for each of the 130 materials include density, specific heat (constant pressure), specific heat (constant volume), Poisson's ratio, Grüneisen constant, adiabatic sound velocity, Young's modulus, isothermal bulk modulus, and volumetric coefficient of thermal expansion.   |                             |                       |                               |  |  |
| Various appropriate elements, oxides, carbides, halides, metallic alloys, semiconductors, optical materials, glasses, plastic<br>and graphites are included in the tabulation. The majority of the materials are high density, low porosity, isotropic and<br>polycrystalline in form.   |                             |                       |                               |  |  |
| <b>15. SUBJECT TERMS</b><br>Thermomechanical properties, Grüneisen volumetric thermal expansion, Poisson's ratio, Heat capacity, Young's modulus,<br>Sound velocity  |                             |                       |                               |  |  |
| 16. SECURITY CL  | ASSIFICATION OF:            |                       | 17. LIMITATION<br>OF ABSTRACT | 18. NUMBER<br>OF PAGES<br>160  | 19a. NAME OF<br>RESPONSIBLE PERSON<br>Tom Park |
| a. REPORT  | b. ABSTRACT                 | c. THIS PAGE          | 1 ·                           |  | 19b. TELEPHONE                                 |
| UNCLASSIFIED   | UNCLASSIFIED                | UNCLASSIFIED          |                               |  | <i>code)</i><br>(310)336-5503                  |
|  | I                           |                       | L                             | _ls  | l<br>tandard Form 298 (Rev. 8-98)              |

...

Standard Form 298 (Rev. 8-98) Prescribed by ANSI Std. 239.18

### Dedication

For Bill Childs; colleague and friend.

#### Foreword

The analysis of radiation interaction with, and damaging effects to, operational military systems requires a comprehensive database of thermophysical and other properties, covering the diversity of materials to be found in such systems, including spacecraft, launch and reentry vehicles, and their components. Computations of nuclear weapon or directed-energy weapon effects requires specialized knowledge and expertise, together with experience using the appropriate computer codes.

With the cessation of the cold war, efforts addressing the vulnerability, survivability, and hardening of military systems were severely scaled back. Consequently, the personnel who had maintained the associated analytical technologies were reassigned, retired, or discharged. Much knowledge and capability was lost in the process.

The Editors of this report have attempted to partially mitigate such losses by preserving this previously unpublished database of equation-of-state and related materials properties data, together with a tutorial on the derivation of equations for computing the Grüneisen constant. The data presented herein was collected and used by Mr. William H. "Bill" Childs in the analysis of thermal stress-related effects, and was found among his files at The Aerospace Corporation Space Materials Laboratory following his death in September, 1997.

During the period, 1965 through 1992, researchers in The Aerospace Corporation's Laboratory Operations conducted experiments on some 28 underground nuclear tests (UGTs) at Mercury, Nevada. Concurrently with these UGTs, and subsequent to the termination of underground testing in 1992, innumerable experiments were conducted using high-energy pulsed-power facilities at government and contractor laboratories in so-called "above ground tests" (AGTs). Bill Childs' career spanned the entire era of underground testing of space-related materials. His analytical efforts were critical to the support of virtually every nuclear weapon effects experiment conducted by Aerospace, whether underground or above ground, as well as the many "paper" studies related to vulnerability, survivability, and hardening done during that time.

In 1981, Childs published the first volume of his compendium of temperature-dependent thermophysical properties. Volume I<sup>\*</sup> presented tables of data for 112 materials, together with curve fits suitable for computer code input. This was followed in 1986 by the publication of Volume II, which presented data on an additional 107 materials. These volumes have become industry standards as data reference for radiation effects modeling and analysis. Childs was in the process of preparing a third volume, intended for the presentation of his collection of thermomechanical properties data, but

<sup>\*</sup> Childs, W. H., "Thermophysical Properties of Selected Space-Related Materials", Vol. I, Aerospace Report No. TOR-0081(6435-02)-01, 20 February, 1981.

<sup>\*\*</sup> Childs, W. H., "Thermophysical Properties of Selected Space-Related Materials", Vol. II, Aerospace Report No. TOR-0086(6435-02)-01, 15 February, 1986.

this was not completed during his lifetime. With its publication at this time, it is appropriate that this volume be dedicated to its original author.

The reader is cautioned that the information and data contained herein are presented as found among Childs' papers. These are known to be the data personally used by Childs, and informally provided by him to other workers in the field of radiation effects. Only minimal attempts have been made to compare the data in Childs' tables against data that might be found in the listed source materials. However, when comparisons were made, no inconsistencies could be found between Childs' data and those of other workers. In particular, Ho (ref. 88) presents a table of data calculated using a somewhat different method but that, nevertheless, agrees with Child's data to within about 10%.

The text has been edited and organized to comply with Corporation document standards. Corrections have been made where errors were found and some editorial changes have been made for clarity. However, the technical text remains essentially as written by Childs.

Data selection was made on the basis of Childs' judgement, in consultation with others. In particular, Dr. Robert Cooper is known to have given much advice and support to Childs' analytical activities. Cooper's editorial notes and comments on a draft copy of the text were found among Childs' papers and have been incorporated in this present document.

The list of data sources and references has been particularly a concern because Childs left multiple versions, including several pages of handwritten notes citing intended additions to the list of references. Explicit reference citations for the properties data selected by Childs and presented in his database could not be found. In an attempt to somewhat compensate for this lack, we have superficially reviewed the referenced documents to identify content related to the 130 materials in the database, without determining the actual source of data selected and tabulated by Childs. These observations of content have been appended to the materials list given in Section 7. However, the uncertainty of specific data origins remains a caveat to the reader.

Some of the referenced documents are quite obscure and will be difficult to locate using ordinary library services. Accordingly, the editors intend to preserve those reference documents found among Childs' holdings by transferring their possession to the Corporate Archivist of The Aerospace Corporation. Interested readers may obtain access to those reports by contacting the Corporate Archivist.

# Symbols and Units

| CB             | Bulk wave velocity                         | (cm/s)                                 |
|----------------|--|--|
| C <sub>L</sub> | Longitudinal wave velocity                 | (cm/s)                                 |
| C <sub>S</sub> | Shear wave velocity                        | (cm/s)                                 |
| C <sub>P</sub> | Heat capacity at constant pressure         | (cal/g-°C)                             |
| Cv             | Heat capacity at constant volume           | (cal/g-°C)                             |
| E              | Internal Energy                            | (cal/g)                                |
| G <sub>R</sub> | Reuss averaged shear modulus               | (dynes/cm <sup>2</sup> )               |
| G <sub>V</sub> | Voigt averaged shear modulus               | (dynes/cm <sup>2</sup> )               |
| B <sub>H</sub> | Hashin averaged shear modulus              | (dynes/cm <sup>2</sup> )               |
| G <sub>S</sub> | Shtrikman averaged shear modulus           | (dynes/cm <sup>2</sup> )               |
| К              | Hashin and Shtrikman averaged bulk modulus | (dynes/cm <sup>2</sup> )               |
| K <sub>R</sub> | Reuss averaged bulk modulus                | (dynes/cm <sup>2</sup> )               |
| K <sub>V</sub> | Voigt averaged bulk modulus                | (dynes/cm <sup>2</sup> )               |
| K <sub>A</sub> | Adiabatic bulk modulus                     | (dynes/cm <sup>2</sup> )               |
| K <sub>I</sub> | Isothermal bulk modulus                    | (dynes/cm <sup>2</sup> )               |
| P              | Pressure                                   | (dynes/cm <sup>2</sup> )               |
| S              | Entropy or degree of disorder              |  |
| Т              | Absolute Temperature                       | (°K)                                   |
| V              | Volume                                     | (cm <sup>3</sup> )                     |
| X <sub>A</sub> | Adiabatic compressibility                  | (dynes/cm <sup>2</sup> ) <sup>-1</sup> |
| XI             | Isothermal compressibility                 | (dynes/cm <sup>2</sup> ) <sup>-1</sup> |
| Y              | Young's modulus of elasticity              | (dynes/cm <sup>2</sup> )               |

| β | Volumetric coefficient of thermal expansion | $(10^{-6} \circ \mathrm{C}^{-1})$ |
|---|---|-----------------------------------|
| γ | Grüneisen constant                          |                                   |
| λ | Lamè elastic constant                       | (dynes/cm <sup>2</sup> )          |
| μ | Shear modulus                               | (dynes/cm <sup>2</sup> )          |
| ν | Poisson's ratio                             |                                   |
| ρ | Density                                     | $(g/cm^3)$                        |

viii

#### Contents

| 1. | Introduction   | 1  |
|----|--|----|
| 2. | Methods of Analysis for the Grüneisen Constant   | 3  |
| 3. | Derivation of Equations to Calculate the Grüneisen Constant<br>Using Various Experimental Parameters | 7  |
| 4. | Equations Linking Five Elastic Constants   | 11 |
| 5. | Development of Equations to Calculate Aggregate Material Properties<br>from Those of Single Crystals | 15 |
| 6. | References   | 19 |
| 7. | List of Materials with their Associated Data References  | 25 |
| 8. | Compendium of Thermomechanical Property Data for 130 Materials                                       | 29 |

#### 1. Introduction

The thermomechanical material properties tabulated in this report are a consistent set of roomtemperature data compiled for 130 space-related materials. These data are essential for analyses to determine material response to pulsed radiation, which relates to survivability assessments based on above and below ground weapons effects experiments. The need for such a compilation has been expressed by analysts on many occasions in connection with DoD, AFSD, AFRL, and DTRAsponsored programs. The nine properties tabulated for each of the 130 materials include density, specific heat (constant pressure), specific heat (constant volume), Poisson's ratio, Grüneisen constant, adiabatic sound velocity, Young's modulus, isothermal bulk modulus, and volumetric coefficient of thermal expansion. Although the units are admittedly inconsistent, they have been selected for usage without conversion by the majority of users.

Among the 130 materials included in the tabulation are representative elements, oxides, carbides, halides, metallic alloys, semiconductors, optical materials, glasses, plastics, and graphites. The majority of the materials are high density, low porosity, isotropic and polycrystalline in form, unless otherwise stated. However, in a few cases, the materials are not completely characterized.

The tabulated values of material properties have been extracted from the literature without undertaking a complete or thorough search. The selected values represent the results of both experimental measurements and calculations. No attempt was made to validate the data. The bibliography, although not complete, provides the opportunity to consult the original references in most cases.

Whenever possible, experimentally measured isothermal properties were compared with values calculated from adiabatic measurements. The approach in this report was to calculate the Grüneisen constant, first based on an equation derived from thermodynamics relating to the adiabatic state, and second by means of an equation derived from thermodynamics relating to the isothermal state. These values are also compared with the Grüneisen constants that have been determined experimentally. This comparison was extended to provide a test of the consistency of the tabulated properties.

Sections 2, 3, and 4 of this report present the derivation of equations used for calculating the Grüneisen constants. Alternate methods of calculating elastic properties for isotropic materials from the anisotropic single-crystal elastic constants are presented in Section 5.

Section 6 provides the list of reference documents used by Childs as data sources for generating the compendium of material properties presented in Section 8. Section 7 presents an alphabetical list of the 130 space-related materials included in the database, together with citations to the specific data sources, to be found in the list of reference documents, for each material.

1

#### 2. Methods of Analysis for the Grüneisen Constant

The format for the Compendium of Thermomechanical Properties presented in Section 8 provides for reporting values of the Grüneisen constant obtained using one or more of three distinct methods. For those materials for which no experimental data were available, values of the Grüneisen constant have been calculated using one of the two algorithms developed below.

<u>Method 1</u> presents experimentally determined values of the Grüneisen constant for materials, when available in the literature.

The <u>second method</u> of calculating the Grüneisen constant uses the relation for isothermal conditions given in Eq. (3.15) of Section 3:

$$\gamma = \frac{\beta K_{\rm I}}{C_{\rm V} \rho},\tag{2.1}$$

where  $\beta$  is the volumetric coefficient of thermal expansion,  $K_{I}$  is the isothermal bulk modulus,  $C_{V}$  is the heat capacity at constant volume, and  $\rho$  is the density.

To be consistent throughout this report, the values for the heat capacity at constant volume,  $C_v$ , will be calculated from the thermodynamic expression given in Eq. (2.3).

$$C_{P} - C_{V} = -T \left(\frac{\partial V}{\partial T}\right)_{P}^{2} \bullet \left(\frac{\partial P}{\partial V}\right)_{T}$$
(2.2)

$$C_{\rm V} = C_{\rm P} - \left(\frac{\beta^2 {\rm TK}_{\rm I}}{\rho}\right),\tag{2.3}$$

where T is the absolute temperature. This equation applies equally to solids, liquids, and gases. There are many methods of calculating the heat capacity at constant volume, such as those given by Dulong and Petit, Einstein, Drude, Debye, and Born and Karman. It is felt that the above relationship should not introduce any appreciable errors in the calculations.

The isothermal bulk modulus, which is not always available for many materials, can be calculated by other expressions as given in Section 4. The table in Section 4 presents the relationships among five elastic constants: bulk modulus (K), Young's modulus (Y), Poisson's ratio (v), Lamè constants ( $\lambda$  and  $\mu$ (shear)). The table is organized to facilitate computation of the remaining three of these parameters when any two of the five are known, for isotropic linear elastic materials.

It would be desirable to calculate the elastic properties for random, macroscopically isotropic aggregates of crystals from the single-crystal anisotropic elastic constants. This is not yet possible, but bounds have been obtained for the aggregate properties from the single-crystal constants (Section 4). These are called the "Voigt" and "Reuss" averages. Voigt averaged the elastic stiffnesses ( $C_{ij}$ ) over all space, and Reuss averaged the elastic compliances ( $S_{ij}$ ). [2] These values are considered the least upper bound and the greatest lower bound, respectively, for the aggregate.

The <u>third method</u> of calculating the Grüneisen constant uses the relation for adiabatic conditions given in Eq. (3.22) of Section 3.

$$\gamma = \frac{\beta K_A}{C_P \rho},\tag{2.4}$$

where  $K_A$  is the adiabatic bulk modulus,  $C_P$  is the heat capacity at constant pressure, and

$$K_{\rm A} = \rho C_{\rm B}^2. \tag{2.5}$$

The adiabatic bulk wave speed  $(C_B)$  is calculated from shock wave measurements, where the longitudinal,  $C_L$ , and the shear,  $C_S$ , speeds have been determined. The shear wave is also referred to as the transverse wave. Then the bulk wave speed can be expressed as

$$C_{\rm B} = \left(C_{\rm L}^2 - \frac{4}{3}C_{\rm S}^2\right)^{\frac{1}{2}}.$$
 (2.6)

The adiabatic bulk modulus can also be calculated from the isotropic elastic properties when shock wave measurements are not available. The longitudinal and shear wave speed can be expressed as follows:

$$C_{L} = \left(\frac{3K_{A}(1-\upsilon)}{\rho(1+\upsilon)}\right)^{\frac{1}{2}}; \quad C_{S} = \left(\frac{3K_{A}(1-2\upsilon)}{2\rho(1+\upsilon)}\right)^{\frac{1}{2}}.$$
 (2.7)

The wave speeds can also be expressed in terms of the Lamè elastic constants.

$$C_{L} = \left(\frac{\lambda + 2\mu}{\rho}\right)^{\frac{1}{2}}; \quad C_{S} = \left(\frac{\mu}{\rho}\right)^{\frac{1}{2}}.$$
(2.8)

The same relationship exists as given in Section 5 by substituting values calculated from  $C_L$  and  $C_S$ .

$$\upsilon = \frac{C_{L}^{2} - 2C_{S}^{2}}{2(C_{L}^{2} - C_{S}^{2})}$$
(2.9)

$$Y = \frac{\rho C_{S}^{2} (3C_{L}^{2} - 4C_{S}^{2})}{(C_{L}^{2} - C_{S}^{2})}$$
(2.10)

$$K_{\rm A} = \rho \left( C_{\rm L}^2 - \frac{4}{3} C_{\rm S}^2 \right) \tag{2.11}$$

#### 3. Derivation of Equations to Calculate the Grüneisen Constant Using Various Experimental Parameters

For most solids, a simple relationship has been shown by Grüneisen to have experimental validity:

$$\gamma = \frac{\text{Volume Coefficient of Thermal Expansion \times Specific Volume}}{\text{Compressibility \times Specific Heat (Constant Volume)}},$$
(3.1)

and  $\gamma$  is called the Grüneisen constant.[5] Experimental values of  $\gamma$  for most solids lie between 1.5 and 2.5. A theoretical basis for the Grüneisen constant has been established by Slater in his derivation of the Mie-Grüneisen equation of state:

$$(\mathbf{P} - \mathbf{P}_0)\mathbf{V} = \gamma(\mathbf{E} - \mathbf{E}_0), \qquad (3.2)$$

where the subscripted values of pressure (P) and internal energy (E) are the volume (V) dependent values at zero Kelvin. [6]

A number of expressions relating the Grüneisen constant to various thermoelastic and thermodynamic parameters can be derived from the Mie-Grüneisen equation of state. A simple and straightforward demonstration of their interrelationships, which follows, involves the use of Jacobians. By differentiating Eq. (3.2) while holding volume constant, we obtain:

$$\gamma = V \left(\frac{\partial P}{\partial E}\right)_{V}$$
(3.3)

$$\left(\frac{\partial P}{\partial E}\right)_{V} = \frac{J(P, V)}{J(E, V)} = \frac{J(P, V) / J(T, V)}{J(E, V) / J(T, V)} = \frac{\left(\frac{\partial P}{\partial T}\right)_{V}}{\left(\frac{\partial E}{\partial T}\right)_{V}}.$$
(3.4)

The specific heat (constant volume) is defined:

$$C_{V} = \left(\frac{\partial E}{\partial T}\right)_{V} = \left(\frac{\partial S}{\partial T}\right)_{V}.$$
(3.5)

Substituting:

$$\gamma = \frac{V}{C_V} \left(\frac{\partial P}{\partial T}\right)_V, \qquad (3.6)$$

and using Maxwell's relation:

$$\left(\frac{\partial S}{\partial V}\right)_{T} = \left(\frac{\partial P}{\partial T}\right)_{V}.$$
(3.7)

Eq. (3.6) can also be written:

$$\gamma = \frac{V}{C} \sqrt{\left(\frac{\partial S}{\partial V}\right)_{\rm T}}.$$
(3.8)

But

$$\left(\frac{\partial P}{\partial T}\right)_{V} = \frac{J(P, V)}{J(T, V)} = \frac{(-)J(V, P)/J(T, P)}{J(V, T)/J(P, T)} = \frac{(-)\left(\frac{\partial V}{\partial T}\right)_{P}}{\left(\frac{\partial V}{\partial P}\right)_{T}},$$
(3.9)

so

$$\gamma = \frac{(-)V}{C_V} \bullet \frac{\left(\frac{\partial V}{\partial T}\right)_P}{\left(\frac{\partial V}{\partial P}\right)_T}.$$
(3.10)

The volume coefficient of thermal expansion is defined:

$$\beta = \frac{1}{V} \left( \frac{\partial V}{\partial T} \right)_{\rm P},\tag{3.11}$$

and the isothermal compressibility is defined:

$$X_{I} = \frac{(-)I}{V} \left(\frac{\partial V}{\partial P}\right)_{T} = \frac{1}{K_{I}},$$
(3.12)

where  $K_I$  is the isothermal bulk modulus. Substituting in Eq. (3.10):

$$\gamma = \frac{\beta V}{C_V X_I} = \frac{\beta V K_I}{C_V}.$$
(3.13)

Usually the Mie-Grüneisen equation of state, Eq. (3.2), is expressed in terms of the specific volume which is related to the density:

$$V = \frac{1}{\rho}.$$
 (3.14)

Therefore, Eq. (3.13) becomes

$$\gamma = \frac{\beta}{C_V X_I \rho} = \frac{\beta K_I}{C_V \rho}.$$
(3.15)

Using the alternate definition of  $C_V$ , Eq. (3.10) can be rewritten:

$$\gamma = \frac{(-)V}{T} \left(\frac{\partial V}{\partial T}\right)_{P} \bullet \frac{\left(\frac{\partial P}{\partial V}\right)_{T}}{\left(\frac{\partial S}{\partial T}\right)_{V}}.$$
(3.16)

But

$$\frac{\left(\frac{\partial P}{\partial V}\right)_{T}}{\left(\frac{\partial S}{\partial T}\right)_{V}} = \frac{J(P,T)/J(V,T)}{J(S,V)/J(T,V)} = \frac{J(P,S)/J(V,S)}{J(S,P)/J(T,P)} = \frac{\left(\frac{\partial P}{\partial V}\right)_{S}}{\left(\frac{\partial S}{\partial T}\right)_{P}},$$
(3.17)

and the specific heat (constant pressure) is defined:

$$C_{P} = \left(\frac{\partial H}{\partial T}\right)_{P} = T\left(\frac{\partial S}{\partial T}\right)_{P}.$$
(3.18)

Substituting in the equation above:

$$\gamma = \frac{(-)V}{C_{\rm P}} \left(\frac{\partial V}{\partial T}\right)_{\rm P} \left(\frac{\partial P}{\partial V}\right)_{\rm S}.$$
(3.19)

The adiabatic (isoentropic) compressibility and bulk modulus are defined:

$$X_{A} = (-)\frac{1}{V} \left(\frac{\partial V}{\partial P}\right)_{S} = \frac{1}{K_{A}}.$$
(3.20)

Substituting in Eq. (3.19):

$$\gamma = \frac{\beta V}{C_P X_A} = \frac{\beta V K_A}{C_P}$$
(3.21)

$$\gamma = \frac{\beta}{C_{\rm P} X_{\rm A} \rho} = \frac{\beta K_{\rm A}}{C_{\rm P} \rho}.$$
(3.22)

Equation (3.19) can be rewritten:

$$\gamma = \frac{(-)V^2\beta}{C_P} \left(\frac{\partial P}{\partial V}\right)_S.$$
(3.23)

The adiabatic (isoentropic) sound speed is defined:

$$C_{\rm B} = V \left[ \left( -\right) \left( \frac{\partial P}{\partial V} \right)_{\rm S} \right]^{\frac{1}{2}}.$$
 (3.24)

$$\gamma = \frac{\beta}{C_{\rm P}} C_{\rm B}^2. \tag{3.25}$$

Several facts are evident from the equations that have been derived. It is evident that Eq. (3.13) is identical to Eq. (3.1), which was the original definition of the Grüneisen constant,  $\gamma$ . It is possible to evaluate  $\gamma$  from several different sets of experimental data:

- (1) Using Eq. (7),  $\gamma$  can be obtained from the specific heat (constant volume), density, volumetric thermal expansion, and isothermal compressibility (or bulk modulus).
- (2) Using Eq. (10),  $\gamma$  can be obtained from the density, specific heat (constant pressure) volumetric thermal expansion, and adiabatic compressibility (or modulus).
- (2) Using Eq. (12),  $\gamma$  can be obtained from the specific heat (constant pressure), volumetric thermal expansion, and adiabatic sound velocity.

# 4. Equations Linking Five Elastic Constants

|      | ۷                                | ц   | Y  | ٨   | K   |
|------|----------------------------------|---|--|---|---|
| λ, μ | ·                                |   | $\frac{\mu(3\lambda+2\mu)}{\lambda+\mu}$ | $\frac{\lambda}{2(\lambda + \mu)}$                                      | $\frac{3\lambda + 2\mu}{3}$                                       |
| λ, Υ |                                  | $\frac{(Y-3\lambda)+\sqrt{(Y-3\lambda)^2+8\lambda Y}}{4}$ |  | $\frac{-(Y + \lambda) + \sqrt{(Y + \lambda)^2 + 8\lambda^2}}{4\lambda}$ | $\frac{(3\lambda + Y) + \sqrt{(3\lambda + Y)^2 - 4\lambda Y}}{6}$ |
| λ, ν |                                  | $\frac{\lambda(1-2v)}{2v}$                                | $\frac{\lambda(1+v)(1-2v)}{v}$           |   | $\frac{\lambda(1+v)}{3v}$   |
| λ, Κ |                                  | $\frac{3(K-\lambda)}{2}$                                  | $\frac{9K(K-\lambda)}{3K-\lambda}$       | $\frac{\lambda}{3K - \lambda}$  |   |
| н, Ү | $\frac{(2\mu - Y)\mu}{Y - 3\mu}$ |   |  | $\frac{Y-2\mu}{2\mu}$   | $\frac{\mu Y}{3(3\mu - Y)}$                                       |
| μ, ν | $\frac{2\mu v}{(1-2v)}$          | -   | $2\mu(1+v)$                              |   | $\frac{2\mu(1+v)}{3(1-2v)}$                                       |
| µ, К | $\frac{3K-2\mu}{3}$              |   | $\frac{9K\mu}{3K+\mu}$                   | $\frac{1}{2} \left[ \frac{3K - 2\mu}{3K + \mu} \right]$                 |   |
| Y, v | $\frac{vY}{(1+v)(1-2v)}$         | $\frac{Y}{2(1+v)}$  |  |   | $\frac{Y}{3(1-2v)}$   |
| Y, K | $\frac{3K(3K-Y)}{9K-Y}$          | $\frac{3YK}{9K-Y}$  |  | $\frac{1}{2} \left[ \frac{3K - Y}{3K} \right]$                          |   |
| v, K | $\frac{3Kv}{1+v}$                | $\frac{3K(1-2v)}{2(1+v)}$                                 | 3K(1-2v)                                 |   |   |

# 5. Development of Equations to Calculate Aggregate Material Properties from Those of Single Crystals

Editor's Note: The text of this section presents the author's unabridged development and rationale for the calculation of aggregate properties from those of single crystals—it has been reproduced with only minor formatting changes from Childs' original draft. It is recognized that the uninitiated reader will likely have some difficulty in following this development because of the lack of rigor and other lapses. However, it is hoped that the inclusion of this section will provide useful insight into Childs' approach. The interested reader may find additional insights by referring to other treatments of this subject to be found in the literature. (cf. Ref. 88.)

The Voigt and Reuss bulk modulus averages are given by

$$K_{\rm V} = (A + 2B)/3$$
 and  $K_{\rm P} = 1/(3a + 6b)$ , respectively, (5.1)

and the shear moduli of rigidity averages are

$$G_{\rm V} = (A - B + 3C)/5$$
 and  $G_{\rm R} = 5/(4a - 4b + 3c)$ . (5.2)

The constants A, B, C and a, b, c are related to the elastic stiffnesses and compliances by the relations

$$3A = C_{11} + C_{22} + C_{33} 3a = S_{11} + S_{22} + S_{33} 3B = C_{23} + C_{31} + C_{12} 3b = S_{23} + S_{31} + S_{12} (5.3) 3C = C_{44} + C_{55} + C_{66} 3c = S_{44} + S_{55} + S_{66} 3c = S_{46} + S_{56} + S_{56} 3c = S_{56} + S_{56} + S_{56} 3c = S_{56} + S_{56} + S_{56} 3c = S_{56} + S_{56$$

Again, knowing any two of the elastic properties, the rest can be calculated from the isotropic elastic relations given in Section 4. No distinction is made between adiabatic and isothermal elastic properties, which should not differ by more than a few percent.

| Crystalline Structure       | Definition of Constants A, B, & C     |         |
|-----------------------------|---------------------------------------|---------|
| Cubic                       | $A = C_{11}$                          |         |
|                             | $\mathbf{B} = \mathbf{C}_{12}$        | (5.4)   |
|                             | $C = C_{44}$                          |         |
|                             |                                       |         |
| Hexagonal and Trigonal      | $A = 1/3 \ (2C_{11} + C_{33})$        |         |
|                             | $B = 1/3 \ (2C_{13} + C_{12})$        | (5.5)   |
|                             | $C = 1/3 \ (2C_{44} + C_{66})$        |         |
|                             | where $C_{66} = 1/2(C_{11} - C_{12})$ | (5.6)   |
| Tetragonal                  | $A = 1/3 (2C_{11} + C_{33})$          |         |
|                             | $B = 1/3 (2C_{13} + C_{12})$          | (5.7)   |
|                             | $C = 1/3 (2C_{44} + C_{66})$          |         |
| Orthorhombic and Monoclinic | $A = 1/3 (C_{11} + C_{22} + C_{33})$  | <u></u> |
|                             | $B = 1/3 (C_{13} + C_{23} + C_{12})$  | (5.8)   |
|                             | $C = 1/3 (C_{44} + C_{55} + C_{66})$  |         |

The constants, A, B, and C have been further reduced for six specific crystalline structures as follows [7]:

Improvements have been made for the upper and lower bounds for cubic crystals and are known as the "Hashin" and "Shtrikman" averages. [2] For single-phase aggregate of a cubic material, the bulk modulus, K, is given unambiguously by

$$K = \frac{1}{3} (C_{11} + 2C_{12})$$
 (5.9)

and the modulus of rigidity is bounded by

$$G_{\rm H} = G_1 + 3 \left( \frac{5}{G_2 - G_1} - 4\sigma_1 \right)^{-1}$$
(5.10)

$$G_{\rm S} = G_2 + 2 \left( \frac{5}{G_1 - G_2} - 6\sigma_2 \right)^{-1},$$
 (5.11)

where

and

$$G_1 = \frac{1}{2} \left( C_{11} - C_{12} \right) \tag{5.12}$$

$$G_2 = C_{44}$$
 (5.13)

$$\sigma_1 = -\frac{3(K+2G_1)}{5G_1(3K+4G_1)} \tag{5.14}$$

$$\sigma_2 = -\frac{3(K+2G_2)}{5G_2(3K+4G_2)}.$$
(5.15)

 $G_H$  is termed the Hashin rigidity, and  $G_S$  is the smaller Shtrikman rigidity.

(

In general, crystals are anisotropic with respect to their elastic properties. That is, the values of these moduli differ with direction in the crystal. A measure of the anisotropy of a cubic crystal is given by the anisotropy factor  $(\tilde{A})$  and is defined as

$$\tilde{A} = \frac{2C_{44}}{(C_{11} - C_{12})} \tag{5.16}$$

For those crystals with  $\tilde{A} > 1$ , such as germanium and silicon, Young's modulus has its maximum value along the <100> direction and the minimum value along the <111> direction. For crystals with  $\tilde{A} < 1$ , such as sodium chloride, Young's modulus has its maximum value along the <111> direction and its minimum along the <100> direction. The variation in elastic properties with direction may be as great as 30%.

#### 6. References

- 1. Gray, D. E., Ed., <u>American Institute of Physics Handbook</u>, Third Edition, McGraw-Hill Book Co., New York, NY, (1972)\*\*
- 2. Simmons, F.S., Wang, H., Single Crystal Elastic Constants and Calculated Aggregate Properties Handbook, MIT Press, MA, (1971)\*\*
- 3. Marsh, S.P., <u>Los Alamos Scientific Laboratory Shock Hugoniot Data</u>, University of California Press, Berkeley and Los Angeles, CA (1980)
- Urzendowski, R., Guenther, A.H., <u>The Grüneisen Parameter and Thermal Properties of</u> <u>Polymers</u>, Air Force Weapons Laboratory, AFWL-TR-71-6, Air Force Weapons Laboratory, Kirtland Air Force Base, NM, (May 1971)\*
- 5. Grüneisen, E., "Zustand des festen Korpers," HandBuch der Physik, 10, 1-59, (1926)\*
- 6. Slater, J.C., <u>Introduction to Chemical Physics</u>, McGraw-Hill 1939, Chapter XIII, Section 4, (1939)
- 7. Hearman, R.F.S., <u>An Introduction to Applied Anisotropic Elasticity</u>, Oxford University Press, (1961)
- 8. Wolfe, W.L., Zissis, G.J., <u>The Infrared Handbook</u>, Office of Naval Research, Department of the Navy, Washington, D.C., (1985)\*\*
- 9. Childs, W.H., <u>Thermophysical Properties of Selected Space-Related Materials</u>, TOR-0081(6435-02)-1, Vol. I, The Aerospace Corporation, El Segundo, CA, (1981)\*
- Childs, W.H., <u>Thermophysical Properties of Selected Space-Related Materials</u>, TOR-0086(6435-02)-1, Vol. II, The Aerospace Corporation, El Segundo, CA, (1986)\*
- McQueen, R.G., Marsh, S.P., "Equation of State for Nineteen Metallic Elements from Shock-Wave Measurements to Two Megabars," <u>Journal of Applied Physics</u>, Vol. 31, No.7, (July 1960)\*
- Touloukian, Y.S., Buyco, E.H., <u>Thermophysical Properties of Matter</u>, The Thermophysical Properties Research Center Data Series, Purdue University, IFI/Plenum New York–Washington (1970)\*
- 13. Kelley, K.K., <u>Contribution to the Data on Theoretical Metallurgy</u>, BOM Bulletin 476, U.S. Government Printing Office, Washington, D.C., (1949)

<sup>\*\*</sup> Report available through The Aerospace Corporation Lauritsen Library.

<sup>\*</sup> Report available through The Aerospace Corporation archivist

- 14. Corning Glass Works, Properties of Selected Commercial Glasses, B-83, New York, NY, (1965)
- 15. Moses, A.J., "Optical Materials Properties," <u>Handbook of Electronic Materials</u>, Vol 1, Hughes Aircraft Co. Electronic Properties Information Center, Plenum Press, New York, (1971)\*
- 16. Taylor, R.E., Groot, H., <u>Thermophysical Properties of POCO Graphite</u>, Properties Research Laboratory, Report AFOSR-77-3280, Purdue University, West Lafayette, IN, (July 1978)\*
- 17. Modern Plastics Encyclopedia Annual Issue, McGraw-Hill, New York, NY, (1964)\*\*
- Morey, G.W., <u>The Properties of Glass</u>, 2<sup>nd</sup> Edition, Reinhold Publishing Corp., New York, NY, (1960)\*
- 19. Vier, D.T., <u>Thermal and Other Properties of Refractories</u>, Tech. Report No.. R056, U.S. Dept. of Commerce, VA, (1975)
- 20. Kingery, W.D., Introduction to Ceramics, John Wiley and Sons, Inc., New York, NY, (1960)\*
- 21. Neuberger, M., <u>Group IV Semiconducting Materials</u>, Handbook of Electronic Materials, Vol. 5, Hughes Aircraft Co. Electronic Properties Information Center, IFI/Plenum, New York, (1971)\*
- 22. Crotwell, G.P., Ward, H.P., <u>Hugoniot Data on Several Materials</u>, AFWL TR-68-82, Air Force Weapons Laboratory, Kirtland Air Force Base, NM, (Oct. 1968)\*
- Touloukian, Y.S., "Elements," <u>Thermophysical Properties of High Temperature Solid</u> <u>Materials</u>, Vol. 1, The Thermophysical Properties Research Center, Purdue University, Macmillan Company, New York (1967)\*\*
- 24. Morris, C.E., et al, Los Alamos Shock Wave Profile Data, University of California Press, Berkeley, CA, (1982)\*\*
- 25. Kohn, B.J., <u>Compilation of Hugonoit Equation of State</u>, AFWL-TR-69-38, Air Force Weapons Laboratory, Kirtland Air Force Base, NM, (1969)\*
- 26. Cost, J.R., Janowski, K.R., Rossi, R.C., <u>Elastic Properties of Isotropic Graphite</u>, TR-0158(3250-10)-13, The Aerospace Corporation, El Segundo, CA, (Jan. 1968)\*
- 27. Kolsky, H., Stress Waves in Solids, Oxford at the Clarendon Press, (1953)\*\*
- 28. Inconel 600, Maxi, (1963)
- 29. E.I. DuPont DeNemours & Co. (Inc.), <u>Kapton<sup>®</sup> Polyimide Film</u>, DuPont Technical Bulletin H-1A, DuPont Co., Electronics Department, Wilmington, DE
- 30. Weast, R.C., Ed., <u>Handbook of Chemistry and Physics</u>, 53<sup>rd</sup> Edition, Chemical Rubber Company Press, Cleveland, OH, (1969)\*\*
- Hanlein, S.L., Hinckley, W.M., Stecher, F.P., <u>Comparison of Mechanical and Acoustic</u> <u>Properties for Selected Nonferrous, Ferrous, and Plastic Materials</u>, NOLTR 70-141, Naval Ordnance Laboratory, Report, White Oak, MD, (July 1970)\*

- 32. Salama, M.A.,, et al, Thermoelastic Analysis of Solar Cell Arrays and Their Material Properties
- 33. General Electric, <u>Silicones</u>, Technical Data Bank S-35, Silicone Products Division, Waterford, NY.
- 34. Rinehart, J.S., <u>Compilation of Dynamic Equation of State Data for Solids and Liquids</u>, U.S. Naval Ordinance Test Station," NRS TP 3798, China Lake, CA, (May 1965)\*
- 35. Brandrup, J., Immergut, E.H., <u>Polymer Handbook 2nd Edition</u>, Wiley-Interscience Publications, New York, (1975)\*
- 36. Urzendowski, R., Guenther, A.H., <u>Thermal Properties and Grüneisen Parameters for Several</u> <u>Polymers, Concretes, and Composite Materials</u>, AFWL-TR-72-37, Air Force Weapons Laboratory. Kirtland Air Force Base, NM, (Sept. 1972)\*
- 37. Weast, R.C., Astle, M.J., Beyer, W.H., <u>Handbook of Chemistry and Physics</u>, 64<sup>th</sup> Edition, CRC Press, Boca Raton, FL, (1984)
- 38. Samsonov, G.V., Ed, The Oxide Handbook 2<sup>nd</sup> Edition, IFI/Plenum, New York, NY, (1982)\*
- Ballard, S.S.,McCarthy, K.A., Wolfe, W.L., <u>Optical Materials for Infrared Instrumentation</u>, R.N. 2389-11-S, University of Michigan, Willow Run Laboratories, Ann Arbor, MI, (Jan. 1959)
- 40. Auld, B.A., Acoustic fields and Waves in Solids Vol. I, Wiley-Interscience, (1973)\*\*
- 41. Darwin, G.E., Buddery, J.H., Beryllium, Academic Press, Inc., New York, (1960)\*\*
- Walsh, J.M., Rice, M.H, McQueen, R.G., Yarger, F.L., "Shock-Wave Compressions of Twenty-Seven Metals, Equations of State of Metals;" <u>Physical Review</u>, Vol. 108, No. 2, pp 196-216; (October 1957)\*
- 43. Spedding, F.H., Daane, A.H., The Rare Earths, John Wiley and Son, Inc., New York, (1961)
- 44. Filyand, M.A., Semenova, E.I., <u>Handbook of the Rare Elements, Trace Elements and Light</u> <u>Elements Vol I</u>, Boston Technical Publishers, Inc., Cambridge, MA, (1968)
- 45. Filyand, M.A., Semenova, E.I., <u>Handbook of the Rare Elements, Refractory Elements Vol II.</u> Boston Technical Publishers., Inc., Cambridge, MA, (1970)
- 46. Filyand, M.A., Semenova, E.I., <u>Handbook of the Rare Elements, Radioactive Elements and</u> <u>Rare Earth Elements Vol III</u>, Boston Technical Publishers., Inc., Cambridge, MA, (1970)
- 47. Krishnan, R.S, et al, Thermal Expansion of Crystals, Pergamon Press, New York, (1979)\*\*
- DeWitt, D.P., <u>Handbook of the Optical, Thermal, and Mechanical Properties of Six</u> <u>Polycrystalline Dielectric Materials</u>, TPRC Report No. 19, Thermophysical Properties Research Center, Purdue University, West Lafayette, IN, (Dec. 1972)\*
- 49. McQuillan, A.D., McQuillan, M.K., Titanium, Butterworths Scientific Pub., London, (1956)\*\*

- 50. Burke, J.J., Weiss, V. Ed., <u>Shock Waves and the Mechanical Properties of Solids</u>, Syracuse University Press, Syracuse, NY, (1971)\*
- 51. Floyd, H.L., <u>Material Properties</u>, <u>Measured and Estimated</u>, Laboratory Report No, 68-6020, Sandia Corporation, Division 2635, (Sept. 1968)\*
- 52. Corning Glass Works, Low Expansion Materials, Corning, NY, (1969)
- 53. Hodges, E.S., et al, <u>Tin and Its Alloys</u>, Edward Arnold LTD, London, (1960)
- 54. Bakken, L.H., Anderson, P.D., <u>An Equation-of-State Handbook (Conversion Relations</u> <u>Between the Wondy/Tody and the PUFF/KO/HEMP Classes of Shock Wave Propagation</u> <u>Computer Codes</u>, SCL-DR-68-123, Sandia Laboratories, Livermore, CA, (Jan. 1969)\*
- 55. Neuberger, M., <u>IV-V Semiconducting Compounds Data Tables</u>, Hughes Aircraft Co. Electronic Properties Information Center, Report S-12, Culver City, CA, (Oct. 1969)\*
- 56. Oswald, R.B., et al, <u>Grüneisen Data from the Free Surface Velocity of Thermoelastic Materials</u>, HDL-TR-1629, Harry Diamond Laboratories, Washington, DC, (May 1973)\*
- 57. Oswald, R.B., McLean, F.B., <u>Grüneisen Data from the One-Dimensional Response of Solids</u>, HDL-TR-1502, Harry Diamond Laboratories, Washington, DC, (June 1970)\*
- 58. Smithells, C.J., Metals Reference Book, Vol. 3, Plenum Press, New York, (1967)\*
- McLean, F.B., Oswald, R.B., Schalborn, D.R., Buxton, L,D., <u>Temperature Dependence of the</u> <u>Dynamic Response of Silicon, Germanium, and Indium Antimonide to a Pulse Electron Beam</u>, HDL-TR-1503; Harry Diamond Laboratories, Washington, D.C., (June 1970)
- Barron, T.H.K., "Grüneisen Parameters for the Equation of State of Solids," <u>Annals of Physics</u>: 1, 77-90 (1957)\*
- Dugdale, J.S., MacDonald, D.K.C., "The Thermal Expansion of Solids," <u>Physical Review</u>, Vol. 89, No. 4 832-834; (Feb., 1953)\*
- 62. Golian, S., Grandey, R., Bandaruk, W., <u>Methods of Calculating Thermal Shock Coefficients</u>; <u>Calculated Coefficients for Most Metals and Various Non-metals</u>, Philco, Corporation, Aeronautic Division, (July 1964)\*
- 63. Touloukian, Y.S., et al, "Thermal Expansion, Metallic Elements and Alloys," <u>Thermophysical</u> <u>Properties of Matter</u>, Volume 12, (1975)\*
- 64. Brugger, K., Fritz, T.C., "Grüneisen Gamma from Elastic Data," <u>Physical Review</u>, Vol. 157, No. 3, pp 524-531, (May 1967)\*
- 65. Ree, J.R., Radiation Damage Study (RADS Program), AFBSD and AVCO Missile Systems
- 66. Wimmer, J.M., <u>Mechanical and Physical Properties of Chemically Vapor-Deposited (CVD)</u> <u>Zinc Sulfide</u>, AFML-TR-70-4013, Air Force Materials Laboratory, Wright-Patterson Air Force Base, OH, (March 1979)\*

- 67. Penning, J.R., et al. <u>Negative Equation of State and Spall Criteria</u>, RTD-TDR-63-3039, Boeing Co., Seattle, WA, (Sept. 1963)\*
- 68. Morgan, D.T., Rockowitz, M., Atkinson, A.L., <u>Measurement of the Grüneisen Parameter and the Internal Energy Dependence of the Solid Equation of State for Aluminum and Teflon</u>, AFWL-TR-6 5-117, AVCO Corp., Wilmington, MA, (Oct. 1965)\*
- Anderson, G.D., Fahrenbruch, A.L., <u>Equation of State of Solids II, Aluminum and Teflon</u>, AFWL-TR-67-43, Stanford Research Institute, Poulter Laboratories, Menlo Park, CA, (Sept. 1967)\*
- 70. Rauschenbach, H.S., <u>Solar Cell Array Design Handbook: The Principles and Technology of</u> <u>Photovoltaic Energy Conversion</u>, Van Nostrand Reinhold Publishers, (April 1980)\*
- 71. Slater, J.C., <u>Note on the Grüneisen Constant for the Incompressible Metals</u>, Physical Review, Vol. 57, 744-746; (April 1940)\*
- Ballard, S.S., Browder, J.S., "Thermal Expansion and Other Physical Properties of the Newer Infrared–Transmitting Optical Material," <u>Journal of Applied Optics</u>, Vol.5, No. 12, (Dec. 1966)\*
- 73. <u>Materials Properties Data Handbook</u>, LMSC F286269, Lockheed Missiles and Space Co., Inc., Sunnyvale, CA, Jan. 1991.\*\*
- 74. Brian, J.K., <u>Compilation of Hugonoit Equation of State</u>, AFWL-TR-69-38, Air Force Weapons Laboratory, Kirtland Air Force Base, NM, (1969)
- 75. Yen, C.C.S., <u>Dynamic Shear Stress Strain, Strain Rate Relations of Iron</u>, TR-0158(3250-40)-3, The Aerospace Corporation, El Segundo, CA, (1967)
- 76. Rice, M.H., PUFF74 EOS Compilations, AFWL-TR-80-21, S-Cubed, La Jolla, CA, (1980)\*\*
- 77. Durvasula, L.N., et al, <u>Handbook of the Properties of Optical Materials</u>, GACIAC HB 84-01, ITT Research Institute, Chicago, IL, (1984)\*
- 78. Knupp, P., <u>Stage III Materials Properties Handbook</u>, PITR-1348-5-R4, Physics International, San Leandro, CA, (March 1983)
- 79. Adachi, S., "GaAs, AIAs, and Al<sub>x</sub>Ga<sub>1-x</sub>As: Material Parameters for Use in Research and Device Applications," Journal of Applied Physics, Vol. 58, No. 3, 1, (August 1985)
- 80. <u>Specification for Manufacture and Quality Assurance of CMX Solar Cell Covers</u>, PS 292 (Issue 2), Pilkington Space Technology, United Kingdom, (1984)
- 81. <u>Structural and Materials Engineering Bulletin, Aluminum-Lithium 8090</u>, M&P 6867, Lockheed Missiles & Space, Co, Palo Alto, CA, (1991)
- Urzendowski, R., et al, <u>Ultrasonic and Thermal Studies of Selected Plastics</u>, <u>Laminated</u> <u>Materials and Metals</u>, AFWL-TR-67-91, Air Force Weapons Laboratory, Kirtland Air Force Base, NM, (1965)

- 83. E.I. DuPont DeNemours & C., Delrin<sup>®</sup> Aceta 1 Resins, Wilmington, DE
- 84. Pennsalt Chemicals Corp., KYNAR, Bulletin VFZR-62, 3 Penn Center, Philadelphia, PA,
- 85. <u>Metals Handbook, 1948 Edition</u>, The American Society for Metals, Materials Park, Cleveland, OH, (1948)\*\*
- Salama, M.A., et al, <u>Stress Analysis and Design of Silicon Solar Cell Arrays and Related</u> <u>Material Properties</u>, TR 32-1552, Jet Propulsion Laboratory, Pasadena, CA, (March 1972)\*\*
- 87. Bogaard, et al, <u>Effects of Rapid Heating Rate on Materials Properties</u>, TEPIAC/CINDAS Report 87, (1986)
- Ho, C.Y. (Ed.), Taylor, R.E., <u>Thermal Expansion of Solids</u>, CINDAS Data Series, Materials Park, OH, ASM International, (1998)\*\*
- 89. Shea, Jr. et al., <u>Above ground Test/Underground Test (AGT/UGT) Validation Program (U)</u>, DNA-TR-88-116, Physics International Co., San Leandro CA, 18 May 1988.

| 1     | Aluminum                    | 1, 2, 5, 8, 22, 25, 27, 31, 34, 42, 47, 51, 56, 57, 58, 62, 68, |
|-------|-----------------------------|---|
| 2     | Aluminum 2024               | 09, 70, 85  |
| 2     | Aluminum Ovida (Dalu)       | 24, 25, 51, 54, 70  |
| 3     | Aluminum Oxide (Foly)       | 2, 24, 30, 47, 40 31, 02, 00                                    |
| 4     | Aluminum Oxide (S.C.)       | 2, 0, 24, 59, 47, 51, 72  |
| 5     |                             | 24, 25, 51, 50, 51, 70  |
| 0     | ATLO                        | 7, 11, 25   |
| /     | All Graphite                | 24, 25, 34, 36, 47, 62, 76                                      |
| 8     | Barium                      | 30  |
| 9     | Beryllium                   | 1, 2, 24, 25, 31, 34, 41, 42, 44, 47, 51, 54, 62, 76, 85        |
| 10    | Beryllium Oxide             | 2, 24, 38, 41, 47, 51, 62                                       |
| 11    | Bismuth                     | 2, 8, 11, 25, 34, 42, 47  |
| 12    | Boron                       | 34, 45  |
| 13    | Boron Carbide               | 24, 25  |
| 14    | Brass 70/30                 | 8, 22, 25, 31, 34, 42, 51, 54, 58, 62                           |
| 15.   | Cadmium                     | 1, 2, 5, 11, 25, 34, 42, 47, 51, 62                             |
| 16    | Cadmium Sulphide (S.C.)     | 2, 8, 39, 40, 47, 51, 77  |
| 17    | Calcium                     | 30  |
| 18    | Calcium Carbonate (Calcite) | 2, 8, 24, 39, 47, 77  |
| 19    | Carbon Phenolic             | 22, 25, 36, 54  |
| 20    | Cerium                      | 46, 62  |
| 21    | Chromium                    | 2, 11, 25, 34, 42, 51, 54, 58, 62                               |
| 22    | Chromium Oxide              | 38  |
| 23    | Cobalt                      | 1, 2, 6, 11, 25, 31, 34, 42, 47, 51, 54, 62, 64                 |
| 24    | Cobalt Oxide                | 38, 51, 85  |
| 25    | Copper                      | 1, 2, 6, 8, 11, 22, 24, 25, 27, 31, 34, 42, 47, 50, 51, 54, 56, |
|       |                             | 57, 58, 62, 64, 70, 88  |
| 26    | Corning 7740 (PYREX)        | 1, 8, 40, 51  |
| 27    | Corning 7940 (Fused Silica) | 1, 8, 14, 39, 40, 47, 48, 51, 62, 64, 72                        |
| 28    | Corning 7971 (ULE)          |   |
| 29    | Corning 9606 (PYROCERAM)    |   |
| 30    | Dysprosium                  | 2, 46, 47, 62   |
| 31    | Erbium                      | 2, 46, 47, 62   |
| 32    | Europium                    | 46, 62  |
| 33    | Gadolinium                  | 2, 46, 47, 62, 77   |
| 34    | Gallium Antimonide (S.C.)   | 2, 8, 39, 47, 77, 88  |
| 35    | Gallium Arsenide            | 8, 21, 39, 40, 47, 51   |
| 36    | Germanium (S.C.)            | 1, 2, 8, 9, 21, 24, 39, 40, 44, 47, 51, 56, 57, 64, 72, 88      |
| 37    | Gold                        | 1, 2, 5, 11, 25, 31, 34, 42, 47, 51, 54, 62, 64                 |
| 38    | Hafnium                     | 2, 25, 31, 45, 47, 54   |
| . ~ ~ |                             | 1   |

## 7. List of Materials with their Associated Data References

| 39 | Hafnium Carbide             | 45, 47   |
|----|-----------------------------|--|
| 40 | Holmium                     | 46, 47, 62   |
| 41 | Indium                      | 2, 34, 42, 44, 47, 51, 62                                  |
| 42 | Indium Antimonide (S.C.)    | 2, 8, 39, 40, 47, 57, 77                                   |
| 43 | INVAR 36/74                 | 47, 58, 70   |
| 44 | Iridium                     | 2, 31, 47  |
| 45 | Iron                        | 1, 2, 5, 6, 8, 11, 24, 25, 34, 42, 47, 51, 54, 58, 62, 85  |
| 46 | Iron (Ni 10)                | 51   |
| 47 | Iron (Ni 18)                | 51   |
| 48 | Iron (Ni 26)                | 51   |
| 49 | Iron Oxide                  | 34, 38   |
| 50 | IRTRAN-1 (MgF2)             | 2, 38, 39, 48, 72, 73                                      |
| 51 | IRTRAN-2 (ZnS)              | 2, 34, 66, 72, 77, 88                                      |
| 52 | IRTRAN-3 (CaF2)             | 2, 5, 34, 39, 48, 72                                       |
| 53 | IRTRAN-4 (ZnSe)             | 2, 34, 72, 77, 88  |
| 54 | IRTRAN-5 (MgO)              | 2, 34, 39, 48, 62, 64, 72                                  |
| 55 | IRTRAN-6 (CdTe)             | 2, 8, 39, 51, 72, 77, 88                                   |
| 56 | Kapton                      | 35 70  |
| 57 | KEL-F                       | 7 39 51  |
| 58 | Kovar                       | 51 70  |
| 59 | Lanthanum                   | 46.62  |
| 60 | Lead                        | 1, 2, 5, 8, 11, 24, 25, 31, 34, 42, 47, 51, 54, 58, 62, 85 |
| 61 | Lead Sulphide (S.C.)        | 2, 5, 8, 39, 47, 55, 77                                    |
| 62 | Lithium Flouride (S.C.)     | 2, 8, 34, 39, 40, 47, 64, 77, 88                           |
| 63 | Lithium Niobate (S.C.)      | 2, 40, 47, 77  |
| 64 | Lucite                      | 1, 2, 25, 34, 35, 50, 67                                   |
| 65 | Leutetium                   | 40, 46, 47, 62   |
| 66 | Magnesium                   | 1, 2, 25, 31, 34, 42, 47, 51, 54, 58, 62, 85               |
| 67 | Magnesium Oxide             | 2, 8, 38, 39, 40, 47, 48, 62, 64, 88                       |
| 68 | Molybdenum                  | 2, 5, 11, 31, 34, 42, 45, 47, 51, 54, 58, 62, 70, 88       |
| 69 | Mylar                       | 25, 35, 51   |
| 70 | Neodymium                   | 46, 47, 62, 76   |
| 71 | Nickel                      | 1, 2, 5, 6, 11, 25, 31, 34, 42, 47, 51, 54, 58, 62         |
| 72 | Nickel Oxide                | 38   |
| 73 | Niobium                     | 2, 6, 24, 25, 34, 42, 45, 47, 54, 58                       |
| 74 | Niobium Carbide             | 45, 47   |
| 75 | Nylon 6                     | 1, 4, 7, 17, 25, 35, 51, 67                                |
| 76 | OTWR (Quartz phenolic)      | 7, 22, 25, 54  |
| 77 | Palladium                   | 2, 5, 6, 25, 31, 34, 42, 47, 51, 54                        |
| 78 | Platinum                    | 1, 2, 5, 6, 8, 25, 31, 34, 42, 47, 51, 54, 62, 88          |
| 79 | Plutonium (alpha)           | 46   |
| 80 | POCO Graphite (AXF)         | 16, 26   |
| 81 | Polyethylene (high density) | 1, 8, 17, 24, 25, 34, 35, 40, 54, 62                       |
| 82 | Polystyrene                 | 1, 4, 17, 25, 31, 34, 35, 40, 51, 62                       |
| 83 | Polyvinylchloride           | 17, 35   |
| 84 | Potassium Bromide (S.C.)    | 1, 2, 5, 8, 34, 39, 47, 77, 88                             |

| 85  | Potassium Chloride (S.C.) | 1, 2, 5, 8, 34, 39, 47, 64, 77, 88                             |
|-----|---------------------------|--|
| 86  | Potassium Iodide (S.C.)   | 2, 8, 34, 39, 47, 77, 88                                       |
| 87  | Praseodymium              | 46, 47, 62   |
| 88  | Pyrolytic Graphite        | 16, 26, 47   |
| 89  | Quartz Phenolic           | 25, 50, 54   |
| 90  | Quartz (S.C.)             | 2, 8, 34, 39, 40, 47, 48, 51, 54, 64, 76, 88                   |
| 91  | Rhenium                   | 2, 44, 47  |
| 92  | Rhodium                   | 31, 34, 42, 47, 62   |
| 93  | Scandium                  | 46   |
| 94  | Silicon                   | 2, 8, 9, 21, 39, 40, 47, 51, 56, 57, 72, 77, 88                |
| 95  | Silicon Carbide           | 9, 25, 62  |
| 96  | Silver                    | 1, 2, 5, 6, 8, 11, 25, 31, 34, 42, 47, 51, 54, 57, 58, 62, 64, |
|     |                           | 70   |
| 97  | Silver Chloride (S.C.)    | 1, 2, 5, 8, 39, 47, 77   |
| 98  | Sodium Chloride (S.C.)    | 2, 4, 5, 8, 24, 34, 47, 64, 72, 77, 88                         |
| 99  | Stainless Steel 304L      | 24, 25   |
| 100 | Strontium                 | 30   |
| 101 | Tantalum                  | 2, 5, 24, 25, 31, 34, 42, 45, 47, 51, 54, 58, 62               |
| 102 | Tantalum Carbide          | 2, 24, 45, 47  |
| 103 | Teflon                    | 4. 8. 25. 35. 51. 68. 69. 70                                   |
| 104 | Terbium                   | 46, 47, 62, 76   |
| 105 | Thallium Bromide (S.C.)   | 2, 34, 39  |
| 106 | Thallium Bromide-Chloride | 2, 34, 39  |
| 107 | Thallium Bromide-Iodide   | 2, 39  |
| 108 | Thallium Chloride (S.C.)  | 2, 39  |
| 109 | Thorium                   | 2, 11, 24, 25, 31, 34, 42, 46, 54                              |
| 110 | Thorium Dioxide           | 2, 38, 47  |
| 111 | Thulium                   | 46   |
| 112 | Tin                       | 1, 2, 8, 11, 24, 25, 31, 34, 42, 47, 51, 53, 58, 62, 85        |
| 113 | Tin Oxide                 | 38, 55   |
| 114 | Titanium                  | 1, 2, 11, 24, 25, 31, 34, 42, 45, 47, 49, 51, 54, 58, 62, 76,  |
|     |                           | 85   |
| 115 | Titanium Carbide          | 2, 24, 45, 47, 62  |
| 116 | Titanium Dioxide          | 8, 38, 39, 47, 48, 49  |
| 117 | Tungsten                  | 1, 2, 5, 6, 11, 24, 31, 34, 45, 47, 51, 54, 58, 62, 88         |
| 118 | Tungsten Carbide          | 24, 25, 45, 58   |
| 119 | Uranium                   | 2, 24, 25, 31, 46, 47, 54                                      |
| 120 | Uranium Oxide             | 2, 38  |
| 121 | Vanadium                  | 2, 11, 25, 31, 34, 45, 54, 58, 62                              |
| 122 | VYCOR                     |  |
| 123 | Ytterbium                 | 46, 47, 62   |
| 124 | Yttrium                   | 2, 46, 47  |
| 125 | Yttrium Aluminate (YAG,   | 40, 47   |
|     | S.C.)                     |  |
| 126 | Zinc                      | 1, 2, 5, 8, 11, 25, 34, 42, 47, 51, 54, 58, 62, 85             |
| 127 | Zinc Oxide                | 2, 38, 47, 50  |

| 128 | Zirconium         | 2, 24, 25, 31, 34, 42, 45, 47, 51 |
|-----|-------------------|-----------------------------------|
| 129 | Zirconium Carbide | 2, 24, 45, 47                     |
| 130 | Zirconium Dioxide | 38, 47, 62                        |

8. Compendium of Thermomechanical Property Data for 130 Materials

# ALUMINUM



| HEAT CAPAC | <u>CITY</u> , (cal/ g –C) |
|------------|---------------------------|
| (Cp)       | (Cv)                      |
| 0.2160     | 0.2064                    |

| YOUNGS MODULUS                 | BULK MODULUS |  |
|--------------------------------|--------------|--|
| (Dynes/cm * 10 <sup>12</sup> ) |              |  |
| 0.706                          | 0.752        |  |



# ALUMINUM 2024

| <u>DENSITY</u><br>(g/cm)<br>2.79 | POISSON'S RATIO<br>0.330                        |
|----------------------------------|---|
| <u>SOUND VELOCITY</u>            | VOL. COEFF. THERMAL                             |
| (cm/microsec)                    | EXPANSION, (10 <sup>-6</sup> °C <sup>-1</sup> ) |
| 0.5209                           | 67.5  |

| <u>HEAT CAPACITY</u> , (cal/ g –C) |        |  |  |
|------------------------------------|--------|--|--|
| (Cp)                               | (Cv)   |  |  |
| 0.2200                             | 0.2117 |  |  |

YOUNGS MODULUSBULK MODULUS(Dynes/cm \* 1012)0.7240.710



# ALUMINUM OXIDE (POLY)



| <u>HEAT CAPACITY</u> , (cal/ g –C) |        |  |
|------------------------------------|--------|--|
| (Cp)                               | (Cv)   |  |
| 0.1870                             | 0.1858 |  |

| YOUNGS MODULUS                 | BULK MODULUS |  |  |
|--------------------------------|--------------|--|--|
| (Dynes/cm * 10 <sup>12</sup> ) |              |  |  |
| 4.060                          | 2.500        |  |  |

| GRÜNEISEN CONSTANT |          |          |  |  |
|--------------------|----------|----------|--|--|
| METHOD 1           | METHOD 2 | METHOD 3 |  |  |
|                    | 1.327    | 1.327    |  |  |
|                    |          |          |  |  |
# ALUMINUM OXIDE (S.C.)



| <u>HEAT CAPACITY</u> , (cal/ g –C) |        |  |
|------------------------------------|--------|--|
| (Cp)                               | (Cv)   |  |
| 0.1850                             | 0.1837 |  |

<u>YOUNGS MODULUS</u> (Dynes/cm \* 10<sup>12</sup>) 4.600 2.401



#### ALUMINUM 6061 — T6



| HEAT CAPACITY, (cal/g –C) |        |  |
|---------------------------|--------|--|
| (Cp)                      | (Cv)   |  |
| 0.2130                    | 0.2041 |  |

| YOUNGS MODULUS                 | BULK MODULUS | <br> |  |
|--------------------------------|--------------|------|--|
| (Dynes/cm * 10 <sup>12</sup> ) |              |      |  |
| 0.738                          | 0.728        |      |  |



#### ANTIMONY



| HEAT CAPACITY, (cal/ g –C) |        |  |
|----------------------------|--------|--|
| (Cp)                       | (Cv)   |  |
| 0.0483                     | 0.0479 |  |

<u>YOUNGS MODULUS</u> (Dynes/cm \* 10<sup>12</sup>)

0.315

0.778

GRÜNEISEN CONSTANT METHOD 1 METHOD 2 METHOD 3 0.801 0.769 0.775

#### ATJ GRAPHITE



| <u>HEAT CAPACITY</u> , (cal/ g –C) |        |  |
|------------------------------------|--------|--|
| (Cp)                               | (Cv)   |  |
| 0.1750                             | 0.1750 |  |

| YOUNGS MODULUS                 | BULK MODULUS |  |
|--------------------------------|--------------|--|
| (Dynes/cm * 10 <sup>12</sup> ) |              |  |
| 0.079                          | 0.057        |  |



# BARIUM

| DENSITY<br>(g/cm) | POISSON'S RATIO                                 |
|-------------------|---|
| 3.5               | 0.229   |
|                   |   |
| SOUND VELOCITY    | VOL. COEFF. THERMAL                             |
| (cm/microsec)     | EXPANSION, (10 <sup>-6</sup> °C <sup>-1</sup> ) |
| 0.1575            | 62.0  |
|                   |   |

| HEAT CAPACITY, (cal/ g –C) |        |  |
|----------------------------|--------|--|
| (Cp)                       | (Cv)   |  |
| 0.0437                     | 0.0430 |  |

YOUNGS MODULUS (Dynes/cm \* 10<sup>12</sup>)

0.141 0.087



#### BERYLLIUM



| HEAT CAPACIT | <u>Y</u> , (cal/ g –C) |
|--------------|------------------------|
| (Cp)         | (Cv)                   |
| 0.4360       | 0.4310                 |

| YOUNGS MODULUS                 | BULK MODULUS |  |
|--------------------------------|--------------|--|
| (Dynes/cm * 10 <sup>12</sup> ) |              |  |
| 3.095                          | 1.147        |  |



# BERYLLIUM OXIDE

| <u>DENSITY</u><br>(g/cm)<br>3.03 | POISSON'S RATIO<br>0.224                        |
|----------------------------------|---|
| <u>SOUND VELOCITY</u>            | VOL. COEFF. THERMAL                             |
| (cm/microsec)                    | EXPANSION, (10 <sup>-6</sup> °C <sup>-1</sup> ) |
| 0.8437                           | 19.0  |

| HEAT CAPACITY, (cal/ g –C) |        |  |
|----------------------------|--------|--|
| (Cp)                       | (Cv)   |  |
| 0.2460                     | 0.2442 |  |

YOUNGS MODULUSBULK MODULUS(Dynes/cm \* 1012)3.5702.157

| <b>GRÜNEISEN CONSTANT</b> |          |          |
|---------------------------|----------|----------|
| METHOD 1                  | METHOD 2 | METHOD 3 |
|                           | 1.314    | 1.324    |
|                           |          |          |

#### BISMUTH



| <u>HEAT CAPACITY</u> , (cal/ g –C) |        |  |
|------------------------------------|--------|--|
| (Cp)                               | (Cv)   |  |
| 0.0293                             | 0.0289 |  |

| YOUNGS MODULUS                 | BULK MODULUS |  |
|--------------------------------|--------------|--|
| (Dynes/cm * 10 <sup>12</sup> ) |              |  |
| 0.503                          | 0.340        |  |



### BORON



| <u>HEAT CAPACITY</u> , (cal/ g –C) |        |  |
|------------------------------------|--------|--|
| (Cp)                               | (Cv)   |  |
| 0.2643                             | 0.2631 |  |

<u>YOUNGS MODULUS</u> (Dynes/cm \* 10<sup>12</sup>) 4.613 2.130

GRÜNEISEN CONSTANT METHOD 1 METHOD 2 METHOD 3 — 1.086 1.091

#### **BORON CARBIDE**

**、** ·



| HEAT CAPACITY, (cal/ g –C) |        |  |
|----------------------------|--------|--|
| (Cp)                       | (Cv)   |  |
| 0.2500                     | 0.2487 |  |

| YOUNGS MODULUS                 | BULK MODULUS |  |
|--------------------------------|--------------|--|
| (Dynes/cm * 10 <sup>12</sup> ) |              |  |
| 4.249                          | 2.157        |  |



# **BRASS 70/30**

| (g/cm)         | <u>POISSON'S RATIO</u>                                  |
|----------------|---|
| 8.52           | 0.350   |
| SOUND VELOCITY | <u>VOL. COEFF. THERMAL</u>                              |
| (cm/microsec)  | <u>EXPANSION</u> , (10 <sup>-6</sup> °C <sup>-1</sup> ) |

| HEAT CAPACITY, (cal/g -C) |        |  |
|---------------------------|--------|--|
| (Cp)                      | (Cv)   |  |
| 0.0905                    | 0.0872 |  |

YOUNGS MODULUSBULK MODULUS(Dynes/cm \* 1012)1.0061.118

| GRÜNEISEN CONSTANT |          |          |
|--------------------|----------|----------|
| METHOD 1           | METHOD 2 | METHOD 3 |
| _                  | 2.069    | 2.148    |
|                    |          |          |

#### CADMIUM



| HEAT CAPACITY, (cal/ g –C) |        |  |
|----------------------------|--------|--|
| (Cp)                       | (Cv)   |  |
| 0.0553                     | 0.0513 |  |

| YOUNGS MODULUS                 | BULK MODULUS |  |
|--------------------------------|--------------|--|
| (Dynes/cm * 10 <sup>12</sup> ) |              |  |
| 0.621                          | 0.572        |  |



### CADMIUM SULPHIDE (S.C.)



| <u>HEAT CAPACITY</u> , (cal/ g –C) |        |  |
|------------------------------------|--------|--|
| (Cp)                               | (Cv)   |  |
| 0.0880                             | 0.0878 |  |

YOUNGS MODULUSBULK MODULUS(Dynes/cm \* 1012)0.4680.614



### CALCIUM



| HEAT CAPACI | <u>TY</u> , (ca!/ g –C) |
|-------------|-------------------------|
| (Cp)        | (Cv)                    |
| 0.1568      | 0.1533                  |

| YOUNGS MODULUS | BULK MODULUS              |
|----------------|---------------------------|
| (Dynes         | s/cm * 10 <sup>12</sup> ) |
| 0.241          | 0.170                     |



# **CALCIUM CARBONATE (CALCITE)**



| HEAT CAPAC | <u> TY</u> , (cal/ g –C) |
|------------|--------------------------|
| (Cp)       | (Cv)                     |
| 0.2030     | 0.2020                   |

| YOUNGS MODULUS | BULK MODULUS           |
|----------------|------------------------|
| (Dynes/cm      | 1 * 10 <sup>12</sup> ) |
| 0.883          | 1.297                  |



#### **CARBON PHENOLIC**



| HEAT CAPAC | <u>ITY</u> , (cal/ g –C) |
|------------|--------------------------|
| (Cp)       | (Cv)                     |
| 0.2085     | 0.2073                   |

| YOUNGS MODULUS | BULK MODULUS           |
|----------------|------------------------|
| (Dynes/cn      | n * 10 <sup>12</sup> ) |
| 0.151          | 0.159                  |



### CERIUM

| <u>DENSITY</u><br>(g/cm) | POISSON'S RATIO                                 |
|--------------------------|---|
| 6.67                     | 0.248   |
|                          |   |
| SOUND VELOCITY           | VOL. COEFF. THERMAL                             |
| (cm/microsec)            | EXPANSION, (10 <sup>-6</sup> °C <sup>-1</sup> ) |
| 0.1742                   | 15.7  |

| HEAT CAPACIT | <u>ſY</u> , (cal/ g –C) |
|--------------|-------------------------|
| (Cp)         | (Cv)                    |
| 0.0490       | 0.0489                  |

YOUNGS MODULUSBULK MODULUS(Dynes/cm \* 1012)0.3000.198



### CHROMIUM

| <u>DENSITY</u><br>(g/cm) | POISSON'S RATIO                                 |
|--------------------------|---|
| 7.16                     | 0.210   |
|                          |   |
| SOUND VELOCITY           | VOL. COEFF. THERMAL                             |
| (cm/microsec)            | EXPANSION, (10 <sup>-6</sup> °C <sup>-1</sup> ) |
| 0.4730                   | 22.7  |

| HEAT CAPAC | <u>ITY</u> , (cal/ g –C) |
|------------|--------------------------|
| (Cp)       | (Cv)                     |
| 0.1075     | 0.1067                   |

| YOUNGS MODULUS | BULK MODULUS           |
|----------------|------------------------|
| (Dynes/c       | m * 10 <sup>12</sup> ) |
| 2.790          | 1.602                  |

| METHOD 2 | <u>METHO</u> | <b>D</b> 2 |
|----------|--------------|------------|
|          |              | <u>U 3</u> |
| 1.129    | 1.1;         | 38         |
|          |              |            |
|          |              |            |

### CHROMIUM OXIDE



| HEAT CAPACITY, (cal/ g –C) |      |  |
|----------------------------|------|--|
| (Cp)                       | (Cv) |  |
| 0.1650                     |      |  |

<u>YOUNGS MODULUS</u> (Dynes/cm \* 10<sup>12</sup>)

| <b>GRÜNEISEN CONSTANT</b> |            |             |   |
|---------------------------|------------|-------------|---|
| METHC                     | DD 1 METHO | OD 2 METHOD | 3 |
| 1.400                     | _          |             |   |
|                           |            |             |   |

# COBALT



| HEAT CAPACITY, (cal/g –C) |        |  |
|---------------------------|--------|--|
| (Cp)                      | (Cv)   |  |
| 0.1010                    | 0.0987 |  |

| YOUNGS MODULUS                 | BULK MODULUS |  |
|--------------------------------|--------------|--|
| (Dynes/cm * 10 <sup>12</sup> ) |              |  |
| 2.040                          | 1.830        |  |



### COBALT OXIDE



| HEAT CAPACITY, (cal/ g –C) |      |  |
|----------------------------|------|--|
| · (Cp)                     | (Cv) |  |
| 0.1750                     |      |  |

YOUNGS MODULUS (Dynes/cm \* 10<sup>12</sup>)

| <b>GRÜNEISEN CONSTANT</b> |         |          |          |  |
|---------------------------|---------|----------|----------|--|
| M                         | ETHOD 1 | METHOD 2 | METHOD 3 |  |
| 1                         | .600    |          |          |  |
|                           |         |          |          |  |

# COPPER

| DENSITY<br>(g/cm)<br>8.94 | POISSON'S RATIO<br>0.343                        |
|---------------------------|---|
| <u>SOUND VELOCITY</u>     | VOL. COEFF. THERMAL                             |
| (cm/microsec)             | EXPANSION, (10 <sup>-6</sup> °C <sup>-1</sup> ) |
| 0.3927                    | 49.6  |

| HEAT CAPACITY, (cal/ g –C) |        |  |
|----------------------------|--------|--|
| (Cp)                       | (Cv)   |  |
| 0.0910                     | 0.0883 |  |

| YOUNGS MODULUS                 | BULK MODULUS |  |
|--------------------------------|--------------|--|
| (Dynes/cm * 10 <sup>12</sup> ) |              |  |
| 1.298                          | 1.378        |  |



### CORNING 7740 (PYREX®)



| HEAT CAPACITY, (cal/ g –C) |        |  |
|----------------------------|--------|--|
| (Cp)                       | (Cv)   |  |
| 0.1840                     | 0.1839 |  |

<u>YOUNGS MODULUS</u> (Dynes/cm \* 10<sup>12</sup>) 0.628 0.349



# **CORNING 7940 (FUSED SILICA)**



| HEAT CAPACITY, (cal/ g –C) |        |  |
|----------------------------|--------|--|
| (Cp)                       | (Cv)   |  |
| 0.1800                     | 0.1800 |  |

<u>YOUNGS MODULUS</u> (Dynes/cm \* 10<sup>12</sup>) 0.725 0.366



### CORNING 7971 (ULE®)



| HEAT CAPACITY, (cal/g-C) |        |  |
|--------------------------|--------|--|
| (Cp)                     | (Cv)   |  |
| 0.1780                   | 0.1780 |  |

YOUNGS MODULUSBULK MODULUS(Dynes/cm \* 1012)0.6760.345



# **CORNING 9606 (PYROCERAM®)**



| HEAT CAPACITY, (cal/g –C) |        |  |
|---------------------------|--------|--|
| (Cp)                      | (Cv)   |  |
| 0.1720                    | 0.1720 |  |

| YOUNGS MODULUS                 | BULK MODULUS |  |
|--------------------------------|--------------|--|
| (Dynes/cm * 10 <sup>12</sup> ) |              |  |
| 1.187                          | 0.761        |  |



# DYSPROSIUM

| <u>DENSITY</u><br>(g/cm)<br>8.54 | <u>POISSON'S RATIO</u><br>0.243                        |
|----------------------------------|--|
| SOUND VELOCITY                   | <u>VOL. COEFF. THERMAL</u>                             |
| (cm/microsec)                    | <u>EXPANSION,</u> (10 <sup>-6</sup> °C <sup>-1</sup> ) |
| 0,2280                           | 28.7   |

| HEAT CAPACITY, (cal/ gC) |        |  |
|--------------------------|--------|--|
| (Cp)                     | (Cv)   |  |
| 0.0414                   | 0.0411 |  |

YOUNGS MODULUS (Dynes/cm \* 10<sup>12</sup>)

0.631 0.410

| <b>GRÜNEISEN CONSTANT</b> |          |          |
|---------------------------|----------|----------|
| METHOD 1                  | METHOD 2 | METHOD 3 |
|                           | 0.861    | 0.801`   |
|                           |          |          |

### ERBIUM



| HEAT CAPACITY, (cal/g –C) |        |  |
|---------------------------|--------|--|
| (Cp)                      | (Cv)   |  |
| 0.0401                    | 0.0398 |  |

| YOUNGS MODULUS                 | BULK MODULUS |
|--------------------------------|--------------|
| (Dynes/cm * 10 <sup>12</sup> ) |              |
| 0.733                          | 0.465        |

| GRÜNEISEN CONSTANT |          |          |  |
|--------------------|----------|----------|--|
| METHOD 1           | METHOD 2 | METHOD 3 |  |
| _                  | 0.891    | 0.873    |  |
|                    |          |          |  |

### EUROPIUM

| <u>DENSITY</u><br>(g/cm) | <u>POISSON'S RATIO</u>                          |
|--------------------------|---|
| 5.25                     | 0.286   |
| SOUND VELOCITY           | VOL. COEFF. THERMAL                             |
| (cm/microsec)            | EXPANSION, (10 <sup>-6</sup> °C <sup>-1</sup> ) |
| 0.1581                   | 75.0  |

| <u>HEAT CAPACITY</u> , (cal/ g –C) |       |  |
|------------------------------------|-------|--|
| (Cp)                               | (Cv)  |  |
| 0.0421                             | 0.411 |  |

YOUNGS MODULUSBULK MODULUS(Dynes/cm \* 1012)0.1470.131



#### GADOLINIUM



| <u>HEAT CAPACITY</u> , (cal/g –C) |        |  |
|-----------------------------------|--------|--|
| (Cp)                              | (Cv)   |  |
| 0.0550                            | 0.0550 |  |

<u>YOUNGS MODULUS</u> (Dynes/cm \* 10<sup>12</sup>) 0.562 0.389



# **GALLIUM ANTIMONIDE (S.C.)**



| HEAT CAPACITY, (cal/ g –C) |       |  |
|----------------------------|-------|--|
| (Cp)                       | (Cv)  |  |
| 0.0602                     | 0.599 |  |

YOUNGS MODULUSBULK MODULUS(Dynes/cm \* 1012)0.8800.574



#### **GALLIUM ARSENIDE**



| HEAT CAPACITY, (cal/g –C) |        |  |
|---------------------------|--------|--|
| (Cp)                      | (Cv)   |  |
| 0.0803                    | 0.0799 |  |

| YOUNGS MODULUS                 | BULK MODULUS |  |
|--------------------------------|--------------|--|
| (Dynes/cm * 10 <sup>12</sup> ) |              |  |
| 0.791                          | 0.797        |  |



# **GERMANIUM (S.C.)**



| HEAT CAPACITY, (cal/g –C) |        |  |
|---------------------------|--------|--|
| (Cp)                      | (Cv)   |  |
| 0.0769                    | 0.0766 |  |

 YOUNGS MODULUS
 BULK MODULUS

 (Dynes/cm \* 10<sup>12</sup>)
 0.778



# GOLD

| <u>DENSITY</u><br>(g/cm)               | POISSON'S RATIO   |
|--|---|
| 19.24                                  | 0.420   |
| <u>SOUND VELOCITY</u><br>(cm/microsec) | <u>VOL. COEFF. THERMAL</u><br><u>EXPANSION</u> , (10 <sup>-6</sup> °C <sup>-1</sup> ) |
| 0.3056                                 | 42.7  |

| HEAT CAPACITY, (cal/ g –C) |        |  |
|----------------------------|--------|--|
| (Cp)                       | (Cv)   |  |
| 0.0331                     | 0.0320 |  |

| YOUNGS MODULUS                 | BULK MODULUS |  |
|--------------------------------|--------------|--|
| (Dynes/cm * 10 <sup>12</sup> ) |              |  |
| 0.812                          | 1.692        |  |



#### HAFNIUM

| <u>DENSITY</u><br>(g/cm) | POISSON'S RATIO                                 |
|--------------------------|---|
| 13.3                     | 0.284   |
|                          |   |
| SOUND VELOCITY           | VOL. COEFF. THERMAL                             |
| (cm/microsec)            | EXPANSION, (10 <sup>-6</sup> °C <sup>-1</sup> ) |
| 0.2984                   | 18.0  |

| HEAT CAPACITY, (cal/ g –C) |        |  |
|----------------------------|--------|--|
| (Cp)                       | (Cv)   |  |
| 0.0345                     | 0.0343 |  |

YOUNGS MODULUS (Dynes/cm \* 10<sup>12</sup>)

1.535

1.184



#### HAFNIUM CARBIDE



| HEAT CAPACITY, (cal/ g –C) |        |  |
|----------------------------|--------|--|
| (Cp)                       | (Cv)   |  |
| 0.0460                     | 0.0458 |  |

| YOUNGS MODULUS | BULK MODULUS           |  |
|----------------|------------------------|--|
| (Dynes/c       | m * 10 <sup>12</sup> ) |  |
| 3.521          | 1.956                  |  |


## HOLMIUM

| <u>DENSITY</u><br>(g/cm) | POISSON'S RATIO   |
|--------------------------|---|
| 8.78                     | 0.255   |
|                          |   |
| SOUND VELOCITY           | VOL. COEFF. THERMAL                                     |
| (cm/microsec)            | <u>EXPANSION</u> , (10 <sup>-6</sup> °C <sup>-1</sup> ) |
| 0.2386                   | 29.4  |

| HEAT CAPACITY, (cal/ g –C) |        |  |
|----------------------------|--------|--|
| (Cp)                       | (Cv)   |  |
| 0.0393                     | 0.0390 |  |

| YOUNGS MODULUS                 | BULK MODULUS |  |
|--------------------------------|--------------|--|
| (Dynes/cm * 10 <sup>12</sup> ) |              |  |
| 0.667                          | 0.458        |  |



## INDIUM

| <u>DENSITY</u><br>(g/cm)<br>7.3 | POISSON'S RATIO<br>0.452                                |
|---------------------------------|---|
| <u>SOUND VELOCITY</u>           | <u>VOL. COEFF. THERMAL</u>                              |
| (cm/microsec)                   | <u>EXPANSION</u> , (10 <sup>-6</sup> °C <sup>-1</sup> ) |
| 0.2231                          | 97.4  |

| HEAT CAPACITY, (cal/g-C) |        |  |
|--------------------------|--------|--|
| (Cp)                     | (Cv)   |  |
| 0.0550                   | 0.0516 |  |

| YOUNGS MODULUS                 | BULK MODULUS |  |
|--------------------------------|--------------|--|
| (Dynes/cm * 10 <sup>12</sup> ) |              |  |
| 0.105                          | 0.363        |  |



## **INDIUM ANTIMONIDE (S.C.)**



| HEAT CAPACITY, (cal/ g –C) |        |  |
|----------------------------|--------|--|
| (Cp)                       | (Cv)   |  |
| 0.0497                     | 0.0496 |  |

<u>YOUNGS MODULUS</u> (Dynes/cm \* 10<sup>12</sup>) 0.626 0.433



#### INVAR® 36/74



| HEAT CAPACITY, (cal/ g –C) |        |  |
|----------------------------|--------|--|
| (Cp)                       | (Cv)   |  |
| 0.1230                     | 0.1230 |  |

| YOUNGS MODULUS                 | BULK MODULUS |  |
|--------------------------------|--------------|--|
| (Dynes/cm * 10 <sup>12</sup> ) |              |  |
| 1.440                          | 0.994        |  |

| GRÜNEISEN CONSTANT |          |          |  |
|--------------------|----------|----------|--|
| METHOD 1           | METHOD 2 | METHOD 3 |  |
| —                  | 0.065    | 0.065    |  |
|                    |          |          |  |

## IRIDIUM

| DENSITY<br>(g/cm)<br>22.5 | <u>poisson's ratio</u><br>0.190                 |
|---------------------------|---|
| SOUND VELOCITY            | VOL. COEFF. THERMAL                             |
| (cm/microsec)             | EXPANSION, (10 <sup>-6</sup> °C <sup>-1</sup> ) |
| 0.3724                    | 19.3  |

| HEAT CAPACITY, (cal/g –C) |        |  |
|---------------------------|--------|--|
| (Cp)                      | (Cv)   |  |
| 0.0308                    | 0.0304 |  |

| YOUNGS MODULUS                 | BULK MODULUS |  |
|--------------------------------|--------------|--|
| (Dynes/cm * 10 <sup>12</sup> ) |              |  |
| 5.798                          | 3.117        |  |

| <b>GRÜNEISEN CONSTANT</b> |          |          |
|---------------------------|----------|----------|
| METHOD 1                  | METHOD 2 | METHOD 3 |
| _                         | 2.077    | 2.100    |
|                           |          |          |

# IRON

| <u>DENSITY</u><br>(g/cm)<br>7.86 | <u>POISSON'S RATIO</u><br>0.293                 |
|----------------------------------|---|
| <u>SOUND VELOCITY</u>            | VOL. COEFF. THERMAL                             |
| (cm/microsec)                    | EXPANSION, (10 <sup>-6</sup> °C <sup>-1</sup> ) |
| 0.4595                           | 35.4  |

| HEAT CAPACITY, (cal/ g –C) |        |  |
|----------------------------|--------|--|
| (Cp)                       | (Cv)   |  |
| 0.1070                     | 0.1051 |  |

| YOUNGS MODULUS                 | BULK MODULUS |  |
|--------------------------------|--------------|--|
| (Dynes/cm * 10 <sup>12</sup> ) |              |  |
| 2.114                          | 1.698        |  |

| <b>GRÜNEISEN CONSTANT</b> |          |          |
|---------------------------|----------|----------|
| METHOD 1                  | METHOD 2 | METHOD 3 |
| 1.690                     | 1.670    | 1.740    |
|                           |          |          |

# IRON (Ni 10)

| <u>DENSITY</u><br>(g/cm)<br>7.88       | POISSON'S RATIO  |
|--|--|
| <u>SOUND VELOCITY</u><br>(cm/microsec) | VOL. COEFF. THERMAL<br>EXPANSION, (10 <sup>-6</sup> °C <sup>-1</sup> ) |
| 0.4457                                 | 28.2   |

| HEAT CAPACITY, (cal/ g –C) |        |  |
|----------------------------|--------|--|
| (Cp)                       | (Cv)   |  |
| 0.1130                     | 0.1119 |  |

<u>YOUNGS MODULUS</u> (Dynes/cm \* 10<sup>12</sup>) 2.022 1.565

GRÜNEISEN CONSTANT METHOD 1 METHOD 2 METHOD 3 — 1.185 1.196

# IRON (Ni 18)

| <u>DENSITY</u><br>(g/cm)<br>7.97 | <u>poisson's ratio</u><br>0.306                 |
|----------------------------------|---|
| SOUND VELOCITY                   | VOL. COEFF. THERMAL                             |
| (cm/microsec)                    | EXPANSION, (10 <sup>-6</sup> °C <sup>-1</sup> ) |
| 0.4403                           | 34.0  |

| HEAT CAPACITY, (cal/g-C) |        |  |
|--------------------------|--------|--|
| (Cp)                     | (Cv)   |  |
| 0.1150                   | 0.1134 |  |

| YOUNGS MODULUS                 | BULK MODULUS |  |
|--------------------------------|--------------|--|
| (Dynes/cm * 10 <sup>12</sup> ) |              |  |
| 1.797                          | 1.543        |  |



# IRON (Ni 26)

| <u>DENSITY</u><br>(g/cm) | POISSON'S RATIO   |
|--------------------------|---|
| 7.97                     | 0.328   |
|                          |   |
| SOUND VELOCITY           | VOL. COEFF. THERMAL                                     |
| (cm/microsec)            | <u>EXPANSION</u> , (10 <sup>-6</sup> °C <sup>-1</sup> ) |
| 0.4368                   | 39.7  |

| HEAT CAPACITY, (cal/g –C) |        |  |
|---------------------------|--------|--|
| (Cp)                      | (Cv)   |  |
| 0.1190                    | 0.1169 |  |

| YOUNGS MODULUS                 | BULK MODULUS |  |
|--------------------------------|--------------|--|
| (Dynes/cm * 10 <sup>12</sup> ) |              |  |
| 1.566                          | 1.521        |  |



### **IRON OXIDE**



| HEAT CAPACITY, (cal/ g –C) |        |  |
|----------------------------|--------|--|
| (Cp)                       | (Cv)   |  |
| 0.1560                     | 0.1535 |  |

| YOUNGS MODULUS                 | BULK MODULUS |  |
|--------------------------------|--------------|--|
| (Dynes/cm * 10 <sup>12</sup> ) |              |  |
| 2.121                          | 1.941        |  |

| GRÜNEISEN CONSTANT |          |          |
|--------------------|----------|----------|
| METHOD 1           | METHOD 2 | METHOD 3 |
|                    | 1.779    | 1.808    |
|                    |          |          |

## IRTRAN® —1 (MgF2)



| <u>HEAT CAPACITY</u> , (cal/ g –C) |        |  |
|------------------------------------|--------|--|
| (Cp)                               | (Cv)   |  |
| 0.2440                             | 0.2418 |  |

 YOUNGS MODULUS
 BULK MODULUS

 (Dynes/cm \* 10<sup>12</sup>)

 1.145
 1.004



## IRTRAN® -2 (ZnS)



| HEAT CAPACITY, (cal/g –C) |        |  |
|---------------------------|--------|--|
| (Cp)                      | (Cv)   |  |
| 0.1130                    | 0.1124 |  |

| YOUNGS MODULUS                 | BULK MODULUS |
|--------------------------------|--------------|
| (Dynes/cm * 10 <sup>12</sup> ) |              |
| 0.966                          | 0.847        |

| <b>GRÜNEISEN CONSTANT</b> |          |          |
|---------------------------|----------|----------|
| METHOD 1                  | METHOD 2 | METHOD 3 |
| —                         | 0.907    | 0.912    |
|                           |          |          |

## IRTRAN® ----3 (CaF2)



| <u>HEAT CAPACITY</u> , (cal/ g –C) |        |  |
|------------------------------------|--------|--|
| (Cp)                               | (Cv)   |  |
| 0.2170                             | 0.2106 |  |

YOUNGS MODULUSBULK MODULUS(Dynes/cm \* 1012)0.9870.866

| GRÜNEISEN CONSTANT |          |          |  |
|--------------------|----------|----------|--|
| METHOD 1           | METHOD 2 | METHOD 3 |  |
| _                  | 1.727    | 1.780    |  |
|                    |          |          |  |

## IRTRAN® -4 (ZnSe)



\_\_\_\_\_

| HEAT CAPACITY, (cal/ g –C) |        |  |
|----------------------------|--------|--|
| (Cp)                       | (Cv)   |  |
| 0.0800                     | 0.0796 |  |

| YOUNGS MODULUS | BULK MODULUS      |
|----------------|-------------------|
| (Dynes/cm * 1  | 0 <sup>12</sup> ) |
| 0.711          | 0.624             |



# IRTRAN® ----5 (MgO)



| <u>HEAT CAPACITY</u> , (cal/ g –C) |        |  |
|------------------------------------|--------|--|
| (Cp)                               | (Cv)   |  |
| 0.2220                             | 0.2188 |  |

| YOUNGS MODULUS | BULK MODULUS         |  |
|----------------|----------------------|--|
| (Dynes/cm      | * 10 <sup>12</sup> ) |  |
| 3.326          | 1.680                |  |

| <b>GRÜNEISEN CONSTANT</b> |          |          |   |
|---------------------------|----------|----------|---|
| METHOD 1                  | METHOD 2 | METHOD 3 | 1 |
|                           | 1.521    | 1.543    |   |
|                           |          |          |   |

# IRTRAN® —6 (CdTe)



| HEAT CAPACITY, (cal/ g –C) |        |  |
|----------------------------|--------|--|
| (Cp)                       | (Cv)   |  |
| 0.0560                     | 0.0559 |  |

| YOUNGS MODULUS | BULK MODULUS            |
|----------------|-------------------------|
| (Dynes/d       | cm * 10 <sup>12</sup> ) |
| 0.366          | 0.244                   |



#### **KAPTON**®

| <u>DENSITY</u><br>(g/cm) | POISSON'S RATIO                                 |
|--------------------------|---|
| 1.42                     | 0.433   |
|                          |   |
| SOUND VELOCITY           | VOL. COEFF. THERMAL                             |
| (cm/microsec)            | EXPANSION, (10 <sup>-6</sup> °C <sup>-1</sup> ) |
| 0.2327                   | 85.2  |

| HEAT CAPACITY, (cal/ g –C) |        |  |
|----------------------------|--------|--|
| (Cp)                       | (Cv)   |  |
| 0.2390                     | 0.2362 |  |

 YOUNGS MODULUS
 BULK MODULUS

 (Dynes/cm \* 10<sup>12</sup>)

 0.031
 0.077



## KEL —F®



| HEAT CAPACITY, (cal/g –C) |        |  |
|---------------------------|--------|--|
| (Cp)                      | (Cv)   |  |
| 0.2200                    | 0.2117 |  |

| YOUNGS MODULUS | BULK MODULUS           |
|----------------|------------------------|
| (Dynes/c       | m * 10 <sup>12</sup> ) |
| 0.035          | 0.047                  |

| <b>GRÜNEISEN CONSTANT</b> |          |          |
|---------------------------|----------|----------|
| METHOD 1                  | METHOD 2 | METHOD 3 |
|                           | 0.554    | 0.576    |
|                           |          |          |

### KOVAR®

| <u>DENSITY</u><br>(g/cm) | POISSON'S RATIO   |
|--------------------------|---|
| 8.34                     | 0.341   |
|                          | ·······   |
| SOUND VELOCITY           | VOL. COEFF. THERMAL                                     |
| (cm/microsec)            | <u>EXPANSION</u> , (10 <sup>-6</sup> °C <sup>-1</sup> ) |
| 0.4038                   | 18.0  |

| HEAT CAPACITY, (cal/g –C) |        |  |
|---------------------------|--------|--|
| (Cp)                      | (Cv)   |  |
| 0.1050                    | 0.1046 |  |

YOUNGS MODULUS BULK MODULUS (Dynes/cm \* 10<sup>12</sup>)

1.297 1.360



## LANTHANUM

| DENSITY<br>(g/cm) | POISSON'S RATIO                                 |
|-------------------|---|
| 6.17              | 0.288   |
|                   |   |
| SOUND VELOCITY    | VOL. COEFF. THERMAL                             |
| (cm/microsec)     | EXPANSION, (10 <sup>-6</sup> °C <sup>-1</sup> ) |
| 0.2048            | 15.7  |

| HEAT CAPACITY, (cal/ g –C) |        |  |
|----------------------------|--------|--|
| (Cp)                       | (Cv)   |  |
| 0.0470                     | 0.0469 |  |

| YOUNGS MODULUS                 | BULK MODULUS |  |
|--------------------------------|--------------|--|
| (Dynes/cm * 10 <sup>12</sup> ) |              |  |
| 0.359                          | 0.243        |  |

| <b>GRÜNEISEN CONSTANT</b> |          |          |
|---------------------------|----------|----------|
| METHOD 1                  | METHOD 2 | METHOD 3 |
| —<br>—                    | 0.335    | 0.315    |
|                           |          |          |

## LEAD

| DENSITY<br>(g/cm)<br>11.3 | POISSON'S RATIO<br>0.440                        |
|---------------------------|---|
| <u>SOUND VELOCITY</u>     | VOL. COEFF. THERMAL                             |
| (cm/microsec)             | EXPANSION, (10 <sup>-6</sup> °C <sup>-1</sup> ) |
| 0.2002                    | 86.9  |

| HEAT CAPACITY, (cal/ g –C) |        |  |
|----------------------------|--------|--|
| (Cp)                       | (Cv)   |  |
| 0.0305                     | 0.0283 |  |

<u>YOUNGS MODULUS</u> (Dynes/cm \* 10<sup>12</sup>) 0.161 0.458

GRÜNEISEN CONSTANT METHOD 1 METHOD 2 METHOD 3 2.780 2.729 2.972

## LEAD SULPHIDE (S.C.)

\_



| HEAT CAPACITY, (cal/ g –C) |        |
|----------------------------|--------|
| (Cp)                       | (Cv)   |
| 0.0390                     | 0.0359 |

| YOUNGS MODULUS | BULK MODULUS           |
|----------------|------------------------|
| (Dynes/cn      | n * 10 <sup>12</sup> ) |
| 0.113          | 0.622                  |



## LITHIUM FLOURIDE (S.C.)



<u>HEAT CAPACITY</u>, (cal/ g –C) (Cp) (Cv) 0.3860 0.3683

<u>YOUNGS MODULUS</u> (Dynes/cm \* 10<sup>12</sup>) 1.059 0.617

GRÜNEISEN CONSTANT METHOD 1 METHOD 2 METHOD 3 — 1.513 1.562

## LITHIUM NIOBATE (S.C.)



| <u>HEAT CAPACITY</u> , (cal/ g –C) |        |  |
|------------------------------------|--------|--|
| (Cp)                               | (Cv)   |  |
| 0.1515                             | 0.1495 |  |

| YOUNGS MODULUS | BULK MODULUS           |
|----------------|------------------------|
| (Dynes/cn      | n * 10 <sup>12</sup> ) |
| 1.728          | 1.174                  |



## LUCITE®

| <u>DENSITY</u><br>(g/cm)<br>1.19 | POISSON'S RATIO<br>0.323                                |
|----------------------------------|---|
| <u>SOUND VELOCITY</u>            | <u>VOL. COEFF. THERMAL</u>                              |
| (cm/microsec)                    | <u>EXPANSION</u> , (10 <sup>-6</sup> °C <sup>-1</sup> ) |
| 0.2177                           | 223.0   |

| HEAT CAPACITY, (cal/ g –C) |        |  |
|----------------------------|--------|--|
| (Cp)                       | (Cv)   |  |
| 0.3100                     | 0.2932 |  |

YOUNGS MODULUS (Dynes/cm \* 10<sup>12</sup>)

0.056

0.060

GRÜNEISEN CONSTANT METHOD 1 METHOD 2 METHOD 3 — 0.815 0.862

#### LEUTETIUM



| HEAT CAPACITY, (cal/g –C) |        |  |
|---------------------------|--------|--|
| (Cp)                      | (Cv)   |  |
| 0.0470                    | 0.0468 |  |

| YOUNGS MODULUS                 | BULK MODULUS |  |
|--------------------------------|--------------|--|
| (Dynes/cm * 10 <sup>12</sup> ) |              |  |
| 0.843                          | 0.526        |  |

| <b>GRÜNEISEN CONSTANT</b> |          |          |  |
|---------------------------|----------|----------|--|
| METHOD 1                  | METHOD 2 | METHOD 3 |  |
| —                         | 0.677    | 0.681    |  |
|                           |          |          |  |

### MAGNESIUM



| HEAT CAPACITY, (cal/g_C) |        |  |
|--------------------------|--------|--|
| (Cp)                     | (Cv)   |  |
| 0.2444                   | 0.2362 |  |

<u>YOUNGS MODULUS</u> (Dynes/cm \* 10<sup>12</sup>) 0.447 0.356

GRÜNEISEN CONSTANT METHOD 1 METHOD 2 METHOD 3 1.460 1.445 1.548

#### MAGNESIUM OXIDE



| <u>HEAT CAPACITY</u> , (cal/ g –C) |        |  |
|------------------------------------|--------|--|
| (Cp)                               | (Cv)   |  |
| 0.2220                             | 0.2190 |  |

| YOUNGS MODULUS                 | BULK MODULUS |  |
|--------------------------------|--------------|--|
| (Dynes/cm * 10 <sup>12</sup> ) |              |  |
| 3.100                          | 1.625        |  |

| <b>GRÜNEISEN CONSTANT</b> |          |          |  |
|---------------------------|----------|----------|--|
| METHOD 1                  | METHOD 2 | METHOD 3 |  |
|                           | 1.559    | 1.482    |  |
|                           |          |          |  |

### MOLYBDENUM

| <u>DENSITY</u><br>(g/cm)<br>10.2 | <u>POISSON'S RATIO</u><br>0.293                 |
|----------------------------------|---|
| SOUND VELOCITY                   | VOL. COEFF. THERMAL                             |
| (cm/microsec)                    | EXPANSION, (10 <sup>-6</sup> °C <sup>-1</sup> ) |
| 0.5033                           | 14.4  |

| HEAT CAPACITY, (cal/ g –C) |        |  |
|----------------------------|--------|--|
| (Cp)                       | (Cv)   |  |
| 0.0592                     | 0.0588 |  |

<u>YOUNGS MODULUS</u> (Dynes/cm \* 10<sup>12</sup>) 3.248 2.612

GRÜNEISEN CONSTANT METHOD 1 METHOD 2 METHOD 3 1.520 1.473 1.498

### **MYLAR**®

| DENSITY<br>(g/cm)<br>1 39 | POISSON'S RATIO  |
|---------------------------|--|
| SOUND VELOCITY            | VOL. COEFF. THERMAL  |
| (cm/microsec)<br>0.2200   | <u>EXPANSION</u> , (10 <sup>-6</sup> °C <sup>-1</sup> )<br>171.0 |

| <u>HEAT CAPACITY</u> , (cal/ g –C) |        |  |
|------------------------------------|--------|--|
| (Cp)                               | (Cv)   |  |
| 0.2260                             | 0.2166 |  |

<u>YOUNGS MODULUS</u> (Dynes/cm \* 10<sup>12</sup>) 0.055 0.063



## NEODYMIUM

| DENSITY<br>(g/cm)<br>7.0 | POISSON'S RATIO<br>0.306                        |
|--------------------------|---|
| <u>SOUND VELOCITY</u>    | VOL. COEFF. THERMAL                             |
| (cm/microsec)            | EXPANSION, (10 <sup>-6</sup> °C <sup>-1</sup> ) |
| 0.2157                   | 20.7  |

| HEAT CAPACITY, (cal/ g –C) |        |  |
|----------------------------|--------|--|
| (Cp)                       | (Cv)   |  |
| 0.0490                     | 0.0489 |  |

| YOUNGS MODULUS                 | BULK MODULUS |  |
|--------------------------------|--------------|--|
| (Dynes/cm * 10 <sup>12</sup> ) |              |  |
| 0.379                          | 0.325        |  |



## NICKEL

| <u>DENSITY</u><br>(g/cm)               | POISSON'S RATIO  |
|--|--|
| 8.9                                    | 0.306  |
|  |  |
| <u>SOUND VELOCITY</u><br>(cm/microsec) | VOL. COEFF. THERMAL<br>EXPANSION, (10 <sup>-6</sup> °C <sup>-1</sup> ) |
| 0.4523                                 | 40.3   |

| <u>HEAT CAPACITY</u> , (cal/ g –C) |        |  |
|------------------------------------|--------|--|
| (Cp)                               | (Cv)   |  |
| 0.1070                             | 0.1046 |  |

| YOUNGS MODULUS                 | BULK MODULUS |  |
|--------------------------------|--------------|--|
| (Dynes/cm * 10 <sup>12</sup> ) |              |  |
| 2.198                          | 1.876        |  |



### NICKEL OXIDE



| HEAT CAPA | <u>CITY</u> , (cal/ g –C) |
|-----------|---------------------------|
| (Cp)      | (Cv)                      |
| 0.1420    |                           |

YOUNGS MODULUS (Dynes/cm \* 10<sup>12</sup>)

| <b>GRÜNEISEN CONSTANT</b> |          |          |
|---------------------------|----------|----------|
| METHOD 1                  | METHOD 2 | METHOD 3 |
| 1.500                     | —        |          |
|                           |          |          |

#### NIOBIUM



| <u>HEAT CAPACITY</u> , (cal/ g –C) |        |  |
|------------------------------------|--------|--|
| (Cp)                               | (Cv)   |  |
| 0.0633                             | 0.0626 |  |

| YOUNGS MODULUS                 | BULK MODULUS |  |
|--------------------------------|--------------|--|
| (Dynes/cm * 10 <sup>12</sup> ) |              |  |
| 1.049                          | 1.703        |  |



## NIOBIUM CARBIDE

| DENSITY<br>(g/cm)                      | POISSON'S RATIO  |
|--|--|
| 7.03                                   | 0.200  |
| <u>SOUND VELOCITY</u><br>(cm/microsec) | <u>VOL. COEFF. THERMAL</u><br><u>EXPANSION,</u> (10 <sup>-6</sup> °C <sup>-1</sup> ) |
| 0.4981                                 | 17.1   |

| HEAT CAPACITY, (cal/ g –C) |        |  |
|----------------------------|--------|--|
| (Cp)                       | (Cv)   |  |
| 0.0880                     | 0.0875 |  |

<u>YOUNGS MODULUS</u> (Dynes/cm \* 10<sup>12</sup>) 3.407 1.893



### NYLON 6



| <u>HEAT CAPACITY</u> , (cal/ g –C) |        |
|------------------------------------|--------|
| (Cp)                               | (Cv)   |
| 0.3710                             | 0.3437 |

<u>YOUNGS MODULUS</u> (Dynes/cm \* 10<sup>12</sup>) 0.039 0.064


### **OTWR (QUARTZ PHENOLIC)**



| <u>HEAT CAPACITY</u> , (cal/ g –C) |        |  |
|------------------------------------|--------|--|
| (Cp)                               | (Cv)   |  |
| 0.4160                             | 0.4159 |  |

<u>YOUNGS MODULUS</u> (Dynes/cm \* 10<sup>12</sup>) 0.240 0.167



### PALLADIUM

| <u>DENSITY</u><br>(g/cm) | POISSON'S RATIO                                 |
|--------------------------|---|
| 11.4                     | 0.335   |
|                          |   |
| SOUND VELOCITY           | VOL. COEFF. THERMAL                             |
| (cm/microsec)            | EXPANSION, (10 <sup>-6</sup> °C <sup>-1</sup> ) |
| 0.3829                   | 35.5  |

| HEAT CAPACITY, (cal/ g –C) |        |  |
|----------------------------|--------|--|
| (Cp)                       | (Cv)   |  |
| 0.0580                     | 0.0567 |  |

| YOUNGS MODULUS                 | BULK MODULUS |  |
|--------------------------------|--------------|--|
| (Dynes/cm * 10 <sup>12</sup> ) |              |  |
| 1.653                          | 1.670        |  |



### PLATINUM

| DENSITY<br>(g/cm) | POISSON'S RATIO   |
|-------------------|---|
| 21.5              | 0.390   |
|                   |   |
| SOUND VELOCITY    | VOL. COEFF. THERMAL                                     |
| (cm/microsec)     | <u>EXPANSION</u> , (10 <sup>-6</sup> °C <sup>-1</sup> ) |
| 0.3538            | 26.5  |

| HEAT CAPACITY, (cal/ g –C) |        |  |
|----------------------------|--------|--|
| (Cp)                       | (Cv)   |  |
| 0.0317                     | 0.0311 |  |

<u>YOUNGS MODULUS</u> (Dynes/cm \* 10<sup>12</sup>) 1.670 2.530



# PLUTONIUM (ALPHA)



| <u>HEAT CAPACITY</u> , (cal/ g –C) |        |  |
|------------------------------------|--------|--|
| (Cp)                               | (Cv)   |  |
| 0.0320                             | 0.0287 |  |

<u>YOUNGS MODULUS</u> (Dynes/cm \* 10<sup>12</sup>)

0.993 0.467



# **POCO GRAPHITE (AXF)**



| HEAT CAPACITY, (cal/ g –C) |        |  |
|----------------------------|--------|--|
| (Cp)                       | (Cv)   |  |
| 0.2110                     | 0.2110 |  |

| YOUNGS MODULUS                 | BULK MODULUS |
|--------------------------------|--------------|
| (Dynes/cm * 10 <sup>12</sup> ) |              |
| 0.138                          | 0.104        |



# POLYETHYLENE (HIGH DENSITY)



| <u>HEAT CAPACITY</u> , (cal/ g –C) |        |  |
|------------------------------------|--------|--|
| (Cp)                               | (Cv)   |  |
| 0.5300                             | 0.4780 |  |

<u>YOUNGS MODULUS</u> (Dynes/cm \* 10<sup>12</sup>) 0.032 0.047



#### POLYSTYRENE

| <u>DENSITY</u><br>(g/cm) | POISSON'S RATIO                                 |
|--------------------------|---|
| 1.05                     | 0.379   |
|                          |   |
| SOUND VELOCITY           | VOL. COEFF. THERMAL                             |
| (cm/microsec)            | EXPANSION, (10 <sup>-6</sup> °C <sup>-1</sup> ) |
| 0.1976                   | 220.0   |

| <u>HEAT CAPACITY</u> , (cal/ g –C) |        |  |
|------------------------------------|--------|--|
| (Cp)                               | (Cv)   |  |
| 0.3200                             | 0.3063 |  |

 YOUNGS MODULUS
 BULK MODULUS

 (Dynes/cm \* 10<sup>12</sup>)
 0.030
 0.042



#### POLYVINYLCHLORIDE



| HEAT CAPACITY, (cal/g –C) |        |  |
|---------------------------|--------|--|
| (Cp)                      | (Cv)   |  |
| 0.2400                    | 0.2286 |  |

| YOUNGS MODULUS                 | BULK MODULUS |  |
|--------------------------------|--------------|--|
| (Dynes/cm * 10 <sup>12</sup> ) |              |  |
| 0.038                          | 0.052        |  |

| <b>GRÜNEISEN CONSTANT</b> |          |          |  |
|---------------------------|----------|----------|--|
| METHOD 1                  | METHOD 2 | METHOD 3 |  |
| —                         | 0.770    | 0.808    |  |
|                           |          |          |  |

# **POTASSIUM BROMIDE (S.C.)**



| HEAT CAPACITY, (cal/ g –C) |        |  |
|----------------------------|--------|--|
| (Cp)                       | (Cv)   |  |
| 0.1040                     | 0.0982 |  |

<u>YOUNGS MODULUS</u> (Dynes/cm \* 10<sup>12</sup>) 0.255 0.167



# POTASSIUM CHLORIDE (S.C.)



| HEAT CAPACITY, (cal/g-C) |        |  |
|--------------------------|--------|--|
| (Cp)                     | (Cv)   |  |
| 0.1636                   | 0.1560 |  |

<u>YOUNGS MODULUS</u> (Dynes/cm \* 10<sup>12</sup>) 0.297 0.174



# POTASSIUM IODIDE (S.C.)



| HEAT CAPACITY, (cal/g –C) |        |  |
|---------------------------|--------|--|
| (Cp)                      | (Cv)   |  |
| 0.0790                    | 0.0746 |  |

YOUNGS MODULUS (Dynes/cm \* 10<sup>12</sup>)

0.175

0.117



#### PRASEODYMIUM



16.2

0.2114

<u>HEAT CAPACITY</u>, (cal/g –C) (Cp) (Cv) 0.0460 0.0459

| YOUNGS MODULUS                 | BULK MODULUS |  |
|--------------------------------|--------------|--|
| (Dynes/cm * 10 <sup>12</sup> ) |              |  |
| 0.352                          | 0.299        |  |



#### **PYROLYTIC GRAPHITE**



| <u>HEAT CAPACITY</u> , (cal/ g –C) |        |  |
|------------------------------------|--------|--|
| (Cp)                               | (Cv)   |  |
| 0.1650                             | 0.1650 |  |

YOUNGS MODULUSBULK MODULUS(Dynes/cm \* 1012)0.5180.247



#### **QUARTZ PHENOLIC**



| HEAT CAPACITY, (cal/g –C) |        |  |
|---------------------------|--------|--|
| (Cp)                      | (Cv)   |  |
| 0.2276                    | 0.2272 |  |

| YOUNGS MODULUS                 | BULK MODULUS |  |
|--------------------------------|--------------|--|
| (Dynes/cm * 10 <sup>12</sup> ) |              |  |
| 0.262                          | 0.177        |  |



# QUARTZ (S.C.)



| HEAT CAPACITY, (cal/g_C) |        |  |
|--------------------------|--------|--|
| (Cp)                     | (Cv)   |  |
| 0.1770                   | 0.1753 |  |

| YOUNGS MODULUS                 | BULK MODULUS |
|--------------------------------|--------------|
| (Dynes/cm * 10 <sup>12</sup> ) |              |
| 0.700                          | 0.370        |



### RHENIUM

| <u>DENSITY</u><br>(g/cm) | POISSON'S RATIO                                 |
|--------------------------|---|
| 21.1                     | 0.288   |
|                          |   |
| SOUND VELOCITY           | VOL. COEFF. THERMAL                             |
| (cm/microsec)            | EXPANSION, (10 <sup>-6</sup> °C <sup>-1</sup> ) |
| 0.4118                   | 18.6  |

| <u>HEAT CAPACITY</u> , (cal/ g –C) |        |  |
|------------------------------------|--------|--|
| (Cp)                               | (Cv)   |  |
| 0.0332                             | 0.0328 |  |

<u>YOUNGS MODULUS</u> (Dynes/cm \* 10<sup>12</sup>) 4.541 3.577



### RHODIUM

| <u>DENSITY</u><br>(g/cm) | POISSON'S RATIO                                 |
|--------------------------|---|
| 12.45                    | 0.328   |
|                          |   |
| SOUND VELOCITY           | VOL. COEFF, THERMAL                             |
| (cm/microsec)            | EXPANSION, (10 <sup>-6</sup> °C <sup>-1</sup> ) |
| 0.4778                   | 24.7  |

| HEAT CAPACITY, (cal/ g –C) |        |  |
|----------------------------|--------|--|
| (Cp)                       | (Cv)   |  |
| 0.0590                     | 0.0580 |  |

YOUNGS MODULUS (Dynes/cm \* 10<sup>12</sup>)

2.940 2.842



### SCANDIUM



| HEAT CAPACITY, (cal/g –C) |        |  |
|---------------------------|--------|--|
| (Cp)                      | (Cv)   |  |
| 0.1370                    | 0.1358 |  |

| YOUNGS MODULUS | BULK MODULUS           |
|----------------|------------------------|
| (Dynes/cr      | n * 10 <sup>12</sup> ) |
| 0.793          | 0.572                  |



# SILICON

| <u>DENSITY</u><br>(g/cm)<br>2.33 | POISSON'S RATIO<br>0.212                        |
|----------------------------------|---|
| <u>SOUND VELOCITY</u>            | VOL. COEFF. THERMAL                             |
| (cm/microsec)                    | EXPANSION, (10 <sup>-6</sup> °C <sup>-1</sup> ) |
| 0.6545                           | 7.9   |

| HEAT CAPACITY | <u>Y</u> , (cal/ g –C) |
|---------------|------------------------|
| (Cp)          | (Cv)                   |
| 0.1700        | 0.1698                 |

| YOUNGS MODULUS                 | BULK MODULUS |
|--------------------------------|--------------|
| (Dynes/cm * 10 <sup>12</sup> ) |              |
| 1.690                          | 0.979        |

| <b>GRÜNEISEN CONSTANT</b> |          |          |
|---------------------------|----------|----------|
| METHOD 1                  | METHOD 2 | METHOD 3 |
| _                         | 0.475    | 0.466    |
|                           |          |          |

#### SILICON CARBIDE



| HEAT CAPACITY, (cal/g-C) |        |  |
|--------------------------|--------|--|
| (Cp)                     | (Cv)   |  |
| 0.1650                   | 0.1645 |  |

| YOUNGS MODULUS                 | BULK MODULUS |  |
|--------------------------------|--------------|--|
| (Dynes/cm * 10 <sup>12</sup> ) |              |  |
| 3.862                          | 1.921        |  |

| <b>GRÜNEISEN CONSTANT</b> |          |          |
|---------------------------|----------|----------|
| METHOD 1                  | METHOD 2 | METHOD 3 |
|                           | 0.945    | 0.912    |
|                           |          |          |

# SILVER

| <u>DENSITY</u><br>(g/cm)<br>10.5 | POISSON'S RATIO   |
|----------------------------------|---|
| SOUND VELOCITY                   | VOL. COEFF. THERMAL   |
| (cm/microsec)<br>0.3176          | <u>EXPANSION</u> , (10 <sup>-5</sup> °C <sup>-1</sup> )<br>56.8 |

| HEAT CAPACITY, (cal/ g –C) |        |  |
|----------------------------|--------|--|
| (Cp)                       | (Cv)   |  |
| 0.0564                     | 0.0541 |  |

YOUNGS MODULUS BULK MODULUS (Dynes/cm \* 10<sup>12</sup>)

1.036

0.827

GRÜNEISEN CONSTANT METHOD 1 METHOD 2 METHOD 3 2.550 2.428 2.474

# SILVER CHLORIDE (S.C.)



| <u>HEAT CAPACITY</u> , (cal/ g –C) |        |  |
|------------------------------------|--------|--|
| (Cp)                               | (Cv)   |  |
| 0.0850                             | 0.0804 |  |

| YOUNGS MODULUS                 | BULK MODULUS |  |
|--------------------------------|--------------|--|
| (Dynes/cm * 10 <sup>12</sup> ) |              |  |
| 0.240                          | 0.442        |  |



# SODIUM CHLORIDE (S.C.)



| HEAT_CAPACITY, (cal/g –C) |        |  |
|---------------------------|--------|--|
| (Cp)                      | (Cv)   |  |
| 0.2040                    | 0.1917 |  |

.

<u>YOUNGS MODULUS</u> (Dynes/cm \* 10<sup>12</sup>) 0.375 0.252



#### **STAINLESS STEEL 304L**



| HEAT CAPACITY, (cal/g-C) |        |  |
|--------------------------|--------|--|
| (Cp)                     | (Cv)   |  |
| 0.1160                   | 0.1131 |  |

| YOUNGS MODULUS                 | BULK MODULUS |  |
|--------------------------------|--------------|--|
| (Dynes/cm * 10 <sup>12</sup> ) |              |  |
| 2.153                          | 1.660        |  |



#### STRONTIUM

| <u>DENSITY</u><br>(g/cm) | POISSON'S RATIO                                 |
|--------------------------|---|
| 2.6                      | 0.297   |
|                          |   |
| SOUND VELOCITY           | VOL. COEFF. THERMAL                             |
| (cm/microsec)            | EXPANSION, (10 <sup>-6</sup> °C <sup>-1</sup> ) |
| 0.2118                   | 67.5  |

| <u>HEAT CAPACITY</u> , (cal/ g –C) |        |  |
|------------------------------------|--------|--|
| (Cp)                               | (Cv)   |  |
| 0.0686                             | 0.0671 |  |

YOUNGS MODULUS (Dynes/cm \* 10<sup>12</sup>)

0.142 0.117



# TANTALUM

| <u>DENSITY</u><br>(g/cm) | POISSON'S RATIO   |
|--------------------------|---|
| 16.6                     | 0.342   |
|                          |   |
| SOUND VELOCITY           | VOL. COEFF. THERMAL                                     |
| (cm/microsec)            | <u>EXPANSION</u> , (10 <sup>-6</sup> °C <sup>-1</sup> ) |
| 0.3388                   | 18.9  |

| HEAT CAPACITY, (cal/ g –C) |        |  |
|----------------------------|--------|--|
| (Cp)                       | (Cv)   |  |
| 0.0330                     | 0.0327 |  |

| YOUNGS MODULUS                 | BULK MODULUS |  |
|--------------------------------|--------------|--|
| (Dynes/cm * 10 <sup>12</sup> ) |              |  |
| 1.857                          | 1.963        |  |



#### **TANTALUM CARBIDE**



| HEAT CAPACITY, (cal/ g –C) |        |  |
|----------------------------|--------|--|
| (Cp)                       | (Cv)   |  |
| 0.0455                     | 0.0453 |  |

YOUNGS MODULUSBULK MODULUS(Dynes/cm \* 1012)2.8481.582



#### **TEFLON**®



| HEAT CAPACITY, (cal/ g –C) |        |  |
|----------------------------|--------|--|
| (Cp)                       | (Cv)   |  |
| 0.2410                     | 0.2302 |  |

| YOUNGS MODULUS                 | BULK MODULUS | • • |
|--------------------------------|--------------|-----|
| (Dynes/cm * 10 <sup>12</sup> ) |              |     |
| 0.014                          | 0.035        |     |



#### TERBIUM

| DENSITY<br>(g/cm)<br>8.23 | POISSON'S RATIO<br>0.261                        |
|---------------------------|---|
| SOUND VELOCITY            | VOL. COEFF. THERMAL                             |
| (cm/microsec)             | EXPANSION, (10 <sup>-6</sup> °C <sup>-1</sup> ) |
| 0.2199                    | 28.3  |

| HEAT CAPACITY, (cal/ g –C) |        |  |
|----------------------------|--------|--|
| (Cp)                       | (Cv)   |  |
| 0.0437                     | 0.0434 |  |

<u>YOUNGS MODULUS</u> (Dynes/cm \* 10<sup>12</sup>)

0.575

0.400



# THALLIUM BROMIDE (S.C.)



| HEAT CAPACITY, (cal/ g –C) |        |  |
|----------------------------|--------|--|
| (Cp)                       | (Cv)   |  |
| 0.0450                     | 0.0397 |  |

| YOUNGS MODULUS | BULK MODULUS           |
|----------------|------------------------|
| (Dynes/cr      | n * 10 <sup>12</sup> ) |
| 0.241          | 0.225                  |

| GRÜNEISEN CONSTANT |          |          |  |
|--------------------|----------|----------|--|
| METHOD 1           | METHOD 2 | METHOD 3 |  |
|                    | 2.494    | 2.830    |  |
|                    |          |          |  |

#### THALLIUM BROMIDE — CHLORIDE



ι.

| HEAT CAPACITY, (cal/ g –C) |        |  |
|----------------------------|--------|--|
| (Cp)                       | (Cv)   |  |
| 0.0480                     | 0.0429 |  |

YOUNGS MODULUS (Dynes/cm \* 10<sup>12</sup>)

0.242

0.228



#### THALLIUM BROMIDE —IODIDE



| <u>HEAT CAPACITY</u> , (cal/ g –C) |        |  |
|------------------------------------|--------|--|
| (Cp)                               | (Cv)   |  |
| 0.0365                             | 0.0307 |  |

| YOUNGS MODULUS                 | BULK MODULUS |  |
|--------------------------------|--------------|--|
| (Dynes/cm * 10 <sup>12</sup> ) |              |  |
| 0.199                          | 0.198        |  |



# **THALLIUM CHLORIDE (S.C.)**



| HEAT CAPACITY, (cal/g-C) |        |  |
|--------------------------|--------|--|
| (Cp)                     | (Cv)   |  |
| 0.0520                   | 0.0459 |  |

YOUNGS MODULUS<br/>(Dynes/cm \* 1012)BULK MODULUS<br/>0.236



### THORIUM

| DENSITY<br>(g/cm)<br>11.7 | POISSON'S RATIO<br>0.302                        |
|---------------------------|---|
| SOUND VELOCITY            | VOL. COEFF. THERMAL                             |
| (cm/microsec)             | EXPANSION, (10 <sup>-6</sup> °C <sup>-1</sup> ) |
| 0.2327                    | 33.1  |

| <u>HEAT CAPACITY</u> , (cal/ g –C) |        |  |
|------------------------------------|--------|--|
| (Cp)                               | (Cv)   |  |
| 0.0283                             | 0.0279 |  |

<u>YOUNGS MODULUS</u> (Dynes/cm \* 10<sup>12</sup>) 0.751 0.632



#### THORIUM DIOXIDE



| HEAT CAPACITY, (cal/ g –C) |        |  |
|----------------------------|--------|--|
| (Cp)                       | (Cv)   |  |
| 0.0560                     | 0.0557 |  |

<u>YOUNGS MODULUS</u> (Dynes/cm \* 10<sup>12</sup>)

0.693

1.373

GRÜNEISEN CONSTANT METHOD 1 METHOD 2 METHOD 3 — 0.696 0.699

# THULIUM

| <u>DENSITY</u><br>(g/cm)<br>9.31 | <u>poisson's ratio</u><br>0.235                 |
|----------------------------------|---|
| SOUND VELOCITY                   | VOL. COEFF. THERMAL                             |
| (cm/microsec)                    | EXPANSION, (10 <sup>-6</sup> °C <sup>-1</sup> ) |
| 0.2223                           | 36.0  |

| <u>HEAT CAPACITY</u> , (cal/ g –C) |        |  |
|------------------------------------|--------|--|
| (Cp)                               | (Cv)   |  |
| 0.0382                             | 0.0377 |  |

| YOUNGS MODULUS                 | BULK MODULUS |
|--------------------------------|--------------|
| (Dynes/cm * 10 <sup>12</sup> ) |              |
| 0.755                          | 0.475        |


# TIN

| <u>DENSITY</u><br>(g/cm) | POISSON'S RATIO   |
|--------------------------|---|
| 7.29                     | 0.340   |
|                          |   |
| SOUND VELOCITY           | VOL. COEFF. THERMAL                                     |
| (cm/microsec)            | <u>EXPANSION</u> , (10 <sup>-5</sup> °C <sup>-1</sup> ) |
| 0.2703                   | 66.4  |

| HEAT CAPACITY, (cal/ g –C) |        |  |
|----------------------------|--------|--|
| (Cp)                       | (Cv)   |  |
| 0.0545                     | 0.0525 |  |

YOUNGS MODULUSBULK MODULUS(Dynes/cm \* 1012)0.4500.469



# TIN OXIDE



| <u>HEAT CAPACITY</u> , (cal/ g –C) |      |  |
|------------------------------------|------|--|
| (Cp)                               | (Cv) |  |
| 0.0830                             | —    |  |

<u>YOUNGS MODULUS</u> (Dynes/cm \* 10<sup>12</sup>)



### TITANIUM



| HEAT CAPACITY, (cal/ g –C) |        |  |
|----------------------------|--------|--|
| (Cp)                       | (Cv)   |  |
| 0.1240                     | 0.1229 |  |

YOUNGS MODULUSBULK MODULUS(Dynes/cm \* 1012)1.0601.104



## **TITANIUM CARBIDE**

| <u>DENSITY</u><br>(g/cm)               | POISSON'S RATIO  |
|--|--|
| 4.9                                    | 0.200  |
|  |  |
| <u>SOUND VELOCITY</u><br>(cm/microsec) | VOL. COEFF. THERMAL<br>EXPANSION, (10 <sup>-6</sup> °C <sup>-1</sup> ) |
| 0.5985                                 | 19.2   |

| HEAT CAPACITY, (cal/ g –C) |        |  |
|----------------------------|--------|--|
| (Cp)                       | (Cv)   |  |
| 0.1340                     | 0.1331 |  |

<u>YOUNGS MODULUS</u> (Dynes/cm \* 10<sup>12</sup>) 3.159 1.755



## TITANIUM DIOXIDE



| HEAT CAPACITY, (cal/ g –C) |        |  |
|----------------------------|--------|--|
| (Cp)                       | (Cv)   |  |
| 0.1690                     | 0.1674 |  |

YOUNGS MODULUSBULK MODULUS(Dynes/cm \* 1012)2.4401.776



## TUNGSTEN



| HEAT CAPACITY, (cal/ g –C) |        |  |
|----------------------------|--------|--|
| (Cp)                       | (Cv)   |  |
| 0.0318                     | 0.0316 |  |

<u>YOUNGS MODULUS</u> (Dynes/cm \* 10<sup>12</sup>) 4.110 3.110

GRÜNEISEN CONSTANT METHOD 1 METHOD 2 METHOD 3 1.540 1.635 1.646

### **TUNGSTEN CARBIDE**



| <u>HEAT CAPACITY</u> , (cal/ g –C) |        |  |
|------------------------------------|--------|--|
| (Cp)                               | (Cv)   |  |
| 0.0510                             | 0.0508 |  |

 YOUNGS MODULUS
 BULK MODULUS

 (Dynes/cm \* 10<sup>12</sup>)

 5.344
 3.190



# URANIUM

| <u>DENSITY</u><br>(g/cm)<br>19.1 | <u>POISSON'S RATIO</u><br>0.197  |
|----------------------------------|--|
| SOUND VELOCITY<br>(cm/microsec)  | VOL. COEFF. THERMAL<br>EXPANSION, (10 <sup>-6</sup> °C <sup>-1</sup> ) |
| 0.2431                           | 41.9   |

| HEAT CAPACITY, (cal/g-C) |        |  |
|--------------------------|--------|--|
| (Cp)                     | (Cv)   |  |
| 0.0276                   | 0.0269 |  |

| YOUNGS MODULUS                 | BULK MODULUS |  |
|--------------------------------|--------------|--|
| (Dynes/cm * 10 <sup>12</sup> ) |              |  |
| 2.054                          | 1.129        |  |



## **URANIUM OXIDE**

| <u>DENSITY</u><br>(g/cm)<br>10.3 | POISSON'S RATIO   |
|----------------------------------|---|
| SOUND VELOCITY                   | VOL. COEFF. THERMAL                                     |
| (cm/microsec)<br>0.3985          | EXPANSION, (10 <sup>-6</sup> °C <sup>-1</sup> )<br>28.2 |

| HEAT CAPACITY, (cal/ g –C) |        |  |
|----------------------------|--------|--|
| (Cp)                       | (Cv)   |  |
| 0.0649                     | 0.0640 |  |

<u>YOUNGS MODULUS</u> (Dynes/cm \* 10<sup>12</sup>) 1.814 1.591



## VANADIUM

| <u>DENSITY</u><br>(g/cm)<br>6.0 | <u>poisson's ratio</u><br>0.365                         |
|---------------------------------|---|
| <u>SOUND VELOCITY</u>           | <u>VOL. COEFF. THERMAL</u>                              |
| (cm/microsec)                   | <u>EXPANSION</u> , (10 <sup>-6</sup> °C <sup>-1</sup> ) |
| 0.5072                          | 23.4  |

| HEAT CAPACITY, (cal/ g –C) |        |  |
|----------------------------|--------|--|
| (Cp)                       | (Cv)   |  |
| 0.1043                     | 0.1033 |  |

<u>YOUNGS MODULUS</u> (Dynes/cm \* 10<sup>12</sup>) 1.276 1.580

GRÜNEISEN CONSTANT METHOD 1 METHOD 2 METHOD 3 1.290 1.379 1.426

# **VYCOR**®

| <u>DENSITY</u><br>(g/cm) | POISSON'S RATIO                                 |
|--------------------------|---|
| 2.18                     | 0.190   |
|                          |   |
| SOUND VELOCITY           | VOL. COEFF. THERMAL                             |
| (cm/microsec)            | EXPANSION, (10 <sup>-6</sup> °C <sup>-1</sup> ) |
| 0.4125                   | 2.4   |

| HEAT CAPACITY, (cal/ g –C) |        |  |
|----------------------------|--------|--|
| (Cp)                       | (Cv)   |  |
| 0.2000                     | 0.2000 |  |

 YOUNGS MODULUS
 BULK MODULUS

 (Dynes/cm \* 10<sup>12</sup>)
 0.690
 0.371

| GRÜNEISEN CONSTANT |          |          |  |
|--------------------|----------|----------|--|
| METHOD 1           | METHOD 2 | METHOD 3 |  |
|                    | 0.049    | 0.049    |  |
|                    |          |          |  |

## YTTERBIUM



| HEAT CAPACITY, (cal/g –C) |        |  |
|---------------------------|--------|--|
| (Cp)                      | (Cv)   |  |
| 0.0346                    | 0.0338 |  |

| YOUNGS MODULUS | BULK MODULUS         |
|----------------|----------------------|
| (Dynes/cm      | * 10 <sup>12</sup> ) |
| 0.178          | 0.138                |

| <b>GRÜNEISEN CONSTANT</b> |          |          |  |
|---------------------------|----------|----------|--|
| METHOD 1                  | METHOD 2 | METHOD 3 |  |
| _                         | 1.089    | 1.053    |  |
|                           |          |          |  |

# YTTRIUM

| <u>DENSITY</u><br>(g/cm)<br>4.46                 | POISSON'S RATIO<br>0.255   |
|--|--|
| <u>SOUND VELOCITY</u><br>(cm/microsec)<br>0.3274 | VOL. COEFF. THERMAL<br>EXPANSION, (10 <sup>-6</sup> °C <sup>-1</sup> )<br>33.9 |

| HEAT CAPACITY, (cal/g –C) |        |  |
|---------------------------|--------|--|
| (Cp)                      | (Cv)   |  |
| 0.0680                    | 0.0671 |  |

<u>YOUNGS MODULUS</u> (Dynes/cm \* 10<sup>12</sup>)

0.663

0.469



# YTTRIUM ALUMINATE (YAG®, S.C.)



| HEAT CAPACITY, (cal/ g –C) |        |  |
|----------------------------|--------|--|
| (Cp)                       | (Cv)   |  |
| 0.1542                     | 0.1521 |  |

| YOUNGS MODULUS                 | BULK MODULUS |
|--------------------------------|--------------|
| (Dynes/cm * 10 <sup>12</sup> ) |              |
| 2.780                          | 1.849        |

| GRÜNEISEN CONSTANT |          |          |  |
|--------------------|----------|----------|--|
| METHOD 1           | METHOD 2 | METHOD 3 |  |
| ·                  | 1.681    | 1.705    |  |
|                    |          |          |  |

## ZINC

 $\psi_{\phi}$ 

| DENSITY<br>(g/cm)<br>6.92 | POISSON'S RATIO<br>0.249                                |
|---------------------------|---|
| <u>SOUND VELOCITY</u>     | <u>VOL. COEFF. THERMAL</u>                              |
| (cm/microsec)             | <u>EXPANSION</u> , (10 <sup>-5</sup> °C <sup>-1</sup> ) |
| 0.3128                    | 90.9  |

| <u>HEAT CAPACITY</u> , (cal/ g –C) |        |  |
|------------------------------------|--------|--|
| (Cp)                               | (Cv)   |  |
| 0.0929                             | 0.0870 |  |

<u>YOUNGS MODULUS</u> (Dynes/cm \* 10<sup>12</sup>) 1.045 0.694



# ZINC OXIDE



| HEAT CAPACITY, (cal/ g –C) |        |
|----------------------------|--------|
| (Cp)                       | (Cv)   |
| 0.1180                     | 0.1177 |

| YOUNGS MODULUS                 | BULK MODULUS |  |
|--------------------------------|--------------|--|
| (Dynes/cm * 10 <sup>12</sup> ) |              |  |
| 1.235                          | 1.411        |  |



# ZIRCONIUM

| DENSITY<br>(g/cm)               | POISSON'S RATIO  |
|---------------------------------|--|
| 6.5                             | 0.332  |
| SOUND VELOCITY<br>(cm/microsec) | VOL. COEFF. THERMAL<br>EXPANSION, (10 <sup>-6</sup> °C <sup>-1</sup> ) |
| 0.3747                          | 17.1   |

 YOUNGS MODULUS
 BULK MODULUS

 (Dynes/cm \* 10<sup>12</sup>)
 0.892



#### **ZIRCONIUM CARBIDE**



| HEAT CAPACITY, (cal/g –C) |        |  |
|---------------------------|--------|--|
| (Cp)                      | (Cv)   |  |
| 0.0900                    | 0.0898 |  |

| YOUNGS MODULUS                 | BULK MODULUS |
|--------------------------------|--------------|
| (Dynes/cm * 10 <sup>12</sup> ) |              |
| 1.379                          | 0.766        |



### **ZIRCONIUM DIOXIDE**



| HEAT CAPACITY, (cal/g –C) |        |
|---------------------------|--------|
| (Cp)                      | (Cv)   |
| 0.1090                    | 0.1079 |

<u>YOUNGS MODULUS</u> (Dynes/cm \* 10<sup>12</sup>)

1.687 1.222

<u>GRÜNEISEN CONSTANT</u> <u>METHOD 1 METHOD 2 METHOD 3</u> — 1.135 1.254

#### LABORATORY OPERATIONS

The Aerospace Corporation functions as an "architect-engineer" for national security programs, specializing in advanced military space systems. The Corporation's Laboratory Operations supports the effective and timely development and operation of national security systems through scientific research and the application of advanced technology. Vital to the success of the Corporation is the technical staff's wide-ranging expertise and its ability to stay abreast of new technological developments and program support issues associated with rapidly evolving space systems. Contributing capabilities are provided by these individual organizations:

Electronics and Photonics Laboratory: Microelectronics, VLSI reliability, failure analysis, solid-state device physics, compound semiconductors, radiation effects, infrared and CCD detector devices, data storage and display technologies; lasers and electro-optics, solid state laser design, micro-optics, optical communications, and fiber optic sensors; atomic frequency standards, applied laser spectroscopy, laser chemistry, atmospheric propagation and beam control, LIDAR/LADAR remote sensing; solar cell and array testing and evaluation, battery electrochemistry, battery testing and evaluation.

Space Materials Laboratory: Evaluation and characterizations of new materials and processing techniques: metals, alloys, ceramics, polymers, thin films, and composites; development of advanced deposition processes; nondestructive evaluation, component failure analysis and reliability; structural mechanics, fracture mechanics, and stress corrosion; analysis and evaluation of materials at cryogenic and elevated temperatures; launch vehicle fluid mechanics, heat transfer and flight dynamics; aerothermodynamics; chemical and electric propulsion; environmental chemistry; combustion processes; space environment effects on materials, hardening and vulnerability assessment; contamination, thermal and structural control; lubrication and surface phenomena.

Space Science Applications Laboratory: Magnetospheric, auroral and cosmic ray physics, wave-particle interactions, magnetospheric plasma waves; atmospheric and ionospheric physics, density and composition of the upper atmosphere, remote sensing using atmospheric radiation; solar physics, infrared astronomy, infrared signature analysis; infrared surveillance, imaging, remote sensing, and hyperspectral imaging; effects of solar activity, magnetic storms and nuclear explosions on the Earth's atmosphere, ionosphere and magnetosphere; effects of electromagnetic and particulate radiations on space systems; space instrumentation, design fabrication and test; environmental chemistry, trace detection; atmospheric chemical reactions, atmospheric optics, light scattering, state-specific chemical reactions and radiative signatures of missile plumes.

**Center for Microtechnology:** Microelectromechanical systems (MEMS) for space applications; assessment of microtechnology space applications; laser micromachining; laser-surface physical and chemical interactions; micropropulsion; micro- and nanosatel-lite mission analysis; intelligent microinstruments for monitoring space and launch system environments.

Office of Spectral Applications: Multispectral and hyperspectral sensor development; data analysis and algorithm development; applications of multispectral and hyperspectral imagery to defense, civil space, commercial, and environmental missions.



Carps

ð.

2350 E. El Segundo Boulevard El Segundo, California 90245-4691 U.S.A.