

REPORT DOCUMENTATION PAGE

Form Approved
OMB No. 0704-0188

Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.

PLEASE DO NOT RETURN YOUR FORM TO THE ABOVE ADDRESS.

1. REPORT DATE (DD-MM-YYYY) 16/04/2003		2. REPORT TYPE Final Report		3. DATES COVERED 15 Nov 1999 to 14 Nov 2000	
4. TITLE AND SUBTITLE Nanotubule Membranes - Fundamentals and applications in Electrochemical Energy and Stochastic Sensing				5a. CONTRACT NUMBER N00014-001-D108	
				5b. GRANT NUMBER N00014-001-D108	
				5c. PROGRAM ELEMENT NUMBER -	
6. AUTHOR(S) Dr. Charles R. Martin				5d. PROJECT NUMBER -	
				5e. TASK NUMBER -	
				5f. WORK UNIT NUMBER -	
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) Department of Chemistry, University of Florida, Gainesville, FL 32611				8. PERFORMING ORGANIZATION REPORT NUMBER -	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) Office of Naval Research 800 N. Quincy St. Arlington, VA 22217-5000				10. SPONSOR/MONITOR'S ACRONYM(S) ONR	
				11. SPONSOR/MONITOR'S REPORT NUMBER(S) -	
12. DISTRIBUTION/AVAILABILITY STATEMENT Distribution Unlimited DISTRIBUTION STATEMENT A Approved for Public Release Distribution Unlimited					
13. SUPPLEMENTARY NOTES -					
14. ABSTRACT <div style="border: 1px solid black; padding: 10px; text-align: center; font-size: 2em; font-weight: bold;">20030502 150</div>					
15. SUBJECT TERMS Nanotubules, Electrochemical Energy, Stochastic Sensing, Bilayer-Mimetic Chemistry, Single Nanopores.					
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT UL	18. NUMBER OF PAGES -	
a. REPORT Unclass.	b. ABSTRACT Unclass.	c. THIS PAGE Unclass.		19a. NAME OF RESPONSIBLE PERSON Charles R. Martin	
				19b. TELEPHONE NUMBER (Include area code) 352-3928205	

GENERAL INSTRUCTIONS FOR COMPLETING SF 298

1. **REPORT DATE.** Full publication date, including day, month, if available. Must cite at least the year and be year 2000 compliant, e.g. 30-06-1998; xx-06-1998; xx-xx-1998.
2. **REPORT TYPE.** State the type of report, such as final, technical, interim, memorandum, master's thesis, progress, quarterly, research, special, group study, etc.
3. **DATES COVERED.** Indicate the time during which the work was performed and the report was written, e.g., Jun 1997 - Jun 1998; 1-10 Jun 1996; May - Nov 1998; Nov 1998.
4. **TITLE.** Enter title and subtitle with volume number and part number, if applicable. On classified documents, enter the title classification in parentheses.
- 5a. **CONTRACT NUMBER.** enter all contract numbers as they appear in the report, e.g. F33615-86-C-5169.
- 5b. **GRANT NUMBER.** enter all grant numbers as they appear in the report, e.g. AFOSR-82-1234.
- 5c. **PROGRAM ELEMENT NUMBER.** Enter all program element numbers as they appear in the report, e.g. 61101A.
- 5d. **PROJECT NUMBER.** Enter all project numbers as they appear in the report, e.g. 1F665702D1257; ILIR.
- 5e. **TASK NUMBER.** Enter all task numbers as they appear in the report, e.g. 05; RF0330201; T4112.
- 5f. **WORK UNIT NUMBER.** Enter all work unit numbers as they appear in the report, e.g. 001; AFAPL30480105.
6. **AUTHOR(S).** Enter name(s) of person(s) responsible for writing the report, performing the research, or credited with the content of the report. The form of entry is the last name, first name, middle initial, and additional qualifiers separated by commas, e.g. Smith, Richard, J., Jr.
7. **PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES).** Self-explanatory.
8. **PERFORMING ORGANIZATION REPORT NUMBER.** Enter all unique alphanumeric report numbers assigned by the performing organization, e.g. BRL-1234; AFWL-TR-85-4017-Vol-21-PT-2.
9. **SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES).** Enter the name and address of the organization(s) financially responsible for and monitoring the work.
10. **SPONSOR/MONITOR ACRONYM(S).** Enter, if available, e.g. BRL, ARDEC, NADC.
11. **SPONSOR/MONITOR'S REPORT NUMBER(S).** Enter report number as assigned by the sponsoring/monitoring agency, if available, e.g. BRL-TR-829; -215.
12. **DISTRIBUTION/AVAILABILITY STATEMENT.** Use agency-mandated availability statements to indicate the public availability or distribution limitations of the report. If additional limitations/restrictions or special markings are indicated, follow agency authorization procedures, e.g. RD/FRD, PROPIN, ITAR, etc. Include copyright information.
13. **SUPPLEMENTARY NOTES.** Enter information not included elsewhere such as: prepared in cooperation with; translation of; report supersedes; old edition number, etc.
14. **ABSTRACT.** A brief (approximately 200 words) factual summary of the most significant information.
15. **SUBJECT TERMS.** Key words or phrases identifying major concepts in the report.
16. **SECURITY CLASSIFICATION.** Enter security classification in accordance with security classification regulations, be.go. U, C, S, etc. If this form contains classified information, stamp classification level on the top and bottom of this page.
17. **LIMITATION OF ABSTRACT.** This block must be completed to assign a distribution limitation to the abstract. Enter UP (Unclassified Unlimited) or SAR (Same as Report). An entry in this block is necessary if the abstract is to be limited.

FINAL REPORT

Grant #: N00014-00-1-0108

Principal Investigator: Dr. Charles R. Martin

Institution: University of Florida

Grant Title: Nanotubule Membranes - Fundamentals and Applications in Electrochemical Energy and Stochastic Sensing

Award Period: 15 Nov 1999 to 14 Nov 2002

Objective: The objectives are: 1) To develop the measurement technology that will allow us to determine if the α -hemolysin channel has been successfully immobilized, 2) To develop ultrathin film channel immobilization technology, and 3) To develop methods for isolating a single nanotubule in an Au nanotubule membrane. For the Electrochemistry Division the objectives are 1) To develop new classes of nanotubule membranes whose transport properties can be modulated electrochemically by applying a potential to the membrane, 2) To show that surface chemistry of these nanotubule membranes can be varied by simple chemical and electrochemical derivatization schemes, 3) To study electroosmotic flow phenomena in these new membranes.

Approach: With funds from a previous ONR grant the P.I. has developed a procedure for preparing Au nanotubules within the pores of a microporous polycarbonate template membrane. These nanotubules have monodisperse diameters that can be controlled at will down to molecular dimensions (<1 nm). For the Biomolecular Division we want to immobilize α -hemolysin channels within these nanotubules to develop a new type of stochastic sensor that is rugged, reliable and practical. We have focused our efforts during the preceding year on two important goals. First, we are exploring methods for preparing surface films that will coat the nanotubule membrane surface and serve as the host for the α -hemolysin channel. Second, we are developing the technology for isolating a single nanotubule in such membranes. For the Electrochemistry Division we are exploring ways of electrochemically modulating transport in nanotubule membranes. We are investigating both the Au nanotubule membranes prepared by electroless deposition of Au within the pores of nanoporous polycarbonate templates and carbon nanotubule membranes prepared by chemical vapor deposition of C within the pores of microporous alumina templates. In both cases the nanotubule material is an electronic conductor. This allows us to apply a potential to the nanotubules relative to an external reference electrode immersed into a contacting electrolyte phase. It is via this route that we electrochemically modulate the transport properties of the membrane. We are electrochemically modulating both transport by diffusion and transport by electroosmotic flow across the membrane.

Accomplishments: For the Biomolecular Division our priority during previous three years was to develop a method preparation and characterization of a "bilayer mimic" on the surface of our gold nanotube membranes that will function as a host for the α -hemolysin channel. We are currently writing a research article on this new method. We have focused on the two objectives noted above - surface films and single pore membranes. In nature, the α -hemolysin channel self-assembles from solution across a lipid bilayer membrane. We need to be able to mimic this process such that the channel assembles at the surface of our nanotube membrane. Hence, the "bilayer mimic" must emulate a lipid bilayer.

The approach we are pursuing to prepare this surface film entails thiol chemisorption based on the micro-contact printing technique of the Whitesides group. By "inking" a poly(dimethylsiloxane) stamp with a desired thiol, we have been able to reproducibly transfer a stable, well-ordered monolayer to the nanotubule membrane surface. Because the key chemical characteristic of the interior of a lipid bilayer membrane is that it is hydrophobic, we have used hexadecanethiol (HDT) for the majority of these studies, and only those results will be presented here. We are currently using AC impedance and cyclic voltammetric methods, as well as contact angle measurements and transport experiments to characterize these films as we need to show that this route yields defect free ultrathin films that chemisorb only to the nanotube mouth and not along the walls of the nanotube.

The AC impedance and cyclic voltammetry data address the issue of whether or not the nanotubules are being wet when both faces are stamped. To study this, one face of the nanotubule membrane was stamped and exposed to solution while the other face was covered with a tape mask. In the voltammetry experiments, the stamped membrane was exposed to a solution of $\text{Fe}(\text{CN})_6^{3-}$. The absence of a large cathodic current indicates that the stamped HDT monolayer is not only blocking redox activity of the $\text{Fe}(\text{CN})_6^{3-}$ on the membrane face, but is also blocking it from occurring in the nanotubules by keeping the solution out of the nanotubules. In the AC impedance experiments, we were able to show that the resistance of the HDT stamped membrane decreases when exposed to a dilute solution of the anionic surfactant dodecylbenzene sulfonic acid (DBS). We have previously shown that DBS partitions into a hydrophobic monolayer, allowing the wetting of nanotubules. Through the experiments done using via these two methods, we were able to confirm that stamped monolayers effectively keep water out of the nanotubules.

We have also begun preliminary work using wild-type *alpha*-Hemolysin (αHL) provided by Dr. Hagan Bayley. In these experiments, we have been studying the interaction of αHL with the stamped monolayer by a series of contact angle measurements. We observed that the contact angle of a stamped membrane decreases significantly after exposure to αHL , suggesting that the αHL is strongly physisorbed to the HDT monolayer.

We have succeeded in etching pores of varying diameter, from $\sim 1 \mu\text{m}$ down to 30 nm, in these membranes, and we have imaged these pores with optical and electron microscopy. We have also developed a procedure based on fluorescence microscopy for isolating a single nanoscopic pore. Briefly, after etching the membrane, it is sputtered with gold to render it optically opaque. A drop of a fluorescent dye is placed on a microscope slide and the etched membrane is placed on top of the drop. The dye wicks through the pore and forms a droplet that is visible using the fluorescent microscope. A piece of Scotch tape with a punch hole is placed around the droplet, effectively isolating a single pore from neighboring pores. We are then able to verify pore diameter using scanning electron microscopy.

For the Electrochemistry Division, we have focused our efforts on the modulation of transport through carbon nanotubule membranes. Using electroosmotic flow, we have completely shut off transport across the membrane as well as enhancing it four fold. We have electrochemically modified the surface chemistry of the carbon nanotubules to prepare membranes with positive, negative, and zero surface charge. As electroosmotic flow is directly related to surface charge the electroosmotic flow across the membrane varies accordingly. Finally, we have prepared poly(vinyl ferrocene) nanotubules conformally within the carbon nanotubules by electropolymerization. These polymeric nanotubules are electrochemically addressable. Reduction and oxidation of the poly(vinylferrocene) nanotubules effectively and reversibly turns electroosmotic flow on and off.

Conclusions: For the Biomolecular Division we have developed a method to prepare and characterize a "bilayer mimic" on the surface of our gold nanotube membranes. This "bilayer mimic" will serve as the host for the α -hemolysin channel. We have also begun experiments that will allow us to study the interaction of the α -hemolysin with this "bilayer mimic". Additionally, we have developed a simple and reliable method to isolate single pores in the nanotube membranes. For the Electrochemistry Division we have investigated transport as a function of electroosmotic flow for carbon nanotubule membranes. Additionally, we have studied the effects of transmembrane applied current, electrolyte pH and concentration, and carbon nanotubules modification on electroosmotic flow. Finally, we have demonstrated dynamic control of electroosmotic flow by using the carbon nanotubule membrane as an electrode to electrochemically vary the membrane surface charge. This is an important step in studying electroosmotic flow at the nanoscale.

REFEREED PUBLICATIONS

1. Wirtz, M.; Martin, C.R. "Nanotube Membrane Sensors: Resistive Sensing and Ion Channel Mimetics," *Sensors Update*, accepted.
2. Lee, S.B.; Mitchell, D.T.; Trofin, L.; Nevanen, T.K.; S`derlund, H.; Martin, C.R. "Antibody-Based Bio/Nanotube Membranes for Enantiomeric Drug Separations," *Science*, **2002**, 296, 2198-2200.
3. Sides, C.R.; Li, N.; Patrissi, C.J.; Scrosati, B.; Martin, C.R. "Nanoscale Materials for Li-ion Batteries," *MRS Bulletin*, accepted.
4. Wirtz, M.; Parker, M.; Kobayashi, Y.; Martin, C.R. "Molecular Sieving and Sensing with Gold Nanotube Membranes," *Chemical Record*, accepted.
5. Wirtz, M.; Yu, S.; Martin, C.R. "Template Synthesized Gold Nanotube Membranes for Chemical Separations and Sensing," *Analyst*, **2002**, 127, 871-879.
6. Steinle, E.D.; Mitchell, D.T.; Wirtz, M.; Lee, S.B.; Young, V.Y.; Martin, C.R. "Ion-Channel Mimetic Micropore and Nanotube Membrane Sensors," *Anal. Chem.*, **2002**, 74, 2416-2422.
7. Miller, S.A.; Young, V.Y.; Martin, C.R. "Electroosmotic Flow in Template-Prepared Carbon Nanotube Membranes," *J. Am. Chem. Soc.*, **2001**, 123, 12335-12342.
8. Miller, S.A.; Martin, C.R. "Controlling the Rate and Direction of Electroosmotic Flow in Template-Prepared Carbon Nanotubule Membranes," *J. Electroanal. Chem.*, accepted.
9. Yu, S.; Lee, S.B.; Kang, M.; Martin, C.R. "Size-Based Protein Separations in Poly(ethylene glycol)- Derivatized Gold Nanotubule Membranes," *Nano Letters*, **2001**, 1, 495-498.
10. Lee, S.B.; Martin, C.R. "Controlling the Transport Properties of Gold Nanotubule Membranes Using Chemisorbed Thiols," *Chemistry of Materials*, **2001**, 13, 3236-3244.
11. Miller, S. A.; Martin, C. R. In *Encyclopedia of Nanoscience and Nanotechnology*; Schwarz, J. A., Contescu, C., Putyera, K., Eds.; Marcel Dekker, Inc.: New York, Accepted for publication.
12. Wirtz, M.; Miller, S. A.; Martin, C. R. *International Journal of Nanoscience* **2002**, 1, 255-268.