

REPORT DOCUMENTATION PAGE

AFRL-SR-AR-TR-03-

Public reporting burden for this collection of information is estimated to average 1 hour per response, including gathering and maintaining the data needed, and completing and reviewing the collection of information. Send all collection of information, including suggestions for reducing this burden, to Washington Headquarters Service, Paperwork Project, 4815 Rte. 2, Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Project, 4815 Rte. 2, Washington, DC 20503.

Number of copies of this report

0293

1. AGENCY USE ONLY (Leave blank)		2. REPORT DATE 22 JUL 03	3. REPORT TYPE AND DATES COVERED FNAL REPORT 21 JAN 00 TO 30 NOV 02
4. TITLE AND SUBTITLE GROWTH AND TAILORING OF PHOTOREFRACTIVE FIBERS USING THE LASER HEATED PEDESTAL GROWTH METHOD			5. FUNDING NUMBERS F49620-00-1-0134
6. AUTHOR(S) DR WILLIAM M. YEN			2303/CX 61102F
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) UNIVERSITY OF GEORGIA DEPARTMENT OF PHYSICS AND ASTRONOMY ATHENS, GA 30602			8. PERFORMING ORGANIZATION REPORT NUMBER
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) AFOSR/NL 4015 WILSON BLVD., ROOM 713 ARLINGTON, VA 22203-1954			10. SPONSORING/MONITORING AGENCY REPORT NUMBER
11. SUPPLEMENTARY NOTES			
20030822 143			
12a. DISTRIBUTION AVAILABILITY STATEMENT APPROVE FOR PUBLIC RELEASE: DISTRIBUTION UNLIMITED			12b. DISTRIBUTION STATEMENT
13. ABSTRACT (Maximum 200 words) Because of detailed evaluation of the quality of our LHPG fibers by Dr. D. Evans of the AFRL, we were able to pinpoint the cause of the majority of the defects in our Laser Heated Pedestal Growth (LHPG) fibers. The principal defects found in our materials lay in the non-uniformity of the diameter of our fibers and in the fact that the fibers contained cracks and striations, especially the thinner fibers, which adversely affect optical transmission. In addition, the fibers were grown in air and showed a dark coloration which required additional treatment and annealing to render transparent. In the course of this period of the grant, we designed and constructed a new LHPG pulling system which remedied the causes of the problems mentioned above. The new LHPG system is totally enclosed in a chamber which allows regulation and control of the atmosphere and temperature in which the fibers are pulled. In addition to air, the system can now accommodate admixtures of nitrogen, oxygen and hydrogen as well as a partial vacuum. Fibers of LiNbO3 grown in the new system under an oxygen atmosphere, for example, no longer show any coloration. We believe the controlled atmosphere also aids in reducing crystalline flaws.			
14. SUBJECT TERMS			15. NUMBER OF PAGES
			16. PRICE CODE
17. SECURITY CLASSIFICATION OF REPORT UNCLAS	18. SECURITY CLASSIFICATION OF THIS PAGE UNCLAS	19. SECURITY CLASSIFICATION OF ABSTRACT UNCLAS	20. LIMITATION OF ABSTRACT

FINAL REPORT

"GROWTH AND TAILORING OF PHOTOREFRACTIVE FIBERS USING THE LASER HEATED PEDESTAL GROWTH METHOD"

Grant Number: F49620-00-1-0134

Period of Report: September 1, 2001 to August 31, 2002

AFOSR Program Manager: Dr. Charles Lee

Principal Investigator: William M. Yen

Institution: University of Georgia, Department of Physics and Astronomy
Athens, GA 30602

SECTION A: SUMMARY OF PROGRESS

Because of detailed evaluation of the quality of our LHPG fibers by Dr. D. Evans of the AFRL, we were able to pinpoint the cause of the majority of the defects in our Laser Heated Pedestal Growth (LHPG) fibers. The principal defects found in our materials lay in the non-uniformity of the diameter of our fibers and in the fact that the fibers contained cracks and striations, especially the thinner fibers, which adversely affect optical transmission. In addition, the fibers were grown in air and showed a dark coloration which required additional treatment and annealing to render transparent.

The physical imperfections of our fibers arose because of small mechanical instabilities in our LHPG system. These consisted of transmitted vibrations from motors and pumps and from occasional random variations in the pulling speed of the stepping motor drive. The coloration of the fibers was traced to the reduction of Nb^{5+} to Nb^{4+} because the fibers were grown in open air.

In the course of this period of the grant, we designed and constructed a new LHPG pulling system which remedied the causes of the problems mentioned above. The new LHPG system is totally enclosed in a chamber which allows regulation and control of the atmosphere and temperature in which the fibers are pulled. In addition to air, the system can now accommodate admixtures of nitrogen, oxygen and hydrogen as well as a partial vacuum. Fibers of LiNbO_3 grown in the new system under an oxygen atmosphere, for example, no longer show any coloration. We believe the controlled atmosphere also aids in reducing crystalline flaws.

The redesigned mechanical system isolates the pulling mechanisms from the optics as well as from the enclosing chamber. The input Reflexicon mirror and the focusing FIR heating mirror are now locked in an optimized position as are the

feeding and pulling mechanisms. The stepping motors have been replaced with micro steppers capable of pulling and feeding with rates as slow as 50nm/min. Again, using this system, fibers grown show a much improved uniformity of diameter and a noticeable reduction in imperfections and scattering centers. Evaluation at the AFRL showed that the transmissivity of the as-grown fibers increased from 20% to 60-75%; additionally, we have been able to pull thinner fibers than before.

We have been able to routinely control the stoichiometry of the LiNbO_3 fibers produced by changing the lithium content of ceramic starting stock material. We had also developed a method with which to monitor the valence of the Fe ions intentional or unintentionally doped into LNO crystals; by properly controlling the growth atmosphere, we have been able to accurately introduce the proper Fe^{3+} doping level into the LHPG fibers we have delivered. We have also made some trial runs at growing alternative photorefractive materials such as KNbO_3 and $\text{BaSrTi}_2\text{O}_7$; the results have been encouraging and we are in a position to provide samples of these materials should the need arise.

Up to 25 fibers of LNO drawn from our new system have been delivered to various collaborators of this effort. These fibers were as long as 30mm in length and in the vicinity of 100-200 μm in diameter. Variations in diameter were down to 5% or so.

The origin of the noise in the nonlinear photorefractive signals obtained in mixing experiments in LNO had been traced to electric charge build up on the surface of the fiber and bulk materials. We have been able to demonstrate (Basun) that by providing a conducting path to ground, the charge and hence the noise induced through this source can be greatly reduced. These results are being prepared for publication.

We have also continued to pursue the possibilities of providing clad and/or tapered fibers of LNO and other photorefractives for additional possible applications.

SECTION B: PERSONNEL SUPPORTED

1). Principal Investigator:

William M. Yen

2). Post Doctoral Associates

Lizhu Lu

Dongdong Jia, for period June –October, 2002

3). Other Associated Researchers

Sergei Basun

G.F. Imbusch

SECTION C: PUBLICATION AND PRESENTATIONS UNDER AFOSR SUPPORT:

1). Refereed Journal:

D.R. Evans, M.A. Saleh, T.J. Bunning, S. Guha, L.Lu, R.S. Meltzer and W.M. Yen, Contra-direction two beam coupling using a single input beam in an iron lithium niobate fiber, Appl. Opt. (to be published, 2002).

S.A. Basun, D.R. Evans, J.O. Barnes, T.J. Bunning, S. Guha, G. Cook and R.S. Meltzer, Optical Spectroscopy of Fe²⁺ and Fe³⁺ ions in LiNbO₃, J. Appl. Phys. 92 (December issue)

M.M. Chirila, N. Y. Garces, L.E. Halliburton, D.E. Evans, S.A. Basun, R.S. Meltzer, W.M. Yen, S.A. Rutkowski, D. Shumov and J.S. Cahill, Thermoluminescence study of stoichiometric LiNbO₃ crystals, J. Appl. Phys. 92, 1221-26 (2002)

2). Proceedings Volumes:

D.R. Evans, T.P. Pottenger, M.A. Saleh, S.A. Basun, G.R. Landis, T.J. Bunning and S. Guha, Investigation of photorefractive nonlinear optical properties of iron-doped lithium niobate in bulk and fiber configurations, Proc. SPIE 4462, 111-124 (2001)

M.A. Saleh, D.R. Evans, R.N. Shariff, T.P. Pottenger, L. Lu, R.S. Meltzer, W.M. Yen, T.J. Bunning and S. Guha, Contra-directional two-wave mixing in bulk and multimode fibers of iron-doped lithium niobate, Proc SPIE 4459, 71-75 (2001)

3). Conference Presentations:

D.R. Evans, T.J. Bunning, S. Guha, S.A. Basun, R.S. Meltzer, Investigation of thermoluminescence and the pyroelectric effect in LiNbO₃: Fe, APS March Meeting, Indianapolis (2002)

D.R. Evans, J.O. Barnes, T.J. Bunning, S. Guha, S.A. Basun, G. Cook and R.S. Meltzer, Determining concentrations of divalent and trivalent iron in lithium niobate using optical absorption spectroscopy, APS March Meeting, Indianapolis (2002)

D.R. Evans, M.A. Saleh, A.S. Allen, T.P. Pottenger, T.J. Bunning, S. Guha, S.A. Basun and G. Cook, Elimination of a photovoltaic-induced fast instability in photorefractive iron-doped lithium niobate crystals, APS March Meeting, Indianapolis (2002)

D.R. Evans, M.A. Saleh, T.P. Pottenger, T.J. Bunning, S. Guha and S.A. Basun, Eliminating photorefractive grating instabilities during contra-directional two-wave mixing in iron-doped lithium niobate, CLEO, Long Beach (May 2002)

