

REPORT DOCUMENTATION PAGE

Form Approved
OMB No. 0704-0188

Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden to Washington Headquarters Service, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188) Washington, DC 20503.

PLEASE DO NOT RETURN YOUR FORM TO THE ABOVE ADDRESS.

1. REPORT DATE (DD-MM-YYYY) 13-00-2006		2. REPORT DATE Final Technical Report		3. DATES COVERED (From - To) 7/1/05 - 6/30/06	
4. TITLE AND SUBTITLE Stress-Engineered Quantum Dots for Multispectral Infra-Red Detector Arrays				5a. CONTRACT NUMBER F49620-98-1-0474	
				5b. GRANT NUMBER	
				5c. PROGRAM ELEMENT NUMBER	
6. AUTHOR(S) Professors Madhukar, A.; Konkar, A.; Campbell, J. C.; Chang, Y. C.; Wang, W. I.				5d. PROJECT NUMBER	
				5e. TASK NUMBER	
				5f. WORK UNIT NUMBER	
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) University of Southern California Dept. of Materials Science & Engineering 3651 Watt Way, VHE 506 Los Angeles, CA 90089-0241				8. PERFORMING ORGANIZATION REPORT NUMBER	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) AFOSR/NE 875 North Randolph St., Room 3112, Suite 325 Arlington, VA 22203-1768 <i>Dr Gernot Pomrenke/NE</i>				10. SPONSOR/MONITOR'S ACRONYM(S)	
				11. SPONSORING/MONITORING AGENCY REPORT NUMBER	
12. DISTRIBUTION AVAILABILITY STATEMENT Approved for public release; distribution unlimited.				AFRL-SR-AR-TR-07-0069	
13. SUPPLEMENTARY NOTES The view, opinion, and/or findings in this report are those of the author(s) and should not be constructed as an official Department of the Air Force position, policy, or decision, unless so designated by other documentation.					
14. ABSTRACT During the above-noted period of this Final Technical Report, the following salient milestones were reached: (1) Introduced and demonstrated the concept of injecting electrons into the quantum dot (QD) active infra-red absorbing region from bracketing doped contact layers (to suppress unwanted dark current) leaving the QD region undoped; (2) Introduced and demonstrated the benefits of the concepts of (a) strain-relieving QD capping layers, (b) current blocking layers, and (c) lateral potential confinement layer for tailoring the QD electronic response to the desired IR response; (3) Demonstrated high performance QDIP devices in the mid and longwavelength IR regions; (4) Demonstrated voltage-tunable mid and long IR dual wavelength QDIPs.					
15. SUBJECT TERMS Quantum dots, semiconductors, InAs, GaAs, molecular beam epitaxy, growth, infra-red detectors, PL, AFM, TEM, cathodoluminescence, photocurrent, noise, responsivity, detectivity, resonant cavity, Bragg mirrors, design and modelling mirrors..					
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT UU	18. NUMBER OF PAGES 8	19a. NAME OF RESPONSIBLE PERSON Anupam Madhukar
a. REPORT Unclassified	b. ABSTRACT Unclassified	c. THIS PAGE Unclassified			19b. TELEPHONE NUMBER (Include area code) 213.740.4323

Final Technical Report

July 01, 1998 - June 30, 2006

Stress-Engineered Quantum Dots for Multispectral Infra-red Detector Arrays

AFOSR Contract No. F49620-98-1-0474

Submitted to

Dr. Gernot Pomrenke
Physics and Electronics Directorate
Air Force Office of Scientific Research
875 North Randolph Street, Room 3112, Suite 325
Arlington, VA 22203-1768

Submitted by

Anupam Madhukar
Principal Investigator
University of Southern California
Los Angeles, CA 90089-0241

This final technical report summarizes the salient accomplishments of the work on self-assembled quantum dot synthesis, tailoring of their electronic properties, and the exploitation of such properties for realization of high performance quantum dot infrared photodetectors (QDIPs) carried under the above noted contract during the period July 1, 1998, through June 30, 2006.

Table of Contents


I. Preamble and Objectives	1
II. Summary of Salient Accomplishments	1
III. List of Publications	3
IV. List of Personnel	6

I. Preamble and Objectives

This Final Technical Report on AFOSR grant number F49620-98-1-0474 summarizes the major accomplishments of the multi-investigator team led by A. Madhukar as the PI and comprising Co-PIs J. C. Campbell (Univ. of Texas, Austin), W. Wang (Columbia University), Y. C. Chang (Univ. of Illinois, Champaign-Urbana), and D. H. Rich (USC, 1998-2003) for the period July 1, 1998 to June 30, 2004, and reduced to A. Madhukar and J. C. Campbell (at the University of Virginia since Jan 1, 2006) from July 1, 2004 until June 30, 2006. Briefly, the overall objectives of this program were:

- (1) Explore epitaxial island semiconductor quantum dot, [also dubbed self-assembled quantum dot (SAQD)] science and the concept of stress engineering, and
- (2) Examine and assess the potential of such stress-engineered quantum dots (QDs) as active regions of infra-red photodetector arrays (QDIPs).

A pictorial representation of the aimed - for QDIP array is shown below. The salient accomplishments are summarized in Section II. This is followed by the List of Publications in Section III and the List of Personnel supported by this grant in Section IV.



Schematic of SAQD-based infrared photodetectors for the 1-12 μ m range.

II. Summary of Salient Accomplishments

(A) Quantum dot growth, structure, and optical property related:

1. Successfully grew GaAs, InGaAs and InAlGaAs capped InAs on GaAs(001) QDs up to ten layer stacking which show low structural defect (threading dislocation, stacking fault) density and correspondingly high PL efficiency and narrow PL linewidth [publications 1, 15, 17, 18, 21-24].

2. Introduced QDIP structures synthesized using migration enhanced epitaxy based capping of InAs quantum dots at very low ($\sim 350^\circ\text{C}$ or less) temperatures to minimize compositional mixing [publications 15, 16].
3. Introduced undoped quantum dot region based QDIP structures with electron injection from n-doped contact layers and, using PL/PLE and photocurrent optical spectroscopy, demonstrated that the electron ground states of the InAs/GaAs(001) QDs in such n-i-n photodetector structures are partially occupied indeed [publications 15, 16].
4. Introduced and exploited the notion of quantum dots buried in compositionally graded capping layers to manipulate the chemical band edge discontinuities and strain distribution to tailor the intraband electronic states [publications 21-24]. (This approach has subsequently been dubbed “quantum dots in-a-well”)
5. Demonstrated *selective tailoring* of the QD electronic energy levels and wave function through introduction of the idea of placing a lateral potential confinement layer (LPCL) at different heights of islands in the InAs/ $\text{In}_{0.15}\text{Ga}_{0.85}\text{As}$ QD system during capping of the InAs islands [publication 22].
6. Demonstrated unimodal intraband infrared photoresponse at 8-9 μm using InGaAs capped 2 ML InAs/GaAs(001) QDs in n-i(QDs)-n QDIP structure [publication 21, 23].
7. Demonstrated voltage-tunable QDIP structures with photocurrent response in the mid (3-6 μm) and long (8-12 μm) wavelength IR regimes [publication 24].
8. Demonstrated dual (mid and long IR) wavelength QD photoluminescence utilizing our previously introduced notion of VDA (variable deposition amount) stacking of differing average size QDs and utilizing the lateral potential confinement layer (LPCL). [unpublished]
9. Demonstrated for the first time the existence and orientation of intraband transition induced dipole moment in self-assembled InAs/GaAs(001) QDs. Simultaneously, the interband dipole moment is also determined [publication 25].
10. Observed temperature-dependence of intraband transition induced dipole moment in self-assembled InAs/GaAs(001) QDs [unpublished].
11. Utilized cathodoluminescence wavelength imaging (CLWI) technique to obtain SAQD images on the meso scale and found a higher-degree of uniformity for domains of the InGaAs capped InAs/GaAs(001) QDs than that of GaAs capped InAs/GaAs(001) QDs [publications 8, 11].
12. Studied the substrate orientation dependence of the formation of InSb quantum dots on on-axis and off-axis GaSb and AlGaSb [unpublished].

(B) Theory

1. Developed a state-of-the-art theoretical modeling code for SAQDs that includes InAs/GaAs SAQDs with different orientations. Have studied the detailed geometric dependence of electronic structures of SAQDs and the predicted optical

- properties are consistent with the experimental findings noted above [publication 10].
2. Modeled dark and tunneling currents in quantum dot arrays [publications 7, 17, 20].

(C) Infrared detector device related:

1. Introduced QDIP device structures with undoped quantum dot region to minimize dark current [publications 15, 16].
2. Demonstrated unimodal intraband infrared photoresponse at 8-9 μm using InGaAs capped 2 ML InAs/GaAs(001) QDs in n-i(QDs)-n QDIP structure [publication 21, 23].
3. Demonstrated the first two-color, voltage tunable, QDIP photoresponse. Using InGaAs capped 2.5 ML InAs/GaAs(001) QDs in n-i(QDs)-n QDIP structure, photoresponse at $\sim 5.5 \mu\text{m}$ and $\sim 9 \mu\text{m}$ is demonstrated [publications 24, 26].
4. Demonstrated QDIP devices with high detectivities at normal incidence. For InAs/GaAs QDIPs with AlGaAs blocking layers have achieved $D^* = 1 \times 10^{10} \text{ cmHz}^{1/2}/\text{W}$, $R = 14 \text{ mA/W}$ at -0.7V bias and 77K [publications 27, 28].
5. Demonstrated unimodal QDIP devices with high responsivity of 22 mA/W and detectivity of $3.2 \times 10^9 \text{ cmHz}^{1/2}/\text{W}$ at 77K and $8.3 \mu\text{m}$ [publications 29, 30].
6. Demonstrated voltage tunable, multi-spectral response utilizing QDIP devices with 2.5ML InAs QDs with InGaAs cap layers and showed mid- and far-infrared detection with detectivities of $5.8 \times 10^9 \text{ cmHz}^{1/2}/\text{W}$ and $7.3 \times 10^8 \text{ cmHz}^{1/2}/\text{W}$ at $5.9 \mu\text{m}$ and $8.9 \mu\text{m}$, respectively, at 77K publications [publication 31].
7. Demonstrated a two-color, voltage tunable intraband photoresponse of QDIP structures based on variable-deposition-amount stacking of InAs QDs [unpublished].
8. Examined the impact of current blocking AlGaAs layers in the InGaAs capped 2ML InAs QDIPs and found equal reduction in dark and photocurrents, thereby leaving the detectivity comparable to that obtained without the use of the current blocking layers [publication 27].
9. Demonstrated dual wavelength response at $\sim 5 \mu\text{m}$ and $\sim 9.5 \mu\text{m}$ in QDIPs containing a lateral potential confinement InAlGaAs layer in the capping layer [unpublished].
10. Calculated reflectivity and electric field distribution of mid infrared microcavities defined by Ge/SiO₂ and Au or GaAs/air and Au mirrors [unpublished].

III. List of Publications

1. I. Mukhametzhanov, R. Heitz, and A. Madhukar, "Punctuated Island Growth: An Approach to Examination and Control of Quantum Dot Density, Size, and Shape Evolution," *App. Phys. Lett.* **75**, 85 (1999).

2. R. Heitz, I. Mukhametzhanov, O. Steier, A. Madhukar, and D. Bimberg, "Enhanced Polar Exciton-Phonon Interaction in Self-Organized InAs/GaAs Quantum Dots," *Phys. Rev. Lett.* **83**, 4654 (1999).
3. R. Heitz, I. Mukhametzhanov, O. Steier, A. Madhukar, and D. Bimberg, "Exciton-Phonon Interaction in Self-Organized InAs/GaAs Quantum Dots," *Proceedings of the MSS-9 Conf.*, July 1999 (Fukuoka, Japan).
4. D. M.-T. Kuo and Y. C. Chang, "Dynamic behavior of electron tunneling in quantum well systems under electric field," *Phys. Rev. B* **60**, 15957 (1999).
5. D. M.-T. Kuo, G. Setlur, and Y. C. Chang, "Optical conductivity and Raman spectra of coupled electron-phonon systems via bosonic algebra," *Phys. Rev. B* **61**, 290 (2000).
6. D. M.-T. Kuo and Y.-C. Chang, "Inter-subband electro-absorption spectra of semiconductor quantum wells," *J. Appl. Phys.* **87**, 2936 (2000).
7. D. M.-T. Kuo and Y. C. Chang, "Electron Tunneling rate in quantum dots under uniform electric field," *Phys. Rev. B* **61**, 11051 (2000).
8. D.H. Rich, C. Zhang, I. Mukhametzhanov, and A. Madhukar, "Cathodoluminescence wavelength imaging of micron scale energy variations in InAs/GaAs self-assembled quantum dots," *Appl. Phys. Lett.* **76**, 3597 (2000).
9. M.L. Seaford, D.H. Tomich, K.G. Eyink, L. Grazulis, K. Mahalingham, Z. Yang, and W.I. Wang, "Comparison of GaAs grown on standard Si(511) and compliant SOI(511)," *J. Electron. Material* **29**, 606 (2000).
10. S. J. Sun and Y. C. Chang, "Modeling self-assembled quantum dots by effective bond-orbital method," *Phys. Rev. B* **62**, 13631 (2000).
11. D.H. Rich, C. Zhang, I. Mukhametzhanov, and A. Madhukar, "Cathodoluminescence wavelength imaging study of clustering in InAs/GaAs self-assembled quantum dots," *Mater. Res. Soc. Proc.* vol. **618** (2000).
12. R. Heitz, O. Stier, I. Mukhametzhanov, A. Madhukar, D. Bimberg, "Quantum-size effect in self-organized InAs/GaAs quantum dots," *Phys. Rev. B* **62**, 11017 (2000).
13. R. Heitz, F. Guffarth, I. Mukhametzhanov, M. Grundmann, A. Madhukar, D. Bimberg, "Manybody effects on the optical spectra of InAs/GaAs quantum dots," *Phys. Rev. B* **62**, 16881 (2000).
14. R. Heitz, H. Born, I. Mukhametzhanov, A. Hoffman, A. Madhukar, D. Bimberg, "Resonant Raman scattering in self-organized InAs/GaAs quantum dots," *Appl. Phys. Lett.* **77**, 3746 (2000).
15. Z.H. Chen, O. Baklenov, E.T. Kim, I. Mukhametzhanov, J. Tie, A. Madhukar, Z. Ye, and J. Campbell, "InAs/Al_xGa_{1-x}As quantum dot infrared photodetectors with undoped active region," *Infrared Phys. & Tech.* **42**, 479 (2001).
16. Z. H. Chen, O. Baklenov, E. T. Kim, I. Mukhametzhanov, J. Tie, A. Madhukar, Z. Ye, and J. C. Campbell, "Normal incidence InAs/Al_xGa_{1-x}As quantum dot infrared photodetectors with undoped active regions," *J. Appl. Phys.* **89**, 4558 (2001).
17. D. M.-T. Kuo, A. Fang, and Y. C. Chang, "Theoretical modeling of dark current and photo-response for quantum well and quantum dot infrared detectors," *Infrared Phys. & Tech.*, **42**, 433 (2001).
18. I. Mukhametzhanov, Z.H. Chen, O. Baklenov, E.T. Kim, and A. Madhukar, "Optical and Photocurrent Spectroscopy Studies of Inter- and Intra-Band Transitions in Size-Tailored InAs/GaAs Quantum Dots," *Phys. Stat. Sol. (b)* **224**, 697 (2001).

19. L. Li, S. J. Sun, and Y. C. Chang, "Systematic study of $\text{Ga}_{1-x}\text{In}_x\text{As}$ self-assembled quantum wires with varying interfacial strain relaxation," *J. Appl. Phys.* **89**, 2251 (2001).
20. David M.-T. Kuo, K. Y. Guo and Y. C. Chang, "Tunneling current in quantum dots arrays," *Appl. Phys. Lett.* **79**, 3851 (2001).
21. E.T. Kim, Z.H. Chen, and A. Madhukar, "Tailoring Detection Bands of InAs Quantum-Dot Infrared Photodetectors Using $\text{In}_x\text{Ga}_{1-x}\text{As}$ Strain-Relieving Quantum Wells," *Appl. Phys. Lett.* **79**, 3341 (2001).
22. E.T. Kim, Z.H. Chen, and A. Madhukar, "Selective Manipulation of InAs QD Electronic States Using a Lateral Potential Confinement Layer," *Appl. Phys. Lett.* **81**, 3473 (2002).
23. Z.H. Chen, E.T. Kim, and A. Madhukar, "Intraband and Interband Photocurrent Spectroscopy of InAs/GaAs(001) Quantum Dots in n-i(QDs)-n Photodetector Structures," *J. Vac. Sci. Technol.* **B20**, 1243 (2002).
24. E.T. Kim, Z.H. Chen, and A. Madhukar, "Tuning Mid- and Long-Wavelength InAs Quantum-Dot Infrared Photodetectors Using $\text{In}_x\text{Ga}_{1-x}\text{As}$ Capping Layers," *J. Vac. Sci. Technol.* **B20**, 1188 (2002).
25. Z.H. Chen, E.T. Kim, and A. Madhukar, "Intraband-Transition-Induced Dipoles in Self-Assembled InAs/GaAs(001) Quantum Dots," *Appl. Phys. Lett.* **80**, 2770 (2002).
26. Z.H. Chen, E.T. Kim, and A. Madhukar, "Normal-Incidence Voltage Tunable Middle and Long Wavelength Infrared Photoresponse in Self-Assembled InAs Quantum Dots," *Appl. Phys. Lett.* **80**, 2490 (2002).
27. Z. Ye, J. Campbell, Z.H. Chen, O. Baklenov, E.T. Kim, I. Mukhametzhanov, J. Tie, and A. Madhukar, "High Performance InAs/GaAs Quantum Dots Infrared Photodetector with/without $\text{Al}_{0.20}\text{Ga}_{0.80}\text{As}$ Blocking Layers," MRS (Material Research Society) Symposium Proceeding, vol.**692**, H9.17.1 (2002).
28. Zhengmao Ye, J. C. Campbell, Z. Chen, E.-T. Kim, and A. Madhukar, "Normal-incidence InAs self-assembled quantum-dot infrared photodetectors with high detectivity," *IEEE J. Quantum Electron.* **38**, 1234 (2002).
29. Zhengmao Ye, J. C. Campbell, Zhonghui Chen, E. T. Kim, and A. Madhukar, "Quantum dot infrared photodetectors," *Proc. SPIE* 4656, 16 (2002).
30. Zhengmao Ye, Joe C. Campbell, Zhonghui Chen, Eui-Tae Kim, and Anupam Madhukar, "InAs quantum dot infrared photodetectors with $\text{In}_{0.15}\text{Ga}_{0.85}\text{As}$ strain-relief cap layers," *J. Appl. Phys.* **92**, 7462 (2002).
31. Zhengmao Ye, Joe C. Campbell, Zhonghui Chen, Eui-Tae Kim, and Anupam Madhukar, "Voltage-controllable multi-wavelength InAs quantum-dot infrared photodetectors for mid- and far-infrared detection," *J. Appl. Phys.* **92**, 4141 (2002).
32. D. M.-T. Kuo and Y. C. Chang, "Tunneling current through a quantum dot with strong electron-phonon interaction," *Phys. Rev.* **B 66**, 085311 (2002).
33. W. Y. Ruan and Y. C. Chang, "Stability of ion-bound excitons in two dimensions," *Phys. Rev.* **B 66**, 115314 (2002).

34. W. Y. Ruan and Y. C. Chang, "Decaying rates of N-electron quasi-bound states in a double-barrier quantum dot under electric and magnetic fields," *Phys. Rev. B* **66**, 155311 (2002).
35. A. Madhukar, "Strain-Engineered Quantum Dots: Nature's Way" in *Nano-optoelectronics*, Edited by M. Grundmann (Springer Verlag, 2002) pp. 23–63.
36. N. Kouklin, H. Chik, J. Liang, M. Tzolov, J. M. Xu, J. B. Heroux, and W. I. Wang, "Highly periodic, three-dimensionally arranged InGaAsN: Sb quantum dot arrays fabricated nonlithographically for optical devices," *J. Phys. D: Appl. Phys.* **36**, 2634, (2003).
37. L. Li, S.J. Sun, and Y.C. Chang, "Optical properties of self-assembled quantum wires for application in infra-red detection," *Infrared Phys. Tech.* **44**, 57 (2003).
38. David M.T. Kuo and Y.C. Chang, "Effects of Coulomb blockade on the photocurrent in quantum dot infrared photodetectors," *Phys. Rev. B* **67**, 035313 (2003).
39. Y.C. Chang, D.M.T. Kuo, "Effects of electron correlation on the photocurrent in quantum dot infrared photodetectors," *Appl. Phys. Lett.* **83**, 156 (2003).
40. Z. Ye, Joe C. Campbell, Z. Chen, E.T. Kim, and A. Madhukar, "Noise and photoconductive gain in InAs quantum dot infrared photodetectors," *Appl. Phys. Lett.* **83**, 1234-1236 (2003).
41. E. T. Kim, A. Madhukar, Z. Ye, and J. C. Campbell, "High detectivity InAs quantum dot infrared photodetectors," *App. Phys. Letts.* **84**, 3277 (2004)
42. A. Madhukar, J. C. Campbell, E.T. Kim, Z. Ye, and Z.H. Chen, "Quantum dot infrared photodetectors," Ch.3 in "Semiconductor Nanostructures for Optoelectronic Applications", Editor T. Steiner, (Artech House Publishers) 2004.

IV. List of Personnel

The following individuals were supported partially or fully by the present grant.

Faculty:

Anupam Madhukar (USC), D. H. Rich (USC), Zhonghui Chen (USC), Atul Konkar (USC), Joe Campbell (UT), Y.C. Chang (UIUC), Wen Wang (CU)

Graduate Students:

E. T. Kim (USC), M. Ho (USC), Y. Zhang (USC), T. Asano (USC), Z. Ye (UT), M. Ho (UT), S.J. Sun (UIUC), A. Fang (UIUC), Z. Yang (CU), X. Yang (CU), C. Pei (CU).

Post Docs:

E.T. Kim (USC), D.M.T. Kuo (UIUC), W. Y. Ruan (UIUC), S. Xin (CU), J. Heroux (CU)