

# Large Resonant Third-order Optical Nonlinearity of CdSe Nanocrystal Quantum Dots

JaeTae Seo<sup>1</sup>, SeongMin Ma<sup>1</sup>, Qiguang Yang<sup>1</sup>, Linwood Creekmore<sup>1</sup>, Russell Battle<sup>1</sup>, Herbert Brown<sup>1</sup>, Ashley Jackson<sup>1</sup>, Tifney Skyles<sup>1</sup>, Bagher Tabibi<sup>1</sup>, William Yu<sup>2</sup>, SungSoo Jung<sup>3</sup>, and Min Namkung<sup>4</sup>

<sup>1</sup> Department of Physics, Hampton University, Hampton, VA, 23668, U.S.A

<sup>2</sup> Department of Chemistry, Rice University, Houston, Texas 77005, USA

<sup>3</sup> Korea Research Institute of Standards and Science, Daejeon, South Korea, 305-600

<sup>4</sup> Astrochemistry Branch, NASA Goddard Space Flight Center, Greenbelt, MD, 20771, USA

Email: jaetae.seo@hamptonu.edu

**Abstract.** Resonant third-order nonlinear optical susceptibility and hyperpolarizability of CdSe nanocrystal quantum dots were revealed to be  $\sim 2.6 \times 10^{-20} - 2.7 \times 10^{-19} \text{ m}^2/\text{V}^2$  and  $\sim 2.2 \times 10^{-40} \text{ m}^5/\text{V}^2$  by using nanosecond degenerate four-wave mixing at 532 nm. The large nonlinearity of the CdSe nanocrystals is attributed to the resonant excitation and multiple nonlinear optical processes.

## 1. Introduction

Colloidal semiconductor nanocrystals have drawn significant attention because of their distinct roles in technical applications, which include their application as a laser power limiter, saturable absorber, optical switch, spacecraft crack indicator, gas sensor, biological labeling, light-emitting diodes, and solar cells. Strong blue-shift of optical bandgap with wide tunability and quantum confinement of electrons in the colloidal quantum dot boundary modifies the optical properties of semiconductor nanocrystals, including nonlinear optical susceptibility and hyperpolarizability. It allows us to customize them according to required applications. In recent years, colloidal semiconductor nanocrystals have attracted great interest for their large nonlinear optical properties with wide bandgap tunability, which differ remarkably from bulk crystals.

Both resonant and non-resonant optical nonlinearity of various materials have been investigated for many years. The processes leading to non-resonant nonlinearity are usually in relatively fast time scales, which are good candidates for optical switching and nonlinear transmission limiting applications. On the other hand, the processes causing resonant nonlinearity are usually in relatively slow time scales, which results in huge optical nonlinearity. Resonant nonlinear optical materials are widely utilized for Q-switching using a negative nonlinear absorption property, and for nonlinear transmission limiting using a positive nonlinear absorption property as well as a nonlinear refraction property or nonlinear phase changes. We discuss the basic understanding of reverse saturable absorption or positive nonlinearity with resonance excitation, considering a multi-level system interacting with the optical field in semiconductor nanocrystals. The process of absorption in a multi-level system is as follows: Absorption of the incident field promotes electrons to the first or higher

## Report Documentation Page

*Form Approved  
OMB No. 0704-0188*

Public reporting burden for the collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to a penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number.

1. REPORT DATE <b>2006</b>	2. REPORT TYPE <b>N/A</b>	3. DATES COVERED <b>-</b>			
4. TITLE AND SUBTITLE <b>Large Resonant Third-order Optical Nonlinearity of CdSe Nanocrystal Quantum Dots</b>		5a. CONTRACT NUMBER			
		5b. GRANT NUMBER			
		5c. PROGRAM ELEMENT NUMBER			
6. AUTHOR(S)		5d. PROJECT NUMBER			
		5e. TASK NUMBER			
		5f. WORK UNIT NUMBER			
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) <b>Department of Physics, Hampton University, Hampton, VA, 23668</b>		8. PERFORMING ORGANIZATION REPORT NUMBER			
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)		10. SPONSOR/MONITOR'S ACRONYM(S)			
		11. SPONSOR/MONITOR'S REPORT NUMBER(S)			
12. DISTRIBUTION/AVAILABILITY STATEMENT <b>Approved for public release, distribution unlimited</b>					
13. SUPPLEMENTARY NOTES <b>THE SEVENTH INTERNATIONAL CONFERENCE ON NEW PHENOMENA IN MESOSCOPIC STRUCTURES &amp; THE FIFTH INTERNATIONAL CONFERENCE ON SURFACES AND INTERFACES OF MESOSCOPIC DEVICES 27 November2 December 2005, Maui, Hawaii, USA</b>					
14. ABSTRACT					
15. SUBJECT TERMS					
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT <b>SAR</b>	18. NUMBER OF PAGES <b>4</b>	19a. NAME OF RESPONSIBLE PERSON
a. REPORT <b>unclassified</b>	b. ABSTRACT <b>unclassified</b>	c. THIS PAGE <b>unclassified</b>			

excited state dependent upon excitation wavelength. From the excited state the electrons can rapidly make a transition to an intermediate state by a non-radiative transition. Before the electrons are completely relaxed to the ground state, they may experience absorption that promotes them to a higher energy state. This process is called two-step absorption. When the absorption cross-section of the excited state is larger than that of the ground state, then the system will exhibit reverse saturable absorption phenomena or positive nonlinear absorption. Of course, it is saturable absorption if the cross-section of the excited state is smaller than that of the ground state.

In this paper, we present the resonant nonlinear optical properties of CdSe nanocrystals using degenerate four-wave mixing (DFWM) by a nanosecond laser pulse at 532 nm (Continuum, Powerlite, Nd:YAG laser, 8 ns, 10Hz).

## 2. Linear Optical Properties

The typical linear absorption spectra of TOPO- passivated CdSe in toluene are shown in figure 1. The absorption spectra of semiconductor nanocrystals with sizes near the exciton Bohr radius clearly exhibit discrete features because of transitions coupling electron and hole quantized states. The semiconductor nanocrystals also exhibit a strong blue-shift of bandgap energy because of their quantum confinement. The average diameter of CdSe nanocrystals was  $\sim 3.5$  nm. Exciton absorption peaks of CdSe nanocrystals were  $\sim 565$ , 537, 469 and 405 nm. Absorption coefficients ( $\alpha = 2.3A/d$ ,  $d = 1$  cm) at 532 nm were 3.5, 1.5, 0.76, and  $0.35$   $\text{cm}^{-1}$  for different concentrations, where the value of absorbance  $A$  is given in the figure 1 and  $d$  is the sample length.




Fig. 1. Absorption spectra of CdSe nanocrystals in toluene. Average diameter of CdSe nanocrystals was  $\sim 3.5$  nm, Exciton absorption peaks were  $\sim 565$ , 537, 469 and 405 nm.

The linear refractive index of CdSe nanocrystals was calculated to be  $\sim 2.34$  for  $\sim 3.5$  nm average diameter [1]

$$n_{CdSe} = \sqrt{1 + \frac{(\epsilon_{bulk} - 1)}{1 + \left(\frac{0.75}{D}\right)^{1.2}}}, \quad (1)$$

where,  $\epsilon_{bulk} \sim 6.2$  is the dielectric constant of bulk CdSe, and  $D$  is the average diameter of CdSe quantum dots in nm.

## 3. Nonlinear Optical Properties

Figure 2 shows logarithmic plots of the DFWM signal from CdSe nanocrystals with resonance excitation of 532 nm and 8-ns temporal pulse width as function of total pump intensity at around zero delay. The DFWM signal near the zero delay was observed to be  $I^{2.9 \sim 3.1}$ , which indicates the dominance of the third-order nonlinearity at the irradiances near and less than  $100$   $\text{MW}/\text{cm}^2$ .

The third-order nonlinear susceptibilities of samples (CdSe dots in toluene or toluene itself) were estimated using the following equation by comparison of the FWM signal beams of samples with that of CS<sub>2</sub> measured under identical conditions [2]

$$\chi_S^{(3)} = \sqrt{\frac{I_S}{I_R}} \left( \frac{n_S}{n_R} \right)^2 \left( \frac{L_R}{L_S} \right) \left( \frac{\alpha L}{e^{-\alpha L/2} (1 - e^{-\alpha L})} \right) \chi_R^{(3)} \quad (2)$$

where  $I$  is the intensity of the FWM signal beam,  $n$  is the refractive index ( $n_s(\text{CdSe})$ ): given by equation (1),  $n_R(\text{CS}_2) \sim 1.63$  [3]),  $L$  ( $L_S = L_R = 1 \text{ mm}$ ) is the sample path length in DFWM,  $\alpha$  is the linear absorption coefficient ( $\text{cm}^{-1}$ ) of the sample at 532 nm, and  $S$  and  $R$  indicate sample and reference. The excellent and stable third-order optical response solvent, carbon disulfide (CS<sub>2</sub>, 99+ %, spectrophotometric grade, Aldrich), was selected as a reference. It has been assumed that the reference has no linear absorption at the excitation wavelength at 532 nm. The absorption length of CdSe in toluene for the DFWM experiment was  $\alpha L \sim 0.35, 0.15, 0.076, \text{ and } 0.035 \ll 1$  for each of the four different concentrations as listed in the figure 1. Therefore, equation (2) is appropriate to calculate the third-order nonlinearity for the Kerr-like medium.




Fig. 2. Logarithmic plot of the DFWM signal in CdSe nanocrystals at 532 nm as function of total pump intensity at around zero delay. The solid line is a best fit to the data, giving an  $I^{2.9-3.1}$  dependence.

The total third-order nonlinear susceptibility of the dilute sample of dots in a matrix (dot volume fraction  $\ll 1$ ) is  $\chi_{tot}^{(3)} = \chi_{dot\_eff}^{(3)} + \chi_{toluene}^{(3)}$ , where,  $\chi_{tot}^{(3)}$  and  $\chi_{toluene}^{(3)}$  are the third-order nonlinear susceptibilities of the sample (dots in matrix) and toluene, and  $\chi_{dot\_eff}^{(3)}$  is the effective third-order nonlinear susceptibility of CdSe quantum dots. The effective third-order nonlinear susceptibility  $\chi_{dot\_eff}^{(3)}$  includes the dielectric effect of nanocrystals and toluene. The third-order susceptibility of pure toluene was measured to be  $\sim 1.6 \times 10^{-21} \text{ m}^2/\text{V}^2$  ( $1.1 \times 10^{-13} \text{ esu}$ ) comparing with the reference sample CS<sub>2</sub>. The third order nonlinear susceptibility and the linear refractive index of CS<sub>2</sub> were reported to be  $\sim 9.5 \times 10^{-21} \text{ m}^2/\text{V}^2$  ( $\sim 6.8 \times 10^{-13} \text{ esu}$ ) and  $\sim 1.63$  at 532 nm in nanosecond time-scale [4]. Therefore, the effective third-order nonlinear susceptibilities of semiconductor nanocrystals were  $\sim 2.6 \times 10^{-20} - 2.7 \times 10^{-19} \text{ m}^2/\text{V}^2$  ( $\sim 1.9 \times 10^{-12} - 1.9 \times 10^{-11} \text{ esu}$ ) for various concentrations of quantum dots  $1.2 \times 10^{-6} - 9.9 \times 10^{-3} \text{ mol/m}^3$  in toluene.

The effective third-order nonlinear susceptibility of the CdSe nanocrystals is correlated with the dot concentration and the effect of the dielectric confinement [5]

$$\chi_{dot\_eff}^{(3)} = f^4 N_a \gamma^h C \quad (SI), \quad (3)$$

where  $f = \frac{3n_{toluene}^2}{n_{dot}^2 + 2n_{toluene}^2}$  is the local field factor,  $n$  is the refractive index ( $n_{dot} = n_s$ ; given by equation (1),  $n_{toluene} \sim 1.5$  [2]),  $N_a$  is Avogadro's number, and  $C$  is the concentration of CdSe quantum dots. The

second-order hyperpolarizability ( $\gamma^h$ ) of CdSe nanocrystals were extrapolated from the slope ( $f^4 N_a \gamma^h$ ) of the third-order nonlinear susceptibility as a function of the concentration plot as shown in figure 3. The hyperpolarizability of CdSe nanocrystals was estimated to be  $\sim 2.2 \times 10^{-40} \text{ m}^5/\text{V}^2$  ( $\sim 1.6 \times 10^{-26}$  esu). The unit conversion between  $\chi^{(3)}$  and  $\gamma^h$  was made based on the following relationships [6]:

$$\chi^{(3)} \left[ \frac{\text{m}^2}{\text{V}^2}, \text{SI} \right] = \frac{4\pi \times 10^{-8}}{9} \chi^{(3)} [\text{esu}], \text{ and } \gamma^h \left[ \frac{\text{m}^5}{\text{V}^2}, \text{SI} \right] = \frac{4\pi \times 10^{-14}}{9} \gamma^h [\text{esu}]. \quad (4)$$




Fig. 3. Third-order nonlinear susceptibility as a function of the concentration of CdSe nanocrystals. The slope of linear fitting revealed the hyperpolarizability of CdSe nanocrystals.

The large nonlinearity of CdSe nanocrystals comes from the resonance excitation at 532 nm. It is well known that resonant excitation enhances the third-order nonlinearity significantly since many processes, such as electronic processes, nuclear processes, and even thermal processes, may contribute to the optical nonlinearity significantly. The possible thermal effect under long pulse laser irradiation is a disadvantage for photonic device applications. We are currently measuring the different components of the third-order nonlinear susceptibility tensor using polarization-resolved as well as time-resolved four-wave mixing techniques, which will help to identify the physical mechanism of the optical nonlinearity of the CdSe nanocrystals in resonant wavelength range.

This work at Hampton University was supported by Army Research Laboratory (DAAD17-02-C-0107), Army Research Office (DAAD19-03-1-0011, W911NF-04-1-0393), National Science Foundation (EEC-0532472, HRD-0400041, PHY0139048), and Department of Energy (DE-FG02-97ER41035).

## References

- [1] L. W. Wang and A. Zunger, "Pseudopotential calculations of nanoscale CdSe quantum dots," *Phys. Rev. B*, **53**, 9579 (1996).
- [2] R. L. Sutherland, *Handbook of Nonlinear Optics*, Marcel Dekker, Inc., 1996, page 390 ( $\chi^{(3)}$ ), page 457-458 (refractive index).
- [3] B. Illine, K. Evain, and M. L. Guennec, "A way to compare experimental and SCRF electronic static dipole polarizability of pure liquids", *J. Mol. Struct. (Theochem)* **630**, 1 (2003).
- [4] P. Wang, H. Ming, J. Xie, W. Zhang, X. Gao, Z. Xu, and X. Wei, "Substituents effect on the nonlinear optical properties of C60 derivatives," *Opt. Comm.* **192**, 387 (2001).
- [5] B. Yu, C. Zhu, and F. Gan, "Optical Nonlinearity of  $\text{Bi}_2\text{O}_3$  nanoparticles studied by Z-scan technique," *J. Appl. Phys.* **82**(9), 4532 (1997).
- [6] X. Zhan, Y. Liu, D. Zhu, X. Liu, G. Xu, and P. Ye, "Large third-order nonlinear optical response of a conjugated copolymer consisting of 2,5-diethylthiophene and carbzole units," *Chem Phys Lett.* **343**, 493 (2001).