



TECHNOLOGY DRIVEN. WARFIGHTER FOCUSED.

Land Vehicle Tire Qualification

March 25, 2009

Report Documentation Page			Form Approved OMB No. 0704-0188		
Public reporting burden for the collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to a penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number.					
1. REPORT DATE 25 MAR 2009		2. REPORT TYPE N/A		3. DATES COVERED -	
4. TITLE AND SUBTITLE Land Vehicle Tire Qualification				5a. CONTRACT NUMBER	
				5b. GRANT NUMBER	
				5c. PROGRAM ELEMENT NUMBER	
6. AUTHOR(S) Richard Vinkovich				5d. PROJECT NUMBER	
				5e. TASK NUMBER	
				5f. WORK UNIT NUMBER	
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) US Army RDECOM-TARDEC 6501 E 11 Mile Rd Warren, MI 48397-5000				8. PERFORMING ORGANIZATION REPORT NUMBER 19662RC	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)				10. SPONSOR/MONITOR'S ACRONYM(S) TACOM/TARDEC	
				11. SPONSOR/MONITOR'S REPORT NUMBER(S) 19662RC	
12. DISTRIBUTION/AVAILABILITY STATEMENT Approved for public release, distribution unlimited					
13. SUPPLEMENTARY NOTES Presented at the Defense Supply Center Columbus Land Tires Privatization Contract Annual Tire Manufacturer Conference, 24-26 March 2009, Renaissance Concourse Hotel, Atlanta, GA, USA, The original document contains color images.					
14. ABSTRACT					
15. SUBJECT TERMS					
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT SAR	18. NUMBER OF PAGES 38	19a. NAME OF RESPONSIBLE PERSON
a. REPORT unclassified	b. ABSTRACT unclassified	c. THIS PAGE unclassified			



LAND VEHICLE TIRE QUALIFICATION



- Qualification for Land Vehicle Tires for Tire Privatization Initiative (TPI) Contract
- Classifications
 - SAE J2014 / Manufacturer's Approved Part No.
 - Cooperative Approved Tire List (CATL)
 - Product Description (ZZ-T-391, ZZ-T-410, ZZ-T-1619)
- Qualification Process Dependent upon Classification
- Vehicle qualification testing inherently qualifies OEM tire for that vehicle system
- Replacement tires qualified via testing requirements per classification

SAE J2014 / Manufacturer's Approved Part No. Tire Qualification Process

- Need or interest established for additional tire source for vehicle system*
- Testing criteria defined based on vehicle performance requirements (Vehicle Mission Profile, Military Requirements, etc.)*
- Testing funded by tire manufacturer unless Govt. determines critical need for second source*
- SAE J2014 test costs prohibitive (est. \$1M - \$2M)*
- Upon successful completion of testing/PM approval, tire P/N added to specific NSN*

SAE J2014:

- Society of Automotive Engineers' specification
- Pneumatic Tires for Military Tactical Wheeled Vehicles
- Developed by SAE Military/Industry Tire Technology Subcommittee
- Describes test and test methodology to evaluate tire and tire/vehicle related performance
- Tests required based on vehicle system and mission profile
- Used as basis for procurement for military vehicles

SAE J2014:

- Tire Traction 4.6
- Vehicle Evasive Maneuver 4.7
- Bead Unseating 4.8
- Rolling Resistance 4.9
- Dimensional Criteria 4.10
- Ride Handling and Stability 4.11
- Mechanical Reliability 4.13
- Tire Treadlife Durability 4.14
- Comparative Stopping Distance 4.15
- Tire Single Wheel, Skid-Resistance 4.16

SAE J2014 4.6 Tire Traction

- Traction performance of candidate tire relative to reference tire.*
- Mud / Sand /Snow*
- No less than 95% of reference tire.*

SAE J2014 4.7 Vehicle Evasive Maneuver

- NATO Lane Change*
- Wet /Dry Pavement*
- Comparison to reference tire*
- Mixed Fitment (reference tire & candidate tire on same vehicle)*

SAE J2014 4.8 Bead Unseating

- Determine tire/rim slip, air loss or bead unseating at minimum recommended inflation pressure*
- Figure 8 course*
- Sand (moisture content as prescribed)*
- Candidate tires as prescribed air loss (same as reference)*

SAE J2014 4.9 Rolling Resistance

- In Accordance with SAE J1269*
- Rolling Resistance Coefficient of candidate tire not exceed reference tire by more than 5%*

SAE J2014 4.10 Dimensional Criteria

- Measurements of Candidate Tire compared to Reference*
- Overall diameter, section width, weight, revolutions per mile, bead width
- Additional: deflection, spring rate, footprint at various loads/inflations
- Comply with T&RA or ETRTO
- Meet requirements for compatibility with reference tire

SAE J2014 Ride Handling and Stability 4.11

- Candidate tire must provide acceptable ride, handling and stability characteristics*
- Various course profiles specific to mission profile*
- Jury Ride evaluation equal or above reference tire rating (may be supplemented by instrumented data)*

SAE J2014 4.13 Mechanical Reliability

- Tire durability in off-road conditions
- Durability course: washboard (as prescribed)
rock terrain (as prescribed)
cross-country (hills/curves with embedded stones)
- 2400 miles duration (Inspection as prescribed)
- Criteria:
 - Candidate tire must exceed 95% of reference tire mileage
 - Candidate tire: less than two like failures or less than reference tire
 - Candidate tire equal to better than reference tire in Performance (*heel/toe wear, chunking, cutting, stone retention, physical appearance*)

Failure Criteria:

- Broken or displaced belts or breakers*
- Tread separation exposing casing
- Ply separation
- Bead damage / separation
- Severe open splices and/or liner separations
- Tire induced loss of air
- Exposed or broken casing
- Bulges in tread or sidewall

SAE J2014 4.14 Tire Treadlife Durability

- 10000 miles duration
- Evaluate tread wear performance of candidate tire*
- Measurements at prescribed intervals*
 - Tread depth at centerline & shoulder*
 - Diameter, section width, tread arc width*
- Conducted on courses required for mission profile*

Criteria:

- Candidate tire exceeds 95% of reference tire mileage*
- Candidate tire less than two like failures or less than reference tire*
- Candidate tire equal or better than reference in Performance (heel/toe wear, chunking, cutting, stone retention, physical appearance)*

SAE J2014 4.15 Comparative Stopping Distance

- Comparison of stopping distance of candidate with reference tire.*
- Wet / Dry Surface
- Candidate tire stopping distance no more than 5% greater than reference tire
- Mixed Fitment

SAE J2014 4.16 Tire Single Wheel, Skid-Resistance

- Candidate tire on test rig vehicle*
- ASTM E274
- Candidate tire peak and slide performance no less than 95% of reference tire*

Other tests may be required in conjunction with SAE J2014 or specific to the vehicle system

Run flat test

- Performance of tire as part of tire/wheel/run flat system

Steady State Handling SAE J2181

- 200 ft diameter course
- Understeer gradient

Thermal Profiling

- Temperature measurements at centerline / belt edge

Backward Stability ANSI B30.5c

- Crane Application



COOPERATIVE APPROVED TIRE LIST (CATL)



- CATL offers a list of approved tires qualified through limited testing
- CATL 1922 – Highway Tires
- CATL 1923 – Off Road Tires
- Grouped by Application (passenger, truck, etc.)
- Approved Manufacturers with tire brands listed

- Historically, CATL used by government agencies when purchasing tires and retreads
 - Department of Defense (Land Vehicle Contract)
 - U.S. Postal Service
 - Department of the Interior
 - State, city and local governments
- Competitive within the approved sources
- DOD Land Vehicle Contract (138 NSNs)
- More cost effective than to test every NSN

Key Roles and Responsibilities

- The DLA Defense Supply Center Columbus (DSCC) has overall management responsibility.
- TARDEC has technical responsibilities which include:
 - test site and test plan approval
 - review and approval of test results
 - notification to DLA of qualifications/changes.

Email: DAMI_TireEngineering@conus.army.mil <NEW ADDRESS

Address: TARDEC Team Tactical Vehicles & Tires

AMSRD-TAR-E/TACT MS: 267

Warren, MI 48397-5000

Standards Used

- ASTM F-1922, Standard, Test Method for Highway Tires
- CTQP-AM-1922 Administrators Manual for Highway Tire Tests

Test Requirements

- 20,000 miles - highway with limited gravel for certain applications
- Reference tires run on the same vehicle at the same time as candidate tires
- Tread Depth measurement of reference and candidate tires taken at specified intervals
- Candidate tires must complete the test and tread wear projections must be at least 95% of that of the reference tire

CATL 1922 Tires

Groups

- Group 1, passenger car tires
- Group 2, light truck tires
- Group 3, medium and heavy truck/bus tires, and Special Application tires

CATL-1922, April 2007

GROUP 1, PASSENGER CAR: NEW TIRES

BRIDGESTONE/FIRESTONE (U.S.A.) INCORPORATED BRANDS

- TEST QUALIFICATION REFERENCE: ACTS-CATL-T1-1/98-051
- QUALIFICATION EXPIRATION DATE: 28 OCTOBER, 2010
- QUALIFIED PRODUCTION POINTS: ALL BRIDGESTONE/FIRESTONE CORP. TIRE MANUFACTURING FACILITIES

GOVERNMENT ITEM NO.	MODEL/BRAND DESIGNATION	CLASS	CODES
BRIDGESTONE BRANDS:			
X1.2.2	"S402"	a/s	AP, PS
X1.2.3	"BLIZZAK WS-15"	s/t	AP, PS
X1.2.5	"S375"	r/t	AP/ PS
X1.2.6	"POTENZA RE900"	a/s	AP, PS
X1.2.7	"POTENZA S-02"	r/t	AP, PS
X1.2.8	"POTENZA RE71"	r/t	AP, PS
X1.2.9	"POTENZA RE940"	a/s	AP, PS
X1.2.10	"POTENZA RE930"	a/s	AP, PS
X1.2.11	"POTENZA RE 92"	a/s	AP, PS
X1.2.12	"POTENZA HP 41"	a/s	AP, PS
X1.2.13	"EAGER"	a/s	AP, PS
X1.2.14	"TURANZA Z"	a/s	AP, PS
X1.2.15	"TURANZA V"	a/s	AP, PS
X1.2.16	"TURANZA H"	a/s	AP, PS
X1.2.17	"TURANZA T"	a/s	AP, PS
X1.2.18	"TURANZA ER30"	r/t	AP, PS
X1.2.19	"TURANZA EL40"	a/s	AP, PS
X1.2.20	"TURANZA EL41"	r/t	AP, PS
X1.2.21	"TURANZA EL42"	r/t	AP, PS
X1.2.22	"401V"	r/t	AP, PS

Standards Used

- ASTM F-1923 Standard Test Method for Off Road and Low Speed Tire
- CTQP-AM-1923 Administrator Manual for Off Road and Low Speed Tire Tests

Test Requirements:

- Off-road, low-speed tires measured and tested in the laboratory.
- Plunger Energy, tensile strength, ultimate elongation, and dimensional criteria must fall within specified limits.

Classification:

Group 1 Off-the-road tires used in intermittent highway service

Class ML (mining and logging)

Group 2 Earthmoving Mining and Logging tires used for short hauls, fork-lift tires, mobile cranes, shovels, mining cars, front end loaders and dozers.

Class C - (compactor)

Class E - (earthmoving)

Class L - (loader and dozer)

Group 3 – Road Grader

Class G - (grader)

Class TG - (traction grader)

Test Evaluation Criteria

- CATL 1922 (20K Treadwear Test)
 - With control tires performing at 100% level for tread wear, the candidate tire must meet 95% projected mileage
- CATL 1923
 - Dimensional Criteria
 - Plunger Energy
 - Tensile Strength
 - Tread (1700 PSI)
 - Sidewall (900 PSI)
 - Ultimate Elongation
 - Tread (400% minimum)
 - Sidewall (300% minimum)

Hidden Defects Inspection:

- A visual inspection of two tires
- One tire shall be cut into eight equal cross sections, with each section being cut circumferentially in midcrown and on each side of the crown at the point of maximum shoulder thickness; any additional cuts deemed necessary for complete inspection of the tire shall be made.
- The cut sections shall then be inspected for evidence of hidden defects such as separation of tread, ply, or bead in accordance with MIL-STD-1224.



CATL 1923 SCHEDULE



No. Characteristics of tires for exam	No. of tires for exam	Test Acc/Rej	Retest Acc/Rej
Visual exam, major <u>Defects (all groups)</u>	<u>3</u>	<u>0/1</u>	<u>0/1</u>
Visual exam, minor <u>Defects (all groups)</u>	<u>3</u>	<u>1/2</u>	<u>0/1</u>
Tire overall diameter (all groups)	3		
Skid depth (all groups)	3		
Tire overall width (all groups)	3		
<u>Total examinations</u>	<u>9</u>	<u>1/2</u>	<u>0/1</u>
Breaking energy* (all groups)			
Hidden defects (all groups)	2		
<u>Total examinations</u>	<u>2</u>	<u>1/2</u>	<u>0/1</u>
Total Tensile strength	3		
Tires Ultimate elongation	3		
<u>=3 total examinations</u>	<u>6</u>	<u>0/1</u>	<u>0/0</u>

*Does not apply to Style Y

Qualification

- For Style X Tires, Group 1, Group 2, and Group 3 will be tested. Qualification will be extended to other classes of tires in the same group which are of equal or higher quality level of construction and materials as certified by the manufacturer
- Qualification may be extended to a tube-type brand or model, provided it is of equivalent construction (design and materials), with the exception of the bead, to the tubeless model qualified. Using this same provision, the tube-type shall qualify the tubeless model or brand.

Qualification (cont'd)

- For Style X tires, qualification may be extended to other manufacturer's production points of a particular group provided the standards and methods of quality control are equivalent at each point of manufacture. The brand or model must be of equivalent compounds and construction from both locations.

GROUP 1, OFF ROAD TIRES, INTERMITTENT HIGHWAY SERVICE

BRIDGESTONE/FIRESTONE (U.S.A) INCORPORATED

- QUALIFICATION PRODUCTION POINTS: ALL BRIDGESTONE/FIRESTONE INC. OTR TIRE MANUFACTURING FACILITIES.
- QUALIFICATION TEST REFERENCE: GSA QPL-1083-3
- QUALIFICATION EXPIRATION DATE: 30 JULY, 2012
- *NOTE: THIS VERSION OF THE CATL WAS PUBLISHED BEFORE RE-QUALIFICATION TESTING WAS COMPLETED. TO VERIFY QUALIFICATIONS AFTER 30 JUL 05, ASK MANUFACTURER TO PROVIDED A COPY OF QUALIFICATION TEST CERTIFICATION.

GOVERNMENT ITEM NO.	MODEL/BRAND DESIGNATION	CLASS
BRIDGESTONE RADIAL BRANDS:		
X1.1.1RA/RB	VKT	E
X1.1.2RA	VFT	E
X1.1.3RA/RB	VSJ	E
X1.1.4RA/RB	VHB	E/ML
X1.1.5RA	VG	E
X1.1.6RA	VMTS	ML
X1.1.7RA/RB	VRLS	ML
X1.1.13RA	VUT	E/L
X.1.1.14RA/RB	VHS	E/ML
BRIDGESTONE BIAS BRANDS:		
X1.1.8BA/BB	VEB	E
X1.1.9BA	VEB2	E
X1.1.10BB	AL	C
X1.1.11BA/BB	AL2	C
X1.1.12BB	RR	C



Qualification Extension Letter



Qualification Extension Request Letter

Date: xx/xx/xx

This is to request qualification extension be granted to your company name for model/brand name and that this tire be added to CATL-1922 (highway) or CATL-1923 (Off-Road/Low Speed) (circle one).

As **manufacturer**, this will certify that the brand designation for which this request is of the same group, have the same type of construction, uses and same generic reinforcing cord in the tire body and belts, has equivalent compounds, and is of equal or better quality level to that of the brand specified below on which this qualification extension request is based.

MODEL/BRAND NAME BY BRAND OWNER	TIRE GROUP	CLASS & CODE(S)	QUALIFIED SIZES(S) (if applicable)	GOVERNMENT ITEM NO.	TEST REFERENCE NO.

As **brand name owner**, this will certify that the above tire brand is made solely by the below signed manufacturer, or (in the case of multiple manufacturers) by the below signed manufacturer and other manufacturer(s) as detailed in the enclosed additional Qualification Extension Request Letter(s).

The name owner Point of Contact (POC) for this request is persons name, telephone xxxxxxxxxx, and fax xxxxxxxxxx.

SIGNED BY CURRENT QUALIFIED
AND LISTED MANUFACTURER

SIGNED BY BRAND NAME OWNER

TITLE

TITLE

CERTIFICATION DATE

CERTIFICATION DATE

Cooperative Approved Tire List (CATL) Qualification Process

1. Tire Manufacturer expresses interest in becoming qualified to specific group of tires within CATL (passenger, light truck, truck/bus, off-road)
2. Tire manufacturer prepares and submits a detailed test plan conforming to ASTM F1922 or ASTM F1923 to TARDEC for review and approval.
3. Tire manufacturer selects a TARDEC approved independent test facility or proposes an independent test facility for TARDEC review and approval.
4. TARDEC selects the control tire.
5. Tire manufacturer contacts with the test facility to perform testing and notifies TARDEC of the test schedule at least 30 days in advance.
6. Test results are certified by the independent test facility and a copy of the test results/final report are sent directly to TARDEC.
7. TARDEC reviews test results/report and notifies the tire manufacturer of the approval or disapproval decision within 30 days.
8. If approved, TARDEC notifies DLA and Michelin. Within 10 days of notification, Michelin publishes the updated CATL via the internet.

(Test cost paid by tire manufacturer)



PURSUIT AND EMERGENCY HIGH SPEED TESTING

- PASSENGER CAR - SAE J 1561 OR ECE 324
- LIGHT TRUCK - SAE J 1633

High Speed Tire Testing:

- Tires are tested for specified time in the laboratory by running against a prescribed diameter wheel at specified load and speed.
- "The tire manufacturer shall supply to the Administrator the test results, by tire model and size, and certification that the particular tire model and size successfully met the requirements of the subject tests."
- "Govt may grant waiver for additional sizes in same design if contractor provides sufficient evidence (construction information, internal testing, etc.) that these additional sizes meet speed rating."
- TEST FACILITIES
 - STANDARDS TESTING LABS
 - AKRON RUBBER DEVELOPMENT LABORATORY
 - SMITHERS SCIENTIFIC SERVICES, INC.

Termination of test (P&EHS Testing)

The test may be considered terminated by one of the following.

- completion of predetermined final step
- tire failure

Upon visual inspection of the dismounted tire, any visible evidence of the following constitutes tire failure:

- tread separation
- cord separation
- ply separation
- bead separation
- sidewall separation
- chunking
- innerliner separation
- cracking

Light Truck Off Road Severe Application (ORSA)

- 2400 Miles of operation for all tires.
- X-ray Examination Bead-to-Bead 360° around test tires at the beginning and conclusion of the test
- Tread depth measurements, outside diameter, section width, tread radius, tread arc width, and Shore A will be taken at 0, 1931, and 3862 km (0, 1200, and 2400 miles).

Pass/Fail Criteria

- Two Like Failures occur within the prescribed test mileage
- Anomalies experience by the control tire due to testing will be acceptable anomalies experienced by the test candidate tire(s)
- All tires tested with projected mileage equal to or higher than 95% of the projected mileage of the established control tire shall be considered qualified for listing on the Administrator's Cooperative Approved Tire List (CATL), issue in effect.

ORSA Major Categories and Percentage of Test to be Conducted in Those Categories

Environment	Percent of Total Test Mileage	Kilometers (Miles) per Shift	Total Kilometers (Miles) at End of Test
Paved road, high speed	6	10 (6)	232 (144)
Paved road, hill and curve	6	10 (6)	232 (144)
Degraded pavement (pot-holes, loose surface, etc.)	8	13 (8)	309 (192)
Secondary road, gravel road	25	40 (25)	965 (600)
Secondary road, embedded rock	25	40 (25)	965 (600)
Level cross-country track, mild	10	16 (10)	386 (240)
Level cross-country track, severe	10	16 (10)	386 (240)
Hilly cross-country track, mild	7	11 (7)	271 (168)
Hilly cross-country track, severe	3	5 (3)	116 (72)

Pass/Fail Criteria (cont'd)

The following anomalies will be considered for pass/fail criteria in comparison to the control tire:

- Severe heel/toe wear
- Broken belts
- Broken cords
- Severe tread chunking
- Tread separation
- Ply separation
- Bead damage separation
- Open splices
- Loss of air from cavity
- Exposed casing structure cord
- Bulges in tread or sidewall
- Out of Round condition

RETREADING ISSUES

- For testing, all tire casings furnished shall meet applicable requirements of Federal Motor Vehicle Standards 139, 109, 110, 117, 119 and 120 part 574; part 575.104; as well as state and local regulations, as applicable.
- Casings furnished for Style Y tires shall be from a tire purchased new in the United States which the original tread rubber has been worn off while in service in the United States.
- The retread facility's identification code shall be located on the same sidewall and as close as possible to the original casing manufacturer's DOT code.
- Any speed category codes and M&S designations that were placed on the casing sidewall by the new tire manufacturer shall also be removed.

REQUALIFICATION

- Once a tire manufacturers particular model/retreading process of tire has been qualified, it shall remain qualified and be listed on CATL 1922 for a period of: four years for Group 1, five years for Group 2, and six years for Group 3. The period of qualification for CATL 1923 is 10 years for all groups.
- At the end of the appropriate time period, the manufacturer shall requalify the original tire model/retreading process which was submitted for qualification or any other tire model to which qualification was extended based on the qualification of the original tire model.

Tires defined by Product Description (ZZ-T-391, ZZ-T-410, ZZ-T-1619)

- Tire must meet product description and requirements by referenced specification*
- Commercial item (agricultural, mining, skid steer, solid tires)*
- Dimensional requirements (tire diameter, width, tread depth) must be in accordance with industry standards (T&RA, ETRTO)*
- Tire must address additional requirements as defined in specification (ozone resistance, identification, carcass strength, etc)*

QUESTIONS?

