

Report Documentation Page				Form Approved OMB No. 0704-0188	
Public reporting burden for the collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to a penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number.					
1. REPORT DATE <b>DEC 2008</b>		2. REPORT TYPE <b>N/A</b>		3. DATES COVERED <b>-</b>	
4. TITLE AND SUBTITLE <b>Assembly Of Proteorhodopsin For Bioinspired Alternative Energy Applications</b>				5a. CONTRACT NUMBER	
				5b. GRANT NUMBER	
				5c. PROGRAM ELEMENT NUMBER	
6. AUTHOR(S)				5d. PROJECT NUMBER	
				5e. TASK NUMBER	
				5f. WORK UNIT NUMBER	
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) <b>Department of Chemistry and Life Science, United States Military Academy West Point, NY 10996</b>				8. PERFORMING ORGANIZATION REPORT NUMBER	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)				10. SPONSOR/MONITOR'S ACRONYM(S)	
				11. SPONSOR/MONITOR'S REPORT NUMBER(S)	
12. DISTRIBUTION/AVAILABILITY STATEMENT <b>Approved for public release, distribution unlimited</b>					
13. SUPPLEMENTARY NOTES <b>See also ADM002187. Proceedings of the Army Science Conference (26th) Held in Orlando, Florida on 1-4 December 2008</b>					
14. ABSTRACT					
15. SUBJECT TERMS					
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT <b>UU</b>	18. NUMBER OF PAGES <b>2</b>	19a. NAME OF RESPONSIBLE PERSON
a. REPORT <b>unclassified</b>	b. ABSTRACT <b>unclassified</b>	c. THIS PAGE <b>unclassified</b>			

# ASSEMBLY OF PROTEORHODOPSIN FOR BIOINSPIRED ALTERNATIVE ENERGY APPLICATIONS

C. Nguyen\*, and J. Ingram

Department of Chemistry and Life Science, United States Military Academy  
West Point, NY 10996

H. Liang<sup>†</sup>, and G. Stucky

Department of Chemistry and Biochemistry, University of California Santa Barbara  
Santa Barbara, CA 93106

<sup>†</sup>Present address: Department of Metallurgical and Materials Engineering, Colorado School of Mines  
Golden, CO 80401

## ABSTRACT

Proteorhodopsin is an integral membrane protein that functions as a light-driven proton pump, which serves as the basis for an alternative energy device. While many membrane proteins are becoming understood, both structurally and mechanistically, little technology exists for the production and incorporation of this important class of molecules into useful devices. The advantage we have in working with proteorhodopsin is that it can be genetically modified and grown in the laboratory to express different optical and charge properties. The strategy to functionally assemble proteorhodopsin requires manipulation of its charge interaction for induced self-assembly in a lipid bilayer, followed by the binding of the protein-lipid complex onto a conductive substrate, such as Kapton<sup>TM</sup> or borosilicate coated with indium tin oxide.

## 1. INTRODUCTION

In 2000, a new family of photoactive trans-membrane protein, known as proteorhodopsin, was identified through genomic analysis of marine bacterioplankton (Beja et al., 2000). Subsequent reports show that proteorhodopsin is ubiquitous in marine environments (Beja et al., 2001). The interest in proteorhodopsin is because of its demonstrated ability to pump protons across cell membranes (Beja et al., 2000). In nature, this action produces a pH gradient that the organism uses to generate ATP for cellular energy. In the laboratory, variants can be easily expressed in *E. coli* to obtain spectrally tuned protein with variances in pH stability and proton pumping efficiency.

The ability to manufacture proton-tight, artificial, biological membranes containing functional, oriented proteins is the limiting technology for a variety of devices ranging from biosensors to photovoltaic cells. While many membrane proteins, such as receptors, transporters, light driven proton pumps, and catalysts are becoming

understood, both structurally and mechanistically, little technology exists for the production and incorporation of this important class of molecules into useful devices. In this work, we are developing a cooperative assembly process that will be used as the basis for functional proteo-gradient membrane units.

## 2. MATERIALS AND METHODS

Proteorhodopsin was expressed and purified as reported (Kelemen et al., 2003). Liposome membranes consisting of 1,2-dioleoyl-3-trimethylammonium-propane (chloride salt) and 1,2-dioleoyl-sn-glycero-3-phosphocholine were purchased from Avanti Polar Lipids, Alabaster, AL, and prepared as reported (Liang et al., 2004). N-dodecyl- $\beta$ -D-maltoside, purchased from Sigma-Aldrich, was used at a concentration of 0.05% in buffer solutions to maintain proteorhodopsin in its solubilized form.

## 3. RESULTS

We have achieved a comprehensive understanding of the size and photoactive properties of the proteorhodopsin and have assembled the protein into a functional two-dimensional and three-dimensional membrane configuration. Preliminary results show that proteorhodopsin can cooperatively assemble with artificial biological lipid membranes to form multi-lamellar structures. Depending on the pH, membrane charge density and hydrophilic loop region sequences, the protein will organize into different arrays of two-dimensional lattices. Furthermore, adjacent membranes can couple to form multi-lamellar superlattices (Liang et al., 2007, 2008). The work with Kapton<sup>TM</sup> and borosilicate coated indium tin oxide are being further developed.

## CONCLUSION

Our objective is to design and express proteorhodopsin variants of interest on a large scale, to assemble the protein into functional proteo-gradient membrane units, to hybridize them with conductive substrates that maintain the biological function of the protein and are mechanically stable. Achieving these objectives allows us to create a bio-inspired alternative energy device, such as a photovoltaic device or fuel cell that will convert clean and abundant solar energy into usable electric power. Such a resource allows warfighters to be more self-sufficient and less reliant on host country support, especially if the host nation infrastructure is minimal, or for operational security necessities.

## ACKNOWLEDGMENTS

This work was supported by a UC Discovery Grant and Genencor International. Part of this work made use of facilities in the Materials Research Laboratory at UCSB, which is supported by the MRSEC Program of the National Science Foundation under Award No. DMR05-20415.

## REFERENCES

- Beja, O., and Coauthors, 2000: Bacterial rhodopsin: evidence for a new type of phototrophy in the sea, *Science*, **289**, 1902-1906.
- Beja, O., E. N. Spudich, J. L. Spudich, M. Leclerc, and E. F. DeLong, 2001: Proteorhodopsin phototrophy in the ocean, *Nature*, **411**, 786-789.
- Kelemen, B. R., M. Du, and R. B. Jensen, 2003: Proteorhodopsin in living color: Diversity of spectral properties within living bacterial cells, *Biochim. Biophys. Acta*, **1618**, 25-32.
- Liang, H., T. E. Angelini, P. V. Braun, and G. C. L. Wong, 2004: Roles of anionic and cationic template components in biomineralization of CdS nanorods using self-assembled DNA-membrane complexes, *J. Am. Chem. Soc.*, **126**, 14157-14165.
- Liang, H., G. Whited, C. Nguyen, and G. D. Stucky, 2007: The directed cooperative assembly of proteorhodopsin into 2D and 3D polarized arrays, *Proc. Natl. Acad. Sci. USA*, **104**, 8212-8217.
- Liang, H., G. Whited, C. Nguyen, A. Okerlund, and G. D. Stucky, 2008: Inherently tunable electrostatic assembly of membrane proteins, *Nano Letters*, **8**, 333-339.