ARMY RESEARCH LABORATORY



Aluminum Alloy 7068 Mechanical Characterization

by Michael Minnicino, David Gray, and Paul Moy

ARL-TR-4913

August 2009

Approved for public release; distribution is unlimited.

NOTICES

Disclaimers

The findings in this report are not to be construed as an official Department of the Army position unless so designated by other authorized documents.

Citation of manufacturer's or trade names does not constitute an official endorsement or approval of the use thereof.

Destroy this report when it is no longer needed. Do not return it to the originator.

Army Research Laboratory

Aberdeen Proving Ground, MD 21005-5069

ARL-TR-4913

August 2009

Aluminum Alloy 7068 Mechanical Characterization

Michael Minnicino, David Gray, and Paul Moy Weapons and Materials Research Directorate, ARL

Approved for public release; distribution is unlimited.

REPORT DOCUMENTATION PAGE					Form Approved OMB No. 0704-0188
Public reporting burden for t and maintaining the data nee including suggestions for rec Davis Highway, Suite 1204, <i>a</i> comply with a collection of in PLEASE DO NOT RETU	this collection of infor ided, and completing fucing the burden, to Arlington, VA 22202 formation if it does no RN YOUR FORM	mation is estimated to ave and reviewing the collectio Department of Defense, W 4302. Respondents should ot display a currently valid TO THE ABOVE ADD	rage 1 hour per response n information. Send com /ashington Headquarters be aware that notwithsta OMB control number. RESS.	, including the time for ments regarding this bu Services, Directorate for anding any other provis	reviewing instructions, searching existing data sources, gathering urden estimate or any other aspect of this collection of information, or Information Operations and Reports (0704-0188), 1215 Jefferson sion of law, no person shall be subject to any penalty for failing to
1. REPORT DATE (DD-N	ИМ-ҮҮҮҮ)	2. REPORT TYPE			3. DATES COVERED (From - To)
August 2009		Final			May 2008–August 2008
4. TITLE AND SUBTITLE	E				5a. CONTRACT NUMBER
Aluminum Allov 70	068 Mechanica	al Characterization	ı		
					5b. GRANT NUMBER
					5c. PROGRAM ELEMENT NUMBER
6. AUTHOR(S) Michael Minnicino	David Grav	and Paul Mov			5d. PROJECT NUMBER
whender winniemo,	, David Gray, i				5e. TASK NUMBER
					5f. WORK UNIT NUMBER
7. PERFORMING ORGA		(S) AND ADDRESS(ES	6)		8. PERFORMING ORGANIZATION
U.S. Army Researc	h Laboratory	.,			REPORT NUMBER
ATTN: AMSRD-A	ARL-WMM-B				ARL-TR-4913
Aberdeen Proving	Ground, MD 2	21005-5069			
9. SPONSORING/MONIT	FORING AGENCY	NAME(S) AND ADDR	ESS(ES)		10. SPONSOR/MONITOR'S ACRONYM(S)
					11. SPONSOR/MONITOR'S REPORT NUMBER(S)
12. DISTRIBUTION/AVA	ILABILITY STATE	MENT			
Approved for public	c release; distr	ibution is unlimite	ed.		
13. SUPPLEMENTARY	NOTES				
14. ABSTRACT					
A relatively new all Ranch, CA), owing strongest aluminum	loy of aluminu its history to t commercially	m is being market he development o produced. This a	ed as "ordnance f ordnance applie alloy is aluminun n terms of its ala	aluminum" by i cations. The alu n zinc, with an a	its developer, Kasier Aluminum (Foothill uminum alloy designation, 7068, is the advertised minimum yield strength of 99 ksi.
to large-caliber mu	nition designer	s.	In terms of its era	istic properties a	and mechanical strength, in sizes of interest
15. SUBJECT TERMS					
aluminum, 7068, el	astic, strength				
16. SECURITY CLASSIF	ICATION OF:		17. LIMITATION OF ABSTRACT	18. NUMBER OF PAGES	19a. NAME OF RESPONSIBLE PERSON Michael Minnicino
a. REPORT b.	ABSTRACT	c. THIS PAGE	1		19h TELEPHONE NUMBER (Include area code)
Unclassified U	nclassified	Unclassified	UU	18	410-306-1919
					Standard Form 298 (Rev. 8/98)

Prescribed by ANSI Std. Z39.18

Contents

Lis	st of Figures	iv
Lis	st of Tables	iv
1.	Introduction	1
2.	Tension Tests	1
3.	Results	2
4.	Discussion	3
5.	Summary	5
6.	References	6
Dis	stribution List	7

List of Figures

Figure 1.	Tension test specimen geometry (units are in inches)	2
Figure 2.	Longitudinal direction stress-strain curves	4
Figure 3.	Transverse direction stress-strain curves	4

List of Tables

Table 1.	Mechanical property comparison of high-strength aluminum alloys	.1
Table 2.	Experimental longitudinal direction properties.	.3
Table 3.	Experimental transverse direction properties.	.3
Table 4.	Typical mechanical properties per AMI.	.3
Table 5.	Summary of 7068 aluminum extrusion direction strengths	.5

1. Introduction

A relatively new alloy of aluminum is being marketed as "ordnance aluminum" by its developer, Kasier Aluminum (Foothill Ranch, CA), owing its history to the development of ordnance applications in the mid 1990s (1). The aluminum alloy designation, 7068, is the strongest aluminum commercially produced. This alloy has an advertised minimum yield strength of 99 ksi (2). The commonly specified material properties for extruded 7068 aluminum are shown in table 1, along with 7050 and 7075 aluminum alloys for comparison (3).

Property		Alloy					
	7068	7075	7050				
Elastic modulus (Msi)	NA	10.4	10.3				
YTS (ksi)	94	73	70				
UTS (ksi)	103	83	81				
Elongation (%)	5	11	10				

 Table 1. Mechanical property comparison of high-strength aluminum alloys.

Note: NA = not available.

It is assumed in the listing of these properties that they are isotropic. However, the extrusion of the metal stock results in preferential orientation and elongation of the crystals, resulting in deformation-induced anisotropy. The result of this anisotropy is the directional dependence of material properties, especially strength. The elastic modulus that defines the slope of the linearly proportional part of the stress-strain curve is insignificantly affected by deformation-induced anisotropy. Another important and often overlooked assumption is that these properties are invariant with respect to the size of extruded stock. The objective of this work is to characterize extruded 7068 aluminum in terms of its elastic properties and mechanical strength in sizes of interest to large-caliber munition designers.

2. Tension Tests

The 7068 aluminum alloy is relevant for large-caliber projectile applications. As a result, test specimens were electronic discharge machined in accordance with ASTM E8 (4) from a 6-indiameter billet in both the billet's extruded (i.e., longitudinal) and transverse directions. The specimen geometry is shown in figure 1. The specimens were painted with a speckle pattern for strain measurement purposes using digital image correlation (5), clamped in an Instron 1127, and pulled at a rate of 0.1 in/s.



Figure 1. Tension test specimen geometry (units are in inches).

3. Results

The mechanical properties computed from the longitudinal and transverse tension test data are shown in tables 2 and 3, respectively. The elastic modulus is calculated using a linear least-squares regression from the linear portion of the stress-strain curve. As expected, the calculated elastic moduli for the longitudinal and transverse directions differ little from each other. The yield tensile strength (YTS) is taken as the stress at 0.2% strain. The ultimate tensile strength (UTS) is the maximum stress seen during the tensile test. The elongation is taken as the largest strain value before specimen rupture (failure). As expected, the longitudinal direction (i.e., the aluminum billet's extruded direction) has a larger YTS and UTS compared to the transverse direction. These findings agree with the larger longitudinal yield and UTS values reported by Advanced Materials International (AMI) (1).

The directional-dependent mechanical properties of AMI are shown in table 4. The directional dependence is attributed to the preferential crystal orientation resulting from the extrusion manufacturing process where the crystals become aligned and elongated along the extrusion direction. The nonrandom distribution of crystal orientation affects the macroscopic mechanical properties, particularly strength values (6). The current experimental results compare well with

	Longitudinal Direction					
Material Property	Test 1	Test 2	Test 3	Test 4	Average	Std. Dev.
Elastic modulus, E (Msi)	10.98	10.05	10.15	10.13	10.33	0.438
Yield strength (ksi)	92.8	91	96.1	96.7	94.20	0.003
UTS (ksi)	98.9	97	101.2	102.1	99.80	2.30
Elongation (%)	10.4	11.5	11.9	15.2	12.25	2.07

Table 2. Experimental longitudinal direction properties.

Table 3. Experimental transverse direction properties.

	Transverse Direction					
Material Property	Test 1	Test 2	Test 3	Average	Std. Dev.	
Elastic modulus, E (Msi)	10.04	9.94	9.97	9.98	0.051	
Yield strength (ksi)	75.5	75.4	74.5	75.13	0.001	
UTS (ksi)	82.2	82.3	82.3	82.27	0.06	
Elongation (%)	2.7	3.1	3.4	3.07	0.35	

Table 4. Typical mechanical properties per AMI.

Direction	YTS (ksi)	UTS (ksi)	Elongation (%)
Longitudinal	99.1	102.9	9
Transverse	87.5	93.5	7

Kaiser's specified minimum values for the longitudinal direction. The current results indicate that reductions in strengths and elongation are significant. The stress-strain curves for the longitudinal and transverse direction specimens are shown in figures 2 and 3, respectively.

4. Discussion

The longitudinal tensile specimens displayed ductile failure surfaces that are inclined 45° relative to the load direction. Conversely, the transverse specimens exhibited a more brittle-like failure surface that was roughly perpendicular to the load direction. This behavior is evident from observation of the stress-strain curves shown in figures 2 and 3. The strain to failure for the longitudinal specimens is greater than 10%, whereas the average strain to failure for the transverse specimens is less than 3.5%. Additionally, the YTS and UTS for the transverse direction are lower than the longitudinal direction. AMI notes this directional strength behavior as well. The calculated elastic moduli for the longitudinal and transverse directions differ little and compare well to the published data, except for elongation. A summary of the 7068 extrusion direction properties is shown in table 5.



Figure 2. Longitudinal direction stress-strain curves.



Figure 3. Transverse direction stress-strain curves.

Table 5.	Summary	of 7068	aluminum	extrusion	direction	strengths.
						0

Organization	Section	YTS UTS		Elongation	
	(in)	(ksi)	(ksi)	(%)	
AMI	3-6.5 in	90	94	5	
Kaiser	Unknown	99	103	9	
ARL data	6 in	94.2	98.8	12.25	

Note: ARL = U.S. Army Research Laboratory.

5. Summary

To date, 7068 aluminum alloy is the strongest commercially-produced aluminum. Strengths for large-caliber, munition-sized components are experimentally found to have a minimum YTS of 91 ksi and minimum UTS of 97 ksi, with a minimum strain to failure of 10.4% in the longitudinal (i.e., extruded) direction. The transverse direction properties are less due to the preferred crystal orientation. The transverse direction strengths have a minimum YTS of 74.5 ksi and a minimum UTS of 82.2 ksi, with a minimum strain to failure of 2.7%. These numbers compare well with other published data.

6. References

- 1. 7068 Data Sheet. AMI, UK. www.advancedmetals.com (accessed 2007).
- 2. Rod and Bar Alloy 7068 Technical Data Sheet. Kaiser Aluminum. www.kaiseraluminum.com (accessed 2006).
- 3. Schwartz, M. *Encyclopedia of Materials, Parts, and Finishes*; 2nd ed.; CRC Press LLC: Boca Raton, 2002.
- 4. ASTM E8. Standard Test Methods of Tension Testing of Metallic Materials. *Annu. Book ASTM Stand.* Vol. 3.01.
- 5. Chu, T. C.; et al. Applications of Digital-Image-Correlation Techniques to Experimental Mechanics. *Experimental Mechanics* **1995**.
- 6. More, Ken-ichiro. *Simulation of Materials Processing: Theory, Methods and Applications*; Taylor and Francis: Toyohashi, Japan, 2001.

- 1 DEFENSE TECHNICAL
- (PDF INFORMATION CTR
 only) DTIC OCA
 8725 JOHN J KINGMAN RD
 STE 0944
 FORT BELVOIR VA 22060-6218
 - 1 DIRECTOR US ARMY RESEARCH LAB IMNE ALC HRR 2800 POWDER MILL RD ADELPHI MD 20783-1197
 - 1 DIRECTOR US ARMY RESEARCH LAB RDRL CIM L 2800 POWDER MILL RD ADELPHI MD 20783-1197
 - 1 DIRECTOR US ARMY RESEARCH LAB RDRL CIM P 2800 POWDER MILL RD ADELPHI MD 20783-1197

ABERDEEN PROVING GROUND

1 DIR USARL RDRL CIM G (BLDG 4600)

- 1 DIRECTOR US ARMY RSRCH LAB AMSRD ARL SED E R ATKINSON 2800 POWDER MILL RD ADELPHI MD 20783-1197
- 1 DIRECTOR US ARMY RSRCH LAB RDRL CI 2800 POWDER MILL RD ADELPHI MD 20783-1197
- DIRECTOR US ARMY RSRCH LAB AMSRD ARL WMM B A ABRAHAMIAN M BERMAN M CHOWDHURY A FRYDMAN R KARGUS T LI 2800 POWDER MILL RD ADELPHI MD 20783-1197
- 1 COMMANDER US ARMY MATRL CMND AMXMI INT 9301 CHAPEK RD FORT BELVOIR VA 22060-5527
- 1 COMMANDER US ARMY TACOM ARDEC AMSRD AAR EM J HEDDERICH BLDG 94 PICATINNY ARSENAL NJ 07806-5000
- 1 COMMANDER US ARMY TACOM ARDEC AMSRD AAR EMT B MACHAK BLDG B1 PICATINNY ARSENAL NJ 07806-5000
- 4 COMMANDER US ARMY TACOM ARDEC AMSRD AAR AEP E K LAUGHLIN S GROESCHLER J LEE J VEGA BLDG 94 PICATINNY ARSENAL NJ 07806-5000

- 1 COMMANDER US ARMY TACOM ARDEC AMSRD AAR AEM J G FLEMING BLDG 65N PICATINNY ARSENAL NJ 07806-5000
- 1 COMMANDER US ARMY TACOM ARDEC AMSRD AAR EBM R CARR BLDG 65N PICATINNY ARSENAL NJ 07806-5000
- 1 COMMANDER US ARMY TACOM ARDEC AMSRD AAR EBM W SHARPE BLDG 1 PICATINNY ARSENAL NJ 07806-5000
- 3 COMMANDER US ARMY TACOM ARDEC SFAE AMO MAS LC R DARCY R JOINSON D RIGOGLIOSO BLDG 354 PICATINNY ARSENAL NJ 07806-5000
- 2 COMMANDER US ARMY TACOM ARDEC AMSRD AAR AEM L P DONADIA D VO BLDG 65 S PICATINNY ARSENAL NJ 07806-5000
- 1 COMMANDER US ARMY TACOM ARDEC AMSRD AAR AEM T LOUZEIRO BLDG 65 PICATINNY ARSENAL NJ 07806-5000
- 1 COMMANDER US ARMY TACOM ARDEC AMSRD AAR AEM L MANOLE BLDG 65N PICATINNY ARSENAL NJ 07806-5000

- 4 COMMANDER US ARMY TACOM ARDEC AMSRD AAR AEM M PALATHINGAL S MUSALLI M LUCIANO E LOGSDEN BLDG 65S PICATINNY ARSENAL NJ 07806-5000
- 2 COMMANDER US ARMY TACOM ARDEC AMSRD AAR AEM A VELLA J LUTZ BLDG 354 PICATINNY ARSENAL NJ 07806-5000
- 1 COMMANDER US ARMY TACOM ARDEC AMSRD AAR AEE P D KAPOOR BLDG 75 PICATINNY ARSENAL NJ 07806-5000
- 1 COMMANDER US ARMY TACOM ARDEC AMSRD AAR AEE P S KERWIEN BLDG 60 PICATINNY ARSENAL NJ 07806-5000
- 1 COMMANDER US ARMY TACOM ARDEC AMSRD AAR AIP M LOS BLDG 1 PICATINNY ARSENAL NJ 07806-5000
- 2 SFSJM CDL AMMUN TEAM AMSIO SMT R CRAWFORD W HARRIS 1 ROCK ISLAND ARSENAL ROCK ISLAND IL 61299-6000
- 1 US ARMY TARDEC AMSRD TAR R D TEMPLETON 6501 E 11 MILE RD MS 263 WARREN MI 48397-5000

- 7 BENET LABS AMSTA AR CCB M SOJA E KATHE G SPENCER P WHEELER S KRUPSKI J VASILAKIS G FRIAR WATERVLIET NY 12189-4050
- 5 BENET LABS AMSTA CCB R S SOPOK E HYLAND D CRAYON R DILLON G VIGILANTE WATERVLIET NY 12189
- 1 PEO GROUND COMBAT SYS SFAE GCS BCT/MS 325 M RYZYI 6501 ELEVEN MILE RD WARREN MI 48397-5000
- 2 USA RDECOM AMSRD AMR AE F T F RUMPF J CHANG BLDG 488 B247 REDSTONE ARSENAL AL 35898
- 1 USA RDECOM AMSRD AMR AE F A M ROGERS BLDG 4488 B244 REDSTONE ARSENAL AL 35898
- 3 USA RDECOM AMSRD AMR AE F M K BHANSALI G LIU R MCFARLAND BLDG 4488 B272 REDSTONE ARSENAL AL 35898
- 1 US ARMY ARDEC AMSRD AAR AEM I D CONWAY BLDG 65 N PICATINNY ARSENAL NJ 07806-5000

- 4 US ARMY RSRCH OFC J PRATER D STEPP D KISEROW W MULLINS PO BOX 12211 RESEARCH TRIANGLE PARK NC 27709-2211
- 1 COMMANDER US ARMY TACOM ARDEC AMSTA AR CCL B J MIDDLETON BLDG 65N PICATINNY ARSENAL NJ 07806-5000
- 1 COMMANDER US ARMY TACOM ARDEC ASIC PRGM INTEGRATION OFC J RESCH BLDG 1 PICATINNY ARSENAL NJ 07806-5000
- 1 COMMANDER US ARMY TACOM ARDEC AMSRD AAR AEW M(D) M MINISI BLDG 65 N PICATINNY ARSENAL NJ 07806-5000
- 1 US ARMY TACOM ARDEC AMSRD AR CCL C S SPICKERT-FULTON BLDG 65 N PICATINNY ARSENAL NJ 07806-5000
- 4 PM ARMS SFAE AMO MAS SMC R KOWALSKI F HANZL P RIGGS M BULTER BLDG 354 PICATINNY ARSENAL NJ 07806-5000
- 1 PM ARMS SFAE AMO MAS MC BLDG 354 PICATINNY ARSENAL NJ 07806-5000

- 7 FORT SILL FIELD ARTILLERY S COFFMAN G LEMONS B LEWIS J HALL D CARLSON R NELSON C NIEDERHAUSER BLDG 700 (KNOX HALL) FORT SILL OK 73503
- 1 FORT SILL FIELD ARTILLERY FDIC USAFAC D BROWN BLDG 700 (KNOX HALL) FORT SILL OK 73503
- 1 FORT SILL FIELD ARTILLERY HQ US ARMY FIRES CTR R HADDOCK 640 MCBRIDE AVE FORT SILL OK 73503
- 1 FORT SILL FIELD ARTILLERY TSM CANNON J TANZI FORT SILL OK 73503
- 1 FORT SILL FIELD ARTILLERY TCM FSC3 J HAITHCOCK 569 CRUIKSHANK CIR FORT SILL OK 73503
- 1 DIRECTOR NGIC IANG TMT 2055 BOULDERS RD CHARLOTTESVILLE VA 22091-5391
- 3 INST FOR ADVANCD TECH H FAIR I MCNAB S BLESS 3925 W BRAKER LN AUSTIN TX 78759-5316
- 1 ALLIANT TECHSYSTEMS INC R DOHRN MN11 1428 600 SECOND ST NE HOPKINS MN 55343

- 1 ATK M JANTSCHER MN07 LW54 5050 LINCOLN DR EDINA MN 55436
- 1 ALLIANT TECHSYSTEMS INC R BECKER MN11 2626 5050 LINCOLN DR EDINA MN 55340-1097
- 2 ATK LAKE CITY SMALL CALIBER AMMUN LAKE CITY ARMY AMMUN PLANT K ENLOW D MANSFIELD PO BOX 1000 INDEPENDENCE MO 64051-1000
- 1 ATK LAKE CITY LAKE CITY ARMY AMMUN PLANT SMALL CALIBER AMMUN J WESTBROOK MO10 003 PO BOX 1000 INDEPENDENCE MO 64051-1000
- 2 DIRECTOR LLNL S DETERESA F MAGNESS PO BOX 808 LIVERMORE CA 94550
- ARMTEC DEFENSE PRODUCTS S DYER
 85 901 AVE 53 PO BOX 848 COACHELLA CA 92236
- 3 PACIFIC NORTHWEST LAB M SMITH G VAN ARSDALE R SHIPPELL PO BOX 999 RICHLAND WA 99352
- 1 CUSTOM ANALYTICAL ENG SYS INC A ALEXANDER 13000 TENSOR LANE NE FLINTSTONE MD 21530

- 3 ALLIANT TECHSYSTEMS INC J CONDON E LYNAM J GERHARD WV01 16 STATE RT 956 PO BOX 210 ROCKET CENTER WV 26726-0210
- 2 GENERAL DYNAMICS OTS FLINCHBAUGH DIV K LINDE G KURZIK PO BOX 127 RED LION PA 17356
- 1 ARROW TECH ASSOC 1233 SHELBURNE RD STE D8 SOUTH BURLINGTON VT 05403-7700
- 1 UNIV OF CINCINNATI DEPT OF AEROSPACE ENG & ENG MECHANICS A TABIEI 722 RHODES HALL PO BOX 210070 CINCINNATI OH 45221-0070
- 4 UNIV OF DELAWARE CTR OF COMPOSITE MTRLS J GILLESPIE S LOPATNIKOV S YARLAGADDA S ADVANI 215 COMPOSITES MANUFAC SCI LAB NEWARK DE 19716
- 1 UNIV OF DELAWARE CTR OF COMPOSITE MTRLS M SANTARE 126 SPENCER LAB NEWARK DE 19716
- 1 DEPT OF MECH ENG UNIV OF NEVADA LAS VEGAS M TRABIA 4505 MARYLAND PKWY BOX 454027 LAS VEGAS NV 89154-4027

ABERDEEN PROVING GROUND

1 US ARMY ATC CSTE DTC AT AD I W FRAZER 400 COLLERAN RD APG MD 21005-5059

62

DIR USARL RDRL LOA F M ADAMSON RDRL SL **R COATES** RDRL WM **B FORCH** J SMITH S KARNA J MCCAULEY **P PLOSTINS** T WRIGHT **RDRL WMB** L BURTON M ZOLTOSKI J NEWILL RDRL WMB A **D** LYON RDRL WMB C **P WEINACHT** RDRL WMB D J COLBURN P CONROY RDRL WMB F W OBERLE **RDRL WMM** S MCKNIGHT J BEATTY **R** DOWDING RDRL WMM A M VANLANDINGHAM RDRL WMM B J BENDER T BOGETTI **R** CARTER W DE ROSSET W DRYSDALE **R EMERSON D HOPKINS R KASTE** L KECSKES E KLIER H MAUPIN M MINNICINO **B POWERS**

NO. OF COPIES ORGANIZATION D SNOHA J SOUTH J SWAB J TZENG AMSRD ARL WMM C M MAHER W SPURGEON RDRL WMM D E CHIN J ADAMS **B** CHEESEMAN J MONTGOMERY **RDRL WMT P BAKER** C HOPPEL RDRL WMT A S SCHOENFELD D HACKBARTH RDRL WMT B R GUPTA **B MCANDREW** RDRL WMT C T BJERKE **G BOYCE T EHLERS** K KIMSEY L MAGNESS **B SCHUSTER B SORENSEN R SUMMERS B WALTERS** RDRL WMT D D CASEM N GNIAZDOWSKI T WEERASOORIYA RDRL WMT E **B RINGERS**