

AFRL-RX-WP-TM-2010-4086

COLLABORATIVE RESEARCH AND DEVELOPMENT (CR&D) Delivery Order 0044: Accelerated Computational Approach to Multiscale Relaxation in Nanoparticulate-polymer Composites

Ras Pandey

University of Southern Mississippi

Alan T. Yeates and Barry L. Farmer Nonmetallic Materials Division

MAY 2008 Final Report

Approved for public release; distribution unlimited.

See additional restrictions described on inside pages

STINFO COPY

AIR FORCE RESEARCH LABORATORY MATERIALS AND MANUFACTURING DIRECTORATE WRIGHT-PATTERSON AIR FORCE BASE, OH 45433-7750 AIR FORCE MATERIEL COMMAND UNITED STATES AIR FORCE

NOTICE AND SIGNATURE PAGE

Using Government drawings, specifications, or other data included in this document for any purpose other than Government procurement does not in any way obligate the U.S. Government. The fact that the Government formulated or supplied the drawings, specifications, or other data does not license the holder or any other person or corporation; or convey any rights or permission to manufacture, use, or sell any patented invention that may relate to them.

This report was cleared for public release by the USAF 88th Air Base Wing (88 ABW) Public Affairs Office (PAO) and is available to the general public, including foreign nationals. Copies may be obtained from the Defense Technical Information Center (DTIC) (http://www.dtic.mil).

AFRL-RX-WP-TM-2010-4086 HAS BEEN REVIEWED AND IS APPROVED FOR PUBLICATION IN ACCORDANCE WITH THE ASSIGNED DISTRIBUTION STATEMENT.

*//Signature//

RITA SCHOLES Project Manager Business Operations Branch Integration and Operations Division Materials and Manufacturing Directorate //Signature//

ROBERT ENGHAUSER Acting Chief Business Operations Branch Integration and Operations Division

This report is published in the interest of scientific and technical information exchange, and its publication does not constitute the Government's approval or disapproval of its ideas or findings.

*Disseminated copies will show "//Signature//" stamped or typed above the signature blocks.

	REP	Form Approved OMB No. 0704-0188						
The public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Department of Defense, Washington Headquarters Services, Directorate for Information Operations and Reports (0704-0188), 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to any penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number. PLEASE DO NOT RETURN YOUR FORM TO THE ABOVE ADDRESS.								
1. REPORT DA	TE (DD-MM-YY)	2. REPORT TYPE		3. DATE	ES COVERED (From - To)		
May 200	8		Final		01 I	December 2005 – 01 April 2008		
COLLABORATIVE RESEARCH AND DEVELOPMENT (CR&D)						F33615-03-D-5801-0044		
Delivery	Order 0044:	on 5b. GRANT NUMBER						
in Nanoparticulate-polymer Composites						5c. PROGRAM ELEMENT NUMBER 61202F		
6. AUTHOR(S)		5d. PROJECT NUMBER						
Ras Pano	lev (Universit	4349						
Alan T. Yeates and Barry L. Farmer (AFRL/RXB)						5e. TASK NUMBER		
						1.0		
		5f WORK UNIT NUMBER						
By:			For:			REPORT NUMBER		
University of Southern Mississippi Universal Technology Corporation						S-531-044		
Department of	Physics and A	stronomy	1270 Device	North Fairfield Roa $15422,2600$	id			
Nonmotallic M	15 59400-5040	allu on (AEDI /DVB		ni, 011 45452-2000				
Air Force Rese	Parch Laborator		')					
Materials and	Manufacturing	Directorate						
WPAFB, OH	45433-7750							
Air Force Mat	eriel Command	l, United States	Air Force					
9. SPONSORI	NG/MONITORING	G AGENCY NAM	E(S) AND ADDRESS(ES)		10. SPONSORING/MONITORING		
Air Force Research Laboratory						AGENCY ACRONYM(S)		
Materials and Manufacturing Directorate						AFRL/RXOB		
Wright-Patterson Air Force Base, OH 45433-7750						11. SPONSORING/MONITORING		
Air Force Materiel Command						AGENCY REPORT NUMBER(S)		
United States Air Force						AFRL-RX-WP-TM-2010-4086		
12. DISTRIBUTION/AVAILABILITY STATEMENT Approved for public release; distribution unlimited.								
13 SLIPPI EMENTARY NOTES								
PAO Cas	e Number: 88A	BW 2009-0044	; Clearance Date: 0	1 Feb 2009. Repo	rt contains colo	r.		
	-			1				
This research	arch in support	of the Air Force	e Research Laborato	orv Materials and	Manufacturing	Directorate was conducted at Wright-		
Patterson AFB. Ohio from 1 December 2005 through 1 April 2008. This task developed and validated Monte Carlo computational								
methods for the modeling of two-dimensional nanoplates in polymer/solvent matrix. Nano-particulate polymer composites consist of								
multi-component systems with such constituents as solvent, polymer chains, clay platelets etc. The vast parameter space includes								
molecular weight of constituents, their concentrations, temperature, and interaction apart from processing and driving mechanism								
(shearing, compression, etc.). The constitutive components can be described by particles, chains, and sheets in a coarse-grained								
modeling by computer simulations. Relaxation of each component and their cooperative dynamics lead to multi-scale responses								
resulting in self-organizing structures. While the stochastic dynamics of each component facilitate equilibration, the physical								
entanglement, local-crowding, and jamining cause endopic constraints that may inder thermal equilibration. The evolving structure may or may not be in thermodynamics equilibrium depending on the time scales. Understanding the structure and dynamics of such a								
multi-component system is known for its complexities. Therefore, we proposed to address some of the issues by accelerated								
computational approach.								
13. SUBJECT TERMS INano-particulate polymer composites								
10. SECURITY	LASSIFICATIO		OF ABSTRACT	OF PAGES	19a. NAME OF	Cles		
a. REPORT	Unclassified	Unclassified	SAR	20	19b. TELEPHO	NE NUMBER (Include Area Code)		
Unclassified		Sherusshired			N/A	,		

Standard	Form 298	3 (Rev.	8-98)
Prescribed	by ANS	Std. Z	39-18

An Accelerated Computational Approach To Multi-Scale Relaxation In Nano-Particulate-Polymer Composites

Alan T. Yeates¹, Ras B. Pandey², Barry L. Farmer¹

Nano-particulate polymer composites¹ consist of multi-component systems with such constituents as solvent, polymer chains, clay platelets etc. The vast parameter space includes molecular weight of constituents, their concentrations, temperature, and interaction apart from processing and driving mechanism (shearing, compression, etc.). The constitutive components can be described by particles, chains, and sheets in a coarse-grained modeling by computer simulations. Relaxation of each component and their cooperative dynamics lead to multi-scale responses resulting in self-organizing structures. While the stochastic dynamics of each component facilitate equilibration, the physical entanglement, local-crowding, and jamming cause entropic constraints that may hinder thermal equilibration. The evolving structure may or may not be in thermodynamics equilibrium depending on the time scales. Understanding the structure and dynamics of such a multi-component system is known for its complexities. Therefore, we proposed to address some of the issues by accelerated computational approach.

Model: We use discrete lattice with ample degrees of freedom to develop an efficient computer simulation model. Particle is represented by a unit cell of the lattice. Chains and sheets are designed from tethering particles/nodes in a linear chain and two-dimensional network respectively. Conformation and dynamics of polymer chains have been studied for a long time², ³; advantages and pitfall of models, approaches, and computational methods have been extensively examined¹. Using the vast amount of knowledge gained from the computer simulation modeling of polymer chains over several decades², we have successfully developed a model for the flexible sheet^{4, 5}. If particle to chain is a large jump in complexity in regard to both structure and dynamics of the underlying polymer system, extending the modeling from a chains to a sheet is even more complex. The idea of bond-fluctuating sheet on a discrete lattice, analogous to a bond-fluctuating chain is a major contribution to a set of basic components (particle, and chain) in modeling composites and the starting point of our investigations^{4, 5}. Attempts are made to understand the fundamental properties of sheet and dispersion of layered platelets in solvent and polymer matrix systematically using Monte Carlo simulations on a cubic lattice of size L^3 . In the following, we briefly describe main results from our investigations.

A platelet (sheet) is described^{4, 5} by a set of L_s^2 nodes tethered together by flexible bonds on a cubic lattice (see Figure 1); the distance between the nearest neighbor nodes is twice the lattice constant, the minimum bond length. A node is represented by a unit cube (i.e., eight sites) of the lattice. Since a lattice site cannot be occupied by more than one node due to excluded volume constraints, the minimum distance between consecutive tethered nodes, (i.e. the bond length) is two in units of the lattice constant. The bond length can fluctuate between 2 and $\sqrt{10}$ with an exception of $\sqrt{8}$ as the node attempts to move stochastically (see below) to one of its 26

¹ Materials and Manufacturing Directorate, Air Force Research Laboratory, AFRL/MLBP, 2941 P Street, Wright-Patterson Air Force Base, OH 45433

² Department of Physics and Astronomy, University of Southern Mississippi, Hattiesburg, MS 39406-5046

adjacent cubes (referred as sites in the following description) similar to the bond-fluctuation model for a polymer chain².



Figure 1. Representation of a Square Sheet.

The interaction energy of a node is described by,

$$E = \sum_{ij} J(i,j),$$

where *i* runs over each node and *j* over neighboring sites within a range *r*. It should be pointed out that the range *r* should be large enough to incorporate appropriate constituents (platelet nodes and solvent particles) in the local vicinity of a node. For example, the minimum value of *r* must be 2 to reach a nearest node in a sheet; typically $r^2 = 6$, 8. The empty lattice sites may constitute an effective medium. Different types of node-node interaction ($J(n,n) = \varepsilon_{nn}$) and node-solvent interaction ($J(n,n) = \varepsilon_{ns}$) can be considered within a range (*r*) which can be varied. The sheet is also referred as tethered membrane which exhibits unique conformational characteristics as it wrinkles and crumples under various conditions (quality of solvent, entropic constraints due to presence of polymer chains, temperature, etc.) while entropy dissipates from its open boundary.

As the nodes execute their stochastic motion, the conformation of the sheet relaxes and approaches its equilibrium value. Relaxation of the radius of gyration (Figure 2) is examined in detail along with its dependence on the temperature (Figure 3). Depending on the node-node interaction (attractive, repulsive), Figure 2 shows how a sheet expands (repulsive) or shrinks (attractive) at low and high temperatures. Our simulations also predict how the radius of gyration varies with the temperature^{5, 6} (see Figure 3). Since the simulations take relatively long time for larger sheets to equilibrate, these studies are limited to few temperatures with the larger sheets. However, the trend in temperature dependence of the radius of gyration with the smaller sheet seems to provide reliable insight into the qualitative picture.



Figure 2. Variation of the mean square radius of gyration (R_g^2) of the sheet (64^2) with the time step (t) on a 200^3 lattice with the node-node interaction nn = -1, 1 and node-solvent interaction ns = -0.5 at temperature T = 2, 10. 10-1000 independent samples are used. Ref [6].

Stochastic dynamics of a node (particle) in a free polymer chain describes short to long time characteristics, e.g., short time Rouse dynamics to long time diffusion. Motion of a node in a tethered membrane exhibits multi-scale dynamics much richer than that of a chain and provides a detail insight into the in-plane segmental dynamics characteristics of the wrinkle modes to long time diffusion. Such investigation requires in-depth analysis⁷ with quality data to probe and identify multi-scale trends⁶ in segmental dynamics and structural relaxation. For example, the mean square displacement of the center node of the sheet with the time step shows well-define modes from short to long time regimes (see Figure 4, 5). From Figure 4, we can recognize three types of power-laws dynamics in sequence: (*i*) short time dynamics, $R_n^2 \propto t^{2v1}$ with $v_1 \sim 1/6$ followed by (*ii*) a faster dynamics $R_n^2 \propto t^{2v2}$ with $v_2 \sim 1/3$ before slowing down substantially, $R_n^2 \propto t^{2v3}$ with $v_3 \sim 1/10$. Although a closer examination of the data in Figure 4 ($t \sim 10^7$) shows the onset of diffusive behavior in the long time despite large fluctuations (see the inset Figure), the large-scale simulation (Figure 5) clarify it with much better accuracy. These multi-scale segmental dynamics are unique characteristics of propagating modes of a tethered membrane, very different from those in a chain. Thus, we find that the local modes propagate via multiple scale dynamics (v_1 , v_2 , v_3) with well-defined crossovers. Further, the type and range of the multi-scale dynamics depends on the type of sheet (ε_{nn}) and underlying matrix in which it is embedded.



Figure 3. Variation of the radius of gyration with the temperature of the sheet (16^{*}) on a 64^3 lattice with the node-node interaction nn = -1, 1 and node-solvent interaction ns = -0.5. Ref. [5,6].



Figure 4. Variation of mean square displacement of the center node (R_n^2) with the time step t of the membrane of size 64^2 on a 200^3 lattice at time steps with interactions $\varepsilon_{nn} = -1$, 1 and $\varepsilon_{ns} = -0.5$ and T=2; 10-1000 independent samples are used ref[6].



Figure 5. Variation of mean square displacement of the center of mass (R_c^2) of the membrane of size 64^2 and that of its center node (R_n^2) with the time step *t* on a 200^3 lattice at time steps with interactions $\varepsilon_{nn} = -1$ and $\varepsilon_{ns} = -0.5$ and T=2.50-100 independent samples are used.

Dispersion of the layer of platelets

Layer of clay platelets is common in clay nano-composites but their uniform dispersion in a composite matrix is highly desirable to achieve optimal performance. Thus, understanding the dispersion of clay platelets in crucial in understanding how to control their distribution – a very difficult issue to achieve in laboratory sample. This is also a challenging issue by computer simulations, as it takes enormous amount of time to exfoliate a stack of sheets with off-lattice computer simulation⁸. Therefore, an accelerated computational method particularly in modeling for sheets is essential – the coarse-grained model for sheet described above sets the basis for following investigation on dispersion and exfoliation of stacked platelets⁹. The underlying lattice structure provides the simplicity and computational efficiency while providing ample degrees of freedom for nodes to move and for sheet bonds to fluctuate. As a result we are able to carry out extensive computer simulations studies⁹ and draw meaningful conclusion on effects of temperature, platelet size, and quality of solvent on the exfoliation of stacked sheets. In the following we briefly describe the dispersion of platelets in (a) effective solvent media, (b) explicit solvent, and (c) polymer matrix.

(a) Effective solvent

We consider a layer of stacked sheets (four) with a small interstitial separation (4 lattice constant); the empty lattice sites represent effective solvent medium. We know that raising the temperature enhances the mobility. As a result the exfoliation of platelets is enhanced which can be verified a result d from the visualization⁹. A quantitative manifestation of the exfoliation can be verified from the changes in the transverse component (y-component normal to initial planar configuration of the layered sheets) of the radius of gyration (R_{gy}) among other quantities such as mobility. Figure 6 shows clearly that R_{gy} increases more rapidly on raising the temperature.



Figure 6. Transverse component of the mean square radius of gyration of each platelet in the stack of 4 at T = 2 and 10 with the node-solvent interaction ε = -1. ref. [9].

Since the relaxation of the sheet depends on its size, our simulations⁹ show that exfoliation is enhanced on decreasing the size of platelets. Quality of solvent plays a critical role in exfoliation of the sheets. Interaction between nodes and the solvent site control the quality of the solvent and can be varied, e.g., an attractive interaction $\varepsilon = -2$ to a repulsive interaction $\varepsilon = +2$ within a range of interaction *r*.

(b) Explicit solvent

Attempts are made to understand the dispersion of layered platelets in presence of solvent that can be identified explicitly. Although the effective solvent medium represented by empty lattice sites is effective and efficient, it is difficult to identify mobility, fluctuation, and correlations. Representing the solvent by particles (each with the same size as the node of the sheet) could be a viable approach. Unlike each empty lattice site representing the characteristics (interaction) of the fluid in effective solvent medium approach, only a fraction (p_w) of lattice sites are occupied by explicit solvent particles. A layer of platelets is immersed in lattice with solvent of concentration p_w . Interaction between solvent and nodes of the sheets can be treated in a similar fashion as described above with effective solvent medium. However, both solvent constituents and clay platelets may lead to their spatial distribution. In addition to dispersion of platelets, one can investigate the intercalation of the solvent and exfoliation of layered platelets can be examined as a function of temperature, quality of the solvent and its concentration; extensive computer simulations are performed¹⁰ to investigate these issues.

Figure 7 shows snapshots to illustrate the effect of the quality of solvent on the dispersion of the layered platelets. The attractive interaction between solvent and the sheets ($\varepsilon = -2$) at the temperature T = I leads to enormous intercalation of solvent particles between the interstitial platelet layers. The interstitial solvent particles tend to hold the platelets so strongly as to cease their dissociation. Reducing the interaction strength (($\varepsilon = -1$) reduces the layer cohesion and sheets begin to disperse.



Figure 7. Snaps of stacked platelets (each of size 16^2) after 10^6 time steps on 64^3 lattice with clay-solvent interaction $\varepsilon = -2$ (T = 1, left top, T=5 right top), $\varepsilon = -1$ (T=1, left bottom), $\varepsilon = 1$ (T=1, right bottom). Solvent particle concentration is 0.2. ref. [10].

Changing the quality of solvent to a repulsive interaction ($\varepsilon = 1, T=1$) causes the platelets to fully exfoliate. Dispersion of layered sheets is also enhanced by raising the temperature (T=5) even with attractive solvent ($\varepsilon = -2$). Note the contrast in the effect of solvent on dispersion from effective solvent media to explicit solvent. While the repulsive interaction reduces dispersion in effective medium (phobic effect), it enhances the dispersion with explicit solvents (philic effect) due to intercalation and stochastic pulling of sheets by solvent. The contrast may be somewhat misleading as the concentration of explicit solvent is much lower than that of the effective medium where each empty site acts as a solvent. However, one may still use the empty sites to represent an effective solvent in addition to particles and sheets with a three component systems – this increases our parameter space and could be interesting future projects. Efforts are made to quantify above observations by analyzing the density profiles and mobility of solvent particles and sheets, and their radius of gyration¹⁰. Figure 8 shows the density profile of solvent particles and sheets to show the effects of temperature on dispersion of both sheets and solvent particles. Clearly the cohesion and dispersion of sheets and solvent is verified at lower temperature (T=1). At higher temperatures, dispersion become dominant and the layering and structural patterns smeared out. The above conclusions are thus verified by other quantities as well¹⁰.



Figure 8. Transverse planar density (dx) of clay (filled) and solvent (open) particles versus x at T = 1-10 with clay-solvent interact $\varepsilon = 1, -1, -2$. A stack of four platelets each of size 162 is used on a lattice of size 643 each with 10 independent runs. Ref [10].

(c) Polymer chain matrix

The above studies are extended further by incorporating mobile polymer chains as the underlying matrix for the layered sheets to disperse in. The polymer chain is modeled by tethered nodes, a bond-fluctuating chain model. The parameters include polymer-clay interaction, concentration of polymers, their molecular weight, temperature, etc. We have carried out an initial investigation¹¹ on the effects of interaction and molecular weight on the dispersion of layered platelets. Figure 9 a snapshot summary to illustrate our observation.



Figure 9. Snapshots of the platelets in mobile polymer chain matrix. Top row is the initial configurations. The polymer chain length $L_c = 4$ (first column), 16 (second column), 64 (third column). Interaction between polymer and sheets $\varepsilon = -1$ (second row) and $\varepsilon = 1$ (third row). Sheets of size 16^2 are used on a 64^3 lattice at temperature T = 1 with the range of interaction $r^2 = 8$. Each configuration is final after 10^6 time steps with the polymer chain concentration $p_c = 0.1$.

Polymer chain matrix, though more complex than the effective medium and explicit particles matrix, provides a more realistic feature in modeling nano-clay composites. Not only is the polymer-clay interaction important in understanding the dispersion of layered sheets but also the heterogeneity caused by entanglement and relaxation of the host matrix. From the visual analysis of the snapshots, one can draw some preliminary conclusions as follows. The repulsive interaction between the polymer chains and the clay platelets enhances dispersion while the attractive interaction suppresses it. This is somewhat similar to the effect of explicit solvent particles matrix at least for the polymer matrix with low molecular weight. Entanglements of the polymer chain occur on increasing their molecular weight. The relaxation time for matrix to rearrange becomes relatively long with high molecular weight polymer chains – the local structures result in configuration in which platelets are embedded in effective caged network of mobile polymer chains. Thus, the entanglement of polymer chains at higher molecular weight suppresses dispersion – an entropic trapping. Interaction driven thermodynamics dominates in a polymer matrix with low molecular weights (as in explicit solvent particles matrix) where dispersion depends on the interaction (type and strength). The entropic trapping prevents exfoliation in a polymer matrix with large molecular weight. Understanding the dispersion

becomes very complex in the intermediate regime where interaction and entanglement are comparable.

Biopolymers

Hybrid systems are becoming increasingly important in designing materials with optimal characteristics with the continued growth in understanding the fundamental properties of bio-molecular and cellular systems. Bio-materials offer high potential to enhance the desirable characteristics. Proteins are some of the most versatile bio-polymer and can be incorporated in hybrid materials to achieve high performance. In this regard, some attempts¹² are made in modeling a polymer chain with specific sequence of amino-acid groups. Unlike a homo-polymer chain, each node is a coarse-grained description of amino-acid group in the bond-fluctuation model where all of the 20 amino acid residues are broadly divided into three groups, hydrophobic (*H*), polar (*P*), and electrostatic (*E*). Using a specific protein, aspartic acid protease (see Figure 10), we are able to describe conformations and dynamics in effective solvent matrix.



Figure 10. A coarse grained description of aspartic acid protease (1DIFA) with *H* (pink), *P* (gold), and *E* (blue). Ref. [12].

The dynamics of the aspartic acid protease chain is examined by analyzing the variation of the RMS displacement of the center node of the chain and that of its center of mass as presented in Figure 11. A systematic change in dynamics from short time to long time regime is clearly seen¹² on increasing the strength of the solvent interaction.



Figure 11. Variation of the RMS displacement of the center node (R_n , left) of aspartic acid chain and that of its center of mass (R_n , right) with the time step t for various solvent media characterized by the interaction strengths ($\epsilon = 0.0 - 3.2$). Lattice size 60³ with 50-2000 independent samples is used in each solvent medium. Ref. [12].

Conformation of the chain is also analyzed in detail, particularly the dependence of the radius of gyration on the solvent strength as presented in Figure 12. Chain expands or swells, i.e., the radius of gyration increases on increasing the solvent interaction strength. Further, the expansion is linear with the interaction strength in relatively weaker solvent interaction regime and nonlinear at higher interaction strengths. Insets in Figure 12 show the variation of the radius of gyration (R_g) of the chain and its end-to-end distance (R_e) in the long time regime in a relatively strong solvent medium. The oscillatory behavior of R_g and R_e seems to suggest that chains contract and expand (a earth-worm motion) over the time scales that depend on the quality of the solvent. These studies provide an insight into how to incorporate a protein chain in composite and investigate its interaction with the clay surface.



Figure 12. Equilibrium radius of gyration (R_{gs}) versus interaction strength. Inset shows the variation of the radius of gyration (R_g) of the aspartic acid chain and its end-to-end distance (R_e) in the long time regime for the solvent interaction ($\varepsilon = 3.2$). Ref. [12].

Ongoing efforts and outlook

Although this is a report at the end of a productive research under-taking, it stimulates enormous amount of important issues to probe by extending these investigations. Some of these are pointed below briefly.

- 1. Effect of rigidity of the platelet on the conformation and dynamics of sheet, and dispersion of layered platelets.
- 2. Effective solvent is an efficient and effective approach but exhibits opposite effects of explicit solvent particles matrix. Studying the dispersion of layered platelets in effective solvent and explicit solvent particles (combined), a three component systems would be interesting.
- 3. On a long term it would be worth exploring the dispersion and exfoliation of layered platelets and intercalation of constituents of the multi-component host matrix, e.g., particles, polymer chains, effective solvent matrix.
- 4. Incorporating protein chains in these systems would be highly desirable.

References

- 1. Polymer Nanocomposites: Synthesis, Characterization, and Modeling; Ramanan Krishnamoorti and Richard A. Vaia, Eds.; American Chemical Society: Washington, DC, ACS symposium Series **2002**, 804.
- 2. *Monte Carlo and Molecular Dynamics Simulations in Polymer Science*; K. Binder, Ed.; Oxford University Press: New York, **1995**.
- 3. M. Rubinstein and R.H. Colby, *Polymer Physics* (Oxford University Press, 2003).
- 4. R.B. Pandey, K.L. Anderson, H. Hendrik, and B.L. Farmer, *J. Polym Sci Part B: Polym Phys* **2005**, *43*, 1041.
- 5. R.B. Pandey, K.L. Anderson, and B.L. Farmer, *J. Polym Sci Part B: Polym Phys* 2005, 43, 3478.
- 6. R.B. Pandey, K.L. Anderson, and B.L. Farmer, *J. Polym Sci Part B: Polym Phys* **2006**, 44, 2512.
- 7. R.B. Pandey, K.L. Anderson, and B.L. Farmer, *Phys. Rev. E* 2007, 75, 061913.
- 8. A. Sinsawa, K.L. Anderson, R.A. Vaia, and B.L. Farmer, *J. Polym Sci Part B: Polym Phys* **2003**, 41, 3272.
- 9. R.B. Pandey, K.L. Anderson, and B.L. Farmer, *J. Polym Sci Part B: Polym Phys* 2006, 44, 3580.
- 10. R.B. Pandey and B.L. Farmer, Macomol. Theor. Sim. (2008, in press).
- 11. R.B. Pandey and B.L. Farmer, presentation at the APS meeting March 10-14, **2008**; a manuscript is planed.
- 12. R.B. Pandey and B.L. Farmer, Phys. Rev. E (2008, in press).