REPORT DOCUMENTATION PAGE		Form Approved OMB No. 0704-0188		
Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing the burden, to Department of Defense, Washington Headquarters Services, Directorate for Information Operations and Reports (0704-0188), 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to any penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number. PLEASE DO NOT RETURN YOUR FORM TO THE ABOVE ADDRESS.				
1. REPORT DATE (DD-MM-YYYY)	2. REPORT TYPE Final Report		3. DATES COVERED (From – To) 1 April 2007 – 01 April 2008	
4. TITLE AND SUBTITLE		5a. CO	NTRACT NUMBER	
Lifetime of Sodium Beta-alumina	Membranes in Molten Sodium Hydroxide	FA8655	j-07-1-3064	
		5b. GRANT NUMBER		
		Grant 07-3064		
		5c. PROGRAM ELEMENT NUMBER		
		61102F		
6. AUTHOR(S)		5d. PROJECT NUMBER		
Dr. Gudmundur Gunnarsson				
		5d. TASK NUMBER		
		5e. WORK UNIT NUMBER		
7. PERFORMING ORGANIZATION NAME	S) AND ADDRESS(ES)	1	8. PERFORMING ORGANIZATION	
Technological Institute of Iceland Keldnaholt Reykjavik IS-112 Iceland			N/A	
9. SPONSORING/MONITORING AGENCY	NAME(S) AND ADDRESS(ES)		10. SPONSOR/MONITOR'S ACRONYM(S)	
EOARD				
Unit 4515 BOX 14				
APO AE 09421			11. SPONSOR/MONITOR'S REPORT NUMBER(S) Grant 07-3064	
12. DISTRIBUTION/AVAILABILITY STATE	MENT			
Approved for public release; distribution is unlimited.				
13. SUPPLEMENTARY NOTES				
14. ABSTRACT				
Summary: Sodium metal can be made by ele are some uncertainties about the lifetime of the project is to address these uncertainties and Electrolysis cells were designed, but it proved It therefore turned out to be impossible to do molten sodium hydroxide for up to 149 day. No or up to 0,33% in 41 days. No change in the (Scanning electron microscopy) revealed that in freeing of grains (1 to 3 micron diameter) for	ectrolysis of molten sodium hydroxide in sodium ne sodium beta-alumina membranes in contac to study if the properties of the membrane deg d impossible to test them because the potentio electrolysis tests with this experimental set-up Aass loss was only 0,15 % in the first 108 days phase composition of the material was observed t the molten sodium hydroxide preferably disso rom the bulk of the material.	m beta-alu t with molte rade upon stat that w . Instead, s s, but in the ed in the 1- plved mate	mina membrane electrolysis cells. However, there en sodium hydroxide. The main objective of this long term contact with molten sodium hydroxide. as to be used was designed for low current density. samples of sodium beta-alumina disk were aged in e next 41 days mass loss accelerated considerably, 49 days. Investigation of aged samples with SEM rial at grain boundaries, which most likely resulted	
Conclusions 1. Sodium beta-alumina membranes were investigated in an SEM after each period. Ra %/day. 2. XRD analysis shows that aging of the sam 3. Examination in an SEM shows that grain s 4. Ageing in molten sodium hydroxide change - First 108 days: Dissolution of material from - After 108 days: Dissolution of material from %/day. 5. In an electrolysis cell for production of sod	aged in molten NaOH at 340 C for 38, 10 the of mass loss increases significantly in the p ples in the test does not change the structure of ize of the sodium beta-alumina is 1-3 microns. as the surface structure of the samples. The m surface of grains. Mass loss is slow, or 1-2 x10 or grain boundaries, leading to freeing of single ium metal, by electrolysis of sodium hydroxide	08 and 14 beriod after of the sodiu ain mecha 0^-3 %/day grains from a it can be	9 days respectively. Samples were weighed and r 108 days, or from 1 to 2 x10^-3 %/day to 8 x10^-3 um beat-alumina samples. nisms seem to be as follows: m the surface. Mass loss is more rapid, or 8 x10^-3	
will lose about 7.3 % of its mass in 5 years or 14,7% in 10 years, assuming that long term corrosion rates are the same as measured in this project. 6. In an economic analysis of a process for production of sodium metal by electrolysis of sodium hydroxide in sodium beta-alumina electrolysis cells it was assumed that the cells would last for 2 years. The results obtained in this project indicate that corrosion of sodium beta-alumina will not be an obstruction when designing a cell with a minimum lifetime of 2 years.				

15. SUBJECT TERMS EOARD, energy storage materials, Fuel Cell	IS		
16. SECURITY CLASSIFICATION OF: a. REPORT b. ABSTRACT c. THIS PAGE	17. LIMITATION OF ABSTRACT	18, NUMBER OF PAGES	19a. NAME OF RESPONSIBLE PERSON SCOTT DUDLEY, Lt Col, USAF
UNCLAS UNCLAS UNCLAS	0, ut		19b. TELEPHONE NUMBER (Include area code) +44 (0)1895 616162

Standard Form 298 (Rev. 8/98) Prescribed by ANSI Std. Z39-18

NMÍ 08-16 8HK07118

Lifetime of Sodium B"- Alumina Membranes in Molten Sodium Hydroxide

Final Report

Project Supported by the USAF European Office of Aerospace Research and Development

Award No. FA8655-07-1-3064

July 2008

Gudmundur Gunnarsson Birgir Johannesson

Innovation Center Iceland Keldnaholt IS-112 Reykjavik Iceland



Table of Contents

Summary	2
1 Introduction	1
2 Methods. Assumptions and Procedures.	2
2.1 Design and construction of electrolysis cells	2
2.2 Ageing of membranes in molten sodium hydroxide	2
3 Results and Discussion	4
4 Conclusions	12
5 References	

List of Figures

2
ļ
;
í
1
;
)
)

List of Tables

Table 1. Mass loss of sodium $\boldsymbol{\beta}$ "-alumina disks after ageing in molten sodium hydroxide at 340°C for differenttimes. Standard deviation is given in parenthesis.4

Summary

Sodium metal can be made by electrolysis of molten sodium hydroxide in sodium β "-alumina membrane electrolysis cells. However, there are some uncertainties about the lifetime of the sodium β "-alumina membranes in contact with molten sodium hydroxide. The main objective of this project is to address these uncertainties and to study if the properties of the membrane degrade upon long term contact with molten sodium hydroxide. Electrolysis cells were designed, but it proved impossible to test them because the potentiostat that was to be used was designed for low current density. It therefore turned out to be impossible to do electrolysis tests with this experimental set-up. Instead, samples of sodium β "-alumina disk were aged in molten sodium hydroxide for up to 149 day. Mass loss was only 0,15 % in the first 108 days, but in the next 41 days mass loss accelerated considerably, or up to 0,33% in 41 days. No change in the phase composition of the material was observed in the 149 days. Investigation of aged samples with SEM (Scanning electron microscopy) revealed that the molten sodium hydroxide preferably dissolved material at grain boundaries, which most likely resulted in freeing of grains (1 – 3 µm diameter) from the bulk of the material.

1 Introduction

Sodium borohydride (SBH) is now widely used as a reducing agent in the chemical industry. SBH can also be used to produce hydrogen for fuel cells. For that application it has the advantage of generating humidified pure hydrogen ready for use in fuel cells. The US based company Millennium Cell (http://www.millenniumcell.com/) has invented and developed the so-called "Hydrogen in Demand Technology", generating hydrogen from sodium borohydride. The most promising applications of this technology are in portable applications using fuel cell technology instead of battery, both for military and civil use. A significant market for sodium borohydride will therefore be generated with increased use of this technology. The single most important barrier to overcome is the price of sodium borohydride. Therefore low cost sodium borohydride from Iceland, where advantage is taken of relatively inexpensive electric energy and geothermal steam, may indeed support such a development. The results of a previous cooperation between IceTec, Icelandic New Energy and Millennium Cell showed that the cost of producing sodium borohydride in Iceland, using a specially developed production process, is highly competitive compared with the world market price of sodium borohydride (Gunnarsson 2004; Ingólfsson 2004). In this process, sodium metal is reacted with hydrogen to yield sodium hydride, which is then reacted with trimethoxyborane to yield SBH. The sodium hydroxide obtained is recycled and used to make sodium metal in sodium β "-alumina membranes electrolysis cells. However, there are still some technical uncertainties regarding this specially developed process and further investigation and research is therefore needed. The largest challenge, and the single most technical uncertainty in this process, concerns the production of sodium metal from sodium hydroxide, using sodium β "-alumina membranes electrolysis cells. The main uncertainty is about the lifetime of sodium β "-alumina membranes in contact with the molten sodium hydroxide. The main objective of this project is to address this uncertainty and to study if long time contact of sodium β"-alumina with molten sodium hydroxide at 330 - 350 °C will affect properties of sodium β "-alumina membranes, particularly the sodium ion conductivity of the sodium β "-alumina.

In this progress report we describe work which took place in the period April 2007 to June 2008.

This project is supported by USAF European Office of Aerospace Research and Development, under award No. FA8655-07-1-3064.

2 Methods, Assumptions and Procedures

In this section, the experimental procedures used in the project are described.

2.1 Design and construction of electrolysis cells

Sodium β "-alumina membranes were purchased from Ionotec ltd. (www.ionotec.com). These were small membranes disks (20 mm in diameter and 2 mm thick) and tubes (length = 70 mm, internal diameter 6.5 mm, wall thickness 1.5 mm). All parts coming into contact with the molten sodium hydroxide should preferably be made of pure nickel. Therefore, nickel beakers, closed end tubes for thermocouples tubes, wires etc., were ordered. Assemblies of the cathode and sodium β "-alumina tubes were designed and made, see Figure 1.



Figure 1. Assemblies of nickel anodes and sodium β "-alumina tubes in the course of preparation. The sodiumalumina tubes are 70mm long.

Equipment for electrochemical measurements was set up and initial measurement made on some test specimens. Electrochemical measurements were to be carried out with a Gamry Instruments PC4/300 potentiostat for electrochemical impedance spectroscopy. The maximum current for that instrument is 300 mA. In the first experiments carried out with the assemblies shown in Figure 1 it became clear that as the test developed, the measured current always exceeded the maximum of 300 mA. It was therefore impossible to obtain meaningful data with this experimental set-up. The tests were thus abandoned.

2.2 Ageing of membranes in molten sodium hydroxide

Disk made of sodium β "-alumina (diameter 20 mm, thickness 2 mm) were used for ageing tests (delivered by Ionotec Ltd). The disks were kept in an oven at 105 °C overnight, then removed from the oven and cooled in nitrogen atmosphere. The mass of the disks was then measured. Nine disks were suspended in nickel wires and placed in molten sodium hydroxide at 340°C. Three disks were then removed from the molten sodium hydroxide after 38 day, three more after 108 day and the last three after 149 days. The disks were washed with distilled water after removal from the molten sodium hydroxide until the pH of the wash

water was down to 8-9. Then the disks were dried in an oven at 105 °C overnight and cooled in nitrogen atmosphere. The mass of the disks was then measured.

Disks, both aged and as received were studied with scanning electron microscopy (SEM) and as well as with X-ray diffraction (XRD).

3 Results and Discussion

The mass loss of the disks after ageing for up to 149 days is shown in Table 1.

Table 1. Mass loss of sodium β "-alumina disks after ageing in molten sodium hydroxide at 340°C for different times. Standard deviation is given in parenthesis.

Ageing time of disks (days)	Cumulative	Mass loss per day (%/day)
	Mass loss (%)	
0 - 38	0,072 (0,005)	1,89.10-3
38 - 108	0,15 (0,01)	1,11.10-3
108 - 149	0,48 (0,05)	8,05·10 ⁻³



Figure 2. Cumulative mass loss of specimens in NaOH at 340°C.

Figure 2 shows the cumulative mass loss as a function of days in NaOH at 340°C. A significant acceleration of mass loss is seen after 108 days. Figure 3 shows the mass loss per day for the three periods, 1-38, 38-108 and 108-149 days. It is clear that mass loss accelerates considerably in the third period, after 108 days.



Figure 3. Mass loss per day for the three periods between measurements of mass of the specimens.

XRD analysis was done on the material before, during and after the aging tests. The results are shown in Figure 4.



Figure 4. XRD spectra of sodium β "-alumina (labelled Alumina – Na1.67MgO0.67Al10.33O17) disks after ageing in molten sodium hydroxide at 340°C for different times. #10 is as received sample sample, #1, #4 and #7 are aged 38,108 and 149 days respectively.

The XRD analysis shows that the disks are mainly made of sodium β "-alumina, and that they contain a small percentage of sodium β -alumina (diaoyudaoite) as is often found in sodium β "-alumina (Stevens 1991). The results of the XRD analysis show that aging of the samples in the test does not change the structure of the sodium β "-alumina samples.

Samples were also investigated with a Scanning Electron Microscope. A selection of images is shown in Figures 5 to 8.

In the as received sample, see Figure 5, some small grains are visible on the surface as well as some porosity. In the micrograph at higher magnification (Figure 3b) it is possible to see some grain boundaries. In sodium β "-alumina, porosity is most often found at grain corners and the grain size is often $1 - 2 \mu m$ (Stevens 1991).

After ageing for 38 days in molten sodium hydroxide the structure of the surface changed considerably, see Figure 6. It seems that some material in between small grains, that are only fraction of a μ m, has been etched away. Some larger grains, $1 - 3 \mu$ m in diameter, are also seen. The small grains seem to be a part of the larger grains. It is also noteworthy that grain boundaries between the 1- 3 μ m grains can now be more clearly seen than in the as received sample, the molten sodium hydroxide seems to preferentially dissolve material at grain boundaries.

The dissolution of material from grain boundaries is more clearly seen in samples aged for 108 days, see Figure 7, and especially for 149 days, see Figure 8. In the samples aged for 149 days it is clearly seen that the sodium β "-alumina disks received are made of material with about $1 - 3 \mu m$ grain size.

The thickness of the disks is 2 mm. A mass loss of 0,1% corresponds to a thinning of the disks by 2 μ m or 1 μ m on either side of the disks, assuming that the mass loss is evenly distributed over the surface of the disks and that the effect of the edges is neglected. The mass loss in the period between 108 and 149 days is 0,33% corresponding to a thinning of the disk by 6,6 μ m or 3,3 μ m on either side. Therefore in the period between 108 and 149 days the disks have lost about 1- 2 layers of sodium β "-alumina grains from the surface of the disks.

Based on the above observation, the corrosion of the sodium β "-alumina in molten sodium hydroxide seems to proceed according to the following processes

- Material is dissolved from the surface of the $1 3 \mu m$ grains. The mass loss associated with this process is relatively small and it can be estimated to be of the order seen in the first 108 days.
- Material is dissolved from grain boundaries, eventually resulting in "freeing" of single grains from the surface. This process seems to speed up the corrosion of the sodium β"-alumina.

When trying to estimate the lifetime of the sodium β "-alumina membranes, in the light of these results, it seems appropriate to assume that the corrosion rate is at least as high as in the period between 108 and 149 days (8,05 \cdot 10^{-3} % per day), and that the period up to about 109 days could be regarded as an incubation time.



Figure 5. Scanning electron micrographs of as received sample at a) 5.000x and b) 50.000x magnification.



Figure 6. Scanning electron micrographs of sample aged 38 days at a) 5.000x and b) 50.000x magnification.



Figure 7. Scanning electron micrographs of sample aged 108 days at a) 5.000x and b) 50.000x magnification.



Figure 8. Scanning electron micrographs of sample aged 149 days at a) 5.000x and b) 50.000x magnification.

In an electrolysis cell for production of sodium metal by electrolysis of sodium hydroxide, the sodium β "-alumina is in contact with molten sodium hydroxide on one side of the membrane and with molten sodium on the other side of the membrane. If it is assumed that the membrane does not corrode on the sodium metal side, and that the long term corrosion rates are the same as measured in the last 41 days. The results obtained here show that the sodium β "-alumina membrane will lose 7,3 % of its mass in 5 years and 14,7 % of its mass in 10 years. Although the mass loss could be considerably higher, the actual lifetime is expected to be considerably longer than assumed in the economic evaluation of the process (Ingólfsson 2004). Here it was found that the cost of sodium metal could be lower than 1 \$/kg for a current density of 0,2 A/cm² if the lifetime of the cells was longer than 2 years (Ingólfsson 2004). The results obtained in this project indicate that corrosion of sodium β "-alumina will not be an obstruction when designing a cell with a minimum lifetime of 2 years.

4 Conclusions

- 1. Sodium β "-alumina membranes were aged in molten NaOH at 340°C for 38, 108 and 149 days respectively. Samples were weighed and investigated in an SEM after each period. Rate of mass loss increases significantly in the period after 108 days, or from $1-2\cdot10^{-3}$ %/day to $8\cdot10^{-3}$ %/day.
- 2. XRD analysis shows that aging of the samples in the test does not change the structure of the sodium β "-alumina samples.
- 3. Examination in an SEM shows that grain size of the sodium β "-alumina is 1-3 μ m.
- 4. Ageing in molten sodium hydroxide changes the surface structure of the samples. The main mechanisms seem to be as follows:
 - First 108 days: Dissolution of material from surface of grains. Mass loss is slow, or 1-2.10⁻³ %/day.
 - After 108 days: Dissolution of material from grain boundaries, leading to freeing of single grains from the surface. Mass loss is more rapid, or 8.10⁻³ %/day.
- 5. In an electrolysis cell for production of sodium metal, by electrolysis of sodium hydroxide, it can be expected that the sodium β "-alumina membrane will lose about 7.3 % of its mass in 5 years or 14,7% in 10 years, assuming that long term corrosion rates are the same as measured in this project.
- 6. In an economic analysis of a process for production of sodium metal by electrolysis of sodium hydroxide in sodium β "-alumina electrolysis cells it was assumed that the cells would last for 2 years. The results obtained in this project indicate that corrosion of sodium β "-alumina will not be an obstruction when designing a cell with a minimum lifetime of 2 years.

5 References

Gunnarsson, G. (2004). Production of sodium borohydride from sodium borate. Process description., Technological Institute of Iceland: 17.

Ingólfsson, H. P. (2004). Production of sodium borohydride from sodium borate. Economic Analysis., Technological Institute of Iceland.

Stevens, R. (1991). Beta-Alumina. <u>Concise Encyclopedia of Advanced Ceramic Materials</u>. Ed. R. J. Brook. Oxford, Peragamon Press: 32-35.

List of symbols, Abbreviations and Acronyms

XRD:	X-Ray Diffraction
SEM:	Scanning Electron Microscopy
SBH:	Sodium Borohydrate
US:	United States
USAF:	United States Air Force
NaOH:	Sodium Hydroxide
IceTec:	Technological Institute of Iceland, now Innovation center
	Iceland.