

# AFRL-RX-WP-TP-2012-0351

## STOCHASTIC-INTEGRAL MODELS FOR PROPAGATION-OF-UNCERTAINTY PROBLEMS IN NONDESTRUCTIVE EVALUATION (PREPRINT)

Jeremy Knopp and Mark P. Blodgett Materials State Awareness & Supportability Branch Structural Materials Division

Elias H. Sabbagh, R. Kim Murphy, Harold A. Sabbagh Victor Technologies, LLC

John C. Aldrin Computational Tools

JULY 2012 Interim

Approved for public release; distribution unlimited.

See additional restrictions described on inside pages

**STINFO COPY** 

AIR FORCE RESEARCH LABORATORY MATERIALS AND MANUFACTURING DIRECTORATE WRIGHT-PATTERSON AIR FORCE BASE, OH 45433-7750 AIR FORCE MATERIEL COMMAND UNITED STATES AIR FORCE

REPORT DOCUMENTATION PAGE							Form Approved OMB No. 0704-0188	
The public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, s sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burder information, including suggestions for reducing this burden, to Department of Defense, Washington Headquarters Services, Directorate for Information Davis Highway, Suite 1204, Arlington, VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall collection of information if it does not display a currently valid OMB control number. <b>PLEASE DO NOT RETURN YOUR FORM TO THE ABOVE ADDF</b>							en estimate or any other aspect of this collection of Operations and Reports (0704-0188), 1215 Jefferson I be subject to any penalty for failing to comply with a	
1. REPORT DATE (DD-MM-YY)2. REPORT TYPE3. DATES						S COVERED (From - To)		
July 2012 Technical Paper 1						1 Jun	une 2012 – 1 July 2012	
4. TITLE AND SUBTITLE							5a. CONTRACT NUMBER	
STOCHASTIC-INTEGRAL MODELS FOR PROPAGATION-OF-UNCERTAINTY							In-house	
PROBLEMS IN NONDESTRUCTIVE EVALUATION (PREPRINT)							5b. GRANT NUMBER	
							5c. PROGRAM ELEMENT NUMBER 65502F	
6. AUTHOR(S)							5d. PROJECT NUMBER	
Jeremy Knopp and Mark P. Blodgett (AFRL/RXCA)							3005	
Elias H. Sabbagh, R. Kim Murphy, Harold A. Sabbagh (Victor Technologies, LLC)							5e. TASK NUMBER	
John C. Aldrin (Computational Tools)							RX	
							5f. WORK UNIT NUMBER	
							LP111200	
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES)							8. PERFORMING ORGANIZATION REPORT NUMBER	
Materials State Awareness & Supportability Branch							AFRL-RX-WP-TP-2012-0351	
Structural Materials Division								
Air Force Research Laboratory, Materials and Manufacturing Directorate								
Wright-Patterson Air Force Base, OH 45433-7750								
Air Force Materiel Command, United States Air Force								
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)							10. SPONSORING/MONITORING	
							AGENCY ACRONYM(S)	
Air Force Research Laboratory								
Materials and Manufacturing Directorate							AFRL/RXCA	
Wright-Patterson Air Force Base, OH 45433-7750						11. SPONSORING/MONITORING AGENCY REPORT NUMBER(S)		
Air Force Materiel Command							AFRL-RX-WP-TP-2012-0351	
United States Air Force								
12. DISTRIBUTION/AVAILABILITY STATEMENT Approved for public release; distribution unlimited. Preprint to be submitted to Applied Computational Electromagnetic Society.								
13. SUPPLEMENTARY NOTES								
The U.S. Government is joint author of this work and has the right to use, modify, reproduce, release, perform, display,								
or disclose the work. PA Case Number and clearance date: 88ABW-2012-1287, 7 March 2012. This document contains								
color.								
14. ABSTRACT								
Generalized polynomical chaos (gPC) and the probabilistic collocation method (PCM) are finding considerable								
application to problems of interest to engineers in which random parameters are an essential feature of the mathematical								
model. So far the applications have been mainly to stochastic partial differential equations, but we extend the method to								
volume-integral equations, which have met great success in electromagnetic nondestructive evaluation (NDE), especially								
with eddy-currents. The problems of main interest to the NDE community in this connection are concerned with the								
issue of 'propagation of uncertainty' when the relevant parameters are not well characterized, or are known simply as								
random variables. We demonstrate the ideas by considering a metallic surface that has undergone a shot-peening								
treatment to reduce residual stresses, and has, therefore, become a random conductivity field.								
15. SUBJECT TERMS								
volume-integral equations, electromagnetic nondestructive evaluation, generalized polynomial chaos, probabilistic collocation method								
16. SECURITY CLASSIFICATION OF: 17. LIMITATION NUMBER OF 19a. NAME OF RESPONSIBLE PERSON (Monitor)								
a. REFORT D. ABSTRACT C. THIS FAGE ABSTRACT.								
					N/A			

### Stochastic-Integral Models for Propagation-of-Uncertainty Problems in Nondestructive Evaluation

Elias H. Sabbagh, R. Kim Murphy, Harold A. Sabbagh

ehs@sabbagh.com, kimmurphy1@aristotle.net, has@sabbagh.com

Victor Technologies, LLC PO Box 7706 Bloomington, IN 47407-7706 USA

John C. Aldrin aldrin@computationaltools.com

> Computational Tools Gurnee, IL 60031 USA

Jeremy Knopp jeremy.knopp@wpafb.af.mil

Air Force Research Laboratory (AFRL/RXLP) Wright-Patterson AFB, OH 45433-7817 USA

Mark P. Blodgett

mark.blodgett@wpafb.af.mil

Air Force Research Laboratory (AFRL/RXLP) Wright-Patterson AFB, OH 45433-7817 USA

**Abstract:** Generalized polynomical chaos (gPC) and the probabilistic collocation method (PCM) are finding considerable application to problems of interest to engineers in which random parameters are an essential feature of the mathematical model. So far the applications have been mainly to stochastic partial differential equations, but we extend the method to volume-integral equations, which have met great success in electromagnetic nondestructive evaluation (NDE), especially with eddy-currents. The problems of main interest to the NDE community in this connection are concerned with the issue of 'propagation of uncertainty' when the relevant parameters are not well characterized, or are known simply as random variables. We demonstrate the ideas by considering a metallic surface that has undergone a shot-peening treatment to reduce residual stresses, and has, therefore, become a random conductivity field.

**Keywords:** volume-integral equations, electromagnetic nondestructive evaluation, generalized polynomial chaos, probabilistic collocation method

#### 1. Introduction

Critical structural components are often treated by shot-peening or low-plasticity burnishing to reduce residual tensile stresses. This process often leaves the surface of the component rough with a profile that can only be defined as a random process. It is necessary to characterize the surface, and the most common method is through the use of eddy-current nondestructive evaluation (NDE). This method measures the conductivity variation, which, because it simulates the rough surface, becomes itself a random field. This paper describes an approach to modeling electromagnetic interactions with a random conductivity field in the context of NDE. The computational engine is based on stochastic volume-integral equations.

#### 2. Volume-Integral Equations

We have introduced the notion of volume-integral equations and their application in eddy-current NDE in a recent series of papers [1-3]. We will remind the reader that the essential feature, for our purpose, is that the 'anomalous region' (the 'flaw') is decomposed into a regular grid of voxels, each of which has uniform conductivity. Because the surface that this grid simulates is random, so, too, is the conductivity variation from voxel to voxel. In other words we have defined a random conductivity field, with each voxel conductivity being a random variable. The discretization process, of course, transforms an infinite-dimensional field (the 'true surface') into a finite-dimensional field, but still with a very large number of random variables. It is this feature that presents a numerical challenge in modeling stochastic integral equations.

#### 3. Theoretical Background

If there are N voxels, then the impedance computed by the volume-integral equation can be written  $Z(l, \sigma_1, \dots, \sigma_N)$ , where l is the position of the probe coil, and the average value of the impedance can be written

$$\int_{-\infty}^{\infty} \cdots \int_{-\infty}^{\infty} Z(l, \sigma_1, \cdots, \sigma_N) p(\sigma_1, \cdots, \sigma_N) d\sigma_1 \cdots d\sigma_N , \qquad (1)$$

where  $p(\sigma_1, \dots, \sigma_N)$  is the joint probability density of the conductivity field. N will generally be large, so we must consider a mapping into a lower-dimensional random space. One such mapping is the Karhunen-Loève expansion [4,5]. The discrete version of the K-L expansion states that every random vector, **V**, has a decomposition

$$\mathbf{V} = \sum_{n=1}^{N} \lambda_n \xi_n \mathbf{v}_n , \qquad (2)$$

where  $\{\lambda_n\}$  and  $\{\mathbf{v}_n\}$  are the eigenpair solutions of the covariance matrix of  $\mathbf{V}$ , and  $\{\xi_n\}$  are uncorrelated random variables,  $E\xi_m\xi_n^* = \delta_{mn}$ . It is hoped that this expansion converges after Mterms, where  $M \ll N$  in (1). The  $\{\xi_n\}_{n=1}^M$  then become the new random variables in expressions such as (1).

We will apply the K-L expansion to the double-exponential measured correlation function,  $C(x, x') = \exp(-|x - x'|/L)$ , which arises from shot-peened copper for two different peening intensities [6]. The discrete covariance matrix,  $G_{mn}$ , for this function is given by [7]:

$$G_{mn} = -2L^{2} \left( 1 - e^{-\delta/L} - \delta/L \right), \qquad m = n$$
  
=  $-2L^{2} e^{-(n-m)\delta/L} \left( 1 - \cosh(\delta/L) \right), \quad m < n$   
=  $-2L^{2} e^{-(m-n)\delta/L} \left( 1 - \cosh(\delta/L) \right), \quad m > n$ , (3)

where L is the correlation length of the process, and  $\delta$  is the length of a one-dimensional cell.

Figure 1 shows the normalized eigenvalue spectrum for a  $32 \times 32$  matrix for three values of the ratio,  $L/\delta$ , and sample functions for the anomalous conductivity profiles are shown in Figures 2-4 for these same values of  $L/\delta$ . Sample functions for the case,  $L/\delta = 0.1$ , are shown in Figure 2, while Figure 3 shows three sample functions for the conductivity profile when  $L/\delta = 1$ , and Figure 4 shows three sample functions for the conductivity profile when  $L/\delta = 3$ .



Figure 1: Normalized eigenvalue spectrum for the double-exponential covariance function for three values of the critical ratio,  $L/\delta$ .



Figure 2: Three sample functions for the conductivity profile when  $L/\delta = 0.1$ . These functions are the departure from the mean value of  $\sigma_{\text{host}} = 3.02 \times 10^5$  S/m. We assume a uniform probability density function, centered at zero and with variance = 1, for the random variables,  $\{\xi_i\}$ , in the Karhunen-Loève expansion.



Figure 3: Three sample functions for the conductivity profile when  $L/\delta = 1$ . These functions are the departure from the mean value of  $\sigma_{\text{host}} = 3.02 \times 10^5$  S/m. We assume a uniform probability density function, centered at zero and with variance = 1, for the random variables,  $\{\xi_i\}$ , in the Karhunen-Loève expansion.



Figure 4: Three sample functions for the conductivity profile when  $L/\delta = 3$ . These functions are the departure from the mean value of  $\sigma_{\text{host}} = 3.02 \times 10^5$  S/m. We assume a uniform probability density function, centered at zero and with variance = 1, for the random variables,  $\{\xi_i\}$ , in the Karhunen-Loève expansion.

#### 4. gPC and PCM

We will assume that the new random variables,  $\{\xi_1, \dots, \xi_M\}$ , that are the result of the K-L expansion, are independent, identically distributed random variables (iid), with the common density function,  $\pi(\xi)$ . The generalized polynomial chaos (gPC) expansion of degree N for  $Z(l, \xi_1, \dots, \xi_M)$  is given by [5]:

$$Z(l,\xi_1,\cdots,\xi_M) = \sum_{0 \le |\mathbf{i}| \le N} \hat{Z}_{i_1}(l) \cdots \hat{Z}_{i_M} \phi_{i_1}(\xi_1) \cdots \phi_{i_M}(\xi_M) , \qquad (4)$$

where  $|\mathbf{i}| = i_1 + \cdots + i_M$  and  $\{\phi_k(\xi_i)\}_{k=0}^N$  is the set of univariate gPC basis functions in  $\xi_i$  of degree  $0 \le k \le N$ . They are orthogonal polynomials associated with the density function,  $\pi(\xi)$ , in the sense that

$$E[\phi_m(\xi_i)\phi_n(\xi_i)] = \int \phi_m(\xi)\phi_n(\xi)\pi(\xi)d\xi = \delta_{mn}\gamma_m, \ 0 \le m, n \le N ,$$
(5)

where  $\gamma_m$  is a normalizing constant.

With this expansion in hand, we can calculate various statistical properties of  $Z(l,\xi_1,\dots,\xi_M)$ [5]. For example,  $[\hat{Z}_0(l)]^M$  is the average value of Z, and the variance and covariance are given by:

$$\operatorname{Var}[Z(l,\xi_{1},\cdots,\xi_{M})] = \sum_{0<|i|\leq N} \gamma_{i_{1}}\cdots\gamma_{i_{M}}\hat{Z}_{i_{1}}^{2}(l_{1})\cdots\hat{Z}_{i_{M}}^{2}(l_{1}) \\ C_{Z}(l_{1},l_{2}) = \sum_{0<|i|\leq N} \gamma_{i_{1}}\cdots\gamma_{i_{M}}\hat{Z}_{i_{1}}(l_{1})\cdots\hat{Z}_{i_{M}}(l_{1})\hat{Z}_{i_{1}}(l_{2})\cdots\hat{Z}_{i_{M}}(l_{2}) , \qquad (6)$$

where the sums exclude |i| = 0.

#### 5. HDMR and ANOVA

High-dimensional model representation (HDMR) and analysis of variance (ANOVA) seek to reduce the complexity of problems with a large number of dimensions, and are the subject of considerable contemporary research in computational methods [8-11].

Instead of the gPC expansion of (4), we consider an ANOVA decomposition as (we suppress the scan variable, l, to simplify notation):

$$Z(\xi_1, \dots, \xi_M) = Z_0 + \sum_{j_1}^M Z_{j_1}(\xi_{j_1}) + \sum_{j_1 < j_2}^M Z_{j_1, j_2}(\xi_{j_1}, \xi_{j_2}) + \sum_{j_1 < j_2 < j_3} Z_{j_1, j_2, j_3}(\xi_{j_1}, \xi_{j_2}, \xi_{j_3}) + \dots + Z_{j_1, \dots, j_M}(\xi_{j_1}, \dots, \xi_{j_M}) ,$$
(7)

where  $Z_0$  is a constant function, the  $\{Z_{j_1}\}$  are one-dimensional functions,  $\{Z_{j_1,j_2}\}$  are two-dimensional functions, and so on, yielding  $2^M$  different terms [9]. The various functions are orthogonal to each other (stochastically uncorrelated), which means that  $Z_0$  is the mean value of Z, and the remaining terms are partial variances, whose sum is the total variance of Z.

ANOVA and PCM will be used to compute the stochastic response of the volume-integral equation given random parameters of the anomalous region that evolves from shot-peening or other surface treatment methods. This response will be expressed in terms of average values and variances, or even probability densities. These will have further ramifications in computing probability-of-detection (POD) for various testing setups, as well as inverting measured data to estimate flaw parameters, etc.

#### References

- H. A. Sabbagh, R. K. Murphy, E. H. Sabbagh, J. C. Aldrin, J. Knopp and M. Blodgett, "Computational Electromagnetics and Model-Based Inversion: A Modern Paradigm for Eddy-Current Nondestructive Evaluation," *ACES Journal*, Vol. 24, No. 6, December 2009, pp. 533-540.
- [2] H. A. Sabbagh, R. K. Murphy, E. H. Sabbagh, J. C. Aldrin, J. S. Knopp and M. P. Blodgett, "The Joy of Computing with Volume Integrals: Foundations for Nondestructive Evaluation of Planar Layered Media," ACES Journal, Vol. 25, No. 9, September 2010, pp. 723-730.
- [3] H. A. Sabbagh, R. K. Murphy, E. H. Sabbagh, J. C. Aldrin, J. S. Knopp and M. P. Blodgett, "The Joy of Computing with Volume Integrals: Validation and Performance Comparison," *ACES Journal*, Vol. 25, No. 9, September 2010, pp. 731-737.
- [4] M. Loève, Probability Theory, D. Van Nostrand, New York, 1955.
- [5] D. Xiu, Numerical Methods for Stochastic Computations: A Spectral Method Approach, Princeton University Press, Princeton, New Jersey, 2010.
- [6] Yu, F., and Nagy, P. B., "Numerical method for calculating the apparent eddy current conductivity loss on randomly rough surfaces," J. App. Physics, Vol. 95, No. 12, 15 June 2004, pp. 8340-8351.
- [7] H. A. Sabbagh, "A Model of Eddy-Current Probes with Ferrite Cores," *IEEE Transactions on Magnetics*, Vol. MAG-23, No. 2, March 1987, pp. 1888-1904.
- [8] Z. Gao and J. Hesthaven, 'On ANOVA expansions and strategies for choosing the anchor point,' unpublished, August 31, 2010.
- [9] M. Griebel, 'Sparse Grids and Related Approximation Schemes for Higher Dimensional Problems,' in L. Pardo, A. Pinkus, E. Suli and M. Todd, editors, *Proceedings Foundations of Computational Mathematics 2005* (FoCM05), Santander, 106-161, Cambridge University Press, 2006.
- [10] J. Foo, G. Karniadakis, 'Multi-element probabilistic collocation method in high dimensions,' J. Computational Physics, 229 (2010) 1536-1557.
- [11] X. Ma, N. Zabaras, 'An adaptive high-dimensional stochastic model representation technique for the solution of stochastic partial differential equations,' J. Computational Physics, 229 (2010) 3884-3915.