

Breakout Session 3

Non Hex Cr Treatments for IVD/Electroplated Al, Zn, Zn Alloy Coatings

By:
Steve Gaydos
And
Lorraine Wass
May 17, 2007

Report Documentation Page

Form Approved
OMB No. 0704-0188

Public reporting burden for the collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to a penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number.

1. REPORT DATE 17 MAY 2007	2. REPORT TYPE	3. DATES COVERED 00-00-2007 to 00-00-2007		
4. TITLE AND SUBTITLE Non Hex Cr Treatments for IVD/Electroplated Al, Zn, Zn Alloy Coatings		5a. CONTRACT NUMBER		
		5b. GRANT NUMBER		
		5c. PROGRAM ELEMENT NUMBER		
6. AUTHOR(S)		5d. PROJECT NUMBER		
		5e. TASK NUMBER		
		5f. WORK UNIT NUMBER		
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) Strategic Environmental Research and Development Program (SERDP), Environmental Security Technology Certification Program (ESTCP), 4800 Mark Center Drive, Suite 17D08, Alexandria, VA, 22350-3605		8. PERFORMING ORGANIZATION REPORT NUMBER		
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)		10. SPONSOR/MONITOR'S ACRONYM(S)		
		11. SPONSOR/MONITOR'S REPORT NUMBER(S)		
12. DISTRIBUTION/AVAILABILITY STATEMENT Approved for public release; distribution unlimited				
13. SUPPLEMENTARY NOTES DoD Metal Finishing Workshop - Chromate Alternatives for Metal Treatment and Sealing, May 15-17, 2007, Layton, UT. Sponsored by SERDP/ESTCP.				
14. ABSTRACT				
15. SUBJECT TERMS				
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT Same as Report (SAR)	
a. REPORT unclassified	b. ABSTRACT unclassified	c. THIS PAGE unclassified		
			18. NUMBER OF PAGES 10	19a. NAME OF RESPONSIBLE PERSON

Treatments for IVD/Electroplated Al

- Metalast TCP HF Qualified on Alumiplate
 - 25 to 50% at RT
 - 25% at 90 F
- All MIL-DTL-81706, Ty II TCP Materials Should Work on Al Coatings
 - Pure (99% Aluminum) to Treat with TCP
 - Henkel
 - CST SurTec
 - Luster-On
 - Metalast

Treatments for IVD/Electroplated Al

- Other Non TCPs That Offer Corrosion Resistance
 - Iridite NCP (Meets Ty II, Class 3)
 - Alodine 2000 (TD-3095 Seal)
 - Sanchem 3300 + 3400 Permanganate – Silicate Process
- Other Non-TCPs With Good Paint Adhesion Only
 - Boegel, Alodine 5700, PreKote
- Anodize or Oxide Coatings
 - Ty IC (BSAA), II (SAA), IIB (TSAA)
 - EC2

MIL-DTL-5541 Issues for Al Coatings

- MIL-DTL-5541 Still Required 2024 for Monthly Salt Spray
- Need to Change 5541 to Read Like MIL-A-8625 for Anodize
 - Corrosion Test with 2024 or Predominant Alloy Used That Month

Zn – Zn Alloy Coatings

- Many To Choose From – Mature Technology
 - Generations
 - I – Inorganics (Good for Zn Alloys)
 - II – III – Organics w / wo Cobalt
 - IV – Nanoparticles – Silica
 - Taylor for Needs – DoD Needs to Specify What They Want
 - Thickness, Elec Properties, Lubricity, Corrosion
 - Technology is Off the Shelf
 - Work with Vendors
 - SERDP – ESTCP Projects

Zn – Zn Alloy Coatings

- No Mil Spec Needed for These Treatments
 - Cd Plate Spec Required 96 hr SS
 - Need to Specify Additional Requirements
- DoD Should Select Non-Cobalt Versions for Evaluation
 - Avoid Future Regs

Installation of Non Hex Cr Systems

- Tighter Controls
 - pH, Temp, Concentration
- Process Less Forgiving
 - Pay Attention to Details
- Contamination
 - Remove Old Cr Tanks and Systems
- Non Hex Cr Costs Are Higher
 - Chemical Costs are Higher
 - Need to Use Technology to Extend Bath Life This Exists for Zn Alloy Systems

Issues for Insert of NonHex Into DoD

- **Non-Cr Primer**

- Need Hex Cr Surface Treatments to Make Non-Cr Primer Work

- Progress Being Made But Not There Yet

Reliability of Non Hex Treatments

- Zn Alloys Treatments Very Reliable
 - Long History With Automotive Industry
- Al Coating Treatments Very Reliable (Not 2024)
- Touch-Up
 - Zn Alloy Coatings
 - Not Typically Done But Possible (Check with Brush Platers)
 - Al Coatings
 - Metalast is Brushable
 - CST SurTec Has Pen Applicators for Their Version
 - Henkel is Qualifying Alodine 871 Touch-N-Prep Pens

What Needed to Implement

- Al Coatings
 - Drop-In Replacement
 - Use MIL-DTL-81706, Ty II
 - Check out Non-Cr Primers
- Zn Alloy Coatings
 - Need to Repeat All Work Done with Hex Cr on Zn-Ni
 - Corr, Galvanic, HE, Re-HE, Paint, Fatigue??, . . .