

DTIC FILE COPY

Serial Number 211,026

Filing Date 16 June 1988

Inventor Charles R. Hegedus
William J. Green

(1)

AD-D013 813

NOTICE

The Government-owned invention described herein is available for licensing. Inquires and requests for licensing information should be addressed to:

DEPARTMENT OF THE NAVY
Office of the Chief of Naval Research
(Code OOCIP)
Arlington, Virginia 22217-5000

Accession For	
NTIS GRA&I	<input checked="" type="checkbox"/>
DTIC TAB	<input type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	
By _____	
Distribution/	
Availability Codes	
Dist	Avail and/or Special
A	

DTIC
COPY
INSPECTED
6

DTIC
ELECTE
AUG 03 1988
S D F

DISTRIBUTION STATEMENT A
Approved for public release;
Distribution Unlimited

1

COMBINATION PRIMER/TOPCOAT COATING

5

STATEMENT OF GOVERNMENT INTEREST

The invention described herein may be manufactured and used by or for the Government of the United States of America for governmental purposes without the payment of any royalties thereon or therefor.

10

BACKGROUND OF THE INVENTION

↙ The present invention relates generally to a coating for metallic or polymeric composite substrates and more particularly to such a coating which can perform as both a primer and a topcoat.

15

Many metal and polymeric composite surfaces require the protection of a coating. For example, ↘ Navy aircraft surfaces need protection from the harsh aircraft-carrier environment, which contains corrosive sea water spray and, on non-nuclear carriers, sulfur dioxide stack gases. Therefore, these aircraft need a coating which will be corrosion inhibitive as well as chemically resistant, weather resistant, flexible, even at low temperatures, and have good surface adhesion.

20

25

Currently, Navy aircraft are painted with a high performance multi-component protective paint system consisting

1 of an epoxy primer and a polyurethane topcoat. Several types
of aircraft also require a coat of spray sealant between the
primer and the topcoat. More than one component has been used
because no single component provides all the desirable
5 properties.

The epoxy primer of the current system is applied to
a dry film thickness ranging from 0.0006 to 0.0009 inches and
is designed to adhere to the substrate, promote adhesion of the
topcoat, and prevent corrosion. However, the primer must be
10 topcoated because it lacks flexibility, especially at low
temperatures (-60°F), resulting in extensive cracking of the
paint system in highly flexed areas of the aircraft. The
primer also lacks weather resistance and cannot be formulated
in the appropriate colors for an aircraft topcoat. In
15 addition, it includes strontium chromate as a corrosion
inhibitor, a known carcinogen.

The polyurethane topcoat currently used is normally
applied over the primer to a dry film thickness of 0.0020 to
0.0022 inches. It provides chemical and weather resistance,
20 flexibility, and the desired optical properties. The topcoat
requires the use of a primer, however, because it will not
inhibit corrosion and does not have adequate adhesion to the
metal substrate.

A 0.0120 inch thick sealant coat is occasionally
25 applied between the primer and topcoat to enhance the



1 flexibility of the coating system. The sealant is soft and easily deformed and is difficult to apply and remove.

The current multi-component coating system described above has several deficiencies. It has a total dry film
5 thickness ranging from 0.0026 to 0.0151 inches, adding considerable weight to an aircraft, for instance. In addition, it is time consuming to apply and remove. The system also generates a high level of volatile organic component (VOC) emissions during the painting operation.

10

SUMMARY OF THE INVENTION

form 1 → Accordingly, it is a general object of the invention to ~~provide a single coating which can be applied directly to a metal or polymeric composite substrate and also perform as a topcoat.~~

15

It is another object to furnish a coating which will provide corrosion protection to a metallic or polymeric composite substrate while being adherent, flexible, chemically resistant, weather resistant, and opaque. *Patent applications. (JES)*

20

Yet another object is to reduce the risk of coating failure due to cracking and allow easy coating touch-up when required.

Still another object is to reduce the amount of time and manpower required to apply and remove a paint system.

25

Another object is to reduce the weight added to an object by a paint system.



1 It is also an object to decrease the level of VOC
emissions during a painting operation and to eliminate the use
of strontium chromate in a paint system.

5 Briefly, these and other objects of the present
invention are accomplished by a coating comprising a
polyurethane binder formed by the reaction of an aliphatic
polyester polyol with hexamethylene diisocyanate. Pigments are
provided for opacity and strength, consisting essentially of
titanium dioxide spherical particles and vesiculated beads.
10 The coating also contains pigments for providing corrosion
prevention, consisting essentially of zinc phosphate, zinc salt
of a substituted benzoic acid, and zinc molybdate.

15 Other objects, advantages, and novel features of the
present invention will become apparent from the following
detailed description thereof.

DESCRIPTION OF THE PREFERRED EMBODIMENT

20 The present invention is a coating for application to
metallic or polymeric composite surfaces which performs as both
a primer and a topcoat, being adherent, flexible, chemically
resistant, weather resistant, corrosion inhibiting, and opaque.
It is particularly useful on Navy aircraft, which are exposed
to a corrosive sea water environment, and require a light
weight coating.

25 The coating contains a polyurethane binder obtained
by reacting a blend of polyester polyols with hexamethylene



1 diisocyanate (HMDI) in stoichiometric proportions. In a
preferred embodiment, the polyester polyol is provided in the
form of a 46.2% (by wt.) solution of aliphatic polyester polyol
in toluene and ethyl glycol acetate. The solution has an
5 equivalent weight of 790 ± 150 , a density of 1.06, a hydroxyl
number of 71 ± 10 , a maximum acid number of 10, and a solids
content of $46.2\% \pm 5\%$. One such polyester polyol blend is
X3009-Part A manufactured by Coatings for Industry.
Preferrably, the HMDI is provided in a 75% (by wt.)
10 concentration in ethyl glycol acetate. This solution has an
isocyanate content of $16.5\% \pm 2.5\%$, a density of 1.07, and an
equivalent weight of 255 ± 15 . A suitable HMDI solution is
X3009-Part B, also manufactured by Coatings for Industry. The
polyurethane polymer formed by the reaction of the two parts
15 forms the continuous matrix of the coating, while also
providing weather resistance, chemical resistance, adhesion,
and flexibility.

Pigments for providing re-enforcing strength and
opacity are also included in the coating. One such pigment is
20 rutile titanium dioxide in the form of spherical particles
having an average particle size of $0.25 \pm .1$ microns. This
pigment provides color to the coating as well. Another such
pigment is titanium dioxide vesiculated beads. The beads have
an average particle size of 6.0 ± 2.0 microns. Their
25 composition by weight is at least 35% titanium dioxide with the



1 balance being polyester polymer. They also include voids,
which constitute $22.3\% \pm 7\%$ of their volume. The beads provide
opacity and strength without significantly increasing the
viscosity of the wet coating. They also assist in reducing
5 gloss due to their high oil absorption characteristics.

Three pigments are included in the coating in
controlled portions for corrosion prevention. One is a zinc
phosphate pigment with an average particle size of 5.0 ± 2.0
microns. Another is a zinc salt of a substituted benzoic acid
10 having one or more hydroxyl groups and a nitro (NO_2) side
group. This pigment is characterized by a molecular weight of
 300 ± 200 , a density of 2 to 3 grams per milliliter, and a
particle specific surface of 16 ± 5 . It also has an ASTM D281
oil absorption of 40 ± 10 , which is good if a low gloss coating
15 is desired. One suitable such zinc salt is a commercial
product of BASF called Sicorin RZ. The third corrosion
preventive ingredient is zinc molybdate, which also provides
opacity and strength. The zinc molybdate particles should have
an average size of 4.0 ± 2.0 microns.

20 Table I sets forth the above pigments and summarizes
various properties connected therewith.

25



TABLE I

	<u>Titanium Dioxide</u>	<u>Zinc Molybdate</u>	<u>Zinc Phosphate</u>	<u>Zinc Salt</u>	<u>Titanium Dioxide Beads</u>
Appearance	White	White	White	White	White
Shape	Spherical	Spherical	Rectangular	Platelet	Spherical
Density (g/ml)	4.0	5.0	3.6	2.5	0.6
Oil Absorption (ASTM D281)	29.3	16.0	23.2	40.0	146.8
Particle Size, Average, in microns	0.25	4.0	5.0	2.5	6.0



1 Four effective formulations of the basic formula of
the coating are set forth in Table II on a weight percent
basis. Formulation A is the preferred one.

TABLE II

5		A	B	C	D
	Polyester polyol blend	37.8	42.0	34.0	38.0
	Titanium dioxide/ particles	1.1	0.5	2.0	1.0
	Titanium dioxide/ vesiculated beads	0.4	0.5	0.9	0.3
10	Zinc phosphate	17.1	18.0	16.5	20.0
	Zinc salt	1.7	3.9	1.0	2.0
	Zinc molybdate	30.1	22.0	35.0	27.1
	HMDI solution	11.8	13.1	10.6	11.6

15 Other ingredients may be added to provide various
desirable features. For instance, to increase the coating's
pot life, 2,4 pentanedione may be added in an amount by weight
of up to 5% of the weight of the basic formula.

20 Also optional is the addition of an anti-settling
agent for improved pigment wetting and dispersion, and
increased shelf life. Any anti-settling solution may be used
and should be added in an amount by weight ranging from 0.3 to
2.0% of the weight of the basic formula. A preferred such
anti-settling agent is a solution of high molecular weight
carboxylic acid salts of polyamine amides known as Anti-Terra-

25



1 204, manufactured by BYK-Chemie USA.

5 The coating may also contain a solvent system such as toluene or 1,1,1 trichloroethane. This is for adjusting the viscosity of the coating and should be added in an amount suitable for the desired viscosity. Any solvent compatible with the resin system will suffice, but should have a solubility parameter of 8.9 ± 0.9 . Tinting pigments may also be added in appropriate amounts to obtain the desired coloring.

10 The coating is prepared by mixing all of the ingredients except the HMDI solution, and milling the resulting mixture to a fineness of grind of ≥ 5 on the ASTM-D-1210 scale. The HMDI solution is then added, and the coating is applied while still liquified to a thickness ranging from 0.0018 to 0.0022 inches. The coating may be applied by brushing, 15 rolling, or spraying it on the surface. If the coating is sprayed on the surface, a solvent system should be added to obtain the desired viscosity, in an amount by volume of about 15% of the volume of the basic formula.

20 In tests, the coating of the present invention provided corrosion protection for an aluminum substrate for over 2000 hours in 5% salt spray. The coating also performed well when exposed to heat, high intensity light and water, extreme cold, hot lubricating oil and other aircraft operational chemicals, and impact testing.

25 Some of the many advantages of the invention should



1 now be readily apparent. For instance, a coating for a
metallic or polymeric composite substrate has been provided
which performs as both a primer and a topcoat. It has the
combined properties of both, being adherent, flexible, chemical
5 and weather resistant, corrosion inhibitive, and opaque, and is
therefore particularly useful in a corrosive seawater
environment. A coating has been provided which reduces the
risk of failure due to cracking, especially at low
temperatures, and is easily touched up, since only one coating
10 need be applied. Additionally, since the coating provided by
the present invention requires only one coat and no sealant, it
requires less application and removal time and manpower (up to
50% less) than currently used coating systems. The coating
provided also adds less film thickness and weight to the coated
15 object (up to 30% less) than existing paint systems, an
important factor for use on aircraft. The coating provided by
the present invention also reduces VOC emissions during the
painting operation and does not contain the carcinogen
strontium chromate.

20 Obviously, many modifications and variations of the
present invention will be readily apparent to those of ordinary
skill in the art in light of the above teachings.



1

ABSTRACT OF THE DISCLOSURE

5

A coating for metallic or polymeric composite substrates is disclosed which performs both as a primer and as a topcoat. It comprises a two component aliphatic polyurethane binder, with titanium dioxide, zinc molybdate, zinc phosphate, an organo-zinc salt, and titanium dioxide vesiculated bead pigments in controlled amounts. The coating exhibits good adhesion, corrosion inhibition, flexibility, chemical and weather resistance, and opacity.

10

15

20

25

10

