Serial Number

<u>053,075</u>

Filing Date

<u>1 April 1998</u>

Inventor

<u>Kirth E. Simmonds</u> <u>Narendra K. Batra</u> <u>Richard B. Mignogna</u>

### **NOTICE**

The above identified patent application is available for licensing. Requests for information should be addressed to:

OFFICE OF NAVAL RESEARCH DEPARTMENT OF THE NAVY CODE OOCC ARLINGTON VA 22217-5660

> This document has been approved for public release and sale; its distribution is unlimited.

> > 19980727 050

DTIC QUALITY INSPECTED 1

PATENT APPLICATION



### **METHOD AND APPARATUS FOR IN SITU MEASUREMENT OF CORROSION IN**

### **LIQUID FILLED TANKS**

#### **BACKGROUND OF THE INVENTION**

#### 1. Field of the Invention

The present invention relates generally to monitoring liquid storage tanks for corrosion. More particularly, the present invention relates to a novel apparatus and method for the *in situ* monitoring such tanks for thinning (due to corrosion) of the tank bottom, and optionally for uneven settling of the tank, using ultrasonic transducers mounted on a mobile robotic device for use inside liquid filled tanks.

#### 2. Description of the Related Art

#### With respect to storage tanks.

Large metal storage tanks are used to store a variety of liquids, including especially water, petroleum, and petroleum products. These tanks, which are commonly made from non-stainless steel plates, are subject to corrosion and eventual failure over time. Even tanks that are intended to store only petroleum and petroleum products almost inevitably will have a substantial amount of water in them, greatly aggravating their tendency to oxidize. Thus, it is necessary to periodically inspect these tanks, and to make repairs before such failure. However, because of the enormous size of these tanks, it is expensive and inconvenient to empty a tank each time it is to be inspected.

15

20

#### PATENT APPLICATION

E.a.

Typical tanks for petroleum products are made from 1/4" to 1/2" thick steel plates welded together. They are commonly hundreds of feet tall and hundreds of feet in diameter. They are usually built above ground, but may also be made at least partially below ground. If such a tank should fail while filled with product, the environmental damage would be staggering.

5

Complicating the inspection process is the presence of sediment in the tanks. At the bottom of most liquid storage tanks there is a layer of sediment including rust, dirt, debris, petroleum solids, etc. This layer may be anywhere from several millimeters to several feet thick. An effective tank inspection system must either be able to see through this sediment, or must be able to displace the sediment to allow for direct inspection.

Bilges of large ships (e.g., aircraft carriers, tankers) likewise must be inspected periodically for corrosion. Many of the same concerns are raised for the inspection of bilges as are raised for the inspection of tanks.

### With respect to corrosion monitoring systems.

Available systems for monitoring liquid filled tanks for corrosion suffer from any of several common shortcomings.

One problem that has not been satisfactorily addressed by the art has been the difficulty of using ultrasonic probes to obtain reflection signals from both the top and bottom surfaces of the base plate of a tank. The sediment layer described above scatters ultrasonic waves, dramatically attenuating these waves, and thereby decreasing their ability to penetrate the bottom steel plate. Moreover,

10

15

#### PATENT APPLICATION

į.

ultrasonic waves scattered from the sediment are a source of noise that present systems do not adequately address.

U.S. Patent No. 5,205,174, issued April 27, 1993 to Silverman et al. (Silverman '174) is representative. This patent teaches the use of ultrasonic transducers for inspecting the bottom surfaces of storage tanks. This system teaches the use of very high frequency ultrasonic pulses (about 15.4 MHz, with a wavelength of 0.0156"). Such high frequency pulses will be so diminished in amplitude that signal detection would be problematic at best. This is particularly true if the ultrasonic pulse is scattered by plate surface that has been roughened by corrosion and attenuated by a layer of sediment. Silverman '174 attempts to mitigate the former problem by including a cleaning system in the apparatus, to remove sediment from the bottom as the apparatus moves along. In principle, this system would work by scrubbing and vacuuming the base free of sediment, irrigating the base with a stream of clean fluid to remove any remaining sediment, and filtering out the sediment so that it is not returned to the tank. At best, this is a very complicated system that does not address the problem of scattering by a surface that has been roughened by corrosion.

15

10

5

#### SUMMARY OF THE INVENTION

Accordingly, it is an object of this invention to provide detailed information on tank bottom thickness.

It is a further object of this invention to provide such information even for heavily corroded 20 liquid storage tanks.

## PATENT APPLICATION

It is a further object of the invention to provide such information even for liquid storage tanks having a layer of sediment on the bottom.

These and additional objects of the invention are accomplished by the structures and processes hereinafter described.

An aspect of the present invention is an apparatus for inspecting a base of a liquid filled tank for corrosion, having (a) a housing for use in the liquid filled tank; (b) a set of one or more ultrasonic transducers mounted to the housing, for directing one or more ultrasonic pulses at the base, where the ultrasonic pulses each have a frequency selected to produce a return signal from the base, and for receiving this return signal; and (c) a data capturing system, for storing information from these return signals. Optional features include a second set of one or more ultrasonic transducers for directing one or more ultrasonic pulses at the liquid/gas interface at a frequency selected to produce a return signal from the liquid/gas interface. a data analysis system, a locomotive system, and a spatial location system.

Another aspect of the invention is a method for inspecting a base of a liquid filled tank for corrosion, having the steps: (a) directing a broadband ultrasonic pulse at the base from an ultrasonic transducer within the tank, where the ultrasonic pulse includes a resonant frequency for the tank base over the range of expected thicknesses for the base; (b) receiving a return signal with the ultrasonic transducer; (c) performing a Fourier analysis on the return signal to generate a frequency domain signal; and (d) determining the thickness of the base from the frequency domain signal.

20

5

#### PATENT APPLICATION

Navy Case No. 78,472 Inventor(s): Simmonds et al.

## **BRIEF DESCRIPTION OF THE DRAWINGS**

A more complete appreciation of the invention will be obtained readily by reference to the following Description of the Preferred Embodiments and the accompanying drawings in which like numerals in different figures represent the same structures or elements, wherein:

FIG. 1 shows a schematic of the system according to the invention.

FIG. 2 shows an elevation of a transducer according to the invention.

FIG. 3 shows an elevation of another transducer according to the invention.

FIG. 4 shows a detailed section of a system according to the invention.

FIG. 5 shows a view of an array of transducers according to the invention.

FIG. 6 shows a schematic of an electronic system according to the invention.

FIG. 6A shows a schematic of another electronic system according to the invention.

FIG. 7 shows a time domain plot of a transducer signal in a method according to the invention.

FIG. 8 shows a frequency domain plot of a gated portion of the time domain signal depicted in FIG. 7.

#### DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

#### With respect to the overall system of the invention.

Referring to FIG. 1, this shows a schematic of the system 10 according to the invention. A 20 tank 12 is filled with a liquid inventory 14, such as a fuel. The tank 12 has a base 13 typically made

10

#### PATENT APPLICATION

of welded steel plates. The system of the invention is preferably designed to image the top 15 and bottom 17 surfaces of the tank base 13. Inside the tank 12 is a remote, automated device 16 housing the ultrasonic transducers (not shown), and the propulsion system 18 (shown here as a motor-driven track device). Also shown (typically inside the tank) are location transmitters 20 in communication with the device 16, for locating the device 16 within the tank 12. The mobile device 16 is typically connected to a data collection and analysis system 22 (typically a programmed digital computer). These connections typically are through a telemetry system (not shown), but alternatively may be through cabling. A microwave power source 24 preferably is used to power the device 16. Alternatively, cabling or large capacity on-board batteries or fuel cells are used to power the device. These power sources may also be used in conjunction with one another, e.g., batteries used as the principal power source during operations, and a microwave power source used to recharge the batteries, and also for additional power during operation.

Propulsion systems may be bottom-drive systems (such as the track drive system shown), or free-swimming systems, such as propeller or jet driven systems.

15

20

#### With respect to the transducers of the invention.

Referring to FIG. 2, this shows an elevation of a typical ultrasonic transducer 30 used according to the invention. Typical transducers used according to the invention will have a piezoelectric element 32 (usually PZT), mounted in a housing 34 that contains the electrodes coupled to the piezoelectric element 32, for driving the element. Typically, the housing 34 also has the

10

5

10

15

### PATENT APPLICATION

contact 37 for electrically connecting the transducer to the console housing the pulse generator and data collection and analysis system (not shown).

Referring to FIG. 3, this shows a preferred ultrasonic transducer 38 used according to the invention. This transducer has separate piezoelectric elements for transmitting 40 and receiving 42. The two piezoelectric elements 40,42 are mounted in a housing 44 that contains the electrodes coupled to the piezoelectric elements 40,42. Preferably, the two elements are coaxial. Preferably, the receiving element has a smaller diameter than the transmitting element–the smaller diameter will permit the receiving element to receive a signal integrated over a smaller area, leading to better spatial resolution. Contacts 37,37' electrically connect the two elements to the console housing the pulse generator and data collection and analysis system (not shown).

The system of the invention will include at least one set of transducers, and preferably two sets of transducers (for illustration purposes, a single transducer is sometimes shown and referred to herein as representative of a set of transducers). As shown in FIG. 4, the first transducer **38** will be directed toward the base of the tank (typically on the bottom of the housing **19**), for imaging the bottom plate of the tank. The optional second transducer **38'** will be directed toward the top of the housing **19**), for measuring the height of the liquid.

The configurations and operating frequencies of the two transducers need not be the same, since they perform different functions.

The first transducer **38** should be configured to generate a signal from the top **15** and bottom **17** surfaces of the tank base **13**. This will entail transmitting a pulse that can penetrate a highly

### PATENT APPLICATION

(\*\*\*

attenuating layer of sediment on the tank floor, and reflect a portion of the pulse back off the top surface. It will further entail transmitting enough of the remaining portion of the pulse to the bottom surface (despite typical further scattering by the corroded top surface of the base and attenuation through the steel plate) so that energy can reflect off the bottom surface of the steel plate. It has been discovered that the frequencies taught in the art (in particular, the frequencies taught in the previously cited Silverman '174) are far too high to successfully generate a useful return signal off both the corroded top and bottom surfaces of the steel base plate. It has been discovered that frequencies between approximately 0.5 MHz and 2.0 MHz are preferred, and that a frequency of about 1.0 MHz is more preferred for a base plate of about 1/4" thickness. Skilled practitioners will recognize that if the pulse frequency is too low, the spatial resolution of the signal will be reduced beyond a point that is acceptable.

10

15

5

The second transducer **38'** should be configured to generate a signal from the top surface of the liquid in the tank **14**. Because spatial resolution will be more critical for imaging the bottom plate than for imaging the liquid surface, using a less expensive single element transducer **30** should be acceptable.

Rather than using a single transducer to image in a given direction, it is preferred to use an array of transducers, to provide imaging over a wide swath of the tank bottom with each pass of the probe. A simple 1-dimensional array of multiplexed transducers will speed up imaging over the tank bottom, for instance. Preferably, as shown in FIG. 5, a 2-dimensional array of transducers is used.

#### PATENT APPLICATION

As shown, an array 39 of transducers 38 may be arranged so that each transducer will vield information about a given portion of a path of a given width over which the array passes.

#### With respect to the electronic system.

Referring to FIG. 6, this schematically depicts an exemplary system according to the invention. An oscillator 50 provides timing for the system. A pulse generator 52 coupled to the oscillator transmits regularly timed broadband ultrasonic pulses to the transducer. A typical commercially available pulse generator will have built-in amplification. In response to a pulse, the transducer transmitter 40 transmits a broadband ultrasonic pulse. The transducer receiver 42 receives 10 a return signal, which it transmits to an amplifier 54. The amplifier 54 amplifies the return signal, and transmits the amplified return signal to a temporal tracking and spectral analyzer 56, that samples the return signal, performs a Fourier analysis on a gated portion of the return signal, and transmits the Fourier analysis data to a computer for data processing and image display 58. A synchronization lead 60 sends a synchronization signal to the temporal tracking and spectral analyzer 15 56, to provide synchronization. An interface bus 62, typically a general purpose interface bus, connects the computer 58, the temporal tracking and spectral analyzer 56, and the pulse generator 52, to provide data transfer and control.

A console 22 typically houses the oscillator 58, pulse generator 52, and other electronic components.

### PATENT APPLICATION

Alternatively, as shown in FIG. 6A, remote, automated device 16 houses most of these electronic components, and microwave transceivers 64 are used for communication between the computer 58 and the device 16.

The optimal gated return signal sampled will depend on the pulse length of the transmitted signal and the transmission time through the liquid medium. It is desired to sample only the portion of the return signal that does not include the pulse output from the transducer or the reflection from the top surface of the tank base. Morever, the gated return signal should not include the subsequent reflections. It has been found that for pulse lengths of about 2  $\mu$ s, gate lengths that are between about two and about ten times the pulse length work well in the present invention.

10

15

20

5

As noted, the peak frequency will be inversely proportional to the thickness of the bottom plate. The relationship between the thickness and the peak frequency is given by  $v = c/\lambda$ , where vis the peak frequency, c is the propagation velocity of the ultrasonic waves in the tank bottom material, and  $\lambda$  is the wavelength of the first harmonic, which will be proportional to the tank bottom thickness. However, it may be that the absolute propagation velocity is not known for a given tank bottom. If the propagation velocity is not known absolutely, then the absolute tank bottom thickness at a given point cannot be determined. However, a relative thickness may be determined. For instance, all the tank bottom thicknesses may be normalized to (expressed as a fraction of) the maximum thickness (corresponding to the point on the tank bottom with the lowest peak frequency). Typically, this map of the normalized tank bottom thickness will be sufficient to achieve the objects of the invention. Alternatively, an estimate of the propagation velocity may be used.

### PATENT APPLICATION

#### With respect to the propulsion system.

A number of propulsion systems are suitable for use in the present invention. For example, a track system 18 will work well in most types of tanks. See Silverman '174, incorporated by reference herein. Other systems that should work include propulsion systems using propellers and propulsion systems using liquid jets.

#### With respect to the positioning system.

Several positioning systems are suitable for use in the present invention. As discussed *supra*, several positioning transmitters may be positioned within the tank, and the device may triangulate a position from these transmitters, similar to what is done with the global positioning system. Alternatively, an inertial navigational system and/or an active sonar system may be used to monitor the position of the device. Temperature correction may be used to enhance the precision of an active sonar locating system.

15

10

5

### With respect to the mapping system.

Thickness data preferably is correlated with positional data collected from the positioning system, to produce a map of the tank bottom. This map may be displayed in any suitable manner, e.g., as a color plot with different colors representing different bottom thicknesses, as a contour plot, grayscale plot, or as a three dimensional bar or line plot.

### PATENT APPLICATION

Having described the invention, the following examples are given to illustrate specific applications of the invention, including the best mode now known to perform the invention. These specific examples are not intended to limit the scope of the invention described in this application.

5

10

## Example 1:

Measurement of Aluminum Plate Thickness for Sample Not Covered by Sediment

An aluminum sample having stepped thicknesses ranging from 0.52 cm to 1.31 cm was placed in a small tray of water. A custom-built ultrasonic transducer was placed in the tank, and aimed at a portion of the aluminum plate having a known thickness of 0.65 cm, from a distance of about 5 cm. The transducer was connected to an analysis unit comprising a Tektronix DSA602A Digitizing Signal Analyzer, a Metrotek Pulser Model MP215 (or, in some experiments, a Stanford Research Model DG535 Four Channel Digital Delay/Pulser Generator and ENI Power Amplifier Model 325LA), a Metrotek Receiver Model MR101 (or a Matec Broadband Receiver Model 605), a Metrotek Scanner and Controller Model C403, and a Panametrics 1 MHz broadband transducer (or Valpey-Fisher special order 1 MHz broadband annular array transducer), configured as shown in FIG. 6. A broadband ultrasonic pulse having a center frequency  $v_{center} = 1.0$  MHz and a bandwidth of approximately from 0.8 MHz to 1.5 MHz (full width at half maximum) was transmitted to the steel plate. The time domain signal received by the transducer is shown in FIG. 7. As seen in FIG. 7, the broadband output pulse lasted about 5  $\mu$ s (from t = 0 to about t = about 5  $\mu$ s). The ultrasonic pulse reflected from the front surface of the Al plate, generating a high intensity return signal for about 10  $\mu$ s, from about (from about t = 55  $\mu$ s to about t = 65  $\mu$ s). After about 65  $\mu$ s, the return

## PATENT APPLICATION

¢₹

signal had a reduced intensity. The next 20  $\mu$ s (from about t = 65  $\mu$ s to about t = 85  $\mu$ s) was taken as the resonant return signal, and was gated for Fourier analysis.

A fast Fourier transform was performed on the gated portion of the return signal, with the results shown in FIG. 8. The peak frequency is associated with the thickness of the plate, as


5 discussed supra.


Obviously, many modifications and variations of the present invention are possible in light of the above teachings. It is therefore to be understood that

the invention may be practiced otherwise than as specifically described.

# ABSTRACT OF THE DISCLOSURE

5 An aspect of the present invention is an apparatus for inspecting a base of a liquid filled tank for corrosion, having (a) a housing for use in the liquid filled tank; (b) a set of one or more ultrasonic transducers mounted to the housing, for directing one or more ultrasonic pulses at the base, where the ultrasonic pulses each have a frequency selected to produce a return signal from the base, and for receiving this return signal; and (c) a data capturing system. for storing information from these 10 return signals. Optional features include a second set of one or more ultrasonic transducers for directing one or more ultrasonic pulses at the liquid/gas interface at a frequency selected to produce a return signal from the liquid/gas interface, a data analysis system, a locomotive system, and a spatial location system. Another aspect of the invention is a method for inspecting a base of a liquid filled tank for corrosion, having the steps: (a) directing a broadband ultrasonic pulse at the base from 15 an ultrasonic transducer within the tank, where the ultrasonic pulse includes a resonant frequency for the tank base over the range of expected thicknesses for the base; (b) receiving a return signal with the ultrasonic transducer; (c) performing a Fourier analysis on the return signal to generate a frequency domain signal; and (d) determining the thickness of the base from the frequency domain signal.






. -


, **r** 


FIE 2

• '



F15 3







.

F16.5


• •



F16. 6




F16. 6A



F16.7

l



F16 8