

AD-P004925



AD ~~XXXXXXXXXX~~

TECHNICAL REPORT ARLCB-TR-85007

# A MORE ACCURATE SOLUTION TO THE ELASTIC-PLASTIC PROBLEM OF PRESSURIZED THICK-WALLED CYLINDERS

PETER C. T. CHEN

PROPERTY OF  
TECHNICAL LIBRARY  
ROCK ISLAND ARSENAL  
ROCK ISLAND, IL 61229

FEBRUARY 1985



US ARMY ARMAMENT RESEARCH AND DEVELOPMENT CENTER  
LARGE CALIBER WEAPON SYSTEMS LABORATORY  
BENET WEAPONS LABORATORY  
WATERVLIET N.Y. 12189

APPROVED FOR PUBLIC RELEASE; DISTRIBUTION UNLIMITED

#### DISCLAIMER

The findings in this report are not to be construed as an official Department of the Army position unless so designated by other authorized documents.

The use of trade name(s) and/or manufacture(s) does not constitute an official indorsement or approval.

#### DISPOSITION

Destroy this report when it is no longer needed. Do not return it to the originator.

COMPONENT PART NOTICE

THIS PAPER IS A COMPONENT PART OF THE FOLLOWING COMPILATION REPORT:

TITLE: Transactions of the Army Conference on Applied Mathematics and  
Computing (2nd) Held at Washington, DC on 22-25 May 1984.

TO ORDER THE COMPLETE COMPILATION REPORT, USE AD-A154 047

THE COMPONENT PART IS PROVIDED HERE TO ALLOW USERS ACCESS TO INDIVIDUALLY AUTHORED SECTIONS OF PROCEEDING, ANNALS, SYMPOSIA, ETC. HOWEVER, THE COMPONENT SHOULD BE CONSIDERED WITHIN THE CONTEXT OF THE OVERALL COMPILATION REPORT AND NOT AS A STAND-ALONE TECHNICAL REPORT.

THE FOLLOWING COMPONENT PART NUMBERS COMPRISE THE COMPILATION REPORT:

AD#: P004 902 thru P004 958 AD#: \_\_\_\_\_  
 AD#: \_\_\_\_\_ AD#: \_\_\_\_\_  
 AD#: \_\_\_\_\_ AD#: \_\_\_\_\_

This document has been approved for public release and sale; its distribution is unlimited.

DTIC FORM 1163  
 MAR 85

Accession For	
NTIS GRA&I	<input checked="" type="checkbox"/>
DTIC TAB	<input type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	
By _____	
Distribution/	
Availability Codes	
Dist	Avail and/or Special
A-1	

DTIC  
 ELECTED  
 AUG 19 1985  
 S  
 A

OPI: DTIC-TID

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER ARLCB-TR-85007	2. GOVT ACCESSION NO.	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) A MORE ACCURATE SOLUTION TO THE ELASTIC-PLASTIC PROBLEM OF PRESSURIZED THICK-WALLED CYLINDERS		5. TYPE OF REPORT & PERIOD COVERED Final
		6. PERFORMING ORG. REPORT NUMBER
7. AUTHOR(s) Peter C. T. Chen		8. CONTRACT OR GRANT NUMBER(s)
9. PERFORMING ORGANIZATION NAME AND ADDRESS US Army Armament Research & Development Center Benet Weapons Laboratory, SMCAR-LCB-TL Watervliet, NY 12189-5000		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS AMCMS No. 6111.02.H600.011 PRON NO. 1A325B541A1A
11. CONTROLLING OFFICE NAME AND ADDRESS US Army Armament Research & Development Center Large Caliber Weapon Systems Laboratory Dover, NJ 07801-5001		12. REPORT DATE February 1985
		13. NUMBER OF PAGES 16
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)		15. SECURITY CLASS. (of this report) UNCLASSIFIED
		15a. DECLASSIFICATION/DOWNGRADING SCHEDULE
16. DISTRIBUTION STATEMENT (of this Report)  Approved for Public Release; Distribution Unlimited		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		
18. SUPPLEMENTARY NOTES  Presented at the Second Army Conference on Applied Math & Computing, RPI, Troy, NY, 22-24 May 1984. Published in the Conference Proceedings.		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number)  Strain-Hardening Materials Pressurized Thick-Walled Cylinders Residual Stresses Finite-Difference Method		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number)  A new method has been developed for solving the partially plastic problems of thick-walled cylinders made of strain-hardening or ideally-plastic materials subjected to any combination of internal pressure, external pressure, and end loads. The incremental strains are chosen as the basic unknowns in the finite-difference formulation. The incremental sizes of the applied loading are determined automatically and no iteration is needed. Complete solutions (CONT'D ON REVERSE)		

20. ABSTRACT (CONT'D)


for the stresses, strains, and displacement have been obtained and all numerical results are very accurate. This approach is also efficient and simple, yet quite general, when compared with many solutions in the literature.




A MORE ACCURATE SOLUTION TO THE ELASTIC-PLASTIC PROBLEM  
OF PRESSURIZED THICK-WALLED CYLINDERS

Peter C. T. Chen

U.S. Army Armament, Munitions, and Chemical Command  
Armament Research and Development Center  
Large Caliber Weapon Systems Laboratory  
Benet Weapons Laboratory  
Watervliet, NY 12189



**ABSTRACT.** A new method has been developed for solving the partially plastic problems of thick-walled cylinders made of strain-hardening or ideally-plastic materials subjected to any combination of internal pressure, external pressure, and end loads. The incremental strains are chosen as the basic unknowns in the finite-difference formulation. The incremental sizes of the applied loading are determined automatically and no iteration is needed. Complete solutions for the stresses, strains, and displacement have been obtained and all numerical results are very accurate. This approach is also efficient and simple, yet quite general, when compared with many solutions in the literature. 

## TABLE OF CONTENTS

	<u>Page</u>
INTRODUCTION	1
BASIC EQUATIONS	2
FINITE-DIFFERENCE FORMULATION	3
OPTIMAL INCREMENTAL LOADING	6
CONVERGENCE STUDY	7
ADDITIONAL RESULTS	10
REFERENCES	14

### TABLES

I. ELASTIC SOLUTION FOR A CLOSED-END TUBE	8
II. INITIAL YIELDING SOLUTION FOR A PLANE-STRAIN TUBE	8
III. ELASTIC-PERFECTLY PLASTIC SOLUTION FOR A PLANE-STRAIN TUBE	9
IV. INCOMPRESSIBLE, IDEALLY-PLASTIC SOLUTION FOR A PLANE-STRAIN TUBE	10
V. ELASTIC-PLASTIC SOLUTION FOR A PLANE-STRAIN TUBE	11
VI. ELASTIC-PLASTIC SOLUTION FOR AN OPEN-END TUBE	12
VII. ELASTIC-PLASTIC SOLUTION FOR A CLOSED-END TUBE	13

## INTRODUCTION

The partially plastic problem of pressurized thick-walled cylinder is of practical importance to pressure vessels and the autofrettage process of gun barrels. Many solutions for this problem have been reported (refs 1-7). For thick tubes under very high pressure operation, the elastic-plastic material model should be represented by the von Mises' yield criterion, Prandtl-Reuss' incremental stress-strain laws, the strain-hardening, and compressibility (ref 8). However, a closed-form solution exists only in the plane-strain case neglecting strain-hardening and compressibility.

For the generalized plane-strain problems considered here, numerical solutions were reported by the finite-difference method (refs 4,7) and finite-element method (ref 5). The incremental displacements were used as the basic unknowns and a displacement function was assumed in the finite-element method (ref 5). The incremental stresses and strains were used in Reference 4 as the basic unknowns, but only the incremental strains were used in Reference 7. The spatial discretization used in References 4 and 7 was based on the forward difference scheme and a fixed sequence of incremental loading was used.

In this report, a new method is developed and more accurate numerical results are obtained. The incremental strains are chosen as the basic unknowns in the finite-difference formulation. Both strain-hardening and ideally-plastic materials can be considered. The spatial discretization is based on the central difference scheme and the incremental sizes of the applied loading are determined automatically in the program. The incremental

---

References are listed at the end of this report.



results are calculated directly and no iteration is needed. The convergence of the approach will be discussed and more accurate results will be reported.

#### BASIC EQUATIONS

Assuming small strain and no body forces in the axisymmetric state of generalized plane-strain, the radial and tangential stresses,  $\sigma_r$  and  $\sigma_\theta$ , must satisfy the equilibrium equation,

$$r(\partial\sigma_r/\partial r) = \sigma_\theta - \sigma_r \quad (1)$$

and the corresponding strains,  $\epsilon_r$  and  $\epsilon_\theta$ , are given in terms of the radial displacement,  $u$ , by

$$\epsilon_r = \partial u/\partial r \quad , \quad \epsilon_\theta = u/r \quad (2)$$

It follows that the strains must satisfy the equation of compatibility

$$r(\partial\epsilon_\theta/\partial r) = \epsilon_r - \epsilon_\theta \quad (3)$$

If the material is assumed to be elastic-plastic, obeying the Mises' yield criterion, the Prandtl-Reuss flow theory, and the isotropic hardening law, the stress-strain relations are (ref 1):

$$d\epsilon_i' = d\sigma_i'/2G + (3/2)\sigma_i'd\sigma/(\sigma H') \quad (4)$$

$$d\sigma > 0 \quad \text{for } i = r, \theta, z$$

$$d\epsilon_m = E^{-1}(1-2\nu)d\sigma_m \quad (5)$$

where  $E$ ,  $\nu$  are Young's modulus, Poisson's ratio, respectively,

$$2G = E/(1+\nu),$$

$$\epsilon_m = (\epsilon_r + \epsilon_\theta + \epsilon_z)/3 \quad , \quad \epsilon_i' = \epsilon_i - \epsilon_m$$

$$\sigma_m = (\sigma_r + \sigma_\theta + \sigma_z)/3 \quad , \quad \sigma_i' = \sigma_i - \sigma_m$$

$$\sigma = (1/\sqrt{2})[(\sigma_r - \sigma_\theta)^2 + (\sigma_\theta - \sigma_z)^2 + (\sigma_z - \sigma_r)^2]^{1/2} > \sigma_0 \quad (6)$$

and  $\sigma_0$  is the yield stress in simple tension or compression. For a strain-hardening material,  $H'$  is the slope of the effective stress/plastic strain

curve

$$\sigma = H(\int d\epsilon^p) \quad (7)$$

For an ideally-plastic material ( $H' = 0$ ), the quantity  $(3/2)d\sigma/(\sigma H')$  is replaced by  $d\lambda$ , a positive factor of proportionality. When  $\sigma < \sigma_0$  or  $d\sigma < 0$ , the state of stress is elastic and the second term in Eq. (4) disappears. Following Yamada et al (ref 9), Eqs. (4) and (5) can be rewritten in an incremental form

$$d\sigma_i = d_{ij}d\epsilon_j \quad \text{for } i, j = r, \theta, z \quad (8)$$

and

$$d_{ij} = 2G[v/(1-2v) + \delta_{ij} - \sigma_i'\sigma_j'/S]$$

where

$$S = \frac{2}{3} \left(1 + \frac{1}{3} H'/G\right) \sigma^2, \quad H'/E = \omega/(1-\omega) \quad (9)$$

$\omega E$  is the slope of the effective stress-strain curve, and  $\delta_{ij}$  is the Kronecker delta.

This form was used in the finite-element formulation for solving elastic-plastic thick-walled tube problems (ref 5). In the following section, the incremental stress-strain matrix will be used in the finite-difference formulation.

#### FINITE-DIFFERENCE FORMULATION

Consider a thick-walled cylinder of inner radius  $a$  and external radius  $b$ . The tube is subjected to inner pressure  $p$ , external pressure  $q$ , and end force  $f$ . The elastic solution for this problem is well-known and the pressure  $p^*$ ,  $q^*$ , or  $f^*$  required to cause initial yielding can be determined by using the Mises' yield criterion. For loading beyond the elastic limit, an incremental approach of the finite-difference formulation is used. The cross-section of

the tube is divided into  $n$  rings with  $r_1=a, r_2, \dots, r_k=\rho, \dots, r_{n+1}=b$  where  $\rho$  is the radius of the elastic-plastic interface. At the beginning of each increment of loading, the distribution of displacements, strains, and stresses are assumed to be known and we want to determine  $\Delta u$ ,  $\Delta \epsilon_r$ ,  $\Delta \epsilon_\theta$ ,  $\Delta \epsilon_z$ ,  $\Delta \sigma_r$ ,  $\Delta \sigma_\theta$ ,  $\Delta \sigma_z$  at all grid points. Since the incremental stresses are related to the incremental strains by the incremental form (Eq. (8)) and  $\Delta u = r \Delta \epsilon_\theta$ , there exists only three unknowns at each station that have to be determined for each increment of loading. Accounting for the fact that the axial strain  $\epsilon_z$  is independent of  $r$ , the unknown variables in the present formulation are  $(\Delta \epsilon_\theta)_i$ ,  $(\Delta \epsilon_r)_i$ , for  $i = 1, 2, \dots, n, n+1$ , and  $\Delta \epsilon_z$ .

The equation of equilibrium (1) and the equation of compatibility (3) are valid for both the elastic and the plastic regions of a thick-walled tube. A first-order-correct finite-difference analog of these two equations at  $i = 1, \dots, n$  has been given in References 4 and 7. Other finite-difference forms can be written. In this report, the difference equations given below are second-order-correct. The equation of compatibility (3) and equation of equilibrium (1) are replaced, respectively, by

$$\text{and} \quad c_{1i}(\Delta \epsilon_\theta)_i + c_{2i}(\Delta \epsilon_r)_i + c_{3i}(\Delta \epsilon_\theta)_{i+1} + c_{4i}(\Delta \epsilon_r)_{i+1} = c_{5i} \quad (10)$$

$$c_{1i}(\Delta \sigma_r)_i + c_{2i}(\Delta \sigma_\theta)_i + c_{4i}(\Delta \sigma_r)_{i+1} + c_{4i}(\Delta \sigma_\theta)_{i+1} = c_{6i} \quad (11)$$

where

$$c_{1i} = -\frac{3}{2} + \frac{1}{2} \gamma_i, \quad c_{2i} = \frac{1}{2} - \frac{1}{2} \gamma_i$$

$$c_{3i} = \frac{3}{2} - \frac{1}{2} \gamma_i, \quad c_{4i} = -\frac{1}{2} + \frac{1}{2} \gamma_i$$

$$c_{5i} = -c_{1i}(\epsilon_\theta)_i - c_{2i}(\epsilon_r)_i - c_{3i}(\epsilon_\theta)_{i+1} - c_{4i}(\epsilon_r)_{i+1}$$

$$c_{6i} = -c_{1i}(\sigma_r)_i - c_{2i}(\sigma_\theta)_i - c_{3i}(\sigma_r)_{i+1} - c_{4i}(\sigma_\theta)_{i+1}$$

and

$$\gamma_i = r_{i+1}/r_i \quad (12)$$

With the aid of the incremental stress-strain relations (8), Eq. (11) can be written as

$$c_{7i}(\Delta\epsilon_\theta)_i + c_{8i}(\Delta\epsilon_r)_i + c_{9i}(\Delta\epsilon_\theta)_{i+1} + c_{10i}(\Delta\epsilon_r)_{i+1} + c_{11i}(\Delta\epsilon_z) = c_{6i} \quad (13)$$

where

$$\begin{aligned} c_{7i} &= c_{1i}(d_{12})_i + c_{2i}(d_{22})_i, & c_{8i} &= c_{1i}(d_{11})_i + c_{2i}(d_{21})_i \\ c_{9i} &= c_{3i}(d_{12})_{i+1} + c_{4i}(d_{22})_{i+1}, & c_{10i} &= c_{3i}(d_{11})_{i+1} + c_{4i}(d_{22})_{i+1} \\ c_{11i} &= c_{1i}(d_{13})_i + c_{2i}(d_{23})_i + c_{3i}(d_{13})_{i+1} + c_{4i}(d_{23})_{i+1} \end{aligned} \quad (14)$$

The boundary conditions for the problem are

$$\begin{aligned} \Delta\sigma_r(a,t) &= -\Delta p, & \Delta\sigma_r(b,t) &= -\Delta q \\ \pi \sum_{i=1}^n [r_i(\Delta\sigma_z)_i + r_{i+1}(\Delta\sigma_z)_{i+1}](r_{i+1}-r_i) &= \mu\pi a^2\Delta p + \Delta f \end{aligned} \quad (15)$$

where  $\mu$  is zero for open-end tubes, and one for closed-end tubes. Using the incremental relations (8), we rewrite Eq. (15) as

$$(d_{12})_1(\Delta\epsilon_\theta)_1 + (d_{11})_1(\Delta\epsilon_r)_1 + (d_{13})_1\Delta\epsilon_z = -\Delta p \quad (16)$$

$$(d_{12})_{n+1}(\Delta\epsilon_\theta)_{n+1} + (d_{11})_{n+1}(\Delta\epsilon_r)_{n+1} + (d_{13})_{n+1}\Delta\epsilon_z = -\Delta q \quad (17)$$

and

$$\begin{aligned} \sum_{i=1}^n [c_{12i}(\Delta\epsilon_\theta)_i + c_{13i}(\Delta\epsilon_r)_i + c_{14i}(\Delta\epsilon_\theta)_{i+1} + c_{15i}(\Delta\epsilon_r)_{i+1} \\ + c_{16i}(\Delta\epsilon_z)] = \mu a^2\Delta p + \Delta f/\pi \end{aligned} \quad (18)$$

where

$$\begin{aligned} c_{12i} &= (r_{i+1}-r_i)r_i(d_{32})_i, & c_{13i} &= (r_{i+1}-r_i)r_i(d_{31})_i \\ c_{14i} &= (r_{i+1}-r_i)r_{i+1}(d_{32})_{i+1}, & c_{15i} &= (r_{i+1}-r_i)r_{i+1}(d_{31})_{i+1} \\ c_{16i} &= (r_{i+1}-r_i)[r_i(d_{33})_i + r_{i+1}(d_{33})_{i+1}] \end{aligned} \quad (19)$$

Now we can form a system of  $2n+3$  equations for solving  $2n+3$  unknowns,  $(\Delta\epsilon_\theta)_i$ ,  $(\Delta\epsilon_r)_i$ , at  $i = 1, 2, \dots, n, n+1$  and  $\Delta\epsilon_z$ . Equations (16), (17), and (18) are

taken as the first and last two equations, respectively, and the other  $2n$  equations are set up at  $i = 1, 2, \dots, n$  using Eqs. (10) and (13). The final system is an unsymmetric matrix of arrow type with the nonzero terms appearing in the last row and column and others clustering about the main diagonal, two below and two above. In the computer program which was developed, the dimensionless quantities  $r/a$ ,  $E\epsilon_r/\sigma_0$ ,  $E\epsilon_\theta/\sigma_0$ ,  $E\epsilon_z/\sigma_0$ ,  $\sigma_r/\sigma_0$ ,  $\sigma_\theta/\sigma_0$ ,  $\sigma_z/\sigma_0$ ,  $p/\sigma_0$ ,  $q/\sigma_0$ ,  $f/(\pi a^2 \sigma_0)$  were used in the formulation and the Gaussin elimination method was used to solve these equations. All calculations were carried out on IBM 4341 with double precision to reduce round-off errors.

#### OPTIMAL INCREMENTAL LOADING

Given any combination of incremental-loading ( $\Delta p$ ,  $\Delta q$ , or  $\Delta f$ ), we can now determine all incremental results (displacements, strains, and stresses) directly. No iteration is needed, while in Reference 4, many iterations in each step were required because a value for  $\Delta\epsilon_z$  was assumed. The sizes of incremental-loading should be chosen properly in order to obtain accurate results at a reasonable cost. When the total applied pressure  $p$  is given, it is natural to divide the loading path in  $m$  equal fixed increments such as  $\Delta p = (p-p^*)/m$ . Larger values of  $m$  give more accurate results. A sequence of decreasing load-increments is a better choice than that of equal increments. In order to increase the efficiency without affecting the accuracy, an adaptive algorithm has been implemented on the basis of a scaled incremental-loading approach (ref 5).

In each step, a dummy load-increment such as  $\Delta p$  is applied and the incremental results  $\Delta\sigma_i$  for  $i = r, \theta, z$  at all grids are determined. For all

grid points at which  $\sigma = \|\sigma_1\| < \sigma$ , we compute the scalar  $\alpha$ 's by the formula

$$\alpha = \frac{1}{2} \{ \Gamma + [\Gamma^2 + 4\|\Delta\sigma_1\|^2(\sigma_0^2 - \|\sigma_1\|^2)]^{1/2} \} / \|\Delta\sigma_1\|^2 \quad (20)$$

where

$$\Gamma = \|\sigma_1\|^2 + \|\Delta\sigma_1\|^2 - \|\sigma_1 + \Delta\sigma_1\|^2 \quad (21)$$

and  $\|\sigma_1\|$ ,  $\|\Delta\sigma_1\|$ ,  $\|\sigma_1 + \Delta\sigma_1\|$  are computed by

$$\|\sigma_1\|^2 = \frac{1}{2} [(\sigma_r - \sigma_\theta)^2 + (\sigma_\theta - \sigma_z)^2 + (\sigma_z - \sigma_r)^2] \quad (22)$$

Let  $\lambda$  be the minimum of the  $\alpha$ 's. Then  $\lambda$  is the load-increment factor just sufficient to yield one additional point. A sequence of  $\lambda(j)$  can be determined for all steps  $j = 1, 2, \dots, m$  and the updated results are

$$\begin{aligned} p(j) &= p(j-1) + \lambda(j)\Delta p(j) \\ \sigma_1(j) &= \sigma_1(j-1) + \lambda(j)\Delta\sigma_1(j) \quad , \quad \text{etc.} \end{aligned} \quad (23)$$

This sequence of incremental loading is optimal for the present problem because all the coefficients  $c$ 's in Eqs. (12), (14), and (19) are functions of the previous stresses and strains.

#### CONVERGENCE STUDY

In order to demonstrate the accuracy of the approach, four convergence studies are made. Consider a thick-walled tube of wall ratio  $b/a = 2$  and subjected to internal pressure only. The cross-section of the tube is divided into  $n$  rings of equal thicknesses, i.e.,  $h = (b-a)/n$ . The first problem is a closed-end tube loaded in the elastic range with  $G = 10^5/3$  psi,  $\nu = 0.3$ ,  $p = 5$  psi. The numerical results with  $n = 10, 20, 50, 100$  are shown in Table I together with the Lamé' solution for the hoop stresses and strains at the boundaries  $a$  and  $b$ . The numerical results are correct up to four digits with  $n = 100$ .

TABLE I. ELASTIC SOLUTION FOR A CLOSED-END TUBE

( $b/a = 2$ ,  $G = 10^5/3$  psi,  $\nu = 0.3$ ,  $p = 5$  psi)

	n	$\sigma_{\theta} _a$	$\sigma_{\theta} _b$	$E\epsilon_{\theta} _a$	$E\epsilon_{\theta} _b$
Exact	-	8.3333	3.3333	9.3333	2.8333
FDM	10	8.3000	3.3000	9.3000	2.8000
	20	8.3256	3.3250	9.3250	2.8250
	50	8.3320	3.3320	9.3320	2.8320
	100	8.3330	3.3330	9.3330	2.8330

The second problem is the initial yielding solution for a plane-strain tube with  $E/\sigma_0 = 200$ ,  $\nu = 0.3$ ,  $\epsilon_z = 0$ . The numerical results with  $n = 10, 20, 50, 100, 200$ , are shown in Table II together with the exact solution for the dimensionless  $\bar{p} = p/\sigma_0$ ,  $\bar{\sigma}_{\theta} = \sigma_{\theta}/\sigma_0$ ,  $\bar{\epsilon}_{\theta} = (E/\sigma_0)(\epsilon_{\theta})$  at  $r = a$  and  $b$ .

TABLE II. INITIAL YIELDING SOLUTION FOR A PLANE-STRAIN TUBE

( $b/a = 2$ ,  $E/\sigma_0 = 200$ ,  $\nu = 0.3$ )

	n	$\bar{p}$	$\bar{\sigma}_{\theta} _a$	$\bar{\sigma}_{\theta} _b$	$\bar{\epsilon}_{\theta} _a$	$\bar{\epsilon}_{\theta} _b$
Exact	-	.43229	.72049	.28820	.82424	.26226
FDM	10	.00110	-.00107	-.00216	-.00054	-.00065
	20	.00028	-.00027	-.00054	-.00014	-.00016
	50	.00005	-.00004	-.00009	-.00002	-.00003
	100	.00001	-.00001	-.00003	-.00001	-.00001
	200	.00001	.00000	-.00001	.00000	.00000

The third problem is the elastic-perfectly plastic solution for a plane-strain tube with  $b/a = 2$ ,  $E/\sigma_0 = 200$ ,  $\nu = 0.3$ ,  $\omega = 0$ ,  $\epsilon_z = 0$ . The numerical results with  $n = 10, 20, 50, 100, 200$  are shown in Table III for the pressure and displacement at the bore corresponding to 50 percent and 100 percent overstrain, i.e.,  $\rho/a = 1.5$  and  $2.0$ .

TABLE III. ELASTIC-PERFECTLY PLASTIC SOLUTION FOR A PLANE-STRAIN TUBE

( $b/a = 2$ ,  $E/\sigma_0 = 200$ ,  $\nu = 0.3$ )

n	50% Overstrain		100% Overstrain	
	$\bar{p}$	$\bar{\epsilon}_{\theta} _a$	$\bar{p}$	$\bar{\epsilon}_{\theta} _a$
10	.71863	1.97725	.79849	3.68937
20	.71825	1.96969	.79790	3.66831
50	.71808	1.96780	.79760	3.66280
100	.71803	1.96759	.79751	3.66211
200	.71801	1.96757	.79747	3.66199

The numerical results converge and are accurate up to four digits with  $n = 100$ . There is no closed-form solution available for comparison. The famous paper by Hodge and White (ref 2) has been used quite often as a basis for assessing the accuracy of other approximate methods. However, the numerical integration is cumbersome. The present formulation is much simpler and seems more accurate. In order to further demonstrate the accuracy of the present approach, a convergence study for an incompressible, ideally-plastic thick tube in plane-strain condition has been made and compared with exact solution (ref 2). The numerical results for a nearly incompressible material ( $\nu =$



0.49999) are shown in Table IV together with the exact solution ( $\nu = 1/2$ ) for the internal pressure and the displacement at the bore corresponding to 50 percent and 100 percent overstrain.

TABLE IV. INCOMPRESSIBLE, IDEALLY-PLASTIC SOLUTION FOR A PLANE-STRAIN TUBE

( $b/a = 2$ ,  $E/\sigma_0 = 200$ ,  $\nu = 0.49999$ )

n	50% Overstrain		100% Overstrain	
	$\bar{p}$	$\bar{\epsilon}_\theta _a$	$\bar{p}$	$\bar{\epsilon}_\theta _a$
10	.72069	1.95714	.80015	3.48806
20	.72077	1.95072	.80034	3.47012
50	.72078	1.94891	.80038	3.46509
100	.72078	1.94865	.80038	3.46437
Exact	.72078	1.94856	.80038	3.46410

We may thus conclude that exact solutions can be obtained by this numerical approach.

#### ADDITIONAL RESULTS

After establishing the convergence and accuracy of this new approach, the numerical results for more general problems have been obtained. Some of the additional results are documented here for future comparison by others. All numerical results presented here are for a thick-walled tube with wall ratio  $b/a = 2$ ,  $E/\sigma_0 = 200$ ,  $\nu = 0.3$ ,  $n = 100$ ,  $\omega = E_t/E = 0.1$ . The numerical results are accurate up to four or five digits. Table V shows the results of the dimensionless quantities  $p/\sigma_0$ ,  $\sigma_\theta/\sigma_0$ ,  $\sigma_z/\sigma_0$ ,  $(E/\sigma_0)\epsilon_r$ ,  $(E/\sigma_0)\epsilon_\theta$ ,  $(E/\sigma_0)\epsilon_z$  at

the inside or elastic-plastic boundary  $\rho$  for  $\rho/a = 1.0, 1.1, 1.2, \dots, 2.0$  in a plane-strain tube with strain-hardening parameter  $\omega = 0.1$ . Tables VI and VII show the similar results of the dimensionless stresses, strains, displacement at the bore or elastic-plastic boundary for various stages of elastic-plastic loadings in an open-end or closed-end tube, respectively.

TABLE V. ELASTIC-PLASTIC SOLUTION FOR A PLANE-STRAIN TUBE  
 ( $b/a = 2, E/\sigma_0 = 200, \nu = 0.3, E_t/E = 0.1, n = 100, \epsilon_z = 0$ )

$\rho/a$	$p/\sigma_0$	Inside $\sigma_\theta/\sigma_0$	$\sigma_\theta/\sigma_0 _\rho$	Inside $\sigma_z/\sigma_0$	$\sigma_z/\sigma_0 _\rho$	$\frac{E}{\sigma_0} \epsilon_r _a$	$\frac{E}{\sigma_0} \frac{U_a}{a}$
1.0	.43229	.72049	.72049	.08646	.08646	-.67438	.82424
1.1	.51296	.66972	.75016	.05586	.10453	-.91636	1.00141
1.2	.58362	.63049	.78249	.02537	.12427	-1.17381	1.20371
1.3	.64556	.60225	.81739	-.00409	.14566	-1.44917	1.43022
1.4	.69982	.58427	.85479	-.03148	.16866	-1.73882	1.68000
1.5	.74725	.57572	.89457	-.05589	.19323	-2.04304	1.95207
1.6	.78851	.57579	.93667	-.07658	.21932	-2.36107	2.24535
1.7	.82416	.58376	.98092	-.09302	.24687	-2.69205	2.55869
1.8	.85466	.59898	1.02718	-.10490	.27581	-3.03504	2.89081
1.9	.88041	.62086	1.07530	-.11205	.30606	-3.38898	3.24034
2.0	.90177	.64885	1.12509	-.11447	.33753	-3.75274	3.60578

TABLE VI. ELASTIC-PLASTIC SOLUTION FOR AN OPEN-END TUBE

( $b/a = 2$ ,  $E/\sigma_0 = 200$ ,  $\nu = 0.3$ ,  $E_t/E = 0.1$ ,  $n = 100$ )

$\rho/a$	$p/\sigma_0$	$\frac{\sigma_\theta}{\sigma_0}   \rho$	$\frac{\sigma_\theta}{\sigma_0}   \rho$	$\frac{\sigma_z}{\sigma_0}   a$	$\frac{\sigma_z}{\sigma_0}   \rho$	$\frac{E}{\sigma_0} \epsilon_r   a$	$\frac{E}{\sigma_0} \frac{U_a}{a}$	$\frac{E}{\sigma_0} \epsilon_z$
1.0	.42857	.71429	.71429	0.0	0.0	-.64286	.84286	-.08571
1.1	.50697	.66772	.74089	-.02818	.00090	-.86384	1.01920	-.10234
1.2	.57515	.63143	.76928	-.05498	.00334	-1.09744	1.21679	-.11883
1.3	.63434	.60489	.79916	-.08033	.00689	-1.34207	1.43368	-.13552
1.4	.68546	.58744	.83021	-.10392	.01106	-1.59572	1.66769	-.15275
1.5	.72929	.57829	.86195	-.12542	.01529	-1.85584	1.91616	-.17089
1.6	.76641	.57659	.89385	-.14463	.01895	-2.11934	2.17590	-.19034
1.7	.79730	.58141	.92520	-.16147	.02135	-2.38245	2.44299	-.21149
1.8	.82236	.59175	.95517	-.17604	.02181	-2.64070	2.71271	-.23466
1.9	.84191	.60652	.98280	-.18862	.01965	-2.88902	2.97950	-.26008
2.0	.85630	.62457	1.00708	-.19963	.01432	-3.12192	3.23718	-.28781

TABLE VII. ELASTIC-PLASTIC SOLUTION FOR A CLOSED-END TUBE

( $b/a = 2$ ,  $E/\sigma_0 = 200$ ,  $\nu = 0.3$ ,  $E_t/E = 0.1$ ,  $n = 100$ )

$\rho/a$	$p/\sigma_0$	$\frac{\sigma_\theta}{\sigma_0}   \rho$	$\frac{\sigma_\theta}{\sigma_0}   a$	$\frac{\sigma_z}{\sigma_0}   \rho$	$\frac{\sigma_z}{\sigma_0}   a$	$\frac{E}{\sigma_0} \epsilon_r   a$	$\frac{E}{\sigma_0} \epsilon_z$	$\frac{U_a}{\sigma_0 a}$	$\frac{E}{\sigma_0} \epsilon_z$
1.0	.43301	.72169	.72169	.14434	.14434	-.69282	.05774	.80829	.05774
1.1	.51408	.66902	.75199	.17341	.11139	-.94569	.06863	.98359	.06863
1.2	.58514	.62897	.78518	.20331	.07731	-1.21580	.07861	1.18564	.07861
1.3	.64758	.60074	.82124	.23449	.04394	-1.50300	.08814	1.41370	.08814
1.4	.70247	.58332	.86014	.26717	.01276	-1807142	.09746	1.66712	.09746
1.5	.75069	.57573	.90186	.30145	-.01509	-2.12799	.10665	1.14532	.10665
1.6	.79290	.57710	.94636	.33724	-.03887	-2.46525	.11566	2.24773	.11566
1.7	.82963	.58672	.99359	.37437	-.05811	-2.81846	.12432	2.57373	.12432
1.8	.86323	.60610	1.04858	.41641	-.07381	-3.22466	.13314	2.95874	.13314
1.9	.88833	.62834	1.09583	.45136	-.08243	-3.56994	.13946	3.29352	.13946
2.0	.91091	.65936	1.15052	.49023	-.08775	-3.96597	.14507	3.68518	.14507

## REFERENCES

1. Hill, R., Mathematical Theory of Plasticity, Oxford University Press, 1950.
2. Prager, W. and Hodge, P. G., Theory of Perfectly Plastic Solids, John Wiley & Sons Publication, Inc., 1951, Chapter 4.
3. Hodge, P. G. and White, G. N., "A Quantitative Comparison of Flow and Deformation Theories of Plasticity," J. Appl. Mech., Vol. 17, 1950, pp. 180-184.
4. Chu, S. C., "A More Rational Approach to the Problem of an Elastoplastic Thick-Walled Cylinder," J. of the Franklin Institute, Vol. 294, 1972, pp. 57-65.
5. Chen, P. C. T., "The Finite Element Analysis of Elastic-Plastic Thick-Walled Tubes," Proc. of Army Symposium on Solids Mechanics, 1972, The Role of Mechanics in Design Ballistic Problems, pp. 243-253.
6. Elder, A. S., Tomkins, R. C., and Mann, T. L., "Generalized Plane-Strain in an Elastic, Perfectly Plastic Cylinder, with Reference to the Hydraulic Autofrettage Process," Tran. 21st Conference of Army Mathematicians, 1975, pp. 623-659.
7. Chen, P. C. T., "Generalized Plane-Strain Problems in an Elastic-Plastic Thick-Walled Cylinder," Trans. 26th Conference of Army Mathematicians, 1980, pp. 265-275.
8. Davidson, T. E. and Kendall, D. P., "The Design of Pressure Vessels for Very High Pressure Operation," Watervliet Arsenal Report WWT-6917. Also in Mechanical Behavior of Materials Under Pressure, (H.L.D. Pugh, Ed.), Elsevier Co., 1970, Chapter 2.

9. Yamada, Y., Yoshimura, N., and Sakurni, T., "Plastic Stress-Strain Matrix and Its Application for the Solution of Elastic-Plastic Problems by the Finite Element Method," Int. J. Mech. Sci., Vol. 10, 1968, pp. 343-354.

TECHNICAL REPORT INTERNAL DISTRIBUTION LIST

	<u>NO. OF COPIES</u>
CHIEF, DEVELOPMENT ENGINEERING BRANCH	
ATTN: SMCAR-LCB-D	1
-DA	1
-DP	1
-DR	1
-DS (SYSTEMS)	1
-DS (ICAS GROUP)	1
-DC	1
 CHIEF, ENGINEERING SUPPORT BRANCH	
ATTN: SMCAR-LCB-S	1
-SE	1
 CHIEF, RESEARCH BRANCH	
ATTN: SMCAR-LCB-R	2
-R (ELLEN FOGARTY)	1
-RA	1
-RM	2
-RP	1
-RT	1
 TECHNICAL LIBRARY	
ATTN: SMCAR-LCB-TL	5
 TECHNICAL PUBLICATIONS & EDITING UNIT	
ATTN: SMCAR-LCB-TL	2
 DIRECTOR, OPERATIONS DIRECTORATE	1
 DIRECTOR, PROCUREMENT DIRECTORATE	1
 DIRECTOR, PRODUCT ASSURANCE DIRECTORATE	1

NOTE: PLEASE NOTIFY DIRECTOR, BENET WEAPONS LABORATORY, ATTN: SMCAR-LCB-TL,  
OF ANY ADDRESS CHANGES.

TECHNICAL REPORT EXTERNAL DISTRIBUTION LIST

	<u>NO. OF COPIES</u>		<u>NO. OF COPIES</u>
ASST SEC OF THE ARMY RESEARCH & DEVELOPMENT ATTN: DEP FOR SCI & TECH THE PENTAGON WASHINGTON, D.C. 20315	1	COMMANDER US ARMY AMCCOM ATTN: SMCAR-ESP-L ROCK ISLAND, IL 61299	1
COMMANDER DEFENSE TECHNICAL INFO CENTER ATTN: DTIC-DDA CAMERON STATION ALEXANDRIA, VA 22314	12	COMMANDER ROCK ISLAND ARSENAL ATTN: SMCRI-ENM (MAT SCI DIV) ROCK ISLAND, IL 61299	1
COMMANDER US ARMY MAT DEV & READ COMD ATTN: DRCDE-SG 5001 EISENHOWER AVE ALEXANDRIA, VA 22333	1	DIRECTOR US ARMY INDUSTRIAL BASE ENG ACTV ATTN: DRXIB-M ROCK ISLAND, IL 61299	1
COMMANDER ARMAMENT RES & DEV CTR US ARMY AMCCOM ATTN: SMCAR-LC SMCAR-LCE SMCAR-LCM (BLDG 321) SMCAR-LCS SMCAR-LCU SMCAR-LCW SMCAR-SCM-O (PLASTICS TECH EVAL CTR, BLDG. 351N)	1 1 1 1 1 1 1	COMMANDER US ARMY TANK-AUTMV R&D COMD ATTN: TECH LIB - DRSTA-TSL WARREN, MI 48090	1
SMCAR-TSS (STINFO) DOVER, NJ 07801	2	COMMANDER US ARMY TANK-AUTMV COMD ATTN: DRSTA-RC WARREN, MI 48090	1
DIRECTOR BALLISTICS RESEARCH LABORATORY ATTN: AMXBR-TSB-S (STINFO) ABERDEEN PROVING GROUND, MD 21005	1	COMMANDER US ARMY MISSILE COMD REDSTONE SCIENTIFIC INFO CTR ATTN: DOCUMENTS SECT, BLDG. 4484 REDSTONE ARSENAL, AL 35898	2
MATERIEL SYSTEMS ANALYSIS ACTV ATTN: DRXSY-MP ABERDEEN PROVING GROUND, MD 21005	1	COMMANDER US ARMY FGN SCIENCE & TECH CTR ATTN: DRXST-SD 220 7TH STREET, N.E. CHARLOTTESVILLE, VA 22901	1

NOTE: PLEASE NOTIFY COMMANDER, ARMAMENT RESEARCH AND DEVELOPMENT CENTER,  
US ARMY AMCCOM, ATTN: BENET WEAPONS LABORATORY, SMCAR-LCB-TL,  
WATERVLIET, NY 12189, OF ANY ADDRESS CHANGES.



TECHNICAL REPORT EXTERNAL DISTRIBUTION LIST (CONT'D)

	<u>NO. OF COPIES</u>		<u>NO. OF COPIES</u>
COMMANDER US ARMY MATERIALS & MECHANICS RESEARCH CENTER ATTN: TECH LIB - DRXMR-PL WATERTOWN, MA 01272	2	DIRECTOR US NAVAL RESEARCH LAB ATTN: DIR, MECH DIV CODE 26-27, (DOC LIB) WASHINGTON, D.C. 20375	1 1
COMMANDER US ARMY RESEARCH OFFICE ATTN: CHIEF, IPO P.O. BOX 12211 RESEARCH TRIANGLE PARK, NC 27709	1	COMMANDER AIR FORCE ARMAMENT LABORATORY ATTN: AFATL/DLJ AFATL/DLJG EGLIN AFB, FL 32542	1 1
COMMANDER US ARMY HARRY DIAMOND LAB ATTN: TECH LIB 2800 POWDER MILL ROAD ADELPHIA, MD 20783	1	METALS & CERAMICS INFO CTR BATTELLE COLUMBUS LAB 505 KING AVENUE COLUMBUS, OH 43201	1
COMMANDER NAVAL SURFACE WEAPONS CTR ATTN: TECHNICAL LIBRARY CODE X212 DAHLGREN, VA 22448	1		

NOTE: PLEASE NOTIFY COMMANDER, ARMAMENT RESEARCH AND DEVELOPMENT CENTER,  
US ARMY AMCCOM, ATTN: BENET WEAPONS LABORATORY, SMCAR-LCB-TL,  
WATERVLIET, NY 12189, OF ANY ADDRESS CHANGES.

