

UNCLASSIFIED

AD NUMBER
AD005843
NEW LIMITATION CHANGE
TO Approved for public release, distribution unlimited
FROM Distribution authorized to U.S. Gov't. agencies and their contractors; Administrative/Operational Use; Jan 1953. Other requests shall be referred to Office of Naval Research, Arlington, VA.
AUTHORITY
ONR ltr, 9 Nov 1977

THIS PAGE IS UNCLASSIFIED

Reproduced by

ed Servic
OCUME

Technical Information Agency
SERVICE CENTER

KNOT

UILDING, DAYTON, 2, OHIO

AD -

5843

REPRODUCED FROM
BEST AVAILABLE COPY

REPRODUCED FROM
BEST AVAILABLE COPY

UNCLASSIFIED

THIS REPORT HAS BEEN DELIMITED
AND CLEARED FOR PUBLIC RELEASE
UNDER DOD DIRECTIVE 5200.20 AND
NO RESTRICTIONS ARE IMPOSED UPON
ITS USE AND DISCLOSURE.

DISTRIBUTION STATEMENT A

APPROVED FOR PUBLIC RELEASE;
DISTRIBUTION UNLIMITED.

AD No. 5843

ASTIA FILE COPY

1

1

Tables of Dielectric Materials Volume IV

Technical Report No. 57
Laboratory for Insulation Research
Massachusetts Institute of Technology

January, 1953

TABLES OF DIELECTRIC MATERIALS
VOLUME IV

Laboratory for Insulation Research
Massachusetts Institute of Technology
Cambridge, Massachusetts

O. N. R. Contracts N5ori-07801
N5ori-07858

January, 1953

Table of Contents

	Page
Introduction	v
Dielectric Parameters	viii
Measurements and Accuracy	xv
Tabulated Dielectric Data	1
I. Solids	1
A. Inorganic	1
1. Crystals	1
2. Ceramics	3
a. Steatite Bodies	3
b. Titania and Titanate Bodies	4
c. Porcelains	6
d. Miscellaneous Ceramics	6
e. Ferrites	7
3. Glasses	9
4. Mica and Glass	13
5. Miscellaneous Inorganics	13
B. Organic With or Without Inorganic Components	15
1. Crystals	15
2. Simple Noncrystals	15
3. Plastics	15
a. Phenol-formaldehyde	15
b. Phenol-aniline-formaldehyde	20
c. Aniline-formaldehyde	21
d. Melamine-formaldehyde	21
e. Urea-formaldehyde	23
f. Benzoguanamine-formaldehyde	23
g. Polyamide Resins	23
h. Cellulose Derivatives	23
1) Acetates	23
2) Propionate	25
3) Nitrate	25
4) Methyl Cellulose	25
5) Ethyl Cellulose	25
i. Silicone Resins	25

Table of Contents

	Page
3. Plastics (cont.)	
j. Polyvinyl Resins	27
1) Polyethylene	27
2) Polyisobutylene	28
3) Polyvinyl chloride-acetate	28
4) Polyvinylidene and vinyl chloride	31
5) Polychlorotrifluoroethylene	31
6) Polytetrafluoroethylene	31
7) Polyvinyl alcohol-acetate	33
8) Polyvinyl acetals	34
9) Polyacrylates	34
10) Polystyrene	35
11) Miscellaneous polystyrenes	37
12) Styrene copolymers, linear	38
13) Styrene copolymers, cross-linked	39
14) Polystyrene plus fillers	40
15) Polychlorostyrenes	40
16) Poly-2,5-dichlorostyrene plus fillers	42
17) Polyvinylcyclohexane	46
18) Poly- α -vinyl naphthalene	46
19) Poly-2-vinylpyridine	46
20) Poly-N-vinylcarbazole	46
k. Polyesters	46
m. Alkyd Resins	48
n. Epoxy Resins	49
o. Miscellaneous Plastics	50
4. Elastomers	51
a. Natural Rubber	51
b. Gutta-percha	51
c. Balata	51
d. Cyclized Rubbers	51
e. Buna Rubbers	52
f. Butyl Rubbers	52
g. Nitrile Rubbers	53

Table of Contents

	Page
4. Elastomers (cont.)	
h. Neoprene	53
i. Thiokol	54
j. Silicone rubbers	54
5. Natural Resins	55
6. Asphalts and Cements	56
7. Waxes	56
8. Woods	59
9. Miscellaneous Organics	60
II. Liquids	61
A. Inorganic	61
B. Organic	62
1. Aliphatic	62
2. Aromatic	63
3. Petroleum Oils	65
4. Silicones	66
Supplementary High-Temperature Table	68
Supplementary High-Humidity Table	69
Graphs of Data Plotted versus Temperature	71
Crystals	72
Steatites	78
Titania and Titanate Bodies	88
Porcelains	94
Miscellaneous Ceramics	101
Glasses	101
Mica and Glass	106
Plastics	109
Phenol-formaldehyde Resins	109
Melamine-formaldehyde Resins	112
Polyamide Resin	113
Cellulose Propionate	114
Ethyl Cellulose	115
Polychlorotrifluoroethylene	116
Miscellaneous Vinyls	117

Table of Contents

	Page
Plastics (cont.)	
Styrene Copolymers, Linear	118
Styrene Copolymers, Cross-linked	119
Polyesters	120
Alkyd Resins	123
Epoxy Resin	125
Elastomers	126
Silicone Rubbers	126
Company Index	127
Materials Index	132

Tables of Dielectric Materials

Volume IV

Laboratory for Insulation Research
Massachusetts Institute of Technology
Cambridge, Massachusetts

About five years have passed since Volume III of the "Tables of Dielectric Materials" was issued. The world situation appeared to quiet down at that time, and we hoped to concentrate the whole activity of this laboratory on fundamental research in the field of dielectrics (polarization, magnetization and conduction). The outbreak of the Korean War found our country again unprepared and demonstrated with expensive clarity that we have to live on the alert for the rest of our lives. In consequence, the laboratory felt bound to retain the practical task assumed in World War II of acting as a clearing house for dielectric materials and their uses. One aspect of this activity is our long-range applied research program of tailoring dielectrics to order for specific applications. This work is concentrated at the present time on the problem of shaping the hysteresis loops of ferroelectrics and of ferromagnetic semiconductors to the requirements of the electrical engineer concerned with the development of memory systems, dielectric and magnetic amplifiers and other nonlinear devices. A second aspect is the "Tables of Dielectric Materials."

The "Tables" in their present form summarize the measurements of this laboratory on the complex permittivity (dielectric constant and loss tangent) and the complex permeability of important dielectrics made in this country. They are intended to aid government agencies, engineers and manufacturers in the proper application of dielectrics and in the development of better products. Volume IV reports on about 250 new materials; simultaneously, it has taken over and amplified the measurements given in the previous volumes as far as they still are of special interest. A number of materials now not in produc-

tion have been retained for this reason but are indicated as "discontinued." The total number of materials included amounts to over 600.

The selection of these materials was undertaken with the full co-operation of the manufacturers concerned. The laboratory measures any important new material free of charge for inclusion in the "Tables" if the manufacturer supplies all additional essential information. If some of this information is "confidential," it is locked away in our files and will be made available only after release by the manufacturer.

We are fully aware that these data should be expanded, especially towards higher temperatures and frequencies. Furthermore, additional measurements on d.c. conductivity, breakdown strength and other electric parameters would be of great value, and a presentation of the materials as in Volume III, where the dielectric characteristics of each individual dielectric have been plotted and essential information given on composition, properties, methods of handling and recommended uses. Finally, a real "dielectric analysis" of the materials should be undertaken, linking their dielectric response to composition and molecular structure. We have to ask for the indulgence of the users of these "Tables" on these scores; *ultra posse nemo obligatur*, or, in free translation, our budget is already stretched to the breaking point by our present obligations.

Volume IV does not contain our more extensive measurements on ferroelectrics and ferromagnetics. These data on nonlinear dielectrics will be issued in a separate Volume V as soon as they are reasonably complete.

The measurements were made by W. B. Westphal, group leader of our dielectric measurements group, who was ably supported by three staff operators: Helen M. Dunn, Patricia A. Fergus and Elizabeth McCarty. Invaluable help in the editing and correcting of the manuscript was given by Harriet B. Armstrong.

This work was sponsored under our O.N.R. contracts jointly by the Navy Department (Office of Naval Research), the Army Signal Corps and the Air Force

(Air Materiel Command); we thank all three Services for their understanding and co-operation.

von Hippel, Director
Laboratory for Insulation Research

Dielectric Parameters

1. ϵ' , the dielectric constant or permittivity relative to vacuum, also designated in the literature as K , κ , ϵ , D.C., etc.
2. $\tan \delta$ or $\tan \delta_d$, the dielectric loss tangent or dissipation factor, also designated in the literature as D.F., $1/Q$, and when losses are low, as power factor or $\cos \theta$.
3. μ' , the magnetic permeability relative to vacuum, also given in the literature as μ' or μ_0 .
4. $\tan \delta_m$, the magnetic loss tangent.
5. ρ , the a.c. volume resistivity in ohm cm. This parameter is used in these tables only for very high-loss materials.

Transformation to other parameters. The dielectric loss factor relative to vacuum, ϵ''/ϵ_0 , is the product of the dielectric loss tangent and ϵ'/ϵ_0 . A.c. volume conductivity, σ , is given by

$$\sigma = \frac{1}{\rho} = \frac{f(\epsilon'/\epsilon_0)\tan \delta}{1.8 \times 10^{12}} \quad [\text{mho cm.}] (f \text{ in c/s})$$

A chart is given (page x) for approximate calculations of σ or ρ from the data given in the tables.

The magnetic loss factor relative to vacuum, μ''/μ_0 , is the product of the magnetic loss tangent and μ'/μ_0 (in analogy to the dielectric loss factor). In the literature, the loss factor is sometimes given as $\frac{1}{\mu_0 Q}$ or in our notation, $\tan \delta_m/(\mu'/\mu_0)$.

The attenuation constant, α , for propagation in free space is

$$\frac{2\pi}{\lambda_0} \left[\frac{\mu'\epsilon'}{\mu_0\epsilon_0} \frac{1 - \tan \delta_d \cdot \tan \delta_m}{2} \left([1 + \tan^2(\delta_d + \delta_m)]^{1/2} - 1 \right) \right]^{1/2},$$

which for nonmagnetic dielectrics reduces to

$$\frac{2\pi}{\lambda_0} \left(\frac{\epsilon'}{\epsilon_0} \right)^{1/2} \left[\frac{(1 + \tan^2 \delta_d)^{1/2} - 1}{2} \right]^{1/2}.$$

Charts for finding α in terms of ϵ'/ϵ_0 and $\tan \delta_d$ are included in this report (pages xi-xiii). They apply also to magnetic dielectrics when the product $(\mu'/\mu)(\epsilon'/\epsilon_0)$ is substituted for ϵ'/ϵ_0 and an equivalent combined loss tangent $\tan \delta_e$ is used instead of $\tan \delta_d$. A graph is given (page xiv) showing $\tan \delta_e$ for values of $\tan \delta_d$ and $\tan \delta_m$ in the range 0.1 to 10. For smaller values, $\tan \delta_e = \tan \delta_d + \tan \delta_m$.

The phase constant β for propagation in free space is


$$\frac{2\pi}{\lambda_0} \left[\frac{\mu' \epsilon'}{\mu_0 \epsilon_0} \frac{1 - \tan \delta_d \cdot \tan \delta_m}{2} \left(\left[1 + \tan^2(\delta_d + \delta_m) \right]^{1/2} + 1 \right) \right]^{1/2},$$

which reduces for nonmagnetic materials to


$$\frac{2\pi}{\lambda_0} \left(\frac{\epsilon'}{\epsilon_0} \right)^{1/2} \left[\frac{(1 + \tan^2 \delta_d)^{1/2} + 1}{2} \right]^{1/2}$$

The intrinsic impedance Z of the material is

$$377 \left(\frac{\mu^* \epsilon_0}{\mu_0 \epsilon^*} \right)^{1/2}$$



Conductivity-resistivity as function of ϵ''/ϵ_0 and frequency.






EQUATION

$$8.686\alpha = \frac{8.636 \cdot \pi \cdot \tan \delta}{\lambda_o} \sqrt{\frac{\epsilon' \mu}{\epsilon_o \mu_o}}$$

$$\frac{\mu}{\mu_o} = 1$$

$\tan \delta = 0.0001 \text{ to } 0.05$








EQUATION

$$8.686\alpha = \frac{17.37\pi}{\lambda_0} \sqrt{\frac{\epsilon'\mu}{\epsilon_0\mu_0} \frac{\sqrt{1+\tan^2\delta}-1}{2}}$$

$$\frac{\mu}{\mu_0} = 1$$

$\tan \delta = 0.05 \text{ to } 50$








EQUATION

$$8.686\alpha = \frac{17.37\pi}{\lambda_0} \sqrt{\frac{\epsilon'\mu}{\epsilon_0\mu_0}} \frac{\tan\delta}{2}$$

$$\frac{\mu}{\mu_0} = 1$$

$\tan\delta = 50 \text{ to } 100$





Measurements and Accuracy

The measurements have been made, in general, on only one batch of the material and refer, unless otherwise specified, to samples dried over phosphorous pentoxide. Due to the wide variety of materials and improvements in techniques, no figures of general validity can be given concerning the accuracy of these measurements. For ϵ'/ϵ_0 , the nominal accuracy is $\pm 2\%$; the accuracy trends are toward $\pm 1\%$ for rigid, low-loss materials ($\tan \delta < 0.005$) and $\pm 5\%$ for high-loss materials ($\tan \delta > 1$). For $\tan \delta_d$, the nominal accuracy is $\pm 5\%$; for high-loss materials, the error may be $\pm 10\%$. For very low-loss materials ($\tan \delta < 0.002$), the accuracy is ± 0.0001 when the losses are given as multiples of 0.0001. When the loss is expressed in multiples of 0.00001, the error may be ± 0.00003 . For μ'/μ_0 , the nominal accuracy is $\pm 5\%$, for $\tan \delta_m$, $\pm 10\%$.

Field strengths. The linear dielectrics, those normally not field-strength sensitive, were measured at field strengths of approximately 50 volts per cm. in the frequency range 10^2 to 10^8 c/s and at lower field strengths at higher frequencies. At high temperatures (near 500°C) many of these materials show field-strength sensitivity, particularly at low frequencies. The effects may be wholly or partly due to space charge polarization.

The ferroelectric and ferromagnetic materials, unless otherwise noted, were measured at field strengths in their linear region. The values thus measured are the initial permittivity and permeability. Typical field strengths are 40 volts/cm. for titanate ceramics, 0.01 volts/cm. for KDP crystals, 0.01 oersteds for the ferrites.

1. Crystals (cont.)

Sodium chloride ^a	$\frac{T}{T^{\circ}C}$	$\frac{1 \times 10^2}{5.90}$	$\frac{1 \times 10^3}{5.90}$	$\frac{1 \times 10^4}{5.90}$	$\frac{1 \times 10^5}{5.90}$	$\frac{1 \times 10^6}{5.90}$	$\frac{1 \times 10^7}{5.90}$	$\frac{1 \times 10^8}{3 \times 10^8}$	$\frac{1 \times 10^9}{3 \times 10^9}$	$\frac{1 \times 10^{10}}{2.5 \times 10^{10}}$
	25	ϵ'/ϵ_0	$\tan \delta$	ϵ'/ϵ_0	$\tan \delta$	ϵ'/ϵ_0	$\tan \delta$	ϵ'/ϵ_0	$\tan \delta$	ϵ'/ϵ_0
	85	6.35	6.11	6.00	5.98	5.98	5.98	5.97	< 5	< 3.9
		170	240	70	6	< 2	< 2	< 2	< 2	< 3.9

a. Fresh crystals (Harskaw). b. Measured with field $\perp$ to cuts indicated. Crown at Lab. Ins. Res. c. U.S.P. d. Crown at Eng. Res. and Dev. Lab., Fort Belvoir, Va. e. KRS-6, 60% ThBr, 40% ThCl. f. KRS-5, 42% ThBr, 58% ThI. g. Linde Air.

I. Solids, A. Inorganic

2. Ceramics

a. Steatite Bodies

ALSiMag A-35^a

ALSiMag A-196^a

ALSiMag 211^a

ALSiMag 228^a

ALSiMag 243^a

ALSiMag 393^b

Ceramic F-66^c

Steatite Type 302^d

Steatite Type 400^d

Steatite Type 410^d

Steatite Type 452^d

Values for tan δ are multiplied by 10^4 ; frequency given in c/s.

T°C	1×10^2	1×10^3	1×10^4	1×10^5	1×10^6	1×10^7	3×10^8	3×10^9	1×10^{10}	2.5×10^{10}
23	ϵ'/ϵ_0	6.10	5.96	5.89	5.86	5.84	5.80	5.75	-----	5.36
	tan δ	150	100	70	50	38	35	37	-----	58
85	ϵ'/ϵ_0	6.84	6.37	6.11	5.96	5.86	5.80	5.75	-----	5.50
	tan δ	890	370	175	103	77	50	50	-----	47
25	ϵ'/ϵ_0	5.90	5.88	5.84	5.80	5.70	5.65	5.60	5.24	5.18
	tan δ	30	59	79.5	55	30.5	19	16	26	38
81	ϵ'/ϵ_0	5.90	5.88	5.84	5.80	5.70	5.65	5.60	-----	5.42
	tan δ	58	40	46.5	70.5	66	40.5	24	-----	18
25	ϵ'/ϵ_0	6.00	5.98	5.98	5.97	5.97	5.96	5.96	5.90	-----
	tan δ	92	34	12	6	5	4	4	14	-----
25	ϵ'/ϵ_0	6.40	6.40	6.40	6.40	6.36	6.30	6.20	5.97	5.83
	tan δ	15.6	20	20	15.6	12.4	11.2	10	13	42
81	ϵ'/ϵ_0	6.52	6.46	6.40	6.40	6.36	6.30	-----	5.95	-----
	tan δ	35.6	22	18	21.5	18.4	11.8	-----	11	-----
22	ϵ'/ϵ_0	6.30	6.30	6.28	6.25	6.22	6.17	6.10	5.76	5.75
	tan δ	12.5	4.5	4.0	< 9	3.7	3.5	3	8.5	12
85	ϵ'/ϵ_0	6.37	6.37	6.37	6.36	6.32	6.28	-----	5.88	-----
	tan δ	21	13.7	8.0	< 9	3.7	3.5	-----	6	-----
24	ϵ'/ϵ_0	4.95	4.95	4.95	4.95	4.95	4.95	4.95	4.95	4.91
	tan δ	38	23	16	12	10	10	10	9.7	14
25	ϵ'/ϵ_0	6.22	6.22	6.22	6.22	6.22	6.22	6.22	-----	6.2
	tan δ	14.5	9	5	2	1	1.5	3	-----	11
25	ϵ'/ϵ_0	5.80	5.80	5.80	5.80	5.80	5.80	5.80	5.8	5.8
	tan δ	32	20	16	13	12	12	12	19	36
25	ϵ'/ϵ_0	5.54	5.54	5.54	5.54	5.54	5.54	5.54	5.5	5.5
	tan δ	160	100	72	60	50	45	39	53	53
25	5.77	5.77	5.77	5.77	5.77	5.77	5.77	5.77	5.7	5.7
	tan δ	55	30	16	9	7	6	6	22	22
25	ϵ'/ϵ_0	8.15	8.15	8.15	8.15	8.15	8.15	8.15	8.15	8.15
	tan δ	65	28	17	12	10	10	10	31	31

a. Magnesium silicate (Am. Lava). b. 93% Al_2O_3 , 6% SiO_2 , 1% MgO (Am. Lava). c. 60% talc, 15% kaolin, 17.5% $BaCO_3$, 7.5% $MgCO_3$ (Bell). d. Centralab.

I. Solids, A. Inorganic (cont.)

2. Ceramics (cont)

a. Steatite Bodies(cont.)		T°C												
Steatite Body 7292 ^a	25	ϵ'/ϵ_0	1×10^2	1×10^3	1×10^4	1×10^5	1×10^6	1×10^7	1×10^8	3×10^8	3×10^9	1×10^{10}	2.5×10^{10}	
			6.55	6.55	6.54	6.53	6.53	6.53	6.53	6.53	6.52	6.51		
	14	$\tan \delta$	14	7	4.8	3.9	4.9	5.2	6.2	6.8	9	10.9		
	24	ϵ'/ϵ_0	6.04	6.04	6.04	6.04	6.04	6.04	---	---	5.90	5.71		
		$\tan \delta$	25	19	15	13	11	10	---	---	24	30		
Grolite #29 ^b														

Crolite #29^b

b. Titania and Titanate

Bodies

Ceramic NPOT96 ^c	25	ϵ'/ϵ_0	29.5	29.5	29.5	29.5	29.5	29.5	29.5	-----	-----	28.9	
		$\tan \delta$	12	4.9	3.3	2.5	1.6	1.7	2	-----	-----	20	
Ceramic N75OT96 ^c	25	ϵ'/ϵ_0	83.4	83.4	83.4	83.4	83.4	83.4	83.4	-----	-----	83.4	
		$\tan \delta$	5.7	4.5	3.5	2.5	2.2	2.3	4.6	-----	-----	14.6	
Ceramic N14OOT110 ^c	25	ϵ'/ϵ_0	131	130.8	130.7	130.5	130.2	130.2	130.0	-----	-----		
		$\tan \delta$	6.7	5.5	3.3	1.4	3.0	5.5	7.0	-----	-----		
Body T106 ^c	25*	ϵ'/ϵ_0	1518	1508	1480								
		$\tan \delta$	31	87	99								

TI Pure R-200^d

	25**	ϵ'/ϵ_0	1308	1280	1260	1245	1232	1220	1210				
		$\tan \delta$	98	120	140	100	85	150	420				
	26	ϵ'/ϵ_0	100	100	100	100	100	100	100	-----	-----	90	
		$\tan \delta$	23	15	6.2	4	3	2.5	2.5	-----	-----	20	
	78	ϵ'/ϵ_0	97.5	97	97	97	97	97					
		$\tan \delta$	130	60	33	13	4.5	2.3					

Tam Ticon T-J, T-L and T-M^e

	24	ϵ'/ϵ_0	96	96	96	96	96	96	-----	-----	96	-----	91
		$\tan \delta$	8	4.5	2	1	2	3	-----	-----	3.4	-----	33
	78	ϵ'/ϵ_0	90	89	88.5	88	87.5	87					
		$\tan \delta$	55	16	4	4	4	4					

Tam Ticon MC^f

	25	ϵ'/ϵ_0	13.9	13.9	13.9	13.9	13.9	13.9	13.9	13.9	13.8	13.8	13.7
		$\tan \delta$	15	11	9	7	4	4	5	9	17	28	65

a. Gen. Ceramics and Steatite. b. Al₂O₃, SiO₂, MgO, CaO, BaO (Crowley). c. Amer. Lava. d. Rutile (Dupont, fired at Lab. Ins. Res.). e. Rutile (Titanium Alloy, fired at Lab. Ins. Res.). f. Magnesium titanate (Titanium Alloy, fired at Lab. Ins. Res.).

* - 3/4" Disk. ** 0.2" disk cut from 3/4" disk.

I. Solids, A. Inorganic (cont.)

2. Ceramics (cont.)

b. Titanate and titanate

bodies (cont.)

bodies (cont.)	T°C	$\frac{1 \times 10^2}{\epsilon'/\epsilon_0}$	$\frac{1 \times 10^3}{\tan \delta}$	$\frac{1 \times 10^4}{\epsilon'/\epsilon_0}$	$\frac{1 \times 10^5}{\tan \delta}$	$\frac{1 \times 10^6}{\epsilon'/\epsilon_0}$	$\frac{1 \times 10^7}{\tan \delta}$	$\frac{1 \times 10^8}{\epsilon'/\epsilon_0}$	$\frac{3 \times 10^8}{\tan \delta}$	$\frac{1 \times 10^{10}}{\epsilon'/\epsilon_0}$	$\frac{2.5 \times 10^{10}}{\tan \delta}$
Titania Ceramic ^a	25	---	---	---	---	33	---	---	---	---	---
	25	---	---	---	---	5.2	60.5	60	---	---	---
	25	---	---	---	---	---	8.3	11	---	---	---
Titania Ceramic ^b	25	---	---	---	---	---	---	---	---	---	---
Tam Ticon C ^c	25	167.8	167.7	167.7	167.7	167.7	167.7	166.8	165	165	165
	82	13.6	4.4	2.5	2	2	2	5	23	85	---
	82	157	156	156	156	156	156	---	---	---	---
	82	400	49	11	6	6	6	---	---	---	---
Tam Ticon S ^d	25	234	233	232	232	232	232	232	---	230	---
	25	21	11	8	5	2	1	1	---	28	---
Tam Ticon B ^e	25	1240	1200	1170	1153	1143	1140	---	1100	150	100
	25	360	130	150	120	105	75	---	500	3000	6000
Tam Ticon BS ^f	25	8700	8500	8200	8100	8000	8000	8000	7000	2000	200
(discontinued)	25	230	200	230	90	48	98	400	5000	4000	---
Mix 71 BaTiO ₃ ^g	25	1740	1720	1680	1650	---	---	---	---	---	---
	25	63	107	170	150	---	---	---	---	---	---
Mix 72 BaTiO ₃ 90% ^g	25	1310	13.7	1300	1280	1275	---	---	---	---	---
SrTiO ₃ 10% ^g	25	31	43	70	77	46	---	---	---	---	---
Mix 73 BaTiO ₃ 80% ^g	25	2163	2160	2120	2020	1960	---	---	---	---	---
SrTiO ₃ 20% ^g	25	94	155	280	200	75	---	---	---	---	---
Mix 74 BaTiO ₃ 70.9% ^g	25	2990	2970	2910	2840	2820	---	---	---	---	---
SrTiO ₃ 29.1% ^g	25	47	61	88	67	40	---	---	---	---	---
Mix 75 BaTiO ₃ 60% ^g	25	1125	1122	1120	1110	1090	---	---	---	---	---
SrTiO ₃ 40% ^g	25	110	72	45	30	19	---	---	---	---	---

a. 84.3% TiO_2 , 11.1% MgCO_3 , 4.6% MgO , 15.4% TiO_2 , 15.4% BaO (Lab. Ins. Res.). b. 84.6% TiO_2 , 15.4% BaO (Lab. Ins. Res.). c. Calcium titanate (Titanium Alloy; fired at Lab. Ins. Res.). d. Strontium titanate (Titanium Alloy; fired at Lab. Ins. Res.). e. Barium titanate (Titanium Alloy; fired at Lab. Ins. Res.). f. 79% barium, 21% strontium titanate (Titanium Alloy; fired at Lab. Ins. Res.). g. Thin sheet (Glenco).

I. Solids, A. Inorganic (cont.)

2. Ceramics (cont.)

b. Titanate and titanate bodies (cont.)

	T ^o C	ϵ'/ϵ_0	$\tan \delta$	$\frac{1 \times 10^2}{740}$	$\frac{1 \times 10^3}{738}$	$\frac{1 \times 10^4}{735}$	$\frac{1 \times 10^5}{732}$	$\frac{1 \times 10^6}{730}$	$\frac{1 \times 10^7}{---$	$\frac{1 \times 10^8}{---$	$\frac{3 \times 10^8}{---$	$\frac{3 \times 10^9}{---$	$\frac{1 \times 10^{10}}{---$
Mix 76 BaTiO ₃ 50% ^a	25			10.7	6	7	21	28	---	---	---	---	---
SrTiO ₃ 50%													
Mix 77 BaTiO ₃ 68.1% ^a	25			892	890	890	890	890	---	---	---	---	---
SrTiO ₃ 28.1%													
MgZrO ₃ 2.8%				16	10	12	25	8	---	---	---	---	---

c. Porcelains

Zirconium Porcelain Zi-4 ^b	25	ϵ'/ϵ_0	$\tan \delta$	6.44	6.40	6.35	6.32	6.32	6.30	6.30	6.23	6.18
				59	40	31	27	23	25	27	45	57
Porcelain, wet process ^c	25	ϵ'/ϵ_0	$\tan \delta$	6.47	6.24	6.08	5.98	5.87	5.82	5.75	---	5.51
				280	180	130	105	90	115	140	---	155
Porcelain, dry process ^c	25	ϵ'/ϵ_0	$\tan \delta$	5.50	5.36	5.23	5.14	5.08	5.04	5.02	---	4.74
				220	140	105	85	75	70	98	---	156
Coors AI-200 ^d	25	ϵ'/ϵ_0	$\tan \delta$	8.83	8.83	8.82	8.80	8.80	8.80	---	8.79	8.79
				14	5.7	4.8	3.8	3.3	3.2	---	10	18
Porcelain #4462 ^e	25	ϵ'/ϵ_0	$\tan \delta$	8.99	8.95	8.95	8.95	8.95	8.95	8.93*	8.90	8.80
				22	9.1	6.0	3.0	2.0	2.0	9*	11	14
Coors AB-2 ^d	25	ϵ'/ϵ_0	$\tan \delta$	8.22	8.18	8.17	8.17	8.16	8.16	---	6.14	8.08
				20	13.4	11.4	10.5	9.0	7.5	---	16	27
ALSiMag 491 ^f	25	ϵ'/ϵ_0	$\tan \delta$	---	---	---	---	8.74	---	---	8.60	8.50
				---	---	---	---	22	---	---	17	23
d. Miscellaneous Ceramics												
Beryllium oxide ^g	25	ϵ'/ϵ_0	$\tan \delta$	4.61	4.47	4.41	4.34	4.28	4.24	4.23	---	4.20
				170	84	74	72	38	19	12.5	---	5
Porous Ceramic AF-497 ^h	25	ϵ'/ϵ_0	$\tan \delta$	---	---	---	---	---	---	---	---	1.472
				---	---	---	---	---	---	---	---	17

a. Thin sheet (Glenco). b. Coors. c. Knox. d. Aluminum oxide (Coors). e. Aluminum oxide (Frenchtown Porcelain). f. Aluminum oxide (Amer. Lava). g. Norton. h. 53% diatomaceous-earth, 32% anthracite coal, 5.5% whiting (Stupakoff). *Frequency = 1×10^9 .

Values for $\tan \delta$ are multiplied by 10^4 ; frequency given in c/s.

I. Solids, A. Inorganic, 2. Ceramics (cont.)

e. Ferrites

Frequency given in c/s; temperature = 25°C.

Freq.	Crowley 20 ^a				Crowley 70 ^a				Crowley BX113 ^{a*}				Crowley BX114 ^a			
	ϵ'/ϵ_0	$\tan \delta_d$	μ'/μ_0	$\tan \delta_m$	ϵ'/ϵ_0	$\tan \delta_d$	μ'/μ_0	$\tan \delta_m$	ϵ'/ϵ_0	$\tan \delta_d$	μ'/μ_0	$\tan \delta_m$	ϵ'/ϵ_0	$\tan \delta_d$	μ'/μ_0	$\tan \delta_m$
10 ²	35400	2.41	---	---	440000	26.7	400	---	19.4	.59	---	---	29	.58	21	---
4x10 ²	9900	3.94	---	---	---	---	---	---	---	---	---	---	19.2	---	---	---
10 ³	5430	2.65	120	---	350000	3.35	400	---	14.7	.20	14.5	---	19.2	.30	17.5	---
10 ⁴	1590	1.47	120	---	250000	.78	400	---	13.0	.066	14.5	---	14.9	.15	15.6	---
10 ⁵	480	1.6	120	---	123000	.64	400	---	12.8	.024	14.5	---	12.9	.06	14.5	---
10 ⁶	---	---	---	---	---	---	440	.28	12.6	.010	14	---	12.6	.024	---	---
3x10 ⁶	---	---	108	.08	---	---	147	1.53	---	---	13	<.1	---	---	16	<.1
10 ⁷	18	1.1	84	.48	16400	1.4	92	.24	12.5	.005	12,47	<.1, .02	12.4	.007	18.5	<.1
2x10 ⁷	---	---	---	---	---	---	---	---	---	---	12	<.2	---	---	---	---
3x10 ⁷	---	---	47	.92	---	---	---	---	---	---	12.8, 46	.05, .03	---	---	20.7	<.1
6.5x10 ⁷	---	---	35	1.16	---	---	41	1.92	---	---	51	.25	---	---	23	<.1
8x10 ⁷	---	---	24.6	1.58	---	---	29	2.36	---	---	49.4	.46	---	---	24	<.1
10 ⁸	---	---	17.9	2.15	---	---	18	3.35	12.5	.0026	37	.74	12.4	.0037	26	<.1
1.2x10 ⁸	---	---	15.9	1.98	---	---	21	2.58	---	---	34	.9	---	---	30	.13
1.4x10 ⁸	---	---	24.6	1.43	---	---	---	---	---	---	28.5	1.15	---	---	31	.32
3x10 ⁸	---	---	---	---	---	---	---	---	---	---	17.9	1.5	---	---	17.6	1.61
9x10 ⁸	12	.07	---	---	---	---	---	---	---	---	5.34	3.4	---	---	3.25	4.46
10 ⁹	12	.07	.98	5.8	---	---	---	---	---	---	---	---	---	---	---	---
3x10 ⁹	12	.04	.28	7.2	42	---	.19	10.6	12	<.012	1.74	1.9	12	<.01	1.34	2.48

a. H. L. Crowley.

*Two samples were measured; they differed as shown by the two sets of values at 10⁷ and 3x10⁷. Lower μ'/μ_0 values were obtained on sample cut from 2" disk, higher values on 3/4" disk. ϵ'/ϵ_0 values did not differ.

I. Solids, A. Inorganic, 2. Ceramics (cont.)

a. Ferrites (cont.)

Frequency given in c/s; temperature = 25°C.

Freq.	Ferramic A ^{a,b}				Ferramic B ^a				Ferramic C ^a				Ferramic D ^a			
	ϵ'/ϵ_0	$\tan \delta_d$	μ'/μ_0	$\tan \delta_m$	ϵ'/ϵ_0	$\tan \delta_d$	μ'/μ_0	$\tan \delta_m$	ϵ'/ϵ_0	$\tan \delta_d$	μ'/μ_0	$\tan \delta_m$	ϵ'/ϵ_0	$\tan \delta_d$	μ'/μ_0	$\tan \delta_m$
10 ³	9.82	.112	19.6	----	20800	4.5	----	----	110000	2.4	240	----	35000	84	380	----
10 ⁴	9.30	.026	19.6	----	19700	4.8	94	----	32000	1.44	240	----	35000	8.1	380	----
10 ⁵	9.13	.0076	19.5	----	15500	.78	----	----	22000	1	----	----	----	----	----	----
10 ⁶	8.99	.0032	19.4	----	8600	.65	----	----	13500	1.32	242	.015	17600	.77	510	<.05
2x10 ⁶	----	----	20.0	----	----	----	108	.027	----	----	259	----	----	----	550	.18
3x10 ⁶	----	----	22	----	----	----	----	----	----	----	267	.068	11000	.80	565	.47
4x10 ⁶	----	----	----	----	----	----	----	----	----	----	----	----	----	----	411	.55
7x10 ⁶	----	----	23	----	----	----	----	----	----	----	----	----	----	----	112	2.76
10 ⁷	8.87	.0016	24.6	.08	1060	2.9	107	.36	2850	2.0	195	.85	6000	.90	52	4.0
2x10 ⁷	----	----	25.4	.177	----	----	----	----	----	----	78	1.6	----	----	17.7	5.8
3x10 ⁷	----	----	----	----	----	----	62	.67	----	----	33.5	2.7	----	----	12.9	6.2
5x10 ⁷	8.5	<.1	12.5	1.00	----	----	----	----	----	----	----	----	485	2.9	----	----
10 ⁸	----	----	7.2	1.29	51	1.56	14.4	1.12	64	.70	16.8	.61	106	3.1	1.09	18.4
3x10 ⁸	----	----	2.8	1.6	----	----	----	----	----	----	----	----	----	----	----	----
5x10 ⁸	----	----	2.0	1.2	----	----	----	----	----	----	----	----	----	----	----	----
10 ⁹	8.5	<.1	3.0	.67	----	----	----	----	----	----	----	----	----	----	----	----
2x10 ⁹	----	----	1.0	2.0	----	----	----	----	----	----	----	----	----	----	----	----
3x10 ⁹	----	----	.6	2.0	20	.68	.29	10	24.6	1.14	.18	22	35	3.3	.15	20
10 ¹⁰	8.5	<.1	1.0	----	15	.52	.42	.37	18.7	.58	.51	1.26	30	1.35	1.9	1.0
Freq.	Ferramic G ^a				Ferramic H ^a				Ferramic I ^a				Ferramic J ^a			
	ϵ'/ϵ_0	$\tan \delta_d$	μ'/μ_0	$\tan \delta_m$	ϵ'/ϵ_0	$\tan \delta_d$	μ'/μ_0	$\tan \delta_m$	ϵ'/ϵ_0	$\tan \delta_d$	μ'/μ_0	$\tan \delta_m$	ϵ'/ϵ_0	$\tan \delta_d$	μ'/μ_0	$\tan \delta_m$
10 ³	----	----	450	----	670000	7.2	720	----	12000	2.9	890	----	----	----	256	----
10 ⁴	23.5	.60	400	----	152500	4.5	720	----	7800	.81	890	----	17.5	1.95	256	----
10 ⁵	15.5	.216	360	----	22400	4.2	720	----	930	3.1	890	<.1	13.8	.37	256	----
10 ⁶	13.6	.069	340	.05	1600	8.2	690	.18	90	4.7	1050	.29	12.6	.062	256	.015
10 ⁷	13.0	.026	245	.66	----	----	300	1.33	26	2.1	215	1.6	12.4	.015	196	.66
3x10 ⁸	----	----	----	----	----	----	----	----	13.6	.114	10.7	1.03	----	----	----	----
3x10 ⁹	----	----	----	----	----	----	----	----	12	.012	.90	.04	----	----	----	----

a. Gen. Ceramics and Steatite. b. Data partly from Rado, Wright and Emerson, Phys. Rev. 80, 273 (1950).

I. Solids, A. Inorganic (cont.)

Values for $\tan \delta$ are multiplied by 10^4 ; frequency given in c/s.

3. Glasses	T ^o C	ϵ'/ϵ_0	$\tan \delta$	$\frac{1 \times 10^2}{\epsilon'/\epsilon_0}$	$\frac{1 \times 10^3}{\tan \delta}$	$\frac{1 \times 10^4}{\epsilon'/\epsilon_0}$	$\frac{1 \times 10^5}{\tan \delta}$	$\frac{1 \times 10^6}{\epsilon'/\epsilon_0}$	$\frac{1 \times 10^7}{\tan \delta}$	$\frac{1 \times 10^8}{\epsilon'/\epsilon_0}$	$\frac{3 \times 10^8}{\tan \delta}$	$\frac{1 \times 10^{10}}{\epsilon'/\epsilon_0}$	$\frac{2.5 \times 10^{10}}{\tan \delta}$
Phosphate Glass #2043r ^a	25	ϵ'/ϵ_0	$\tan \delta$	5.25	5.25	5.25	5.25	5.25	5.25	5.24	5.23	5.00	4.93
Phosphate Glass #2279x ^b	25	ϵ'/ϵ_0	$\tan \delta$	4.92	4.92	4.92	4.92	4.92	4.92	4.92	4.92	4.9	4.9
Borosilicate Glass ^c	25	ϵ'/ϵ_0	$\tan \delta$	4.05	4.05	4.05	4.05	4.05	4.05	4.05	4.05	4.05	4.05
Corning 001c ¹	24	ϵ'/ϵ_0	$\tan \delta$	13.6	8.6	4.4	4.4	5.8	7.0	8.0	10.6	15.5	34
Corning 0014 ^a	25	ϵ'/ϵ_0	$\tan \delta$	6.68	6.63	6.57	6.50	6.43	6.39	6.33	6.1	5.96	5.87
Corning 0080 ^f	23	ϵ'/ϵ_0	$\tan \delta$	77.5	53.5	35	23	16.5	15	23	60	90	110
Corning 0090 ^g	20	ϵ'/ϵ_0	$\tan \delta$	6.78	6.77	6.76	6.75	6.73	6.72	6.70	6.69	6.64	6.62
Corning 0100 ^h	25	ϵ'/ϵ_0	$\tan \delta$	23.1	17.2	14.4	12.2	12.4	13.8	17.0	19.5	70	180
Corning 0120 ⁱ	23	ϵ'/ϵ_0	$\tan \delta$	8.30	7.70	7.35	7.08	6.90	6.82	6.75	6.71	6.71	8.25
Corning 0100 ^h	25	ϵ'/ϵ_0	$\tan \delta$	9.15	9.15	9.15	9.14	9.12	9.10	9.02	8.67	8.45	122
Corning 0120 ⁱ	23	ϵ'/ϵ_0	$\tan \delta$	12	8	7	7	8	12	18	54	103	6.87
Corning 1770 ^j	25	ϵ'/ϵ_0	$\tan \delta$	7.18	7.17	7.16	7.14	7.10	7.10	7.07	7.00	6.95	106
Corning 1990 ^k	24	ϵ'/ϵ_0	$\tan \delta$	6.75	6.70	6.66	6.65	6.65	6.65	6.65	6.64	6.60	6.51
Corning 1991 ^m	24	ϵ'/ϵ_0	$\tan \delta$	46	30	20	14	12	13	18	41	63	127
Corning 3320 ⁿ	24	ϵ'/ϵ_0	$\tan \delta$	6.25	6.16	6.10	6.03	6.00	6.00	6.00	5.95	5.83	5.44
Corning 7040 ^o	25	ϵ'/ϵ_0	$\tan \delta$	49.5	42	33	26	27	34	38	56	84	140
Corning 7050 ^p	25	ϵ'/ϵ_0	$\tan \delta$	8.40	8.38	8.35	8.32	8.30	8.25	8.20	7.99	7.94	7.84
	24	ϵ'/ϵ_0	$\tan \delta$	4	4	3	4	5	7	9	19.9	42	112
	24	ϵ'/ϵ_0	$\tan \delta$	8.10	8.10	8.08	8.08	8.08	8.06	8.00	7.92	7.83	7.83
	24	ϵ'/ϵ_0	$\tan \delta$	12	9	6	5	5	7	12	38	51	51
	24	ϵ'/ϵ_0	$\tan \delta$	5.00	4.93	4.88	4.82	4.79	4.78	4.77	4.74	4.72	4.7
	25	ϵ'/ϵ_0	$\tan \delta$	80	58	43	34	30	30	32	55	73	120
	25	ϵ'/ϵ_0	$\tan \delta$	4.84	4.82	4.79	4.77	4.73	4.70	4.68	4.67	4.64	4.52
	25	ϵ'/ϵ_0	$\tan \delta$	50	34	25.5	20.5	19	22	27	44	57	73
	25	ϵ'/ϵ_0	$\tan \delta$	4.88	4.84	4.82	4.80	4.78	4.76	4.75	4.74	4.71	4.64
	25	ϵ'/ϵ_0	$\tan \delta$	81	56	43	33	27	28	35	52	61	83

a. Contains 2% iron oxide (Am. Optical). b. Aluminum-zinc phosphate. (ca. 70% P₂O₅) (Am. Optical). c. 73.2% SiO₂, 24.8% B₂O₃ (Components and Systems Lab., Air Materiel Command). d. Soda-potash-lead silicate ca. 20% PbO. e. Lead-barium glass. f. Soda-lime-silicate. g. Potash-lead-silicate. h. Potash-soda-barium silicate. i. Soda-potash-lead-silicate. j. Lime-alumina-silicate. k. Iron-sealing glass. m. 45% SiO₂, 14% K₂O, 6% Na₂O, 3% PbO, 5% CaO (iron-sealing glass). n. Soda-potash-borosilicate. o. Soda-potash-borosilicate. p. Soda-borosilicate (ca. 70% SiO₂).

I. Solids, A. Inorganic (cont.)

Values for $\tan \delta$ are multiplied by 10^4 ; frequency given in c/s.

3. Glasses (cont.)	T ^o C	ϵ'/ϵ_0	$\tan \delta$	1×10^2	1×10^3	1×10^4	1×10^5	1×10^6	1×10^7	1×10^8	3×10^8	3×10^9	1×10^{10}	2.5×10^{10}
Corning 7052 ^a	23	ϵ'/ϵ_0		5.20	5.18	5.14	5.12	5.10	5.10	5.09	-----	5.04	4.93	4.85
		$\tan \delta$		68	49	34	26	24	28	34	-----	58	81	114
Corning 7055	25	ϵ'/ϵ_0		5.45	5.41	5.38	5.33	5.31	5.30	5.27	5.25	-----	5.08	-----
		$\tan \delta$		45	36	30	28	28	29	38	49	-----	130	-----
Corning 7060 ^b	25	ϵ'/ϵ_0		5.02	4.97	4.92	4.86	4.84	4.84	4.84	-----	4.82	4.80	4.65
		$\tan \delta$		89	55	42	40	36	30	30	-----	54	98	90
Corning 7070 ^c	23	ϵ'/ϵ_0		4.00	4.00	4.00	4.00	4.00	4.00	4.00	4.00	4.00	4.00	3.9
		$\tan \delta$		6	5	5	6	8	11	12	12	12	21	31
	100	ϵ'/ϵ_0		4.17	4.16	4.15	4.14	4.13	4.10	-----	-----	4.00	4.00	-----
		$\tan \delta$		50	22	13	10	9	11	-----	-----	19	21	-----
Corning 7230 ^d	25	ϵ'/ϵ_0		3.88	3.86	3.85	3.85	3.85	3.85	-----	-----	3.75	-----	-----
		$\tan \delta$		33	23	16	13	11	12	-----	-----	22	-----	-----
Corning 7570	25	ϵ'/ϵ_0		14.58	14.56	14.54	14.53	14.52	14.50	14.42	14.4	-----	14.2	-----
		$\tan \delta$		11.5	13.5	15.9	16.5	19.0	23.5	.33	44	-----	98	-----
Corning 7720 ^e	24	ϵ'/ϵ_0		4.74	4.70	4.67	4.64	4.62	4.61	-----	-----	-----	4.59	-----
		$\tan \delta$		78	42	29	22	20	23	-----	-----	-----	43	-----
Corning 7740 ^f	25	ϵ'/ϵ_0		4.80	4.73	4.70	4.60	4.55	4.52	4.52	-----	-----	4.52	4.50
		$\tan \delta$		128	86	65	54	49	45	45	-----	-----	85	96
Corning 7750 ^f	25	ϵ'/ϵ_0		4.45	4.42	4.39	4.38	4.38	4.38	-----	-----	4.38	4.38	-----
		$\tan \delta$		45	33	24	20	18	19	-----	-----	43	54	-----
Corning 7900 ^g	20	ϵ'/ϵ_0		3.85	3.85	3.85	3.85	3.85	3.85	-----	3.85	3.84	3.82	3.82
		$\tan \delta$		6	6	6	6	6	6	-----	6	6.8	9.4	13
	100	ϵ'/ϵ_0		3.85	3.85	3.85	3.85	3.85	3.85	-----	3.85	3.84	3.82	-----
		$\tan \delta$		37	17	12	10	8.5	7.5	-----	7.5	10	13	-----
Corning 7911	25	ϵ'/ϵ_0		-----	-----	-----	-----	-----	-----	-----	-----	-----	3.82	-----
		$\tan \delta$		-----	-----	-----	-----	-----	-----	-----	-----	-----	6.5	-----
Corning 8460 ^h	25	ϵ'/ϵ_0		8.35	8.30	8.30	8.30	8.30	8.30	8.30	-----	8.10	8.06	8.05
		$\tan \delta$		11	9	7.5	7	8	10	16	-----	40	57	60
Corning 8830	25	ϵ'/ϵ_0		5.38	5.28	5.20	5.11	5.05	5.01	5.00	4.97	-----	4.83	-----
		$\tan \delta$		204	130	91	73	60	54	57	63	-----	99	-----

a. Soda-potash-lithia-borosilicate. b. Soda-borosilicate (Pyrex). c. Low alkali potash-lithia-borosilicate. d. Aluminum borosilicate.

e. Soda-lead borosilicate. f. Soda-borosilicate (ca. 80% SiO₂). g. 96% SiO₂. h. Barium borosilicate.

I. Solids, A. Inorganic (cont.)

Values for $\tan \delta$ are multiplied by 10^4 ; frequency given in c/s.

Glasses (cont.)	T°C	ϵ'/ϵ_0	$\frac{1 \times 10^2}{\tan \delta}$	$\frac{1 \times 10^3}{\tan \delta}$	$\frac{1 \times 10^4}{\tan \delta}$	$\frac{1 \times 10^5}{\tan \delta}$	$\frac{1 \times 10^6}{\tan \delta}$	$\frac{1 \times 10^7}{\tan \delta}$	$\frac{1 \times 10^8}{\tan \delta}$	$\frac{3 \times 10^8}{\tan \delta}$	$\frac{3 \times 10^9}{\tan \delta}$	$\frac{1 \times 10^{10}}{\tan \delta}$	$\frac{2.5 \times 10^{10}}{\tan \delta}$
Corning 8871 ^a	25	ϵ'/ϵ_0	8.45	8.45	8.45	8.45	8.45	8.43	---	8.40	8.34	8.05	7.82
Corning 9010	25	$\tan \delta$	18	13	9	7	6	7	---	14	26	49	70
Corning Lab. No. 1890S	25	ϵ'/ϵ_0	6.51	6.49	6.48	6.45	6.44	6.43	6.42	6.40	---	6.27	---
	25	$\tan \delta$	50.5	36.2	26.7	22.7	21.5	22.6	30	41	---	91	---
" E " Glass ^b	23	ϵ'/ϵ_0	19.2	19.2	19.2	19.1	19.0	19.0	19.0	---	17.8	---	---
	23	$\tan \delta$	12.5	13	16.5	21	27	37	57	---	124	---	---
Foamglas ^c	23	ϵ'/ϵ_0	6.43	6.40	6.39	6.37	6.32	6.25	6.22	---	---	6.11	---
	23	$\tan \delta$	42	34	27	18	15	17	23	---	---	60	---
Fused Silica 915c ^d	25	ϵ'/ϵ_0	90.0	82.5	68.0	44.0	17.5	9.0	---	---	---	5.49	---
	25	$\tan \delta$	1500	1600	2380	3200	3180	1960	---	---	---	455	---
Fused Silica 915c ^{d,e}	25	ϵ'/ϵ_0	3.78	3.78	3.78	3.78	3.78	3.78	3.78	3.78	---	3.78	---
	25	$\tan \delta$	6.6	2.6	1.1	0.4	0.1	0.1	0.3	0.5	---	1.7	---
Fused quartz ^f	25	ϵ'/ϵ_0	3.78	3.78	3.78	3.78	3.78	3.78	3.78	---	3.78	3.78	3.78
	25	$\tan \delta$	0.08	0.13	<0.05	---	---	---	---	---	0.6	1	2.5
Soda-Silica Glasses ^g	25	ϵ'/ϵ_0	8.5	7.5	6	4	2	1	1	---	---	---	---
	25	$\tan \delta$	6.4	6.2	5.7	---	5.4	---	---	5.1	---	5.05	4.9
9% Na ₂ O, 91% SiO ₂	25	$\tan \delta$	2500	820	400	---	130	---	---	100	---	130	160
	25	ϵ'/ϵ_0	8.2	6.7	6.1	---	5.6	---	---	5.2	---	5.15	5.04
12% Na ₂ O, 88% SiO ₂	25	$\tan \delta$	1900	600	300	---	150	---	---	100	---	155	170
	25	ϵ'/ϵ_0	9.4	7.4	6.6	6.2	5.9	5.7	---	5.5	---	5.27	---
16% Na ₂ O, 84% SiO ₂	25	$\tan \delta$	3000	960	500	250	165	130	---	110	---	180	---
	25	ϵ'/ϵ_0	10.8	8.3	7.3	6.8	6.6	6.3	---	5.9	---	5.6	6.1
20% Na ₂ O, 80% SiO ₂	25	$\tan \delta$	4000	1500	670	360	220	180	---	140	---	200	280
	25	ϵ'/ϵ_0	13	9.7	8.4	---	7.6	---	---	6.7	---	6.3	---
25% Na ₂ O, 75% SiO ₂	25	$\tan \delta$	6700	2400	1000	---	310	---	---	170	---	220	---
	25	ϵ'/ϵ_0	18	12	10.4	---	8.5	---	---	7.5	---	7.2	7.0
30% Na ₂ O, 70% SiO ₂	25	$\tan \delta$	11000	3900	1300	---	400	---	---	190	---	240	350

a. Alkaline lead silicate. b. Owens-Corning. c. Soda-lime (Pittsburgh-Corning). d. SiO₂ (Corning). e. Sample B-135. f. SiO₂ (General Electric). g. Composition in mole % of oxides as mixed (Lab. Ins. Res.).

I. Solids, A. Inorganic (Cont.)		Values for $\tan \delta$ are multiplied by 10^4 ; frequency given in c/s.									
3. Glasses (cont.)	T°C		$\frac{1 \times 10^2}{}$	$\frac{1 \times 10^3}{}$	$\frac{1 \times 10^4}{}$	$\frac{1 \times 10^5}{}$	$\frac{1 \times 10^6}{}$	$\frac{1 \times 10^7}{}$	$\frac{3 \times 10^8}{}$	$\frac{3 \times 10^9}{}$	$\frac{1 \times 10^{10}}{}$
Alkali-silica glasses ^a											
12.8% Li ₂ O, 87.2% SiO ₂	25	ϵ'/ϵ_0	9.94	6.54	5.45	5.1	4.95	4.92	4.9	---	4.80
		$\tan \delta$	9700	3600	1000	310	174	124	79	---	102
12.8% Na ₂ O, 87.2% SiO ₂	25	ϵ'/ϵ_0	8.09	6.61	6.00	5.8	5.66	5.57	5.4	---	5.33
		$\tan \delta$	3050	1370	450	240	159	126	118	---	182
12.8% K ₂ O, 87.2% SiO ₂	25	ϵ'/ϵ_0	7.53	6.49	6.25	6.17	6.09	6.02	5.8	---	5.8
		$\tan \delta$	502	360	200	121	90	80	99	---	220
12.8% K ₂ O, 87.2% SiO ₂	25	ϵ'/ϵ_0	7.10	6.63	6.30	6.12	6.10	6.08	5.95	---	5.75
Quenched		$\tan \delta$	730	470	270	160	119	103	106	---	240
12.8% Rb ₂ O, 87.2% SiO ₂	25	ϵ'/ϵ_0	5.39	5.32	5.23	5.22	5.21	5.20	5.15	---	5.05
		$\tan \delta$	98	89	58	46	41	38	59	---	120
6.4% Li ₂ O, 6.4% Na ₂ O, 87.2% SiO ₂	25	ϵ'/ϵ_0	5.15	5.08	5.05	5.05	5.04	5.03	5.00	---	4.95
		$\tan \delta$	145	87	47	28	19	17	26	---	52
6.4% Li ₂ O, 6.4% Na ₂ O, 87.2% SiO	25	ϵ'/ϵ_0	5.15	5.09	5.05	5.05	5.04	5.02	4.98	---	4.94
Quenched		$\tan \delta$	150	87	47	27	19	21	31	---	57
3.3% Li ₂ O, 6.6% K ₂ O, 71% SiO ₂	25	ϵ'/ϵ_0	5.23	5.19	5.17	5.15	5.14	5.10	5.07	---	5.04
		$\tan \delta$	53	47	37	28	24	24	40	---	83
3.3% Li ₂ O, 6.6% K ₂ O, 91% SiO ₂	25	ϵ'/ϵ_0	5.38	5.35	5.28	5.26	5.23	5.20	5.15	---	5.08
Quenched		$\tan \delta$	102	74	44	30	30	33	49	---	102
6.4% Na ₂ O, 6.4% K ₂ O, 87.2% SiO ₂	25	ϵ'/ϵ_0	5.68	5.62	5.58	5.56	5.56	5.54	5.51	---	5.50
		$\tan \delta$	102	75	42	31	25	23	40	---	115
6.4% Na ₂ O, 6.4% K ₂ O, 87.2% SiO ₂	25	ϵ'/ϵ_0	5.70	5.62	5.58	5.56	5.56	5.55	5.54	---	5.53
Quenched		$\tan \delta$	129	89	47	36	33	34	44	---	160

a. Composition in mole % of oxides as mixed (Lab. Ins. Res.)

I. Solids A. Inorganic (cont.) Values for tan δ are multiplied by 10^4 ; frequency given in c/s.

4. Mica and Glass		T ^o C	ϵ'/ϵ_0	$\tan \delta$	1×10^2	1×10^3	1×10^4	1×10^5	1×10^6	1×10^7	1×10^8	3×10^8	3×10^9	1×10^{10}	2.5×10^{10}
Mycalox 2821 ^a (discontinued)		25	ϵ'/ϵ_0		7.50	7.50	7.50	7.50	7.50	7.45	7.45	-----	-----	7.09	
			$\tan \delta$		60	28	17	13	10	9	9	-----	-----	27	
Mycalox 400 ^b		25	ϵ'/ϵ_0		7.47	7.45	7.42	7.40	7.39	7.38	-----	-----	-----	7.12	
			$\tan \delta$		29	19	16	14	13	13	-----	-----	-----	33	
80			ϵ'/ϵ_0		7.64	7.59	7.54	7.52	7.50	7.47	-----	-----	-----	7.32	
			$\tan \delta$		150	85	50	25	16	14	-----	-----	-----	57	
Mycalox K10 ^c		24	ϵ'/ϵ_0		9.5	9.3	9.2	9.1	9.0	9.0	-----	-----	11.3*	11.3*	
			$\tan \delta$		170	125	76	42	26	21	-----	-----	40	40	
Mykroy Grade 8 ^d		25	ϵ'/ϵ_0		6.87	6.81	6.76	6.74	6.73	6.73	6.72	-----	6.68**	6.96**	6.66
			$\tan \delta$		95	66	43	31	26	24	25	-----	38	48	81
Mykroy Grade 38 ^d		25	ϵ'/ϵ_0		7.71	7.69	7.64	7.61	7.61	7.61	-----	-----	7.68**	8.35**	
			$\tan \delta$		43	33	27	24	21	14	-----	-----	35	40	
5. Miscellaneous Inorganics															
Ruby mica ^e		26	ϵ'/ϵ_0		5.4	5.4	5.4	5.4	5.4	5.4	5.4	-----	5.4		
			$\tan \delta$		25	6	3.5	3	3	3	2	-----	3		
Canadian mica (field I sheet)		25	ϵ'/ϵ_0		6.90	6.90	6.90								
			$\tan \delta$		15	2	1								
(field II sheet)		25	ϵ'/ϵ_0		11.5	8.7	7.3								
			$\tan \delta$		2300	980	400								
Marble S-3030 ^f (after drying over P ₂ O ₅)		25	ϵ'/ϵ_0		15.6	12.8	11.4	10.6	10.0	9.5	9.1	8.8	-----	8.6	
			$\tan \delta$		2000	1100	630	390	360	370	290	250	-----	120	
(after baking)		25	ϵ'/ϵ_0		9.45	9.42	9.29	9.25	9.07	8.98	8.85	-----	-----	8.53	
			$\tan \delta$		180	130	81	75	110	120	120	-----	-----	110	
(after 60% humidity for 3 weeks)		25	ϵ'/ϵ_0		-----	-----	-----	-----	-----	9.35	8.95				
			$\tan \delta$		-----	-----	-----	-----	-----	500	250				
Selenium, amorphous ^g		25	ϵ'/ϵ_0		6.00	6.00	6.00	6.00	6.00	6.00	6.00	6.0	6.00	6.00	6.00
			$\tan \delta$		18	4	< 3	< 5	< 3	< 2	< 2	< 5	1.8	6.7	13
Quinterra ^h (Measured at 50% R.H.)		25	ϵ'/ϵ_0		5.75	4.80	4.1	3.3	3.1						
			$\tan \delta$		1770	1500	1240	590	250						
Quinorgo #3000 ⁱ (Measured at 50% R.H.)		25	ϵ'/ϵ_0		8.75	6.4	4.9	4.0	3.3						
			$\tan \delta$		210	2310	2150	1350	870						

a. Mica, glass (Gen. Elec.). b. Mica, glass (Mycalox). c. Mica, glass, TiO₂ (Mycalox). d. Mica, glass (Electronic Mech.).

e. Muscovite. f. Class A (Tenn. Marble). g. Amer. Smelt. and Refining. h. Asbestos fiber, chrysotile, Type I (Johns-Manville).

i. 85% chrysotile asbestos, 15% organic material (Johns-Manville).

*Not corrected for variations of density. **Samples nonhomogeneous.

I. Solids, B. Organic, with or without inorganic components - Values for $\tan \delta$ are multiplied by 10^4 ; frequency given in c/s.

1. Crystals	T°C	ϵ'/ϵ_0	$\tan \delta$	1×10^2	1×10^3	1×10^4	1×10^5	1×10^6	1×10^7	1×10^8	3×10^8	3×10^9	1×10^{10}	2.5×10^{10}
α -Trinitrotoluene ^a	26	ϵ'/ϵ_0	$\tan \delta$	2.64	2.64	2.64	2.64	2.64	2.64					
				36	20	11	6	4.5	4					
α -Trinitrotoluene at ca. 20% humidity ^b	25	ϵ'/ϵ_0	$\tan \delta$	3.80	3.09	2.93	2.90	2.89	2.89	2.89	2.89	2.86	2.82	
Santicizer 9 ^c	25	ϵ'/ϵ_0	$\tan \delta$	4.19	3.76	3.56	3.51	3.47	3.43	3.35				3.21
				1140	560	350	185	120	110	71				28
Naphthalene ^d	25	ϵ'/ϵ_0	$\tan \delta$	-----	2.85	2.85	2.85	2.85	2.85	-----	2.8	-----	-----	-----
				-----	19	9	5	3	2	-----	2.1	-----	-----	-----
Orthoterphenyl ^e	25	ϵ'/ϵ_0	$\tan \delta$	2.8	2.8	2.8	2.8	2.8	2.8	-----	-----	-----	2.74	-----
				3.7	4.7	6.0	6.3	6	5	-----	-----	-----	2.7	-----
Metaterphenyl ^e	25	ϵ'/ϵ_0	$\tan \delta$	-----	2.86	2.86	-----	2.86	2.86	2.66	-----	2.83	-----	-----
				-----	4.5	4.5	-----	9.5	10.1	5	-----	0.7	-----	-----
Paraterphenyl ^e	25	ϵ'/ϵ_0	$\tan \delta$	-----	-----	-----	-----	-----	-----	(2.95-3.20 depending on degree of crystallization)	-----	2.95	-----	-----
				-----	2	1	< 2	< 2	< 2	< 2	-----	2.1	-----	-----
Aroclor 1268 ^f	25	ϵ'/ϵ_0	$\tan \delta$	2.64	2.64	2.64	2.64	2.64	2.64					
				14	3.5	2	< 3	< 6	< 6					
2. Simple Noncrystals														
Aroclor 5460 ^g	25	ϵ'/ϵ_0	$\tan \delta$	2.43	2.43	2.42	2.42	2.41	2.41	2.41				
				< 3	4	16	20	18	13	8				
Aroclor 4465 ^h	25	ϵ'/ϵ_0	$\tan \delta$	2.81	2.80	2.79	2.79	2.79	2.79	2.79				
				45	17	6.6	4	2.4	1.5	1.0				
3. Plastics														
a. Phenol-formaldehyde														
Bakelite BM-120 ⁱ	25	ϵ'/ϵ_0	$\tan \delta$	4.87	4.74	4.62	4.50	4.36	4.16	3.95	-----	3.70	3.68	3.55
(preformed and preheated)				300	220	200	210	280	350	380	-----	438	410	390

a. Chem. Lab. M.I.T. b. War Dept., Picatinny Arsenal. c. o- and p-toluene sulfonamides (Monsanto). d. Eastman Kodak; recryst. and resbl. Lab. Ins. Res. e. Monsanto, recryst. Lab. Ins. Res. f. Nonachlorobiphenyl (Monsanto). g. Nonachloroterphenyls (Monsanto). h. Chlorinated mixture of biphenyl and terphenyl (Monsanto). i. 46% wood flour, 8% misc. (Bakelite).

I. Solids, B. Organic (cont.)

3. Plastics (cont.)

a. Phenol-formaldehyde

(cont.)	T°C	Values for tan δ are multiplied by 10 ⁴ ; frequency given in c/s.									
		1x10 ²	1x10 ³	1x10 ⁴	1x10 ⁵	1x10 ⁶	1x10 ⁷	1x10 ⁸	3x10 ⁸	3x10 ⁹	1x10 ¹⁰
Bakelite BM-120 ^a	27	ε'/ε ₀	5.50	4.90	4.65	4.45	4.30	---	---	3.70	3.55
(not preformed or preheated)		tan δ	740	345	320	350	415	---	---	400	500
Bakelite BM-250 ^b	57	ε'/ε ₀	7.80	6.35	5.70	5.30	4.90	4.65	---	4.15	---
		tan δ	2950	1150	530	380	430	470	---	530	---
	88	ε'/ε ₀	18.2	8.5	6.5	5.7	5.2	5.0	---	4.40	---
		tan δ	7600	3700	1400	600	400	420	---	700	---
(preformed and preheated)	25	ε'/ε ₀	37	22	12	7.2	5.3	5.0	---	---	5.0
		tan δ	3000	3700	3900	2900	1250	220	---	---	320
Bakelite BT-48-306 ^c	24	ε'/ε ₀	8.2	7.15	6.5	5.9	5.4	4.9	---	3.64	3.52
		tan δ	1350	820	630	560	600	730	---	519	366
Bakelite BM-16981 ^d	25	ε'/ε ₀	7.6	6.1	5.4	5.1	4.9	4.8	---	4.6	4.5
		tan δ	2300	1000	500	300	200	130	---	100	120
(not preformed or preheated)											
Bakelite BM-16981 ^d	25	ε'/ε ₀	4.82	4.73	4.66	4.62	4.60	4.59	---	4.57	4.57
		tan δ	140	120	100	70	52	50	---	90	85
(preformed and preheated)	25	ε'/ε ₀	5.05	4.87	4.80	4.79	4.72	4.67	---	---	4.52
		tan δ	190	160	130	90	72	60	---	---	82
Laminated Fiberglass BK-174 ^e	24	ε'/ε ₀	14.2	9.8	7.2	5.9	5.3	5.0	4.54	4.40	4.37
		tan δ	2500	2600	1600	880	460	340	240	290	360
Catalin 200 base, white ^f	22*	ε'/ε ₀	8.6	8.2	7.9	7.5	7.0	6.5	---	4.89	---
		tan δ	400	290	330	400	500	650	---	1080	---
85**		ε'/ε ₀	53.5	34	24	17	12	9.5	---	5.81	---
		tan δ	9800	2000	5200	1800	1000	1100	---	1910	---
25**		ε'/ε ₀	6.9	6.7	6.6	6.5	6.3	5.8	5.1	4.61	---
		tan δ	130	170	260	330	380	480	878	926	---

a. 46% wood flour, 8% misc. (Bakelite). b. 66% asbestos fiber (Bakelite). c. 100% (Bakelite). d. Mica-filled (Bakelite).

e. 31.6% Bakelite's BV-17085, 68.4% Fiberglass (Owens Corning). f. Catalin.

* Measured December, 1943. ** Same material measured after two years at room temperature and humidity.

I. Solids, B. Organic 3. Plastics (cont.)

a. Phenol-formaldehyde

(cont.)	T°C	1x10 ²	1x10 ³	1x10 ⁴	1x10 ⁵	1x10 ⁶	1x10 ⁷	1x10 ⁸	3x10 ⁸	3x10 ⁹	1x10 ¹⁰	2.5x10 ¹⁰
Catalin 500 base, yellow ^a	22*	ε'/ε ₀	9.7	9.4	8.8	8.1	7.3	6.3	4.90	4.72		
		tan δ	280	320	400	550	760	1200	996	870		
	25**	ε'/ε ₀	4.92	4.86	4.78	4.69	4.57	4.40	4.02	3.7	3.41	
Catalin 500 base, standard ^a	25	ε'/ε ₀	20.0	15.2	12.6	10.8	9.6	8.4	620	520	360	
		tan δ	2800	1500	1000	860	940	1200	5.79	4.77	4.43	
	25*	ε'/ε ₀	94	44	16	11	8	6	1540	1250	1300	
Catalin 700 base (Frystal) ^a	80*	tan δ	16500	8000	4100	2300	1600	1400	4.74	1530		
		ε'/ε ₀	----	----	51	18.5	10.0	7.4	----	4.77		
		tan δ	----	----	13200	6600	3700	2400	----	1640		
Durez 1601, natural ^b	25**	ε'/ε ₀	58	24	14	9.6	8.0	6.6	4.1	3.7		
		tan δ	14000	6400	3100	1900	1500	1400	740	500		
	26	ε'/ε ₀	5.09	4.94	4.80	4.68	4.60	4.55	4.51	4.48	4.47	
Durite 500 ^c	24	tan δ	270	210	132	100	80	70	----	62	62	
		ε'/ε ₀	5.10	5.03	4.95	4.86	4.78	4.72	4.72	4.71	4.70	
		tan δ	130	104	86	78	82	102	115	126	128	
Formica IX ^d (field ⊥ to laminate)	26	ε'/ε ₀	5.23	5.15	4.96	4.78	4.60	4.32	4.04	3.57***	3.55+	
		tan δ	230	165	170	230	340	490	570	600***	700+	
	26	ε'/ε ₀	6.50	5.70	5.30	5.00	4.75	4.35	3.95	3.35***	3.25+	
Formica IX ^e (field ⊥ to laminate)	26	tan δ	1350	600	430	400	410	480	500	400***	460+	
	25	ε'/ε ₀	3.73	3.65	3.61	3.61	3.59	3.47	3.24++	3.20	3.12	
		tan δ	121	132	200	207	187	187	183++	178	173	
Grade YN-25 ^f (field to laminate)	25	ε'/ε ₀	3.87	3.77	3.68	3.61	3.55	3.47	----	----	----	
		tan δ	166	150	182	204	182	191	----	----	----	
	25	ε'/ε ₀	4.25	4.18	4.10	3.95	3.87	3.73	3.40	3.22	3.12	3.05
Panelyte Grade 776 ^g (field ⊥ to laminate)	25	tan δ	190	150	160	200	280	370	390	370	340	310
		ε'/ε ₀										

a. Catalin. b. 67% mica (Durez). c. 65% mica, 4% lubricants (Durite). d. 50% paper laminate (Formica). e. 40% cotton fabric (Formica). f. 50% Nylon fabric (Formica). g. Paper base (St. Regis).

*Measured December, 1943. **Same material measured after two years at room temperature and humidity. ***Rod stock in coaxial line. +Rod stock in H₁₁ (TE₁₁) mode of circular guide. ++Freq. = 1 x 10⁹.

I. Solids, B. Organic (Cont.).

3. Plastics (cont.)

a. Phenol-formaldehyde (cont.)

Micarta #254^a

T ^o C	ϵ'/ϵ_0	$\times 10^2$	$\times 10^3$	$\times 10^4$	$\times 10^5$	$\times 10^6$	$\times 10^7$	$\times 10^8$	$\times 10^8$	$\times 10^9$	$\times 10^{10}$
-13		4.9	4.7	4.5	4.4	4.2	4.0	3.4	3.4	3.34	3.13
	tan δ	250	220	240	280	370	390	370	286	215	
25	ϵ'/ϵ_0	5.30	4.95	4.81	4.66	4.51	4.20	3.85	3.78	3.43	3.25
	tan δ	760	330	260	270	360	470	550	470	505	3.21
82	ϵ'/ϵ_0	9.2	6.3	5.5	5.3	5.1	4.9	-----	-----	4.02	3.21
	tan δ	4100	1820	690	360	300	400	-----	-----	984	773

Micarta #496^b

(field $\perp$ to laminate)

Micarta #496^b

(field $\parallel$ to laminate)

Phenolic paper laminate

JH-1410^c

Resinox 10231^d

Resinox 10900^e

Taylor Grade GGG^f

(field $\parallel$ laminate)

(field $\perp$ laminate)

Dilecto (Macoboard)^g

Values for tan δ are multiplied by 10^4 ; frequency given in c/s.

a. Cresylic acid-formaldehyde, 50% α -cellulose (Westinghouse).											
c. 35% paper (Catalin).											
d. 53% filler (Monsanto).											
e. 35% mica, 18% filler (Monsanto).											
f. 40% random glass mat (Taylor).											
g. 45% cresol-phenol formaldehyde, 15% tung oil, 15% nylon (Continental Diamond).											
*Samples turned from sheet stock. **freq = 1 $\times 10^9$.											

I. Solids, B. Organic (Cont.)

3. Plastics (cont.)

a. Phenol-formaldehyde (cont.)

Dilecto (hot punching)

XXX-P-26^a

(Field II sheet)

(Field I sheet)

(Field I sheet)

(Field I sheet)

(Field I sheet)

(Field I sheet)

(Field I sheet)

(Field I sheet)

(Field I sheet)

(Field I sheet)

(Field I sheet)

(Field I sheet)

(Field I sheet)

(Field I sheet)

(Field I sheet)

(Field I sheet)

(Field I sheet)

(Field I sheet)

(Field I sheet)

(Field I sheet)

(Field I sheet)

(Field I sheet)

(Field I sheet)

(Field I sheet)

Values for tan δ are multiplied by 10^4 ; frequency given in c/s.

	1×10^2	1×10^3	1×10^4	1×10^5	1×10^6	1×10^7	1×10^8	3×10^8	3×10^9	1×10^{10}
ϵ'/ϵ_0	14.7	8.61	6.68	5.76	5.05	4.60	4.10	3.78	3.45	3.35
$\tan \delta$	6420	2970	1380	840	720	705	690	680	500	480
ϵ'/ϵ_0	---	---	---	---	---	---	---	4.36	---	3.72
$\tan \delta$	---	---	---	---	---	---	---	950	---	770
ϵ'/ϵ_0	---	---	---	---	---	---	---	4.76	---	4.27
$\tan \delta$	---	---	---	---	---	---	---	990	---	820
ϵ'/ϵ_0	4.29	4.21	4.14	4.01	3.89	3.73	3.56	3.35	---	---
$\tan \delta$	137	119	137	180	250	340	390	440	---	---
ϵ'/ϵ_0	5.74	5.09	4.77	4.57	4.32	4.16	---	---	---	---
$\tan \delta$	1990	620	360	284	273	308	---	---	---	---
ϵ'/ϵ_0	7.42	5.38	4.80	4.52	4.34	4.21	---	---	---	---
$\tan \delta$	6700	1910	630	380	290	322	4.80	---	---	---
ϵ'/ϵ_0	5.36	5.29	5.20	5.10	5.01	4.92	170	---	4.34*	4.59**
$\tan \delta$	270	130	115	122	138	150	---	149*	188*	230**
ϵ'/ϵ_0	---	---	---	---	---	---	---	---	---	---
$\tan \delta$	---	---	---	---	---	---	---	---	---	---
ϵ'/ϵ_0	6.70	5.70	5.30	4.90	4.55	4.30	4.15	---	3.65	---
$\tan \delta$	2000	820	520	470	430	400	390	---	350	---
ϵ'/ϵ_0	13.8	7.0	5.8	5.2	4.9	4.5	4.3	---	3.72	---
$\tan \delta$	9000	3300	1200	550	460	470	420	---	800	---
ϵ'/ϵ_0	---	---	---	---	---	---	---	---	---	1.36
$\tan \delta$	---	---	---	---	---	---	---	---	---	750
ϵ'/ϵ_0	---	---	---	---	---	---	---	---	1.21	---
$\tan \delta$	---	---	---	---	---	---	---	---	80	---
ϵ'/ϵ_0	---	---	---	---	---	---	---	---	1.185	---
$\tan \delta$	---	---	---	---	---	---	---	---	58	---
ϵ'/ϵ_0	---	---	---	---	---	---	---	---	---	---
$\tan \delta$	---	---	---	---	---	---	---	---	---	---

a. 45% cresol-phenol formaldehyde, 15% tung oil, 40% α paper (Conti. Diamond). b. Cresylic acid-formaldehyde, 60-65% glass fabric (Westinghouse). c. Phenol-furfuraldehyde (Durite). d. Expanded phenolic, den. 0.202 (Rezolin). e. Sponge Rubber Prod. *Stacked sheets in coaxial line. **Stacked sheets in H_{11} (TE_{11}) mode of circular guide.

I. Solids, B. Organic (Cont.)

3. Plastics (cont.)

b. Phenol-aniline-formaldehyde

	T°C	ϵ'/ϵ_0	tan δ	Values for tan δ are multiplied by 10^4 ; frequency given in c/s.									
				1×10^2	1×10^3	1×10^4	1×10^5	1×10^6	1×10^7	1×10^8	3×10^8	1×10^9	2.5×10^{10}
Bakelite BM-262 ^a	25	ϵ'/ϵ_0	tan δ	4.95	4.80	4.74	4.72	4.67	4.66	4.65	-----	4.55	4.5
(preformed and preheated)		tan δ		98	82	75	60	55	55	57	-----	105	89
Bakelite BM-262 ^a	26	ϵ'/ϵ_0	tan δ	4.9	4.8	4.75	4.7	4.7	4.65	4.65	4.58	4.45	
(not preformed or preheated)		tan δ		235	165	113	83	70	65	80	90	104	
	84	ϵ'/ϵ_0	tan δ	5.8	5.4	5.1	5.0	4.9	4.8	4.7	4.58	-----	
		tan δ		680	440	280	210	160	135	120	120	-----	
Bakelite BM-1895 ^b	25	ϵ'/ϵ_0	tan δ	4.80	4.72	4.70	4.67	4.64	4.61	4.58	4.55	4.43	4.35
(preformed and preheated)		tan δ		87	77	80	65	52	52	80	98	102	130
Bakelite BM-1895 ^b	28	ϵ'/ϵ_0	tan δ	5.0	4.9	4.75	4.65	4.55	4.5	4.5	-----	4.44	
(not preformed or preheated)		tan δ		138	122	106	90	72	57	60	-----	91	96
	84	ϵ'/ϵ_0	tan δ	5.8	5.3	5.0	4.8	4.65	4.6	4.6	-----	4.6	
		tan δ		740	470	310	225	175	140	125	-----	132	
Durez 11863 ^c	-12	ϵ'/ϵ_0	tan δ	4.68	4.59	4.52	4.48	4.42	4.39	-----	-----	4.32	4.31
(preformed and preheated)		tan δ		97	84	66	52	43	38	-----	-----	44	47
	25	ϵ'/ϵ_0	tan δ	4.76	4.70	4.64	4.60	4.55	4.50	4.48	-----	4.45	4.42
		tan δ		108	100	82	62	52	48	52	-----	69	76
	30	ϵ'/ϵ_0	tan δ	5.26	5.03	4.87	4.74	4.63	4.55	-----	-----	4.40	4.38
		tan δ		504	290	195	145	125	113	-----	100	106	
Durez 11863 ^c	26	ϵ'/ϵ_0	tan δ	5.44	5.22	5.04	4.90	4.78	4.69	-----	-----	4.52	4.49
(not preformed or preheated)		tan δ		760	390	230	160	115	88	-----	63	63	
Formica Grade MF-66	25	ϵ'/ϵ_0	tan δ	4.53	4.50	4.43	4.38	4.31	4.24	4.11	4.09	3.90	3.85
Fiberglass		tan δ		106	95	107	102	95	109	160	195	260	300
	79	ϵ'/ϵ_0	tan δ	4.94	4.75	4.66	4.59	4.51	4.44	4.35	-----	4.20	4.10
		tan δ		350	192	135	110	105	110	130	-----	346	702
Resinox 7934 ^e	25	ϵ'/ϵ_0	tan δ	4.62	4.46	4.34	4.28	4.20	4.13	4.10	4.05	4.04	4.04
(preformed and preheated)		tan δ		220	210	178	130	99	88	85	84	84	83

a. 62% mica (Bakelite). b. 59.5% mica, 8.5% misc. (Bakelite). c. 43% mica, 5% misc.; discontinued, substitute 12810 (Durez). d. 40% glass mat (Formica). e. 60% mica (Nonsantc).

I. Solids, B. Organic (Cont.)

3. Plastics (cont.)

Values for tan δ are multiplied by 10^4 ; frequency given in c/s.

c. Aniline-formaldehyde Cibanite E ^a	T ^o C	ϵ'/ϵ_o	tan δ	1×10^2	1×10^3	1×10^4	1×10^5	1×10^6	1×10^7	1×10^8	3×10^8	3×10^9	1×10^{10}	2.5×10^{10}
				ϵ'/ϵ_o	$\tan \delta$	ϵ'/ϵ_o	$\tan \delta$	ϵ'/ϵ_o	$\tan \delta$	ϵ'/ϵ_o	$\tan \delta$	ϵ'/ϵ_o	$\tan \delta$	ϵ'/ϵ_o
Dilectene 100 ^b (1943 product)	25	3.58	29	3.6	45	3.6	34	3.6	32	3.6	30	3.6	28	3.6
	84	3.6	33	3.6	34	3.6	37	3.6	35	3.6	33	3.6	31	3.6
	25	3.68	33	3.68	32	3.68	30	3.68	28	3.68	26	3.68	24	3.68
	(1944 product)	3.68	33	3.68	32	3.68	30	3.68	28	3.68	26	3.68	24	3.68
d. Melamine-formaldehyde Formica Grade FF-41 ^c (sheet stock)	26	6.15	400	6.15	119	6.15	86	6.15	5.85	5.75	5.65	5.5	5.4	5.3
	26	6.15	400	6.15	119	6.15	86	6.15	5.85	5.75	5.65	5.5	5.4	5.3
	24	6.55	400	6.55	142	6.55	85	6.55	6.05	6.00	5.90	5.80	5.70	5.60
	24	6.55	400	6.55	142	6.55	85	6.55	6.05	6.00	5.90	5.80	5.70	5.60
Formica Grade FF-55 ^d (field I to laminate)	24	6.55	400	6.55	142	6.55	85	6.55	6.05	6.00	5.90	5.80	5.70	5.60
	24	6.55	400	6.55	142	6.55	85	6.55	6.05	6.00	5.90	5.80	5.70	5.60
	25	6.70	1900	6.70	690	6.70	190	6.70	6.6	6.4	6.3	6.1	6.0	5.9
	25	6.70	1900	6.70	690	6.70	190	6.70	6.6	6.4	6.3	6.1	6.0	5.9
GMF Melamine ^e (field II to laminate)	25	6.70	1900	6.70	690	6.70	190	6.70	6.6	6.4	6.3	6.1	6.0	5.9
	25	6.70	1900	6.70	690	6.70	190	6.70	6.6	6.4	6.3	6.1	6.0	5.9
	27	6.70	1900	6.70	690	6.70	190	6.70	6.6	6.4	6.3	6.1	6.0	5.9
	27	6.70	1900	6.70	690	6.70	190	6.70	6.6	6.4	6.3	6.1	6.0	5.9
Melmac Resin 592 ^f (field I to laminate)	57	8.15	1250	8.15	695	8.15	490	8.15	750	8.15	490	750	8.15	490
	57	8.15	1250	8.15	695	8.15	490	8.15	750	8.15	490	750	8.15	490
	88	21.8	7400	21.8	3400	21.8	1650	21.8	1650	21.8	1650	1650	21.8	1650
	88	21.8	7400	21.8	3400	21.8	1650	21.8	1650	21.8	1650	1650	21.8	1650
Melmac Type 107 ^g (Ivory WB 48)	28	7.00	240	7.00	690	7.00	140	7.00	6.75	6.50	6.20	5.90	5.60	5.30
	28	7.00	240	7.00	690	7.00	140	7.00	6.75	6.50	6.20	5.90	5.60	5.30
	28	7.00	240	7.00	690	7.00	140	7.00	6.75	6.50	6.20	5.90	5.60	5.30
	28	7.00	240	7.00	690	7.00	140	7.00	6.75	6.50	6.20	5.90	5.60	5.30

a. 100% (Ciba). b. 100% (Continental-Diamond). c. 55% filler (Formica). d. Glass fiber mat (Formica). e. Glass lamina #6038 (Mica Insulator). f. Mineral filler (Am. Cyanamid). g. 25% alpha pulp, Zn stearate (Am. Cyanamid).

*Stacked sheets in coaxial line. ** Stacked sheets in H₁₁ (TE₁₁) mode of circular guide.

I. Solids. B. Organic 3. Plastics (Cont.)			Values for tan δ are multiplied by 10^4 ; frequency given in c/s.										
d. Melamine-formaldehyde (cont.)	T $^{\circ}$ C		1×10^2	1×10^3	1×10^4	1×10^5	1×10^6	1×10^7	1×10^8	3×10^8	3×10^9	1×10^{10}	2.5×10^{10}
Melmac Molding Compound 1500 ^a	25	ϵ'/ϵ_0 tan δ	6.50 308	6.31 173	6.18 162	6.01 221	5.85 320	5.53 415	5.10 500	4.37* 523*	4.20 520	4.10 505	
Melmac Molding Compound 1502 ^b	25	ϵ'/ϵ_0 tan δ	8.43 2020	6.95 960	6.37 460	6.04 350	5.77 410	5.36 510	4.90 560	4.40* 620*	4.20 620	4.00 520	
Polyglas M ^c	24	ϵ'/ϵ_0 tan δ	5.58 140	5.53 71	5.49 64	5.40 69	5.32 93	5.22 160	-----	-----	4.86** 339**	5.22** 660**	
	80	ϵ'/ϵ_0 tan δ	8.4 4000	6.5 1400	5.9 280	5.8 95	5.8 65	5.8 110	-----	-----	5.68** 498**	5.32** 721**	
Micarta #259 ^d (field $\perp$ to laminate)	24	ϵ'/ϵ_0 tan δ	6.13 190	6.07 125	5.97 105	5.90 85	5.81 108	5.72 145	5.55 200	-----	-----	4.80** 322**	
Micarta #259 ^d (field $\parallel$ to laminate)	24	ϵ'/ϵ_0 tan δ	-----	-----	-----	-----	-----	-----	-----	4.83*** 150***	4.75*** 260***	5.12+ 380+	4.70** 400**
Panelyte 140 ^e (field $\perp$ to laminate)	24	ϵ'/ϵ_0 tan δ	6.15 135	6.05 93	6.00 120	5.93 155	5.82 155	5.70 170	5.55 215	5.5 260	-----	4.70 360	4.62 260
Panelyte 140 ^e (field $\parallel$ to laminate)	25	ϵ'/ϵ_0 tan δ	-----	-----	-----	-----	-----	-----	-----	4.95 210	4.73 250	-----	4.60 260
Plaskon Melamine ^f	24	ϵ'/ϵ_0 tan δ	7.73 190	7.57 122	7.40 150	7.26 240	7.00 410	6.45 640	6.0 850	5.73 985	4.93 1028	4.60 1100	
	80	ϵ'/ϵ_0 tan δ	9.86 1800	8.7 560	8.4 210	8.4 140	7.9 220	7.5 410	7.0 700	-----	5.5 1250	5.04 1490	
Resimene 803-A ^g (not preformed or preheated)	24	ϵ'/ϵ_0 tan δ	7.05 410	6.90 210	6.75 190	6.50 270	6.20 440	5.70 660	5.20 820	5.04 859	4.53 820	4.23 760	
Resimene 803-A ^g (powder preheated)	25	ϵ'/ϵ_0 tan δ	-----	-----	-----	-----	-----	-----	-----	-----	-----	3.75 320	3.74 300

a. 40% wood flour, 18% plasticizer (Am. Cyanamid). b. 60% melamine, formaldehyde and aniline polymer with wood flour filler (Am. Cyanamid). c. 56.5% A. Cyanamid's Melmac 7278, 43.5% Owens-Corning's Glass "E" (Hood Rubber). d. 65-70% Fiberglass (Westinghouse). e. Fiberglass (St. Regis). f. α -cellulose (Libbey-Owens-Ford). g. 40% cellulose (Monsanto).
 * Freq. = 1×10^9 . ** Sample nonhomogeneous; stacked layers. ***In coaral lines. +In $H_{11}(TE_{11})$ mode circular guide. ++In $H_{01}(TE_{01})$ mode rectangular guide.

I. Solids. B. Organic 3. Plastics (cont.) Values for $\tan \delta$ are multiplied by 10^4 ; frequency given in c/s.

e. Urea-formaldehyde Beetle Resin ^a	T°C	ϵ'/ϵ_0	$\tan \delta$	1×10^2	1×10^3	1×10^4	1×10^5	1×10^6	1×10^7	1×10^8	3×10^8	3×10^9	1×10^{10}	2.5×10^{10}
27		6.5	300	6.2	240	6.05	5.9	5.65	5.4	5.1	---	4.57	4.47	---
Plaskon Urea, natural ^b	24													
		ϵ'/ϵ_0		6.7	280	6.4	6.2	6.0	5.7	5.2	5.1	4.79	4.65	---
		$\tan \delta$		7.8	7.8	7.4	7.1	6.8	6.6	---	---	694	782	---
80		ϵ'/ϵ_0		8.8	600	420	320	300	350	---	---	5.54	4.27	---
		$\tan \delta$		9.40	6.35	6.15	6.00	5.75	5.42	---	---	819	1630	---
Plaskon Urea, brown ^b	24													
		ϵ'/ϵ_0		6.65	260	240	250	280	350	420	438	4.60	4.55	---
		$\tan \delta$		320	4.58	4.50	4.40	4.26	4.15	3.96	3.62*	3.52	3.38	---
f. Benzoguanamine-formaldehyde Benzoguanamine Resin ^c	25													
		ϵ'/ϵ_0		4.72	189	127	140	196	273	320	342*	336	318	---
		$\tan \delta$		348	3.75	3.60	3.45	3.33	3.24	3.16	---	---	---	---
g. Polyamide Resins Nylon 66 ^d	25													
		ϵ'/ϵ_0		3.88	193	233	254	257	244	210	---	3.03	---	---
		$\tan \delta$		144	3.50	3.35	3.24	3.14	3.05	3.0	---	2.84	---	2.3
Nylon 610 ^d	25													
		ϵ'/ϵ_0		3.60	186	208	221	218	205	200	---	117	---	105
		$\tan \delta$		155	11.2	9.0	6.3	4.4	3.7	3.4	---	2.94	---	---
84		ϵ'/ϵ_0		13.5	1400	1580	2030	1720	1150	670	---	356	---	---
		$\tan \delta$		2350	4.2	4.0	3.7	3.2	3.05	3.0	---	2.85	---	---
Nylon 610 ^d -90% humidity	25													
		ϵ'/ϵ_0		4.5	640	600	500	380	280	220	---	125	---	---
		$\tan \delta$		650	3.76	3.64	3.49	3.36	3.24	3.17	3.06*	3.02	3.02	---
Nylon FM 10001 ^d	25													
		ϵ'/ϵ_0		3.84	180	262	275	232	214	175	140*	120	107	---
		$\tan \delta$		115	2.94	2.80	2.72	2.64	2.61	2.58	---	2.54	2.53	---
Resin #908 ^e	25													
		ϵ'/ϵ_0		3.25	500	274	165	114	92	83	---	62	57	---
		$\tan \delta$		1070	---	---	---	---	---	---	---	---	---	---

h. Cellulose Derivatives

1) Acetates

IL-1^f

25		ϵ'/ϵ_0		3.82	3.77	3.67	3.53	3.42	3.30	3.29	3.28	3.24	3.24	3.1
		$\tan \delta$		95	150	200	230	230	210	210	220	290	400	310
85		ϵ'/ϵ_0		3.98	3.96	3.90	3.77	3.58	3.44	---	---	3.30	---	---
		$\tan \delta$		34	75	135	210	270	280	---	---	290	---	---

a. Cellulose (Am. Cyanamid). b. α -cellulose (Libbey-Owens-Ford). c. 28% α paper (Am. Cyanamid). d. Hexamethylene-adipamide (Dupont).
e. Code RC-2072 (General Mills). f. 55.4% acetyl (Hercules).

* Freq. = 1×10^9 .

I. Solids, B. Organic, 3. Plastics (cont.)

h. Cellulose Derivatives (cont.)

1) Acetates (cont.)	T ^o C	ϵ'/ϵ_0	$\frac{1 \times 10^2}{\epsilon'}$	$\frac{1 \times 10^3}{\epsilon'}$	$\frac{1 \times 10^4}{\epsilon'}$	$\frac{1 \times 10^5}{\epsilon'}$	$\frac{1 \times 10^6}{\epsilon'}$	$\frac{1 \times 10^7}{\epsilon'}$	$\frac{1 \times 10^8}{\epsilon'}$	$\frac{3 \times 10^8}{\epsilon'}$	$\frac{1 \times 10^9}{\epsilon'}$	$\frac{3 \times 10^9}{\epsilon'}$	$\frac{1 \times 10^{10}}{\epsilon'}$	$\frac{2.5 \times 10^{10}}{\epsilon'}$
Lumarith XFA-H ^a	25	ϵ'/ϵ_0	4.61	4.51	4.36	4.13	3.79	3.57	3.37	3.20*	3.13	3.13	3.08	
		tan δ	152	240	340	428	480	423	380	365*	340	340	325	
Fibestos 2050TVA C-1686 ^b	26	ϵ'/ϵ_0	4.75	4.53	4.30	3.82	3.60	3.52	3.35					
		tan δ	180	305	380	425	430	400	350					
Tenite I 008A H ^c	26	ϵ'/ϵ_0	4.65	4.55	4.40	4.20	3.96	3.72	3.47		3.16			3.08
		tan δ	102	173	286	370	430	465	410			310		350
Tenite I 008A H ^c	26	ϵ'/ϵ_0	4.55	4.48	4.33	4.14	3.90	3.63	3.40			3.25	3.16	3.11
		tan δ	80	175	270	345	393	405	380			310	300	300
Tenite I 008A H ^c	26	ϵ'/ϵ_0	4.97	4.86	4.70	4.52	4.25	3.88	3.57		3.24			
		tan δ	123	175	285	400	495	560	550			380		
Tenite I 008A ME ^c	26	ϵ'/ϵ_0	4.87	4.80	4.60	4.40	4.18	3.80	3.5		3.26	3.09		
		tan δ	117	170	290	380	465	525	550			370	330	
Tenite I 008A S ^c	26	ϵ'/ϵ_0	5.14	5.06	4.90	4.64	4.30	3.96	3.65			3.23		
		tan δ	100	160	280	405	530	620	580			420		
Tenite I 008A S ^c	26	ϵ'/ϵ_0	5.34	5.28	5.15	4.90	4.57	4.20	3.75			3.20		3.1
		tan δ	85	135	230	370	540	690	700			480		380
Tenite II 205A H ^d	26	ϵ'/ϵ_0	3.54	3.50	3.44	3.38	3.28	3.18	3.05			2.80		
		tan δ	78	107	158	174	178	180	190			267		
Tenite II 205A H ^d	25	ϵ'/ϵ_0	3.54	3.48	3.42	3.37	3.30	3.18	3.08	3.00	2.91	2.82		
		tan δ	50	97	156	175	178	175	170	179	280	298		
Tenite II 205A ME ^d	27	ϵ'/ϵ_0	3.60	3.56	3.50	3.40	3.30	3.22	3.10			2.87		
		tan δ	80	117	170	192	200	200	200			310		
Tenite II 205A MS ^d	27	ϵ'/ϵ_0	3.67	3.64	3.55	3.45	3.40	3.28	3.15			2.92	2.83	
		tan δ	23	115	178	213	220	227	250			370	360	
Tenite II 205A S ^d	27	ϵ'/ϵ_0	3.80	3.75	3.66	3.58	3.48	3.38	3.20			2.98		
		tan δ	82	95	155	204	225	247	300			460		
Tenite II 205A S ^d	27	ϵ'/ϵ_0	3.83	3.80	3.74	3.66	3.58	3.44	3.30			3.08		2.8
		tan δ	80	90	150	200	235	260	320			520		360

a. 28% plast. (Celanese). b. 26% plasticizer (Monsanto). c. 23-31% plasticizer, pigments, dyes (Term. Eastman). d. 5-15% plasticizer pigments, dyes (Term. Eastman).

* Freq. = 1×10^9 .

I. Solids, B. Organic 3. Plastics (cont.)

h. Cellulose Derivatives (cont.)

2) Propionate

Forticel^a

T°C	1x10 ²	1x10 ³	1x10 ⁴	1x10 ⁵	1x10 ⁶	1x10 ⁷	1x10 ⁸	1x10 ⁹	3x10 ⁹	1x10 ¹⁰	2.5x10 ¹⁰
25	ε'/ε ₀	3.52	3.48	3.41	3.33	3.23	3.18	3.08	2.95	2.88	2.87
	tan δ	60	101	157	188	175	164	192	247	289	308

3) Nitrate

Pyralin^b

27	ε'/ε ₀	10.8	8.4	7.5	7.0	6.6	6.1	5.2	-----	3.74	3.32
	tan δ	6400	1000	450	400	640	930	1030	-----	1650	1310

78

ε'/ε₀

tan δ

	ε'/ε ₀	-----	7.5	6.7	6.3	6.2	6.1	5.2	-----	4.0	1620
	tan δ	-----	7000	1500	600	640	930	1030	-----	1620	1620

4) Methyl Cellulose

Methocel^c

22	ε'/ε ₀	7.6	6.8	6.4	6.1	5.7	4.9	4.3	-----	3.35	550
	tan δ	1280	570	330	400	650	1020	1000	-----	550	550

5) Ethyl Cellulose

Ethocel LT5^c

25	ε'/ε ₀	3.11	3.09	3.05	3.02	3.01	2.96	2.90	2.77	2.74	2.70
	tan δ	75	65	63	76	113	150	160	170	210	250

Lumarith #22361^d

24	ε'/ε ₀	3.10	3.06	3.02	2.99	2.92	2.87	2.80	-----	2.74	2.67
	tan δ	48	48	52	67	115	158	160	-----	196	256
84	ε'/ε ₀	3.00	3.00	2.90	2.85	2.80	2.80	2.80	-----	2.79	2.66
	tan δ	78	70	66	66	90	140	200	-----	214	402

1. Silicone Resins

Formica G7^e

(field I laminate)

25	ε'/ε ₀	3.73	3.73	3.73	3.73	3.73	3.73	3.73	3.92	3.90	3.90
	tan δ	17	16	15	14	12	15	19	3.92	3.90	3.90

(field II laminate)

25	ε'/ε ₀	5.18	4.72	4.37	4.09	3.99	3.95	3.94	3.92	3.90	3.90
	tan δ	790	575	570	530	97	25	22	40	55	45

Formica G6^e

(field II laminate)

25	ε'/ε ₀	3.99	3.91	3.87	3.85	3.82	3.82	3.82	3.81	3.79	3.74
	tan δ	210	110	96	130	46	22	27	37	51	61

(field I laminate)

25	ε'/ε ₀	3.79	3.79	3.79	3.79	3.79	3.79	3.79	3.79	3.79	3.79
	tan δ	13	11.5	10.5	10	10.5	13.3	13.3	13.3	13.3	13.3

a. 8% plast. (Celanese). b. 25% camphor (DuPont). c. Dow. d. 13% plast. (Celanese). e. Fiberglass laminate (Formica).

I. Solids, B. Organic 3. Plastics (cont.) Values for $\tan \delta$ are multiplied by 10^4 ; frequency given in c/s.

1. Silicone Resins

(cont.)		$T^\circ C$	$\frac{1 \times 10^2}{\epsilon' / \epsilon_0}$	$\frac{1 \times 10^3}{\tan \delta}$	$\frac{1 \times 10^4}{\epsilon' / \epsilon_0}$	$\frac{1 \times 10^5}{\tan \delta}$	$\frac{1 \times 10^6}{\epsilon' / \epsilon_0}$	$\frac{1 \times 10^7}{\tan \delta}$	$\frac{1 \times 10^8}{\epsilon' / \epsilon_0}$	$\frac{1 \times 10^9}{\tan \delta}$	$\frac{1 \times 10^{10}}{\epsilon' / \epsilon_0}$
DC 996 cured 16 hrs. at $150^\circ C^a$		25	ϵ' / ϵ_0	3.08	3.04	3.02	3.01	2.99	2.98	2.96	
			$\tan \delta$	83	74	65	52	42	38	31	
DC 996 cured 16 hrs. at $250^\circ C^a$		25	ϵ' / ϵ_0	2.90	2.90	2.90	2.90	2.90	2.90	2.90	
			$\tan \delta$	14	15	16.5	17.5	18	17	16.5	
DC 2101 ^b		24	ϵ' / ϵ_0	2.90	2.90	2.90	2.90	2.90	2.90	2.90	
(discontinued)			$\tan \delta$	70	56	49	46	45	45	45	
Polyglas S ^c		24	ϵ' / ϵ_0	3.60	3.59	3.58	3.57	3.57	3.56	-----	3.55 3.53
			$\tan \delta$	11	11	12	13	15	19	-----	40 46
80			ϵ' / ϵ_0	3.60	3.59	3.58	3.57	3.57	3.56	-----	3.55 3.51
			$\tan \delta$	27	17	11	10	10	14	-----	46 49
Molding Compound XM-3 ^d		25	ϵ' / ϵ_0	4.03	4.00	3.99	3.98	3.95	3.93	-----	3.85 3.85
			$\tan \delta$	51	52	50	47	38	42	-----	67 94
Dilecto (Silicone glass laminate) CB-261S (field 1 sheet) ^e		25	ϵ' / ϵ_0	3.83	3.82	3.81	3.80	3.80	3.79	3.79	
			$\tan \delta$	12.8	13	13	12.3	12.9	14.8	23.5	
90			ϵ' / ϵ_0	3.74	3.73	3.71	3.69	3.63	3.56		
			$\tan \delta$	21	20	8.5	21	39	26		
200			ϵ' / ϵ_0	3.50	3.62	3.44	3.42	3.40	3.35		
			$\tan \delta$	339	74.7	32.6	22.7	31.4	30		
(field II sheet)		25	ϵ' / ϵ_0	4.97	4.48	4.43	3.95	3.92	3.87	3.82	3.76
			$\tan \delta$	580	560	440	185	55	29	42	57
220			ϵ' / ϵ_0	4.68	4.26	4.18	4.18	-----	-----	-----	3.87**
			$\tan \delta$	1620	526	300	195	-----	-----	-----	75**
25*			ϵ' / ϵ_0	4.05	3.93	3.90	3.85				
			$\tan \delta$	104	60	42	31				

a. Methyl, phenyl, and methyl phenyl polysiloxane resin (Dow Corning). b. Cross-linked organo-siloxane polymer (Dow Corning). c. 16% DC 2101, 84% Corning's 790 glass powder (Lab. Ins. Res.). d. 35% methyl and phenyl polysilicone resin, 45% glass fibers, 19% silica filler (Dow Corning). e. 50% DC-2103, 50% staple fibre glass base (Cont. Diamond).

*After temperature run. ** 200°C.

I. Solids B. Organic 3. Plastics (cont.) Values for $\tan \delta$ are multiplied by 10^4 ; frequency given in c/s.

1. Silicone Resins (cont.)		T°C	ϵ'/ϵ_0	$\tan \delta$	$\frac{1 \times 10^2}{\epsilon'/\epsilon_0}$	$\frac{1 \times 10^3}{\tan \delta}$	$\frac{1 \times 10^4}{\epsilon'/\epsilon_0}$	$\frac{1 \times 10^5}{\tan \delta}$	$\frac{1 \times 10^6}{\epsilon'/\epsilon_0}$	$\frac{1 \times 10^7}{\tan \delta}$	$\frac{1 \times 10^8}{\epsilon'/\epsilon_0}$	$\frac{1 \times 10^9}{\tan \delta}$	$\frac{3 \times 10^9}{\epsilon'/\epsilon_0}$	$\frac{1 \times 10^{10}}{\tan \delta}$	$\frac{2.5 \times 10^{10}}{\epsilon'/\epsilon_0}$		
Dilecto (silicone glass laminate) GB 112S ^a (field 1 sheet)	25	ϵ'/ϵ_0	3.56	13.5	3.56	3.56	3.56	3.55	3.54	3.54	3.54						
		$\tan \delta$	3.41	26.4	3.39	16.2	14.9	16.1	11.1	8.5	11.4	18.6					
		ϵ'/ϵ_0	3.18	236	43	3.18	3.18	3.17	3.15	3.10							
(field 1 sheet)	25	$\tan \delta$	236	43	23	23	195	21	15.4								
		ϵ'/ϵ_0	6.55	5.72	4.94	3.96	3.84	3.82	3.80	3.78	3.76	3.70					
		$\tan \delta$	1250	910	1080	516	128	37	25	39	52	87					
215		ϵ'/ϵ_0	10.93	8.60	6.65	4.92								3.78			
		$\tan \delta$	2000	2080	1800	1410									80		
		ϵ'/ϵ_0	5.71	5.16	4.54	3.98											
25*		$\tan \delta$	624	880	940	640											
		ϵ'/ϵ_0	3.94	3.92	3.90	3.90	3.90	3.90	3.88					3.88**	3.89**		
		$\tan \delta$	18	16	15	14	15	26	37					67**	99**		
Taylor Grade GSC ^c (field 1 laminate)	25	ϵ'/ϵ_0	5.07	4.14	4.11	4.04	4.03	4.01				3.91	3.90	3.85			
		$\tan \delta$	99	72	83	44	20	15					30	39	40		
		ϵ'/ϵ_0	3.78	3.77	3.77	3.77	3.77	3.74	3.74								
(field 1 laminate)	25	$\tan \delta$	13.4	12.5	11	9.5	9.3	11.9	18								
		ϵ'/ϵ_0	4.10	4.00	3.94	3.94	3.94	3.94	3.94	3.92	3.92	3.75					
		$\tan \delta$	160	160	100	34	21	20	30	44	55	63					
(field 1 laminate)	25	ϵ'/ϵ_0	3.74	3.74	3.74	3.74	3.74	3.74	3.74	3.74							
		$\tan \delta$	15	14	13	12	13	15	22								
		ϵ'/ϵ_0	4.14	4.14	4.13	4.13	4.13	4.11	4.10					4.07**	4.06**		
DC 2104 Laminate (XL-269) ^e	25	$\tan \delta$	32	29	26	22	22	29	34								
		ϵ'/ϵ_0	2.26	2.26	2.26	2.26	2.26	2.26	2.26					2.26	2.25		
		$\tan \delta$	< 2	< 2	< 2	< 2	< 2	< 2	< 2					3.1	3.6		
Polythene A-3305 ^g (Now replaced by Alathon)	24	ϵ'/ϵ_0	2.25	2.25	2.25	2.25	2.25	2.25	2.25	2.25			2.25	2.25	2.24		
		$\tan \delta$	5	< 3	< 3	< 5	< 4	< 3					3	4	6.7		
		ϵ'/ϵ_0	2.25	2.25	2.25	2.25	2.25	2.25	2.25	2.25	2.25			2.25	2.20		
80		$\tan \delta$	< 5	< 3	< 3	< 5	< 4	< 3					7.2	8.5			

a. 50% DC-2103, 50% continuous-filament glass base (Cont. Diamond). b. 45% methyl and phenyl polysiloxane resin, 55% ECC-261 Fiberglass (Dow-Corning). c. 45-50% DC-2103, 50-55% staple fibre glass cloth (Taylor). d. 45-50% DC-2103, 50-55% staple fibre glass cloth (Taylor). e. 35% methyl and phenyl polysiloxane resin, 65% ECC-181 fiberglass (Dow-Corning). f. 0.1% antioxidant (Bakelite). g. 100% polyethylene (DuPont).

*Measured after temperature run. **field 1 laminate, at other frequencies field 1 sheet.

I. Solids, B. Organic 3. Plastics J. Polyvinyl Resins (cont.)

1) Polyethylene

(cont.)

Polyethylene ^a		Values for tan δ are multiplied by 10 ⁴ ; frequency given in c/s.									
T°C		1x10 ²	1x10 ³	1x10 ⁴	1x10 ⁵	1x10 ⁶	1x10 ⁷	1x10 ⁸	3x10 ⁸	3x10 ⁹	1x10 ¹⁰
23	ε'/ε ₀	2.25	2.25	2.25	2.25	2.25	2.25	2.25	2.25	2.25	2.24
	tan δ	< 2	< 2	< 2	< 2	< 2	< 2	< 2	5.8	5.8	6.6
23	ε'/ε ₀	2.26	2.26	2.26	2.26	2.26	2.26	2.26	2.26	2.25	2.25
	tan δ	< 5	5	6	7	8	9	10	10.6	11.7	11.9
-12	ε'/ε ₀	2.38	2.37	2.36	2.35	2.35	2.34	2.33	2.32	2.32	2.30
	tan δ	24	21	19	18	21	28	39	36	36	22
23	ε'/ε ₀	2.38	2.37	2.36	2.36	2.35	2.34	2.33	2.33	2.32	2.31
	tan δ	28	28	27	27	28	30	42	51	50	44

2) Polyisobutylene

Polyisobutylene^b

Run 5047-2

Copolene B^c

3) Polyvinyl chloride-

acetate

Vinylite QVNA^d

20	ε'/ε ₀	3.18	3.10	3.02	2.96	2.88	2.87	2.85	2.84		
	tan δ	130	185	225	210	160	115	81	55		
47	ε'/ε ₀	3.60	3.52	3.41	3.28	3.14	3.02	2.92	2.81		
	tan δ	100	166	240	261	228	162	110	77		
76	ε'/ε ₀	3.92	3.83	3.68	3.3	3.0	2.87	2.8	2.8		
	tan δ	180	220	320	400	350	270	190	175		
96	ε'/ε ₀	6.60	5.30	4.40	3.7	3.3	2.8	2.7	2.7	2.6	
	tan δ	1500	1400	1200	980	740	500	320	280	180	
110	ε'/ε ₀	9.9	8.6	6.8	5.6						
	tan δ	1030	1330	1780	1900						
25	ε'/ε ₀	7.72	7.20	6.40	5.25	4.13	3.45	3.05	2.99	2.94	2.82
	tan δ	570	640	1060	1500	1550	1200	650	460	185	150
Vinylite VG-5901, black ^f	ε'/ε ₀	6.5	5.5	4.6	3.9	3.4	3.1	3.0	2.94	2.88	2.83
	tan δ	1020	1180	1190	1000	740	500	280	200	106	105

a. Bakelite. b. 100% Esso Lab.). c. 61% polyisobutylene B-100, 39% Marbon B (Am. Phenolic). d. 100% polyvinyl chloride (Bakelite).

e. 40% polyvinyl chloride-acetate, 40% plast., 14% misc. (Bakelite). f. 62.5% polyvinyl chloride-acetate, 29% plast., 8.5% misc. (Bakelite).

I. Solids, B. Organic 3. Plastics J. Polyvinyl Resins (cont.) Values for $\tan \delta$ are multiplied by 10^4 ; frequency given in c/s.

3) Polyvinyl chloride

(cont.)	T°C	1×10^2	1×10^3	1×10^4	1×10^5	1×10^6	1×10^7	1×10^8	3×10^8	1×10^{10}	2.5×10^{10}
Vinylite VG-5904, black ^a	25	ϵ'/ϵ_0	8.1	7.5	6.6	5.4	4.3	3.3	3.1	2.83	
		$\tan \delta$	550	710	1060	1390	1400	670	500	320	
Vinylite VU-1900, clear ^b	24	ϵ'/ϵ_0	6.55	5.65	4.70	3.90	3.30	2.95	2.80	2.62	2.62
		$\tan \delta$	1000	1150	1300	1180	880	560	-----	104	110
	79	ϵ'/ϵ_0	10.3	8.15	7.5	6.5	5.5	4.3	3.4	2.84	2.60
		$\tan \delta$	7300	1250	720	800	1550	1550	-----	498	351
Vinylite VHH ^c	22	ϵ'/ϵ_0	3.20	3.12	3.06	3.00	2.91	2.88	2.83	2.79	
		$\tan \delta$	100	130	155	150	140	90	-----	76	
	47	ϵ'/ϵ_0	3.56	3.48	3.38	3.27	3.16	3.02	2.9	2.79	
		$\tan \delta$	110	142	190	227	206	152	114	92	
Vinylite VMS ^d	20	ϵ'/ϵ_0	3.10	3.08	3.02	2.95	2.90	2.85	2.8	2.74	
		$\tan \delta$	115	140	170	170	140	105	80	63	
Vinylite VMW ^e	20	ϵ'/ϵ_0	3.20	3.15	3.05	2.96	2.90	2.84	2.8	2.74	
		$\tan \delta$	135	165	197	190	150	110	80	59	
Geon 2046 ^f	23	ϵ'/ϵ_0	6.95	6.10	5.05	4.13	3.55	3.15	3.00	2.89	2.83
		$\tan \delta$	820	1100	1320	1200	890	570	211	116	116
	80	ϵ'/ϵ_0	9.1	8.8	8.3	7.6	6.5	5.0	4.0	3.06	2.90
		$\tan \delta$	250	300	410	680	1540	2800	1500	484	328
Geon 80365 ^g	25	ϵ'/ϵ_0	3.67	3.65	3.58	3.52	3.42	3.39	3.34		
		$\tan \delta$	68	95	133	145	130	115	120		
Geon 80384 ^h	25	ϵ'/ϵ_0	3.43	3.34	3.23	3.14	3.05	3.96	3.95		
		$\tan \delta$	120	184	224	217	158	114	101		

a. 54% polyvinyl chloride-acetate, 41% plast., 5% misc. (Bakelite). b. 64.5% polymer of 95% vinyl chloride and 5% vinyl acetate, 32% Flexol D.O.P., 3.5% misc. (Bakelite). c. Polymer of 87% vinyl chloride and 13% vinyl acetate (Bakelite). d. Polymer of 91% vinyl chloride and 9% vinyl acetate (Bakelite). e. Polymer of 95% vinyl chloride and 5% vinyl acetate (Bakelite). f. 59% polyvinyl chloride, 30% dioctyl phosphate, 6% stabilizer, 5% filler (Goodrich). g. 71% polyvinyl chloride, 10.5% filler, 5% plasticizer, 8.5% stabilizer (Goodrich). h. 87.8% polyvinyl chloride, 10.5% stabilizer (Goodrich).

I. Solids B. Organic 3. Plastics J. Polyvinyl Resins (cont.) Values for tan δ are multiplied by 10^4 ; frequency given in c/s.

3) Polyvinyl Chloride (cont.)		T °C	Values for tan δ are multiplied by 10 ⁴ ; frequency given in c/s.										
			1x10 ²	1x10 ³	1x10 ⁴	1x10 ⁵	1x10 ⁶	1x10 ⁷	1x10 ⁸	3x10 ⁸	3x10 ⁹	1x10 ¹⁰	
Koroseal 5CS-243 ^a	27	ε'/ε ₀	6.1	5.65	5.00	4.15	3.60	3.20	2.9	2.73	2.62		
		tan δ	790	1000	1300	1250	930	560	300	112	120		
Lucoflex ^b	25	ε'/ε ₀	----	----	----	----	----	----	2.75				
		tan δ	----	----	----	----	----	----	170				
Polyvinyl chloride 1006 ^c	25	ε'/ε ₀	6.1	----	4.55	----	3.3						
		tan δ	760	----	1100	----	760						
Polyvinyl chloride 1018 ^d	25	ε'/ε ₀	6.2	----	4.95	----	3.15						
		tan δ	630	----	950	----	920						
Polyvinyl chloride 1216 ^e	25	ε'/ε ₀	6.1	----	4.4	----	3.2						
		tan δ	1170	----	1110	----	450						
Polyvinyl chloride 1406 ^f	25	ε'/ε ₀	6.05	----	4.5	----	3.6						
		tan δ	870	----	940	----	480						
Ultron Wire Compound UL300 ^g	25	ε'/ε ₀	3.31	3.22	3.10	2.98	2.85						
		tan δ	150	210	250	220	155						
Ultron Wire Compound UL1004 ^h	25	ε'/ε ₀	6.4	----	4.65	----	3.3						
		tan δ	810	----	1210	----	740						
Ultron Wire Compound UL2 4001 ^k	25	ε'/ε ₀	6.7	----	4.7	----	3.5						
		tan δ	1100	----	1210	----	700						
Polyvinyl chloride W-174 ^m	25	ε'/ε ₀	5.45	4.77	4.17	3.75	3.52	3.25	3.00				
		tan δ	815	930	880	740	550	425	415				
Polyvinyl chloride W-175 ⁿ	25	ε'/ε ₀	5.94	5.20	4.51	3.90	3.44	3.37	3.04				
		tan δ	840	960	960	865	580	430	360				
Polyvinyl chloride W-176 ^p	25	ε'/ε ₀	6.21	5.52	4.70	3.96	3.53	3.28	3.00				
		tan δ	730	940	1070	960	720	520	500				

a. 63.7% polyvinyl chloride, 33.1% di-2-ethylhexylphthalate, lead silicate (Goodrich). b. Unplasticized polyvinyl chloride (Lucoflex Plastic). c. 57.5% polymer, 12.6% fillers, 28.7% plasticizers (Monsanto). d. 52.4% polymer, 15.1% fillers, 31.4% plasticizers (Monsanto). e. 57.5% polymer, 10.4% fillers, 31.6% plasticizers (Monsanto). f. 59.4% polymer, 10.7% fillers, 29.7% plasticizers (Monsanto). g. 100% polymer (Monsanto). h. 64.7% polymer, 2% filler, 32.5% plasticizers (Monsanto). k. 60.1% polymer, 7.8% fillers, 31.2% plasticizers (Monsanto). n. 65% Geon 101, 35% Paraplex G-25 (Rohm and Haas). o. 65% Geon 101, 35% Paraplex G-50 (Rohm and Haas). p. 65% Geon, 35% Paraplex G-60 (Rohm and Haas).

I. Solids B. Organic 3. Plastics J. Polyvinyl Resins (cont.) Values for $\tan \delta$ are multiplied by 10^4 ; frequency given in c/s.

3) Polyvinyl Chloride (cont.)		T°C	ϵ'/ϵ_0	$\tan \delta$	1×10^2	1×10^3	1×10^4	1×10^5	1×10^6	1×10^7	1×10^8	3×10^8	3×10^9	1×10^{10}	2.5×10^{10}
Plasticell ^a	25		ϵ'/ϵ_0		1.04	1.04	1.04	1.04	1.04	----	1.04	1.04*	1.04	1.04	
			$\tan \delta$		21	11	< 15	< 15	10	----	10	18*	55	50	
Ensolite M2240 ^b	25		ϵ'/ϵ_0		1.51	1.36	1.29	1.24	1.16						
			$\tan \delta$		3200	610	330	340	420						
Ensolite M2239 ^b	25		ϵ'/ϵ_0		1.48	1.40	1.31	1.25	1.20						
			$\tan \delta$		2850	770	280	250	340						
Ensolite 3036 ^b (field 1 plane of sample)	25		ϵ'/ϵ_0		1.30	1.24	1.19	1.17	1.16						
			$\tan \delta$		368	263	187	137	111						
(field 11 plane of sample)	25		ϵ'/ϵ_0		----	----	----	----	----	----	----	1.14*	1.12	1.10	
			$\tan \delta$		----	----	----	----	----	----	----	87*	86	30	

4) Polyvinylidene and Vinyl chloride

Saran B-115 ^c		ϵ'/ϵ_0	$\tan \delta$	ϵ'/ϵ_0	$\tan \delta$	ϵ'/ϵ_0	$\tan \delta$	ϵ'/ϵ_0	$\tan \delta$	ϵ'/ϵ_0	$\tan \delta$	ϵ'/ϵ_0	$\tan \delta$	ϵ'/ϵ_0	$\tan \delta$
23		4.88		4.65		4.17		3.60		3.18		2.82		2.71	
		450		630		885		845		570		180		72	
84		5.13		4.94		4.85		4.71		4.40		3.2		2.76	
		800		210		130		320		780		900		242	

5) Polychlorotrifluoroethylene

Kel-F ^d		ϵ'/ϵ_0	$\tan \delta$	ϵ'/ϵ_0	$\tan \delta$	ϵ'/ϵ_0	$\tan \delta$	ϵ'/ϵ_0	$\tan \delta$	ϵ'/ϵ_0	$\tan \delta$	ϵ'/ϵ_0	$\tan \delta$	ϵ'/ϵ_0	$\tan \delta$
26		2.72		2.63		2.53		2.46		2.43		2.35		2.30	
		210		270		230		135		82		60		30	
25		2.82		2.76		2.65		2.50		2.46		2.42		2.35	
		148		225		212		140		96		75		51	
25		2.84		2.75		2.68		2.58		2.51		2.45		2.35	
		126		207		234		204		175		214		150	

6) Polytetrafluoroethylene

Dilecto (Teflon Iaminate)		ϵ'/ϵ_0	$\tan \delta$	ϵ'/ϵ_0	$\tan \delta$	ϵ'/ϵ_0	$\tan \delta$	ϵ'/ϵ_0	$\tan \delta$	ϵ'/ϵ_0	$\tan \delta$	ϵ'/ϵ_0	$\tan \delta$	ϵ'/ϵ_0	$\tan \delta$
25		2.76		2.74		2.74		2.74		2.73		2.73		2.73	
		8.9		6.1		6		6		5.8		6.2		11.8	
250		2.48		2.46		2.46		2.46		2.44		2.44		2.44	
		80		36		18		14		14		2.5			
25**		2.70		2.68		2.69		2.69		2.69		2.69		2.69	
		4.7		3.9		4.7		4.8							

a. Expanded polyvinyl chloride (Sponge Rubber). b. Modified polyvinyl chloride (U. S. Rubber). c. Polyvinylidene and vinyl chlorides (Dow). d. Polychlorotrifluoroethylene (Kellogg). e. Plasticized polychlorotrifluoroethylene (Kellogg). f. 65-68% Teflon, 32-35% continuous-filament glass base (Cont. Diamond).

Values for ten δ are multiplied by 10^4 ; frequency given in c/s.

6) Polytetrafluoro-ethylene (cont.)	T ^o C	1x10 ²	1x10 ³	1x10 ⁴	1x10 ⁵	1x10 ⁶	1x10 ⁷	1x10 ⁸	3x10 ⁸	3x10 ⁹	1x10 ¹⁰	2.5x10 ¹⁰
Dilecto (Teflon Laminate	25	ε'/ε _o	3.35	3.18	3.17	3.16	3.15	3.15	3.15**	3.15	3.10	
GB-112T) ^a		tan δ	361	169	108	42	23	24	31**	38	47	
(field laminate)	250	ε'/ε _o	---	---	---	---	---	---	---	---	3.10	
		tan δ	---	---	---	---	---	---	---	---	70	
Teflon ^b	25*	ε'/ε _o	3.26	3.24	3.21	2.1	2.1	2.1	2.1	2.1	2.08	2.08
		tan δ	66	17.3	27	< 2	< 2	< 2	1.5	1.5	3.7	6
	22	ε'/ε _o	2.1	2.1	2.1	2.1	2.1	2.1	2.1	2.1	2.08	2.08
		tan δ	< 5	< 3	< 3	< 2	< 2	< 2	1.5	1.5	3.7	6
	100	ε'/ε _o	2.04	2.04	2.04	2.04	2.04	2.04	---	---	2.04	2.04
		tan δ	10	2	< 3	< 2	< 2	---	---	---	5.1	5.1
Chemelac M1405 ^c	25	ε'/ε _o	2.50	2.50	2.50	2.50	2.50	2.50	2.50	2.50	2.08	2.08
		tan δ	18	2.7	3	5	7.2	9	8	6.8	12.7	12.7
Chemelac M1406 ^d	25	ε'/ε _o	---	---	170	72	---	---	---	---	33	33
		tan δ***	---	> 10000	2400	62	---	---	---	---	145	145
Chemelac M1407 ^e	25	ρ	---	520	440	410	---	---	---	---	---	---
		ε'/ε _o	3.42	2.85	2.74	2.71	2.65	2.63	2.63	2.63	2.63	2.63
		tan δ	917	350	180	150	147	158	158	158	158	158
Chemelac M1411 ^f	25	ε'/ε _o	2.14	2.14	2.14	2.14	2.14	2.14	2.14	2.14	2.14	2.14
(field ⊥ sheet)		tan δ	18.5	7	6.8	7	9.2	10	10	10	10	10
(field sheet)	25	ε'/ε _o	---	---	---	---	---	---	---	---	2.52	2.52
		tan δ	---	---	---	---	---	---	---	---	25	25
Chemelac M1412 ^g	25	ε'/ε _o	---	---	---	---	---	---	---	---	2.35	2.35
		tan δ	---	---	---	---	---	---	---	---	15	15
Chemelac M1414 ^h	25	ε'/ε _o	---	---	---	---	---	---	---	---	33	33
		tan δ	---	---	---	---	---	---	---	---	3.9	3.9
		tan δ***	---	> 10000	> 1000	> 100	11.8	4.8	---	---	4.8	4.8
		ρ	---	95	95	95	95	80	---	---	---	---

a. 65-68% Teflon, 32-35% continuous-filament glass base (Cont. Diamond). b. Polytetrafluoroethylene (DuPont). c. 75% Teflon, 25% calcium fluoride (U.S.Gasket). d. 80% Teflon, 20% carbon (U.S. Gasket). e. 88% Teflon, 12% ceramic (U.S.Gasket). f. 75% Teflon, 25% Fiberglass (U.S.Gasket). g. 75% Teflon, 25% glass (U.S.Gasket). h. 75% Teflon, 25% graphite (U.S.Gasket).

```

*After temperature run. **Freq. = 1 x 109. ***tan δ not multiplied by 104.

```

I. Solids, B. Organic 3. Plastics J. Polyvinyl resins (cont.) Values for $\tan \delta$ are multiplied by 10^4 ; frequency given in c/s.

6) Polytetrafluoro-

ethylene (cont.)	T°C	ϵ'/ϵ_0	1×10^2	1×10^3	1×10^4	1×10^5	1×10^6	1×10^7	1×10^8	3×10^8	1×10^{10}	2.5×10^{10}
Chemelac M1418-2 ^a	25	$\tan \delta$	2.30	2.20	2.20	2.15	2.15	2.14	2.14			
(desiccated 48 hrs. P ₂ O ₅)			600	200	45	4	2	2.5	5			
(dried in oven)	25	ϵ'/ϵ_0	2.	2.15	2.15	2.15	2.15					
		$\tan \delta$	11	6	2.7	1.5	1.8					
Chemelac M1418-5 ^b	25	ϵ'/ϵ_0	2.27	2.23	2.18	2.18	2.16	2.16	2.16			
		$\tan \delta$	450	118	32	8.8	5.7	5.9	7.1			
Chemelac M1422 ^c	25	ϵ'/ϵ_0	2.72	2.72	2.72	2.72	2.72	2.72	2.72			
		$\tan \delta$	11.9	7.7	4.5	2.8	2.0	1.8	2.4			
Chemelac M1423 ^d	25	ϵ'/ϵ_0	-----	1.308	-----	-----	-----	-----	-----	1.30		
		$\tan \delta$	-----	1.81	-----	-----	-----	-----	-----	62		

7) Polyvinyl alcohol-acetate

Elvanol 51A-05 ^e	25	ϵ'/ϵ_0	8.2	7.8	7.2	6.2	5.2	4.5	-----	3.74	3.50	3.46
		$\tan \delta$	430	440	580	720	900	1000	-----	550	502	620
	85	ϵ'/ϵ_0	400	100	33	16	10	7.3	-----	4.67		
		$\tan \delta$	15000	13000	9000	3600	2300	2000	-----	1770		
	23	ϵ'/ϵ_0	14.0	10.4	8.0	6.6	5.7	5.0	-----	3.75		
		$\tan \delta$	4050	1850	1150	1000	950	900	-----	715		
	68	ϵ'/ϵ_0	85	26	14	9.5	7.5	5.8				
		$\tan \delta$	9600	8100	4000	1600	1400	1500				
	100	ϵ'/ϵ_0	3000	400	50	18	13	8.7	-----	5.6	4.1	
		$\tan \delta$	15000	22000	20000	4800	2700	2600	-----	2300	3000	
	26	ϵ'/ϵ_0	-----	-----	58	27	14	7	-----	4.12		
		$\tan \delta$	-----	-----	8200	5900	4100	2700	-----	840		
	26	ϵ'/ϵ_0	-----	-----	45.5	22.0	12.5	7.5	-----	3.89	3.8	3.8
		$\tan \delta$	-----	-----	7600	5100	3500	2500	-----	640	636	730
	25	ϵ'/ϵ_0	3.09	3.07	3.05	3.02	2.98	2.94	2.90	2.88		
		$\tan \delta$	49	50	52	56	65	49	37	28		
	85	ϵ'/ϵ_0	7.3	7.15	5.9	3.75	3.25	2.95	2.90	2.87		
		$\tan \delta$	180	590	2400	1830	830	560	200	85		

a. 90% Teflon, 10% quartz (U.S.Gasket). b. 75% Teflon, 25% quartz (U.S.Gasket). c. 80% Teflon, 20% titanium dioxide (U.S.Gasket).
d. Air-filled Teflon (U.S.Gasket). e. Polyvinyl alcohol-acetate, 11-14% acetoxy (DuPont). f. Polyvinyl alcohol-acetate, 0-1.5% acetoxy (DuPont). g. Polyvinyl acetate (DuPont).

8) Polyvinyl acetals		T°C	$\frac{1 \times 10^2}{\epsilon'/\epsilon_0}$	$\frac{1 \times 10^3}{\tan \delta}$	$\frac{1 \times 10^4}{\epsilon'/\epsilon_0}$	$\frac{1 \times 10^5}{\tan \delta}$	$\frac{1 \times 10^6}{\epsilon'/\epsilon_0}$	$\frac{1 \times 10^7}{\tan \delta}$	$\frac{1 \times 10^8}{\epsilon'/\epsilon_0}$	$\frac{3 \times 10^8}{\tan \delta}$	$\frac{3 \times 10^9}{\epsilon'/\epsilon_0}$	$\frac{1 \times 10^{10}}{\tan \delta}$	$\frac{2.5 \times 10^{10}}{\epsilon'/\epsilon_0}$		
Formvar, Type E ^a		26	ϵ'/ϵ_0	3.16	3.12	3.08	3.00	2.92	2.85	-----	2.76	-----	2.7		
			$\tan \delta$	54	100	154	190	190	165	-----	113	-----	115		
		88	ϵ'/ϵ_0	3.55	3.5	3.4	3.25	3.1	2.95	2.85	2.80	-----			
			$\tan \delta$	60	83	102	145	213	310	300	227	-----			
Alvar 11/90 ^b		25	ϵ'/ϵ_0	3.17	3.14	3.09	3.03	2.96	2.90	2.82	2.80	2.73	2.70	2.65	
			$\tan \delta$	65	70	100	140	180	160	125	119	136	175	175	
		84	ϵ'/ϵ_0	3.84	3.54	3.40	3.25	3.05	2.90	-----	2.74	-----			
			$\tan \delta$	575	390	270	195	180	225	-----	196	-----			
Butvar, Low OH ^c		27	ϵ'/ϵ_0	2.69	2.67	2.65	2.63	2.61	2.59	-----	2.51	2.48	2.46		
			$\tan \delta$	38	40	56	88	124	138	-----	111	107	99		
Butvar 55/98 ^c		27	ϵ'/ϵ_0	3.04	3.02	2.98	2.94	2.86	2.75	2.67	2.62	-----			
			$\tan \delta$	41	59	108	161	215	216	177	-----	172	-----		
9) Polyacrylates															
Lucite HM-119 ^d (now replaced by HM-140)		-12	ϵ'/ϵ_0	3.0	2.9	2.8	2.7	2.63	2.60	2.59	-----	2.58	2.57		
			$\tan \delta$	330	250	190	140	102	70	55	-----	35.4	34		
		23	ϵ'/ϵ_0	3.20	2.84	2.75	2.68	2.63	2.60	2.58	-----	2.58	2.57	2.57	
			$\tan \delta$	620	440	315	220	145	100	67	-----	51.3	49	32	
		81	ϵ'/ϵ_0	3.97	3.45	3.08	2.86	2.72	2.62	2.59	-----	2.58	2.57		
			$\tan \delta$	600	820	720	540	380	220	130	-----	77	95		
Lucite, sintered ^e (obsolete)		27	ϵ'/ϵ_0	2.29	2.12	2.01	2.00	2.00	2.00	2.00	-----	1.82	-----		
			$\tan \delta$	408	290	195	116	66	49	40	-----	52	-----		
Gafite cast polymer ^f (sheet sample)		25	ϵ'/ϵ_0	3.25	3.12	3.02	2.97	2.90	2.88	2.83	-----	-----	-----		
			$\tan \delta$	310	240	183	155	115	77	64	-----	-----	-----		
(rod sample)		25	ϵ'/ϵ_0	-----	-----	-----	-----	-----	-----	-----	2.75	2.75	2.75		
			$\tan \delta$	-----	-----	-----	-----	-----	120	-----	99	78	83		
Flexiglas ^g		27	ϵ'/ϵ_0	3.40	3.12	2.95	2.84	2.76	2.71	-----	2.66	2.60	2.59		
			$\tan \delta$	605	465	300	200	140	100	-----	62	57	67		
		80	ϵ'/ϵ_0	4.30	3.80	3.34	3.00	2.80	2.70	-----	-----	2.56	-----		
			$\tan \delta$	700	895	800	520	320	210	-----	-----	79	-----		

a. Polyvinyl formal (Shawinigan). b. Polyvinyl acetal (Shawinigan). c. Polyvinyl butyral (Shawinigan). d. Polymethyl methacrylate (DuPont). e. DuPont. f. Methyl and alpha-chloroacrylate (Gen. Aniline). g. Polymethyl methacrylate (Rohm and Haas).

I. Solids, B. Organic 3. Plastics J. Polyvinyl Resins (cont.) Values for $\tan \delta$ are multiplied by 10^4 ; frequency given in c/s.

9) Polyacrylates		$\frac{1 \times 10^2}{1 \times 10^3} \frac{1 \times 10^4}{1 \times 10^5} \frac{1 \times 10^6}{1 \times 10^7} \frac{1 \times 10^8}{3 \times 10^8} \frac{1 \times 10^9}{3 \times 10^9} \frac{1 \times 10^{10}}{2.5 \times 10^{10}}$											
(cont.)													
T°C													
Polyethyl methacrylate ^a	22	ϵ'/ϵ_0	2.90	2.75	2.65	2.55	2.53	-----	-----	-----	2.51	2.50	2.5
		$\tan \delta$	420	294	185	90	75	-----	-----	-----	75	97	83
	80	ϵ'/ϵ_0	3.87	3.36	2.86	2.61	2.57	2.55	-----	-----	2.49	2.48	
		$\tan \delta$	810	1060	960	400	260	140	-----	-----	91	135	
Polybutyl methacrylate ^a	-12	ϵ'/ϵ_0	2.50	2.46	2.44	2.41	2.40	-----	-----	2.38			
		$\tan \delta$	190	120	68	33	25	-----	-----	48			
	24	ϵ'/ϵ_0	2.82	2.62	2.52	2.43	2.42	-----	-----	2.38	2.36		
		$\tan \delta$	605	360	200	80	55	-----	-----	44	46		
	81	ϵ'/ϵ_0	3.70	3.52	3.14	2.60	2.48	-----	-----	2.39			
		$\tan \delta$	150	650	1200	470	220	-----	-----	185			
Polysobutyl methacrylate ^a	25	ϵ'/ϵ_0	2.70	2.68	2.63	2.45	2.45	2.42	2.40	2.39	2.38	2.37	
		$\tan \delta$	111	70	50	35	46	52	47	31	39	52	
	80	ϵ'/ϵ_0	2.9	2.7	2.5	2.44	2.42	2.42	2.40	2.39	2.38		
		$\tan \delta$	830	600	360	100	80	70	65	54	59		
Polycyclohexyl methacrylate ^b	25	ϵ'/ϵ_0	2.58	2.52	2.52	2.52	2.48	2.47	-----	2.46	-----	2.46	
		$\tan \delta$	46	47.5	60	28	23	25	-----	34.9	-----	41	
	84	ϵ'/ϵ_0	2.63	2.60	2.55	2.42	2.39	2.37	-----	2.37	-----		
		$\tan \delta$	150	124	98	68	38	32	-----	49			
10) Polystyrene													
Polystyrene ^c													
(commercially molded)													
Sheet, Stock	25	ϵ'/ϵ_0	2.56	2.56	2.56	2.56	2.56	2.55	2.55	2.55	2.54	2.54	2.54
		$\tan \delta$	< 0.5	< 0.5	< 0.5	0.7	< 2	< 1	3.5	3.3	4.3	12	
	80	ϵ'/ϵ_0	2.54	2.54	2.54	2.54	2.54	2.54	2.54	2.54	2.53		
		$\tan \delta$	9	2	< 1	< 2	< 2	< 3	2.7	4.5	5.3	5.3	
Rod Stock													
Sample A	25	$\tan \delta$	-----	-----	-----	-----	-----	-----	-----	2.5	3.6	4.8	
		$\tan \delta$	-----	-----	-----	-----	-----	-----	-----	12	-----	22	
Sample B	25	$\tan \delta$	-----	-----	-----	-----	-----	-----	-----	16			
		$\tan \delta$	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	
Sample B	80	$\tan \delta$	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	
		$\tan \delta$	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	

ids, B. Organic 3. Plastics J. Polym. Sci. A-1

is the same as for

different frequencies; for rod stock, ϵ'/ϵ_0

a. Dupont. b. Polaroid. c. For sheet stock, various samples used for different frequencies; for rod stock, ϵ'/ϵ_0 is the same as for sheet stock (Plax).

I. Solids. B. Organic 3. Plastics J. Polyvinyl Resins (cont.) Values for $\tan \delta$ are multiplied by 10^4 ; frequency given in c/s.

10) Polystyrene (cont.)	T ^o C	ϵ'/ϵ_0	$\tan \delta$	$\times 10^2$	$\times 10^3$	$\times 10^4$	$\times 10^5$	$\times 10^6$	$\times 10^7$	$\times 10^8$	$\times 10^8$	$\times 10^9$	$\times 10^{10}$	$\times 10^{10}$
Styron C-176 ^a	25	ϵ'/ϵ_0	$\tan \delta$	2.55	2.55	2.55	2.55	2.55	2.55	2.55	2.55	2.54	2.54	2.54
	80	ϵ'/ϵ_0	$\tan \delta$	2.55	2.55	2.55	2.55	2.55	2.55	2.55	2.55	2.54	2.54	2.54
Styron C-176, 30% humidity ^b	25	ϵ'/ϵ_0	$\tan \delta$	12	12	12	12	12	12	12	12	12	12	12
Styron C-176, 50% humidity ^b	25	ϵ'/ϵ_0	$\tan \delta$	12	12	12	12	12	12	12	12	12	12	12
Styron C-176, 90% humidity ^b	25	ϵ'/ϵ_0	$\tan \delta$	12	12	12	12	12	12	12	12	12	12	12
Styron C-176 + 0.5% paraffin, 90% humidity ^b	25	ϵ'/ϵ_0	$\tan \delta$	12	12	12	12	12	12	12	12	12	12	12
Styron 411-A ^c (formerly Exp. Plastic Q-247)	22	ϵ'/ϵ_0	$\tan \delta$	2.55	2.55	2.55	2.55	2.55	2.55	2.55	2.55	2.54	2.54	2.54
	79	ϵ'/ϵ_0	$\tan \delta$	2.55	2.55	2.55	2.55	2.55	2.55	2.55	2.55	2.54	2.54	2.54
Styron 475 ^b	25	ϵ'/ϵ_0	$\tan \delta$	2.62	2.61	2.59	2.56	2.56	2.55	2.55	2.55	2.53	2.53	2.53
Styron 666 ^b	25	ϵ'/ϵ_0	$\tan \delta$	3.6	3.0	2.4	2.6	4.2	7.6	11	19*	36	17	17
Styron 671 ^b	25	ϵ'/ϵ_0	$\tan \delta$	1.75	1.1	1.1	1.1	1.1	1.2	2	2.7*	3.1	3.4	3.4
	25	ϵ'/ϵ_0	$\tan \delta$	2.55	2.55	2.55	2.55	2.54	2.54	2.54	2.54	2.54	2.54	2.54
		$\tan \delta$		.97	.64	< .5	< .5	.2	.38	.57	1.47*	1.76	2.1	2.1

a. Polystyrene (Dow). Similar values given by Dow's C-244 and Q-247.1; Catalin's Iocalin #1 Color 4000; Bakelite's IMS-4A-621, XRS-23-B10012-442, XRS-23-B10012-52Q, XRS-23-B10016-D63, XRS-23-B10012-D107; Monsanto's Samples D-277, D-279 (extra purity), D-334.

b. Polystyrene (Dow). c. Polystyrene (Dow). Similar values given by Monsanto's Lustron Res. Sample D-276.

*Freq. = 1×10^6 .

I. Solids, B. Organic 3. Plastics J. Polyvinyl Resins (cont.) Values for $\tan \delta$ are multiplied by 10^4 ; frequency given in c/s.

10) Polystyrene													
(cont.)													
T°C	ϵ'/ϵ_0	$\tan \delta$	$\frac{1 \times 10^2}{\text{-----}}$	$\frac{1 \times 10^3}{2.14}$	$\frac{1 \times 10^4}{2.14}$	$\frac{1 \times 10^5}{2.14}$	$\frac{1 \times 10^6}{2.14}$	$\frac{1 \times 10^7}{2.14}$	$\frac{1 \times 10^8}{2.14}$	$\frac{3 \times 10^8}{\text{-----}}$	$\frac{3 \times 10^9}{2.11}$	$\frac{1 \times 10^{10}}{\text{-----}}$	$\frac{2.5 \times 10^{10}}{\text{-----}}$
26			7.6	6.3	4.6	3	3	3	4	-----	6.3	-----	-----
27			-----	-----	-----	-----	-----	-----	-----	-----	1.03	-----	-----
			-----	-----	-----	-----	-----	-----	-----	-----	<0.3	-----	-----
25			1.03	1.03	1.03	1.03	1.03	1.03	-----	-----	1.03	1.03	1.03
			< 2	< 1	< 1	< 1	< 2	< 2	-----	-----	1	1.5	-----
25			2.55	2.55	2.55	2.55	2.55	2.55	-----	-----	2.55	-----	-----
			1	1	0.5	< 2	< 2	< 3	-----	-----	2.4	-----	-----
25			-----	2.50	2.50	2.50	2.50	2.50	-----	-----	2.48	-----	-----
			-----	9	5.5	< 5	2	8	-----	-----	12.8	-----	-----
25			2.63	2.58	2.58	2.58	2.58	2.58	2.58	2.55*	2.51	2.51	-----
			2.5	1.3	1.8	2.5	2.3	1.4	2.8	7.3*	8.2	6.5	-----
25			2.98	2.95	2.92	2.90	2.86	2.83	2.80	2.77*	2.75	2.75	-----
			62	73	80	74	65	55	43	36*	38	43	-----
22			2.68	2.66	2.65	2.65	2.65	2.65	2.65	2.65	2.65	2.63	2.63
			29	18.4	5	< 2	< 2	< 2	1.6	1.9	2.2	2.3	4
78			2.7	2.7	2.67	2.65	2.65	2.65	2.65	-----	2.63	-----	-----
			91	67	25	6.5	4	4	3	-----	2.0	-----	-----
11) Misc. Polystyrenes													
25			2.60	2.60	2.60	-----	2.59	2.58	2.57	2.57*	2.57	2.56	-----
			.7	.6	.61	-----	.7	1	2.1	4.8*	4.5	3	-----
25			2.60	2.59	2.58	2.57	2.56	2.55	2.52	2.50*	2.49	2.49	-----
			7.3	6.2	4.7	3.6	2.2	1.5	1.2	1.9*	2.0	2.6	-----
25			2.45	2.45	2.45	2.45	2.45	2.45	-----	-----	2.45	-----	-----
			2	3.4	3.9	< 2	0.7	3.7	-----	-----	9	-----	-----

a. Dow. b. 99.75% polystyrene, 0.25% filler (Dow). c. From Dow's N-100 styrene (Lab. Ins. Res.). d. 50% polystyrene, 50% chlorinated diphenyl (Monsanto). e. Poly alpha-methylstyrene (Dow). f. Polyvinyltoluene (Dow). g. Pressed fibers (Polaroid).
*Freq. = 1×10^9 .

I. Solids, B. Organic 3. Plastics J. Polyvinyl Resins (cont.) Values for tan δ are multiplied by 10^4 ; frequency given in c/s.

12) Styrene copolymers														
linear	T°C	1×10^2	1×10^3	1×10^4	1×10^5	1×10^6	1×10^7	1×10^8	3×10^8	3×10^9	1×10^{10}	2.5×10^{10}		
Styrene-2,4-dimethyl- styrene copolymer ^a	25	ϵ'/ϵ_0	2.53	2.53	2.53	2.52	2.52	2.52	2.51*	2.50	2.49			
		$\tan \delta$	1.6	1.3	0.8	0.7	0.9	1.2	1.5	4.0*	5.4	2.8		
Styrene-acrylonitrile copolymer ^a	25	ϵ'/ϵ_0	2.96	2.95	2.92	2.87	2.80	2.78	2.77*	2.77	2.76			
		$\tan \delta$	59	63	67	67	64	50	41	40*	41	45		
Darex copolymer 3 ^b	25	ϵ'/ϵ_0	2.53	2.53	2.52	2.51	2.50	2.49	-----	2.48	2.45			
		$\tan \delta$	23.7	21.5	30.9	38.9	34.8	26.8	23.8	-----	21.3	20.9		
Darex copolymer 43E ^b	25	ϵ'/ϵ_0	2.54	2.54	2.54	2.54	2.54	2.54	-----	2.54	2.53			
		$\tan \delta$	5.5	2.8	2.2	2.8	3.9	6.2	8.2	-----	9.8	13		
Darex copolymer I-34 ^c	25	ϵ'/ϵ_0	2.55	2.54	2.54	2.53	2.52	2.52	2.51	-----	2.50	2.48		
		$\tan \delta$	20.4	12.7	17.5	19.5	12	15	14	-----	11.6	12		
Darex copolymer I-43 ^b	25	ϵ'/ϵ_0	2.56	2.56	2.56	2.56	2.55	2.55	-----	2.55	2.54			
		$\tan \delta$	7.3	2.5	2.3	2.2	3	4	5.5	-----	8.9	11.6		
Styraloy 22 ^c	-12	ϵ'/ϵ_0	2.4	2.4	2.4	2.4	2.4	2.4	-----	2.4	2.4			
		$\tan \delta$	8	8	4	15	36	52	-----	28	18	2.4		
	23	ϵ'/ϵ_0	2.4	2.4	2.4	2.4	2.4	2.4	2.40	2.4	2.4	2.4		
		$\tan \delta$	9	6	5	7	12	30	52	46	32	24		
	81	ϵ'/ϵ_0	2.4	2.4	2.4	2.4	2.4	2.4	-----	2.4	2.4			
		$\tan \delta$	16	10	8	6	6	13	-----	51	55			
Marbon S ^d	25	ϵ'/ϵ_0	2.62	2.62	2.62	2.61	2.60	2.57	2.55*	2.55	2.54			
		$\tan \delta$	17.4	14.1	13.8	13.8	18.3	22.1	22.2	20.6*	20	19		
Code 7206		ϵ'/ϵ_0	2.55	2.55	2.54	2.54	2.54	2.53	2.52*	2.52	2.52			
		$\tan \delta$	10	6	3.5	3.9	6.1	7.9	8.3	10*	11	12.5		
Marbon S-1	25	ϵ'/ϵ_0	2.56	2.56	2.56	2.56	2.56	2.56	2.52*	2.51	2.51			
		$\tan \delta$	5.4	4	3.2	3.0	4.0	5.0	7.2	9.0*	9.7	10		
Code 7254 ^d	25	ϵ'/ϵ_0	2.60	2.57	2.56	2.56	2.56	2.55	2.52*	2.52	2.52			
		$\tan \delta$	5.4	3.1	3	4.9	6.7	9	10	11.8*	11.9	11.5		
Marbon 8000 ^e		ϵ'/ϵ_0												
		$\tan \delta$												
Marbon 9200 ^f		ϵ'/ϵ_0												
		$\tan \delta$												

a. Am. Cyanamid. b. Dewey and Almy. c. Copolymer of butadiene and styrene (Dow). d. Butadiene-styrene copolymer, ca. 10% butadiene (Marbon). e. Butadiene-styrene copolymer ca. 15% butadiene (Marbon). f. Butadiene-styrene copolymer ca. 14% butadiene (Marbon).

*Freq. = 1×10^9 .

I. Solids, B. Organic 3. Plastics J. Polyvinyl Resins (cont.) Values for tan δ are multiplied by 10^4 ; frequency given in c/s.

12) Styrene copolymers, linear (cont.)		T°C		$\frac{1 \times 10^2}{\epsilon'/\epsilon_0}$	$\frac{1 \times 10^3}{\tan \delta}$	$\frac{1 \times 10^4}{\epsilon'/\epsilon_0}$	$\frac{1 \times 10^5}{\tan \delta}$	$\frac{1 \times 10^6}{\epsilon'/\epsilon_0}$	$\frac{1 \times 10^7}{\tan \delta}$	$\frac{1 \times 10^8}{\epsilon'/\epsilon_0}$	$\frac{1 \times 10^9}{\tan \delta}$	$\frac{3 \times 10^9}{\epsilon'/\epsilon_0}$	$\frac{1 \times 10^{10}}{\tan \delta}$	$\frac{2.5 \times 10^{10}}{\epsilon'/\epsilon_0}$
Piccolastic D-125 ^a		25	ϵ'/ϵ_0	2.58	2.58	2.58	2.58	2.58	2.58	2.58	2.58	2.55	2.52	
			$\tan \delta$	2	1.5	1	1	1	1.5	3	5	5	5	
Styrene (50%) and 1,3,5-trivinyl-2,4,6-trichlorobenzene (50%) copolymer		25	ϵ'/ϵ_0	2.70	2.70	2.70	2.70	2.70	2.70	2.70	2.66	2.65	2.65	
			$\tan \delta$	8.5	8.9	9.7	10	11	16.2	26	20	21	19	
Styrene (50%) and 1,4-divinyl-2,3,5,6-tetrachlorobenzene (50%) copolymer		25	ϵ'/ϵ_0	2.70	2.70	2.70	2.70	2.70	2.70	2.70	2.70	2.70	2.70	
			$\tan \delta$	6	7.4	8.2	7.8	8.2	12.0	22	13.2	13.8	13.6	
S-40 ^c		25	ϵ'/ϵ_0	2.40	2.40	2.40	2.39	2.39	2.39	2.38	2.37	2.37	2.35	
			$\tan \delta$	21	14	13	12	8	6	6	6.4	6.4	7.1	
S-60 ^c		25	ϵ'/ϵ_0	2.50	2.49	2.48	2.46	2.46	2.45	2.45	2.44	2.44	2.44	
			$\tan \delta$	27	24	20	15	10	6	4	6.5	6.5	7.4	
13) Styrene copolymers cross-linked														
Copolymer 8012 ^d		25	ϵ'/ϵ_0	2.58	2.58	2.58	2.58	2.58	2.57	2.55	2.54	2.53	2.52	
			$\tan \delta$	2.7	1.3	.87	.7	1.1	2	3.8	6.8	8.8	8.9	
Plastic EK2784 ^d		25	ϵ'/ϵ_0	2.59	2.59	2.59	2.56	2.56	2.56	2.56	2.55	2.54	2.52	
			$\tan \delta$	2.6	1.5	1.2	1.4	1.8	2.3	4.2	8.8	6.7	4.7	
Exp. Plastic Q-166 ^e		23	ϵ'/ϵ_0	3.44	3.40	3.38	3.36	3.32	3.22	3.05	2.71	2.71	2.62	
			$\tan \delta$	45	55	70	110	180	350	420	315	315	250	
		80	ϵ'/ϵ_0	3.25	3.23	3.21	3.19	3.16	3.12	3.05	2.85	2.85	2.63	
			$\tan \delta$	550	95	41	38	55	110	250	570	570	550	
Exp. Plastic Q-166 ^e plus Fiberglass		23	ϵ'/ϵ_0	4.46	4.42	4.37	4.30	4.21	4.09	3.95	3.78	3.78	3.70	3.6
			$\tan \delta$	160	110	96	120	180	250	320	241	241	231	200
		79	ϵ'/ϵ_0	4.5	4.4	4.4	4.3	4.2	4.1	4.0	3.8	3.8	3.7	
			$\tan \delta$	880	320	140	85	80	130	220	415	415	470	
Exp. Plastic Q-200.5 ^f		26	ϵ'/ϵ_0	2.55	2.55	2.55	2.55	2.55	2.55	2.55	2.55	2.55	2.55	2.54
			$\tan \delta$	4	< 2	< 2	< 2	2	3.4	4	5.2	5.2	24	
		100	ϵ'/ϵ_0	2.56	2.56	2.56	2.56	2.55	2.55	2.55	2.55	2.55*	2.55	
			$\tan \delta$	20	7	2	< 2	< 2	< 3	7.6*	7.6*	7.6*	7.6*	

a. Methylstyrene-styrene copolymer (Penn. Ind. Chem.). b. Sprague (two different castings measured in the ranges $10^2 - 10^8$ and $10^9 - 10^{10}$ c/s.) c. Standard Oil Dev. Co. N.J. d. Catalin. e. Dow. f. Cross-linked with o-, m-, p-divinylbenzenes (Dow).

*Measurements made at 78°C.

I. Solids, B. Organic 3. Plastics J. Polyvinyl Resins (cont.) Values for $\tan \delta$ are multiplied by 10^4 ; frequency given in c/s.

13) Styrene copolymers cross-linked (cont.) T°C		1×10^2	1×10^3	1×10^4	1×10^5	1×10^6	1×10^7	1×10^8	3×10^8	1×10^{10}	2.5×10^{10}
Exp. Plastic Q-344 ^a		ϵ'/ϵ_0	$\tan \delta$	ϵ'/ϵ_0	$\tan \delta$	ϵ'/ϵ_0	$\tan \delta$	ϵ'/ϵ_0	$\tan \delta$	ϵ'/ϵ_0	$\tan \delta$
24		2.40	11	2.40	20	2.38	20	2.38	2.38	2.31	2.31
80		2.4	2.4	2.39	2.38	2.38	2.38	2.35	2.33	2.31	2.31
22		2.51	21	2.51	16	2.51	19	2.51	2.50	2.49	2.49
Exp. Plastic Q-475.5 ^a		ϵ'/ϵ_0	$\tan \delta$	ϵ'/ϵ_0	$\tan \delta$	ϵ'/ϵ_0	$\tan \delta$	ϵ'/ϵ_0	$\tan \delta$	ϵ'/ϵ_0	$\tan \delta$
80		2.48	4	2.48	2	2.48	2	2.48	2.47	2.47	2.47
25		2.58	6	2.58	2	2.55	2	2.55	2.53*	2.51	2.51
25		6.8	2.58	3.3	2.5	4.7	7.3	7.8	7.6*	7.2	6.7
25		2.58	2.58	2.58	2.58	2.58	2.58	2.58	2.55*	2.52	2.52
25		7.7	6	3.5	1.8	2.6	3.6	6.2	15*	8.8	7.5
25		2.58	2.58	2.58	2.58	2.58	2.58	2.58	2.53*	2.52	2.51
25		6	2.9	2.4	1.9	2	3.7	6.8	10.6*	11	8
25		2.58	2.58	2.58	2.58	2.58	2.58	2.58	2.57	2.52	2.52
25		6.6	2.8	2.1	2.1	2.1	3	5.5	16	7.6	6.3
25		2.51	2.51	2.51	2.51	2.50	2.50	2.47	2.47	2.46	2.46
25		8	10	13	27	34	31	29	30	39	39
25		2.55	2.55	2.55	2.55	2.55	2.55	2.55	2.55*	2.54	2.54
25		2.1	1.1	1	1.1	1.3	2	3.8	4.6*	4.8	4.7
25		2.64	2.64	2.62	2.62	2.62	2.62	2.62	2.60	2.59	2.59
25		20	15.6	11	7	4.7	9	11	11	5	5
25		2.59	2.59	2.59	2.58	2.58	2.58	2.58	2.58	2.57	2.57
25		4	5	8	12	16	19	20	19	17.5	17.5
23		2.64	2.64	2.64	2.63	2.62	2.62	2.62	2.62	2.62	2.62
23		6	7	11	19	33	39	34	28	28	28

a. Cross-linked polystyrene (Dow). b. Goodyear. c. Esso C oil in styrene-divinylbenzene solution (Polaroid). d. Rex Corp.

e. 32.5% polystyrene, 53.5% poly-2,5-dichlorostyrene, 13% hydrogenated terphenyl, 0.5% divinylbenzene (U.S. Bur. Stand.).

f. U. S. Rubber.

*Freq. = 1×10^9 .

I. Solids B. Organic 3. Plastics J. Polyvinyl resins (cont.) Values for $\tan \delta$ are multiplied by 10^4 ; frequency given in c/s.

14) Polystyrene plus fillers		T ^o C	ϵ'/ϵ_0	1×10^2	1×10^3	1×10^4	1×10^5	1×10^6	1×10^7	1×10^8	3×10^8	3×10^9	1×10^{10}	2.5×10^{10}
Polystyrene 91%, carbon 9% ^a		26	ϵ'/ϵ_0	3.85	3.85	3.85	3.85	3.95	3.84	---	3.81	3.60	3.46	
			$\tan \delta$	17	24	30	33	32	37	---	310	386	344	
Polystyrene 70%, carbon 30% ^a		25	ϵ'/ϵ_0	---	---	---	---	---	---	---	11*	9.1	8.8	
			$\tan \delta$	---	---	---	---	---	---	---	2300*	2500	1100	
Polystyrene 50%, carbon 50% ^a		25	ϵ'/ϵ_0	---	---	---	---	---	---	---	25.9*	20.8	19.4	
(molded at 1000 p.s.i.)			$\tan \delta$	---	---	---	---	---	---	---	7300*	5600	2800	
(molded at 10000 p.s.i.)		25	ϵ'/ϵ_0	---	---	---	---	---	---	---	36*	25	24	
			$\tan \delta$	---	---	---	---	---	---	---	4600*	6200	3000	
Lustrer Loaded Glass Mat ^b		25	ϵ'/ϵ_0	3.04	3.04	3.02	3.00	2.97	2.97	2.96	---	---	---	
(field $\perp$ plane of laminate)			$\tan \delta$	13.8	8.8	7.4	7	8.3	10.6	13.8	---	---	---	
(field in plane of laminate)		25	ϵ'/ϵ_0	---	---	---	---	---	---	---	---	3.07	3.07	
			$\tan \delta$	---	---	---	---	---	---	---	---	31	36	
Polyglas P ⁺ (experimental) ^c		24	ϵ'/ϵ_0	3.36	3.36	3.36	3.36	3.36	3.36	---	---	3.35	3.33	3.32
			$\tan \delta$	8	7	7	7	7	7	---	---	7.8	8.4	14.0
		79	ϵ'/ϵ_0	3.36	3.36	3.36	3.36	3.36	3.36	---	---	3.35	3.33	
			$\tan \delta$	30	17	12	9	8	7	---	---	14	19	
Polyglas P ⁺ (technical) ^d		25	ϵ'/ϵ_0	3.38	3.38	3.38	3.38	3.38	3.38	---	3.36	3.35	3.34	
			$\tan \delta$	9	9	9	9	9	9	---	9.6	11.7	19	
15) Polychlorostyrenes														
Plastic CX-8 ^e		24	ϵ'/ϵ_0	2.61	2.61	2.60	2.60	2.60	2.60	2.6	---	2.60	---	2.59
			$\tan \delta$	< 2	< 2	< 2	< 2	< 2	2	2.5	---	3.1	---	29
		80	ϵ'/ϵ_0	2.61	2.61	2.60	2.60	2.60	2.60	2.6	---	2.60	---	
			$\tan \delta$	6	2	< 3	< 3	< 3	3	4	---	7.3	---	
Plastic CQ-10DM ^f		25	ϵ'/ϵ_0	2.70	2.70	2.70	2.70	2.70	2.70	2.69	2.67	2.66	---	
			$\tan \delta$	5	5	5	6	8	10	11	11	10.8	---	
		100	ϵ'/ϵ_0	2.66	2.65	2.65	2.65	2.65	2.65	2.65	2.65	2.65	---	
			$\tan \delta$	33	17	8	6	7	11	16	17	17	---	

a. Cabot's #9 (Lab. Ins. Res.). b. 30% fiberglass (Monsanto). c. 18.6% Dow's C-244 polystyrene, 81.4% Corning's 790-glass powder, 0.25% paraffin, 0.1% Dow Corning's Ignition Sealing Compound No. 4 (Lab. Ins. Res.). d. Id. except that Monsanto's polystyrene was used (Monsanto). e. 97% poly-2,5-dichlorostyrene (Mathieson). f. Copolymer of 50% 2,4,6-trichlorostyrene, 25% 2,3,6-trichlorostyrene, 25% 2,4,6-trichlorostyrene (Mathieson).

*Freq. = 1×10^9 .

I. Solids B. Organic 3. Plastics 1. Polyvinyl Resins (cont.) Values for $\tan \delta$ are multiplied by 10^4 ; frequency given in c/s.

15) Polychlorostyrenes													
(cont.)													
Poly-3, 4-dichloro-styrene ^a													
T°C	ϵ'/ϵ_0	$\tan \delta$	1×10^2	1×10^3	1×10^4	1×10^5	1×10^6	1×10^7	1×10^8	3×10^8	3×10^9	1×10^{10}	2.5×10^{10}
25	ϵ'/ϵ_0	$\tan \delta$	2.94	2.93	2.91	2.88	2.85	2.80	2.77	----	2.72	2.70	
82	ϵ'/ϵ_0	$\tan \delta$	85	70	57	50	42	35	27	----	20	20	
	ϵ'/ϵ_0	$\tan \delta$	3.0	2.90	2.85	2.83	2.78	2.73	2.68	----	2.65		
103	ϵ'/ϵ_0	$\tan \delta$	203	157	115	77	63	60	55	----	32		
	ϵ'/ϵ_0	$\tan \delta$	3.08	2.92	2.85	2.81	2.8	2.8	2.75	----	2.7	2.7	
153	ϵ'/ϵ_0	$\tan \delta$	355	275	200	120	82	78	70	----	60	60	
	ϵ'/ϵ_0	$\tan \delta$	6.0	4.9	3.7	3.3							
24	ϵ'/ϵ_0	$\tan \delta$	850	1700	1400	750							
	ϵ'/ϵ_0	$\tan \delta$	2.60	2.60	2.60	2.60	2.60	2.60	2.60	----	2.60	2.60	2.60
90	ϵ'/ϵ_0	$\tan \delta$	10	7	5	5	4	4	5	----	8.7	12	16
	ϵ'/ϵ_0	$\tan \delta$	2.69	2.69	2.68	2.68	2.68	2.67	2.65	----	2.64	2.60	
Polyglas D ^c (experimental) ^c 24	ϵ'/ϵ_0	$\tan \delta$	50	25	14	8	5.5	5.5	7	----	11	18	
	ϵ'/ϵ_0	$\tan \delta$	3.22	3.22	3.22	3.22	3.22	3.22	3.22	----	3.22	3.22	
79	ϵ'/ϵ_0	$\tan \delta$	7	6	5	5	6	6	7	----	8	8.5	
	ϵ'/ϵ_0	$\tan \delta$	3.2	3.2	3.2	3.2	3.2	3.2	3.2	----	3.2	3.2	
Polyglas D ^d (technical) ^d 24	ϵ'/ϵ_0	$\tan \delta$	34	17	11	8	7	7	8	----	13	16	
	ϵ'/ϵ_0	$\tan \delta$	3.25	3.25	3.25	3.25	3.25	3.25	3.24	----	3.23	3.22	3.22
	ϵ'/ϵ_0	$\tan \delta$	3	3	4	4	5	6	7	----	12	13	14
	ϵ'/ϵ_0	$\tan \delta$	3										
16) Poly-2,5-dichloro-styrene plus fillers													
Poly-2,5-dichlorostyrene (58.1%), TiO ₂ (41.9%) ^e 23	ϵ'/ϵ_0	$\tan \delta$	5.30	5.30	5.30	5.30	5.30	5.30	5.30	----	5.30	5.30	
	ϵ'/ϵ_0	$\tan \delta$	26	14	8	5	3	3	3	----	6	8.5	
Poly-2,5-dichlorostyrene (34.7%), TiO ₂ (65.3%) ^e 24	ϵ'/ϵ_0	$\tan \delta$	10.2	10.2	10.2	10.2	10.2	10.2	10.2	----	10.2	10.2	
	ϵ'/ϵ_0	$\tan \delta$	16	8	6	4	3	3	3	----	7.5	13	
Poly-2,5-dichlorostyrene (18.6%), TiO ₂ (81.4%) ^e 23	ϵ'/ϵ_0	$\tan \delta$	23.6	23.4	23.2	23.1	23.0	23.0	23.0	----	----	23.0	
	ϵ'/ϵ_0	$\tan \delta$	60	41	30	20	12	9	8	----	----	15.6	

a. ca. 95% (Monsanto). b. Copolymer of o- and p-chlorostyrenes (Dow). c. 34.9% Monsanto's poly-2,5-dichlorostyrene; 64.9% Corning's 790 glass powder, 0.1% paraffin wax, 0.1% Dow Corning's Ignition Sealing Compound No. 4 (Lab. Ins. Res.). d. Id. (Monsanto).

e. Monsanto's Styramic HT; Titanium Alloy's Tam Ticon T, heavy grade (Lab. Ins. Res.).

a. Monsanto's Styramic HT; Titanium Alloy's Tam Ticon MC (Lab. Ins. Res.). b. Monsanto's Styramic HT; Titanium Alloy's Tam Ticon S ((Lab. Ins. Res.). c. Monsanto's Styramic HT; Titanium Alloy's Tam Ticon B (Lab. Ins. Res.). d. Monsanto's D-1795; Plastic Metals' Plast-Iron, minus 20 mesh, annealed (Lab. Ins. Res.).

I. Solids B. Organic 3. Plastics J. Polyvinyl Resins (cont.) Values for $\tan \delta$ are multiplied by 10^4 ; frequency given in c/s.

16) Poly-2,5-dichlorostyrene

plus fillers (cont.) $T^\circ C$

Poly-2,5-dichlorostyrene 25
(60%), Fe (40%)^a

	1×10^2	1×10^3	1×10^4	1×10^5	1×10^6	1×10^7	1×10^8	3×10^8	3×10^9	1×10^{10}
ϵ'/ϵ_0	---	---	---	---	---	---	---	---	5.3	5.2
μ'/μ_0	---	---	---	---	---	---	---	---	1.16	.96
$\tan \delta_d$	---	---	---	---	---	---	---	---	270	190
$\tan \delta_m$	---	---	---	---	---	---	---	---	2300	2620

85

ϵ'/ϵ_0	---	---	---	---	---	---	---	---	5.1	---
μ'/μ_0	---	---	---	---	---	---	---	---	1.27	---
$\tan \delta_d$	---	---	---	---	---	---	---	---	---	---
$\tan \delta_m$	---	---	---	---	---	---	---	---	---	---

Poly-2,5-dichlorostyrene 25
(49.3%), Fe (50.7%)^a

ϵ'/ϵ_0	9.8	9.7	9.5	9.2	9.0	8.7	---	---	---	---
μ'/μ_0	---	3.00	---	---	---	2.70	---	---	6.93	---
$\tan \delta_d$	110	130	160	190	220	320	---	---	1.24	---
$\tan \delta_m$	---	---	---	---	---	340	---	---	644	---

Poly-2,5-dichlorostyrene 25
(40.7%), Fe (59.3%)^a

ϵ'/ϵ_0	---	---	---	---	---	---	---	---	10	---
μ'/μ_0	---	---	---	---	---	---	---	---	1.37	---
$\tan \delta_d$	---	---	---	---	---	---	---	---	1400	---
$\tan \delta_m$	---	---	---	---	---	---	---	---	4500	---

Poly-2,5-dichlorostyrene 25
(92%), Fe₃O₄ (8%)^b

ϵ'/ϵ_0	---	---	---	---	---	---	---	---	2.76	2.64
μ'/μ_0	---	---	---	---	---	---	---	---	1.03	1.03
$\tan \delta_d$	---	---	---	---	---	---	---	---	---	---
$\tan \delta_m$	---	---	---	---	---	---	---	---	---	---

Poly-2,5-dichlorostyrene 25
(83.7%), Fe₃O₄ (16.3%)^b

ϵ'/ϵ_0	---	---	---	---	---	---	---	---	---	---
μ'/μ_0	---	---	---	---	---	---	---	---	---	---
$\tan \delta_d$	---	---	---	---	---	---	---	---	---	---
$\tan \delta_m$	---	---	---	---	---	---	---	---	---	---

Poly-2,5-dichlorostyrene
(75%) Fe₃O₄ (25%)^b

ϵ'/ϵ_0	---	---	---	---	---	---	---	---	420	580
μ'/μ_0	---	---	---	---	---	---	---	---	3.44	---
$\tan \delta_d$	---	---	---	---	---	---	---	---	1.12	---
$\tan \delta_m$	---	---	---	---	---	---	---	---	26	---

a. Monsanto's D-1795; Plastic Metals' Plast-Iron, minus 200 mesh, annealed (Lab. Ins. Res.). b. Monsanto's D-1795; Mallinckrodt's magnetite (Lab. Ins. Res.).

I. Solids B. Organic 3. Plastics J. Polyvinyl Resins (cont.) Values for $\tan \delta$ are multiplied by 10^4 ; frequency given in c/s.

16) Poly-2,5-dichlorostyrene plus fillers (cont.) $T^{\circ}C$		1×10^2	1×10^3	1×10^4	1×10^5	1×10^6	1×10^7	1×10^8	3×10^8	3×10^9	1×10^{10}
Poly-2,5-dichlorostyrene 25		ϵ'/ϵ_0	----	----	----	----	----	----	4.08	4.07	
(55.9%) Fe_3O_4 (34.1%) ^a		μ'/μ_0	----	----	----	----	----	----	1.30	1.17	
		$\tan \delta_d$	----	----	----	----	----	----	42		
		$\tan \delta_m$	----	----	----	----	----	----	390	1010	
Poly-2,5-dichlorostyrene 25		ϵ'/ϵ_0	----	----	----	----	----	----	5.00	4.98	
(56.2%) Fe_3O_4 (43.8%) ^a		μ'/μ_0	----	----	----	----	----	----	1.45	1.23	
		$\tan \delta_d$	----	----	----	----	----	----	75		
		$\tan \delta_m$	----	----	----	----	----	----	560	1720	
Poly-2,5-dichlorostyrene 25		ϵ'/ϵ_0	----	----	----	----	----	----	7.4	7.3	7.3
(46.0%) Fe_3O_4 (54.0%) ^a		μ'/μ_0	----	----	----	----	----	----	1.65	1.32	.91
		$\tan \delta_d$	----	----	----	----	----	----	150		
		$\tan \delta_m$	----	----	----	----	----	----	780	2400	3500
Poly-2,5-dichlorostyrene 25		ϵ'/ϵ_0	----	----	----	----	----	----	9.8	9.5	
(35.7%) Fe_3O_4 (64.3%) ^a		μ'/μ_0	----	----	----	----	----	----	1.94	1.41	
		$\tan \delta_d$	----	----	----	----	----	----	450	180	
		$\tan \delta_m$	----	----	----	----	----	----	980	3000	
Poly-2,5-dichlorostyrene 25		ϵ'/ϵ_0	----	----	----	----	----	----	20	18	
(24.5%) Fe_3O_4 (75.5%) ^a		μ'/μ_0	----	----	----	----	----	----	2.38	1.60	
		$\tan \delta_d$	----	----	----	----	----	----	2000	300	
		$\tan \delta$	----	----	----	----	----	----	1430	3700	
Poly-2,5-dichlorostyrene 25		ϵ'/ϵ_0	24.8	16.9	11.9	7.6	5.0	----	3.76		
(38.55%) $(Mn, Fe)_3O_4$ (61.45%) ^b		μ'/μ_0	----	----	----	----	----	----	2.56		
		$\tan \delta_d$	2500	2500	2400	1900	900	----			
		$\tan \delta_m$	----	----	----	----	----	----	4000		
Poly-2,5-dichlorostyrene 25		ϵ'/ϵ_0	----	99	39	21	7.4	----	6.9	6.5	
(21.3%) $(Mn, Fe)_3O_4$ (78.7%) ^b		μ'/μ_0	----	----	----	----	----	----	4.3	1.32	
		$\tan \delta_d$	----	2700	10000	4800	930	----	90	< 50	
		$\tan \delta_m$	----	----	----	----	----	----	4900	13200	

a. Monsanto's D-1795; Mallinckrodt's magnetite (lab. Ins. Res.). b. Monsanto's D-1795; iron-manganese oxide (lab. Ins. Res.).

I. Solids B. Organic 3. Plastics J. Polyvinyl Resins (cont.) Values for $\tan \delta$ are multiplied by 10^4 ; frequency given in c/s.

17) Polyvinyl cyclohexane		T°C	ϵ'/ϵ_0	$\tan \delta$	1×10^2	1×10^3	1×10^4	1×10^5	1×10^6	1×10^7	1×10^8	3×10^8	3×10^9	1×10^{10}
Polyvinylcyclohexane ^a		24	ϵ'/ϵ_0	$\tan \delta$	2.25	2.25	2.25	2.25	2.25	2.25	2.25	2.25	2.25	2.25
			$\tan \delta$		15	2	< 2	< 2	< 2	< 2	< 2	1.8	1.8	3.9
18) Poly- α -vinyl naphthalene			ϵ'/ϵ_0	$\tan \delta$										
Poly- α -vinyl naphthalene ^b		24	ϵ'/ϵ_0	$\tan \delta$	-----	2.6	2.6	2.6	2.6	2.6	2.6			
			$\tan \delta$		-----	9.5	6.7	7.5	8.7	13	22			
19) Poly-2-vinylpyridine			ϵ'/ϵ_0	$\tan \delta$										
Poly-2-vinylpyridine ^b		22	ϵ'/ϵ_0	$\tan \delta$	4.91	4.64	4.26	3.77	3.56	3.33	3.1	3.06	2.98	
			$\tan \delta$		360	460	560	600	560	420	280	240	135	
2-Vinylpyridine-styrene copolymer ^b		23	ϵ'/ϵ_0	$\tan \delta$	3.44	3.38	3.26	3.13	3.00	2.90	2.82	-----	2.76	
			$\tan \delta$		168	230	270	290	260	185	120	-----	65	
20) Poly-N-vinylcarbazole			ϵ'/ϵ_0	$\tan \delta$										
Polectron #24 ^c		25	ϵ'/ϵ_0	$\tan \delta$	2.95	2.95	2.95	2.95	2.95	2.95	2.95	-----	2.88	
			$\tan \delta$		13	9	6	5	4	5	6	-----	9.3	
80			ϵ'/ϵ_0	$\tan \delta$	2.95	2.95	2.95	2.95	2.95	2.95				
			$\tan \delta$		19	10	8	9	9	7				
k. Polyesters			ϵ'/ϵ_0	$\tan \delta$										
Laminac 4115 ^d		25	ϵ'/ϵ_0	$\tan \delta$	3.24	3.22	3.20	3.17	3.12	3.07	2.94	2.87*	2.83	2.82
			$\tan \delta$		37.5	43.2	68.3	113	135	147	141	107*	93	88
Experimental Resin PDL7-669 ^d		25	ϵ'/ϵ_0	$\tan \delta$	4.15	4.05	3.93	3.77	3.58	3.44	3.20	-----	3.00	2.95
			$\tan \delta$		155	192	247	306	313	282	240	-----	155	142
Laminac PDL7-627 ^d		25	ϵ'/ϵ_0	$\tan \delta$	3.26	3.25	3.23	3.18	3.08	3.06	3.03	2.96*	2.92	2.86
			$\tan \delta$		50.5	42.8	67.8	115	140	148	135	107*	95	91.4
Laminac PDL7-650 ^d		25	ϵ'/ϵ_0	$\tan \delta$	3.02	3.00	2.98	2.95	2.89	2.82	2.78	-----	2.74	2.72
			$\tan \delta$		39.1	45.0	60.2	100	119	114	108	-----	92	96
Laminac 4-205 ^d		25	ϵ'/ϵ_0	$\tan \delta$	4.45	4.36	4.24	4.03	3.86	3.69	3.49	-----	3.21	3.15
			$\tan \delta$		147	162	219	301	360	345	340	-----	240	243
Formica Z65 ^e		25	ϵ'/ϵ_0	$\tan \delta$	5.21	5.10	5.00	4.89	4.70	4.35	-----	3.83*	3.69	3.49
			$\tan \delta$		191	162	212	317	434	570	-----	485*	445	425
(field II laminate)			ϵ'/ϵ_0	$\tan \delta$	4.77	4.70	4.68	4.60	4.45	4.17				
(field I laminate)		25	ϵ'/ϵ_0	$\tan \delta$										
			$\tan \delta$		125	108	131	185	302	418				

a. Hydrogenated polystyrene (Dow). b. Lab. Ins. Res. c. Poly-N-vinylcarbazole, 1.3% HB-40 oil (Gen. Aniline). d. Amer. Cyanamid.
e. 50% Shell's DAP 85/80, 50% paper (Formica).
*F_{req.} = 1×10^9 .

I. Solids B. Organic 3. Plastics (cont.) Values for $\tan \delta$ are multiplied by 10^4 ; frequency given in c/s.

k. Polyesters (cont.)		$T^\circ C$	1×10^2	1×10^3	1×10^4	1×10^5	1×10^6	1×10^7	1×10^8	3×10^8	3×10^9	1×10^{10}
Formica Z80 ^a		25	ϵ'/ϵ_0	4.76	4.75	4.72	4.65	4.46	4.08	3.77	3.53*	3.41
(field II laminate)			$\tan \delta$	175	160	210	310	420	565	500	390*	310
(field I laminate)		25	ϵ'/ϵ_0	4.52	4.42	4.38	4.33	4.15	3.91			250
			$\tan \delta$	95	96	130	197	330	440			
Glastic S ^b		26	ϵ'/ϵ_0	3.50	3.39	3.29	3.22	3.16	3.14	3.07		
			$\tan \delta$	330	250	160	98	100	105	130		
Glastic MF ^b		26	ϵ'/ϵ_0	3.92	3.82	3.76	3.72	3.65	3.57	3.53		
			$\tan \delta$	270	185	135	125	130	130	135		
Plaskon 911 ^c		24	ϵ'/ϵ_0	3.88	3.81	3.75	3.66	3.56	3.42	3.25	3.17	3.07
			$\tan \delta$	89	125	165	210	240	240	220	217	175
		80	ϵ'/ϵ_0	4.27	4.17	4.06	3.95	3.83	3.70	3.55	3.26	3.10
			$\tan \delta$	165	150	155	200	270	320	340	299	248
Marco Resin MR-21C ^d		25	ϵ'/ϵ_0	3.37	3.35	3.31	3.25	3.16	3.08	2.90	2.84	2.82
			$\tan \delta$	53	51	65	102	150	170	149	106	123
Marco Resin MR-23C ^d		25	ϵ'/ϵ_0	4.56	4.50	4.40	4.28	4.14	3.88	3.24	2.92	2.82
			$\tan \delta$	130	140	170	220	340	570	810	500	410
Marco Resin MR-25C ^d		25	ϵ'/ϵ_0	3.27	3.24	3.20	3.15	3.10	3.06	2.90	2.77	2.73
			$\tan \delta$	76	72	82	108	138	165	190	185	135
Laminating Resin MP, Glass reinforced ^e		25	ϵ'/ϵ_0	-----	-----	-----	-----	-----	-----	-----	-----	4.26
			$\tan \delta$	-----	-----	-----	-----	-----	-----	-----	-----	110
Laminating Resin MT, Glass reinforced ^f		25	ϵ'/ϵ_0	-----	-----	-----	-----	-----	-----	-----	-----	4.24
			$\tan \delta$	-----	-----	-----	-----	-----	-----	-----	-----	88
Laminate BD-44 ^g		24	ϵ'/ϵ_0	3.32	3.28	3.22	3.19	3.14	3.08	3.02	2.99	2.91
			$\tan \delta$	95	81	85	105	125	140	150	132	109

a. 52% Shell's DAP 25/50, 48% yarn fabric (Formica). b. With Fiberglass (Laminated Plastics). c. Unsaturated polyester (Libby-Ovens-Ford). d. Unsaturated polyester (Marco). e. Resin of 50% Vibron x-1039 alkyd and 50% triallyl cyanurate plus catalyst and Fiberglass ECC-181-114 (Naugatuck). f. Resin of 45% polyethylene tetraclophthate-maleate alkyd and 55% triallyl cyanurate plus catalyst and Fiberglass ECC-181-11¹ (Naugatuck). g. Selectron 5003, Fiberglass (Ovens-Corning).

*Freq. = 1×10^9 .

I. Solids B. Organic 3. Plastics (cont.) Values for tan δ are multiplied by 10^4 ; frequency given in c/s.

k. Polyesters (cont.)	T ^o C	ϵ'/ϵ_0	$\tan \delta$	1×10^2	1×10^3	1×10^4	1×10^5	1×10^6	1×10^7	1×10^8	3×10^8	3×10^9	1×10^{10}	2.5×10^{10}
Laminate BK 164 ^a	24	ϵ'/ϵ_0	$\tan \delta$	4.12	4.10	4.09	4.07	4.05	4.03	4.00	3.98	3.94	3.90	
Stypol 16b ^b	25	ϵ'/ϵ_0	$\tan \delta$	67	58	63	80	96	110	112	108	120	130	
Stypol 16c ^b	25	ϵ'/ϵ_0	$\tan \delta$	-----	-----	-----	-----	-----	-----	-----	-----	-----	2.88	
Stypol 16d ^b	25	ϵ'/ϵ_0	$\tan \delta$	-----	-----	-----	-----	-----	-----	-----	-----	-----	180	
Paraplex P13 ^c	25	ϵ'/ϵ_0	$\tan \delta$	-----	-----	-----	-----	-----	-----	-----	-----	-----	2.75	
Paraplex P43 ^c	25	ϵ'/ϵ_0	$\tan \delta$	-----	-----	-----	-----	-----	-----	-----	-----	-----	160	
Polydiallyl phthalate ^d	26.8	ϵ'/ϵ_0	$\tan \delta$	-----	-----	-----	-----	-----	-----	-----	-----	-----	2.81	
Allymer CR-39 ^e	24	ϵ'/ϵ_0	$\tan \delta$	-----	-----	-----	-----	-----	-----	-----	-----	-----	140	
	84	ϵ'/ϵ_0	$\tan \delta$	-----	-----	-----	-----	-----	-----	-----	-----	-----	2.77	
Allymer CR-39 laminate ^f	25	ϵ'/ϵ_0	$\tan \delta$	4.02	4.00	3.92	3.92	3.65	3.32	3.08	2.89*	2.77	2.77	
Phoresin ^g	25	ϵ'/ϵ_0	$\tan \delta$	73	108	184	310	530	590	600	440*	320	290	
		ϵ'/ϵ_0	$\tan \delta$	3.23	3.22	3.19	3.16	3.11	3.04	2.98	2.89*	2.85	2.85	
		ϵ'/ϵ_0	$\tan \delta$	33	43	68	98	130	160	160	110*	100	80	
		ϵ'/ϵ_0	$\tan \delta$	3.60	3.57	3.50	3.42	3.35	3.24	3.1	-----	2.95	2.95	
		ϵ'/ϵ_0	$\tan \delta$	104	95	118	150	200	241	195	-----	118	118	
		ϵ'/ϵ_0	$\tan \delta$	4.18	4.14	4.03	3.85	3.52	3.27	3.07	-----	2.88	-----	2.76
		ϵ'/ϵ_0	$\tan \delta$	90	120	210	380	520	460	330	-----	203	-----	165
		ϵ'/ϵ_0	$\tan \delta$	4.90	4.84	4.70	4.47	4.18	3.85	3.45	-----	3.02	-----	
		ϵ'/ϵ_0	$\tan \delta$	130	140	170	250	440	840	740	-----	370	-----	
		ϵ'/ϵ_0	$\tan \delta$	4.84	4.80	4.73	4.57	4.37	4.17	3.98	-----	3.78	-----	
		ϵ'/ϵ_0	$\tan \delta$	73	80	120	208	315	295	205	-----	140	-----	
		ϵ'/ϵ_0	$\tan \delta$	3.98	3.84	3.70	3.65	3.49	3.32	3.15	3.10	3.03	3.02	2.96
		ϵ'/ϵ_0	$\tan \delta$	260	270	320	330	280	210	165	145	171	165	164
M. Alkyd resins														
Chlorinated alkyd	25	ϵ'/ϵ_0	$\tan \delta$	-----	-----	-----	-----	-----	-----	-----	-----	-----	1.179	
diisocyanate, foamed ^h		ϵ'/ϵ_0	$\tan \delta$	-----	-----	-----	-----	-----	-----	-----	-----	-----	27	
Alkyd, diisocyanate, foamed ^k	25	ϵ'/ϵ_0	$\tan \delta$	1.223	1.223	1.223	1.223	1.218	1.205	1.20	-----	1.20	1.19	
Red Glyptal #1201 ^m	25	ϵ'/ϵ_0	$\tan \delta$	19.8	14.7	22.7	33.5	41	42	38	-----	34	22	
		ϵ'/ϵ_0	$\tan \delta$	4.9	4.5	4.1	4.0	3.9	3.8					
		ϵ'/ϵ_0	$\tan \delta$	760	600	500	400	320	290					

a. 38% polyester (Bakelite BR3-16631), 62% Fiberglas (Owens-Corning). b. Robertson. c. Rohm and Haas. d. Shell Dev. e. Allyl resin (Southern Alkali Corp.) f. 40% resin, 60% BCC-11-148 Fiberglas (Southern Alkali Corp.). g. Diallyl phenyl phosphonate resin (Victor). h. Cornell Aeronautical Labs. k. Goodyear Aircraft. m. General Electric.

*Frequency = 1×10^9 .

I. Solids B. Organic 3. Plastics (cont.) Values for $\tan \delta$ are multiplied by 10^4 ; frequency given in c/s.

m. Alkyd resins (cont.)		T°C	ϵ'/ϵ_0	$\frac{1 \times 10^2}{\tan \delta}$	$\frac{1 \times 10^3}{\epsilon'/\epsilon_0}$	$\frac{1 \times 10^4}{\tan \delta}$	$\frac{1 \times 10^5}{\epsilon'/\epsilon_0}$	$\frac{1 \times 10^6}{\tan \delta}$	$\frac{1 \times 10^7}{\epsilon'/\epsilon_0}$	$\frac{1 \times 10^8}{\tan \delta}$	$\frac{3 \times 10^8}{\epsilon'/\epsilon_0}$	$\frac{3 \times 10^9}{\tan \delta}$	$\frac{1 \times 10^{10}}{\epsilon'/\epsilon_0}$
#51 Permo Potting Compound ^a	Glastic Grade GF ^b	25	ϵ'/ϵ_0	3.18	2.95	2.83	2.74	2.70	2.64	2.59	2.55*	2.53	2.52
		25	$\tan \delta$	730	410	260	174	124	101	120	182*	125	122
Glastic Grade MM ^b	Glastic Grade MP ^b	25	ϵ'/ϵ_0	-----	-----	-----	-----	3.76					
		25	$\tan \delta$	-----	-----	-----	-----	95					
Glastic Grade A-2 ^b	Plaskon Alkyd Special ^c	25	ϵ'/ϵ_0	4.17	4.13	4.09	4.02	3.96	3.88	3.78			
		25	$\tan \delta$	102	87	84	99	115	125	136			
Plaskon Alkyd 411 ^c	Plaskon Alkyd 420 ^c	25	ϵ'/ϵ_0	-----	-----	-----	-----	3.56					
		25	$\tan \delta$	-----	-----	-----	-----	267					
Plaskon Alkyd 422 ^c	Plaskon Alkyd 440 ^c	25	ϵ'/ϵ_0	-----	-----	-----	-----	4.34					
		25	$\tan \delta$	-----	-----	-----	-----	518					
Plaskon Alkyd 440A ^c	Plaskon Alkyd 442 ^c	25	ϵ'/ϵ_0	5.32	5.10	4.96	4.90	4.76	4.65	4.55	4.54*	4.50	4.47
		25	$\tan \delta$	366	236	170	147	149	152	138	121*	108	138
n. Epoxy resins	Araldite Casting Resin Type B ^d	25	ϵ'/ϵ_0	6.02	5.77	5.60	5.36	5.19	4.95	4.63	-----	4.32	4.31
		25	$\tan \delta$	340	240	220	260	310	320	288	-----	220	178
Araldite E-134 ^d	Araldite Casting Resin G ^d	25	ϵ'/ϵ_0	5.50	5.35	5.24	5.10	5.03	4.90	4.82			
		25	$\tan \delta$	270	160	130	147	153	147	145			
Araldite E-134 ^d	Araldite Casting Resin G ^d	25	ϵ'/ϵ_0	5.47	5.26	5.14	5.01	4.92	4.85	4.77	4.75*	4.75	4.72
		25	$\tan \delta$	365	213	151	134	120	113	110	100*	104	126
Araldite E-134 ^d	Araldite Casting Resin G ^d	25	ϵ'/ϵ_0	5.13	5.04	4.95	4.85	4.73	4.61	4.50	4.42*	4.38	4.33
		25	$\tan \delta$	191	151	154	185	196	188	172	133*	137	146
Araldite E-134 ^d	Araldite Casting Resin G ^d	25	ϵ'/ϵ_0	5.28	5.19	5.10	4.97	4.90	4.78	4.65	4.63*	4.62	4.61
		25	$\tan \delta$	165	133	131	143	146	146	134	124*	141	149
Araldite E-134 ^d	Araldite Casting Resin G ^d	25	ϵ'/ϵ_0	5.02	4.89	4.80	4.71	4.59	4.50	4.44	4.37*	4.34	4.29
		25	$\tan \delta$	212	189	140	141	146	142	122	127*	131	141
Araldite E-134 ^d	Araldite Casting Resin G ^d	25	ϵ'/ϵ_0	3.67	3.67	3.67	3.65	3.62	3.49	3.35	3.28	3.09	3.01
		25	$\tan \delta$	17	24	50	110	190	270	340	340	270	220
Araldite E-134 ^d	Araldite Casting Resin G ^d	25	ϵ'/ϵ_0	7.3	6.1	5.3	4.7	4.4	4.1	3.7	3.5	3.2	3.1
		25	$\tan \delta$	1200	1050	920	760	770	1000	1300	750	460	390
Araldite E-134 ^d	Araldite Casting Resin G ^d	25	ϵ'/ϵ_0	4.05	3.99	3.92	3.81	3.69	3.54	3.39	3.25*	3.15	3.10
		25	$\tan \delta$	105	104	141	210	270	288	300	311*	310	263

a. Hardman. b. Laminated Plastics. c. Libbey-Owens-Ford. d. Ciba.

I. Solids B. Organic 3. Plastics (cont.) Values for tan δ are multiplied by 10^4 ; frequency given in c/s.

n. Epoxy Resins													
(cont.)													
T°C		ϵ'/ϵ_0	$\tan \delta$	1×10^2	1×10^3	1×10^4	1×10^5	1×10^6	1×10^7	1×10^8	3×10^8	1×10^9	2.5×10^{10}
25	Araldite Adhesive			4.00	3.97	3.91	3.82	3.71	3.46	3.27	3.14		
	Type I Natural ^a			29	52	120	200	300	350	340	230		
25	Araldite Adhesive			11.6	11.6	11.5	11.3	11.0	10.5	10.2	9.9	9.6	9.2
	Type I Silver ^a			38	62	120	190	300	370	360	520	980	
25	Hysol 6000 ^b			3.47	3.43	3.38	3.30	3.26	3.17	3.10	3.07	3.00	2.96
				73	61	70	92	130	170	170	150	120	120
25	Hysol 6020 ^b			3.96	3.90	3.82	3.67	3.54	3.42	3.29	3.01	2.99	
				68	113	206	260	272	266	299	274	252	
25	Hysol 630 flexible			6.65	6.15	5.75	5.37	4.74	4.15	3.61	3.20	3.11	
	Potting Compound ^b			605	485	469	593	840	1010	900	380	324	
25	Hysol 6000 PR ^b			3.85	3.80	3.69	3.64	3.57	3.44	3.33	3.18	3.18	
				90	99	107	163	227	248	250	192	180	
25	Hy-tuf laminate Grade			4.67	4.62	4.52	4.45	4.34	4.21	4.15			
	GF181 ^b (field I laminate)			92	99	125	145	212	239	242			
25	(field II laminate)			----	----	----	----	----	----	----	4.14*	4.08	4.05
				----	----	----	----	----	----	----	171*	177	180
25	Epon Resin RN-48 ^c			3.64	3.63	3.61	3.57	3.52	3.44	3.32	3.13*	3.04	2.91
				31	38	68	111	142	191	264	220*	210	184
o. Miscellaneous Plastics													
23	E Resin ^d			2.49	2.49	2.48	2.48	2.47	2.45	2.45	2.43	2.42	
				7	4	< 3	< 5	5	8	8	6	5	
80				2.5	2.5	2.5	2.5	2.5	2.45	2.45	2.4	2.4	
				25	14	8	5	4	6	7	15	17	
25	Same material after			2.56	2.56	2.55	2.54	2.54	2.54	2.53	2.5	2.44	2.43
	3 1/2 yrs. at room temp.			8	11	16	19	21	22	19	16	7	11
	and humidity												
24	Permalin 3256 ^e			4.27	4.22	4.12	4.01	3.86	3.70	3.5	3.1	3.0	
				98	120	170	230	300	330	340	276	290	
99				4.95	4.85	4.75	4.61	4.48	4.28	4.05	3.34		
				200	155	160	200	300	440	570	580		
125				5.12	5.04	4.92	4.77	4.62	4.4	4.1	3.38		
				280	180	170	185	260	410	550	560		
25	Piccopale Resin ^f			2.33	2.33	2.33	2.33	2.33	2.33	2.33	2.30		
				< 3	< 3	< 3	----	< 5	2	8	3.5		

a. Ciba. b. Houghton Labs. c. Shell Chem. d. Cross-linked addition hydrocarbon polymer (Esso Lab.). e. Cross-linked addition polymer (Gen. Elec.). f. Linear addition hydrocarbon copolymer made with aliphatic dienes and olefins (Penn. Industrial Chem.).
^gfreq. = 1×10^9 .

I. Solids, B. Organic 4. Elastomers

Values for tan δ are multiplied by 10^4 ; frequency given in c/s.

a. Natural Rubber		T°C													
Hevea rubber ^a			ϵ'/ϵ_0	$\tan \delta$	1×10^2	1×10^3	1×10^4	1×10^5	1×10^6	1×10^7	1×10^8	3×10^8	3×10^9	1×10^{10}	
	-12			2.4	2.4	2.4	2.4	2.4	2.4	2.4	2.4				
				10	14	24	44	55	38	33					
25				2.4	2.4	2.4	2.4	2.4	2.4	2.4	2.4	---	2.15		
				28	18	14	14	18	32	50	---	30			
80				2.4	2.4	2.4	2.4	2.4	2.4	2.4	2.4	---			
				132	79	48	27	21	21	30	---				
27				2.94	2.94	2.93	2.88	2.74	2.52	2.42	---	2.36			
				48	24	62	220	446	410	180	---	47			
27				4.09	4.01	3.92	3.80	3.64	3.44	3.3	---	3.25			
				130	155	182	230	308	405	265	---	148			
27				---	36	27	14	9.0	7.0	6.8	---	6.3			
				---	25000	12000	4000	2500	1600	850	---	234			
25				---	---	---	---	---	---	---	---	1.31	1.31		
				---	---	---	---	---	---	---	---	75	94		
25				3.46	3.39	3.28	3.18	2.96	2.80	2.72	2.63*	2.60			
				169	230	274	320	370	550	215	170*	180			
b. Gutta-percha															
Gutta-percha ^g															
25				2.61	2.60	2.58	2.55	2.53	2.50	2.47	2.45	2.40	2.38		
				5	4	9	21	42	80	120	110	60	50		
c. Balata															
Balata, precipitated ^h															
25				2.50	2.50	2.50	2.50	2.50	2.47	2.42	2.41	2.40	2.39		
				9	5	4	5	15	33	62	63	37	30		
d. Cyclized Rubbers															
Pliolite ⁱ															
27				2.5	2.5	2.5	2.5	2.5	2.5	2.45	---	2.4			
				52	35	31	31	37	46	46	---	31			
25				2.6	2.6	2.6	2.55	2.55	2.55	---	---	---	2.5		
				92	98	78	60	44	33	---	---	---	---	33	

a. Pale crepe (Rubber Res. Corp.). b. 100 pts. pale crepe, 6 pts. sulfur (Rubber Res. Corp.). c. 100 pts. pale crepe, 1 pt. stearic acid, 10 pts. United Black, 5 pts. Kadox, 0.5 pts. Captax, 3 pts. sulfur (Rubber Res. Corp.). d. 100 pts. pale crepe, 1 pt. stearic acid, 40 pts. United Black, 5 pts. Kadox, 1 pt. Captax, 3 pts. sulfur (Rubber Res. Corp.). e. Cellular Rubber Prod. f. Depolymerized rubber (Hardman). g. Palaquium Oblongifolium (Hermann Weber). h. Minusops Globosa (Hermann Weber). i. Goodyear.

*Freq. = 1×10^9 .

I. Solids B. Organic 4. Elastomers (cont.) Values for $\tan \delta$ are multiplied by 10^4 ; frequency given in c/s.

d. Cyclized Rubbers (cont.)		Values for $\tan \delta$ are multiplied by 10^4 ; frequency given in c/s.									
T ^o C	ϵ'/ϵ_0 tan δ	1×10^2	1×10^3	1×10^4	1×10^5	1×10^6	1×10^7	1×10^8	3×10^8	3×10^9	1×10^{10}
24		14	12	9.5	7.9	6.3	4.8	4.0	----	3.76	
		7800	1900	850	900	2000	1900	1000	----	740	
e. Buna Rubbers											
Air seal ^b											
24	ϵ'/ϵ_0	15.3	8.9	6.2	4.4	3.6	3.3	3.1	3.0	2.8	2.8
	tan δ	5200	3100	2300	1700	990	740	580	410	180	120
GR-S (Buna S) uncured ^c											
-12	ϵ'/ϵ_0	----	2.5	2.5	2.5	2.5	2.45	2.45	----	2.45	
	tan δ	----	13	24	62	80	50	71	----	44	
26	ϵ'/ϵ_0	2.5	2.5	2.5	2.5	2.50	2.45	2.45	----		
	tan δ	6	9	10	18	38	69		----		
80	ϵ'/ϵ_0	----	2.5	2.5	2.5	2.50	2.45	2.45	----		
	tan δ	----	4	4	4	6	22	60	----		
GR-S (Buna S) compound ^d											
26	ϵ'/ϵ_0	2.66	2.66	2.66	2.65	2.56	2.52	2.52	----	2.49	2.44
	tan δ	7	9	25	60	120	160	95	----	56	50
GR-S (Buna S) compound HXG-117-G ^e											
25	ϵ'/ϵ_0	2.98	2.97	2.95	2.93	2.91	2.88	2.82	----	2.78	2.77
	tan δ	10	24	54	100	120	128	80	----	57	48
80	ϵ'/ϵ_0	2.84	2.83	2.82	2.81	2.78	2.76	2.72	2.70	2.69	
	tan δ	86	31	26	33	65	110	120	114	83	
Hycar OR Cell-tite ^f											
25	ϵ'/ϵ_0	1.41	1.40	1.39	1.38	1.38	1.38	1.38	----	1.38	1.37
	tan δ	115	58	50	51	56	54	47	----	39	38
Marbon S, Buna S Hardboard ^g											
25	ϵ'/ϵ_0	1.31	1.31	1.31	1.30	1.30	1.30	1.29	----	1.28	1.27
	tan δ	14	12	22	36	37	28	19	----	17	16
f. Butyl Rubbers											
GR-I (butyl rubber) ^h											
25	ϵ'/ϵ_0	2.39	2.38	2.37	2.36	2.35	2.35	2.35	----	2.35	2.35
	tan δ	34	35	27	13	10	10	10	----	9	8
GR-I compound ⁱ											
25	ϵ'/ϵ_0	2.43	2.42	2.41	2.40	2.40	2.40	2.39	----	2.38	2.38
	tan δ	50	60	58	38	22	15	10	----	9.3	9.9

a. Solution and suspension of thermosetting resins and vulcanizable elastomers (Goodyear). b. Kearney. c. Copolymer of 75% butadiene and 25% styrene (Rubber Res. Corp.). d. 100 pts. GR-S, 1 pt. stearic acid, 5 pts. Kadox, 5 pts. Captax, 3 pts. Sulfur (Rubber Res. Corp.). e. Ifur, Solanac, Altax, Methyl Tuads, zinc oxide, Akroflex, Heliozone, Cumar ME, stearic acid, limestone, Marbon S-1, etc. (Gen. Cable). f. Based on butadiene polymer (Sponge Rubber Prod.). g. U.S. Rubber. h. Copolymer of 98-99% isobutylene, 1-2% isoprene (Rubber Res. Corp.). i. 100 pts. GR-I 44-7 M₂K, 5 pts. zinc oxide (from ZnCO₃), 1 pt. Tuads, 1.5 pts. sulfur (Rubber Res. Corp.).

I. Solids B. Organic 4. Elastomers (cont.) Values for $\tan \delta$ are multiplied by 10^4 ; frequency given in c/s.

1. Thiokol Thiokol, Type FA compound ^a	T°C	Values for $\tan \delta$ are multiplied by 10^4 ; frequency given in c/s.										
		1×10^2	1×10^3	1×10^4	1×10^5	1×10^6	1×10^7	1×10^8	3×10^8	3×10^9	1×10^{10}	2.5×10^{10}
23	ϵ'/ϵ_0	----	2260	515	200	110	70	30	24	16	14	13.6
	$\tan \delta$	----	12900	8000	5100	3900	3200	2800	2800	2200	1500	1000
25	ϵ'/ϵ_0	----	17900	15200	7550	740	106	----	20.5*	17.1	8.4	
	$\tan \delta$	----	36300	56400	88000	40000	27000	----	2600*	2300	2200	
25	ϵ'/ϵ_0	----	17300	5100	600	215	90	----	17*	14.3	8.5	
	$\tan \delta$	----	10000	17000	36000	18000	7600	----	3000*	3600	4000	
J. Silicone Rubbers												
Silastic 120 ^d	25	ϵ'/ϵ_0	5.78	5.76	5.75	5.75	5.75	5.75	5.74	5.73	5.72	
		$\tan \delta$	51	30	16	10	8	12	27	52	510	
Silastic 125 ^d	25	ϵ'/ϵ_0	7.1	7.1	7.0	7.0	6.9	6.8	----	7		
		$\tan \delta$	40	26	18	13	12	14	30	----	430	
Silastic 150 ^e	25	ϵ'/ϵ_0	5.87	5.85	5.79	5.61	5.39	5.09	5.0	5.0	5.0	
		$\tan \delta$	43	48	108	200	270	280	230	250	800	
Silastic 152 ^f	25	ϵ'/ϵ_0	2.96	2.95	2.95	2.95	2.95	2.95	2.93*	2.90	2.85	
		$\tan \delta$	5.8	5.2	4	3.5	5.4	10.4	20	59*	167	
Silastic 160 ^g	25	ϵ'/ϵ_0	9.32	9.27	9.2	9.0	8.8	8.4	8.0	7.9	7.6	
		$\tan \delta$	47	31	60	150	250	270	310	310	1400	
Silastic 167 ^h	25	ϵ'/ϵ_0	8.6	8.6	8.6	8.5	8.5	8.5	8.5	----	8	
		$\tan \delta$	52	32	19	12	11	13	16	----	360	
Silastic 180 ⁱ	25	ϵ'/ϵ_0	4.66	4.60	4.56	4.53	4.53	4.52	4.5	4.5	4.5	
		$\tan \delta$	67	63	54	40	30	27	35	56	170	
Silastic 181 ^j	25	ϵ'/ϵ_0	3.36	3.30	3.26	3.23	3.20	3.19	3.18	3.16	3.11	
		$\tan \delta$	62	67	65	58	37	28	29	36	100	
Silastic 250 ^k	25	ϵ'/ϵ_0	3.19	3.18	3.17	3.16	3.10	3.07	3.05	3.04	3.00	
		$\tan \delta$	55	30	69	106	64	29	28	44	190	

a. 100 pts. Thiokol (organic polysulfide), 10 pts. zinc oxide, 60 pts. semi-reinforcing carbon black, 1 pt. stearic acid, 0.5 pt. diphenylguanidine, 0.35 pt. Altax (Thiokol). b. 100 pts. polysulfide copolymer of bis (2-chloroethyl) formal and ethylene dichloride, 60 pts. carbon blacks, compounding ingredients. (Thiokol). c. 100 pts. polysulfide polymer of bis (2-chloroethyl) formal, 60 pts. carbon blacks, compounding ingredients. (Thiokol). d. 50% siloxane elastomer, 50% TiO_2 (Dow Corning). e. 3% siloxane elastomer, 35% ZnO , 30% CaCO_3 . (Dow Corning). f. Dow Corning. g. 33% siloxane elastomer, 33% ZnO , 33% TiO_2 (Dow Corning). h. 33% siloxane elastomer, 67% TiO_2 (Dow Corning). i. 35% siloxane elastomer, 35% SiO_2 , 30% TiO_2 (Dow Corning). j. 45% siloxane elastomer, 55% SiO_2 (Dow Corning). k. 70% siloxane elastomer, 30% SiO_2 (Dow Corning).

*Freq. = 1×10^9 .

I. Solids, B. Organic 4. Elastomers (cont.) Values for $\tan \delta$ are multiplied by 10^4 ; frequency given in c/s.

J. Silicone Rubbers (cont.)		T°C	1×10^2	1×10^3	1×10^4	1×10^5	1×10^6	1×10^7	1×10^8	3×10^8	3×10^9	1×10^{10}
			ϵ'/ϵ_0	$\tan \delta$	ϵ'/ϵ_0	$\tan \delta$	ϵ'/ϵ_0	$\tan \delta$	ϵ'/ϵ_0	$\tan \delta$	ϵ'/ϵ_0	$\tan \delta$
Silastic X4342 ^a	25		3.22	3.18	3.16	3.16	3.14	3.12	3.11	3.08	3.08	3.00
			51	64	60	48	29	20	23	35	83	110
Silastic 6167 ^b	25		10.1	10.1	10.0	10	10	10	10	10	10	10
			41	26	17	13	9.5	10	27	55	450	1000
Silastic 6181 ^c	25		3.66	3.53	3.42	3.35	3.31	3.30	3.27	3.25	3.23	3.20
			200	250	190	100	57	34	32	36	88	160
Silastic X-6734 ^d	25		3.21	3.12	3.12	3.12	3.10	3.08	3.08	3.08	3.01	3.00
			28	19	31	53	37	23	29	44	144	213
Silastic 7181 ^c	25		3.72	3.55	3.45	3.37	3.33	3.31	3.31	3.28	3.20	3.15
			210	250	190	97	53	29	24	29	75	170
SE-450 ^e	25		3.09	3.08	3.08	3.08	3.07	3.06	3.05	3.03*	2.97	2.88
			16	7.2	5.3	7	11	17	30	74*	158	183
SE-460 ^e	25		3.14	3.12	3.11	3.10	3.10	3.09	3.07	3.05*	3.02	2.94
			56	54	44	25	12	15	23	57*	98	180
SE-550 ^e	25		3.14	3.12	3.10	3.10	3.10	3.08	3.06	3.02*	3.00	2.94
			13	7.8	6.5	7	9.5	16	31	84*	143	195
SE-972 ^e	25		3.40	3.35	3.25	3.22	3.20	3.18	3.16	3.15*	3.13	3.08
			64	67	58	46	30	27	32	65*	97	146
Natural Resins												
Amber ^f	25		2.7	2.7	2.7	2.7	2.65	2.65	-----	2.6	2.6	
			12.5	18	31	43	56	68	-----	82	90	
	80		2.85	2.85	2.85	2.8	2.8	2.75	-----	2.65	2.60	
			24	19	22	40	70	93	-----	110	115	
Stellac, natural XI ^g	28		3.86	3.81	3.75	3.66	3.47	3.26	3.10	-----	2.86	
			65	74	128	225	310	350	300	-----	254	
	70		6.50	5.65	5.10	4.60	4.33	4.00	3.80	-----	3.45	
			1050	860	650	460	400	540	700	-----	732	

a. 50% siloxane elastomer, 50% SiO₂ (Dow Corning). b. 33% siloxane elastomer, 67% TiO₂ (Dow Corning). c. 45% siloxane elastomer, 55% SiO₂ (Dow Corning). d. 70% siloxane elastomer, 30% SiO₂ (Dow Corning). e. General Electric. f. Fossil resin (Amber Mines). g. Contains ca. 3.5% wax (Zinsser).
*Freq. = 1×10^9 .

I. Solids B. Organic (Cont.) Values for $\tan \delta$ are multiplied by 10^4 ; frequency given in c/s.

5. Natural Resins (cont.)		T°C	ϵ'/ϵ_0	$\tan \delta$	1×10^2	1×10^3	1×10^4	1×10^5	1×10^6	1×10^7	1×10^8	3×10^9	1×10^{10}	2.5×10^{10}	
Shellac, natural Zinfo ^a		27	ϵ'/ϵ_0	tan δ	3.84 58	3.82 64	3.75 132	3.66 250	3.50 313	3.30 341	3.1 345	2.86 290			
		28	ϵ'/ϵ_0	tan δ	3.99 137	3.92 102	3.84 131	3.69 205	3.50 304	3.32 347	3.2 340	2.94 270			
Shellac, garnet dewaxed ^c		26	ϵ'/ϵ_0	tan δ	3.60 58	3.56 64	3.48 118	3.40 205	3.30 285	3.20 317	3.05 310	2.75 267			
		23	ϵ'/ϵ_0	tan δ	3.19 105	3.12 85	3.09 86	3.04 91	3.00 100	2.98 110	2.98 118	2.91 125	2.90 135	2.87 120	
6. Asphalts and Cements															
Gilsonite ^e		26	ϵ'/ϵ_0	tan δ	2.68 58	2.66 35	2.63 25	2.61 19	2.58 16	2.57 13	2.56 11	-----	2.55 9.3		
		22	ϵ'/ϵ_0	tan δ	2.65 39	2.65 35	2.65 26	2.64 14	2.64 11	2.64 10	2.64 11	-----	2.5 11	2.5 12	
Cenco Sealstix ^g		23	ϵ'/ϵ_0	tan δ	3.90 452	3.75 335	3.55 275	3.37 240	3.23 240	3.13 272	-----	2.96 210			
		25	ϵ'/ϵ_0	tan δ	2.48 43.9	2.48 35.5	2.48 28.9	2.48 25.9	2.48 25.5	2.48 22.2	2.47 15	-----	2.40 7.8	2.35 6.8	
7. Waxes															
Acravax C ⁱ		24	ϵ'/ϵ_0	tan δ	2.60 157	2.58 68	2.57 45	2.55 30	2.54 20	2.53 15	2.52 12	2.48 15	2.45 19	2.44 21	
		85	ϵ'/ϵ_0	tan δ	----- -----	5.0 7000	3.2 3500	2.63 560	2.50 180	2.46 130	-----	-----	2.45 228		
Apiezon Wax "W" ^j		22	ϵ'/ϵ_0	tan δ	2.75 186	2.69 120	2.66 70	2.64 39	2.63 25	2.63 19	-----	2.62 16			
		70	ϵ'/ϵ_0	tan δ	3.29 450	3.14 420	2.97 340	2.88 210	2.82 110	2.79 61	-----	-----			

e. Contains ca. 3.5% wax (Zinsser). b. Natural, ca. 2% wax (Zinsser). c. Natural, wax-free (Zinsser). d. From zein and rosin (Filtered Rosin Products). e. 99.9% natural bitumen (U.S. Rubber). f. Asphaltic product (U.S. Rubber). g. De Khotinsky Cement (Central Scientific). h. Central Scientific. i. Cetylacetamide (Clyco). j. Shell Oil.

I. Solids B. Organic		(cont.) Values for tan δ are multiplied by 10^4 ; frequency given in c/s.												
7. Waxes (cont.)	T°C	ϵ'/ϵ_0	$\frac{1 \times 10^2}{\epsilon'/\epsilon_0}$	$\frac{1 \times 10^3}{\epsilon'/\epsilon_0}$	$\frac{1 \times 10^4}{\epsilon'/\epsilon_0}$	$\frac{1 \times 10^5}{\epsilon'/\epsilon_0}$	$\frac{1 \times 10^6}{\epsilon'/\epsilon_0}$	$\frac{1 \times 10^7}{\epsilon'/\epsilon_0}$	$\frac{1 \times 10^8}{\epsilon'/\epsilon_0}$	$\frac{3 \times 10^8}{\epsilon'/\epsilon_0}$	$\frac{3 \times 10^9}{\epsilon'/\epsilon_0}$	$\frac{1 \times 10^{10}}{\epsilon'/\epsilon_0}$	$\frac{2.5 \times 10^{10}}{\epsilon'/\epsilon_0}$	
Beeswax, white ^a	23	ϵ'/ϵ_0	2.65	2.63	2.56	2.48	2.43	2.41	2.39	---	2.35	2.35		
		tan δ	140	118	266	190	84	68	60	---	50	48		
	55	ϵ'/ϵ_0	2.52	2.50	2.46	2.43	2.39	2.36	2.34	---	2.31			
		tan δ	82	44	25	25	35	58	125	---	216			
Beeswax, yellow ^b	23	ϵ'/ϵ_0	2.73	2.66	2.59	2.53	2.49	2.45	2.42	---	2.39	2.36		
		tan δ	240	140	240	150	92	84	90	---	75	62		
Cereso Wax AA ^c	24*	ϵ'/ϵ_0	2.35	2.35	2.35	2.34	2.33	2.32	---	---	2.29	2.27		
		tan δ	5	6	7	8	8	7	---	---	4.6	5.0		
	46*	ϵ'/ϵ_0	2.35	2.35	2.35	2.34	2.33	2.32	---	---	2.28	2.27		
		tan δ	< 5	< 3	3	5	8	10	---	---	6.2	6		
Cereso Wax, brown ^c	22	ϵ'/ϵ_0	---	2.28	2.28	2.28	2.28	2.28	2.27	---	2.25			
		tan δ	---	5	10	13	11	7	2	---	2.8			
Ceresin, white ^d	25	ϵ'/ϵ_0	2.3	2.3	2.3	2.3	2.3	2.3	2.3	---	2.25	2.24		
		tan δ	8	6	5	5	4	4	4	---	4.6	6.5		
Ceresin, yellow ^e	20	ϵ'/ϵ_0	---	2.25	2.25	2.25	2.25	2.25	2.25	---	2.25	2.25		
		tan δ	---	4	5	7	7	5	4	---	4.2	4		
Estavax ^f	25	ϵ'/ϵ_0	2.30	2.30	2.30	2.30	2.30	2.30	2.30	2.30	2.29	2.28	2.28	
		tan δ	7	< 2	2	4	5	4	2.5	2.3	2.9	3.7	4.6	
	80	ϵ'/ϵ_0	2.18	2.18	2.18	2.18	2.18	2.18	2.18	2.18	2.17	2.16		
		tan δ	11	7	3	< 2	< 2	< 4	5	6.4	7.9	8.5		
Halowax #1001 ^g cold-molded	26	ϵ'/ϵ_0	5.45	5.45	5.45	5.40	5.40	5.30	4.2	3.46	2.92	2.86	2.84	
		tan δ	18	17	7	8	45	450	2700	1620	583	296	200	
hot-molded	25	ϵ'/ϵ_0	3.78	3.78	3.76	3.74	3.70	3.62	3.37	3.17	2.57			
		tan δ	16	8	6	8.6	32	400	1200	1210	496			

a. Bromund. b. Candy. c. Mainly petroleum aliphatic hydrocarbons (Socony-Vacuum). d. Vegetable and mineral waxes (Kuhne-Libby).
e. Vegetable and mineral waxes (Mitchell-Rand). f. Long-chain, singly unsaturated (Lovell). g. Tri- and tetrachloronaphthalenes (Bakelite).

*Similar data were obtained after incorporation of 0.5% phenyl mercuric stearate.

I. Solids B. Organic (Cont.) Values for $\tan \delta$ are multiplied by 10^4 ; frequency given in c/s.

7. Waxes (cont.)	T ^o C	ϵ'/ϵ_0	$\tan \delta$	1×10^2	1×10^3	1×10^4	1×10^5	1×10^6	1×10^7	1×10^8	3×10^8	3×10^9	1×10^{10}	2.5×10^{10}
Halowax #11-314 ^a	23	ϵ'/ϵ_0	$\tan \delta$	3.11	3.04	3.01	2.99	2.98	2.96	2.93	2.92	2.89	2.87	
	45	ϵ'/ϵ_0	$\tan \delta$	3.11	3.04	3.01	2.99	2.98	2.96	2.93	---	---	2.87	
Kel-F Wax #150 ^b	25	ϵ'/ϵ_0	$\tan \delta$	3.01	2.97	2.91	2.75	2.52	2.35	2.25	2.24	2.23	2.22	
	24	ϵ'/ϵ_0	$\tan \delta$	83	93	252	510	540	425	270	218	113	90	
Opalwax ^c	47	ϵ'/ϵ_0	$\tan \delta$	13.2	10.3	7.0	4.3	3.2	2.9	2.7	---	---	2.52	2.5
	20	ϵ'/ϵ_0	$\tan \delta$	14.2	11.4	8.2	5.4	3.7	3.0	2.7	---	---	160	160
Ozokerite ^d	25	ϵ'/ϵ_0	$\tan \delta$	2.26	2.26	2.26	2.26	2.26	2.26	2.26	---	---	2.47	
	20	ϵ'/ϵ_0	$\tan \delta$	6	6	8	10	9	7	6	---	---	236	
Paraffin Wax 132 ^o ASTM ^e	25	ϵ'/ϵ_0	$\tan \delta$	2.25	2.25	2.25	2.25	2.25	2.25	2.25	---	2.25	2.24	2.2
	81	ϵ'/ϵ_0	$\tan \delta$	< 2	< 2	< 2	< 2	< 2	< 2	< 2	---	2.0	2.1	< 3
Paraffin Wax 135 ^o AMP ^f	24	ϵ'/ϵ_0	$\tan \delta$	2.02	2.02	2.02	2.02	2.02	2.02	---	---	2.00	---	
	20	ϵ'/ϵ_0	$\tan \delta$	5	1.2	.5	< 2	< 2	< 3	---	---	5.2	---	
Parowax ^g	20	ϵ'/ϵ_0	$\tan \delta$	2.25	2.25	2.25	2.25	2.25	2.25	2.25	---	2.25	2.25	
	25	ϵ'/ϵ_0	$\tan \delta$	12.5	5.5	< 3	< 2	< 2	< 4	---	---	1	2	
Polinel ^h	25	ϵ'/ϵ_0	$\tan \delta$	2.89	2.87	2.87	2.85	2.84	2.80	2.72	2.62*	2.59	2.58	
	25	ϵ'/ϵ_0	$\tan \delta$	67	44	36	43	82	166	240	180*	195	199	
Sealing wax, Red Express ⁱ	25	ϵ'/ϵ_0	$\tan \delta$	3.68	3.32	3.40	3.32	3.29	3.27	3.2	---	3.09	---	
Thermoplastic Composition 1766EX ^j	25	ϵ'/ϵ_0	$\tan \delta$	249	150	99	79	80	100	120	---	122	---	
	25	ϵ'/ϵ_0	$\tan \delta$	3.77	3.72	3.68	3.63	3.60	3.58	3.56	---	---	3.58	
Thermoplastic Composition 3738 ^j	25	ϵ'/ϵ_0	$\tan \delta$	122	106	87	60	44	32	28	---	---	20	
	25	ϵ'/ϵ_0	$\tan \delta$	2.65	2.60	2.57	2.56	2.55	2.54	2.54	2.52*	2.52	2.49	
	3738 ^j	ϵ'/ϵ_0	$\tan \delta$	112	91	67	41	25	16	15	13*	13	13	

a. 80% 1,4-, 10% 1,5-, 10% 1,2-dichloronaphthalenes (Bakelite). b. Polychlorotrifluoroethylene (Kellogg). c. Mainly 12-hydroxystearin (DuPont). d. Natural paraffin (Allison). e. Mainly C₂₂ to C₂₉ aliphatic, saturated hydrocarbons (Stand. Oil N.J.). f. Gulf. g. Paraffin wax (Socony Vacuum). h. Lovell. i. Dennison. j. Mitchell-Rand.

*Freq. = 1×10^9 .

I. Solids		B. Organic (cont.)		Values for $\tan \delta$ are multiplied by 10^4 ; frequency given in c/s.													
7. Waxes (cont.)		$T^\circ C$		ϵ'/ϵ_0	$\tan \delta$	1×10^2	1×10^3	1×10^4	1×10^5	1×10^6	1×10^7	1×10^8	3×10^8	3×10^9	1×10^{10}	2.5×10^{10}	
Thermoplastic composition 25			25	ϵ'/ϵ_0	$\tan \delta$	2.84	2.79	2.76	2.64	2.59	2.54	2.51	2.48	2.45	2.45		
3767A ^a					140	160	170	120	98	78	69	32	27				
Vistavar ^b			25	ϵ'/ϵ_0	$\tan \delta$	2.34	2.34	2.34	2.34	2.32	2.30	2.30	2.27	2.26			
					2	3	9.2	12.1	13.3	13.6	13.3	9.0	5				
Wax 3760 ^c			25	ϵ'/ϵ_0	$\tan \delta$	2.36	2.36	2.36	2.36	2.36	2.36	2.36	2.31*	2.31	2.31	2.31	
					21.7	8.8	7.1	5.6	4.3	2.7	2.6	3.6*	4.9	14.2			
Wax S-1167 ^d			25	ϵ'/ϵ_0	$\tan \delta$	19.9	10.2	5.9	4.1	3.3	3.1	2.9	2.6	2.6	2.6	2.6	
					7200	3900	2300	1700	1000	600	470	300	190	92			
Wax S-1184 ^d			25	ϵ'/ϵ_0	$\tan \delta$	2.43	2.43	2.43	2.40	2.40	2.40	2.37	2.34*	2.30	2.21	2.21	
					29.4	21.5	21.5	16.4	11.3	9.3	13.8	20*	24	54			
Wax Compound F-590 ^e			26	ϵ'/ϵ_0	$\tan \delta$	2.37	2.34	2.32	2.32	2.32	2.32	2.32	2.32	2.32	2.32	2.32	2.32
					80	99	78	44	20	8	5	6.2	6.2	6.2	6.2	6.2	
Wax Compound #1340 ^e			26	ϵ'/ϵ_0	$\tan \delta$	2.30	2.30	2.30	2.30	2.30	2.30	2.30	2.30	2.25	2.25	2.25	2.25
					1	2	2	< 5	4	4	4	4	4.2	4.2	4.2	4.2	
8. Woods																	
Balsa			26	ϵ'/ϵ_0	$\tan \delta$	1.4	1.4	1.4	1.4	1.37	1.35	1.30	1.22	1.22	1.20	1.20	1.20
					50	40	43	77	120	135	135	135	100	83	83	83	83
Yellow Birch			25	ϵ'/ϵ_0	$\tan \delta$	2.91	2.88	2.82	2.78	2.70	2.60	2.47	2.40	2.13	1.95	1.95	1.87
(field 1 to grain)					72	90	140	220	290	360	400	390	330	280	260	260	260
Fir, Douglas			25	ϵ'/ϵ_0	$\tan \delta$	2.04	2.00	1.97	1.95	1.93	1.90	1.88	1.86	1.82	1.80	1.80	1.78
(field 1 to grain)					48	80	130	190	260	310	330	320	270	290	320	320	320
Fir, Douglas, plywood			25	ϵ'/ϵ_0	$\tan \delta$	2.1	2.1	2.05	1.95	1.90	1.80	1.78	1.7	1.7	1.7	1.5	1.5
(field 1 to grain)					115	105	130	170	230	320	330	360	330	270	290	220	220
Fir, Douglas, staypak			25	ϵ'/ϵ_0	$\tan \delta$	7.3	7.05	6.9	6.65	6.3	5.6	4.6	4.0	3.5	3.3	3.2	3.2
(field 1 to grain)					82	130	200	320	500	750	800	850	700	550	460	460	460
Mahogany			25	ϵ'/ϵ_0	$\tan \delta$	2.42	2.40	2.36	2.30	2.25	2.17	2.07	2.01	1.88	1.7	1.6	1.6
(field 1 to grain)					86	120	150	195	250	310	320	300	250	210	200	200	200
Poplar, yellow			25	ϵ'/ϵ_0	$\tan \delta$	1.84	1.79	1.78	1.76	1.75	1.70	1.60	1.50	1.42	1.4	1.4	1.4
(field 1 to grain)					42	54	83	133	190	220	200	150	200	170	170	170	170

a. Mitchell-Rand. b. Polybutene (Cantol Wax). c. Mitchell-Rand. d. Glyco. e. Zophar Mills.
*Freq. = 1×10^9 .

I. Solids B. Organic (cont.) Values for $\tan \delta$ are multiplied by 10^4 ; frequency given in c/s.

		T°C	1×10^2	1×10^3	1×10^4	1×10^5	1×10^6	1×10^7	1×10^8	3×10^8	3×10^9	1×10^{10}	2.5×10^{10}
9. Miscellaneous	Paper, Royalgrey ^a	25	ϵ'/ϵ_0	3.29	3.22	3.10	2.99	2.86	2.77	2.75	2.70	2.62	
			$\tan \delta$	77	117	200	380	570	660	660	560	403	
		82	ϵ'/ϵ_0	3.52	3.49	3.40	3.31	3.14	3.08	3.00	2.94	2.84	
			$\tan \delta$	74	61	85	230	440	630	720	800	827	
	Leather, sole, dried	25	ϵ'/ϵ_0	3.9	3.6	3.4	3.2	3.1	3.1				
			$\tan \delta$	350	300	280	280	300	380				
	Leather, sole, ca. 1 1/2% moisture	25	ϵ'/ϵ_0	14.0	9.3	6.9	5.6	4.9	4.5				
			$\tan \delta$	7000	3700	2200	1400	1000	1000				
	Soap, Ivory ^b	25	ϵ'/ϵ_0	----	----	----	----	----	----	----	2.96		
			$\tan \delta$	----	----	----	----	----	----	----	1765		
	Steak (bottom round)	25	ϵ'/ϵ_0	----	24400	----	197	50	----	50	40	30	15
			$\tan \delta$	----	405000	----	610000	260000	----	7800	3000	3700	4000
	Suet	25	ϵ'/ϵ_0	750	210	----	14	4.5	2.6	2.5	2.5	2.5	2.4
			$\tan \delta$	30000	25000	----	17000	9300	1500	1200	700	500	500

a. Rogers. b. Procter and Gamble.

II. LIQUIDS

Values for $\tan \delta$ are multiplied by 10^4 ; frequency given in c/s.

A. Inorganic		T°C	Water, conductivity ^a																														
			1.5	5		15		25		35		45		55		65		75		85		95											
		ε'/ε ₀	tan δ	ε'/ε ₀	tan δ	ε'/ε ₀	tan δ	ε'/ε ₀	tan δ	ε'/ε ₀	tan δ	ε'/ε ₀	tan δ	ε'/ε ₀	tan δ	ε'/ε ₀	tan δ	ε'/ε ₀	tan δ	ε'/ε ₀	tan δ	ε'/ε ₀	tan δ										
		1.5	87.0	1900	87.0	87	87	86.5	80.5	38	15	87.0	190	85.5	220	81.7	310	78.2	400	74.8	485	71.5	590	68.2	720	64.8	865	61.5	1030	58	12400	55	1430
		5	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---
		15	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---
		25	78.2	4000	78.2	78.2	78	77.5	76.7	55	34	78.2	400	74.0	160	74.0	125	71.0	105	68	92	64.5	84	61	60.5	59	3200	57	2600	52	70		
		35	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---
		45	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---
		55	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---
		65	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---
		75	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---
		85	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---
		95	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---

a. Research Laboratory of Physical Chemistry, M.I.T. b. NaCl, Mallinckrodt's Analytical Reagent.

*. ϵ'/ϵ_0 of conductivity water assumed for purpose of calculating $\tan \delta$ from conductivity measurements.

** Data of Collie, Hasted and Ritson, Proc. Phys. Soc. 60, 145 (1948).

II. Liquids B. Organic

Values for $\tan \delta$ are multiplied by 10^4 ; frequency given in c/s.

1. Aliphatic	T°C	ϵ'/ϵ_0	1×10^2	1×10^3	1×10^4	1×10^5	1×10^6	1×10^7	1×10^8	3×10^8	3×10^9	1×10^{10}
Heptane ^a	25	ϵ'/ϵ_0	1.971	1.971	1.971	----	----	----	----	1.97	1.97	1.97
		$\tan \delta$	< 3	< 0.4	< 0.4	----	----	----	< 2.5	< 2.5	1	16
Methyl alcohol ^b	25	ϵ'/ϵ_0	----	----	----	----	31	31.0	31.0	30.9	23.9	8.9
		$\tan \delta$	----	----	----	----	2000	260	380	800	6400	8100
Ethyl alcohol ^c	25	ϵ'/ϵ_0	----	----	----	----	24.5	24.1	23.7	22.3	6.5	1.7
		$\tan \delta$	----	----	----	----	900	330	620	2700	2500	680
n-Propyl alcohol ^d	25	ϵ'/ϵ_0	----	----	----	----	20.1	20.1	19.0	16.0	3.7	2.3
		$\tan \delta$	----	----	----	----	180	170	2000	4200	6700	900
n-Butyl alcohol ^d	25	ϵ'/ϵ_0	----	----	----	17.4	17.4	17.4	14.8	11.5	3.5	
		$\tan \delta$	----	12000	12000	1000	95	240	2700	5500	4700	
Ethylene Glycol ^e	25	ϵ'/ϵ_0	----	----	42	41	41	41	41	39	12	7
		$\tan \delta$	----	----	30000	3000	300	80	450	1600	10000	7800
Butyraldehyde ^e	25	ϵ'/ϵ_0	----	6.7	6.7	----	6.7	----	----	----	----	
		$\tan \delta$	----	51000	5200	----	50	----	----	----	----	
Dibutyl sebacate ^f	26	ϵ'/ϵ_0	4.92	4.73	4.63	4.60	4.58	4.56	----	4.55	3.80	
		$\tan \delta$	790	110	14	3	3	16	----	383	2120	
Diocetyl sebacate ^f	26	ϵ'/ϵ_0	4.05	4.05	4.03	4.02	4.01	4.00	----	3.77	2.15	
		$\tan \delta$	85	12	5	4	7	55	----	1040	1290	
Carbon tetrachloride ^g	25	ϵ'/ϵ_0	2.17	2.17	2.17	2.17	2.17	2.17	2.17	2.17	2.17	2.17
		$\tan \delta$	60	8	0.4	< 0.4	< 0.4	< 2	< 2	< 1	4	16
Tetrachloroethylene ^h	25	ϵ'/ϵ_0	2.28	2.28	2.28	2.28	2.28	2.28	----	----	2.28	
		$\tan \delta$	15	2	0.7	1	2	2	----	----	10	
Hexachlorobutadiene ⁱ	25	ϵ'/ϵ_0	2.55	2.55	2.55	2.55	2.55	2.55	2.55	2.55	2.51	2.47
		$\tan \delta$	3	1.5	1	< 1	< 1	2	16	55	240	130

a. Practical (Solvents Supply Laboratory, M.I.T.). b. Absolute, analytical grade (Mallinckrodt). c. Absolute (U.S. Industrial Chemicals). d. Eastman Kodak. Dried and refractionated, Lab. Ins. e. Eastman Kodak. f. Resinous Products. g. Purified, Lab. Ins. Res. h. Eastman Kodak, fractionated Lab. Ins. Res. i. Hooker, fractionated Lab. Ins. Res.

Values for tan δ are multiplied by 10^4 ; frequency given in c/s.

II. Liquids B. Organic (cont.)

1. Aliphatic (Cont.)	T°C	1×10^2	1×10^3	1×10^4	1×10^5	1×10^6	1×10^7	1×10^8	3×10^8	1×10^9	3×10^9	1×10^{10}
Dichloropentanes #40 ^a	25	ϵ'/ϵ_0	334	17.1	8.65	----	7.76	----	7.57	----	6.81	----
		tan δ	5200000	1060000	135000	----	2700	----	840	----	1980	----
Dichloropentanes #14 ^a	25	ϵ'/ϵ_0	----	8.24	8.06	8.05	8.05	----	----	----	----	----
		tan δ	----	7500	720	85	16	----	----	----	----	----
Kel-F Oil, Grade #1 ^b	25	ϵ'/ϵ_0	2.61	2.61	2.60	2.61	2.61	2.58	2.53	----	2.34	2.15
		tan δ	22	.3	1.3	2.0	17	140	380	----	870	860
Kel-F Oil, Grade #3 ^b	25	ϵ'/ϵ_0	2.73	2.73	2.73	2.73	2.73	----	2.48	----	2.22	2.12
		tan δ	7.9	.8	1.3	7.3	65	----	930	----	696	420
Kel-F Oil, Grade #10 ^b	25	ϵ'/ϵ_0	2.83	2.83	2.83	2.83	2.78	----	2.40	----	2.26	2.13
		tan δ	2.1	.45	1.1	6.1	393	----	820	----	300	274
Kel-F Grease #40 ^b	25	ϵ'/ϵ_0	2.88	2.88	2.86	2.78	2.57	----	2.25	----	2.20	2.19
		tan δ	5.4	3.8	18	111	570	----	350	----	140	106
Perfluorodihexyl ether (experimental) ^c	25	ϵ'/ϵ_0	1.871	1.871	----	1.87	1.87	----	1.86	----	1.86	1.85
		tan δ	0.8	0.3	< .4	.3	3.5	----	55	----	122	920
Heptacosafuorotributyl amine (exp.) ^c	25	ϵ'/ϵ_0	1.853	1.853	1.853	1.85	1.85	1.85	1.85	----	1.85	1.85
		tan δ	.15	< .1	< .1	< .1	1.2	11	25	----	28	20

2. Aromatic

HB-40 oil ^d	25	ϵ'/ϵ_0	2.59	2.59	2.59	2.59	2.57	2.54	2.48	----	2.40	2.34
		tan δ	1.3	< .4	< .3	13	76	160	93	----	30	17
Pyranol 1467 ^e	25	ϵ'/ϵ_0	4.42	4.40	4.40	4.40	4.40	4.08	3.19	----	2.84	2.62
		tan δ	36	3	3.6	25	260	1300	1500	----	1200	740
Aroclor 1221 ^f	25	ϵ'/ϵ_0	----	----	----	4.55	4.53	4.35	3.85	3.10	2.75	2.65
		tan δ	----	----	----	9	80	800	2000	1900	1030	590
Aroclor 1232 ^g	25	ϵ'/ϵ_0	----	----	----	5.88	5.85	4.60	3.65	3.00	2.82	2.75
		tan δ	----	----	----	22	220	2600	3240	2000	95	51
Aroclor 1242 ^h	25	ϵ'/ϵ_0	----	----	----	5.89	5.85	3.50	2.93	2.80	2.72	2.69
		tan δ	----	----	----	70	700	3000	1850	780	400	223
Aroclor 1248 ⁱ	25	ϵ'/ϵ_0	----	----	5.58	5.57	5.10	2.80	2.76	2.78	2.71	2.68
		tan δ	----	----	26	260	1900	1000	410	300	151	118
Aroclor 1254 ^j	25	ϵ'/ϵ_0	----	5.05	5.04	3.70	2.90	2.75	2.72	2.71	2.70	2.69
		tan δ	----	42	415	2380	1130	170	78	52	44	40

a. Sharples. b. Polychlorotrifluoroethylene (Kellogg). c. Minn. Mining. d. Monsanto. e. Chlorinated benzenes and diphenyls (Gen. Elec.). f. Monochlorobiphenyl (Monsanto). g. Dichlorobiphenyl (Monsanto). h. Trichlorobiphenyl (Monsanto). i. Tetrachlorobiphenyl (Monsanto). j. Pentachlorobiphenyl (Monsanto).

II. Liquids B. Organic (cont.)

2. Aromatic

Values for $\tan \delta$ are multiplied by 10^4 ; frequency given in c/s.

(cont.)	$T^\circ C$	ϵ'/ϵ_0	$\tan \delta$	1×10^2	1×10^3	1×10^4	1×10^5	1×10^6	1×10^7	1×10^8	3×10^8	3×10^9	1×10^{10}
Pyranol 1476 ^a	26	ϵ'/ϵ_0	$\tan \delta$	5.04	5.04	5.04	4.91	3.85	2.81	---	2.74	2.70	2.70
		$\tan \delta$		6	6	54	480	2500	1100	---	130	42	38
Aroclor 1260 ^b	25	ϵ'/ϵ_0	$\tan \delta$	4.33	4.26	3.46	2.89	2.83	2.79	---	2.73	---	2.72
		$\tan \delta$		86	593	1500	645	185	37	---	4.6	---	9.4
Aroclor 1262 ^c	25	ϵ'/ϵ_0	$\tan \delta$	4.03	3.44	2.86	2.76	2.75	2.75	---	---	2.75	2.75
		$\tan \delta$		392	1400	683	186	46	15.7	---	---	6.0	4.9
Aroclor 5442 ^d	25	ϵ'/ϵ_0	$\tan \delta$	---	---	---	---	---	---	---	---	2.78	2.78
		$\tan \delta$		---	---	---	---	---	---	---	---	7.2	7.2
Halowax oil 1000 ^e	25	ϵ'/ϵ_0	$\tan \delta$	4.77	4.76	4.76	4.75	4.74	---	---	4.67	3.52	2.99
		$\tan \delta$		490	50	5	< 1	< 2	---	---	500	2500	1900
	80	ϵ'/ϵ_0	$\tan \delta$	4.30	4.30	4.30	4.29	4.26	---	---	4.16	3.96	3.30
		$\tan \delta$		7800	930	80	15	11	---	---	170	1400	2800
Nitrobenzene ^f	25	ϵ'/ϵ_0	$\tan \delta$	---	---	36	36	35.6	34.4	---	---	31.1	---
		$\tan \delta$		---	---	3900	350	80	90	---	---	1660	---
Styrene N-100 ^g	22	ϵ'/ϵ_0	$\tan \delta$	2.40	2.40	2.40	2.40	2.40	2.40	---	---	2.40	2.36
		$\tan \delta$		38	5	< 1	< 3	< 3	< 3	---	---	20	58
Styrene N-100, purified ^h	25	ϵ'/ϵ_0	$\tan \delta$	2.40	2.40	2.40	2.40	---	---	---	---	2.38	2.38
		$\tan \delta$		15	1.8	< 0.5	< 3	---	---	---	---	13	37
Styrene N-100, ^g sat. with water	27	ϵ'/ϵ_0	$\tan \delta$	2.40	2.40	2.40	---	---	---	---	---	2.40	---
		$\tan \delta$		47	4.8	1.8	---	---	---	---	---	14	---
Styrene dimer ^g	25	ϵ'/ϵ_0	$\tan \delta$	---	---	---	2.7	2.7	2.7	2.7	---	2.5	---
		$\tan \delta$		---	---	---	9	3	2	18	---	110	---
2,5-Dichlorostyrene ⁱ	24	ϵ'/ϵ_0	$\tan \delta$	2.58	2.58	2.58	2.58	2.58	2.58	---	2.58	2.52	---
		$\tan \delta$		85	9	1	< 5	< 3	< 3	---	37	114	---
Pyranol 1478 ^j	26	ϵ'/ϵ_0	$\tan \delta$	4.55	4.53	4.53	4.53	4.53	4.53	---	4.50	3.80	---
		$\tan \delta$		150	14	2	< 5	2	12	---	381	2310	---
β -chloroethyl-2,5- dichlorobenzene ^k	24	ϵ'/ϵ_0	$\tan \delta$	---	6.05	5.45	5.22	5.20	5.20	5.20	5.18	3.31	---
		$\tan \delta$		---	---	5000	25	5	30	430	1100	3240	---
Ethylpolychlorobenzene ^m (discontinued)	25	ϵ'/ϵ_0	$\tan \delta$	4.12	4.12	4.12	4.12	4.12	4.12	4.10	3.84	2.70	2.55
		$\tan \delta$		13.6	1.3	1	< 2	6	55	550	1400	1260	660
	100	ϵ'/ϵ_0	$\tan \delta$	3.62	3.62	3.62	3.62	3.62	3.62	---	3.46	3.12	2.59
		$\tan \delta$		380	40	3.7	< 1	1	5	---	220	1720	3800

a. Isomeric pentachlorodiphenyls (Gen. Elec.). b. Hexachlorodiphenyl (Monsanto). c. Heptachlorodiphenyl (Monsanto). d. Pentachloroterphenyls (Monsanto). e. 50% mono-, 40% di- and trichloronaphthalenes (Bakelite). f. Purified Lab. Ins. Res. g. Dow Chemical Co. h. Fractionated (Lab. Ins. Res.). i. Monsanto (fractionated Lab. Ins. Res.). j. Isomeric trichlorobenzenes (Gen. Elec.). k. Monsanto. m. DuPont.

II. Liquids, B. Organic (cont.) Values for $\tan \delta$ are multiplied by 10^4 ; frequency given in c/s.

3. Petroleum Oils	T ^o C	ϵ'/ϵ_0	$\tan \delta$	$\frac{1 \times 10^2}{\epsilon'/\epsilon_0}$	$\frac{1 \times 10^3}{\tan \delta}$	$\frac{1 \times 10^4}{\epsilon'/\epsilon_0}$	$\frac{1 \times 10^5}{\tan \delta}$	$\frac{1 \times 10^6}{\epsilon'/\epsilon_0}$	$\frac{1 \times 10^7}{\tan \delta}$	$\frac{1 \times 10^8}{\epsilon'/\epsilon_0}$	$\frac{3 \times 10^8}{\tan \delta}$	$\frac{3 \times 10^9}{\epsilon'/\epsilon_0}$	$\frac{1 \times 10^{10}}{\tan \delta}$
Aviation gasoline	25	ϵ'/ϵ_0	$\tan \delta$	---	---	---	---	---	---	---	---	---	---
100 octane													
Aviation gasoline	25	ϵ'/ϵ_0	$\tan \delta$	---	---	---	---	---	---	---	---	---	---
91 octane													
Jet fuel JP-1	25	ϵ'/ϵ_0	$\tan \delta$	---	---	---	---	---	---	---	---	---	---
Jet fuel JP-3	25	ϵ'/ϵ_0	$\tan \delta$	---	---	---	---	---	---	---	---	---	---
Kerosene	25	ϵ'/ϵ_0	$\tan \delta$	---	---	---	---	---	---	---	---	---	---
Vaseline	25	ϵ'/ϵ_0	$\tan \delta$	---	---	---	---	---	---	---	---	---	---
Cable Oil 5314 ^a	80	ϵ'/ϵ_0	$\tan \delta$	---	---	---	---	---	---	---	---	---	---
Cable Oil FL101270 ^b	26	ϵ'/ϵ_0	$\tan \delta$	---	---	---	---	---	---	---	---	---	---
Transil Oil 100 ^a	26	ϵ'/ϵ_0	$\tan \delta$	---	---	---	---	---	---	---	---	---	---
Bayol-D ^c	24	ϵ'/ϵ_0	$\tan \delta$	---	---	---	---	---	---	---	---	---	---
Bayol-F ^d	24	ϵ'/ϵ_0	$\tan \delta$	---	---	---	---	---	---	---	---	---	---
Marcol ^e	24	ϵ'/ϵ_0	$\tan \delta$	---	---	---	---	---	---	---	---	---	---

a. Aliphatic and aromatic hydrocarbons (Gen. Elec.). b. California Res. Corp. c. 77.6% paraffins, 22.4% naphthenes (Stanco).
d. 74.5% paraffins, 25.5% naphthenes (Stanco). e. 72.4% paraffins, 27.6% naphthenes (Stanco).

II. Liquids, B. Organic (cont.) Values for $\tan \delta$ are multiplied by 10^4 ; frequency given in c/s.

3. Petroleum Oils (cont.)		T°C	1×10^2	1×10^3	1×10^4	1×10^5	1×10^6	1×10^7	1×10^8	3×10^8	1×10^{10}	2.5×10^{10}
Bayol ^a		24	ϵ'/ϵ_0	2.14	2.14	---	---	---	---	2.14	2.14	---
			$\tan \delta$	2	< 1	---	---	---	---	9.3	18	---
Bayol-16 ^b		24	ϵ'/ϵ_0	2.15	2.15	2.15	2.15	2.15	---	2.15	2.15	---
			$\tan \delta$	7.7	1	< 1	< 2	< 3	---	9.9	13.5	---
Fractol A ^c		26	ϵ'/ϵ_0	2.17	2.17	2.17	---	2.17	---	2.17	2.16	2.12
			$\tan \delta$	< 1	< 1	< 2	---	< 3	---	7.2	11.3	19
Primol-D ^d		24	ϵ'/ϵ_0	2.17	2.17	2.17	2.17	2.17	---	2.17	2.16	---
			$\tan \delta$	< 1	< 1	< 1	< 2	< 3	---	7.7	10.6	---
Diala Oil 15 ^e		25	ϵ'/ϵ_0	2.16	2.16	2.16	2.16	2.16	2.16	2.16	2.16	2.12
			$\tan \delta$	< 0.8	< 0.8	< 0.4	< 5	< 3	10	16.3	18.6	20
4. Silicones												
DC500		-15	ϵ'/ϵ_0	2.20	2.20	2.20	2.20	2.20	---	2.20	---	---
			$\tan \delta$	< 5	< 3	< 3	< 3	< 2	---	18.6	---	---
0.65 cs. at 25°C ^f		22	ϵ'/ϵ_0	2.20	2.20	2.20	2.20	2.20	---	2.20	2.19	2.13
			$\tan \delta$	1	< 0.4	< 0.4	< 3	< 2	---	1.4	30	60
DC500		23	ϵ'/ϵ_0	2.66	2.66	2.66	2.66	2.66	---	---	2.65	2.48
			$\tan \delta$	12	1.5	< 0.4	< 3	3	---	---	68	410
10 cs. at 25°C ^f		22	ϵ'/ϵ_0	2.76	2.76	2.76	---	---	---	2.75	2.72	2.61
			$\tan \delta$	0.4	< 0.4	< 0.4	---	---	---	94	240	390
DC200		23	ϵ'/ϵ_0	2.76	2.76	2.76	---	---	---	---	---	---
			$\tan \delta$	0.8	0.4	< 0.4	---	---	---	2.76	2.70	2.55
100 cs. at 25°C ^f		22	ϵ'/ϵ_0	2.78	2.78	2.78	2.78	2.78	---	---	2.74	2.74
			$\tan \delta$	0.8	0.8	0.6	< 3	< 2	---	96	320	550
1000 cs. at 25°C ^f		-17	ϵ'/ϵ_0	2.90	2.90	2.90	2.90	2.90	---	2.87	---	---
			$\tan \delta$	< 5	< 3	< 3	< 3	2	---	130	---	---
7600 cs. at 130°C ^f		23	ϵ'/ϵ_0	2.75	2.75	2.75	2.75	2.75	---	2.74	2.69	---
			$\tan \delta$	0.5	0.2	< 0.4	< 5	2	---	11	103	225
		83	ϵ'/ϵ_0	2.56	2.56	2.56	2.56	2.56	---	---	2.55	---
			$\tan \delta$	< 5	< 3	< 3	< 3	2	---	---	60	---

a. 72.0% paraffins, 28.0% naphthenes (Stanco). b. 68.9% paraffins, 31.1% naphthenes (Stanco). c. 57.4% paraffins, 42.6% naphthenes (Stanco). d. 49.4% paraffins, 50.6% naphthenes (Stanco). e. Petroleum hydrocarbons, mainly naphthenes (Shell). f. Methyl or ethyl siloxane polymer (Dow Corning).

II. Liquids, B. Organic (cont.)		Values for $\tan \delta$ are multiplied by 10^4 ; frequency given in c/s.										
4. Silicones (cont.)		T°C	1×10^2	1×10^3	1×10^4	1×10^5	1×10^6	1×10^7	1×10^8	3×10^8	3×10^9	1×10^{10}
DC550 ^a		25	ϵ'/ϵ_0	2.90	2.90	2.90	2.90	2.88	---	2.88	2.77	2.60
			$\tan \delta$	170	18	3.7	3.8	12	---	130	210	220
DC710 ^a		25	ϵ'/ϵ_0	2.98	2.98	2.98	2.98	2.97	---	2.93	2.79	2.60
			$\tan \delta$	13	.7	3	10	50	---	200	140	170
Ignition Sealing Compound #4 ^b		25	ϵ'/ϵ_0	2.75	2.75	2.75	2.75	2.75	2.74	2.72	2.65	2.49
			$\tan \delta$	15	6	4	4	6	15	28	92	270
		80	ϵ'/ϵ_0	2.6	2.6	2.6	2.6	---	---	---	2.54	---
			$\tan \delta$	64	18	6	< 4	---	---	---	47	---
SF96-40 ^c		25	ϵ'/ϵ_0	2.71	2.71	2.71	2.71	2.71	---	2.71	2.70	2.67
			$\tan \delta$	< .3	< .03	< .03	< 1	< 1	---	11	95	186
SF96-100 ^c		25	ϵ'/ϵ_0	2.73	2.73	2.73	2.73	2.73	---	2.73	2.71	2.69
			$\tan \delta$	< .6	< .06	< .03	< 1	< 1	---	11	107	200
SF96-1000 ^c		25	ϵ'/ϵ_0	2.73	2.73	2.73	2.73	2.73	---	2.73	2.71	2.695
			$\tan \delta$	< .3	< .03	< .03	< 1	.8	---	13	106	203

a. Methyl and methyl phenyl polysiloxane (Dow Corning). b. Organosiloxane polymer (Dow Corning). c. Gen. Elec.

Supplementary High-Temperature Data on Plastics

	T°C		Frequency given in c/s.						
			10 ²	10 ³	10 ⁴	4x10 ⁴	10 ⁵	10 ⁶	3x10 ⁹
Formica FF-41 (after 5 yrs. storage, various samples)	25	ϵ'/ϵ_0	6.27	6.19	6.12	6.08	5.97	---	3.87
		tan δ	.018	.0085	.0081	.0090	.012	---	.0143
	100	ϵ'/ϵ_0	---	11.2	6.73	6.23	6.07	---	4.00
		tan δ	---	.50	.18	.055	.040	---	.0144
Formica IE (after 5 yrs. storage)	25	ϵ'/ϵ_0	5.92	5.32	5.01	4.87	4.86	4.85	---
		tan δ	.112	.057	.038	.036	.040	.042	---
	100	ϵ'/ϵ_0	---	16.0	8.16	6.69	6.22	5.84	---
		tan δ	---	.42	.29	.173	.151	.080	---
Formica MF-66	200	ϵ'/ϵ_0	---	12.8	7.17	6.4	---	---	---
		tan δ	---	.847	.245	.134	---	---	---
Formica XI	100	ϵ'/ϵ_0	9.77	6.66	5.87	5.66	5.61	5.44	---
		tan δ	.42	.195	.073	.046	.035	.029	---
Micarta 259	100	ϵ'/ϵ_0	9.39	6.75	6.14	6.03	---	---	5.2
		tan δ	.44	.16	.043	.022	---	---	.025
Micarta 299	200	ϵ'/ϵ_0	12.8	6.7	5.0	4.8	4.75	4.6	4.4
		tan δ	.59	.36	.158	.081	.046	.015	.016
Micarta 496 (after 5 yrs. storage)	25	ϵ'/ϵ_0	7.31	6.35	5.89	5.73	---	---	---
		tan δ	.16	.074	.045	.041	---	---	---
	100	ϵ'/ϵ_0	---	15.5	8.53	7.42	7.26	6.31	---
		tan δ	---	.68	.305	.178	.116	.064	---



		Frequency given in c/s.					
$T^{\circ}C$		$\frac{10^2}{\epsilon'/\epsilon_0}$	$\frac{10^3}{\tan \delta}$	$\frac{10^4}{\epsilon'/\epsilon_0}$	$\frac{10^5}{\tan \delta}$	$\frac{10^6}{\epsilon'/\epsilon_0}$	$\frac{3 \times 10^9}{\tan \delta}$
25	GMG Melamine, dry	8.2	7.0	6.7	6.6	6.4	
25	after 6 or 8 mos., 90% rel. hum.	42.5	16.8	10.4	7.65	6.57	
25	Hycol 6030, dry and after 4 days in H_2O , no change at 1×10^9 .	.75	.54	.27	.10	.030	
25	Lucite HM-119, dry and after 18 months at 90% relative humidity, $25^{\circ}C$, no change in the range 10^2 to 10^6 c/s.	---	---	---	---	---	2.74
25	Lumarith 22361, dry	---	---	---	---	---	.0196
25	after 20 days or more at 90% rel. hum.	---	---	---	---	---	3.14
25	Micarta 496, dry	---	---	---	---	---	.047
25	after 24 hrs., 90% rel. hum.	---	---	---	---	---	3.78
25	Nylon, See page 23	---	---	---	---	---	.059
25	Poly-2,5-dichlorostyrene, dry	---	---	---	---	---	3.94
25	after 20 days, 90% rel. hum.	---	---	---	---	---	.071
25	Polystyrene, See pages 36 and 37	---	---	---	---	---	2.59
25	Polythene, dry	---	---	---	---	---	.00026
25	after 10 days, 90% rel. hum.	---	---	---	---	---	2.59
25	Teflon, dry and after 18 months at 90% relative humidity, $25^{\circ}C$, no change in the range 10^2 to 10^6 c/s.	---	---	---	---	---	.00085
25	Vinylite VU-1900, dry and after 18 months at 90% relative humidity, $25^{\circ}C$, no change in the range 10^2 to 10^6 c/s.	---	---	---	---	---	2.26

Data at Fixed Frequency as a Function of Temperature

Inorganic Crystals

Aluminum oxide, sapphire*

Linde Air




*Field $\perp$ to optic axis and field $\parallel$ to optic axis.

Inorganic Crystals (cont.)

Potassium dihydrogen phosphate*

Brush





*Field || to optic axis, 15 volts/cm.

Inorganic Crystals (cont.)

Thallium iodide (pressed sample)

Eng. Res. and Dev. Lab.





Inorganic Crystals (cont.)

KRS-6 (ThCl, 40%, ThBr, 60%)

Eng. Res. and Dev. Lab.

Thallium bromide


ϵ/ϵ_0



Inorganic Crystals (cont.)

KRS-5 (ThBr, 42%, ThI, 58%)
 ϵ'/ϵ_0



Eng. Res. and Dev. Lab.



Inorganic Crystals (cont.)

Titanium dioxide, rutile*

Linde Air




*Field $\perp$ to optic axis and field $\parallel$ to optic axis.

Steatite Bodies

AlSiMag A-196


Amer. Lava



Steatite Bodies (cont.)

AlSiMag A-196



Amr. Lava



Steatite Bodies (cont.)

AlSiMag A-35


Amer. Lava




Steatite Bodies (cont.)

Amer. Lava

AlSiMag 228
 ϵ'/ϵ_0




$\tan \delta$



Steatite Bodies (cont.)


AlSiMag 243

Amer. Lava



AlSiMag 505


Amer. Lava



Steatite Bodies (cont.)


Ceramic F-66

Bell



Steatite Body 7292


Gen. Ceramics and Steatite



Steatite Bodies (cont.)

Steatite Type 302

Centralab




Steatite Bodies (cont.)

Centralab

Steatite Type 302


$\tan \delta$



Steatite Bodies (cont.)

Steatite Type 400, 452



Centralab



Steatite Bodies (cont.)

Steatite Type 410
 ϵ/ϵ_0


Centralab



Titania and Titanate Bodies

Ceramic NPOT 96


Amer. Lava




Titania and Titanate Bodies (cont.)

Ceramic NPOT 96

Amer. Lava




Titania and Titanate Bodies (cont.)



Titania and Titanate Bodies (cont.)

Ceramic N750T96
tan δ


Amer. Lava



Titania and Titanate Bodies (cont.)

Ceramic N1400T110


Amer. Lava



Titania and Titanate Bodies (cont.)

Ceramic N1400T110
 $\tan \delta$


Amer. Lava



Porcelains

Zirconium porcelain Z1-4

Coors




Porcelains (cont.)

Zirconium porcelain Zi-4

Coors

$\tan \delta$




Porcelains (cont.)

Coors AI-200

Coors


ϵ'/ϵ_0




Porcelains (cont.)

Coors AI-200

Coors




Porcelains (cont.)



Porcelains (cont.)

Coors


Coors AB-2
tan δ



Porcelains (cont.)


Porcelain, wet process; dry process

Knox



AlSiMag 491


Amer. Lava



Miscellaneous Ceramics

Porous Ceramic AF-497


Stupakoff





Glasses

Borosilicate Glass



Components and Systems Lab.



Glasses (cont.)





Glasses (cont.)



Glasses (cont.)

General Electric

Fused Quartz
 ϵ/ϵ_0





Glasses (cont.)

Alkali-silica-glasses
 ϵ'/ϵ_0

Frequency = 1×10^{10} c/s.


Lab. Ins. Res.



Mica and Glass

Mycalex 2821


General Electric



Mica and Glass (cont.)

Mycalex 2821
 $\tan \delta$



General Electric



Mica and Glass (cont.)

Mykroy Grade 8, Grade 38
 ϵ/ϵ_0



Electronic Mech.



Phenol-formaldehyde Resins

Resinox 10231



Monsanto



Phenol-formaldehyde Resins (cont.)

Monsanto


Resinox 10900



Phenol-formaldehyde Resins (cont.)

Taylor Grade GGG



Taylor



Melamine-formaldehyde Resin

Melmac Molding Compound 1502



Amer. Cyanamid



Polyamide Resin

Nylon FM 10,001



DuPont



Cellulose Propionate

Forticel

Celanese




Ethyl Cellulose


Ethocel LT5

Celanese

ϵ'/ϵ_0





$\tan \delta$



Polychlorotrifluoroethylene

Kel-F Grade 300


Kellogg



Miscellaneous Vinyls


Experimental Plastic Q406

Dow



Experimental Plastic Q817.1



Dow




Styrene Copolymers, Linear

Styrene-acrylonitrile copolymer


Amer. Cyanamid



Styrene Copolymers, Linear (cont.)




Styrene Copolymers, Cross-linked



Polyesters


Laminac 4115

Amer. Cyanamid





Laminac PDL7-627

Amer. Cyanamid



Polyesters (cont.)




Polyesters (cont.)


Paraplex P43

Rohm and Haas



ϵ'/ϵ_0



$\tan \delta$




Polyesters (cont.)



Alkyd Resins (cont.)

Chlorinated alkyd
diisocyanate, foamed

Cornell Aero-
nautical Labs.




Epoxy Resin


Araldite Casting Resin Type B

Ciba

ϵ/ϵ_0



$\tan \delta$




Silicone Rubbers


Silastic 181, 250, 6167

Dow Corning

ϵ'/ϵ_0



$\tan \delta$



Company Index

- A -	Page		Page
AIRCRAFT-MARINE PRODUCTS INC., . . .	14	CELANESE CORP. OF AMERICA, .	24, 25,
1523 N. Fourth St.		Plastics Div.	114, 115
Harrisburg, Pa.		290 Ferry St.	
ALLISON AND CO., W. M., ...	58	Newark 5, N. J.	
162 Water St.		CELLULAR RUBBER PRODUCTS, INC., .	51
New York, N. Y.		P.O. Box 126	
AMBER MINES INC., ...	55	Willimantic, Conn.	
353 Fifth Ave.		CENTRAL SCIENTIFIC CO., ...	56
New York, N. Y.		79 Amherst St.	
AMERICAN CYANAMID CO., . .	21-23, 38, 46,	Cambridge, Mass.	
Plastics Devel. Labs.	112, 118-121	CENTRALAB GLOBE-UNION INC., . . .	3,
1937 West Main St.		932 E. Keefe Ave.	84-87
Stamford, Conn.		Milwaukee 1, Wis.	
AMERICAN LAVA CORP., . .	3, 4, 6, 78-82,	CIBA CO., INC., . .	21, 49, 50, 125
Chattanooga 5, Tenn.	88-93, 100	Plastics Div.	
AMERICAN OPTICAL CO., ...	9	627 Greenwich St.	
Southbridge, Mass.		New York, N. Y.	
AMERICAN PHENOLIC CORP., ...	28	COMPONENTS AND SYSTEMS LAB.	
1830 South 54th Ave.		SEE: U.S., Components and	
Chicago 50, Ill.		Systems Lab.	
AMERICAN SMELTING AND REFINING CO., .	13	CONTINENTAL-DIAMOND FIBRE CO.	18, 19,
120 Broadway		Bridgeport, Pa.	21, 26, 27, 31, 32
New York 5, N. Y.		COORS PORCELAIN CO., . . .	6, 94-99
		Golden, Colo.	
- B -		CORNELL AERONAUTICAL LABS.,	48, 124
BAKELITE CORP., .	15, 16, 20, 27-29, 36,	Cornell University	
30 East 42nd St.	48, 57, 58, 64	Ithaca, N. Y.	
New York 17, N. Y.		CORNING GLASS WORKS, 9-11,	26, 41, 42,
BELL TELEPHONE LABORATORIES, . . .	3, 83	Physical Lab.	102, 103
463 West St.		Res. and Devel. Dept.	
New York, N. Y.		Corning, N. Y.	
BROMUND AND CO., E. A., ...	57	CROWLEY AND CO., Henry L., . .	4, 7
258 Broadway		1 Central Ave.	
New York, N. Y.		West Orange, N. J.	
BRUSH DEVELOPMENT CO., ...	1, 73		
3405 Perkins Ave.		- D -	
Cleveland 14, O.		DENNISON MFG. CO., ...	58
- C -		45 Ford Ave.	
CALIFORNIA RESEARCH CORP., ...	65	Framingham, Mass.	
Box 1627		DEWEY AND ALMY CHEMICAL CO., . .	38
Richmond, Calif.		Organic Chemicals Div.	
CANDY AND CO., INC., ...	57	Cambridge 40, Mass.	
35th St. at Maplewood Ave.		DOW CHEMICAL CO., 36-42, 46, 64, 117	
Chicago, Ill.		Plastics Div.	
CANTOL WAX CO., ...	59	Midland, Mich.	
211 N. Washington St.		DOW CORNING CORP., .	26, 27, 41, 42,
Bloomington, Ind.		Midland, Mich.	54, 55, 66, 67, 126
CATALIN CORP. OF AMERICA, . . .	16-18, 36	DU PONT DE NEMOURS AND CO., INC., E.I.	
Plant and Labs.	39, 119	Electrochemicals Dept.	33, 64
Fords, N. J.		Niagara Falls, N. Y.	

Company Index (cont.)

	Page		Page
DU PONT DE NEMOURS AND CO., INC., E.I.		GENERAL ELECTRIC CO., ...	48
Organic Chemicals Dept., ...	53	Chemical Div.	
P.O. Box 525		Pittsfield, Mass.	
Wilmington, Del.		Plastics Dept., ...	50
Pigments Dept., ...	4	1 Plastics Ave.	
Newport, Del.		Pittsfield, Mass.	
Polychemicals Dept., 23,25,27,32,34,35,		1 River Rd., ...	13,106,107
Wilmington, Del.	58,113	Schenectady, N. Y.	
DUREZ PLASTICS AND CHEMICALS, INC.	17,20	Chemicals Dept., ...	55,67
North Tonawanda, N. Y.		Waterford, N. Y.	
DURITE PLASTICS, INC.,*	17,19	Lamp Dept., ...	11,104
5000 Summerdale Ave.		113 East 152nd St.	
Philadelphia, Pa.		Cleveland 10, O.	
- E -		GENERAL MILLS, INC., ...	23
EASTMAN KODAK CO., ...	15,62	2010 East Hennepin Ave.	
Rochester 4, N. Y.		Minneapolis 13, Minn.	
ELECTRONIC MECHANICS, INC., ...	13,108	GLASTIC CORP., THE, ...	47,49
70 Clifton Blvd.		1823 East 40th St.	
Clifton, N. J.		Cleveland 3, O.	
ENGINEER RESEARCH AND DEVEL. LAB.		GLENCO CORP., ...	5,6
SEE: U.S., Eng. Res. and Devel. Lab.		Metuchen, N. J.	
ENJAY CO., INC., ...	28,39,50	GLYCO PRODUCTS CO., ...	56,59
15 West 51st St.		26 Court St.	
New York 19, N. Y.		Brooklyn 2, N. Y.	
ESSO LABORATORIES		GOODRICH CHEMICAL CO., B.F.,	29,30
SEE: ENJAY CO., INC.		Avon Lake Experimental Station	
- F -		P.O. Box 122	
FILTERED ROSIN PRODUCTS, INC., ...	56	Avon Lake, O.	
Brunswick, Ga.		GOODYEAR AIRCRAFT CORP., ...	48
FORMICA CO., THE, ...	17,20,21,25,46,47	Akron 15, O.	
4614 Spring Grove Ave.		GOODYEAR TIRE AND RUBBER CO., INC., THE	
Cincinnati 32, O.		Plastics Dept., ...	40,51,52
FRENCHTOWN PORCELAIN CO., ...	6	Akron 16, O.	
Frenchtown, N. J.		GULF OIL CO., ...	58
- G -		P.O. Box 2038	
GENERAL ANILINE AND FILM CORP., ...	34,46	Pittsburgh, Pa.	
Coal and Lincoln Sts.		- H -	
Easton, Pa.		HARDMAN CO., H.V., ...	49,51
GENERAL CABLE CORP., ...	52	571 Cortlandt St.	
Bayonne, N. J.		Belleville 9, N. J.	
GENERAL CERAMICS AND STEATITE CORP.,	4,	HARSHAW CHEMICAL CO., ...	1,2
Keasbey, N. J.	8,83	1945 East 97th St.	
GENERAL ELECTRIC CO., ...	63-65	Cleveland 6, O.	
100 Woodlawn Ave.		HERCULES POWDER CO., INC., ...	23
Pittsfield, Mass.		Cellulose Products Dept.	
		Parlin, N. J.	

* Now The Borden Co., Chemical Div., 350 Madison Ave., New York 17, N. Y.

Company Index (cont.)

	Page		Page
HOOD RUBBER CO., ...	22	MARCO CHEMICALS, INC., ...	47
98 Nichols Ave.		Sewaren, N. J.	
Watertown 72, Mass.		MASS. INST. OF TECH., 1,2,5,11,12,26,	
HOOVER ELECTROCHEMICAL CO., ...	62	Lab. for Insul. Res. 37,41-46,62,	
Niagara Falls, N. Y.		77 Mass. Ave. 64,105	
HOUGHTON LABS., INC., ...	50	Cambridge 39, Mass.	
322 Bush St.		MATHIESON CHEMICAL CORP., ...	41
Olean, N. Y.		P.O. Box 480	
- J -		Niagara Falls, N. Y.	
JOHNS-MANVILLE, ...	13	MICA INSULATOR CO., ...	21
22 East 40th St.		801 Broadway	
New York 16, N. Y.		Schenectady, N. Y.	
- K -		MINNESOTA MINING AND MFG. CO., ...	63
KEARNEY CORP., JAMES R., ...	52	900 Farquhar Ave.	
4236 Clayton Ave.		St. Paul 6, Minn.	
St. Louis 10, Mo.		MITCHELL-RAND INSULATION CO., 57-59	
KELLOGG CO., THE M. W., ...	31,58,63,116	51 Murray St.	
P.O. Box 469		New York, N. Y.	
Jersey City 3, N. J.		MONSANTO CHEMICAL CO., 15,18,20,22,	
KNOX PORCELAIN CORP., ...	6,100	Plastics Div., 24,30,36,37,	
Knoxville 11, Tenn.		Springfield 2, Mass. 41-45,63,64	
KURNE-LIBBY CO., ...	57	MYCALEX CORP. OF AMERICA, ...	13
54 Front St.		60 Clifton Blvd.	
New York 4, N. Y.		Clifton, N. J.	
- L -		- N -	
LAMINATED PLASTICS, INC.		NAUGATUCK CHEMICAL, ...	47,53
SEE: GLASTIC CORP.		Naugatuck, Conn.	
LIBBEY-OWENS-FORD GLASS CO., ...	22,23,47	NORTON CO., ...	1,6
Plaskon Div. 49,123		Worcester 6, Mass.	
2112-24 Sylvan Ave.		- O -	
Toledo 6, O.		OWENS-CORNING FIBERGLAS CORP., 11,16,	
LINDE AIR PRODUCTS CO., THE, ...	1,2,72,77	Newark, O. 22,47,48	
East Park Dr. and Woodward Ave.		- P -	
Tonawanda, N. Y.		PENNSYLVANIA INDUSTRIAL CHEMICAL CORP.	
LOVELL CHEMICAL CO., ...	57,58	Clairton, Pa., 39,50	
Watertown 72, Mass.		(Products distributed by Standard	
LUCOFLEX PLASTIC FABRICATING INC., ...	30	Chemical Co., Akron 8, O.)	
242 Village St.		PITTSBURGH CORNING CORP., ...	11
Medway, Mass.		632 Duquesne Way	
- M -		Pittsburgh, Pa.	
MALLINCKRODT CHEMICAL WORKS, 44,45,61,62		PLASKON DIV., ...	22,23,47,49
3600 North Second St.		Libbey-Owens-Ford Glass Co.	
St. Louis, Mo.		2112-24 Sylvan Ave.	
MARBON CORP., ...	38	Toledo 6, O.	
1926 West 10th Ave.		PLASTIC METALS, INC., ...	43,44
Gary, Ind.		Johnstown, Pa.	
		FLAX CORP., ...	35
		133 Walnut St.	
		Hartford 5, Conn.	

Company Index (cont.)

	Page		Page
POLAROID CORP., ...	35,37,40	SOUTHERN ALKALI CORP., ...	48
Cambridge, Mass.		Barberton, O.	
PROCTER AND GAMBLE MFG. CO., ...	60	SPONGE RUBBER PRODUCTS CO., 19,31,52	
Cincinnati 1, O.		Shelton, Conn.	
- R -		SPRAGUE ELECTRIC CO., ...	39
RESINOUS PRODUCTS AND CHEMICAL CO.		North Adams, Mass.	
SEE: ROHM and HAAS CO.		STANCO DISTRIBUTORS, INC., . . . 65,66	
REX CORP., ...	40	Chemical Products Dept.	
Hayward Rd.		26 Broadway	
West Acton, Mass.		New York 4, N. Y.	
REZOLIN, INC., ...	19	STANDARD OIL CO. OF N. J., . . . 58	
5736 West 96th St.		26 Broadway	
Los Angeles 45, Calif.		New York, N. Y.	
ROBERTSON CO., H. H., ...	48,123	STANDARD OIL DEVEL. CO.	
2400 Farmers Bank Bldg.		SEE: ENJAY CO., INC.	
Pittsburgh 22, Pa.		STUPAKOFF CERAMIC AND MFG. CO., 6,101	
ROGERS PAPER MFG. CO., ...	60	Hillview Ave.	
Manchester, Conn.		Latrobe, Pa.	
ROHM AND HAAS CO., ...	30,34,48,62,122	- T -	
Washington Sq.		TAYLOR FIBRE CO., ...	18,27,111
Philadelphia 5, Pa.		Norristown, Pa.	
RUBBER RESERVE CORP., ...	51,52	TENNESSEE EASTMAN CORP., ...	24
Washington 1, D.C.		Kingsport, Tenn.	
- S -		TENNESSEE MARBLE, INC., ...	13
ST. REGIS PAPER CO., ...	17,22	Knoxville, Tenn.	
Panelyte Div.		THIOKOL CORP., ...	54
Enterprise Ave.		780 North Clinton Ave.	
Trenton, N. J.		Trenton 7, N. J.	
SHARPLES CHEMICALS, INC., ...	63	TITANIUM ALLOY MFG. DIV., 4,5,42,43	
123 South Broad St.		National Lead Co.	
Philadelphia 9, Pa.		Hyde Park Blvd.	
SHAWINIGAN PRODUCTS CORP., ...	34	Niagara Falls, N. Y.	
Empire State Bldg.		- U -	
New York 1, N. Y.		U.S. GASKET CO., ...	32,33
SHELL CHEMICAL CORP., ...	50	P.O. Box 93	
Resins and Plastics Dept.		Camden, N. J.	
50 West 50th St.		UNITED STATES (GOVERNMENT)	
New York 20, N. Y.		Components and Systems Lab., 9,101	
SHELL DEVEL. CO., ...	46-48	Air Matériel Command	
4560 Horton St.		Wright-Patterson Air Force Base	
Emeryville 8, Calif.		Dayton, O.	
SHELL OIL CO., ...	56,66	Engineer Research and Devel. Lab.	
Special Products Dept.		Fort Belvoir, Va., ...	2,74-76
50 West 50th St.		National Bureau of Standards, 40	
New York 20, N. Y.		Washington, D. C.	
SOCONY-VACUUM OIL CO., INC., . . . 57,58		War Dept., ...	15
Technical Service Div.		Picatinny Arsenal	
412 Greenpoint Ave.		Dover, N. J.	
New York, N. Y.			

Company Index (cont.)

	Page		Page
U.S. INDUSTRIAL CHEMICALS, INC., . .	62	WEBER AND CO., HERMANN, ...	51
60 East 42nd St.		76 Beaver St.	
New York 17, N. Y.		New York 5, N. Y.	
U.S. RUBBER CO., ...	31,40,52,53,56	WESTINGHOUSE ELECTRIC CORP.,18,19,22	
General Labs.		Research Labs.	
Passaic, N. J.		East Pittsburgh, Pa.	
- V -		- Z -	
VICTOR CHEMICAL WORKS, ...	48	ZINSSER AND CO., Wm., ...	55,56
Board of Trade Bldg.		516 West 59th St.	
141 West Jackson Blvd.		New York, N. Y.	
Chicago 4, Ill.		ZOPHAR MILLS, INC., ...	59
- W -		112-130 26th St.	
WAR DEPT., Picatinny Arsenal		Brooklyn, N. Y.	
SEE: U.S. War Dept., Picatinny Arsenal			

Materials Index

- A -		Page		Page
Acrawax C		56	Bentonite	14
Acrylate resins	34,35		Benzenes and diphenyls, chlorinated	63
Acrylonitrile-butadiene copolymer		53	Benzenes, chloro-	64
Air seal		52	Benzoguanamine-formaldehyde resin	23
Alathon	27,70		Beryllium oxide	6
Alcohols		62	Biphenyls, chlorinated	15,63,64
Alkyd resins	47-49,123,124		Bitumen, natural	56
Allyl resins	47,48		Buna S (GR-S) and compounds	52
Allymer CR-39, CR-39 + glass		48	Bureau of Standards Casting Resin	40
AlSiMag A-35	3,80		Butadiene-acrylonitrile copolymer	53
AlSiMag A-196	3,78,79		Butadiene, chloro-	53,62
AlSiMag 211	3		Butadiene-styrene copolymer	38,52
AlSiMag 228	3,81		Butvar, Low OH and 55/98	34
AlSiMag 243	3,82		n-Butyl alcohol	62
AlSiMag 393	3		Butyl rubbers	52
AlSiMag 491	6,100		Butyraldehyde	62
AlSiMag 505	82			
Aluminum oxide	1,3,6,72,96-100		- C -	
Alvar 11/90	34		Cable Oil 5314 and PL101270	65
Amber	55		Calcium titanate	5
Ammonium dihydrogen phosphate	1		Carbon and plastic mixtures	41
Amplifilm	14		Carbon tetrachloride	62
Aniline-formaldehyde resins	21		Catalin 200, 500, and 700 base	16,17
Apiezon Wax "W"	56		Catalin 8012	39,119
Araldite Adhesive, Type I	50		Catalin EK 2784	39
natural and silver			Cellulose Acetate II-1	23
Araldite Casting Resin, Type B	49,125		Cellulose acetate + plasticizer	24
Araldite Casting Resin G	49		Cellulose acetates	23,24
Araldite E-134	49		Cellulose derivatives	23-25
Aroclor 1221, 1232, 1242, 1248, 1254	63		Cellulose nitrate and camphor	25
Aroclor 1260, 1262, 5442	64		Cellulose propionate	25,114
Aroclor 1268, 4465, 5460	15		Cements and asphalts	56
Asbestos	13		Cenco Sealstix	56
Asphalts and Cements	56		Ceramic F-66	3,83
			Ceramic NPOT 96	4,88,89
- B -			Ceramic N75OT96	4,90,91
Bakelite BM-120	15,16,69		Ceramic N1400T110	4,92,93
Bakelite BM-250, BT-48-306,	16		Ceramic T106	4
BM-16981, and BM-16981 powder			Ceramics	3-8,78-101
Bakelite BM-262, BM-1895	20,69		Cerese Wax AA and brown	57
Bakelite BRS-16631 + glass	48		Ceresin, white and yellow	57
Bakelite BV-17085 + glass	16		Cetylacetamide	56
Balata, precipitated	51		Chemelac M1405, M1406, M1407,	32
Barium-strontium titanate	5,6		M1411, M1412, and M1414	
Barium titanate	5		Chemelac M1418-2, M1418-5,	33
Barium titanate and plastic mixtures	43		M1422, and M1423	
Bayol, Bayol-16	66		Chemlac B-3	56
Bayol-D, Bayol-F	65		Chlorinated benzenes and biphenyls	15,63,64
Beeswax, white, yellow	57			
Beetle resin	23			

Materials Index (cont.)

	Page
β -chloroethyl-2,5-dichlorobenzene . . .	64
Chlorostyrenes, ortho and para, . . .	42
copolymer	
Cibanite	21
Coors AB-2	6,98,99
Coors AI-200	6,96,97
Copolene B	28
Corfoam 114	19
Corning Glass Nos. 0010, 0014, . . .	9
0080, 0090, 0100, 0120, 1770	
Corning Glass No. 1990	9,102
Corning Glass Nos. 1991, 3320, . . .	9
7040, 7050	
Corning Glass Nos. 7052, 7055, 7060 . .	10
Corning Glass No. 7070	10,102
Corning Glass Nos. 7230, 7570, 7720, .	10
7740, 7750, 7900	
Corning Glass No. 7911	10,103
Corning Glass Nos. 8460, 8830	10
Corning Glass Nos. 8871, 9010, ...	11
Lab. No. 189CS	
Crepe, pale and compounds	51
Cresylic-acid	18,19,68,70
formaldehyde resins	
Crolite No. 29	4
Crowloy 20, 70, BX113, BX114	7
Crystals, inorganic	1,2,72-77
Crystals, organic	15

- D -

Darex No. 3, 43E, X-34, X-43	38
DeKhotinsky Cement	56
Diala Oil	66
Diallyl phenyl phosphonate resin . . .	48
Diatomaceous-earth ceramic	6,101
Dibutyl sebacate	62
Dichloronaphthalenes, mixture of . .	58
the 1,2-, 1,4- and 1,5- isomers	
Dichloropentanes #14, #40	63
2,5-Dichlorostyrene	64
Dilectene 100	21
Dilecto (hot punching)	19
Dilecto (mecoboard)	18
Dilecto GB-112S	27
Dilecto GB-112T	31,32
Dilecto GB-261S	26
Diocetyl sebacate	62
Diphenyl (SEE: Biphenyl)	
Dow C-244	36

	Page
Dow Experimental Plastic Q-166, . . .	39
Q-166 + Fiberglas, Q-200,5	
Dow Experimental Plastic Q-247.1 . . .	36
Dow Experimental Plastic Q-344	40
Dow Experimental Plastic Q-406	37,117
Dow Experimental Plastic Q-409	42
Dow Experimental Plastic Q-475.5 . . .	40
Dow Experimental Plastic Q-764.6, . .	37
Q-767.2	
Dow Experimental Plastic Q-817.1 . . .	37,117
Durez 1601, natural	17
Durez 11863	20
Durite #500	17
Durite #221X	19

- E -

E Resin	50
Elastomers	51-55
Elvacet 42A-900	33
Elvanol 51A-05, 50A-42, 70A-05, . .	33
72A-05, 72A-51	
Ensolite M22240, M22239, 3036	31
Epon Resin RN-48	50
Epoxy resins	49,50,125
Estawax	57
Ethocel LT5	25,115
Ethyl alcohol	62
Ethyl cellulose	25,115
Ethylene Glycol	62
Ethylpolychlorobenzene	64

- F -

Ferramic A,B,C,D,G,H,I,J	8
Ferrites	7,8
Fiberglas	22,68
Fiberglas BK-174, laminated	16
Fibestos 2050TVA C-1686	24
Foanglas	11
Formaldehyde resins, aniline	21
Formaldehyde resins, benzoguanamine .	23
Formaldehyde resins, cresol . 18,19,68,70	
Formaldehyde resins, melamine . 21,22,112	
Formaldehyde resins, phenol 15-19,109-111	
Formaldehyde resins, phenol-aniline .	20
Formaldehyde resins, urea	23
Formica FF-41 (sheet, rod stock) . 21,68	
Formica FF-55	21,69
Formica G7, G6	25
Formica Grade MF-66	20,68

Materials Index (cont.)

	Page		Page
Formica XX, LE	17,68	Halowax #11-314	58
Formica YN-25	17	Halowax Oil 1000	64
Formica Z65	46	Heptacosafuorotributyl amine	63
Formica Z80	47	Heptane	62
Formvar, Type E	34	Hexachlorobutadiene	62
Forticel	25,114	Hexamethylene-adipamide polymer	23,113
Fractol A	66	Hycar OR Cell-tite	52
Furfuraldehyde resin, phenol	19	Hydrocarbon polymer, cross-linked	50
- G -		Hydrocarbons, petroleum	65,66
Gafite cast polymer	34	12-Hydroxystearin	58
Gasoline, aviation, 100 and 91 octane	65	Hysol 6000 and 6020	50
Geon 2046, 80365, 80384	29	Hysol 6030	50,70
Gilschite	56	Hy-tuf Laminate Grade GF181	50
Glass, alkali-silica	12,105	- I -	
Glass, alkaline lead silicate	11	Ice	1
Glass, aluminum borosilicate	10	Ignition Sealing Compound #4	67
Glass, aluminum zinc-phosphate	9	Iron and plastic mixtures	43,44
Glass and mica	13,69,106-108	Iron-manganese oxide	45
Glass and plastic mixtures	41,42	and plastic mixtures	
Glass, barium borosilicate	10	Isobutylene-isoprene copolymer	52
Glass, borosilicate	9,101	- J -	
Glass, "E"	11	Jet fuel JP-1 and JP-3	65
Glass, iron-sealing	9,102	- K -	
Glass Lamicoid #6038	21,70	Kel-F	31
Glass, lead-barium	9	Kel-F Grade 300 and 300-P25	31,116
Glass, lime-alumina-silicate	9	Kel-F Grease #40	63
Glass, low alkali, potash-	10,102	Kel-F Oil, Grade #1, #3, #10	63
lithia-borosilicate		Kel-F Wax #150	58
Glass, Phosphate 2043x, 2279x	9	Kerosene	65
Glass, potash-lead-silicate	9	Koroseal 5CS-243	30
Glass, potash-soda-barium-silicate	9	Kralastic BE, BM, D, EBMU, F	53
Glass, silica	11,102	KRS-5	2,76
Glass, soda-borosilicate	9,10	KRS-6	2,75
Glass, soda-lead-borosilicate	10	- L -	
Glass, soda-lime-silicate	9,11	Laminac 4115	46,120
Glass, soda-potash-borosilicate	9	Laminac 4-205	46,121
Glass, soda-potash-lead-silicate	9	Laminac PDL7-627 and PDL7-650	46,120
Glass, soda-potash-lithia-borosilicate	10	Laminate BD-44 and BK 164	47,48
Glass, soda-silica	11	Leather, sole	60
Glasses	9-12,101-105	Liquids, aliphatic	62,63
Glastic GF, MM, MP, and A-2	48	Liquids, aromatic	63,64
Glastic S and MF	47	Liquids, inorganic	61
Glyptol #1201 (red)	48	Liquids, organic	62-67
GR-I (butyl rubber) and compound	52	Liquids, petroleum	65,66
GR-S (Buna S) and compounds	52	Liquids, silicone	66,67
Gutta-percha	51		
- H -			
Halowax #1001	57		

Materials Index (cont.)

	Page		Page
Lithium fluoride	1	Naphthalene, chloro	64
Loalin	36	Naugatuck Laminating Resin MP and MT	47
Lucite HM-119 and HM-140	34,70	Neoprene GN and compound	53
Lucite, sintered	34	Nitrobenzene	64
Lucoflex	30	Nylon 66 and 610	23
Lumarith XFA-H4 and 22361	24,25,70	Nylon FM 10,001	23,113
Lustrex loaded glass mat	41		
		- O -	
- M -		Oil, HB-40	63
Magnesium oxide	1	Oils, petroleum	65,66
Magnesium silicate	3,78-82	Opalwax	58
Magnesium titanate	4	Ozokerite	58
Magnesium titanate and	43		
plastic mixture		- P -	
Magnetite and plastic mixtures	44,45	Panelyte Grade 140 and 776	17,22
Marble S-3030	13	Paper, Royalgrey	60
Marbon S, Buna S Hardboard	52	Paraffin, natural	58
Marbon S (Code 7206), S-1 (Code 7254), 38		Paraffin Wax 132° ASTM and 135° AMP.	58
8000 and 9200		Paraplex P13 and P43	48,122
Marco Resin MR-21C, MR-23C and MR-25C	47	Parowax	58
Marcel	65	Perfluorodihexyl ether	63
Mathieson Plastic CY-8 and CQ-10DM	41	Permafil 3256	50
Meat	60	Permo Potting Compound #49 and #51	49,51
Melamine-formaldehyde resins	21,22,112	Petroleum oils	65,66
Melamine GMC	21,70	Phenol-aniline-formaldehyde resins	20
Melmec 7278 + "E" glass	22	Phenol-formaldehyde resins 15-19,109-111	
Melmec Molding Comp. 1500,1502	22,112	Phenol-furfuraldehyde resin	19
Melmec Resin 592	21	Phenolic, Expanded	19
Melmec Type 1077 (Ivory WB 48)	21	Phenolic paper laminate JH-1410	18
Methacrylate resins	34,35	Phoresin	48
Methocel	25	Piccolastic D-125	39
Methyl alcohol	62	Piccopale Resin	50
Methyl cellulose	25	Plaskon 911	47
Methylstyrene-styrene copolymer	39	Plaskon Alkyd 411,420,422,440, ...	49
Mica and glass	13,69,106-108	440A and 442	
Mica, Canadian	13	Plaskon Alkyd Special	49,123
Mica, ruby	13	Electrical Granular	
Micarta #254	18	Plaskon melamine	22
Micarta #259	22,68	Plaskon Urea, natural and brown	23
Micarta #299	19,68	Plasticall	31
Micarta #496	18,68,70	Plast-Iron and plastic mixtures	43,44
Millimar	56	Plaxiglas	34
Muscovite	13	Plicene Cement	56
Mycalox K10	13	Pliobond M-190-C	52
Mycalox 400	13,69	Pliolite and Pliolite GR	51
Mycalox 2821	13,106,107	Pliolite S5,S3,S6B and S6	40
Mykroy Grade 8 and 38	13,108	Polaroid Resin C	40
		Polelectron #24	46
- N -		Polinel	58
Naphthalene	15		

Materials Index (cont.)

	Page		Page
Polyamide resins	23,113	Polyvinylidene and vinyl chlorides	31
Polybutene	59	Poly- α -vinyl-naphthalene	46
Polybutyl methacrylate	35	Poly-2-vinylpyridine	46
Poly-2-chlorobutadiene-1,3	53	Polyvinyl resins	27-46
Polychlorostyrenes	41,42	Polyvinyltoluene	37,117
Polychlorotrifluoroethylene	31,58,63,116	Poly-p-xylylene	37
Polycyclohexyl methacrylate	35	Porcelain, wet and dry process	6,100
Polydiallyl phthalate	48	Porcelain #4462	6
Poly-2,5-dichlorostyrene	40-42,70	Porcelains	6,94-100
Poly-2,5-dichlorostyrene	42-45	Porous Ceramic AF-497	6,101
+ fillers		Potassium bromide	1
Poly-3,4-dichlorostyrene	42	Potassium dihydrogen phosphate	1,73
Polyesters	46-48,120-123	Primol-D	66
Polyethyl methacrylate	35	n-Propyl alcohol	62
Polyethylene	27,28,70	Prystal	17
Polyethylene (effect of milling)	28	Pyralin	25
Polyethylene DE-3401	27	Pyranol 1467,1476 and 1478	63,64
Polyglas D ⁺	42	Pyrex	10
Polyglas M	22		
Polyglas P ⁺	41	- Q -	
Polyglas S	26	Quartz, fused	11,104
Polyisobutyl methacrylate	35	Quinorgo #3000	13
Polyisobutylene B-100 + Marbon B	28	Quinterra	13
Polyisobutylene, Run 5047-2	28		
Polymethyl methacrylate	34,70	- R -	
Polystyrene	35-37,117	Resimene 803-A	22
Polystyrene, cast in vacuo and	37	Resinox 7934	20
cast in air		Resinox 10231	18,109
Polystyrene + chlorinated diphenyl	37	Resinox 10900	18,110
Polystyrene, cross-linked	39,40,119	Resins, natural	55,56
Polystyrene Fibers Q-107	37	Rexolite 1422	40
Polystyrene + fillers	41	Royalite 149-11, M21982-1 and M22190	53
Polystyrene Foam Q-103	37	Rubber, butyl (GR-I)	52
Polystyrene, hydrogenated	46	Rubber, cellular	51
Polystyrene, α -methylstyrene	37,117	Rubber, cyclized	51,52
Polytetrafluoroethylene	31-33,70	Rubber, GR-S (Buna S) and compounds	52
Polythene A-3305	27,70	Rubber, Hevea and compounds	51
Polyvinyl acetal	34	Rubber, natural	51
Polyvinyl acetate	33	Rubber, nitrile	53
Polyvinyl alcohol-acetates	33	Rubber, silicone	54,126
Polyvinyl butyral	34	Rutile	2,4,77
Poly-N-vinylcarbazole	46		
Polyvinyl chloride 1006,1018,1216, ...	30	- S -	
1406,W-174,W-175 and W-176		S-40 and S-60 resins	39
Polyvinyl chloride-acetate	28-31	Santicizer 9	15
Polyvinyl chloride-acetate	28,29	Sapphire	1,72
+ plasticizer		Saran B-115	31
Polyvinyl chlorides	28-31	Sealing Wax, Red Express	58
Polyvinylcyclohexane	46	Selectron 5003 + glass	47
Polyvinyl formal	34		

Materials Index (cont.)

	Page		Page
Selenium, amorphous	13	Styron C-176, 411-A, ...	36
Selenium, multi-crystalline	1	475, 666 and 671	
Shellac, natural XL	55	Suet	60
Shellac, natural Zinfo, pure C	56	Sulfur, crystalline	2
garnet and garnet dewaxed		Sulfur, sublimed	2
Silastic 120, 125, 150, 152, ...	54		
160, 167 and 180		- T -	
Silastic 181 and 250	54,126	Tam Ticon B, BS, C, MC and S	4,5,43
Silastic X4342	55	Tam Ticon T-S, T-L and T-M	4
Silastic 6167	55,126	Taylor Grade GCG	18,111
Silastic 6181, X-6734 and 7181	55	Taylor Grade GSC and GSS	27
Silica, fused 915c	11,103	Teflon	31-33,70
Silicon dioxide, fused	11,103	Teflon Laminate GB-112T	31,32
Silicone fluids DC200 and DC500	66	Tenite I 008A H ₂ ,H ₄ ,M,MH,S and S ₄	24
Silicone fluids DC550 and DC710	67	Tenite II 205A H ₂ ,H ₄ ,MH,MS,S ₂ ,S ₄	24
Silicone fluids SF96-40, ...	67	Terphenyl, meta-, nona-, ...	15
SF96-100 and SF96-1000		ortho- and para-	
Silicone glass laminates	26,27	Terphenyls, chlorinated	64
Silicone Molding Compound XM-3	26	Tetrachloroethylene	62
Silicone resin DC996 and DC2101	26	Thallium bromide	2,75
Silicone resins	25-27	Thallium bromide-chloride	2,75
Silicone rubber SE-450, SE-460, ...	55	Thallium bromide-iodide	2,76
SE-550 and SE-972		Thallium iodide	2,74
Silicone rubbers	54,55,126	Thermoplastic Composition 1766EX	58
Snow	1	and 3738	
Soap	60	Thermoplastic Composition 3767A	59
Sodium chloride	2	Thiokol, Type FA, PRI and ST	54
Sodium chloride, aqueous solutions	61	TI Pure R-200.	4
Soils	14	Titanate ceramics	5,6
Steak	60	Titania and titanate bodies	4-6,88-93
Steatite bodies	3,4,78-87	Titanium dioxide ceramics	4,5
Steatite Body 7292	4,83	Titanium dioxide, rutile	2,4,77
Steatite Type 302, 400, 410	3,84-87	Titanium dioxide + plastic mixtures	42
and 452		Toluene sulfonamides, mixture	15
Strontium titanate	5	of ortho- and para- isomers	
Strontium titanate and	43	Transil Oil 100	65
plastic mixtures		Trichlorobenzenes, mixture of	64
Stypol 16B, 16C and 16D	48,123	isomeric	
Styraloy 22	38	Trichloronaphthalenes, mixture	64
Styramic #18	37	of isomeric	
Styramic HT	42,43	α-Trinitrotoluene	15
Styrene copolymers, ...	39,40,119		
cross-linked		- U -	
Styrene copolymers, ...	38,39,118,119	Ultron Wire Compound UL300, ...	30
linear		UL1004 and UL2 4001	
Styrene dimer	64	Urea-formaldehyde resins	23
Styrene N-100, dry and	64		
saturated with water		- V -	
Styrene-acrylonitrile	38,53,118	Vaseline	65
copolymer			
Styrofoam 103.7	37		

Materials Index (cont.)

	Page
Vibron 140 and 141	40
Vynlite QYNA, VG-5544 and VG-5901 .	28
Vynlite VG-5904, VYHE, VYNS and . .	29
VYNW	
Vynlite VU-1900	29,70
2-Vinylpyridine-styrene copolymer .	46
Vistawax	59

	Page
Water, conductivity	61
Wax 3760	59
Wax Compound F-590 and #1340	59
Wax S-1167 and S-1184	59
Waxes	56-59
Wood	59

- Z -

Zirconium porcelain Zi-4	6,94,95
----------------------------------	---------

UNCLASSIFIED

UNCLASSIFIED

