

THIS REPORT HAS BEEN DELIMITED
AND CLEARED FOR PUBLIC RELEASE
UNDER DOD DIRECTIVE 5200.20 AND
NO RESTRICTIONS ARE IMPOSED UPON
ITS USE AND DISCLOSURE.

DISTRIBUTION STATEMENT A

APPROVED FOR PUBLIC RELEASE;
DISTRIBUTION UNLIMITED.

Armed Services Technical Information Agency

Because of our limited supply, you are requested to return this copy WHEN IT HAS SERVED YOUR PURPOSE so that it may be made available to other requesters. Your cooperation will be appreciated.

AD

35880

NOTICE: WHEN GOVERNMENT OR OTHER DRAWINGS, SPECIFICATIONS OR OTHER DATA ARE USED FOR ANY PURPOSE OTHER THAN IN CONNECTION WITH A DEFINITELY RELATED GOVERNMENT PROCUREMENT OPERATION, THE U. S. GOVERNMENT THEREBY INCURS NO RESPONSIBILITY, NOR ANY OBLIGATION WHATSOEVER; AND THE FACT THAT THE GOVERNMENT MAY HAVE FORMULATED, FURNISHED, OR IN ANY WAY SUPPLIED THE SAID DRAWINGS, SPECIFICATIONS, OR OTHER DATA IS NOT TO BE REGARDED BY IMPLICATION OR OTHERWISE AS IN ANY MANNER LICENSING THE HOLDER OR ANY OTHER PERSON OR CORPORATION, OR CONVEYING ANY RIGHTS OR PERMISSION TO MANUFACTURE, USE OR SELL ANY PATENTED INVENTION THAT MAY IN ANY WAY BE RELATED THERETO.

Reproduced by
DOCUMENT SERVICE CENTER
KNOTT BUILDING, DAYTON, 2, OHIO

UNCLASSIFIED

AD No. 35880
ASTIA FILE COPY

Technical Report No. 12

Contract N6 onr - 07129

NR 017 - 412

Physics of the Solid State

University of Illinois
Department of Physics
Urbana, Illinois

Principal Investigator

Robert J. Maurer

June 1954

U. S. Department of the Navy

Office of Naval Research

Washington, D. C.

IONIC CONDUCTIVITY OF NaCl AND KCl

George A. Russell

May 1954

The work done in conjunction with this report was an attempt to determine the cause of apparent increases in conductivity in KCL and NaCl crystals. The increase is noted when the crystals are heated to temperatures above 400 degrees centigrade and allowed to remain there for an hour or so. This increase was first noted by Mr. Joseph Aschner and later confirmed by Mr. Dale Compton both working with Harshaw crystals and crystals grown at the University of Illinois. In addition, Mr. Compton noted this effect in a report on conductivity of KCL and NaCl crystals grown by Dr. Pick.

The apparatus (Crystal holder) used for holding the crystals during the measurements made by Mr. Aschner and Mr. Compton was made from a variety of materials. It consisted of a stainless steel sleeve holding platinum coated Nickel contacts. These contacts held the crystal under slight spring tension. The crystal was painted on two sides with "Dag" to form electrodes. The crystal and lower portion of the holder were in the region of highest temperature while the upper portion of the crystal holder was in a cooler atmosphere. The holder and crystal were in an atmosphere of Helium supplied directly from a Helium tank.

The cause of the apparent increase in conductivity was believed to be due to impurities introduced by the holder when heated to the higher temperatures. To investigate this possibility a new holder was designed. This holder was so designed that only Platinum and Vycor were in the high temperature region. Approximately the same pressure was placed on the crystals and the crystals were again painted on two sides with the "Dag"

coating.

The results obtained are included in the form of plots of log conductivity vs reciprocal temperature and the data from which the plots were made is included.

The data given refers to plots on the succeeding pages.

Plot I. NaCl sample from Harshaw.

Dimensions: $t = .0435''$
 $A = .0971'' \times .0820''$

Temperature increasing:

T	529°	568°	651°	732°	814°	895°
σ	2.38×10^{-8}	8.51×10^{-8}	7.04×10^{-7}	2.82×10^{-6}	7.78×10^{-6}	3.78×10^{-5}
T	976°	°K				
σ	1.46×10^{-4}	ohm ⁻¹ cm ⁻¹				

Temperature decreasing:

T	975°	891°	809°	726°	643°	559°
σ	1.39×10^{-4}	2.54×10^{-5}	6.78×10^{-6}	2.48×10^{-6}	5.47×10^{-7}	6.05×10^{-8}
T	515°	°K				
σ	1.47×10^{-8}	ohm ⁻¹ cm ⁻¹				

Plot II NaCl sample from Pick (Gottingen)

Dimensions: $t = .0805''$
 $A = .1177'' \times .0900''$

Temperature increasing:

T	516°	571°	616°	667°	716°	763°
σ	2.87×10^{-9}	1.78×10^{-8}	5.92×10^{-8}	1.57×10^{-7}	3.2×10^{-7}	6.2×10^{-7}
T	814°	862°	911°			
σ	1.99×10^{-6}	5.8×10^{-6}	2.49×10^{-5}			

Temperature decreasing:

T	880°	798°	744°	687°	632°	575°
σ	1.12×10^{-5}	1.37×10^{-6}	4.9×10^{-7}	2.15×10^{-7}	8.14×10^{-8}	1.87×10^{-8}
T	543°					
σ	5.63×10^{-9}					

Plot III. NaCl sample from Pick. (Crystal remained at 700°C for two hours)

Dimensions: t - .0805"

A - .1142" x .0782"

Prior to remaining at 700°C for two hours:

T	514°	569°	618°	668°	715°	765°
σ	3.04×10^{-9}	1.78×10^{-8}	6.3×10^{-8}	1.6×10^{-7}	3.2×10^{-7}	6.4×10^{-7}
T	813°	863°	911°	959°	975°	
σ	1.53×10^{-6}	6.06×10^{-6}	2.45×10^{-5}	8.36×10^{-5}	1.266×10^{-4}	

After remaining at 700°C for two hours:

T	922°	864°	802°	747°	694°	640°
σ	3.38×10^{-5}	7.25×10^{-6}	1.43×10^{-6}	5.74×10^{-7}	2.78×10^{-7}	1.16×10^{-7}
T	585°	532°				
σ	3.12×10^{-8}	1.34×10^{-8}				

Plot IV. KCl sample from Pick. (Crystal remained at 400°C for two hours)

Dimensions: t - .0519"

A - .0673" x .0611"

Prior to remaining at 400°C for two hours:

T	517°	571°	619°	668°	716°	764°	813°
σ	3.28×10^{-4}	1.99×10^{-8}	3.12×10^{-8}	7.06×10^{-8}	1.85×10^{-7}	3.47×10^{-7}	8.3×10^{-7}
T	861°	910°	934°				
σ	2.19×10^{-6}	8.78×10^{-6}	1.69×10^{-5}				

After remaining at 400°C for two hours:

T	879°	796°	742°	687°	632°	575°
σ	4.24×10^{-6}	7.72×10^{-7}	3.45×10^{-7}	1.49×10^{-7}	5.59×10^{-8}	1.57×10^{-8}
T	542°	521°				
σ	6.05×10^{-9}	3.28×10^{-9}				

Plot V. KCl sample from Pick. (Crystal left at 700°C for 40 minutes)

Dimensions: $t = .0692''$
 $A = .0828'' \times .0811''$

Prior to remaining at 700°C for 40 minutes:

T	500°	548°	603°	660°	715°	770°
σ	8.14×10^{-9}	1.43×10^{-8}	3.69×10^{-8}	8.98×10^{-8}	1.99×10^{-7}	4.33×10^{-7}
T	825°	880°	937°			
σ	1.00×10^{-6}	3.89×10^{-6}	1.53×10^{-5}			

After remaining at 700°C for 40 minutes:

T	909°	855°	801°	748°	693°	638°
σ	7.54×10^{-6}	1.65×10^{-6}	5.36×10^{-7}	2.36×10^{-7}	934×10^{-8}	3.73×10^{-8}
T	585°	533°				
σ	1.54×10^{-8}	3.93×10^{-9}				

Plot VI. KCl sample from Harshaw. (Crystal left at 650°C for one hour)

Dimensions: $t = .1348''$
 $A = .1420'' \times .1564''$

Prior to remaining at 650°C for one hour:

T	476°	557°	642°	722°	802°	884°
σ	2.81×10^{-10}	2.52×10^{-9}	1.14×10^{-8}	3.49×10^{-8}	2.62×10^{-7}	3.39×10^{-6}
T	911°					
σ	3.64×10^{-6}					

After remaining at 650°C for one hour:

	211°	82°	745°	659°	576°	508°
σ	6.88×10^{-6}	7.4×10^{-7}	8.30×10^{-8}	2.08×10^{-8}	4.93×10^{-9}	1.36×10^{-10}

From the data and plots the following results seem to be indicated:

1. The results are the same with the new crystal holder as with the holder used by Mr. Aschner and Mr. Compton and, since great care was taken to see that the holder used here was very clean, it seems that the source of change in conductivity is not due to an introduction of impurities by the holder.


2. The change in conductivity is not apparent unless the crystal is left at temperatures above 400°C for periods of thirty minutes or longer. This was noted for all types of crystals used. This would seem to indicate that either a chemical reaction is occurring that can only take place at higher temperatures or that some plastic deformation is taking place in the crystal. However, it was noted that no measurable change in crystal dimensions occurred. The dimensions of the crystals were measured just prior to and just after each conductivity run.


3. The change in conductivity is more apparent in the KCl crystals than in the NaCl crystals.


4. Two possible sources of impurity introduction still have not been investigated. The Helium supply, although believed to be very clean from other considerations, could be filtered as a check on a source of impurity introduction. Also, the method of putting electrodes on the crystals should be investigated. A method other than painting with "Dag" might yield fruitful results.


5. The holder used here was used for about 20 conductivity runs over a period of about four months and has not given any electrical or mechanical trouble. Thus it seems to have better operational characteristics than the crystal holder previously used.


*"Dag" - Dispersion No. 154 (Graphite in Alcohol) Acheson Colloids Corporation.














TECHNICAL REPORTS DISTRIBUTION LIST

University of Illinois
Contract N6onr-07129
NR 017-412

A. Government Distribution

Department of Defense

Research and Development Board
Pentagon Building
Washington 25, D. C. (2 copies)

Department of the Navy

Chief of Naval Research
Office of Naval Research
Washington 25, D. C.
Attn: Physics Branch (2 copies)

Director, Naval Research Laboratory
Washington 20, D. C.
Attn: Technical Information Officer (9 copies)

ONR, Branch Offices

Commanding Officer
U. S. Navy Office of Naval Research
Branch Office
346 Broadway
New York 13, New York (1 copy)

Commanding Officer
Office of Naval Research
Branch Office
The John Crear Library Building
Tenth Floor, 86 E. Randolph Street
Chicago 1, Illinois
Telephone: Central 6-4288

Commanding Officer
U. S. Navy Office of Naval Research
Branch Office
801 Donahue Street
San Francisco 24, California (1 copy)

Commanding Officer
U. S. Navy Office of Naval Research
Branch Office
1030 East Green Street
Pasadena 1, California (1 copy)

Government Distribution List continued

Office of Assistant Naval Attache for Research
Navy No. 100, Fleet Post Office
New York, New York (2 copies)

Director
Naval Research Laboratory
Washington 20, D. C.
Attn: Code 2021 (1 copy)

Chief of Bureau of Aeronautics
Navy Department
Washington 25, D. C. (1 copy)

Chief of Bureau of Ordnance
Navy Department
Washington 25, D. C.
Attn: Code REA (1 copy)

Chief of Bureau of Ships
Navy Department
Washington 25, D. C.
Attn: Code 330 (1 copy)

Department of the Air Forces

Army Air Forces
War Department
Washington 25, D. C.
Attn: A.E./A.S. -2 Collection Branch (1 copy)

Department of the Army

Chief, Engineering and Technical Division
Office of the Chief Signal Officer
SIGTM-5 - The Pentagon
Washington 25, D. C. (1 copy)

Department of Commerce

Director
National Bureau of Standards
Washington 25, D. C. (1 copy)

National Research Council
Division of Physical Sciences
2101 Constitution Avenue
Washington 25, D. C. (1 copy)

Dr. L. R. Maxwell
Naval Ordnance Laboratory
Silver Spring, Maryland (1 copy)

Government Distribution List continued

Los Alamos Scientific Laboratory
Los Alamos, New Mexico
Attn: Dr. Calvin Potts (1 copy)

B. Non-Government Distribution

Brown University
Department of Physics
Providence, Rhode Island
Attn: H. E. Farnsworth (1 copy)

Case School of Applied Science
Department of Physics
Cleveland, Ohio
Attn: E. C. Crittenden, Jr. (1 copy)

Cornell University
Department of Physics
Ithaca, New York
Attn: Lloyd P. Smith (1 copy)

Director, Research Laboratory of Electronics
Massachusetts Institute of Technology
Cambridge 39, Massachusetts
Attn: J. A. Stratton (1 copy)

Director of Laboratory for Insulation Research
Massachusetts Institute of Technology
Cambridge 39, Massachusetts
Attn: A. Von Hippel (1 copy)

Oregon State College
Department of Chemistry
Corvallis, Oregon
Attn: Dr. A. B. Scott (1 copy)

California Institute of Technology
Division of Chemistry and Chemical Engineering
Pasadena, California
Attn: Dr. L. Pauling (1 copy)

University of California
Department of Physics
Berkeley, California
Attn: Leonard B. Loeb (1 copy)

Non-Government Distribution List continued

University of Pennsylvania
Department of Physics
Philadelphia Pennsylvania
Attn: W. E. Stephens (1 copy)
 H. B. Callen (1 copy)
 F. C. Hix (1 copy)

Washington State College
Department of Physics
Pullman, Washington
Attn: P. A. Anderson (1 copy)

Smith College
Department of Chemistry
Northampton, Massachusetts
Attn: Dr. G. S. Dunham (1 copy)

Dr. E. Billig, Head
General Physics Department
Associated Electrical Industries, Ltd.
Aldermaston, Berkshire, England
Via: Office of the Assistant Naval
 Attache for Research
 Navy No. 100
 Fleet Post Office
 New York 4, New York (1 copy)

Ohio State University
Department of Physics
Columbus 10, Ohio
Attn: Dr. P. M. Harris (1 copy)

Dr. R. J. Maurer
Department of Physics
University of Illinois
Urbana, Illinois (1 copy)

Dr. Frederick Seitz
Department of Physics
University of Illinois
Urbana, Illinois (1 copy)

Dr. Karl Lark-Horovitz
Purdue University
Department of Physics
Lafayette, Indiana (1 copy)

Dr. L. W. McKeehan
Yale University
Sloane Physics Laboratory
New Haven, Connecticut (1 copy)

Non-Government Distribution List continued

**Dr. R. C. Hermann
8621 Georgia Avenue
Applied Physics Laboratory
The Johns Hopkins University
Silver Spring, Maryland**

Note: In those cases where an ONR Resident Representative has cognizance of the contract, one copy of the technical report should be sent to the Representative.