

AD-234 926

RIA-77-U83

# SPRINGFIELD ARMORY

RESEARCH AND DEVELOPMENT



TECHNICAL  
LIBRARY

Report: SA-TR18-1070

Date: 12 February 1960

Report Title: A Determination of the Distribution of Chromium Plate in the  
Bores of Small Arms Barrels.

Author:

M. S. Spivak  
M. S. Spivak  
Chem Engr

Approved:

H. F. Hawthorne  
H. F. Hawthorne  
Chief, Res and Dev Div

MASTER FILE  
DO NOT REMOVE

SPRINGFIELD, MASSACHUSETTS

Report: SA-TR18-1070

Date: 12 February 1960

Report Title: A Determination of the Distribution of Chromium Plate in the Bores of Small Arms Barrels.

Author:

*M. S. Spivak*

M. S. SPIVAK  
Chem Engr.

Approved:

*H. F. Hawthorne*

H. F. HAWTHORNE  
Chief, Res and Dev Div

Project Title: Engineering for the Application of Chromium Plating of Small Arms Barrel Bores.

Ord Project: Industrial Preparedness Measure

DA Project: None

Preparing Agency: Springfield Armory  
Springfield, Mass.

This report has no distribution limitations. Initial distribution of this report has been made in accordance with the attached distribution list. Requests for additional copies of this report will be made to ASTIA.

ABSTRACT

AD

Accession

UNCLASSIFIED

Springfield Armory, Springfield, Mass.

A DETERMINATION OF THE DISTRIBUTION OF CHROMIUM PLATE  
IN THE BORES OF SMALL ARMS BARRELS, M. S. Spivak, Tech  
Rpt SA-TR18-1070, 12 Feb 60, 13 pp incl illus, Ord Proj -  
Industrial Preparedness Measure.

Unclassified Report.

Nonlimited distribution.

1. Chromium Plating -  
Distribution
2. Plating, Chromium
3. Gun barrels -  
Plating

An investigation was made to develop a method for the determination of the distribution of chromium plate in the bores of small arms barrels. Barrels of various calibers were chromium plated according to Springfield Armory procedures. These barrels were then sectioned and the chromium thickness was measured at the lands and grooves. Graphs were plotted of groove chromium thickness versus land chromium thickness for the various barrels. Ratios of land-to-groove chromium plating thicknesses have been established for calibers 0.30, 0.45, 0.50, 20mm, and 30mm barrel bores. These ratios apply to barrel bores which have been chromium plated under existing plating procedures used at Springfield Armory. Procedures are described and results discussed.

UNCLASSIFIED

FOR READER'S USE - DO NOT REMOVE



**SUBJECT**

**A determination of the Distribution of Chromium Plate in the Bores of Small Arms Barrels.**

**OBJECT**

**To determine the ratio of chromium deposited on the lands to that deposited on the grooves in small arms barrels, thereby providing a means of calculating the chrome thickness on either segment when only one has been measured.**

**SUMMARY**

**1. Various caliber barrels were chrome plated according to existing Springfield Armory procedures, and then sectioned to permit measurement of chromium thickness at the lands and grooves. A graph of Groove Chromium Thickness VS Land Chromium Thickness for the various barrels was plotted, thereby permitting the determination of the land-to-groove ratio for each barrel tested.**

**2. Copper and steel anodes were used in the plating procedures.**

**REPORT**  
**SA-TR18-1070**

1. INTRODUCTION

- a. Existing methods employed at the Springfield Armory for inspection of barrel bores and gaging of chromium plating thickness depend on measurement of the bore diameter (at the lands) after the lands and grooves have been electropolished, and again, after they have been chrome-plated. One half of the differential in readings is accepted as being representative of the amount of chromium deposited in the bore. Chromium thickness on the grooves is not measured. It has been found, however, that groove information is highly desirable.
- b. It was necessary to develop a method for determining the thickness of chromium deposited in the grooves without involving redesign of gages or modification of the plating procedure.
- c. A possible method is the establishment of a ratio of groove-to-land thickness (providing that variations in plating procedure are taken into account) for each caliber barrel.

2. MATERIALS AND EQUIPMENT

a. Barrels:

Barrels of various sizes ranging from .30 caliber to 30mm on the bore diameter.

b. Plating:

- (1) Generator (12 volt)
- (2) Steel and Copper electrodes between 1/8 inch and 3/8 inch diameter.
- (3) Standard electropolishing and chromium plating solutions. See Tables I and II for compositions.

**REPORT**  
**SA-TR18-1070**

**2. MATERIALS AND EQUIPMENT - Continued**

(4) Air gages, electropolishing and electroplating, for each caliber barrel.

(5) Fixtures

**c. Metallographic:**

(1) Saw (metal cutting, automatic)

(2) Grinding Machine

(3) Abrasive papers of various grit size.

(4) Wax finishing wheel

(5) Lucite mounting material

(6) Mount compressor

(7) Metal etchant

(8) Microscope

**3. PROCEDURE**

**a. Electropolishing and Plating**

All barrels were electropolished, and plated in the standard solutions. (See Tables I and II). The amount of chromium deposited during electro-plating was approximately equal to the amount of steel removed during electropolishing. The barrels were gaged after each procedure. Gaging methods used were those currently practiced at the Springfield Armory.



TABLE I

Composition of Chrome Plating Solution

* Constituent	Composition	
	oz/gal	g/l
Hexavalent Chromium (Calc. as $\text{CrO}_3$ )	29.0	218.0
Trivalent Chromium (Calc. as $\text{CrO}_3$ )	3.4	26.0
Sulfate (Calc. as $\text{H}_2\text{SO}_4$ )	0.34	2.6
Iron	0.40	3.0

$$\begin{array}{l} \text{* Chromic Acid} = \frac{104}{\text{Sulphate} \quad 1} \end{array}$$

TABLE II

\* Composition of Electropolishing Solution

Constituent	Per cent Composition
Sulphate	34.10
Phosphate	37.09
Iron	1.93

$$\text{* Specific Gravity at } 75^\circ\text{F} = 1.67$$



REPORT  
SA-TR18-1070

3. PROCEDURE - Continued

b. Sectioning

Two or more representative sample sections of each plated barrel were submitted for investigation. The section faces were ground perpendicular to the plated surfaces, and submitted to metallographic procedures. All sections were etched with a 5% Nital solution.

c. Determination of Thickness

Thickness of chromium deposit was determined by microscopic measurement using magnifications of 250X and 1,000X. Land and groove thicknesses were measured consecutively around the interior perimeter of the sample sections; the number of lands and grooves varied with bore size (See Table III). The thickness measurements were then averaged (See Table IV), and the mean of each section was taken as representative of the chromium thickness (See Figures 1, 2, and 3).

TABLE III

Number of Lands and Grooves  
in Various Barrel Bores

Barrel	No. of Lands	No. of Grooves
.30 Caliber	4	4
.45 Caliber	6	6
.50 Caliber	8	8
20mm	9	9
30mm	16	16

4. DISCUSSION OF RESULTS

- a. The results of Figures 1, 2, and 3 indicate that, in general, the ratio of groove-to-land chromium thickness (less than '1" in all of the barrels

TABLE IV

Average Thicknesses of Chromium Plate in Barrel Bores

Type Bbl.	Anode Used	Av. Thickness of Chromium on the Land Thickness ( $10^{-3}$ inches)	Av. Thickness of Chromium on the Groove Thickness ( $10^{-3}$ inches)
.30 Cal.	Steel	3.80	3.13
		3.05	2.64
		2.43	2.07
		3.52	2.80
		5.21	4.71
		5.75	4.72
		9.48	8.44
		9.74	8.62
.30 Cal.	Copper	1.70	1.19
		2.08	1.45
		5.37	4.39
		5.75	5.09
		11.30	9.87
		11.42	9.91
.45 Cal.	Steel	1.32	1.06
		1.42	1.11
		1.57	1.26
		1.57	1.28
		5.28	4.84
		1.04	1.00
		5.69	4.95
		6.44	5.88
		6.53	5.86
		1.03	.97
		1.82	1.63

REPORT  
SA-TR18-1070

TABLE IV - Continued

Average Thicknesses of Chromium Plate in Barrel Bores


Type Bbl.	Anode Used	Av. Thickness of Chromium on the Land Thickness ( $10^{-3}$ inches)	Av. Thickness of Chromium on the Groove Thickness ( $10^{-3}$ inches)
.45 Cal.	Steel	6.80	5.97
		7.25	6.61
		8.55	7.58
.50 Cal.	Steel	1.66	1.28
		1.78	1.37
		5.00	4.35
		5.08	4.17
		9.70	7.80
20mm	Steel	2.01	1.38
		2.02	1.43
		3.71	2.65
		3.83	2.61
		5.17	3.61
		5.18	3.58
		8.62	5.68
		8.62	5.96
		10.25	7.41
20mm	Copper	10.25	7.55
		1.78	1.14
		1.87	1.26
		3.80	2.88
		5.20	3.95
		5.87	4.35




TABLE IV - Continued

Average Thickness of Chromium Plate in Barrel Bores


Type Bbl.	Anode Used	Av. Thickness of Chromium on the Land Thickness ( $10^{-3}$ inches)	Av. Thickness of Chromium on the Groove Thickness ( $10^{-3}$ inches)
30mm	Steel	1.75	1.15
		3.93	2.82
		4.04	2.87
		4.25	3.00
		6.60	4.60
		2.31	7.43
		2.34	1.53
		2.92	1.92
		2.93	1.94
		5.30	3.44
		10.47	6.60
		10.62	6.70













4. DISCUSSION OF RESULTS - Continued

examined) decreases as the barrel size increases. The exception to this pattern appears in the case of the .45 caliber barrels, where the curve approximates that of the .30 caliber barrel.

- b. Anode material (copper or steel) appears to have little effect on the groove-to-land chromium thickness ratio.

5. CONCLUSIONS

The ratio of land-to-groove chromium plating thickness has been established (See Figures 1, 2, and 3) for .30 caliber, .45 caliber, .50 caliber, 20mm, and 30mm barrel bores. The ratios apply to barrel bores which have been chromium plated under existing plating procedures used at the Springfield Armory.

6. RECOMMENDATIONS

A study should be made to determine the change of inside diameter of the bores (measured at the grooves) resulting from the difference of steel removal during electropolishing and chromium deposited during plating.

This report was edited under Contract DA-19-020-504-ORD-4800 by Associated Engineers, Inc., from technical data compiled by Springfield Armory.

DISTRIBUTION

Copies

✓ Chief of Ordnance  
Department of the Army  
Washington 25, D. C.  
ATTN: ORDTB (1)  
ORDIR (1)

2

✓ Commanding General  
Ordnance Weapons Command  
Rock Island, Illinois  
ATTN: ORDOW-FM (1)  
ORDOW-TX (1)  
ORDOW-PEQUA (1)  
ORDOW-IE (1)

4

✓ Commanding Officer  
Diamond Ordnance Fuze Laboratories  
Washington 25, D. C.  
ATTN: Technical Reference Section  
ORDTL 06.33

1

✓ Armed Services Technical Information Agency  
Arlington Hall Station  
Arlington 12, Virginia

10

✓ Commanding Officer  
Detroit Arsenal  
Center Line, Michigan

1

✓ Commanding Officer  
Frankford Arsenal  
Philadelphia, Pennsylvania  
ATTN: Pitman-Dunn Laboratory (1)  
Small Arms Division (1)

2

(1)



**REPORT**  
**SA-TR18-1070**

**DISTRIBUTION - Continued**

	<u>Copies</u>
✓ Commanding Officer Picatinny Arsenal Dover, New Jersey ATTN: ORDBB-TM2	2
✓ Commanding General U. S. Army Ordnance Arsenal Redstone Arsenal, Alabama	2
✓ Commanding Officer Rock Island Arsenal Rock Island, Illinois ATTN: Laboratory	1
✓ Commanding Officer Watertown Arsenal Watertown, Massachusetts ATTN: Laboratory (1) Ordnance Materials Research Office (1)	2
✓ Commanding Officer Watervliet Arsenal Watervliet, New York ATTN: Laboratory	1
✓ Commanding General Aberdeen Proving Ground Aberdeen, Maryland ATTN: ORDBG-DPD	2

**DISTRIBUTION - Continued**

**Copies**

✓ Commanding General Fort Monmouth, New Jersey ATTN: Signal Corps Engineering Laboratory Squier Signal Laboratory - Materials Section	1
✓ Commanding General Fort Belvoir, Virginia ATTN: Research and Development Laboratories Materials Branch	1
✓ Commanding Officer Office of the Quartermaster General Washington 25, D. C. ATTN: Research and Development Division Chemicals and Plastics Branch	1
✓ Commanding Officer Office of Ordnance Research Post Office Box CM, Duke Station Durham, North Carolina	1
✓ President, U.S. Army Infantry Board United States Continental Army Command Fort Benning, Georgia	1
✓ President, U.S. Army Armor Board United States Continental Army Command Fort Knox, Kentucky	1
✓ Commanding General U.S. Army Ordnance Special Weapons Ammunition Command Dover, New Jersey	1

REPORT  
SA-TR18-1070

DISTRIBUTION - Continued

Copies

✓ Commander  
✓ Air Materiel Command  
Engineering Division, Materials Laboratory  
Wright-Patterson Air Force Base, Ohio

1

✓ Commander  
✓ Air Proving Ground Center  
Eglin Air Force Base, Florida  
ATTN: PGTRI, Tech. Lib.

1

✓ Commander  
✓ Air Research and Development Command  
Andrews Air Force Base  
Washington 25, D. C.  
ATTN: RDT-DAG

1

✓ Chairman, National Aeronautics and Space Administration  
Lewis Research Center  
21,000 Brookpark Road  
Cleveland 35, Ohio

1

✓ Director, Office of Naval Research  
Department of the Navy  
Washington 25, D. C.  
ATTN: Code 423

1

✓ Chief, Bureau of Aeronautics  
Department of the Navy  
Airborne Equipment Division  
Washington 25, D. C.  
ATTN: Materials Branch, Code AE-44

1



DISTRIBUTION - Continued

Copies

✓ Commander U.S. Naval Ordnance Laboratory Department of the Navy 8050 Georgia Avenue Silver Spring, Maryland ATTN: Code WC-1	1
✓ Chief, Bureau of Ships Department of the Navy Washington 25, D. C. ATTN: Research and Development Division - Code 346 (1) Material Development Division - Code 345 (1)	2
✓ Director U.S. Naval Research Laboratory Washington 20, D. C. ATTN: Technical Information Officer	1
✓ Chief, Bureau of Ordnance Department of the Navy Washington 25, D. C. ATTN: Research and Development Division Materials and Handling Branch - Code Re-1	1
✓ Commander, U.S. Naval Air Experimental Station Building 600 Philadelphia 12, Pennsylvania	1
✓ Superintendent U.S. Naval Weapons Plant Washington 25, D. C.	1

REPORT  
SA-TR18-1070

DISTRIBUTION - Continued

Copies

COPIES OF THIS UNCLASSIFIED REPORT WERE TRANSMITTED BY  
SPRINGFIELD ARMORY DIRECT TO THE FOLLOWING ADDRESSEES:

✓ Director, National Bureau of Standards  
Department of Commerce  
Washington 25, D. C.  
ATTN: Electrodeposition Section  
Division of Chemistry

1

✓ Associated Engineers, Inc.  
1 Silver Street  
Agawam, Massachusetts  
ATTN: Mr. A. J. Rettie, Project Engineer  
Mr. E. M. Pietras, Technical Writer

2

TWO COPIES OF THIS REPORT WERE TRANSMITTED BY SPRINGFIELD  
ARMORY TO THE FOLLOWING ADDRESSEE BY SPECIAL COVER LETTER  
IN ACCORDANCE WITH OCTI-200-4-57, PAR. 9a:

✓ Office of Technical Services  
Department of Commerce  
Washington 25, D. C.  
ATTN: Acquisitions Sections

2