

Reproduced by the

CA. Warvena A. S. Alan

ARMED SERVICES TECHNICAL INFORMATION AGENCY ARLINGTON HALL STATION ARLINGTON 12, VIRGINIA





NOTICE: When government or other drawings, specifications or other data are used for any purpose other than in connection with a definitely related government procurement operation, the U. S. Government thereby incurs no responsibility, nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use or sell any patented invention that may in any way be related thereto.

63-2-2

TECHNICAL INFORMATION SERIES

294 885

R6ISDI45

H.L.FRIEDMAN

AdU

THE KINETICS OF THERMAL DEGRADATION OF CHARRING PLASTICS

I. GLASS REINFORCED PHENOLFORMALDEHYDE

ITERS IEU IL ETA

SPACE SCIENCES LABORATORY

B 3 6 0

MISSILE AND SPACE DIVISION

SPACE SCIENCES LABORATORY

AEROPHYSICS OPERATION

THE KINETICS OF THERMAL DEGRADATION OF CHARRING PLASTICS*

I. GLASS REINFORCED PHENOL-FORMALDEHYDE

By

Henry L. Friedman⁺

 * This work was performed under the auspices of the U. S. Air Force Space Systems Division, Contract No. AF 04(647)-269.

+ Physical Cnemist, Polymer Degradation Chemistry

R61SD145 August, 1961

;

MISSILE AND SPACE DIVISION



	т	_
L	TABLE OF CONTENTS	PAGE
T	Abstract	ii '
	Introduction	1
	Experimental	2
	Kinetic Analysis	5
	Tests of the Kinetic Equation	9
	Discussion	12
	Summary	16
	Acknowledgements	17
	References	18
	Tables	19
	Figures	21

.

ABSTRACT

A technique was devised for obtaining rate laws and kinetic parameters which describe the thermal degradation of plastics from thermogravimetric analysis data. The method is based on the intercomparison of experiments which were performed at different linear rates of temperature rise.

The method was applied to a fiberglass reinforced phenolformaldehyde resin. The kinetic equation that was thus derived was checked by a variety of techniques, including a comparison with constant temperature data that were available in the literature. The tests indicated that the equation was applicable to a major part of the degradation process.

THE KINETICS OF THERMAL DEGRADATION OF CHARRING PLASTICS*

I. GLASS REINFORCED PHENOL-FORMALDEHYDE

Henry L. Friedman

Introduction

Kinetics of thermal degradation of solids have been evaluated from thermogravimetric analysis (TGA) at linear rates of temperature rise in a number of studies. van Krevelen, van Heerden, and Huntjens¹ studied the decomposition of coal. Freeman and Carroll² investigated the degradation of calcium oxalate monohydrate. Their technique was applied to the decomposition of a styrenated polyester by Anderson and Freeman³, and was modified by the same authors⁴ for polystyrene and polyethylene. Doyle⁵ studied the degradation of a large number of plastics. Friedman⁶ investigated the decomposition of a glass reinforced phenol-formaldehyde. A more sophisticated approach will be used in the present paper, than was employed for the earlier work.

In all of the earlier studies, calculations were based on experiments which were performed at a single rate of temperature rise. In the present paper, kinetic calculations are based on an intercomparison of experiments which were carried out at several different rates of temperature rise.

^{*} This work was performed under the auspices of the U. S. Air Force Space Systems Division, Contract No. AF 04(647)-269.

Experimental

Fiberglass reinforced CTL 91-LD Phenolic (a product of Cincinnati Testing and Research Laboratory) was used for this study. The laminate was prepared from resin impregnated glass sheets that were supplied by U. S. Polymeric Chemicals, Inc. The sheets, which originally consisted of 42 weight per cent resin, were B-staged in a 200°F oven for one hour. They were then cured in a 225°F press at 100 p.s.i. for 15 minutes, followed by 265°F at 100 p.s.i. for three hours. The cured laminate was allowed to cool to room temperature in the press, and was then post cured in a 265°F oven for 16 hours.

In order to prepare TGA samples, the surface layers were split off and discarded. The underlying material was converted to thin flakes by end milling under liquid nitrogen. The flakes were dried in a desiccator overnight, and were further dried by holding the sample in a porcelain crucible in the Chevenard Thermobalance for one hour at 100°C just before TGA was allowed to commence. Samples lost less than one per cent of their original weight during the preconditioning period.

Four 200 mg samples of the flakes were subjected to TGA at linear heating rates of 50, 100, 180, and 360^OC/hr. Degradation was carried out in a stream of dry nitrogen to maximum temperature

of 900°C. After TGA was completed, the residue from each test was burned in air at 1000°C until only glass remained. Original resin contents were found to range from 35.0 to 36.1 weight per cent.

Residual weight fractions of organic material were calculated on a glass-free basis, and are shown as a function of temperature in Figure 1. Note that the curves are displaced to higher temperatures with increased heating rate, as would be predicted from kinetic theory. Rates of weight loss are plotted as a function of time and temperature in Figure 2. Rates were measured from enlarged graphs of Figure 1 with a Gerber Derivimeter. All of the rate curves had the same general shape. Slow weight loss commenced almost immediately and continued to above 300°C. Between 300 and 400°C, the rate of loss of weight increased as the temperatures were elevated, reached a maximum in the vicinity of 500°C and then decreased for the remainder of the heating period. Inspection of Figure 2 shows that there are a number of hills and valleys in the rate curves. Since they vary markedly from curve to curve, they are thought to be caused by scatter of the TGA data rather than indications of changes in the degradation process.

The early weight loss accounted for less than 10 per cent of the total loss, and appeared to be associated with a different process. It was, therefore, decided to eliminate this portion from the kinetic analysis. An arbitrary initial weight of plastic was

chosen from the TGA data at a temperature between 300 and 400°C where examination of the rate curves showed that the major weight loss process appeared to begin. Although it was likely that the main degradation process started at somewhat lower temperatures, and that the early degassing process continued to higher temperatures, it was felt that the errors associated with rate measurements would be far more serious than errors caused by a reasonable estimate of initial weight. Figure 3 shows residual weight fractions of organic material, with the early weight loss process eliminated.

Kinetic Analysis

The following very general kinetic equation was assumed to hold for this material.

$$\frac{1}{w_0} \frac{dw}{dt} = A e^{-\Delta E/RT} f(w/w_0)$$
(1)

where w = weight of organic material.

 w_0 = original weight of plastic.

t = time, hrs.

ŧ

A = pre-exponential factor of rate constant, hr.⁻¹.
 ∠E = activation energy of rate constant, cal./mole.
 R = gas constant, 1.987 cal./^oK mole.
 T = absolute temperature, ^oK.

f (w/w_0) = a function of the weight of organic material. Taking logarithms of (1) gives

$$\ln \left(-\frac{1}{w_{o}} \frac{dw}{dt}\right) = \ln A + \ln f \left(w/w_{o}\right) - \frac{\triangle E}{RT}$$
(2)

f (w/w₀) is assumed to be constant for constant values of w/w₀. This is comparable to assuming that the chemistry of the process is independent of temperature, and is dependent only on the instantaneous weight of the organic material. A dozen values of w/w₀ were selected, ranging from 0.675 to 0.950, at equal intervals. Values of $(1/w_0)$ (dw/dt) and T were determined for each w/w₀ for each TGA experiment.

Plots of ln $(-1/w_0)$ (dw/dt) vs. 1/T are shown for each value of w/w_0 in Figure 4. The slope of each line is equal to $-\triangle E/R$, while the intercept is $\ln / A \propto f (w/w_0) / J$. The lines of Figure 4 were obtained from least squares treatments of the data. $\triangle E$'s and $\ln / A \propto f (w/w_0) / s$ are plotted as functions of w/w_0 in Figure 5. \triangle E varies from 50 to 72 kcal/mole. The range of variation that is associated with each point represents only the probable error of the points based on the least squares treatment. The real errors are larger. Note, however, that trends in the values of $\triangle E$ and $\ln / A \propto f (w/w_0) / are identical. This indicates that$ a positive error in A, which would make the reaction appear to go faster, is compensated for by a positive error in $\triangle E$, which would tend to make the reaction appear to go slower. Negative errors would balance in the reverse way. Thus it appears that the kinetics of the overall process are consistent.

The 12 different $\triangle E$'s were averaged to give 57.7 kcal. Experimental parameters and the $\triangle E$ were substituted in (2) to give 48 values of $\ln [A \ge f(w/w_0)]$. Average $\ln [A \ge f(w/w_0)]$ is are plotted as a function of w/w_0 in Figure 6. The range associated with each point is the standard deviation of the average of four values. The smooth curve in Figure 6 tended to confirm that the kinetics of the overall process were consistent. $f(w/w_0)$ was assumed to have the form

$$f(w/w_0) = \left(\frac{w - w_f}{w_0}\right)^n$$
(3)

where $w_f = final$ weight of char.

n = kinetic order of the reaction.

w - wf is a measure of the amount of material which is available for decomposition at any instant of time, and is a convenient mathematical form which allows the degradation to be completed when all of the original plastic is converted to char. Equation (3), or very similar forms, can be derived from theory for processes where a solid reactant is converted to a constant ratio of gaseous and solid products. Multiplying both sides of (3) by A and taking logarithms,

$$\ln \int A \times f (w/w_0) = \ln A + n \ln \left(\frac{w - w_f}{w_0}\right)$$
(4)

If the assumed form of f (w/w_0) is correct, then a plot of $\ln \int A \ge f (w/w_0) \int vs. \ln \int (w - w_f)/w_0 \int should give a straight$ line where the slope is n and the intercept is $\ln A$. This type of plot is shown in Figure 7. A straight line resulted for all values of the abscissa below - 1.3 (equivalent to w/w_0 below 0.9). The positive deviation at higher weights could be attributed to contributions of the early weight loss process. In calculating values of $(w - w_f)/w_0$, it was necessary to assume a value of w_f . Examination of Figure 3 indicated that decomposition was essentially completed at 900°C, so the convenient average value of $w_f/w_o = 0.61$ was selected. Calculations based on Figure 7 showed that n = 5.0 and A = 5.98 x 10¹⁸ hr.⁻¹. The form of the overall kinetic equation is

$$-\frac{1}{w_0} \frac{dw}{dt} = k \left(\frac{w - w_f}{w_0}\right)^5$$
(5)
where $k = A e^{- \triangle E/RT}$, hr.⁻¹.

.

Tests of the Kinetic Equation

Three different tests were made on the applicability of equation (5). The first was an examination of Arrhenius plots for the individual runs. k's were calculated from (5) by using the values of the other terms which were calculated earlier in the paper. w_f/w_o was assumed to be 0.61 for all but the 100°C/hr. run, where the value of 0.59 was employed. Arrhenius plots of the four runs are shown in Figure 8. The lines are based on visual inspection of the data. The $\triangle E$'s and A's which were derived from the lines are listed in Table 1. Note that the values of k are higher than the Arrhenius lines at the lowest temperatures. This is thought to be due to the early weight loss process, and is comparable to the deviations from linearity in Figure 6. The method of least squares was applied to all the data of Figure 8, except for the two lowest temperatures of each TGA run. $\triangle E$ was found to be 55 kcal, while A is 10¹⁸ hr.⁻¹. These values will be used for all further calculations.

The second test is based on the fact that at the maximum (-dw/dt), the second derivative $(-d^2w/dt^2)$ is equal to zero. Since the heating rate is linear

$$\frac{dT}{dt} = \rho$$
(6)
where ρ = heating rate, ^oC/hr.

Substituting (6) in (5) and rearranging gives

$$-\frac{dw}{dt} = \frac{A}{\rho_{w_0}4} e^{-\Delta E/RT} (w - w_f)^5$$
(7)

Taking derivatives of (7)

$$-\frac{d^2 w}{dT^2} = \frac{A}{\rho} \left(\frac{w - w_f}{w_o}\right)^4 e^{-\Delta E/RT} \left[5 \frac{dw}{dT} + (w - w_f) \frac{\Delta E}{RT^2}\right]$$
(8)

-

For $(-d^2w/dT^2) = 0$ at the maximum rate

$$5 \frac{\mathrm{d}\mathbf{w}}{\mathrm{d}\mathbf{T}} + (\mathbf{w} - \mathbf{w}_{\mathbf{f}}) \frac{\Delta \mathbf{E}}{\mathbf{R}\mathbf{T}_{\mathbf{m}}^{\mathbf{Z}}} = 0$$
(9)

where T_m = temperature at maximum rate, $^{O}K_{\bullet}$

(9) may be arranged to

$$\underline{\frown}_{E} = \frac{5RT_{m}^{2} (-dw/dT)}{w - w_{f}}$$
(10)

1

The four values of $\triangle E$ which were calculated from (10) are listed in Table 1.

The third test was to derive the individual TGA curves from equation (5). (5) was rearranged for integration to give

$$-\int_{W_0}^{W} \frac{\mathrm{d}W}{(W-W_0)^5} = \frac{A}{\rho_{W_0}^4} \int_{T_0}^{T} e^{-\triangle E/RT} \,\mathrm{d}T \tag{11}$$

where w_0 = the arbitrary choice of initial weight of plastic. T_0 = temperature at w_0 , ${}^{O}K_{\bullet}$ Integration and solution for w gives

$$w = w_{f} +$$
(12)
$$\frac{\rho^{0.25} w_{o} (w_{o} - w_{f})}{\rho^{w_{o}^{4}} + 4A (w_{o} - w_{f})^{4} \left[T e^{-\Delta E/RT} - T_{o} e^{-\Delta E/RT_{o}} + \right]}$$

$$\frac{\Delta E}{R} \left(\int_{v_{o}}^{\infty} \frac{e^{-v}}{v} dv - \int_{v}^{\infty} \frac{e^{-v}}{v} dv \right) \right]^{0.25}$$

where $v = \triangle E/RT$ and $v_0 = \triangle E/RT_0$.

Solutions for the integrals which appear in (12) are tabulated in several sources^{7,8}. Reference⁸ was used for this work. Figure 9 shows a typical thermogram that was derived by this technique. Note that in the lower temperature range the experimental curve shows a higher weight loss than the theoretical curve. This was expected, since the kinetic analysis and Arrhenius plots had both shown that the early weight loss process continues after temperatures which are greater than T_0 .

A plot of actual vs. calculated w/w_0 's for all TGA curves is shown in Figure 10. Note that the deviations from the 45^o line at the higher mass end are rather systematic. The curve that is shown may be used to correct calculated values of w in the region where the early weight loss process is important.

Discussion

The various tests of equation (5) showed that the kinetic analysis of CTL 91-LD phenolic degradation that was formulated in this paper is reasonable for a large part of the decomposition The main deviation between experiment and analysis process. occurred during early degradation, where the actual weight loss exceeded the calculated loss. The earliest weight loss can probably be attributed to desorption of adsorbed gases. The resin was probably not completely cross-linked at the point where TGA started. As heating continued, further cross-linking probably occurred, and further weight loss could be attributed to the evolution of some condensation products. Since degradation probably started before cross-linking was completed, there is probably no simple value for wo, in the way that it was used. Examination of Figure 9 shows that a slightly lower would make the theoretical curve fit the experiment better. It is altogether reasonable, when one considers the argument that was presented above, that the effective wo be lower than the chosen value. It is also not surprising that the theoretical weight at 900°C is slightly higher than the experimental figure. Adjustments could probably be made in the choice of both wo and w_f, so that very accurate theoretical TGA curves would result, except for the very earliest weight loss processes.

A fifth order weight dependence is unusual for polymer degradation. Of course, order does not mean the same thing in this type of process as it does for a gas or a solution. Since this resin is a highly cross-linked material, it is likely that the high order was associated with a rather complex mechanism which occurred in the solid state. Note, however, that a preexponential factor of about 3×10^{14} sec.⁻¹ and an activation energy of 55 kcal. are not unusual for some thermoplastics.

Inspection of the low temperature end of the TGA curves showed that very low activation energies could be attributed to that part of the decomposition. In the earlier kinetic analysis⁶, this author studied TGA experiments which were performed only at 180°C/hr. on a sample where the resin content had not been determined. Since that analysis covered temperatures ranging between 404 and 524°C, it is reasonable that an activation energy of 15 kcal. was calculated. Madorsky and Straus^{9,10} investigated the thermal degradation of this material in vacuum and at constant temperature. All of their rate measurements were concerned with early degradation processes. They estimated an activation energy of 18 kcal. from their data. It is felt that none of the work concerned with early degradation is definitive, and that this region requires further study.

Madorsky and Straus carried out a few experiments to comparatively high extents of reaction, and it is possible to compare their data with that of the present work. Total percent of volatilization was reported as a consequence of heating for a given length of time at 420, 500, and 800°C. To compare data, equation (5) was integrated to give

$$w = w_{f} + \frac{w_{o} (w_{o} - w_{f})}{\sqrt[4]{w_{o}^{4} + 4 \times 10^{18} \text{ t e}^{-55,000/\text{RT}} (w_{o} - w_{f})^{4}} \sqrt[4]{0.25}}$$
(13)

These workers pyrolyzed a sample of phenolic at $1200^{\circ}C^{10}$. Elemental analysis showed that 99.2% of the residue was carbon when the residue weight was 51.6% of that of the original sample. w₀ was assumed to be unity and w_f was assumed to be 0.516. Although equation (13) ignored early weight loss and w₀ was defined on a different basis than that by which the equation was derived, it was felt that the calculation would still be meaningful. w_f is probably the most important parameter for this calculation so long as the extent of reaction is great enough for most or all of the early weight loss gases to be evolved. The three runs that were chosen seemed to qualify reasonably well on this basis. The results of comparison are listed in Table 2. The agreement between the results is excellent and lends further support to the present kinetic analysis.

The kinetic analysis technique that was employed in this paper has several advantages. By its use it was possible to

calculate an activation energy for the main degradation process without any knowledge of the form of the kinetic equation. It was also useful for the purpose of deriving a semi-empirical rate law, which would be difficult to arrive at by other methods. This method could also serve as a check for systems where the rate laws seem to be so simple that TGA experiments would only be carried out at one rate of heating under normal circumstances.

Summary

A technique was devised for obtaining rate laws and kinetic parameters which describe the thermal degradation of plastics from TGA data. The method is based on the intercomparison of experiments which were performed at different linear rates of heating. By this method it is possible to determine the activation energy of certain processes without knowing the form of the kinetic equation.

This technique was applied to fiberglass reinforced CTL 91-LD Phenolic, where the rate law

$$-\frac{1}{w_0} \frac{dw}{dt} = 10^{18} e^{-55,000/RT} \left(\frac{w - w_f}{w_0}\right)^5, hr^{-1}$$

was found to apply to a major part of the degradation. The equation was successfully tested by several techniques, including a comparison with constant temperature data that were available in the literature. The activation energy was thought to be correct to within 10 kcal.

Acknowledgments

The author is particularly grateful to C. D. Doyle and Mrs. M. A. Spodnewski of the General Engineering Laboratory of the General Electric Co., Schenectady, N. Y., for carrying out all of these experiments. He is also indebted to S. Blecher and Mrs. R. Flitter for their help with the mathematics and computations.

References

- D. W. van Krevelen, C. van Heerden, and F. J. Huntjens, Fuel <u>30</u>, 253 (1951).
- 2. E. S. Freeman and B. Carroll, J. Phys. Chem. <u>62</u>, 394 (1958).
- 3. D. A. Anderson and E. S. Freeman, J. Appl. Polymer Sci. <u>1</u>, 192 (1959).
- 4. D. A. Anderson and E. S. Freeman, in publication.
- C. D. Doyle, WADD Tech. Rept. 61-255, May 1951; Anal. Chem. 33, 77 (1961); WADD Tech. Rept. 60-101, 215, Sept. 1960; etc.
- 6. H. L. Friedman, WADD Tech. Rept. 60-101, 295, Sept. 1960.
- 7. E. Jahnke and F. Emde, <u>Tables of Functions with Formulae</u> and Curves, Dover Publications, N. Y., 1945.
- 8. C. A. Coulson and W. E. Duncanson, Phil. Mag. <u>33</u>, 754 (1942).
- 9. S. L. Madorsky and S. Straus, WADC Tech. Rept. 59-64, March 1959.
- S. L. Madorsky and S. Straus, N. B. S. Rept. 6478, Quarterly Rept. to WADC, May 1 to July 31, 1959.

*Arrhenius plot average values were calculated from examination of all data in Figure 8.

TABLE 1

Kinetic Farameters Calculated by Different Methods

TABLE 2

.

٦

.

.

Comparison Between Results of the Present Work with Experiments of Madorsky and Straus

Temperature, ^O C	Reference	Heating Time, Minutes	w/w _o observed	w/w _o calculated
420	10	130	0.838	0.876
500	9	30	0.72	0.717
800	9	5	0.53	0.542



Figure 1. TGA Curves of CTL 91-LD Phenolic on Glass Free Basis.



Figure 2. Derivatives of TGA Curves.



Figure 3. TGA Curves Corrected for Some Early Degassing.



Figure 4. Arrhenius Type Plots for Determining Kinetic Parameters.



Figure 5. Kinetic Parameters as a Function of Sample Weight.



Figure 6. Plot of $\ln \left[Axf(w/w_0)\right]$ as a Function of Sample Weight.



Figure 7. Plot for the Determination of A and Kinetic Order.



١.

Figure 8. Arrhenius Plots of the TGA Data.



ţ

Figure 9. Experimental and Theoretical TGA Curves for the 50°C/hr. Heating Rate.



Figure 10. Comparison Between Experiment and Theory.

GENERAL 🍘 ELECTRIC

SPACE SCIENCES LABORATORY MISSILE AND SPACE VEHICLE DEPARTMENT

.

.

Ł

.

TECHNICAL INFORMATION SERIES

AUTHOR	SUBJECT CLASSIFICATION	NO.											
Henry L.	Plastic Degradation	R61SD145											
Friedman	Kinetics	AUGUST 19	61										
THE KINETICS OF THERMAL DEGRADATION OF CHARRING PLASTICS. I. GLASS REINFORCED PHENOL- FORMALDEHYDE													
ABSTRACT													
A tecnr	nique was devised for obt	aining rat	е										
1aws and kir	netic paramete <mark>rs which de</mark>	scribe the											
thermal degr	adation of plastics from	thermo-											
gravimetric	analysis data. The meth	od is base	d										
on the inter	-comparison of experimen	ts which											
G. E. CLASS	REPRODUCIBLE COPY FILED AT	NO. PA	GES										
I	G. E. TECHNICAL INFORMATION CE	NTFR											
GOV. CLASS	PHILADELPHIA, PENNA.	30											
Abstract (Co	ontinued)	,,,											
were perform	were performed at different linear rates of temperature rise.												
temperature													
The method was applied to a fiberglass													
reinforced p	reinforced phenol-formaldehyde resin. The												
kinetic equa	kinetic equation that was thus derived was												
checked by a	variety of techniques, :	including a	a										
comparison w	comparison with constant temperature data that were available in the literature. The tests												
were availab													
indicated that the equation was applicable to a major part of the degradation process.													
						By cutting out this rectangle and folding on the center line, the above information can be fitted							
						into a standard card file.							

_____ Fri Iman AUTHOR Henry COUNTERSIGNED_ Defense Electronics DIVISION_ Space Technology Center, King of Prussia, Pa. LOCATION_