

AD641120

TECHNICAL REPORT 6614

AD

GAS-LIQUID CHROMATOGRAPHY OF THE
ALKYL ALPHA CYANOACRYLATES

Reported by: Duane E. Bartak
R. K. Kulkarni

August 1966

CLEARINGHOUSE FOR FEDERAL SCIENTIFIC AND TECHNICAL INFORMATION			
Hardcopy	Microfiche		
\$1.00	\$1.50	15 pp	20
/ ARCHIVE COPY			

U. S. ARMY MEDICAL BIOMECHANICAL RESEARCH LABORATORY
WALTER REED ARMY MEDICAL CENTER
Washington, D. C. 20012

Distribution of this document is unlimited

AD

TECHNICAL REPORT 6614

Project: 3A025601A821 01 097

**GAS-LIQUID CHROMATOGRAPHY OF THE
ALKYL ALPHA CYANOACRYLATES**

**Reported by: Duane E. Bartak
R. K. Kulkarni**

August 1966

**U.S. ARMY MEDICAL BIOMECHANICAL RESEARCH LABORATORY
WALTER REED ARMY MEDICAL CENTER
Washington, D. C. 120012**

Distribution of this document is unlimited

ABSTRACT

The purity of the cyanoacrylate monomers was estimated by gas-chromatographic technique. Some of the impurities, like diglyme, cyanoacetates were identified by noting the retention volumes. A plot of the retention volumes vs. number of carbons in the alkyl part of the cyanoacrylates was found to be linear; however, the use of temperature programming to obviate the broadening of the peaks for compounds having higher retention volumes was not successful, due to the shifting of the base line with increase in temperature.

INTRODUCTION

The n-alkyl cyanoacrylate monomers, known for their applications as adhesives, are being investigated by the Army Medical Biomechanical Research Laboratory with regard to tissue reaction, toxicity, and overall suitability as surgical adjuncts.¹ A procedure was necessary to determine the purity of each of the monomers which were synthesized in our laboratory to be used for further research. Gas-liquid chromatography offered a technique which was both fast and accurate for the determination of purities of the monomers and the identification of the impurities that were present.

EXPERIMENTAL

Apparatus: F & M Model 700 gas chromatograph equipped with an F & M dual hydrogen flame ionization detector was used. The recording device was a Model LS11A Westronics recorder.

Column: Columns were prepared from 1/4-inch o.d. stainless steel tubing in lengths of 6 feet. The inert support was 80/100 mesh chromosorb P containing 10% by weight of Silicone Gum Nitrile (F & M Scientific Company).

Chromatograph Conditions: The column temperature was maintained at 165° C for methyl through butyl homologs and 185° for amyl through nonyl homologs. Injection port temperature was 210° at all times. Helium zero-grade gas supplied by Matheson was used as the carrier gas at 25 p.s.i. and at a flow rate of 30 ml/min at outlet measured with soap bubble apparatus with a setting of 3.0 on the flowmeter on the F & M 700 chromatography.

Detector temperature was 230° C with hydrogen setting of 2.5 on the flowmeter at 30 p.s.i., and compressed air at 2.5 arbitrary units setting on the flowmeter at 12 p.s.i.

ANALYSIS

Samples of the monomers prepared were made up at 3-5% by weight in methylene chloride. Nitromethane was also used; however, it was more hygroscopic and therefore difficult to use in presence of monomers prone to polymerize with water. 1.0 μ l to 2.0 μ l (sample size) were injected with a 10 μ l Hamilton syringe into the column. The impurities were identified by comparing retention times of known compounds under identical conditions to that of the impurity in the sample and also by spiking the sample with the suspected impurity and observing

if the impurity peak was superimposed by the added "suspect" with no shoulders or tailing of the impurity peak.

DISCUSSION

Listed in Table I are the monomers prepared and the purity calculated for each monomer and the impurities identified. The corresponding alcohols were present as an impurity to a greater degree than any other. The presence of alcohols can be explained by reviewing the cyanoacrylate preparation by the cyanoacetate which is the product of esterification of the corresponding alcohol and cyano-acetic acid.² Diglyme (diethyleneglycol dimethyl ether) was another impurity identified whose presence can be explained since it is also a starting material in the synthesis of the alkyl cyanoacrylates. Chromatograms # 1 and # 2 are typical chromatograms of n-heptyl and isobutyl cyanoacrylates.

To help further identification and to check the separation of the cyanoacrylate monomers, a mixture of the n-homologous series of methyl through octyl was prepared and injected. Chromatogram # 3 shows the effective separation of 5% monomer mixture by weight in methylene chloride.

The relative retention volumes for each of the cyanoacrylates are calculated and reported in Table II.³ N-butyl cyanoacrylate is given the value of 1.00.

Graph I illustrates the linearity when the log of the retention time versus the number of carbon atoms in the homologous series is plotted.

Temperature programming was attempted to speed up the analysis of the monomer mixture; however, due to substrate bleeding at higher column temperatures, there was large baseline drifting. Therefore, quantitative results were found not to be acceptable with the large drift of baseline.

Due to the fact that standard n-alkyl cyanoacrylate samples were not available, the internal normalization method was employed.⁴ Results obtained from this method are independent of sample size within reasonable limits, as the procedure is to sum the areas of all the peaks and divide this value into the area of the individual peak. However, detector response must be approximately the same for all compounds being evaluated to avoid large error in such measurements. Detector

response for the n-alkyl cyanoacrylate and various alcohols and other impurities present in some of the work presently being carried out.

CONCLUSIONS

Gas-liquid chromatograph is a useful tool for the determination of the purities of the alkyl cyanoacrylates. It offers a fast and accurate method for the identification of impurities that may be present.

RECOMMENDATIONS

The investigation of the relative sensitivity of the members of the homologous series of cyanoacrylates, and also the impurities, is necessary for evaluation of the true purities of the samples. This work is already in progress. The gas chromatographic evaluation may be extended to measure the purity of the polymers of cyanoacrylates as well, because they get cracked and depolymerized in the chromatographic columns. More careful work on temperature programming is proposed, using properly equilibrated columns for avoiding the baseline drift commonly experienced, as of now.

Citation of specific commercial equipment, material or trade names in this report does not constitute an official endorsement or approval of the use of such commercial products.

TABLE I
MONOMERS

Cyanoacrylate	Purity	Impurities
Methyl	98.7%	Not identified
Ethyl	99.5%+	None measurable
Propyl	99.5%+	None measurable
Butyl	99.5%+	None measurable
Amyl	99.2%	0.8% Amyl Alcohol
Hexyl	96.8%	1.8% Isomer of Hexyl Cyanoacrylate; 1.4% Hexyl Alcohol
Heptyl	99.1%	0.8% Heptyl Alcohol
Octyl	98.8%	0.3% Octyl Alcohol
		0.9% Unidentified
Nonyl	97.9%	2.1% Nonyl Alcohol
Iso-Propyl	99.5%+	None measurable
Iso-Butyl	99.5%+	None measurable
Iso-Amyl	99.5%+	None measurable
Ethyl Hexyl	99.0%	1.0% Ethyl Hexyl Alcohol
Cellosolve	98.0%	2.0% Not Identified

TABLE II
Relative Retention Volumes of N-Alkyl
Cyanoacrylates at 170° C
(N-Butyl Cyanoacrylate assigned relative retention volume of 1.00)

	Retention Volume	Relative Retention Volume
Methyl Cyanoacrylate	132 ml	0.48
Ethyl Cyanoacrylate	150 ml	0.56
N-Propyl Cyanoacrylate	199 ml	0.73
N-Butyl Cyanoacrylate	274 ml	1.00
N-Amyl Cyanoacrylate	383 ml	1.40
N-Hexyl Cyanoacrylate	542 ml	1.98
N-Heptyl Cyanoacrylate	765 ml	2.79
N-Octyl Cyanoacrylate	1100 ml	4.01


REFERENCES

1. S. C. Woodward, et al, *Annals Surg.* 162: 113-122 (1965).
2. USAMBRL Technical Report 6520, Leonard, F., et al, "Synthesis and Degradation of Poly Alkyl Alpha Cyanoacrylates", November 1965.
3. Burchfield, H.P. and Storrs, E.E., Biochemical Applications of Gas Chromatography, N.Y. Academic Press, 1962, pp. 11-14.
4. Dal Nogare, S. and Juvet, R.S., Jr., Gas-Liquid Chromatography, N.Y. Interscience Publishers, 1965, pp. 256-257.

11

24 May 66
Back

Plot: Retention Time vs. Number of Carbon Atoms in α -Olefin Series of Quin-Acetylenes

[illegible]


Chenmoyda PPA #1

[illegible]

(2) Average 1 2/3 ft

[illegible]

CONTINUED ON NEXT PAGE



UNCLASSIFIED

Security Classification

DOCUMENT CONTROL DATA - R&D		
(Security classification of title, body of abstract and indexing annotation must be entered when the overall report is classified)		
1. ORIGINATING ACTIVITY (Corporate author) U.S.A. Medical Biomechanical Research Laboratory WRAMC, Forest Glen Section		2a. REPORT SECURITY CLASSIFICATION UNCLASSIFIED 2b. GROUP
3. REPORT TITLE GAS-LIQUID CHROMATOGRAPHY OF THE ALKYL ALPHA CYANOACRYLATES		
4. DESCRIPTIVE NOTES (Type of report and inclusive dates) Technical Report		
5. AUTHOR(S) (Last name, first name, initial) R. K. Kulkarni Duane E. Bartak		
6. REPORT DATE August 1966	7a. TOTAL NO. OF PAGES 3	7b. NO. OF REFS 4
8a. CONTRACT OR GRANT NO. b. PROJECT NO. 3A025601A821 01 097 c. d.		9a. ORIGINATOR'S REPORT NUMBER(S) Technical Report #6614 9b. OTHER REPORT NO(S) (Any other numbers that may be assigned this report)
10. AVAILABILITY/LIMITATION NOTICES Distribution of this document is unlimited.		
11. SUPPLEMENTARY NOTES		12. SPONSORING MILITARY ACTIVITY USA Medical R & D Command Department of the Army Washington, D.C. 20315
13. ABSTRACT The purity of the cyanoacrylate monomers was estimated by gas-chromatographic technique. Some of the impurities, like diglyme, cyanoacetates, were identified by noting the retention volumes. A plot of the retention volumes vs. number of carbons in the alkyl part of the cyanoacrylates was found to be linear; however, the use of temperature programming to obviate the broadening of the peaks for compounds having higher retention volumes was not successful, due to the shifting of the base line with increase in temperature. KEY WORDS Gas Chromatography of Cyanoacrylates Purity of Cyanoacrylates by Gas Chromatography GLC Determination of Cyanoacrylates by GLC		

DD FORM 1473
1 JAN 64

UNCLASSIFIED

Security Classification

Unclassified

Security Classification

14. KEY WORDS	LINK A		LINK B		LINK C	
	ROLE	WT	ROLE	WT	ROLE	WT

INSTRUCTIONS

1. **ORIGINATING ACTIVITY:** Enter the name and address of the contractor, subcontractor, grantee, Department of Defense activity or other organization (corporate author) issuing the report.

2a. **REPORT SECURITY CLASSIFICATION:** Enter the overall security classification of the report. Indicate whether "Restricted Data" is included. Marking is to be in accordance with appropriate security regulations.

2b. **GROUP:** Automatic downgrading is specified in DoD Directive 5200.10 and Armed Forces Industrial Manual. Enter the group number. Also, when applicable, show that optional markings have been used for Group 3 and Group 4 as authorized.

3. **REPORT TITLE:** Enter the complete report title in all capital letters. Titles in all cases should be unclassified. If a meaningful title cannot be selected without classification, show title classification in all capitals in parentheses immediately following the title.

4. **DESCRIPTIVE NOTES:** If appropriate, enter the type of report, e.g., interim, progress, summary, annual, or final. Give the inclusive dates when a specific reporting period is covered.

5. **AUTHOR(S):** Enter the name(s) of author(s) as shown on or in the report. Enter last name, first name, middle initial. If military, show rank and branch of service. The name of the principal author is an absolute minimum requirement.

6. **REPORT DATE:** Enter the date of the report as day, month, year, or month, year. If more than one date appears on the report, use date of publication.

7a. **TOTAL NUMBER OF PAGES:** The total page count should follow normal pagination procedures, i.e., enter the number of pages containing information.

7b. **NUMBER OF REFERENCES:** Enter the total number of references cited in the report.

8a. **CONTRACT OR GRANT NUMBER:** If appropriate, enter the applicable number of the contract or grant under which the report was written.

8b, 8c, & 8d. **PROJECT NUMBER:** Enter the appropriate military department identification, such as project number, subproject number, system numbers, task number, etc.

9a. **ORIGINATOR'S REPORT NUMBER(S):** Enter the official report number by which the document will be identified and controlled by the originating activity. This number must be unique to this report.

9b. **OTHER REPORT NUMBER(S):** If the report has been assigned any other report numbers (either by the originator or by the sponsor), also enter this number(s).

10. **AVAILABILITY/LIMITATION NOTICES:** Enter any limitations on further dissemination of the report, other than those imposed by security classification, using standard statements such as:

- (1) "Qualified requesters may obtain copies of this report from DDC."
- (2) "Foreign announcement and dissemination of this report by DDC is not authorized."
- (3) "U. S. Government agencies may obtain copies of this report directly from DDC. Other qualified DDC users shall request through _____."
- (4) "U. S. military agencies may obtain copies of this report directly from DDC. Other qualified users shall request through _____."
- (5) "All distribution of this report is controlled. Qualified DDC users shall request through _____."

If the report has been furnished to the Office of Technical Services, Department of Commerce, for sale to the public, indicate this fact and enter the price, if known.

11. **SUPPLEMENTARY NOTES:** Use for additional explanatory notes.

12. **SPONSORING MILITARY ACTIVITY:** Enter the name of the departmental project office or laboratory sponsoring (paying for) the research and development. Include address.

13. **ABSTRACT:** Enter an abstract giving a brief and factual summary of the document indicative of the report, even though it may also appear elsewhere in the body of the technical report. If additional space is required, a continuation sheet shall be attached.

It is highly desirable that the abstract of classified reports be unclassified. Each paragraph of the abstract shall end with an indication of the military security classification of the information in the paragraph, represented as (TS), (S), (C), or (U).

There is no limitation on the length of the abstract. However, the suggested length is from 150 to 225 words.

14. **KEY WORDS:** Key words are technically meaningful terms or short phrases that characterize a report and may be used as index entries for cataloging the report. Key words must be selected so that no security classification is required. Identifiers, such as equipment model designation, trade name, military project code name, geographic location, may be used as key words but will be followed by an indication of technical context. The assignment of links, rules, and weights is optional.

Unclassified

Security Classification