

AMMRC TR 70-11

ARMY MATERIALS AND MECHANICS RESEARCH CENTER  
WATERTOWN, MASSACHUSETTS, 02172

AD716235

Library

# GROWTH OF SAPPHIRE DISKS FROM THE MELT BY A GRADIENT FURNACE TECHNIQUE

FREDERICK SCHMID and DENNIS J. VIECHNICKI  
CERAMICS DIVISION

April 1970

This document has been approved for public release and sale; its distribution is unlimited.

ARMY MATERIALS AND MECHANICS RESEARCH CENTER  
Watertown, Massachusetts 02172

OFFICIAL FILE COPY

The findings in this report are not to be construed as an official Department of the Army position, unless so designated by other authorized documents.

Mention of any trade names or manufacturers in this report shall not be construed as advertising nor as an official indorsement or approval of such products or companies by the United States Government.

#### DISPOSITION INSTRUCTIONS

Destroy this report when it is no longer needed.  
Do not return it to the originator.

AMMRC TR 70-11

**GROWTH OF SAPPHIRE DISKS FROM THE MELT BY A  
GRADIENT FURNACE TECHNIQUE**

Technical Report by

*FREDERICK SCHMID and DENNIS J. VIECHNICKI*

April 1970

D/A Project 1T062105A330

AMCMS Code 502E.11.296

Ceramic Materials Research for Army Materiel

Agency Accession Number DA OA4772

This document has been approved for public release and sale; its distribution is unlimited.

CERAMICS DIVISION

ARMY MATERIALS AND MECHANICS RESEARCH CENTER

Watertown, Massachusetts 02172

ARMY MATERIALS AND MECHANICS RESEARCH CENTER


GROWTH OF SAPPHIRE DISKS FROM THE MELT BY A GRADIENT FURNACE TECHNIQUE

ABSTRACT

Single crystal  $\text{Al}_2\text{O}_3$  (sapphire) is a candidate material for various window applications. A gradient furnace technique has been developed for the growth of large sapphire disks, 7.3 cm in diameter and 1.5 cm thick, from the melt in molybdenum crucibles. The disks are free of gas bubbles and inclusions and consist of several large pie-shaped grains. Within the grains dislocation densities of  $1 \times 10^5 \text{ cm}^{-2}$  have been measured. The disks are essentially transparent to radiation from wavelengths of 0.25  $\mu\text{m}$  in the ultraviolet spectrum to 4.5  $\mu\text{m}$  in the infrared spectrum.




FREDERICK SCHMID  
Metallurgist



DENNIS J. VEECHNICKI  
Research Ceramic Engineer

APPROVED:

  
for

I. BERMAN  
Chief  
Ceramics Division

## GROWTH OF SAPPHIRE DISKS FROM THE MELT BY A GRADIENT FURNACE TECHNIQUE

Single crystal  $\text{Al}_2\text{O}_3$  (sapphire) is a candidate material for various window applications in the visible spectrum and in the infrared spectrum. Growth of sapphire from the melt as reported in the literature has been accomplished using a Verneuil technique,<sup>1</sup> a Czochralski technique,<sup>2-4</sup> and a floating zone technique.<sup>3,4</sup> These techniques, however, did not appear to offer the flexibility required to fabricate large single crystals in significant quantities for various window applications. New crystal growth techniques from the melt would have to be developed if sapphire were to be widely used as a window material. It was felt that a casting or controlled solidification technique, where the melt was contained in a crucible and growth of the solid circumscribed by the crucible, could be developed. A gradient furnace technique was evolved for the growth of sapphire disks. This report will describe the technique and the sapphire disks produced.

The gradient furnace is a vacuum graphite resistance furnace\* with a helium-cooled tungsten/molybdenum heat exchanger projecting up into it as illustrated schematically in Figure 1. The material to be melted, in this case previously fused  $\text{Al}_2\text{O}_3$ , is contained in a molybdenum crucible which is seated atop the heat exchanger. A seed crystal is located at the base of the crucible in the center directly above the heat exchanger. The material is melted except for the seed




Figure 1. SCHEMATIC OF GRADIENT FURNACE

\*Vacuum Specialties, Inc., 34 Linden St. Somerville, Massachusetts

crystal which is cooled by the heat exchanger directly below it. The helium flow through the heat exchanger is increased and more heat is removed from the material. The melt nucleates on the seed crystal, and the solid grows out from the seed crystal. The driving force for growth is created by the temperature gradients set up in the material as the heat flows from the heating elements, through the material, and out the heat exchanger where the bulk of it is removed by the helium. The technique is flexible in that a variety of crucible shapes and sizes may be used. A conical crucible is illustrated in Figure 1. Figure 2 illustrates the arrangement used to grow sapphire disks where a flat dish-shaped crucible is employed. Two sapphire disks are seen in Figure 3. The one on the left, 7.3 cm in diameter and 1.5 cm thick, is just as removed from the crucible with no machining. The one on the right, 7.3 cm in diameter and 0.9 cm, has been ground and polished to a submicron finish\* and a portion removed for other studies. Semi-quantitative spectrochemical analysis† of similar disks revealed that molybdenum content is below 100 ppm indicating that reaction between molten  $\text{Al}_2\text{O}_3$  and the molybdenum crucible is minimal. No gas bubbles were observed with the naked eye

or with a petrographic microscope to 500X. When the disks were observed in a polariscope, a structure consisting of wedge-shaped columnar sub-grains radiating from the center of the disk was seen. X-ray analysis of the disks was conducted using the Laue method. Laue patterns obtained at various locations on both sides of the disks revealed that the grains were misoriented by less than  $10^\circ$ . The disks in Figure 3 are oriented so that the  $(11\bar{2}0)$  planes are nearly parallel to the faces of the disks. Dislocation densities on the  $(0001)$  plane were determined in the interior of the large grains after etching with hot orthophosphoric acid.<sup>5</sup> Dislocation densities of  $1 \times 10^5 \text{ cm}^{-2}$  were obtained which were comparable to sapphire grown by the Czochralski technique.<sup>3-5</sup> Absorption edges of a sapphire disk 0.9 cm thick were determined




Figure 2. SCHEMATIC ARRANGEMENT IN THE GRADIENT FURNACE FOR THE GROWTH OF SAPPHIRE DISKS

\*Bomas Machining Specialties, Inc., 114 N. Beacon St., Brighton, Massachusetts

†Jarrel-Ash Division of Fisher Scientific Company, Waltham, Massachusetts

using three spectrophotometers\* and the results are shown in Figure 4. The disk was essentially transparent to radiation from 0.25  $\mu\text{m}$  in the ultraviolet to 4.5  $\mu\text{m}$  in the infrared.




Figure 3. SAPPHIRE DISKS GROWN BY THE GRADIENT FURNACE TECHNIQUE. The one at the left is as removed from the crucible with no machining. The one at the right has been ground and polished to a submicron finish and a portion was removed for other studies.




Figure 4. A PLOT OF PERCENT TRANSMISSION VERSUS WAVELENGTH FOR SAPPHIRE GROWN BY THE GRADIENT FURNACE TECHNIQUE

\*Model 202 Ultraviolet-Visible Spectrophotometer, Perkin-Elmer Corp., Main Avenue, Norwalk, Connecticut;  
Models IR-12 and DK-1A Spectrophotometers, Beckman Instruments, Inc., 2500 Harbor Blvd., Fullerton, California

A casting or controlled solidification technique employing a gradient furnace has been developed for the growth of large sapphire disks. Sapphire disks 7.3 cm in diameter and 1.5 thick have been reproducibly grown to shape in molybdenum crucibles. The simplicity and flexibility of the technique makes it attractive for growth of even larger crystals required for lightweight, transparent armor applications.

#### ACKNOWLEDGMENTS

The authors gratefully acknowledge the assistance of C. S. King and W. H. Earle and thank R. E. Sacher for performing the optical studies.

#### LITERATURE CITED

1. VERNEUIL, M. A. *Memoire sur la Reproduction Artificielle du Rubis par Fusion*. Ann. Chim. Phys., (8th Series), v. 3, 1904, p. 20-48.
2. PALADINO, A. E., and ROITER, B. D. *Czochralski Growth of Sapphire*. J. Am. Ceram. Soc., v. 47, no. 9, 1964, p. 465.
3. RUBIN, J. J., and VAN UITERT, L. G. *Growth of Sapphire and Ruby by the Czochralski Technique*. Mat. Res. Bull., v. 1, no. 3, 1966, p. 211-214.
4. COCKAYNE, B., CHESSWAS, M., and GASSON, D. B. *Single-Crystal Growth of Sapphire*. J. Matls. Sci., v. 2, 1967, p. 7-11.
5. SAHAGIAN, C. S. *Crystal Perfection of  $\alpha$  -  $Al_2O_3$  as a Function of Growth Method*. Air Force Cambridge Research Laboratories - 66 - 659, Physical Sciences Research Papers No. 268, September 1966.



ARMY MATERIALS AND MECHANICS RESEARCH CENTER  
WATERTOWN, MASSACHUSETTS 02172

TECHNICAL REPORT DISTRIBUTION

No. of Copies	To
1	Office of the Director, Defense Research and Engineering, The Pentagon, Washington, D. C. 20301
20	Commander, Defense Documentation Center, Cameron Station, Building 5, 5010 Duke Street, Alexandria, Virginia 22314
1	Defense Ceramics Information Center, Battelle Memorial Institute, 505 King Avenue, Columbus, Ohio 43201
1	Defense Metals Information Center, Battelle Memorial Institute, Columbus, Ohio 43201
	Chief of Research and Development, Department of the Army, Washington, D. C. 20310
2	ATTN: Physical and Engineering Sciences Division
	Commanding Officer, Army Research Office (Durham), Box CM, Duke Station, Durham, North Carolina 27706
1	ATTN: Information Processing Office
	Commanding General, U. S. Army Materiel Command, Washington, D. C. 20315
1	ATTN: AMCRD-TC
	Commanding General, Deseret Test Center, Fort Douglas, Utah 84113
1	ATTN: Technical Information Office
	Commanding General, U. S. Army Electronics Command, Fort Monmouth, New Jersey 07703
2	ATTN: AMSEL-GG-DD
	Commanding General, U. S. Army Missile Command, Redstone Arsenal, Alabama 35809
1	ATTN: Technical Library
	Commanding General, U. S. Army Munitions Command, Dover, New Jersey 07801
1	ATTN: Technical Library
	Commanding General, U. S. Army Natick Laboratories, Natick, Massachusetts 01762
1	ATTN: Technical Library
	Commanding General, U. S. Army Satellite Communications Agency, Fort Monmouth, New Jersey 07703
1	ATTN: Technical Document Center
	Commanding General, U. S. Army Tank-Automotive Command, Warren, Michigan 48090
2	ATTN: AMSTA-BSL, Research Library Br
	Commanding General, U. S. Army Weapons Command, Research and Development Directorate, Rock Island, Illinois 61201
1	ATTN: AMSWE-RER-L, Technical Library
	Commanding Officer, Aberdeen Proving Ground, Maryland 21005
1	ATTN: Technical Library, Building 313
	Commanding Officer, Frankford Arsenal, Bridge and Tacony Streets, Philadelphia, Pennsylvania 19137
1	ATTN: Library, H1300, Bl. 51-2
	Commanding Officer, Harry Diamond Laboratories, Connecticut Avenue and Van Ness Street, N. W., Washington, D. C. 20438
1	ATTN: Technical Information Office
	Commanding Officer, Department of the Army, Ohio River Division Laboratories, Corps of Engineers, 5851 Mariemont Avenue, Cincinnati, Ohio 45227
1	ATTN: ORDLB-TR
	Commanding Officer, Picatinny Arsenal, Dover, New Jersey 07801
1	ATTN: SMUPA-RT-S
	Commanding Officer, Redstone Scientific Information Center, U. S. Army Missile Command, Redstone Arsenal, Alabama 35809
4	ATTN: AMSMI-RBLD, Document Section
	Commanding Officer, Watervliet Arsenal, Watervliet, New York 12189
1	ATTN: SWEWV-RDT, Technical Information Services Office
1	Dr. Boaz Avitzur
1	Commanding Officer, U. S. Army Aviation Materiel Laboratories, Fort Eustis, Virginia 23604
	Librarian, U. S. Army Aviation School Library, Fort Rucker, Alabama 36360
1	ATTN: Bldg. 5907

No. of Copies	To
2	Commanding Officer, USACDC Ordnance Agency, Aberdeen Proving Ground, Maryland 21005 ATTN: Library, Building 305
1	Director, Naval Research Laboratory, Anacostia Station, Washington, D. C. 20390 ATTN: Technical Information Officer
1	Chief of Naval Research, Department of the Navy, Arlington, Virginia 22217 ATTN: Code 471
2	Air Force Materials Laboratory, Wright-Patterson Air Force Base, Ohio 45433 ATTN: AFML (MAA)
1	AFML (MAT)
1	AFML (MAM)
1	AFML (MAN)
1	National Aeronautics and Space Administration, Washington, D. C. 20546 ATTN: Mr. B. G. Achhammer
1	Mr. G. C. Deutsch - Code RR-1
1	National Aeronautics and Space Administration, Marshall Space Flight Center, Huntsville, Alabama 35812 ATTN: R-P&VE-M, Mr. R. J. Schwinghamer
1	M-F&AE-M, Mr. W. A. Wilson, Building 4720
1	Panametrics, 221 Crescent Street, Waltham, Massachusetts 02154 ATTN: Mr. K. A. Fowler
1	Professor R. M. Spriggs, Lehigh University, Materials Research Center, Bethlehem, Pennsylvania 18015
1	Professor V. S. Stubican, Department of Materials Science, The Pennsylvania State University, University Park, Pennsylvania 16802
1	Professor F. F. Y. Wang, Department of Material Science, State University of New York at Stony Brook, Stony Brook, Long Island, New York 11790
1	Professor M. H. Leipold, Department of Materials Science, University of Kentucky, Lexington, Kentucky 40506
1	Dr. Stuart L. Blank, Bell Telephone Laboratories, Inc., Murray Hill, New Jersey 07974
1	Dr. S. L. Blum, IIT Research Institute, 10 W. 35th Street, Chicago, Illinois 60616
1	Dr. W. H. Rhodes, AVCO Corporation, Lowell, Massachusetts
1	Professor M. C. Flemings, Department of Metallurgy and Materials Science, Massachusetts Institute of Technology, Cambridge, Massachusetts 02139
2	Director, Army Materials and Mechanics Research Center, Watertown, Massachusetts 02172 ATTN: AMXMR-STL
1	AMXMR-AM
1	AMXMR-P
1	AMXMR-XS
2	Authors

79 TOTAL COPIES DISTRIBUTED

1 Editor  
1 Reading  
34 Authors  
15 Total Copies Available

## DOCUMENT CONTROL DATA - R &amp; D

(Security classification of title, body of abstract and indexing annotation must be entered when the overall report is classified)

1. ORIGINATING ACTIVITY (Corporate author) Army Materials and Mechanics Research Center Watertown, Massachusetts 02172		2a. REPORT SECURITY CLASSIFICATION Unclassified	
		2b. GROUP	
3. REPORT TITLE  GROWTH OF SAPPHIRE DISKS FROM THE MELT BY A GRADIENT FURNACE TECHNIQUE			
4. DESCRIPTIVE NOTES (Type of report and inclusive dates)			
5. AUTHOR(S) (First name, middle initial, last name)  Frederick Schmid and Dennis J. Viechnicki			
6. REPORT DATE April 1970	7a. TOTAL NO. OF PAGES 7	7b. NO. OF REFS 5	
8a. CONTRACT OR GRANT NO.  b. PROJECT NO. D/A 1T062105A330  c. AMCMS Code 502E.11.29600  d. Agency Accession Number DA OA4772		9a. ORIGINATOR'S REPORT NUMBER(S)  AMMRC TR 70-11	
		9b. OTHER REPORT NO(S) (Any other numbers that may be assigned this report)	
10. DISTRIBUTION STATEMENT  This document has been approved for public release and sale; its distribution is unlimited.			
11. SUPPLEMENTARY NOTES		12. SPONSORING MILITARY ACTIVITY  U. S. Army Materiel Command Washington, D. C. 20315	
13. ABSTRACT  Single crystal $\text{Al}_2\text{O}_3$ (sapphire) is a candidate material for various window applications. A gradient furnace technique has been developed for the growth of large sapphire disks, 7.3 cm in diameter and 1.5 cm thick, from the melt in molybdenum crucibles. The disks are free of gas bubbles and inclusions and consist of several large pie-shaped grains. Within the grains dislocation densities of $1 \times 10^5 \text{ cm}^{-2}$ have been measured. The disks are essentially transparent to radiation from wavelengths of 0.25 $\mu\text{m}$ in the ultraviolet spectrum to 4.5 $\mu\text{m}$ in the infrared spectrum. (Authors)			

14. KEY WORDS	LINK A		LINK B		LINK C	
	ROLE	WT	ROLE	WT	ROLE	WT
Gradient furnaces Sapphire Windows Crystal growth Dislocations Optical properties Density (mass/volume) Transparent armor						

AMMRC TR 70-11

GROWTH OF SAPPHIRE DISKS FROM THE MELT BY A GRADIENT FURNACE TECHNIQUE

Schmid and Viechnicki

DEPARTMENT OF THE ARMY

ARMY MATERIALS AND MECHANICS RESEARCH CENTER

Watertown, Massachusetts 02172

OFFICIAL BUSINESS

POSTAGE AND FEES PAID  
DEPARTMENT OF THE ARMY

THIRD CLASS MAIL