

FTD-MT-24-893-71

AD 737886

State of the second second

O FOREIGN TECHNOLOGY DIVISION



AN AUTOMATIC DILATOMETER

M. Ye. Gurevich and L. N. Larikov





Approved for public release; distribution unlimited.

NATIONAL TECHNICAL INFORMATION SERVICE Springfield Via 22151

12

FTD-MT- 24-393-71

EDITED MACHINE TRANSLATION

AN AUTOMATIC DILATOMETER

By: M. Ye. Gurevich and L. N. Larikov

English pages: 5

Source: Fazovyye Prevrashcheniya. Sbornik Statey. Metallofizika (Phase Conversions. Collection of Articles. The Physics of Metals), No. 27, 1970, pp. 230-234.

This document is a SYSTRAN machine-aided translation, post-edited for technical accuracy by: TSgt V. Mesenzeff

Approved for public release; distribution unlimited.

THIS TRANSLATION IS A RENDITION OF THE ORIGI-NAL FOREIGN TEXT WITHOUT AMY ANALYTICAL OR EDITOPIAL COMMENT. STATEMENTS OR THEORIES ADVOCATED OR IMPLIED ARE THOSE OF THE SOURCE AND DO NOT NECESSARILY REFLECT THE POSITION OR OPINION OF THE FOREIGN TECHNOLOG J DI-VISION.

UR/0000-79-000-027

PREPARED BY:

TRANSLATION DIVISION FOREIGN TECHNOLOGY DIVISION WP-AFB, OHIO.

FTD-MT- 24-893-71

L'address and the second second

Date 1 Dec. 19 71

(Security classification of title, body of	OCUMENT CONTROL DATA - R & D	woott is classified		
Foreign Technology D Air Force Systems Con U.S. Air Force	vision UNCLASS	UNCLASSIFIED		
AN AUTOMATIC DILATOM	TER			
Translation THOMIST (First name, middle initial, last name	•)			
Gurevich, M. Ye. and	Larikov, L. N.	OF NEFS		
1970	#12	3		
ROJECT NO. 7351	DE. ORIGINATOR'S REPORT NUMBER(3) FTD-MT-24-893-71 D. OTHER REPORT NO(8) (Any other number Mis report)			
Approved for public r	elesse; distribution unlimited. Foreign Technology Wright-Patterson AF	Division B, Ohio		
Approved for public r	rm of dilatometer for automatical ng small changes in dimensions ov nge is described. The normal wor ees K, and special measures are i damage by extreme heat and cold. onic circuits are of a high degre nably simple in construction. Go f this instrument in determining asion of superpurity Ni are prose	Division B, Ohio ly er king n- c of the nted.		

UNCLASSIFIED

Security Classification

. 164

U.Senters

Mickel Thermal Expansion Ultrahigh Purity Metal Metallographic Analysis Physics Laboratory Instrument
Nickel Thermal Expansion Ultrahdgh Purity Metal Metallographic Analysis Physics Laboratory Instrument

.

All figures, graphs, tables, equations, etc. merged into this translation were extracted from the best quality copy available.

FTD-MT-24-8+3+71

Station Ages in succession

See.

()

<u>Translator's note</u>: On several occasions, symbols found in formulae and calculations appear to have been rendered incorrectly in the original document. They will be shown exactly as they appear in the original.

FTD-MT-24-893-71

The Annual Courts of the second

100 Mar.

U. S. BOARD ON GEOGRAPHIC NAMES TRANSLITERATION SYSTEM

198 19 19 19 19

Block	Italic	Transliteration	Block	Ttolda	
A a	A a	A. a	DIUCK	Tratic	Transliteration
Бб	5 8	B. b	P P	7 7	R, r
Вв	B .	V v	C C	C c	S, s
Гг	<i>.</i>	v, v	T T	Тм	T. t
		u, g	Уу	Yy	II. n
<u> </u>	40	D, d	0	0 4	
E ė	E 4	Ye, ye; E, e [*]	XX	Y L	
жж	Жж	Zh. zh	17 11		Kn, kh
3 .	3 ,	7. 7	Lag. 86 L.*	4 4	TS, ts
Им	Ни			4 4	Ch, ch
8	A a		и ш	LLI M	Sh. sh
	<i>K</i>	1, y	Щщ	Щы	Sheh sheh
	A K	K, K	ъъ	2 1	
ЛЛ	ЛA	L, 1	53 m	11 11	10
Мм	Мм	M. m	h h		1, Y
Ни	Ни	N. D	D .		
0 0	0 0		8	5 1	Е. е
Пя		0,0	(a) (c)	lo b	Yu. wy
		r, p	Яя	8 .	Ya. va

* ye initially, after vowels, and after b, b; e elsewhere. When written as B in Russian, transliterate as yB or B. The use of diacritical borks is preferred, but such marks may be omitted when expediency dictates.

FTD-MI-24-893-71

AN AUTOMATIC DILATOMETER

M. Ye. Gurevich and L. N. Larikov

The problem of the determination of the true thermal linear expansion coefficient (α) in a wide temperature range is of considerable interest [1, 2]. At the present time, the determination of α is done by the analytical treatment of the results of measurements obtained by means of dilatometers or other instruments which determine the variation of the linear dimensions of the sample with the temperature change. Such a treatment requires a considerable amount of time on the part of the experimenter. In processing the dilatometric curve, which expresses function $\frac{\Delta L}{T} = f(T)$. a sufficiently significant calculated interval is selected by the graphic differentiation method, while the function, in most cases, is approximated. The reduction of the discrete interval for the calculations involves additional expenditures of time and an increase in the requirements for quality in registering the temperature dependence of the change in linear dimensions. This i: due to the fact that the average linear expansion coefficient is usually used during the designing. However, the requirements of many areas of new technology advocate the need for a sufficiently strict knowledge of α for a wide temperature range.

Significant difficulties in determining the true linear expansion coefficient value lie in the necessity of accounting for the

FTD-MT-24-84 -71

1

distortions introduced due to the variation in the coefficient of linear expansion of the parts of the measuring device in contact with a sample, while for a device where there are no such contacts there are other errors connected, for example, with the parallax in the optical systems, and so on. These errors must be considered in processing the measurement results.

The Institute of Metal Physics of the Academy of Sciences of the Ukrainian SSR has developed and built an automatic dilatometer AD-3 (Fig. 1); which measures and records the temperature function of the true thermal expansion coefficient over a wide temperature range (-196 to +1100°C) [3].



Fig. 1. General view of installation AD-3.

Determination of function $\frac{1}{l_6}\left(\frac{dl}{dT}\right) = \alpha(T)$ is conducted by means of the automatic functional conversion of voltage, which simulates the change in linear dimensions of the sample. The elongation of a sample which is heated or cooled at a constant rate is measured by a highly sensitive $\left(\frac{\Delta l}{l} < 10^{-4}\right)$ electronic dilatometer, which converts the change in the linear dimensions into voltage or current

FTD-MT-24-893-71

oscillations. Thus, determination of the linear expansion coefficient is reduced to the operational computation of the rate of change in the dimension of sample. The use of analog-to-digital differentiator facilitates functional conversion even when the rate of expansion (compression) of the sample is small.¹

To determine the true value of α , the correction method based on the continuous automatic input of correction immediately during the experiment has been used. The temperature function of the linear expansion of the dilatometer parts, having value in this respect, is premeasured on the same instrument, simulated by means of a functional potentiometer, and is introduced into the summing circuit synchronously with the measured value. In this case, the correction value is reduced to the same scale as the value of linear expansion.

The functional diagram of the instrument is given in Fig. 2. Tested sample 1 is placed into thermostat 2. The maintenance of the thermal condition of the experiment (heating or cooling according to the program given earlier, isothermal holdings, etc.) is accomplished by means of control unit 3, which includes temperature measuring device and program assigning and controlling equipment. The change in dimensions of the sample is transmitted by a pusher to the displacement meter 4. From the displacement meter the voltage, which simulates the changes in linear dimensions together with the voltage produced in correction unit 6 and simulating the temperature function of errors, is fed to the input of adder circuit 5. After algebraic addition in unit 5 the voltage, proportional to the "true" change in dimension of the sample, is fed to the functional converter 7, and from the output of the converter - to the input of the twocoordinate exectronic potentiometer 8, also fed to which is the signal concerning the temperature change of the sample.

FTD-MT-24-893-71

¹The analog differentiator, the use of which enabled us to obtain identical results, was also tested; however, such device has a number of deficiencies (high sensitivity to external influences, the need for precision equipment, etc.).



of installation AD-3.

Thus, instrument AD-3 enabled us to study the quantitative regularities of thermal expansion of the materials and their linear expansion coefficient, and in cases when there is no anisotropy - the magnitude and distribution of volume effects and the volumetric expansion coefficient.

Furthermore, an automatic dilatometer allows us to determine the rates of the processes, connected with the change in dimensions of the sample (phase transformations and others) under isothermal conditions or with temperature variation. In the latter case, a second sample is added (the standard), which together with the investigated sample forms the differential circuit for measuring linear elongations.

Nickel samples of high purity were measured on the automatic dilatometer AD-3. Figure 3 gives the temperature function of linear expansion of the nickel $\left(\frac{M}{l_0} = f(T)\right)$. As seen from the figure the result obtained on instrument AD-3 is in good agreement with the most reliable literature data, obtained by the interference methods [1]. The instrument very clearly fixes the value and nature of the slight effect of the intermittent variation in the true linear expansion coefficient at the Curie point. The result of the determination of true linear expansion coefficient of nickel (in the same sample) is given in Fig. 4. This result also agrees well with the values of a obtained by the same authors [1] using the calculation method ty measuring the length of the sample at various temperatures.

FTD-MT-24-893-71



Fig. 3. Change in the linear expansion of nickel as a function of temperature: the points according to the data of work [1]; the line was obtained on instrument AD-3.



Fig. 4. Thermal linear expansion coefficient of nickel as a function of temperature: the points according to the data of work [1]; the line was obtained on instrument AD-3.

BIBLIOGRAPHY

1. Nix F.C., Mac Nair D. - Phys. Rev., Lancaster, Pa, New York, 1941. 60, 8, 1942. 61, 1.2. 2. Лариков Л. Н., Фальченко В. М., Коблова Е. А. -МФЖ, 1966, 2, 213. 216. 3. Лариков Л. Н., Гуревич М.Е. Авторское свидетельство № 218491. Бюллетень вобретений, 17, 1968.

The Institute of Metal Physics of the Academy of Sciences of the Ukrainain SSR

Submitted 3 April 1965

FTD-MT-24-8)3-21