

AD-753 273

STRESS-CORROSION CRACKING OF Al-Zn-Mg
ALLOYS: THE CORROSION BEHAVIOR OF GRAIN
BOUNDARY CONSTITUENTS

A. J. Sedriks, et al

Martin Marietta Corporation

Prepared for:

Office of Naval Research

December 1972

DISTRIBUTED BY:

NTIS

National Technical Information Service
U. S. DEPARTMENT OF COMMERCE
5285 Port Royal Road, Springfield Va. 22151

AD753273

MARTIN MARIETTA

Corporate Research and
Development Laboratory / **RIAS**

SIXTH

~~Fifth~~ Technical Report to ONR

STRESS-CORROSION CRACKING OF
Al-Zn-Mg ALLOYS: THE CORROSION
BEHAVIOR OF GRAIN BOUNDARY
CONSTITUENTS

by A. J. Sedriks, J. A. S. Green and
D. L. Novak

Reproduced by
**NATIONAL TECHNICAL
INFORMATION SERVICE**
U S Department of Commerce
Springfield Va. 22151

December 1972

DTIC
DEC 1972

UNCLASSIFIED

Security Classification

DOCUMENT CONTROL DATA - R & D		
(Security classification of title, body of abstract and indexing annotation must be entered when the overall report is classified)		
1. ORIGINATING ACTIVITY (Corporate author) Research Institute for Advanced Studies (RIAS) Martin Marietta Corporation, 1450 S. Rolling Road Baltimore, Maryland 21227		2a. REPORT SECURITY CLASSIFICATION UNCLASSIFIED
		2b. GROUP N/A
3. REPORT TITLE STRESS-CORROSION CRACKING OF Al-Zn-Mg ALLOYS: THE CORROSION BEHAVIOR OF GRAIN BOUNDARY CONSTITUENTS.		
4. DESCRIPTIVE NOTES (Type of report and inclusive dates) Technical Report No. 86		
5. AUTHOR(S) (First name, middle initial, last name) A. J. Sedriks, J. A. S. Green, and D. L. Novak.		
6. REPORT DATE December 1972	7a. TOTAL NO. OF PAGES 20 / 8	7b. NO. OF REFS 12
8a. CONTRACT OR GRANT NO. N00014-67-C-0496, NR 031-716	9a. ORIGINATOR'S REPORT NUMBER(S) RIAS TR 72-25c	
b. PROJECT NO.		
c.	9b. OTHER REPORT NO(S) (Any other numbers that may be assigned this report)	
d.		
10. DISTRIBUTION STATEMENT Distribution of this document is unlimited.		
11. SUPPLEMENTARY NOTES		12. SPONSORING MILITARY ACTIVITY Metallurgy Branch Office of Naval Research Arlington, Virginia 22217
13. ABSTRACT - Earlier studies by the authors have supported the view that the propagation of intergranular stress-corrosion cracks in age-hardened Al-Zn-Mg alloys in aqueous chloride solutions occurs by localized anodic dissolution of the material in the grain boundary region. This region is characterized, after age-hardening, by relatively coarse MgZn ₂ precipitates in the boundary plane and adjacent precipitate-free zones. Hence, if crack propagation does occur by dissolution, then it would be expected that it would be governed by the corrosion behavior of the grain boundary constituents in solutions of compositions approximating those existing at the crack tip (i. e., solutions containing aluminum ions and having a pH = ~ 3.5). Since the grain-boundary constituents in Al-Zn-Mg alloys are generally too fine for their corrosion behavior to be studied in situ, an experimental approach involving simulation was adopted. This involved the examination of the corrosion behavior of a small ingot of MgZn ₂ , the Al-Zn-Mg alloy in the as-quenched state, and pure aluminum. The pure aluminum and the as-quenched alloy were considered to represent the two limiting cases of the material comprising the precipitate-free zone; pure aluminum representing the limiting case of the solute-depleted region and the as-quenched alloy the vacancy depleted region. Potentiostatic polarization and weight-loss studies showed that the MgZn ₂ was in all cases more active than both the pure aluminum and the as-quenched alloy. These and other observations are examined in terms of a mechanism of stress-corrosion cracking involving the spontaneous dissolution of MgZn ₂ inter-metallic, and the deformation-induced destruction of the bridges of solid separating the intermetallic particles.		

DD FORM 1473
1 NOV 63

I

UNCLASSIFIED

Security Classification

UNCLASSIFIED

Security Classification

14.	KEY WORDS	LINK A		LINK B		LINK C	
		ROLE	WT	ROLE	WT	ROLE	WT
	1. Metallurgy 2. Electrochemistry 3. Stress-Corrosion 4. Corrosion 5. Aluminum Alloys						

Technical Report No. **6**

to

The Office of Naval Research
Contract N00014-67-C-0496, NR 031-716

**STRESS-CORROSION CRACKING OF Al-Zn-Mg ALLOYS:
THE CORROSION BEHAVIOR OF GRAIN BOUNDARY CONSTITUENTS**

by


A. J. Sedriks, J. A. S. Green and D. L. Novak

December 1972

Reproduction in whole or in part is permitted
for any purpose of the United States Government.
Distribution of this document is unlimited.

Research Institute for Advanced Studies
(RIAS)

Martin Marietta Corporation
1450 South Rolling Road
Baltimore, Maryland 21227



Paper presented at 5th International Congress
on Metallic Corrosion, Tokyo, May 1972. To
be published.

III

/

**STRESS-CORROSION CRACKING OF Al-Zn-Mg ALLOYS:
THE CORROSION BEHAVIOR OF GRAIN-BOUNDARY CONSTITUENTS**

by

A. J. Sedriks*, J. A. S. Green, and D. L. Novak
Research Institute for Advanced Studies
Martin Marietta Corporation
1450 South Rolling Road
Baltimore, Maryland 21227

ABSTRACT

Earlier studies by the authors have supported the view that the propagation of intergranular stress-corrosion cracks in age-hardened Al-Zn-Mg alloys in aqueous chloride solutions occurs by localized anodic dissolution of the material in the grain boundary region. This region is characterized, after age-hardening, by relatively coarse $MgZn_2$ precipitates in the boundary plane and adjacent precipitate-free zones. Hence, if crack propagation does occur by dissolution, then it would be expected that it would be governed by the corrosion behavior of the grain boundary constituents in solutions of compositions approximating those existing at the crack tip (i. e. solutions containing aluminum ions and having a $pH = \sim 3.5$). Since the grain-boundary constituents in Al-Zn-Mg alloys are generally too fine for their corrosion behavior to be studied in situ, an experimental approach involving simulation was adopted. This involved the examination of the

*Now at International Nickel Ltd., Wiggin Street, Birmingham, England.

corrosion behavior of a small ingot of MgZn_2 , the Al-Zn-Mg alloy in the as-quenched state, and pure aluminum. The pure aluminum and the as-quenched alloy were considered to represent the two limiting cases of the material comprising the precipitate-free zone; pure aluminum representing the limiting case of the solute-depleted region and the as-quenched alloy the vacancy depleted region. Potentiostatic polarization and weight-loss studies showed that the MgZn_2 was in all cases more active than both the pure aluminum and the as-quenched alloy. These and other observations are examined in terms of a mechanism of stress-corrosion cracking involving the spontaneous dissolution of MgZn_2 intermetallic, and the deformation-induced destruction of the bridges of solid solution separating the intermetallic particles.

INTRODUCTION

It is now well-established that stress-corrosion cracks in age-hardened Al-Zn-Mg alloys follow grain boundaries (1), and recent studies by Sedriks et. al. (2-4) have supported the view that the propagation of these cracks in aqueous chloride solutions occurs by localized anodic dissolution of the material in the grain boundary region. Furthermore, work by Brown et. al. (5) has shown that the solution at the tips of propagating stress-corrosion cracks in aluminum alloys contains aluminum ions and exhibits a "steady" $\text{pH} = \sim 3.5$.

As shown schematically in Fig. 1, the grain boundary in age-hardened (susceptible) Al-Zn-Mg alloys contains coarse $MgZn_2$ intermetallic particles and is delineated on both sides by a precipitate-free zone (PFZ). Hence, if the propagation of intergranular stress-corrosion cracks occurs by a dissolution mechanism, then it would be expected that the stress-corrosion processes would be governed by the corrosion behavior of the grain boundary constituents (i. e., the $MgZn_2$ intermetallic and the PFZ) in solutions of composition observed to exist at the crack tip (i. e. in solutions containing aluminum ions and having a $pH \sim 3.5$). Previous studies of the corrosion behavior of $MgZn_2$ have been carried out in either neutral solutions⁽⁶⁾ or solutions buffered to a $pH = 4.7$ ⁽⁷⁾.

For Al-Zn-Mg alloys which have been quenched and aged at temperatures below the G.P. zone solvus, the solid solution in the PFZ is considered to be "solute depleted"⁽⁸⁾, and in the limiting case approximates to pure aluminum. For alloys aged above the G.P. zone solvus the solid solution within the PFZ varies in composition. Near the $MgZn_2$ particles on the boundary plane the solid solution is "solute depleted". However, further away from these $MgZn_2$ particles the PFZ contains some solute which was prevented from precipitating by vacancy depletion⁽⁸⁾. In the limiting case this would correspond to the as-quenched alloy. Hence, the corrosion behavior of the solid solution within the PFZ would be expected to lie somewhere between the limits defined by the corrosion behavior of pure aluminum and the

as-quenched alloy. Accordingly, in attempting to determine the corrosion behavior of the grain boundary region a comparison was carried out of the polarization behavior and weight-loss data of pure aluminum, the as-quenched alloy, and the intermetallic $MgZn_2$.

EXPERIMENTAL

Studies were performed on a ternary Al-Zn-Mg alloy (5.35 Zn, 2.52 Mg, 0.01 Cu, 0.02 Fe, 0.025 Si, 0.02 Mn, 0.01 Cr and 0.003 Ti, weight percent), a high purity (99.999 pct) aluminum, and the intermetallic $MgZn_2$. The intermetallic, which was prepared from high purity materials, was kindly supplied by Dr. F.H. Cocks of the Tyco Corporate Technology Center.

On the basis of the arguments presented in a previous publication⁽⁹⁾, the solution at the tip of a propagating stress corrosion crack should have a pH of ~ 3.5 and contain $\sim 10.6\%$ $AlCl_3$. This solution represents the composition at which $Al(OH)_3$ begins to precipitate. In practice, however, it was found impossible to investigate the corrosion behavior in such a border-line solution because of the ease with which $Al(OH)_3$ could be precipitated on weight-loss specimens, electrodes and container walls. Consequently, the studies were carried out in two more "stable" solutions, i. e. a pH = 2.75, 10.6% $AlCl_3$ solution and a pH = 3.5, 2.05% $AlCl_3$ solution.

To determine weight-loss, the procedures outlined by Fontana and Greene⁽¹⁰⁾ were followed, and the results were expressed as "mils

per year" (mpy). In the polarization studies the cell and electrode arrangements adopted were similar to those described by Greene⁽¹¹⁾, although the use of sheet specimens made it necessary to modify the electrode holder and to use masking materials. In all cases polarization was commenced at the open circuit potential and the potential was increased at a stepping rate of 20 mV per min using a Wenking potentiostat in conjunction with a saturated calomel electrode (SCE). During all polarization studies the solution was stirred at a fixed rate.

Some straining electrode studies, also, were carried out which were aimed at establishing the re-passivation characteristics of the alloy. In these studies the specimens were mounted in polyethylene containers and gripped in a constant-load tensile test rig. The test solution was added and the open-circuit potential recorded prior to stressing. The potential was set at the open circuit value (zero net current) by means of the Wenking potentiostat. The specimen was then rapidly stressed in tension to a value above its yield stress, and the current required to maintain the set potential was obtained using a Clevite Brush Mark 250 recorder operating at a chart speed of 5 in/sec.

RESULTS

The weight-loss studies, carried out using the above solutions, showed that the $MgZn_2$ was in all cases more active than both pure aluminum and the as-quenched alloy. The open circuit potentials,

E_{CORR} , and the weight-loss data for these materials in the pH = 3.5, 2.05% AlCl_3 solution are shown in Table I. Typical anodic and cathodic polarization curves of the materials are shown in Figs. 2 and 3. These results clearly demonstrate that the MgZn_2 particles at the grain boundary will actively dissolve in "crack-tip solutions" while the solid within the PFZ will act as a cathode.

The straining electrode studies were aimed at establishing whether the solid within the PFZ would continue to dissolve actively or would re-passivate in the "crack-tip solution". To date, all the results indicate that the solid within the PFZ will rapidly passivate after the MgZn_2 particles have been dissolved. For example, Fig. 4 shows a typical trace of the build-up and decay of current after plastically deforming the Al-Zn-Mg alloy in the pH = 3.5, 2.05% AlCl_3 solution. While some of the current may be consumed by dissolution, it is evident from the trace that the surface becomes passivated within less than one second of the time the protective film is ruptured by plastic deformation.

DISCUSSION AND CONCLUSIONS

The present studies show that the solid within the PFZ is significantly noble (cathodic) in relation to the intermetallic MgZn_2 . Also, it is found that when the film on the solid solution is ruptured (e. g. by plastic deformation) it will rapidly reform to passivate the surface.

Since the MgZn_2 particles will rapidly dissolve in "crack-tip solutions", Table I, the mechanism of crack propagation then can be equated with the mechanism by which the crack progresses through the "bridges" of solid solution separating the MgZn_2 particles at the grain boundary. If it is argued that the crack propagates through these "bridges" by dissolution, not only is it necessary that the solid comprising these "bridges" be rendered active by plastic deformation, but also that this active state be maintained until the next MgZn_2 particle is reached by the crack front. Alternatively, it could be argued that the dissolution of the "bridges" is not necessary and that the sharp crevices left by the dissolved MgZn_2 particles will link by ductile rupture (i. e. plastic flow) enabling the crack front to reach MgZn_2 particles further along the boundary. However, a mechanism which does not involve the dissolution of aluminum is inconsistent with the observed composition of the solution at the crack tip. If dissolution was confined to MgZn_2 particles only, then a steady pH region of $\text{pH} = \sim 6.5$ would be expected⁽¹²⁾, as characterized by the solubility product of zinc hydroxide. Yet Brown et. al.⁽⁵⁾ have reported a $\text{pH} = \sim 3.5$ and the presence of aluminum ions in solutions in the steady pH region. Clearly, then, some dissolution of aluminum is occurring at the crack tip, with the pH being determined by the solubility product of aluminum hydroxide. However, it could be argued that while dissolution of aluminum does occur - for example at the fresh surfaces exposed by the ductile rupture process prior to

repassivation - the crack advances primarily by ductile rupture and not by dissolution. Thus, the unresolved mechanistic question at this stage is whether the crack advances through the "bridges" of solid solution separating the $MgZn_2$ particles by dissolution, ductile rupture, or by a combination of both processes, and further work should address itself to this question.

In terms of promising approaches to mitigate susceptibility to stress-corrosion cracking, the present work suggests that factors which influence the size and distribution of the $MgZn_2$ particles at the grain boundary plane may also influence susceptibility. For example, provided that other factors are kept constant, it would be expected that heat treatments or minor alloying additions which would yield increased $MgZn_2$ interparticle spacing along the boundary also would yield improved resistance to stress-corrosion cracking.

ACKNOWLEDGMENTS

The authors wish to thank Dr. A. R. C. Westwood of RIAS for valuable discussions. The financial support received from the Office of Naval Research under Contract N00014-67-C-0496, NR 031-716, is gratefully acknowledged.

REFERENCES

1. E. H. Dix, Jr., Trans. ASM, 42, 1057 (1950).
2. A. J. Sedriks, P. W. Slattery, and E. N. Pugh, Trans. ASM, 62, 238 (1969).
3. A. J. Sedriks, P. W. Slattery, and E. N. Pugh, Trans. ASM, 62, 815 (1969).
4. A. J. Sedriks, J. A. S. Green, and D. L. Novak, Met. Trans., 1, 1815 (1970).
5. B. F. Brown, C. T. Fujii, and E. P. Dahlberg, J. Electrochem. Soc., 116, 218 (1969).
6. G. M. Ugiansky, J. Kruger, and R. W. Staehle, "Electrochemical Behavior of Al-Zn-Mg Alloys", paper presented at the 1971 NACE Meeting, Chicago, Illinois, March 1971.
7. S. B. Brummer, R. O. Bell, F. H. Cocks, A. Cordellos, M. Krebs, and J. Russo, Fifth Quarterly Report to NASA (NAS 8-20297), Nov. 1967, Tyco Laboratories, Inc., Waltham, Mass.
8. G. W. Lorimer and R. B. Nicholson, Acta Met., 14, 1009 (1966).
9. A. J. Sedriks, J. A. S. Green and D. L. Novak, Corrosion - NACE, 27, 198 (1971).
10. M. G. Fontana and N. D. Greene, Corrosion Engineering, p. 8, McGraw-Hill Book Co., New York (1967).
11. N. D. Greene, Experimental Electrode Kinetics, Rensselaer Polytechnic Institute, Troy, New York (1965).
12. A. J. Sedriks, J. A. S. Green, and D. L. Novak, Proceedings of the U. R. Evans International Conf. on Localized Corrosion, Dec. 1971, Williamsburg, in press.

TABLE I

Open-circuit potentials. E_{CORR} , and weight loss of various materials in a solution of pH = 3.5 containing 2.05% AlCl_3 .

<u>Material</u>	<u>E_{CORR}</u> (mV vs. SCE)	<u>Weight-Loss</u> (mpy)
Pure aluminum	- 720	3.1
As-quenched Al-Zn-Mg	- 900	5.5
MgZn_2	- 1035	52.8




Fig. 1. A schematic representation of the grain boundary region in an Al-Zn-Mg alloy aged above the G.P. zone solvus.




Fig. 2. Potential-anodic current density variation.




Fig. 3. Potential-cathodic current density variation.




Fig. 4. Potentiostatic current flow, as a function of time, resulting from the disruption of the surface film by plastic deformation.