UNCLASSIFIED

AD NUMBER

AD828188

LIMITATION CHANGES

TO:

Approved for public release; distribution is unlimited.

FROM:

Distribution: Further dissemination only as directed by Air Force Materials Laboratory, Wright-Patterson AB, OH 45433, JAN 1968, or higher DoD authority.

AUTHORITY

AFML ltr, 7 Dec 1972

THIS PAGE IS UNCLASSIFIED

AD828188

RESEARCH FOR IMPROVED SUBSONIC AND SUPERSONIC RAIN EROSION RESISTANT MATERIALS

GEORGE F. SCHMITT, JR.

TECHNICAL REPORT AFML-TR-67-211

JANUARY 1968

This document may be further distributed by any holder <u>only</u> with specific prior approval of the Elastomers and Coatings Branch (MANE), Nonmetallic Materials Division, Air Force Materials Laboratory, Wright-Patterson Air Force Base, Ohio 45433.

AIR FORCE MATERIALS LABORATORY AIR FORCE SYSTEMS COMMAND WRIGHT-PATTERSON AIR FORCE BASE, OHIO



MAR 1 2 1968

NOTICE

When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the United States Government thereby incurs no responsibility nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data, is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use, or sell any patented invention that may in any way be related thereto.

Copies of this report should not be returned unless return is required by security considerations, contractual obligations, or notice on a specific document.

200 - February 1968 - CO455 - 25-555

-

RESEARCH FOR IMPROVED SUBSONIC AND SUPERSONIC RAIN EROSION RESISTANT MATERIALS

GEORGE F. SCHMITT, JR.

This document may be further distributed by any holder only with specific prior approval of the Elastomers and Coatings Branch (MANE), Nonmetallic Materials Division, Air Force Materials Laboratory, Wright-Patterson Air Force Base, Ohio 45433.

FOREWORL

This report was prepared by the Elastomers and Coatings Branch, Nonmetallic Materials Division, Air Force Materials Laboratory, under Project No. 7340, "Nonmetallic and Composite Materials," Task No. 734007, "Coatings for Energy Utilization, Control, and Protective Functions." The work was conducted with George F. Schmitt, Jr. acting as Project Engineer.

This report covers a period from 1 May 1964 to 30 April 1966.

Manuscript released by the author for publication July 1967.

The author wishes to express his grateful appreciation to Messrs C. J. Hurley, R. L. Vissoc, and H. Maas, of the University of Dayton Research Institute for their assistance and operation of the whirling-arm equipment, to Mr. Harold A. Schuetz of the Air Force Aero Propulsion Laboratory for his advice and assistance in developing the whirling-arm capability and keeping it running, and to Mr. James H. Weaver of the Air Force Materials Laboratory for his preparation of the metal-plated specimens used during this investigation.

This technical report has been reviewed and is approved.

W. P. JOHNSON, Acting Chief Elastomers and Coatings Branch Nonmetallic Materials Division

ABSTRACT

Investigations of advanced coatings materials performed on a whirling-arm rain erosion simulation device at 500 mph have led to new protective coatings which are capable of providing protection against damage from rain droplet impingement at subsonic velocities. Polyurethane coatings were determined to be the most erosion resistant of the elastomericpolymeric materials currently available. These polyurethanes are a considerable improvement over the specification neoprene $ero \varepsilon_{100}$ coating. Plasma-sprayed ceramic coatings of alumina and alumina/titania are potentially applicable for supersonic erosion protection where dielectric properties must be maintained. Electroplated nickel coatings directly applied to plastic laminates will provide several orders of magnitude improvement in erosion resistance over conventional elastomeric coatings.

(This abstract may be further distributed by any holder <u>only</u> with specific prior approval of the Elastomers and Coatings Branch (MANE) Nonmetallic Materials Division, Air Force Materials Laboratory, Wright-Patterson AFC, Ohio 45433.)

TABLE OF CONTENTS

SECTION		PAGE
I.	INTRODUCTION	1
п.	PHENOMENON OF RAIN EROSION	2
III.	REQUIREMENTS FOR RAIN EROSION RESISTANT MATERIALS	3
	Subsonic Rain Erosion Resistant Coatings	3
	Supersonic Rain Erosion Resistant Coatings	3
	Anticipated Future Requirements	4
IV.	LABORATORY EQUIPMENT	5
v.	VARIABLES STUDIES	6
	Measurement of Drop Size and Shape	6
	Effect of Rainfall Rate, Drop Size, and Velocity	6
VI.	MATERIALS INVESTIGATION	8
	Elastomers-Polymers	8
	Ceramics	9
	Metals	10
VII.	DISCUSSION	11
VIII.	CONCLUSIONS	12
IX.	FUTURE WORK	13
Х.	REFERENCES	14

v

.

ILLUSTRATIONS

FIGURE		PAGE
1.	Hypothetical Flight Plan for a M3 Aircraft	34
2	Flight Plan for M2.2 Supersonic Transport	35
	Hypothetical Flight Plan for M3 Supersonic Transport	36
4 .	6 Foot Diameter Rain Erosion Facility (Inside of Test Enclosure)	37
5.	6 Foot Diameter Rain Erosion Facility (Spray Ring, Whirling- Arm, and Periscope Tube)	38
6.	6 Foot Diameter Rain Erosion Facility (Test Enclosure and Periscope Tube Location)	39
7.	6 Foot Diameter Rain Erosion Facility Control Room (Telescope Mount, Strobe Power Unit, and Motor Load Bank)	40
8.	6 Foot Diameter Rain Erosion Facility Control Room (Motor Controls and Test Instrumentation)	41
9.	Aluminum Subsonic Rain Erosion Specimen (1/8" Leading Edge Radius)	42
10.	Larninate Subsonic Rain Erosion Specimen (3/32 " Leading Edge Redius)	43
11.	Conformal Aluminum or Laminate Subsonic Rain Erosion Specimen	44
12.	Effect of Needle Size on Drop Size (15- and 18-Gauge Needles)	45
13.	Effect of Needle Size on Drop Size (19- and 20-Gauge Needles)	46
14.	Effect of Pressure on Drop Size (5 and 20 PSI)	47
15.	Effect of Needle Size and Pressure on Drop Size (15- and 22-Gauge Needles)	48
16.	Effect of Velocity on Erosion of Neoprene Coatings (4 inches/hour Rainfall)	49
17.	Effect of Velocity on Erosion of Neoprene Coatings (8 inches/hour Rainfall)	50
18	Effect of Rainfall Rate on Erosion of Neoprene Coatings	51
19	. Erosion Thickness Dependence of Urethane and Neoprene Coatings	52
20	. Comparative Erosion Resistance of Materials (Applied as Coatings up to 35 mils Thick)	53

TABLES

TABLE		PAGE
I	Summary of Rain Erosion Requirements	15
II	Sizes of Water Drops from Hypodermic Syringes at Varying Line Pressures	16
111	Erosion Times as a Function of Velocity, Drop Size, and Rainfall Rate	17
IV	Evaluation of Specification Neoprene at Varying Thicknesses on Aluminum Substrates	20
v	Exposure Times for Elastomeric-Polymeric Materials on 1/8-in. L. E. Aluminum Specimens	21
VI	Exposure Times for Uncoated and Elastomeric-Coated 3/32-in. L. E. Glass Laminate Specimens	23
VII	Exposure Times for Elastomeric-Polymeric Materials on Conformal Aluminum Specimens	24
VIII	Exposure Times for Elastomeric-Polymeric Materials on Conformal Laminate Specimens	25
IX	Exposure Times for Ceramic Materials on Aluminum Substrates	27
x	Exposure Times for Ceramic Materials on Laminate Substrates	29
XI	Exposure Times of Metal Specimens	30

۱ ر

SECTION I

INTRODUCTION

The investigation of the phenomenon known as rain erosion, that is, materials damage caused by the impingement of rain droplets at high speeds, has long been a concern of the United States Air Force. The Air Force Materials Laboratory at Wright-Patterson Air Force Base has conducted and sponsored rain erosion research since 1947 when such erosion was first observed on aircraft flying at speeds of 400 MPH and above.

Past research on rain erosion has been principally concerned with mechanism studies which were conducted by Engel (Reference 1), materials research by Wahl and others (Reference 2), and laboratory simulation techniques by Beal and Wahl (Reference 3). These investigations were continued at a high level of effort until 1957 when they were considerably reduced.

With the ever-increasing use of fighter aircraft that fly supersonically and missiles that operate in a supersonic regime or are carried externally on high speed aircraft and repeatedly exposed, the "rain erosion" of the nose sections and leading edges on these systems became a major concern for their efficient all-weather operation. By 1964 the pressing problems introduced by these increased supersonic and high subsonic speed flights and the severe rain erosion damage at these velocities necessitated reactivating research and experimentation in this area. Such work is currently being pursued at an accelerated rate of effort by the Air Force Materials Laboratory.

An excellent state-of-the-art survey summarizing investigations in rain erosion over the past twenty years has been published (Reference 4). This report contains a comprehensive bibliography of rain erosion publications during this period and serves as a basis for much of the work currently being conducted.

The work reported includes investigation of improved materials for subsonic and possibly supersonic rain erosion resistance by use of a whirling-arm simulation device. The purpose is to provide a better insight into the phenomenon of rain erosion, an investigation of promising materials and resultant damage caused by water droplet impact, and information on which to base future contractual and in-house research.

SECTION II

PHENOMENON OF RAIN EROSION

Resistance to erosion by water drops is more than simply impact or abrasion resistance. The phenomenon is characterized by two distinct actions. The first is the impact of the drop striking the aircraft or missile; at high speeds this is like a solid particle hitting the system. The second is a radial flow of water as the drop fragments. This rush of water in a radial direction is at a velocity approximately three to four times that of the impact velocity and sets up high shear stresses in the coating or surface material.

There are almost as many suggested mechanisms of erosion failure as there are classes of materials (Reference 1). Thin resilient coatings such as neoprenes or polyurethanes will transmit the shear stress to the substrate causing a failure in the adhesive bond. Additional impacts on this same area cause the coating to stretch or deform, 'bubble'' and then burst under repeated impingement.

Plastic type materials and soft metals flow plastically under the compressive stress of the water impact resulting in cratering and pitting. The pits or craters grow in size until rapid erosion occurs.

Plastic laminated materials will fail by eroding away of the upper layers of fabric resulting in holes in the surface. This erosion is often rapid enough to cause structural failure of the entire component.

Another form of failure is that associated with materials which do not deform under impact loads, such as ceramics and high hardness metals. These impacts cause small imperfections in the surface to be removed with subsequent work hardening and fracture in the pits formed. As these imperfections are removed, protrusions are formed against which the flowing liquid acts to exert a shear stress and a turning moment. Once again failure of the coating or surface may result.

The mechanisms described above operate at subsonic speeds and are sure to be compounded at supersonic velocities.

SECTION III

REQUIREMENTS FOR RAIN EROSION RESISTANT MATERIALS

The needs for protective materials to resist the impacts and shear stresses of rain drops actually fall into two broad classes; i.e., subsonic protection and supersonic protection. The absonic regime is of interest because of applications for aircraft and helicopter blades ich may be exposed to rain environments at high subsonic speeds. Supersonic exposure ay be excerienced on advanced supersonic aircraft and missiles where penetration of rain clouds may be necessary and desirable for tactical and evasive purposes.

SUBSONIC RAIN EROSION RESISTANT COATINGS

Protection of subsonic aircraft and helicopter rotor blades is currently accomplished by neoprene coatings (sprayed, brushed, or prefabricated boots) applied to leading edges and radomes. This material has been in use for over 10 years and, while it does afford some protection, it has severe limitations. At speeds greater than 500 MPH, the temperature limitations (max 200°F) become a problem; the neoprene coating also will not withstand the more severe impacts and shear stresses at these higher speeds. Another limitation is its poor weathering characteristics when exposed to ultraviolet light and ozone.

Extreme care must be taken during application of the neoprene to obtain a smooth surface since its erosion resistance is highly sensitive to the coating process.

The need for an improved elastomeric coating to protect reinforced plastic radomes, helicopter blades, etc. from subsonic rain impacts is wide-spread and vital. A nonmetallic coating is needed for protection of radomes because of the incompatibility of metals with radar (both offensively and defensively). If an elastomeric material can be found to withstand the shear and impact stresses on the surface exposed to the rain and still retain enough integrity to prevent this stress from destroying the adhesive bond, protection can be afforded the structural component coated with this material.

Another area of concern for coatings which possess subsonic erosion resistance is the high temperatures supersonic aircraft and missiles may experience in flight, although not necessarily in rain. These may reach 400°F at Mach 2 and 650°F at Mach 3, which are beyond the capability of most available elastomeric coatings. New subsonic protective coatings must retain their resistance after the high temperature exposure.

SUPERSONIC RAIN EROSION RESISTANT COATINGS

Pilots are presently instructed to avoid rain at supersonic speeds. However, for low level aircraft dash missions and high speed missiles, it is necessary to be able to penetrate rainstorms supersonically since avoidance is often impossible or even undesirable. Unprotected parts of aircraft and missiles such as radomes in this type of exposure will be destroyed in a matter of seconds. To overcome this problem, ceramic caps or all-ceramic radomes are currently used on a limited basis in lieu of plastic radomes. However, these are limited because of inherent brittleness, matching problems and structural weaknesses of the ceramics.

It has been shown that in order to obtain sufficient erosion resistance, a ceramic must be applied in a highly dense form. Again the use of metals for this purpose is prohibited because of radar transmission requirements. In 1960 Engel (Reference 5), and earlier, Wahl and co-workers (Reference 6) at Cornell, presented theoretical and experimental data leading to the conclusion that both hot pressed aluminum oxide and white sapphire (single crystal alpha alumina) are essentially not eroded by 2 mm water drops at speeds up to Mach 10.

The supersonic high performance tactical missile regime presents still another difficulty which cannot be avoided and that is the problem of extremes of erosion and elevated temperature. The ceramics will certainly withstand temperatures up to 1200°F in air but developing a plastic laminate which will withstand such temperatures is another problem. The areas of thermal matching of the protective ceramic coating with the plastic substrate, as well as thermal shock and adhesion, drastically complicate the situation. Times at temperature generally decrease as velocity increases.

An area in which use of metals is permissible, would be exposed structural components of advanced systems where radar compatibility is not a prime requirement. This would also apply in very high speed turbines and compressors, now being designed, in which damage to blades from water drops and dust particles is of concern

ANTICIPATED FUTURE REQUIREMENTS

Based on projected flight profiles of advanced systems (References 7 and 8), the following requirements for rain erosion protection can be projected. (See Figures 1, 2 and 3.) A typical Mach 3 military aircraft on a 21/2 hour mission has the possibility of encountering rain of 0.1-0.3 inches/hour at Mach 0.9 for 50 minutes and rain of up to 2.0 inches/hour at Mach 1.2 for as much as 30 minutes. (See Figure 11.) Although the probability of its being in the rain for all this time is very low, if it is exposed to rain 10 percent of the mission, this would represent a significant amount of rain exposure. When this is projected over the service life of the aircraft, the requirement appears to be sufficient resistance to withstand rainfall of 2.0 inches/hour at Mach 1.5 for one hour. Fortunately the flight speeds above Mach 2 are at altitudes where rain is insignificant; however, the temperature cycling problem is still pertinent.

The needs for a Mach 2.2 supersonic transport are not quite as severe but still require an improvement in the state-of-the-art. A supersonic transport of this type on a run from London to New York which would consume about 192 minutes has the possibility of experiencing 32 minutes at Mach 0.9 in rainfall ranging from 0.2 to 1.9 inches/hour. Again the probability exists of encountering rain for only a small fraction of the flight time. Assuming a 30,000 flight hour life of the aircraft, the amount of possible and probable rain exposure becomes large.

The Mach 3 supersonic transport will experience a limited amount of rain because of its flight profile. Upon a typical departure from JFK International Airport it might experience 10 minutes in rain of 0.1 to 2.0 inches/hour. Upon arrival at the same airport from across the Atlantic it might undergo 11-15 minutes in 0.1 to 1.25 inches/hour rainfall. Here again a 30,000 flight hour life would require rain erosion resistance of at least an hour at Mach 1. As mentioned before, the thermal cycling environment of 650°F for Mach 3 is a major consideration. See Table I for a summary of anticipated rain erosion requirements.

With the above requirements becoming increasingly vital, this AFML investigation was undertaken to provide a basis for decision-making and direction of future coatings research to overcome the rain erosion problem.

SECTION IV

LABORATORY EQUIPMENT

Subsonic rain erosion investigations were conducted on an apparatus located in Building 20A at Wright-Patterson Air Force Base, Ohio. This equipment consisted of a 6-foot diameter propeller blade made of tempered boiler plate mounted vertically on a 100 horsepower electric motor. At 2400 RPM it was capable of attaining speeds of 500 miles per hour at the blade tip. (This equipment was disassembled and removed at the conclusion of the research reported herein to be replaced by a supersonic whirling-arm rig.)

The speed of the equipment was regulated by a resistor bank from which rigid control was possible. A revolution counter was utilized for monitoring velocity along with vibration pickups for gauging specimen balance and smooth operation. The specimens were observed during operation by use of a mirror and periscope arrangement and a stroboscopic unit synchronized with the blade revolutions. This system enabled the observer to note the time of coating failure; i.e., penetration to the substrate or loss of adhesion.

The water system used to simulate the rain environment consisted of a 6-foot diameter circle of 2-inch pipe equipped with twelve equally spaced hypodermic needles to yield a rainfall simulation of from 2 to 24 inches per hour. The hypodermic needles were 18-gauge (1.245 mm ID) which produce rain droplets of 1.5-2.0 mm diameter as determined photographically. The water system operated with 35 psig in the spray ring; this pressure enabled a stream of waterdrops to impinge on the material specimens (which were inserted in the blade tip) without distortion when running.

The whirling-arm apparatus is shown in Figures 4-8.

The specimen configurations were of several types: 1/8-inch leading edge aluminum, 3/32-inch leading edge laminate specimens, and conformal specimens of aluminum or various laminated materials. (See Figures 9, 10, and 11 for these configurations.) The conformal specimens were employed extensively since they were easy to coat and their low drag and light weight enabled efficient operation of the apparatus.

SECTION V

VARIABLES STUDIES

The simulation of the rain environment which an aircraft flying at subsonic velocities would encounter, is a very difficult experimental task. The use of a whirling-arm device enables attainment of velocity, and the water system described provides repeated water impacts which are necessary for true simulation. The other variables which must be considered in designing an evaluation technique for rain erosion resistance are numerous and difficult to correlate. Among these are velocity of test specimen, rainfall intensity, rain droplet size and shape, configuration of leading edge upon which the material is applied, deciding when a material has failed, isolating erosion failures from adhesive failures, etc.

A number of studies have been conducted on the 500 MPH equipment and are described below:

MEASUREMENT OF DROP SIZE AND SHAPE

A unique method of measuring drop size and shape has been developed by Mr. Harold A. Schuetz of the Air Force Aero Propulsion Laboratory. In this technique a stroboscopic unit is focused on the water stream from a hypodermic syringe. The firing time of the unit is adjusted so that the individual droplets may be seen.

The water stream is positioned in front of a Plexiglass sheet on which a 1 by 1 cm grid has been scribed. A Polaroid camera is adjusted so that the strobe unit will flash enough times in its shutter time to permit taking of photographs.

A series of runs was made with different sizes of needles (15, 18, 19, 20, 22, 23 and 26gauge) at varying line pressures (2.5, 5, 10, 15 and 20 PSIG). See Table II. The droplet size was highly dependent on needle gauge and somewhat dependent on line pressure. A sample of photographs taken is shown in Figure 12-15 which illustrates the effect of needle size and line pressure on droplet configuration.

EFFECT OF RAINFALL RATE, DROP SIZE, AND VELOCITY

A study of the effect of rainfall rate, drop size, and velocity on the erosion characteristics of various materials was conducted. Two basic materials were chosen: a specification black neoprene coating and a polyurethane boot. These were applied to the 1/8-inch leading edge aluminum specimens for evaluation.

Runs were made at several speeds (300, 400, 450 and 500 MPH) in four to eight inches per hour of simulated rain with drop sizes of 2.5 mm diameter (15-gauge needle), 1.8 mm diameter (18-gauge needle), and 0.4 mm diameter (22-gauge needle). The results of these evaluations are shown in Table III and Figures 16-18. As expected, erosion was more severe with increasing speed and failure times were considerably faster in the heavier rainfall. The larger drops also promoted an increased rate of erosion.

The erosion resistance of the urethane system was approximately twice that of the neoprene. However, it should be pointed out that the thickness of the urethane coating was also approximately three times that of the neoprene. Other urethanes investigated have exhibited resistance three to four times that of the specification neoprene material at similar thicknesses of the two materials (See Figure 19).

Additional specimens of the neoprene coating at varying thicknesses on the conformal aluminum specimens prepared by brushing or dip-coating were also evaluated at 500 MPH in 2 inches/hour rainfall as a base line. The results of this investigation are summarized in Table IV. Once again the erosion rate was directly a function of rainfall rate, drop size, and velocity.

SECTION VI

MATERIALS INVESTIGATION

The investigation of numerous materials for their rainerosion resistance was concentrated on several classes of coatings and structural materials. The classes of materials included polymeric-elastomeric materials, ceramics, metals, and reinforced plastic laminates. The emphasis has been on nonmetallic materials since protection of electromagnetic windows which require a nonmetallic surface is of prime concern. However, for aircraft leading edges and coatings on turbine and compressor blades of engines, the use of metals is pertinent.

The examinations of materials were initially conducted by applying coatings on the 1/8-inch leading edge aluminum specimens (See Figure 9) and the 3/32-inch leading edge laminate specimens (See Figure 10); these specimens were then exposed to a simulated rain environment of 24 or 12 inches/hour rainfall at 500 MPH. The rainfall rate was later reduced to 2 inches/hour to more nearly correspond with what might actually be experienced in a practical case. The specimen holder on the whirling-arm was later adapted to accommodate the conformal aluminum and laminate specimens (See Figure 11), which are identical in configuration to the specimens previously employed at Cornell Aeronautical Laboratory from 1950 to 1959 (Reference 2). The rain erosion protective coatings specifications (Mil-C-7439B and C-27315) were developed using this specimen shape (References 9 and 10). The only change necessary was to use a specimen 2.5 inches long rather than 5 inches long.

All evaluations were conducted at 500 miles per hour with most being conducted in 2 inches/ hour simulated rainfall.

ELASTOMERS-POLYMERS

The polymeric-elastomeric materials evaluated on the 1/8-inch leading edge radius specimens indicated that polyurethane elastomers were the most promising for protection from rain. Other elastomers and/or polymers investigated included:

fluorosilicones dimethyl silicones silicone sealants and rubbers carborane-silicone copolymer polyimides (2 kinds) phenoxy polymers (3 kinds) poly-paraxylylene ionomer films (2 kinds) urethane tapes black neoprene white neoprene neoprene over Kel-F paint-on urethanes (5 kinds) elastomeric urethanes (6 kinds)

The evaluations of these materials on the 1/8-inch leading edge radius aluminum and 3/32-inch leading edge radius laminates are summarized in Tables V and VI respectively.

Since the adaptation of the whirling arm to utilize the conformal specimen configuration, additional elastomeric type materials have been examined on aluminum and reinforced laminates. These include:

polycarbonate sheet neoprene boots with gum rubber and/or Dacron cloth backing sprayed neoprene cork sheet abrasive tapes (5 kinds) Teflon sheet unfilled urethanes fluidized-bed epoxy fluidized-bed silicone-epoxy Plexiglas sheet Nitroso polymer formulations (2 kinds)

These results are included in Tables VII and VIII.

The evaluations of all elastomeric materials have indicated that polyurethanes exhibit superior erosion resistance compared to other elastomers as materials per se. However, when they are applied as coatings or as sheets bonded on the substrates, difficulties with adhesion, cold flow of the urethane films, and structural failure by chipping away of the coating are experienced. The neoprene material on the other hand, erodes more rapidly and uniformly by a gradual wearing-away of the surface. Of the other elastomers examined, most exhibited inferior resistance to the rain impacts with some (ionomers, glass resins, Teflon) failing because of brittleness. It should be noted that none of these materials, or the urethanes, for that matter, were formulated or developed specifically for rain erosion protection. Therefore, failures in rain should by no means be construed as indicating inferiority of these materials for other applications.

CERAMICS

The need for nonmetallic materials which withstand supersonic rain impact has prompted the evaluation of numerous ceramic materials. A number of materials were evaluated including alumina, silica, titania and zirconia. These were generally examined as thin coatings (0.030-in. or less) over plastic laminates or aluminum substrates.

Since the ceramics must be in a highly dense form to possess sufficient rain erosion resistance, methods of depositing dense coatings were investigated. Among the techniques examined were flame spraying, plasma spraying, high solids film casting, spraying on a male mold and then bonding the coating to the laminate, or spraying on a mold and then laying up a laminate on the inside.

The substrates on which the ceramics were evaluated included 1/32-inch leading edge radius aluminum, 1/8-inch leading edge radius aluminum, conformal aluminum specimens, and PBI and polyester laminates with a 3/32-inch leading edge radius.

Of the methods of application examined, plasma-spraying produced ceramic coatings with the highest level of resistance. The flame-sprayed coatings also resisted the rain but not as well.

A principal difficulty anticipated and experienced was that of coating-metal or coatinglaminate interfacial adhesion. In many instances the failure of the material under the influence of rain impact was a bond failure rather than erosion or brittle fracture. Several surface preparation techniques were employed to improve this interfacial adhesion such as grit blasting, porcelain enamel primers, and special adhesives with only limited success.

Despite the difficulties and shortcomings of the ceramic materials examined, it is believed that this class of materials offers the best hope for erosion resistant nonmetallic coatings capable of providing protection at supersonic velocities in the rain environment.

The evaluation of the ceramics applied by various techniques on the aluminum substrates are summarized in Table IX while those of ceramics on plastic laminates are included in Table X.

METALS

Metals are necessary for leading edge surfaces, helicopter rotor blades, compressor blade surfaces, and other structural components of aircraft, and must be considered for the possible damage they may suffer when exposed to rain. A number of metallic surfaces have been exposed to the rain environment for varying periods and the soft metals, for examples, aluminum, flow plastically upon repeated impact with cratering and pit formation. Hard metals such as stainless steel, titanium, and nickel, withstand the impact and shear forces for extended periods in rain.

Several techniques for obtaining thin metal coatings, for example electroplating and plasma spraying of metal mixtures, have also been examined. Plastic reinforced laminates coated with electroplated metals have been prepared for this study by Mr. James H. Weaver of the Elastomers and Coatings Branch, Air Force Materials Laboratory (Reference 11). These plated metals, particularly nickel, have exhibited outstanding resistance to rain erosion on metallic and plastic laminate substrates. It is believed that the use of electroplated metals may be an improvement in the state-of-the-art for rain protection where metal surfaces are allowable.

The results of metal surface investigations are presented in Table XI.

For a relative ranking of the resistance of various classes of materials, see Figure 20.

.....

ť, •

SECTION VII

DISCUSSION

The superior performance of the polyurethane materials in resisting the subsonic rain environment may be attributed to several factors. The urethanes are tougher than many other elastomers and simply have sufficient strength (impact, tensile, abrasion resistance) to withstand the rain impact.

The neoprene material performs relatively well in rainbecause of its resiliency and ability to recover between successive impacts. Although the polyurethanes are not as resilient in general, as the neoprene, a material based on urethanes but designed specifically for resistance to rain damage will lead to an improved erosion protective coating. A research program with that specific goal is now being conducted under Air Force sponsorship. This effort will study the chemical structure, physical properties, and rain erosion resistance of urethanes, and will develop a substantially superior subsonic rain-resistant coating.

The high density ceramics needed for supersonic rain erosion protection are desirable as thin coatings because of weight reduction and efficient electromagnetic design considerations. With this in mind, the bulk densities required for erosion resistance are difficult to obtain in a 30 mil coating (an upper limit for design purposes).

Of the methods currently available for depositing inorganic oxide ceramics with reasonable control over density as a function of process conditions and a relatively high deposition rate, plasma spraying appears to offer the most promise for obtaining and controlling the thin dense ceramic surfaces. Other techniques include flame spraying, vacuum evaporation, sputtering, and chemical vapor deposition. However, on the basis of evaluations conducted in this program, the plasma spraying should yield supersonic protective coatings.

Based on the above considerations, the Air Force is sponsoring a research effort to investigate plasma-spraying and chemical vapor deposition and their process variables as a route to obtaining thin, dense, adherent ceramic coatings.

It is readily apparent that the subsonic and supersonic rain environments present a difficult challenge for protective coatings. Progress is being made with hopes for new and improved protective coatings for both regimes.

The plating of nickel coatings on plastic laminates for rain erosion resistance is one of the significant improvements to arise from this investigation. The nickel withstands the rain impacts for long periods of time with no erosion evident, if care is taken to obtain good adhesion to the plastic substrate. Unfortunately the electromagnetic requirements for radomes, which necessitate the use of nonmetallic materials, preclude protection of these surfaces with the electrodeposited nickel. It is expected that the use of these plated coatings will provide substantial improvements in protection of plastic leading edges for aircraft and compressor blades, rotor blades, and other structural applications.

The failure times on the whirling-arm facility at Wright-Patterson Air Force Base are considerably faster than those obtained on other whirling-arm equipment. This may be attributed to the nature of the water injection system in which a small stream of water droplets must be propelled horizontally at a reasonably high pressure in order to reach the specimens while rotating and mounted on the vertical blade tip. The multiple water drop impacts per revolution with this technique actually simulates a much higher rainfall intensity than the nominal rate based on water flow measurements and area exposed. Further, the relaxation and recovery times for elastomers passing intermittently through the water streams from the needles may be such as to prolong the life of these materials in the rain environment.

The results indicated for various materials do give a relative ranking of their rain erosion resistance similar to those obtained on other whirling-arm devices even though orders of magnitude are different.

SECTION VIII

CONCLUSIONS

1. Of the elastomeric-polymeric materials currently available, the polyurethanes withstand subsonic rain damage best.

2. The rain erosion resistance of the polyurethanes is thickness-dependent up to 15 mils, (this is also true for specification neoprene and other materials at varying thicknesses).

3. Coatings of improved polyurethanes designed specifically for rain erosion resistance, should offer substantially improved protection against rain impact and shear forces at subsonic velocities when compared with the difficult-to-apply neoprene.

4. Dense oxide ceramics offer the best hope for nonmetallic supersonic erosion resistant materials.

5. Plasma-spraying of ceramics is a deposition process with considerable promise for obtaining thin, dense, and adherent coatings.

6. Electroplated nickel over plastic reinforced laminates offers several orders of magnitude improvement over conventional elastomeric or even ceramic rain erosion protective coatings. The application of plated coatings is limited to instances where electromagnetic considerations do not dictate a nonmetallic coating.

SECTION IX

FUTURE WORK

1. The Air Force Materials Laboratory's whirling-arm capability has been completely rede_igned and a new apparatus capable of variable speeds to Mach 1.2 will be constructed. This equipment will utilize an 8-foot 4340 steel, double-arm blade operating in a horizontal position and powered by a 400 HP motor. Other features will include an improved rain simulation system and an optical viewing system utilizing closed circuit television.

2. Use of the above equipment when completed will enable increased emphasis on ceramic materials for supersonic protection. Evaluations can be conducted supersonically where they have been made at 500 MPH in the past for lack of a supersonic capability.

3. Several materials systems will be examined, including oxide ceramics and plated materials applied over elastomeric coatings, to give a hard surface and a "bumper" effect.

4. Additional research in the protection of plastics by plated metals will be conducted. This will be extended to sand erosion resistance investigations in an attempt to utilize its protective ability for helicopter rotor blade and aircraft engine compressor blade applications.

5. Correlations will be made between actual flight tests, such as the Rough Rider series, and experimental results obtained on the whirling arm. Other promising materials will be flight tested, where possible.

6. The evaluation of promising new materials for subsonic and supersonic applications will continue as before.

SECTION X

REFERENCES

- 1. Olive G. Engel, <u>Mechanism of Rain Erosion A Review and Evaluation of the Present</u> <u>State of the Problem</u>, WADC Technical Report 53-192, Part X, December 1957.
- 2. N. E. Wahl, R. R. Lapp, and R. H. Stutzman, <u>Summary Report on the Rain Erosion of</u> <u>Aircraft Materials</u>, WADC Technical Report 53-185, Part V, October 1958.
- 3. J. L. Beal, and N. E. Wahl, <u>Study and Design of A Supersonic Rotating Arm Rain Erosion</u> <u>Test Apparatus</u>, WADC Technical Report 57-435, October 1957.
- 4. N. E. Wahl, <u>Investigation of the Phenomena of Rain Erosion at Subsonic and Supersonic</u> <u>Speeds</u>, AFML-TR 65-330, October 1965.
- 5. Olive G. Engel, <u>Mechanism of Rain Erosion-Resistance of White Sapphire and Hot-</u> <u>Pressed Alumina to Collision with Liquid Drops</u>, WADC Technical Report 53-192, Part XV, June 1960.
- 6. Wahl, Lapp and Stutzman, op cit.
- 7. G. H. Underwood, "Transparencies for Supersonic and Hypersonic Flight," <u>Aircraft</u> Engineering, Vol XXXVI, No. 12, p. 379, December 1964.
- 8. <u>Proceedings of the Conference on Aircraft Operating Problems</u>, Langley Research Center, National Aeronautics and Space Administration, 10-12 May 1965.
- Military Specification MIL-C-7439B, Coating System, Elasumeric Rain Erosion Resistant and Rain Erosion Resistant with Anti-Static Treatment for Exterior Aircraft and Missile Plastic Parts, 4 February 1955.
- 10. Military Specification MIL-C-27315 (USAF), <u>Coating Systems, Elastomeric, Thermally</u> <u>Reflective and Rain Erosion Resistant</u>, 9 December 1959.
- 11. J. H. Weaver, <u>Nickel Electroplated Nonconductive Materials for Rain Erosion Protection</u>, AFML-TR-68.

TABLE I

SUMMARY OF RAIN EROSION REQUIREMENTS

System	Time at Speed in Rain	Maximum Temperature
Present tactical support aircraft	30 min @500 mph	200 ⁰ F
Improved tactical support aircraft	30 min up to Mach 2.0 (low level)	450 ⁰ F
Mach 3.0 military	120 min @Mach 0.9 + 60 min @Mach 1.5	650 ⁰ F
Mach 2.2 SST	300 min @Mach 0.9	500 ⁰ F
Mach 3.0 SST	60 min @Mach 1.0	650 ⁰ f
High performance missile (to Mach 5.0)	up to 30 sec; up to Mach 5.0	2000 ⁰ F

-

-1

4

*

TABLE II

Gauge No.*	Inside Diameter of Needle, mm	Line Pressure, PSIG	Average Size of Drop. mm
15	1 829	9.5	
	1.023	2.5	3.0
		5.0	2.8
		10.0	2.5
		15.0	2.5
1		20.0	2.5
18	1.245	2.5	2.0
		5.0	1.0
		10 0	1.0
		15.0	1.0
		20.0	1.0
19	1.067	20.0	1.0
		5.0	1.3
		10.0	1.1
		15.0	0.9
		20.0	0.05
20	0.889	2 5	0.0
_		5.0	0.0
		10 0	0.7
		15.0	0.6
		20.0	0.0
22	0.711	2.5	0.0
		5.0	0.5
		10.0	0.4
		15.0	0.4
		20.0	0.0
23	0.635	2.5	0.2
		5.0	0.2
		10.0	0.15
		15.0	0.15
		20.0	0.15
26	0.457	5.0	0.3
	1	10.0	0 15
	1	15.0	
		20.0	0.1
*Corresponds to B	irmingham Wire Gauge		

SIZES OF WATER DROPS FROM HYPODERMIC SYRINGES AT VARYING LINE PRESSURE

Η
9
AB
E.

EROSION TIMES AS A FUNCTION OF VELOCITY, DROP SIZE, AND RAINFALL RATE

Comments	No erosion	No erosion	Erosion failure ²	Erosion failure	No erosion	Erosion failure	Slight erosion	Erosion failure	Pinhole failure	Erosion failure	Erosion failure	No erosion	No erosion	No erosion	No erosion	Pinhole erosion	Slight erosion	Erosion failure	Erosion failure	Slight erosion	Slight erosion	Erosion failure	Erosion failure	Erosion failure	Erosion failure	Erosion failure					
Time to Failure (sec)	600.0	568.8	158.6	142.2	39.2	23.4	18.6	33.4	252.4	1200.0	300.0	300.0	64.2	90.2	135.6	79.6	600.0	600.0	600.0	600.0	600.0	500,0	387.6	405.6	500 . 0	600.0	33.2	74.0	34.6	107.4	26.8
Rainfall Rate (inches/hour)	4	4	4	4	4	4	4	4	4	4	4	4	4	4	4	4	4	4	4	4	4	4	4	4	8	8	80	ø	œ	æ	8
Droplet Diameter (mm)	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	1.8	1.8	1.8	1.8	1.8	1.8	1.8	1.8	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	2.5	2.5	2.5	2.5	2.5	2.5	2.5
Velocity (mph)	300	300	400	400	450	450	500	500	300	300	400	400	450	450	500	500	300	300	400	400	450	450	500	200	300	300	400	400	450	450	500
1 Specimen No.	V-1	V-3	V-5	V-7	V-9	V-11	V-13	V-15	V-17	V-19	V-21	V-23	V-25	V-27	V-29	V-31	V-33	V-35	V-37	V-39	V-41	V-43	V - 45	V-47	V-49	V-51	V-53	V-55	V-57	V-59	V-61

17

) 6

£

AFML-TR-67-211

to re (sec) Comments	11.2 Erosion failure	00.0 No erosion	13.0 Pinhole erosio	50.2 Erosion failure	15.4 Erosion failure	29.0 Erosion failure	37.4 Erosion failure	58.0 Erosion failure	76.6 Erosion failure	00.0 No erosion	00.0 No erosion	00.0 Slight erosion	00.0 Slight erosion	05.2 Erosion failure	64.2 Erosion failure	88. 6 Erosion failure	03.8 Erosion failur	00.0 No erosion	16.4 Erosion failur	00.0 No erosion	91.0 Erosion failur	00.0 No erosion	00.0 No erosiôn	00.0 No erosion	21.2 Erosion &	adhesion failur
Time Failu		120	2				-			90	9	9	9	4	ē	-	ñ	9		12		9	ō 	ō		
Rainfall Rate (inches/hour)	ω,	æ	8	8	8	8	8	8	8	8	8	æ	8	8	8	8	8	4	4	4	4	4	4	8	80	
Droplet Diameter (mm)	2.5	1.8	1.8	1.8	1.8	1.8	1.8	1.8	1.8	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	2.5	2.5	1.8	1.8	0.4	0.4	2.5	2.5	
Velocity (mph)	500	300	300	400	400	450	450	500	500	300	300	400	400	450	450	200	200	300	500	300	500	300	500	300	500	
Specimen ¹ No.	V-63	V-65	V-67	V-69	V-71	V-73	V-75	V-77	V-79	V-81	V-83	V-85	V-87	V-89	V-91	V-93	V-95	V-97	6-3-Λ	V-101	V-103	V-105	V-107	V-109	V-111	

TABLE III (CONTD)

Specimen ¹ No.	Velocity (mph)	Droplet Diameter (mm)	Rainfall Rate (inches/hour)	Time to Failure (sec)	Comments
V-113 V-115 V-117 V-119	200 200 200	1.8 1.8 0.4 0.4	∞ ∞ ∞ ∞	600.0 231.6 600.0 483.4	No erosion Erosion failure No erosion Severe erosion
Notes: A Sr Sr	Il substrates ar becimens V-1 tl becimens V-97 becimens V-109	re 1/8 in. leading edg hrough V-95 are 11-1 through V-107 are 22 9 through V-119 are 2	ge radius 2024 aluminu <i>m</i> 2 mils Goodyear 23-56 2 mils Goodrich black E6 22 mils Goodrich yellow	black neoprene pe stane urethane, Estane urethane.	r Mil-C-7439B.
1. Specint on the	ien numbers ac whirling arm.	tually represent two	materials specimens wh	ich were evaluate	l at the same time
2. A failu	re of the coatir	ng is that moment wh	en it is penetrated to the	: aluminum substr	ate.

TABLE III (CONTD)

AFML-TR-67-211

\geq	
띰	
B	
Ę	

EVALUATION¹ OF SPECIFICATION NEOPRENE² AT VARYING THICKNESSES ON ALUMINUM SUBSTRATES³

Spe No	cimen ⁴	Number of Coats	Application Method	Coating Thickness (mils)	Time to Failure (sec)	Comments
000000000000000000000000000000000000000	255331199755 2253311997755 225	うううらららっこここ 4 4 4	Brush Brush Brush Brush Dip Dip Dip Dip	9-12 9-12 9-12 17-20 17-20 10-13 10-13 16-19 16-19 16-19	318.0 314.4 387.8 389.6 489.4 181.8 135.0 153.2 189.4 189.4	Erosion failure Erosion failure Erosion failure Erosion failure Erosion failure Erosion failure Erosion failure Erosion failure Erosion failure
1.	All eval	uations wer	e conducted at 50	0 mph in 2 inches/hou	ır simulated raınfall.	
2.	Goodyea	ır 23-56 neo	prene per Mil-C	-7439B.		
<u>з</u> .	All subs	strates are (conformal leading	g edge 2024 aluminum.		
4.	Specime	sn numbers	represent two ide	entical specimens which	ch were evaluated tog	ether.

Erosion failure is a penetration of the coating to the substrate without loss of adhesion.

ۍ.

20

t

AFML-TR-67-211

TABLE V

EXPOSURE TIMES FOR ELASTOMERIC-POLYMERIC MATERIALS ON 1/8°L. E. ALUMINUM SPECIMENS

Specimen ¹ No.	Material	Primer or Adhesive	Coating Thickness (mils)	Rainfall (inches/ hour)	Time to ² Failure (sec)	Type of Failure
22-23	Specification reopress (A)	Bosture 1007	20			
24-25	Specification neoprene (A)	Bostik 1007	20	24	43.0	Erosion
67-68	Spec. white neoprene (A)	Bostik 1007	20	24	23.7	Erosion
69-70	Spec. white neoprene (A)	Bostik 1007	20	24	26. 2	Erosion
71-72	Specification neoprene (B)	Bostik 1007	20	24	14.2	Erosion
51-52	Fluorosilicone	BOSTIK 1007	20	24	16.4	Erosion
53-54	Fluorosilicone	RTV sulicone	20	24	45.6	Erosion
55-56	Dimethylsilicone	RTV silicone	10	24	16.8	Erosion
57-58	Dimethylsilicone	RTV silicone	20	24	19.0	Erosion
115	Dimethylsilicone	RTV silicone	22	24	17.8	Erosion
59-60	Dimethylsilicone gum	RTV silicone	22	24	14.4	Erosion
61-62	Dimethylsilicone gum	RTV silicone	10	24	15.2	Erosion
113	Dimethylsilicone gum	RTV silicone	20	24	20.0	Erosion
114	Dimethylsilicone gum	RTV silicone	20	24	24 2	Erosion
63-64	Silicone	RTV silicone	10	24	17.3	Erosion
65-66	Silicone	RTV silicone	20	24	16.2	Erosion
112	Silicone sealant	RTV silicone	30	24	38.0	Erosion
117	Silicone rubber	BTV silicone	30	24	28.2	Erosion
118	Silicone rubber	RTV silicone	30	24	10.9	Erosion
75-76	Unfilled polyurethane (A)	Epoxy adhesive	30	24	46.1	Erosion
77-78	Unfilled polyurethane (A)	Epoxy adhesive	30	24	129.4	Erosion
40	Coal-tar polyurethane	Epoxy adhesive	30	24	76.0	Adhesion
119	Modified polyurethane	Epoxy adhesive	30	24	76.0	Adhesion
120	Modified polyurethane	Epoxy adhesive	15	24	75.8	Adhesion
81	Black polyurethane (A)	Bostik 1007	22 + 2	24	77.4	Adhesion
82	Black polyurethane (A)	Bostik 1007	22 + 2	24	217.0	Erosion
125	Black polyurethane (A)	Bostik 1007	22 + 2	12	310.0	Adhesion
83	Yellow polyurethane	Bostik 1007	22 + 2	24	194.0	Erosion
126	Vellow polyurethane	Bostik 1007	22 + 2	24	272.0	Erosion
91	Polyimide film (A)	Epoxy adhesive	$\frac{22+2}{5+2}$	12	310.0	Adhesion
92	Polyimide film (A)	Epoxy adhesive	5	24	6.3	Erosion
93	Polyimide film (A)	Epoxy adhesive	5	12	21.0	Erosion
94	Polyimide film (A)	Epoxy adhesive	5	12	10.7	Erosion
96	Phenoxy polymer (A)	-	2.8	24	98.9	Erosion
97	Phenoxy polymer (A)	-	2.8	24	50.3	Erosion
98	Phenoxy polymer (A)	-	2.8	12	36. 3	Erosion
99	Phenoxy polymer (A)	-	9.0	24	43.2	Erosion
100	Phenoxy polymer (A)	-	9.0	24	42.9	Erosion
101	Phenoxy polymer (A)	-	9.0	12	85, 2	Erosion
103-104	Phenoxy polymer (A)	-	9.0	12	85.2	Erosion
105-106	Phenoxy polymer (B)	-	6.0	12	None	No adhesion
107-108	Phenoxy polymer (C)	-	6.0	24	None	No adhesion
109-110	Phenoxy polymer (C)	~	6.0	12	None	No adhesion
80	Carborane-silicone	-	40.0	24	0	Complete failure
C-1 & C-2	Specification neoprene (A)	Bostik 1007	40.0	24	1.4	Complete failure
C-3 & C-4	Specification neoprene (A)	Bostik 1007	20.0	2	157.8	Erosion
127-128	Modified polyurethane	Primer 90-15-T	15	2	420 2	Erosion
129	Modified polyurethane	Primer 91-15-T	15	2	555.8	Erosion
130	Modified polyurethane	Primer 91-15-T	15	2	555, 8	Erosion
132-133	Black polyurethene (B)	Primer 91-15-W	15	2	570.0	Erosien
134	Black polyurethane (B)	_	10	2	76.0	Adhesion
135	Black polyurethane (B)	-	iŏ I	2	58 4	Adhesion
136	Black polyurethane (B)	- 1	īõ	2	160.2	Erosion
137	Black polyurethane (B)	-	10	2	281.2	Erosion
130-140	Black polyurethane (B)		10	2	204. 2	Erosion
155-156	Ionomer A	-	10	2	160.8	Erosion
157-158	lonomer A		8	2	227.2	Erosion
159-160	Ionomer B	-	10	2	32 6	Erosion
161-162	lonomer B	-	īō	2	122.9	Erosion
163-164	Unfilled polyurethane (B)	Epoxy adhesive	30	2	90.0	Erosion

21

1

.

TABLE V (CONTD)							
Specimen ¹ No.	Material	Primer or Adnesive	Coating Thickness (mils)	Rainfall (inches/ hour)	Time to ² Failure (sec)	Type of Failure	
$165 \\ 166 \\ 167 \\ 180 \\ 180 \\ 183 \\ 183 \\ 184 \\ 183 \\ 184 \\ 185 \\ 186 \\87 \\ 188 \\ 189 \\ -190 \\ 191 \\ -192 \\ 204 \\ -205 \\ 206 \\ -207 \\ 208 \\ -207 \\ 208 \\ -207 \\ 208 \\ -207 \\ 208 \\ -207 \\ 208 \\ -207 \\ 208 \\ -352 \\ 353 \\ -354 \\ 416 \\ 417 \\ 418 $	Unfilled polyurethane (B) Unfilled polyurethane (B) Unfilled polyurethane (C) Unfilled polyurethane (C) Unfilled polyurethane (C) Polyparaxylylene Polyparaxylylene Polyparaxylylene Polyparaxylylene Polyparaxylylene Polyparaxylylene Polymide film (B) Glass resin (A) Glass resin (A) Glass resin (A) Glass resin (A) Moless resin (A) Moless resin (A) Moless resin (A) Moless resin (A) White neoprene (B) Spec. white neoprene (A) White polyester	Epoxy adhesive Epoxy adhesive Epoxy adhesive Epoxy adhesive 	30 30 30 30 5 5 3 3 1.6 1.0 1.6 1.0 5 5 3 3 1.6 1.0 5 5 0.75 0.75 10 15 8.25 8.25 8.25 10.0	2 2 2 2 2 2 2 2 2 2 2 2 2 2 2 2 2 2 2 2	$\begin{array}{c} 279.8\\ 490.3\\ 422.0\\ 1530.7\\ 1320.2\\ 3.0\\ 4.8\\ 4.8\\ 4.8\\ 1.6\\ 0\\ -244.2\\ 300.0\\ 46.6\\ 75.3\\ 46.6\\ 40.1\\ 360.0\\ 780.0\\ 780.0\\ 512.0\\ 267.0\\ 698.2\\ 698.2\\ 698.2 \end{array}$	Adhesion Adhesion Erosion Erosion Adhesion Adhesion Adhesion Adhesion Not run Erosion Erosion Erosion Erosion Erosion Erosion Erosion Erosion Erosion Erosion Erosion Erosion Erosion Erosion Erosion Erosion Erosion Erosion Erosion	
1. When tw together	When two numbers are listed for a particular material, they represent two identical specimens which were evaluated together.						
2. A failur	2. A failure of the coating is that moment when it is penetrated to the substrate.						

3. Centrifugal force loosened coating before water was turned on.

.

ŧ.

-

Speci- men No,	Laminate Resin	Coating	Coating Thickness (mils)	Rainfall (inches/ hour)	Time to failure (sec)	Comments
15	Polyester	-	-	24	26.90	Severe erosion thru
16	Polyester	-	- 1	24	44. 35	upper plies Severe erosion thru
20	Polyester		-	24	3.0	upper plies Moderate erosion
21	Polyester	-	- 1	24	3.0	Moderate erosion
13	Polybenzimidazole (PBI)	-	-	24	3.7	Severe delamination
						(Specimen was 'ow- resin content)
18	Polybenzimidazole (PBI)	-	-	24	43.0	Severe erosion
19	Polybenzimidazole (PBI)	-	-	24	43.0	Severe erosion
123	Polyester	-	-	2	None	Destroyed in test
198	Polyester	-	-	2	43.8	Moderate erosion
199	Polyester	-	-	2	43.8	Moderate erosion
11	Polyester	Unfilled urethane (D)	5	24	4 2	Erosion & Adhesion
	-		-			failure
12	Polyester	Unfilled urethane (D)	5	24	4 2	English & Adhenies
			Ŭ		7.4	failune
14	Polyester	Spec. neoprene (A)	8	24	26.0	
		speet neoprene (11)	v	-1	20.9	Complete penetration
17	PBI	Spec neoprene (A)			40 55	of coating
		opeet neoprene (H)	o	24	40.00	Complete penetration
34	PBI	Advanced DBI meanin				of coating
35	PBI	Advanced PBI real	+	24	31.0	Erosion in plies
36	PBI	Reluimide upmish	1	29	31.0	Erosion in plies
37	PBI	Polyimide varnish	2	24	44.5	Erosion in plies
121	Polyastan	Folyimide varnish	2	24	44.5	Erosion in plies
	A OLJEBIEL	mou poryurethane	15	2	386.0	Complete adhesion
124	DBI	D-1-()A				loss
103	r DI	Polyimide varnish	2	2	386.0	Erosion completely
						thru laminate

TABLE VI EXPOSURE TIMES FOR UNCOATED AND ELASTOMERIC-COATED 3/32 " L. E. GLASS LAMINATE SPECIMENS

23

ŧ

-

ſ

TABLE VII

EXPOSURE TIMES FOR ELASTOMERIC-POLYMERIC MATERIALS ON CONFORMAL ALUMINUM SPICIMENS

Specimen		D	Coating	Rainfall	Time to	
No	Costuna	Primer or	Thickness	(inches/	Failure	
	Couting	Adhesive	(mils)	hour)	(sec)	Comments
C-5&6	Specification neoprene (A)	Bostik	0-12			
C-7&8	Specification neoprene (A)	Bostik	9-12	1 5	318.0	Erosion failure
C-9&10	Specification neoprene (A)	Bostik	0-12	1 5	314.4	Erosion failure
C-11&12	Specification neoprene (A)	Bostin	17.20	6	387.8	Erosion failure
C-13&14	Specification neoprene (A)	Bostik	17-20	4	359.6	Erosion failure
C-15&16	Specification neoprene (A)	Bostik	17-20		489.4	Erosion failure
320-321	Polycarbonate	Boblin	10	1 6	288.0	Erosion failure
			. 10	4	32.0	Erosion & adhesion
322-323	Polycarbonate	-	1 10		07.0	loss
			1 10	1 2	21.8	Erosion & adhesion
324-325	Polycarbonate	-	20			1088
326-327	Polycarbonate	-	20		00.0	Erosion failure
327-329	Polycarbonate	-	20		76.4	Erosion failure
330-331	Polycarbonate	-	30	6	44.4	Erosion failure
361-362	Polyurethane white paint	Epoxy regin	30	1 5	85.8	Erosion failure
363-364	Polyurethane white paint	Epoxy resin		6	27.4	Adhesion failure
365-366	Polyurethane white paint	Enoxy resin	1 10		32.0	Adhesion failure
367-368	Polyurethane white paint	Epoxy rusin	10	1 1	14.7	Adnesion failure
419-420	Black urethane tape	Epoxy advesive	25		12.4	Adhesion failure
421-422	Black urethane tape	Epoxy adhesive	25	1 1	490.8	Erosion failure
423-424	Black urethane tape	Epoxy adhesive	25	4	405.0	Erosion failure
425-426	Plack urethane tape	Epoxy adhesive	25	4	516.2	Adhesion failure
471	Black urethane (A)	Bostik	10	4	398.4	Erosion failure
472	Black urethane (A)	Bostik	10	4	101.0	Erosion failure
473	Black urethane (A)	Bostik	10	2	24/1.4	Erosion failure
474	Black neoprene (C)	Bostik	1 10 1		2295.8	Erosion failure
475-476	Black neoprene (C)	Bostik	1 10		200.0	Erosion failure
477-478	Black neoprene (C)	Bostik	20	2	250 0	Erosion failure
479	Black neoprene (C)	Bostik	20	2	209.0	Erosion failure
480	Black neoprene (C)	Bostik	40	2	253.2	Erosion failure
481-482	Black neoprene (C)	Bostik	40	2	200.4	Erosion lailure
483-484	White neoprene (C)	Bostik	10	2	226 0	Erosion failure
485	White neoprene (C)	Bostik	10	2	216 6	Erosion failure
516-517	Cork sheet	Epoxy adhesive	35	2	210.0	Erosion failure
518-519	Cork sheet	Epoxy adhesive	35	2	6.4	Erosion failure
528-529	Nitroso-TiO ₂		4-5	2	3.5	Erosion failure
530-531	Nitroso-TiO2	· -	4-5	2	3.0	Erosion failure
532-533	Abrasive tape (A)	Acrylic adhesive	1 14	2	130.6	Erosion failure
534-535	Abrasive tape (B)	Acrylic adhesive	15	2	133.6	Erosion failung
536-537	Abrasive tape (C)	Acrylic adhesive	16	2	122 8	Erosion failure
538-539	Abrasive tape (D)	Acrylic adhesive	16	2	132 2	Erosion failung
540-541	Abrasive tape (E)	Acrylic adhesive	14	2	153.0	Erosion failure
546-547	Preetched Teflon	Epoxy adhesive	35	2	19.0	Structural &
				-		arogion failure
548-549	Preetched Teflon	Epoxy adhesive	35	2	20.2	Structurel &
				-		erosion failure
550-551	Unfilled urethane (E)	Epoxy adhesive	35	2	354.0	Erosion failure
552-553	Unfilled urethane (E)	Epoxy adhesive	35	2	450.4	Erosion failure
556-557	Fluidized bed epoxy	-	15	2	133.8	Erosion failure
558-559	Fluidized bed epoxy	- 1	15	2 1	124.4	Erosion failure
560-561	Fluidized bed silicone-epoxy	-	10	2	100.0	Erosion failure
562-563	Fluidized bed silicone-epoxy	-	10	2	100.0	Erosion failure
564-565	Plexiglass	Epoxy adhesive	62, 5	2	119.2	Structural failure
588-589	Nitroso-stainless steel powder		3-4	2	11.2	Erosion failure
590-591	Nitroso-stainless steel powder	-	3-4	2	10.0	Erosion failure
622-623	Cork coated w/neoprene	Epoxy adhesive	46.5	2	8.0	Erosion failure
524-625	Cork coated w/neoprene	Epoxy adhesive	46.5	2	7.4	Erosion failure
				-		

24

¢

TABLE VIII

EXPOSURE TIMES FOR ELASTOMERIC-POLYMERIC MATERIALS ON CONFORMAL LAMINATE SPECIMENS

Specimen No.	Coating	Primer or Adhesive	Laminate Resin	Coating Thickness (mils)	Rainfall (inches/ hour)	Time to Failure (sec)	Comments
369-370	Molded neoprene (A)	Urethane adhesive	EDOXY		2	163 6	Adhesion failure
371-372	Molded neoprene (A)	Urethane adhesive	Epoxy	ii	2	101.2	Erosion failure
373-374	Molded neoprene (A)	Epoxy adhesive	Epoxy	11	2	200.2	Erosion failure
375-376	Neoprene boot	Epoxy adhesive	Epoxy	20	2	17.4	Erosion failure
	10 mils neoprene						
	5 mils gum rubber			1			
377	Neoprene boot	Urethane adhesive	EDOXY	. 18	2	22.0	Fragion failure
511	8 mils peoprene	Cretilale adhesive	Dpoxy	10	-	22.0	LIOSION JANUTE
	10 mils gum rubber						
378	Neoprene boot	Epoxy adhesive	Epoxy	18	2	22.0	Moderate erosion
	8 mils neoprene						
	10 mils gum rubber		_				
379	Neoprene boot	Urethane adhesive	Ероху	21	2	24.4	Adhesion failure
	10 mils gum rubber			1			
	4 mils urethane						
380	Neoprene boot	Epoxy adhesive	Epoxy	21	2	86.0	Erosion failure
	6 mils neoprene						
	10 mils gum rubber						
	4 mils urethane		~				
381-382	Molded neoprene (A)	Urethane adhesive	Epoxy	18	2	114.0	Erosion failure
385	Neonrene boot	Urethane adhesive	Epoxy	10	2	121.0	Erosion failure
	5 mils neoprene	oremaie aunebrie	- poxy		~	120.4	Diosion isnure
	5 mils Dacron cloth						
386	Neoprene boot	Urethane adhesive	Epoxy	10	2	163.0	Erosion failure
	5 mils neoprene					_	_
207 200	5 mils Dacron cloth	Energy adheading	Eren				12
301-300	heoprene boot w/heoprene	Lpoxy adhesive	Lpoxy	20	z	78.0	Erosion lailure
	10 mils neoprene						
	5 mils gum						
	5 mils Dacron cloth						
389	Special compound neoprene	Epoxy adhesive	Epoxy	12	2	363.0	Erosion failure
200	boot	17					
380	Special compound neoprene	Epcxy adnesive	Epoxy	18	2	363.0	Moderate Prosion
391 - 392	Spraved peoprene (B)	-	EDOXY	13	2	180 8	Erosion and
	-p, (-,		-pony			100.0	adhesion failure
393-394	Sprayed necprene (B)	-	Epoxy	13	2	243.6	Erosion and
							adhesion failure
395-396	White urethane paint (A)	-	Epoxy	5	2	57.8	Erosion failure
397-398	White urethane paint (B)	-	Epoxy	10	2	35.2	Erosion failure
401	Neoprene boot	Ilrethane adh	Epoxy	20	2	17 0	Adhesion failure
402	Neoprene boot	Urethane adh.	Epoxy	20	ž	17.0	Erosion failure
403-404	Sprayed urethane	-	Epoxy	5	2	76.8	Erosion failure
405-408	Neoprene boot, Dacron	Epoxy adhesive	Epoxy	10	2	64.0	Erosion failure
407	backing	T	_				
407	Urethane boot	Urethane adh.	Epoxy	10	2	17.6	Adhesion failure
486-487	Black urethane (A)	Bostik	Polyester	10	2	44.0	Erosion failure
488	Black urethane (A)	Bostik	Polvester	10	2	174.4	Erosion failure
489	Black neoprene (C)	Bostik	Polyester	10	2	87.4	Erosion failure
±90-491	Black neoprene (C)	Bostik	Polyester	10	2	135.4	Erosion failure
492-493	Black neoprene (C)	Bostik	Polyester	20	2	145.4	Moderate erosion
494	Black neoprene (C)	Bostik	Polyester	20	2	186.4	Erosion failure
490	Black neoprene (C)	DOSTIK	Polyester	-40	2	186.4	Erosion lailure
496-497	Black neoprene (C)	Bostik	Polyester	40	2	245.0	Erosion failure
					-		in upper layer
498-495	White neoprene (C)	Bostik	Polyester	10	2	264. 4	Erosion failure
500	White neoprene (C)	Bostik	Polyester	10	2	414.4	Erosion failure
513	conted with anown-			-	z	79.4	Erosion through
	stainless steel fabric						Tabric & piles
	arranged in longitudinal						
	direction						

TABLE VIII (CONTD)

Specimen No.	Coating	Primer or Adhesive	Laminate Resin	Coating Thickness (mils)	Rainfall (inches/ hour)	Time to Failure (sec)	Comments
514	Epoxy-E glass laminate coated with epoxy- stainless steel fabric arranged in circular			-	2	79.4	Erosion through fabric & plies
515	direction Epoxy-E glass laminate coated with epoxy- stainless steel fabric arranged in circular direction			-	2	51.4	Erosion through fabric & plies
409-410	Uncoated epoxy laminate (A)			-	2	43.4	Penetration of
444-445	Uncoated Aluminum phos- phate laminate				2	22.0	Eroded com-
447-448	Polyimide - E glass laminate			-	2	49.0	Eroded com-
463-464	Polyimide-E glass laminate			-	2	42.0	Eroded com -
449-450	Epoxy-E glass laminate (B)			-	2	60.0	Penetration of 5 plies of fabric
503-504	Uncoated polyester laminate			-	2	91.0	Eroded ccm-
649-650	Plexiglass molded specimen			125	2	112.4	Erosion through
651-652	Polyvinylchloride molded specimen			125	2	95.0	Erosion through
653-654	Kel-F molded specimen			125	2	370.0	Erosion through specimen

TABLE IX

EXPOSURE TIMES FOR CERAMIC MATERIALS ON ALUMINUM SUBSTRATES

			Rainfall			
6			Thickness	(inches/	Failure	
No	Material	Primer or Adhesive	(mils)	hour)	(sec)	Comments
	AVAILED & AWA					
		1/8-in. L. E. Specimens				
		_	18	24	55.0	Coating completely
46	Plasma-sprayed Al2O3	-	10	~~	00.0	gone
145	Rokide A sprayed alumina	-	10	2	11.8	[#] rosion failure
146	Rokide A sprayed alumina	-	10	2	11.8	· . osion failure
147	Rokide A alumina impregnated	-	10	2	10.0	Erosion failure
	w/Epon 1031				10.0	Europies failung
148	Rokide A alumina impregnated	-	10	.х	10.0	Erosion failure
	w/Epon 1031		7-9000 49	2	24 8	Coating gone
193	Vacuum evaporated alumina		8-10 000 A	0 2	24. 9	Coating gone
194	Plasma-apraved AlaOa	-	30	2	600.	Adhesion failure
1°10	(High velocity argon electrode-					
1	(111gh verser)					
213	Plasma-sprayed Al ₂ O ₃	-	30	2	600.0	Adhesion failure
	(High velocity argon electrode-					
	550 amps)		16		127.0	Enonion failure
214	Plasma-sprayed Al2O3	-	15	4	137.0	Erosion fanare
1	(High velocity argon electrode-					
1	AUU amps)	_	20	2	137.0	Erosion failure
415	(Standard nitrogen electrode)			-		
265	Plasma spraved Al2O3	-	11	2	97.0	Erosion failure
266	Plasma sprayed Al ₂ O ₃		15-20	2	97.0	Erosion failure
267	Plasma sprayed Al ₂ O ₃	-	9	2	95.4	Erosion failure
268	Plasma sprayed Al ₂ O ₃	-	1 1		00.4	Erosion failung
269	Plasma sprayed ZrO ₂	-			240 0	Erosion failure
270	Plasma sprayed ZrO2	-	37		240.0	Erosion failure
271	Plasma sprayed 2rO2	_	12	2	93.0	Erosion failure
272	Plasma sprayed 2102	Porcelain enautil	30	2	1058.0	Erosion to sub-
410	Flasma sprayed Al203			_		strate
277	Plasma sprayed Al ₂ O ₃	Porcelain enamel	30	2	1058.0	Erosion to sub-
1						strate
280	Rokide A alumina	-	30	2	202.4	Erosion failure
281	Rokide A alumina	-	30	2	50.2	Regin gone
284	Rokide A alumina w/organic	• -	30	1	000.0	ceramic eroded
205	resin Bakida A alumina w/organic	_	30	2	600.0	Erosion failure
265	regin					
288	Rokide A alumina	Secondarily bonded	30	2	1433.0	Erosion on surface
289	Rokide A alumina	Secondarily bonded	30	2	1433.0	Erosion failure
290	Rokide A alumina w/organic	Secondarily bonded	30	2	1354.0	Erosion lanore
	resin	Secondonily honded	30	2	1354 0	Erosion failure
291	Rokide A alumina w/organic	Secondarily bonded	30	^	1354.0	Light where
202	Poride A alumina sintered	Secondarily bonded	30	2	52.0	Adhesion failure
493	A brs @ 2500°F	Deconduring bonded				
294	Rokide A alumina sintered	Secondarily bonded	30	2	203.2	Slight erosion
1	4 hrs @ 2500°F					Duration failurg
295	Rokide A alumina w/organic	Secondarily bonded	30	2	202.2	Erosion lallure
	resin sintered 4 hrs @ 2500°F		20		52.0	Regin gone cost-
296	Rokide A alumina w/organic	Secondarily bonded	30	-	52.0	ing cracked
0.00	resin sintered 4 hrs @ 2500°F	Bickled Al	25	2	227.4	Adhesion failure
297	Plasma sprayed AlaOa	Grit blasted Al	32	2	731.4	Erosion failure
299	Plasma sprayed Al2O2	Grit blasted Al	40	2	731.4	Erosion failure
300	Plasma sprayed Al ₂ O ₂	Green enamel primer	24	2	222.6	dhesion failure
301	Plasma sprayed Al ₂ O ₃	Green enamel primer	22		326.2	Aunesion failure
302	Plasma sprayed Al ₂ O ₃	Grey enamel w/grit	34	2	1140.8	Erosion fatture
		Diast	37	2	890.0	Erosion failure
303	Plasma sprayed Al ₂ O ₃	blast	, ³	l °	000.0	
EE4	Chemically strengthened	-	125	2	8400.0	Chipping away of
007	alumina					ceramic
555	Chemically strengthened	-	125	2	8400.0	Slight wear on
1	alumina w/Cr2O3		1	ł		surface

. 1

				<u> </u>		
Specimen No.	Material	Primer or Adhesive	Coating Thickness (mils)	Rainfall Rate (inches/ hour)	Time to Failure (sec)	Comments
					r	
		1/32-in. L. E. Specimens				
141	Rokide A sprayed alumina	-	10	2	269.2	Erosion failure
142	Roxide A sprayed alumina	-	10	2	269.2	Erosior failure
143	Rokide A alumina impregnated w/Epon 1031	-	10	2	56,0	Erosion failure
144	Rokide A alumina impregnated w/Epon 1031	-	10	2	56.0	Erosion failure
278	Rokide A alumina	_	30	2	121 0	Enonion failung
279	Rokide A alumina	-	30	2	121 0	Erosion failune
282	Rokide A alumina w/organic	-	30	2	462 2	Broston lanure
	resin	-	30	-	403.4	Ceramic eroded
283	Rokide A alumina w/organic resin	-	30	2	463.2	Erosion failure
286	Rokide A alumina	Secondarily bonded	30	2	575.6	Severe erosion
287	Rokide A alumina w/organic	Secondarily bonded	30	2	2100.0	Severe erosion
292	Rokide A alumina w/organic resin sintered 4 hrs @ 2500°F	Secondarily bonded	30	2	575.6	on edge Erosion failure
		Conformal Specimens				
336	Rokide A alumina	-	30	2	101.4	Erosion evident,
337	Rokide A alumina	-	30	2	101.4	Adhesion failure
			· · · ·			

TABLE IX (CONTD)

Notes: Specimens 282, 283, 284, 285, 287, 290, 291, 292, 295 and 296 were impregnated with a high temperature organic resin after spraying to reduce porosity.

Approximately 110 specimens of various plasma-sprayed materials on the conformal aluminum and laminate specimens have been evaluated by this Laboratory in support of Contract AF33(615)-3342 for research for improved, dense, ceramic rain erosion resistant coatings being conducted by the Brunswick Corp. Data on these specimens will be documented in reports from this contract.

٠

ł

TABLE X

EXPOSURE TIMES FOR CERAMIC MATERIALS ON LAMINATE SUBSTRATES

Specimen			Coating Thickness	Rainfall Rate (inches/	Time to Failure	
No.	Material	Substrate	(mils)	hour)	(sec)	Comments
30	Elama approved AlaO-	DPI lominate	20	24	000.0	
31	Flame sprayed AlaOa	PBI laminate	30	24	286.0	Erosion failure
38	94% AloO 6% Epoxy	PBI laminate	15	24	200.0	Erosion lallure
39	94% AloO2 - 6% Epoxy	Polvester laminate	15	24	13.8	Erosion failure
47	Plasma sprayed AlpO3	AIPO laminate	10	24	2 0	Erosion failure
48	Plasma sprayed Al ₂ O ₂	AIPO laminate	15	24	2.0	Erogion failure
49	Plasma sprayed Al ₂ O ₂	PBI laminate	15	24	13.5	Erosion failure
50	Plasma sprayed Al ₂ O ₃	PBI laminate	15	24	13.5	Erosion failure
85	Flame sprayed AlaOa	PBI laminate	30	24	73.0	Erosion failure
86	Flame sprayed Al2O3	PBI laminate	30	12	156.6	Erosion failure
87	Flame sprayed Al _{2O2}	PBI laminate	30	24		Destroyed during
	2-3					test
88	Flame sprayed Al ₂ O ₃	PBI laminate	30	24	73.0	Erosion failure
89	Flame sprayed Al ₂ O ₃	PBI laminate	30	12	156.0	Erosion failure
149	Rokide A alumina	Polvester laminate	10	2	840 9	Erosion failure
150	Rokide A alumina	Polvester laminate	10	2	240.9	Erosion failure
151	Rokide A alumina w/Epon 1031	Polvester laminate	10	2	497.2	Erosion failure
152	Rokide A alumina w/Epon 1031	Polvester laminate	10	2	1097.2	Erosion failure
216	Flame sprayed Al ₂ O ₂	PBI laminate	30	2	147.0	Erosion failure
217	Flame sprayed Al ₂ O ₃	PBI laminate	30	2	147 0	Erosion failure
218	Flame sprayed AlaOa	PBI laminate	30	Ã	28.2	Adhesion failure
219	Flame sprayed AlaOa	PBI laminate	30	4	28.2	Slight polighing
221	Flame spraved AlaOa	PBI laminato	20	e .	120.0	Digit polising
	2-3	i bi fammate	30	0	130.0	Penetration into
222	Flame apraved AloOo	PBI laminate	30	6	126.0	Penetration into
	r tame sprayed miges	- Di minimate		v I	130.0	laminete
332	Rokide A alumina	PBI laminate	30	2	35.2	Erosion failure
333	Rokide A alumina	PBI laminate	30	2	35.2	Erosion failure
334	Rokide A alumina	Polvester laminate	30	2	11 0	Erosion failure
335	Rokide A alumina	Polvester laminate	30	2 1	11.0	Moderate erosion
			20	-		

All specimens are 3/32-in. leading edge configuration.

TABLE XI

EXPOSURE TIMES OF METAL SPECIMENS

				Rainfall		
		Specimen	Coating	Rate	Time of	
No.	Material	Configuration	(mils)	hour)	(sec)	Comments
26	2024 aluminum	1/8" L. E. radiua	-	24	900.0	Moderate pitting
27	2024 aluminum	1/8" L. E. radius	-	24	900.0	Moderate pitting
28	2024 aluminum	1/8" L. E. radius	-	12	1800.0	Severe pitting
29	2024 aluminum	1/8" L. E. radius	-		1800.0	No visible effect
43	403 stainless steel	0.025" L. E. radius	-	24	1800.0	No visible effect
44	titanium-6Al-4V	0.015" L. E. radius	-	24	1800.0	No visible effect
45	titanium-6Al-4V	0.025" L. E. radius	-	24	1800.0	No visible effect
171-172	Electroplated nickel	1/8" L. E. radius	8	2	3600.0	No effect; wash
173-174	Electroplated nickel	1/8" L. E. radius	16	2	3600.0	effect No effect; wash
175	Electroplated nickel	3/32" L. E. polyester	6	2	3948.2	effect No effect
176	Electroplated nickel	laminate 3/32" L. E. polyester	6	2	1800.0	Small hole in
170	Electroplated sheet	laminate	6		1421 0	coating Bonstration to
178	Electroplated chromium	laminate	8	<u></u>	1421.0	laminate
179	Electroplated chromium	3/32" L. E. polyester laminate	6	2	30.0	Adhesion failure
256	Electroplated nickel	3/32" L. E. polyester laminate	10	2	370.6	Adhesion loss
257	Electroplated nickel	3/32" L. E. polyester laminate	10	2	234.0	Adhesion loss
258	Electroplated nickel	3/32" L. E. polyester	10	2	136.0	Adhesion loss
355	Electroplated nickel	3/32" L. E. PBI	2.2	2	411.8	Erosion failure
356	Electroplated nickel	3/32" L. E. PBI	2.2	2	411.8	Erosion failure
357	Electroplated nickel	3/32" L. E. PBI	6.0	2	2760.0	Erosion failure
358	Electroplated nickel	3/32" L. E. PBI	6.0	2	2760.0	Erosion failure
455	Electroplated nickel	3/32" L. E. PBI	6.3	2	741.6	Adhesion failure
456	Electroplated nickel	3/32" L. E. PBI	6.3	2	1480.0	Erosion failure
457	Electroplated nickel	3/32" L. E. PBI	9.1	2	2760.0	Erosion failure
458	Electroplated nickel	3/32" L. E. PBI	9.1	2	10,000	Erosion failure
520	Electroplated nickel	laminate 3/32" L. E. PBI	6	2	5400	Erosion failure
521	Electroplated nickel	3/32" L. E. PBI	6	2	22, 980	No erosion
522	Electroplated nickel	3/32" L. E. PBI	12	2	33, 000	No erosion
523	Electroplated nickel	3/32" L. E. PBI	12	2	19, 020	Erosion failure
524	Electroplated nickel	laminate 3/32" L. E. PBI	16	2	7200	No erosion
525	Electroplated nickel	laminate 3/32" L. E. PBI	16	2	7200	No erosion
526	Electroplated nickel	laminate 3/32" L. E. polyester	16	2	3600	No erosion
527	Electroplated nickel	laminate 3/32" L. E. polyester	16	2	3600	No erosion
304	Plasma-sprayed nickel	laminate 1/8" L. E. aluminum	14-15	2	13.4	Adhesior failure
305	aluminide Plasma-sprayed nickel	1/8" L. E. aluminum	12-15	2	76.0	Penetration of
306-207	aluminide Plasma-sprayed nickel	1/8" L E aluminum	10-11	2	20.4	coating Adhesion failure
300-301	aluminide-tungsten	L, U, L, A, aluminum	10-11		20. 4	
338-339	Beryllium	0.025" L. E. radius	-	6	1800.0	No effect

TABLE XI (CONTD)

Specimen No.	Material	Specimen Configuration	Coating Thickness (mils)	Rainfall Rate (inches/ hour)	Time of Exposure (sec)	Comments
427-428	Plasma-sprayed nickel	Conformal aluminum	3	2	67.2	Erosion failure
453-454	aluminum Plasma-sprayed nickel	Conformal aluminum	1	2	68.0	Erosion failure
655	aluminum-zirconia Vapor deposited silicon carbide	Conformal graphite	1	2	265. 6	Erosion failure
Note: Exposures on nickel-plated specimens which exhibit no effect after the times shown are being continued						

CODE LIST -- RAIN EROSION SPECIMENS

			· · · · · · · · · · · · · · · · · · ·
Specimen	Report	Coating Material	Supplier
1103.	DESIGNATION	Table V	
00.05.415	Specification neophone A	Goodyear 23-56	Goodyear Tire & Bubber Co.
22-25, 415 C-1 thm C-16	specification neoptene x	Goodyean 20 00	
67-70	Spec. white neoprene A	Gaco N-83 white	Gates Engineering Co.
71-74	Specification neoprene B	Gaco N-700-9	Gates Engineering Co.
51-54	Fluoronilicone	Q-94-003	Dow Corning
55-56	Dimethylsilicone	Q-92-009	Dow Corning
115, 116	-		
59-62	Dimethylsilicone gum	Q-90-092	Dow Corning
113, 114			
63-66	Silicone	Q-90-090	Dow Corning
111-112	Silicone sealant	Q-90-031	Dow Corning
117, 118	Silicone rubber	3-900 B O 655	Armstrong Cork
75-78	Unfilled polyurethane A	P. U. 555	Amicon Corporation
40, 41, 119	Coal tar & modified	-	Anneon corporation
120, 127-131	Polyurethanes	Estano 4071	B E Goodrich
81, 82, 125	Black urethane A	Listalle 4011	D. F. Goodrien
411-413	Vollow unothang	Estane	B. F. Goodrich
03, 04, 120	Polyimide A	H-film	du Pont
91-94	Phenoxy A	Phenoxy-A	Union Carbide
103-106	Phenoxy B	Phenoxy-T-5	Union Carbide
107-110	Phenoxy C	Phenoxy-T-8	Union Carbide
79-80	Carborane-silicone	-	Thioko
132-138	Black urethane B	KE-7802	Goodrich Aerospace
139-140	Black polyurethane C	KE-7801	Goodrich Aerospace
155-158	Ionomer A	Surlyn A ER-1601	du Pont
159-162	Ionomer B	Surlyn A	du Pont
163-166	Unfilled polyurethane B	LD-550	du Pont
167, 168, 197	Unfilled polyurethane C	ECD-498	du Pont
180-188	Polyparaxylylene	Parylene C	Union Carbide
189-192	Polyimide B		Solar
204, 205	Glass resin A	Resin 100	Owens-Illinois
209-211		Desis 650	Owong-Illinois
206-207	Glass resin B	Resin 650	3M
351-354	Transparent uretnane		Goodyear Tire & Rubber Co.
416	White neoprene B		Grumman
418	white polyester		
		Table VI	
11 12	Unfilled urethane D	Proseal 798	Coast Mfg.
34 35	Advanced PBI resin	AFR-151	Narmco
36 37 124	Polyimide varnish	"ML" varnish	du Pont
121	Modified polyurethane	-	Amicon
			L
		Table VII	
320-331	Polycarbonate	Lexan	Union Carbide
361-368	Polyurethane white paint	XA-5094	3M
419-426	Black urethane tape	-	3M
471-473	Black urethane A	Estane XA4071-1	B. F. Goodrich
474-482	Black neoprene C	Neoprene XA4071-2	B. F. Goodrich
483-485	White neoprene C	Neoprene XA4071-4	B. F. Goodrich
516-519	Cork sheet	AC-2755	Armstrong
532-533	Abrasive tape A	Urethane w/abrasive	3M
	_	particles	
534-535	Abrasive tape B	Urethane w/abrasive	JM
		particles	214
536-537	Abrasive tape C	Ureinane w/abrasive	3141
	Aburnation tana D	Unothene w/shreeive	3M
538-539	Abrasive tape D	Danticles	
640 541	Abreature tame F	I(rethane w/ahragive	3M
240-241	ADPasive tape E	narticles	
620-621	Nitroso-TiOs	Nitroso copolymer	Thiokol
548-540	Teflon	-	du Pont
550-553	Unfilled urethane E	Adiprene L-315	du Pont
556-559	Fluidized bed epoxy	E627	Armstrong Products
		-	

•

CODE LIST--RAIN EROSION SPECIMENS (CONTD)

Specimen Nos.	Report Designation	Coating Material	Supplier					
		Table VII						
560-563 564-565 588-591	Fluidized bed silicone-epoxy Plexiglass Nitroso-stainless steel	- Nitroso terpolymer	Dow Corning AFML Thiokol					
	Table VIII							
369-374 395-396 397-400	Molded neoprene A White urethane paint A White urethane paint B	Goodyear 23-56 Catalac Prestec	Douglas Douglas Douglas					
Table IX								
46, 212-215 265-268 265-272 145-148 280-296 276, 277 297-303 141-144 279-292 336, 337 554-555	Plasma sprayed Al ₂ O ₃ Plasma sprayed Al ₂ O ₃ Plasma sprayed Zr ₂ O ₃ Rokide A alumina Rokide A alumina Plasma sprayed Al ₂ O ₃ Rokide A alumina Rokide A alumina Chem strengthened Al ₂ O ₃		Brunswick Quantum Quantum Naval Ordnance Lab. Goodyear Aerospace Brunswick NOL Goodyear Aerospace Linden Labs.					
	r	Table X						
30, 31, 85-89 216-222 38-39 47-50 149-152 332-335	Fiame-sprayed Al ₂ O ₃ 94% Al ₂ O ₃ -6% Epoxy Plasma sprayed Al ₂ O ₃ Rokide A alumina Rokide A alumina		Narmco Amicon Brunswk NOL Goodyear Aerospace					
	T	able XI						
304-305 306-307 427-428	Plasma sprayed nickel aluminide Plasma sprayed nickel aluminide-tungsten carbide Plasma sprayed nickel-aluminum	-	Monsanto Monsanto					
453-454 655	Plasma sprayed nickel-aluminum- zirconia Vapor deposited silicon carbide	-	Monsanto Monsanto Texas Instrument					

33

ŧ



Figure 1. Hypothetical Flight Plan for a M3 Aircraft



Figure 2. Flight Plan for M2.2 Supersonic Transport



Figure 3. Hypothetical Flight Plan for M3 Supersonic Transport

36



Figure 4. 6 Foot Diameter Rain Erosion Facility (Inside of Test Enclosure)



Figure 5. 6-Foot Diameter Rain Erosion Facility (Spray Ring, Whirling-Arm, and Periscope Tube)



6-Foot Diameter Rain Erosion Facility (Test Enclosure and Periscope Tube Location) Figure 6.



Figure 7. 6-Foot Diameter Rain Erosion Facility Control Room (Telescope Mount, Strobe Power Unit, and Motor Load Bank)



6-Foot Diameter Rain Erosion Facility Control Room (Motor Controls and Test Instrumentation) Figure 8.



Figure 9. Aluminum Subsonic Rain Frosion Specimen (1/8" Leading Edge Radius)

SCALE FULL SIZE

42

¥.



Figure 10. Laminate 5 sonic Rain Erosion Specimen (3/32" Leading Edge Radius)



.0025 Airfoil-4-Inch Chord

Distance From Leading Edge

%Chord	Ordinate	Abscissa		
	(1)	(A)		
. 00	.°00	. 000		
1.25	. 05	. 158		
2.50	. 10	. 218		
5.00	. 20	. 296		
7.50	. 30	.350		
10.00	.40	. 390		
15.00	. 60	.446		
20.00	.80	.478		
25.00	1.00	.485		
30.00	1.20	. 500		

Outer Dimensions of 1/8 Inch Specimen

Dimensions in Inches

۰...

Materials-2024-T4 Aluminum Resin-Reinforced Laminate

Figure 11. Conformal Aluminum or Laminate Subsonic Rain Erosion Specimen

















ġ



Figure 16. Effect of Velocity on Erosion of Neoprene Coatings (4 inches/hour Rainfall)





Figure 17. Effect of Velocity on Erosion of Neoprene Coatings (8 inches/hour Rainfall)











Figure 20. Comparative Erosion Resistance of Materials (Applied as Coatings up to 35 mile Thick)

UNCLASSIFIED Security Classification

DOCUMENT CO	NTROL DATA - R&	D Itored when	the overall report is classified)			
1 ORIGINATING ACTIVITY (Corporate author) Air Force Materials Jahoratowy		2. REPORT SECURITY CLASSIFICATION				
Wright-Patterson Air Force Base, Ohio 45433		26 GROUP				
3 REPORT TITLE RESEARCH FOR IMPROVED SUBSONIC MATERIALS	AND SUPERSON	IC RAIN	N EROSION RESISTANT			
4 DESCRIPTIVE NOTES (Type of reputt and inclusive dates)						
5 AVITHOR(S) (List name, first name, initial)						
Schmitt, George F. Jr.						
6 REPORT DATE October 1967	74. TOTAL NO. OF P	AGES	75. NO. OF REFS			
8. CONTRACT OF GRANT NO.	94. ORIGINATOR'S RE	PORT NUM	IBER(S)			
5. PROJECT NO. 7340	AFML-TR-67-211					
c. Task No. 734007	9b. OTHER REPORT NO(5) (Any other numbers that may be seeigned this report)					
d.						
with specific prior approval of the Elastomers and Coatings Branch (MANE) Nonmetallic Materials Division, Air Force Materials Laboratory, Wright-Patterson AFB, Ohio 45433						
	Air Force Materials Laboratory					
	Wright-Patterson AFB, Ohio 45433					
Investigations of advanced coatings mater: simulation device at 500 MPH have led to ne viding protection against damage from rain of Polyurethane coatings were determined to be polymeric materials currently available. The ment over the specification neoprene erosion alumina and alumina/titania are potentially a where dielectric properties must be maintai applied to plastic laminates will provide seve erosion resistance over conventional elaston	als performed o w protective coa iroplet impingen e the most erosic ese polyurethan a coating. Plasm upplicable for su ned. Electroplat eral orders of m peric coatings.	n a whin bent at a on resis os are a a-spray personic ad nicke agnitude	rling-arm rain erosion nich are capable of pro- subsonic velocities. tant of the elastomeric- considerable improve- ved ceramic coatings of e erosion protection of coatings directly e improvement in			
(This abstract may be further distributed by Elastomers and Coatings Branch (MANE) No terials Laboratory, Wright-Patterson AFB,	any holder <u>only</u> nmetallic Materi Ohio 45433.)	with spe als Divi	ecific prior approval of the Ision, Air Force Ma			
DD 50RM 1473	TT					
		Sec	urity Classification			

UNC LASSIFIED

Security Classification		LIN	K A	LIN	кв	LIN	кс
A KEY WORDS	ł	ROLE	WT	ROLE	wт	ROLE	WT
Rain erosion Subsonic Polyurethane Coatings Plasma Sprayed Alumina Coatings Electroplated Nickel Coatings							
INSTRUCTIONS							

1. ORIGINATING ACTIVITY: Enter the name and address of the contractor, subcontractor, grantee, Department of De-fense activity or other organization (corporate author) issuing the report.

24. REPORT SECURITY CLASSIFICATION: Enter the over-2a. REPORT SECOND TO CLASSIFICATION. Unter the order all security classification of the report. Indicate whether "Restitcted Data" is included. Marking is to be in accord-ance with appropriate security regulations.

2b. GROUP: Automatic downgrading is specified in DoD Di-rective 5200, 10 and Armed For an Industrial Manual. Enter the group number. Also, when applicable, show that optional markings have been used for Group 3 and Group 4 as author-ized. ized.

3. REPORT TITLE: Enter the complete report title in all capital letters. Titles in all cases should be unclassified. If a meaningful title cannot be selected without classification, show title classification in all capitals in parenthesia immediately following the title.

4. DESCRIPTIVE NOTES: If appropriate, enfor the type of report, e.g., interim, progress, summary, annual, or final. Give the inclusive dates when a specific reporting period is covered

5. AUTHOR(S): Enter the name(s) of author(s) as shown on or in the report. Enter tast name, first name, middle initial. If military, show rank and branch of service. The name of the principal anthor is an absolute minimum requirement.

6. REPORT DATE: Enter the date of the report as day, month, year; or month, year. If more than one date appears on the report, use date of publication.

7a. TOTAL NUMBER OF PAGES: The total page count should follow normal pagination procedures, i.e., enter the number of pages containing information.

7b. NUMBER OF REFERENCES Enter the total number of references cited in the report.

8s. CONTRACT OR GRANT NUMBER: If appropriate, enter the applicable number of the contract or grant under which the report was written.

8c, & 8d. PROJECT NUMBER: Enter the appropriate military department identification, such as project number, subproject number, system numbers, task number, etc.

9a. ORIGINATOR'S REPORT NUMBER(S). Enter the offical report number by which the document will be identified and controlled by the originating activity. This number must be unique to this report.

9b. OTHER REPORT NUMBER(S): If the report has been assigned any other report numbers (either by the originator or by the sponsor), also enter this number(s).

10. AVAILABILITY/LIMITATION NOTICES: Enter any limstations on further dissemination of the report, other than those

imposed by security classificat such as:

- (1) "Qualified requesters may obtain copies of this report from DDC."
- "Foreign announcement and dissemination of this report by DDC is not authorized." (2)
- "U. S. Government agencies may obtain copies of this report directly from DDC. Other qualified DDC users shall request through (3)
- (4) "U. S. military agencies may obtain copies of this report directly from DDC. Other qualified users shall request through
- "All distribution of this report is controlled. Qual-ified DDC users shall request through (5)

If the report has been furnished to the Office of Technical Services, Department of Commerce, for sale to the public, indi-cate this fact and enter the price, if known-

11. SUPPLEMENTARY NOTES: Use for additional explanatory notes.

12. SPONSU ING MILITARY ACTIVITY: Enter the name of the departmental project office or laboratory sponsoring (pay-ing for) the research and development. Include address,

13. ABSTRACT: Enter an abstract giving a brief and factual summary of the document indicative of the report, even though it may also appear elsewhere in the body of the technical re-port. If additional space is required, a continuation sheet shall he attached.

It is highly desirable that the abstract of classified reports be unclassified. Each paragraph of the abstract shall end with an indication of the military security classification of the in-formation in the paragraph, represented as (TS). (S), (C), or (U)

There is no limitation on the length of the abstract. How-ever, the suggested length is from 150 to 225 words.

14. KEY WORDS: Key words are technically meaningful terms or short phrases that characterize a report and may be used as index entries for cataloging the report. Key words must be selected so that no security classification is required. Identi-fiers, such as equipment model designation, trade name, military project code name, geographic location, may be used as key words but will be followed by an indication of technical con-text. The assignment of links, rules, and weights is optional.

UNCLASSIFIED

Security Classification