UNCLASSIFIED

AD NUMBER

AD843739

LIMITATION CHANGES

TO:

Approved for public release; distribution is unlimited.

FROM:

Distribution authorized to U.S. Gov't. agencies only; Administrative/Operational Use; OCT 1968. Other requests shall be referred to Naval Civil Engineering Lab., Port Hueneme, CA.

AUTHORITY

NCEL ltr 12 Mar 1969

THIS PAGE IS UNCLASSIFIED

AD 843739 2

Technical Note N-992

WATER VAPOR DIFFUSION THROUGH PROTECTIVE COATINGS. PART I. A METHOD OF MEASURING WATER VAPOR PERMEABILITY OF COATING FILMS BY RADIOISOTOPE TRACER TECHNIQUE AND ITS APPLICATION

By

E. S. Matsui

October 1968

Each transmittal of this document outside the agencies of the U. S. Government must have prior approval of the U. S. Naval Civil Engineering Laboratory. OV 26 1968

41

NAVAL CIVIL ENGINEERING LABORATORY Port Hueneme, California WATER VAPOR DIFFUSION THROUGH PROTECTIVE COATINGS. PART I. A METHOD OF MEASURING WATER VAPOR PERMEABILITY OF COATING FILMS BY RADIOISOTOPE TRACER TECHNIQUE AND ITS APPLICATION Technical Note N-992 Z-R011-01-01-087

by

. 7

E. S. Matsui

ABSTRACT

A method of measuring the permeability constant and the diffusion rate of water vapor through a polymer film by the radiochemical method is elaborated. It demonstrates that the radiochemical method, as compared to the ASTM Standard Method, is precise, sensitive and rapid. The radiochemical method is also useful in the investigation of other parameters which influence permeability of water vapor.

Each transmittal of this document outside the agencies of the U. S. Government must have prior approval of the U. S. Naval Civil Engineering Laboratory.

A 19/14 WHITE SECTIOF --- 5:5710 الشرين

INTRODUCTION

The Naval Facilities Engineering Command is responsible for the operation and maintenance of the many structures throughout the Naval Shore Establishment. These structures are subject to corrosion and deterioration from their natural environment and must be protected to minimize this deterioration and resultant costly repairs. It is a well established^{1,2,3,4,5} and recognized fact that metal

It is a well established^{1,2,3,4,3} and recognized fact that metal corrosion is electrochemical in nature, and no further discussion is necessary on this basic subject. Since practically all electrochemical or common corrosion processes require the presence of water or water vapor, it should be possible to prevent or reduce corrosion by isolating metallic surfaces from water or water vapor.

Painting is the most widely used method for minimizing corrosion of large surface areas because of the simplicity of application and the low initial cost. Paints, however, have inherent deficiencies that allow water or other corrosive materials to penetrate the film to the substrate in varying degrees and eventually affect the protection of coatings. Hence a detailed study of the mechanism of water vapor permeation through organic coatings should help in understanding the limitations of these paint films and, hopefully, will suggest ways and means by which they may be improved.

BACKGROUND

The permeability of coatings to moisture has been studied by many workers,⁶,⁷,⁸,⁹,¹⁰,¹¹ but their studies have been very limited and the accuracy of data on water vapor transmission is much less than desired. This situation is caused by the difficulty associated with measuring accurately the quantity of water vapor diffusing through a film. The amount is usually too minute to be accurately measured by chemical means, and is in a form which is not determinable by the usual analytical methods.

In the method for measuring water vapor transmission through a film given in ASTM Standard D1653-62T, the loss of weight of water passing through a sample film is determined under a specific set of conditions. This method will not afford results in a reasonably short time because the weight of water vapor passed is too small to be measured accurately. This method is neither as sensitive nor as accurate as one desires and so is used only for the preliminary determination of water vapor transmission. It also lacks versatility in its application, in that the method does not provide for controlled experiments in which the effects of changing temperature, vapor pressure, etc., can be used to characterize the mechanisms of water vapor diffusion.

This study was undertaken to develop an improved method for measuring vapor diffusion through films as applied to paint, by using tritiated water as a tracer. With such a technique, the permeability coefficient of widely differing materials could be measured with high speed and accuracy. Systems have been proposed 14, 15 and investigated, 16, 17, 18 in which radioisotope tracer techniques are used to measure water vapor and ionic diffusion through protective films.

This report describes the development of a sensitive and versatile radiometric method to measure water vapor permeability through organic membranes and its application to an investigation of the basic factors which may play an important role in water vapor transmission.

THEORY OF PERMEATION

The mechanism of vapor diffusion through an organic membrane is not a simple diffusion process as in a porous material. It is a generally accepted theory^{6,12} that the permeation process occurs in three stages: (1) condensation and dissolving of water vapor in one side of the film, (2) diffusion through the film, (3) evaporation from the other side. Because of this dual transfer mechanism of solution and diffusion, the permeability of the vapor is a product of its diffusion coefficient (D) through the membrane and its solubility (S) in the membrane. It is mathematically expressed as⁶, 12

$$\mathbf{P}_r = \mathbf{D} \mathbf{S} \tag{1}$$

Where

P = Permeability in gm-cm/cm²/cmHg/hr,

- D = Diffusion Coefficient in cm²/hr,
- S = Solubility of penetrant in $gm/cm^3/cmHg$.

The driving force for water vapor diffusion through the organic membrane is the vapor pressure difference between its two faces. The amount of water vapor (Q) diffusing through a given membrane at a given temperature is dependent upon the effective area (A), the thickness (d), the vapor pressure differential between the faces of the membrane (Δp), and the time (t), according to the following one-dimensional steady state equation⁶,13 from Fick's Law;

$$Q = \frac{P_r}{d} \cdot A \cdot t \cdot \Delta p \qquad (2)$$

The permeability (P_r) which characterizes the water vapor transmission resistance of the membrane under consideration is dependent upon the nature of both the membrane and the permeating vapor. It is interesting to note that this permeability equation (2) is completely analogous¹² to the basic heat conduction equation:

$$Q = \frac{K}{d} \cdot A \cdot t \cdot \Delta p$$
 (3)

in which permeability (P_r) is analogous to conductivity (K), and the partial pressure difference (Δp), is analogous to the temperature difference (ΔT).

The dependence of the amount of water vapor (Q) diffusing through the membrane upon the time (t), and area (A) in Equation (2) seems obvious. The validity of the linear dependence of amount of diffusing water vapor (Q) on vapor pressure and inverse linear dependence on membrane thickness will be examined. The validity of the independence of permeability (P_r), from varied vapor pressures, thicknesses and temperatures of film will also be investigated.

RADIOCHEMICAL EXPERIMENTAL METHOD

Apparatus

Diffusion Cell: A detailed diagram of the present design of the diffusion cell is shown in Figure 1. The diffusion cell is made of Plexiglas (A) and Pyrex glass tubing (B). Each half of the diffusion cell consists of a water mantle (C) and an exposure chamber (D). The water mantles (C) maintain the desired temperature in the chambers and the sample membrane (E) during the experiments. The sample membrane is placed between two fine copper gauzes (F). An O ring (G) and a rubber gasket (H) are used for sealing the two halves of the diffusion cell. When the cell is assembled, the exposed portion of the sample membrane is 20 cm^2 in area. The copper gauzes give even support to the sample membrane while protecting it from damage which might occur by a sudden change in pressure between the two chambers. The lower chamber is provided with a thermocouple probe (I) which enables an experimenter to monitor the temperature of the sample membrane directly rather than relying on the water mantle temperature. Screw (J) is tightened with moderate fingertight force to secure a high-vacuum seal.

Vacuum System: In order to measure the permeation rate through a sample membrane, a known constant pressure of water vapor is maintained on the surface of the sample membrane by means of a vacuum system represented diagrammatically in Figure 2. The vacuum system, including the glass tubing and stopcocks is made of high-vacuum grade Pyrex glass except for the previously described diffusion cell (1,2). The vessel

(3) which contains tritiated water is connected, through a T-shape stopcock (4), with the lower half of the diffusion cell (1) (separated from the upper half (2) by the sample membrane), and with an arm of the manometer (6) through T-shape stopcock (5). The other arm of the manometer is connected through a T-shape stopcock (16) to the upper half of the diffusion cell (2). The manometer thus provides direct reading of vapor pressure differential between the two faces of the sample membrane rather than the assumed vapor pressure on one surface based on the temperature of the tritiated water in the vessel (3). This manometer is also equipped with a vapor pressure controlling device (7) which regulates the temperature of the tritiated water in the vessel.

The desired temperature of the sample membrane, the diffusion cell, and the entire vacuum system is maintained constant throughout an experiment by the water mantle and the heating element (18), partially shown in Figure 2, which is wound over all the glass tubing. This temperature regulating device prevents condensation of tritiated water vapor within the Pyrex glass tubing by maintaining the temperature above the dew point at all times.

The vacuum system is designed in such a way that the diffusion cell, the mercury manometer or other elements can be disconnected from the assembly by a number of controlling stopcocks as can be seen in Figure 2.

Method of Determining Permeability

The unpignented films described in this report were prepared by the method described by Drisko and Matsui.¹⁹ Films that were not of uniform thickness (deviation of more than \pm 0.2 mil) and not free of air bubbles and other flaws which might affect experimental results were rejected. Film thickness were measured with a micrometer.

A sample membrane was placed in the diffusion cell and the cell (1,2) was mounted on the vacuum system as shown in Figure 2. The tritiated water (approximately 10 to 15 ml) of known activity (approximately 15 microcuries (μ c) per ml) in the vessel (3) was frozen by a mixture of dry ice and cellosolve, and the vessel was evacuated several times to remove dissolved gas prior to the experiments. The cold trap and the Drierite (14) are connected in series before the vacuum pump to remove any residual tritiated water vapor which may be present in the vacuum system during the evacuation. Stopcock (4) was then closed with respect to vessel (3). The same operation was followed with the absolute alcohol in tube (8) and then stopcock (9) was closed to avoid reabsorption of gas from the atmosphere until the experiment begins.

The whole vacuum system, with stopcocks (4) and (9) closed, was then evacuated for 15 minutes, or longer, until the pressure of the vacuum system was reduced to less than 1.0 mmHg as indicated by the vacuum gage (13). The stopcocks of the receiving tubes (10, 11, and 12) were then closed and one of the receiving tubes (10) was dipped in a Dewar flask containing dry ice and cellosolve mixture.

Stopcock (15) was then closed and T-shape stopcock (5) was turned with the foot of the "T" toward stopcock (15) to cut off the pumping action from the experimental system and to connect each half of the diffusion cell (1,2) separated by the sample membrane, to an arm of the manometer (6). The vapor pressure controlling device was later adjusted to obtain the desired vapor pressure difference.

Tritiated water vapor from the vessel was admitted into the manometer through T-shape stopcock (4). As soon as the desired vapor pressure was obtained as indicated by the manometer, tritiated water vapor was admitted into lower half of the diffusion cell through the T-shape stopcock (4). Admission of the tritiated water vapor into the lower half of the cell is the initial moment (t = 0) of the experiment.

The stopcock for receiving tube (10), which was immersed in coolant, was then opened to condense and freeze out any tritiated water vapor which passed through the sample membrane. Freezing of the receiving tube ensured a constant pressure difference between the two faces of the sample membrane, since any vapor which passes through the membrane will be frozen out in the receiving tube.

After a predetermined length of time, approximately one to two hours, the vessel (3) was closed from the rest of the system by turning stopcock (4), and that time was recorded as the end of the experiment.

Vapor from the warmed absolute alcohol (approximately 40° C) in tube (8) was then released into the upper half (2) of the diffusion cell to purge it of any residual tritiated water vapor which was carried to and frozen out in receiving tube (10). The stopcock for the receiving tube (10) was closed after repeating the above purging procedure several times.

Method of Counting and Calculation

The tritiated water vapor condensed by the preceding procedure emits extremely soft β -radiation. A liquid scintillation spectrometer is most suitable for counting such a low energy beta emitter.

A most widely used scintillation solution, and the one used in these studies, is a mixture of "PPO", 2,5-diphenyloxazole, and "POPOP", p-bis-(2-5-phenyloxazolyl)-benzene, dissolved in toluene. This scintillation solution is commercially available.

The receiving tube (10), which contains the condensed tritiated water vapor, was then removed from the vacuum system and diluted with 1 ml of absolute alcohol. The absolute alcohol was added to make the liquid sample miscible with the scintillation solution. The sample diluted with alcohol was then transferred into a counting vial and diluted to its full volume (approximately 20 ml) with the scintillation solution.

The amount of the tritiated water vapor diffused through the sample membrane was used to calculate the diffusion rate, R, in

 $mg/cm^2/hr$ and permeability constant, P_r , for the membrane in $mg-mm/cm^2/hr/cmHg$ by mean of the following formulas:

Diffusion rate (R) =
$$\frac{N \cdot 100}{a \cdot A \cdot t \cdot k}$$
 (4)

Permeability Constant (P_r) =
$$\frac{N \cdot d \cdot 100}{a \cdot k \cdot A \cdot t \cdot \Delta p}$$
 (5)

where

- N = Rate in counts per minute
- a = Specific activity of tritiated water, counts per min/mg
- A = Effective area of sample membrane, cm^2
- t = Exposed time, hours
- k = Efficiency of scintillation counter, %
- d = Thickness of sample membrane, mm
- Δp = Vapor pressure difference between the two faces of the sample membrane, cmHg

In order to reduce the random error of counting to less than 1% at the 95% probability level, each sample is counted to register 40,000 or more counts at each measurement. The specific activity (a) of the tritiated water in the vessel is selected so as to give a required minimum count (40,000 plus) within a reasonable time (approximately 10-20 minutes). For highly impermeable membranes, tritiated water of higher activity should be used. Because of the high activity of the tritiated water, background activity need not be considered.

Counting efficiency (k) of the liquid scintillation counter is determined by applying the channel ratio method²⁰ described by E. T. Buch.

Since a steady rate of diffusion was not immediately attained during the experiment, a collection of condensates was repeated until the scintillation counts indicated that a diffusion rate plateau had been reached. A minimum of five samples was collected for analysis after a steady rate of diffusion was attained.

Processing of the results of the above procedure is greatly simplified by use of computer techniques. The liquid scintillation spectrometer can be loaded with up to 100 samples and each sample counted as many times as desired. The number of counts from each channel is automatically put on punch cards. These punched cards are fed into the computer along with other essential data. The computer will compute and print out counting rate, channel ratio, counting efficiency, diffusion rate, and the permeability constant of each sample in tabular form. The computer program together with input and output data is shown in Appendix A.

LABORATORY RESULTS

Reliability of Counting Data

The reliability of measured values obtained by the above radiochemical method was determined by taking the count of each sample five times as shown in Table 1. The results show that the random count error of the above system is less than 1% per each measurement. It also indicates that the counting system is precise to a high degree, as long as each count is more than the required 40,000. However, it is preferable to take the count of each sample more than once since faulty operation or malfunctioning of instruments would not be discovered by a single counting.

Precision of Radiochemical Method

An alkyd resin was obtained from a local paint manufacturer and unpigmented films of several thicknesses were prepared as previously described.

Each prepared film was placed in the diffusion cell and exposed to the tritiated water vapor. The vapor pressure difference and temperature of the sample film were maintained at 20 mmHg and 30° C, respectively, throughout the experiment. The exposure times were varied from 50 minutes to 180 minutes for each sample film. The scintillation count of each sample was read and the diffusion rate determined as previously described. A minimum of five condensates was collected for each film after a state of steady vapor flow rate was attained.

The results for the water vapor diffusion rates are given in Table 2. The coefficients of variation were 4.02, 2.67, 7.50 and 3.79% at film thicknesses of 0.9, 1.9, 2.7 and 3.5 mils, respectively.

The precision of this radiochemical method was evaluated by comparing it with the precision obtained by the ASIM Standard method (D1653-62). The ASIM Standard Method uses a permeability cup which consists of two parts, - a shallow flanged cup and a flat ring matching the flange on the cup. Water is poured into the cup and the film under test is held tightly between the cup and ring by means of clamps.

The cup, so assembled, was placed in a dessicator and weighed each 24 hours for a period of one week. Phosphorous pentoxide was used as the dessicant. The dessicator was placed in a well ventilated room where the temperature was maintained between 70° to 85° F. The

diffusion rate of water vapor passing through the film was determined from the weight loss rate.

The amount of moisture diffusing through a film is affected by the film thickness, as stated previously in formula (2). Since it is very difficult, if not impossible, to reproduce films with exactly the same thicknesses, the films used in the ASTM Standard Method were first used in the radiochemical method.

The diffusion rates obtained by the above ASTM Standard method are given in Table 3. The coefficients of variation were 8.86, 8.34, 8.56, and 59.66 at film thicknesses of 0.9, 1.9, 2.7 and 3.5 mils respectively, which are considerably larger than the coefficients of variation obtained by the radiochemical method. These larger values of the coefficients of variation were obtained even though the weight loss incurred in the first 24 hours period was excluded from the calculations because the water vapor diffusion rate did not attain a steady state of flow during that period.

The greater precision of the radiochemical method was determined statistically by the F-test. The F-test is a statistical measure used to compare the precision of two sets of measurements by taking the "atio of two variances. When the ratio of the variances (F-ratio) exceeds the critical value of F, which is obtained from the statistical table F, it implies that there is indeed a significant difference in the precision between the two systems. The critical value of significance, F, at the 99% and 99.9% levels are 3.37 and 5.30 respectively. The F-ratio obtained, 19.78, greatly exceeds the above two critical values. This indicates a very highly significant improvement in precision by the radiochemical method over that obtained by the ASTM Standard Method.

Summary of the Laboratory Results

Reliability of the above counting system was very good, and the random error of the counting system was well below 1% as shown in Table 1.

The sensitivity of the above counting system can be increased to measure down to 1 microgram (1 x 10^{-6} gm), whereas the analytical balance used in the ASTM Standard Method is accurate to 0.2 mg (200 x 10^{-6} gm). However, the precision of the diffusion system used in the radiochemical method as a whole is approximately ± 10 microgram (μ g) at the 95% confidence level as shown in Table 2.

The diffusion rate, once a steady state of flow is attained, can be measured in a shorter time (1~2 hours) over one day whereas the ASTM Standard method required readings at 24 hour intervals over one week. Shorter intervals between readings by the radiochemical method is possible because of the almost instantaneous establishment of a vapor pressure gradient between the two surfaces of the sample membrane in the vacuum system, whereas, it may take several hours before a steady state pressure gradient can be established by the ASTM Standard Method.

Statistical analysis indicated that the greater precision obtained by the radiochemical method was very highly significant over the precision obtained by the ASTM Standard Method.

Precisely monitorable vapor pressure differentials and temperatures with the radiochemical apparatus provide the means of examining the effects of vapor pressure and temperature separately on the permeability of the films, whereas it is not possible to monitor temperature without affecting vapor pressure by the ASTM Standard Method.

Since the tritiated water emits very soft \exists -radiation and only a small amount (approximately 150 µc per month) was used, elaborate safety precuations were not necessary. The U. S. Atomic Energy Commission (AEC) does not require a license for a package of tritiated water whose activity is less than 250 µc. A total of ten license-exempt quantities of tritium may be possessed at any one time. However, experimenters using radioisotopes may be subjected to institutional and local regulations in addition to AEC regulations.

APPLICATION OF RADIOCHEMICAL METHOD TO MOISTURE PERMEABILITY RESEARCH

Effect of Thickness

Equation 2 states that the amount of water (Q) diffusing through a permeable membrane at a given temperature is inversely proportional to thickness (d) and that the permeability constant (P_r) is independent of thickness (d). This inverse linear dependence of (Q) on thickness (d) was studied by testing a series of unpigmented films (alkyd TT-R-266 Type II and epoxy-polyamide cured) of different thicknesses. The films were prepared, and the diffusion rates and permeability constants (P_r) determined as described earlier. All sample films were subjected to a vapor pressure difference (Δp) of 2.0 cmHg at a temperature of 30° C during the measurements.

The rate of the moisture diffusing through the membrane increased inversely with the film thickness (d) in both type as shown in Table 4. The data obtained from samples less than 1 mil in thickness were not reliable, no doubt because of difficulty in preparing such thin films without pin holes or other defects. Since only two generic types of films, alkyd and epoxy, were tested, it is not established here whether all other types of films would behave similarly, but it is a reasonable assumption that they would differ only in degree as suggested in Figure 3.

The average permeability constants of the alkyd and of the epoxy films were 4.196 \pm 0.200 and 1.000 \pm 0.077 µg/mm/cm²/hr/cmHg respectively at the 95% confidence limit. It means that 19 times out of 20 the average permeability constant (P_r) will lie within the above range.

However, data in Table 4 show that the permeability constants (P_r) of the alkyd films fluctuated more than did those of the epoxy films. If permeability constant (P_r) is independent of thickness, then the plot of the diffusion rate versus 1/d (inverse thickness) should be a straight line passing through the origin with a slope of $P_r(A \cdot \Delta p)$, because area (A), vapor pressure difference (Δp), and temperature were maintained constant during the experiment. The plots of diffusion rate for progressively thinner alkyd films deviated from the expected straight line, determined by step-wise linear regression analysis (STRAP), while plots of diffusion rate for the epoxy films were as expected a straight line passing through the origin (see Figure 3). Output from STRAP are shown in Appendix B.

This indicates that the independence of the permeability constant from thickness is valid only for some types of films. Equation 1 states that the permeability constant (P_r) is a product of its diffusion coefficient (D) and the solubility (S) in the membrane. It follows that the independence of the permeability constant from thickness is no longer true if the film is made from materials that absorb much water, or is hydrophilic in nature, as demonstrated by the alkyd films which are more hydrophilic than the epoxy films.

The plots of diffusion rate, R, versus thickness, d, on semilogarithmic graph shown in Figure 4 suggest that it is possible that the diffusion rate of moisture increase inversely in exponential function with the thickness as the membrane becomes more hydrophilic in nature.

Effect of Vapor Pressure

Equation 2 states that the amount of water (Q) diffusing through a membrane is directly proportional to the vapor pressure difference (Δp) and that the permeability constant (P_r) is independent of the vapor pressure difference (Δp) . This linear dependence of (Q) on vapor pressure difference (Δp) was examined by subjecting two types of 2-milthick unpigmented films (alkyd and epoxy), to a series of different vapor pressure differences (Δp) at a constant temperature.

The results of the diffusion rates and the permeability constants are given in Table 5. They show that the diffusion rate of both films (alkyd and epoxy) increased with vapor pressure difference (see Figure 5).

Here again, as mentioned in the preceeding section, it is not established that all other generic types of films will behave similarly, since only two types of clear films (alkyd and epoxy), were tested. However, it can be reasonably assumed that most other types of paint films will behave similarly. It would be desirable, if time permits, to use many other different generic types of films in this type of study since so many different types of coating have been developed in recent years.

The average permeability constant (P₁) of the alkyd and epoxy films were 3.478 ± 0.333 and $1.024 \pm 0.110 \ \mu g/mm/cm^2/hr/cmHg$ at the 95% confidence limits respectively.

Examination of Table 5 reveals that the permeability constant of each film, alkyd and epoxy, seems to increase with vapor pressure difference. If permeability constant is independent of vapor pressure change as stated in Equation 2, then a plot of the diffusion rate versus vapor pressure difference would be a straight line passing through the origin with a slop of $(P_r \cdot A)/d$. However, the plot for the alkyd films shows considerable deviation from a straight line, determined by STRAP, as the vapor pressure difference increased, whereas the plot for the epoxy film deviated only slightly. This indicates that the permeability constant of the alkyd film is not independent of vapor pressure difference. The permeability constant of the epoxy film was also affected by vapor pressure difference but to a lesser degree as shown in Figure 5.

A statistical analysis, F-test, was performed to ascertain whether the varying values of the permeability constant were due to the standard deviation of individual measurements or due to the existence of true differences among the permeability constants. For 3 and 16 degrees of freedom, the critical F-value at the 0.01 level was 5.29 for the alkyd, and for the epoxy film for 2 and 12 degrees of freedom, the critical F-value at the 0.01 level was 6.03. The F-ratios obtained, 14.82 and 12.04 for alkyd and epoxy respectively, exceeded their critical values. This indicates that the fluctuations among the permeability constants are not solely due to the standard deviation of individual measurements but due to a true difference among the permeability constants. Hence the permeability constant of both films, alkyd and epoxy, indeed increased as vapor pressure increased.

The deviation from independency of the permeability constant from vapor pressure becomes more apparent with films which are more hydrophilic, as shown by the greater deviation of the alkyd film which is more hydrophilic than the epoxy film. This phenomena may be explained by Equation 1 which states that the permeability constant (P_r) is a product of the diffusion constant (D) and solubility (S), whereas solubility (S) is function of kP as stated in the Equation (6) of Henry's Law.^{6,9,23}

$S = kP \tag{6}$

k is the solubility constant and P is the partial pressure of the penetrant. Thus, if solubility (S) is pressure dependent, then the permeability constant (P_r) will also be pressure dependent as the results of this study appears to corroborate.

Effect of Temperature

The effect of temperature on the diffusion rate and permeability constant of the alkyd and epoxy films, 1.4 and 2.0 mil-thick respectively, were tested by subjecting films to a series of different temperatures while maintaining vapor pressure constant at 30 mmHg. The results are given in Table 6.

Within the range of temperatures tested, the diffusion rate of the alkyd film appeared unaffected while the epoxy film increased slightly with temperature as shown in Figure 6. The average diffusion rate of alkyd film was $323.29 \pm 4.99 \ \mu g/cm^2/hr$ at the 95% confidence limits. The coefficient of variation was 5.54% which indicates that the effect of the temperature on the diffusion rate was negligible. The average diffusion rate of the epoxy film, was $47.00 \pm 4.56 \ \mu g/cm^2/hr$ at the 95% confidence limits. The coefficient of variation was 23.54% which indicates that the effect of the temperature of the epoxy film, was $47.00 \pm 4.56 \ \mu g/cm^2/hr$ at the 95% confidence limits. The coefficient of variation was 23.54% which indicates that there is a measurable dependence of diffusion rate on temperature for the epoxy film.

The average permeability constant (P_r) of alkyd film was 4.186 + 0.142 µg/mm/cm²/hr/cmHg at the 95% confidence limits. The coefficient of variation was 9.02% which indicates that the permeability constant of the alkyd film was independent on the temperature change. The average permeability constant (P_r) of the epoxy film was 1.183 + 0.115 µg/mm/ cm²/hr/cmHg at the 95% confidence limits. The coefficient of variation was 22.87% which indicates a somewhat larger fluctuation of the permeability constant which appeared to increase with an increase in temperature as seen in Table 6.

The results of the above experiments differ from those of other researchers 13, 17 who have stated that the increase of permeability as much as doubled for a 10°C rise in temperature. Since the permeability (P_r) is proportional to the product of solubility (S) and diffusion constant (D) as stated earlier in Equation 1, the effect of temperature on permeability is two-fold. The first effect is upon the solubility (S). During the diffusion process, water vapor first condenses on the surface of the membrane as part of the solution process. Since the condensation process of the water vapor is exothermic, the solubility of water into the polymer at the constant vapor pressure decreased as temperature increases. The second effect of temperature is on the diffusion constant (D). Since the diffusion is an activated process, 6,9,13 the diffusion rate of water in the polymer increases as temperature increases. The trend of these two parameters to vary in opposite direction leads to an anomalous and puzzling variation of the permeability with temperature. However, as the temperature is further raised, the rate of increase of the diffusion constant (D) becomes greater than the rate of decrease of solubility (S), and as a result, the permeability begins to increase with increase in temperature as the results of this study appears to corraborate.

CONCLUSION

A method of measuring the permeability constant and the diffusion rate of water vapor through a polymer film, alkyd or epoxy, by the radiochemical method has been elaborated. It demonstrates that the radiochemical method, as compared to the ASTM Standard Method, is very sensitive, rapid, and precise. The diffusion rate, once a steady state of flow is attained, can be measured in shorter time intervals $(1 \sim 2 \text{ hours})$ over one day whereas the ASTM Standard Method required readings at 24 hour intervals over one week. The sensitivity of the above counting system can be increased to measure down to 1 microgram $(1 \times 10^{-6} \text{ gm})$, whereas the analytical balance used in the ASTM Standard Method is accurate to 0.2 mg (200 x 10^{-6} gm). Further, the radiochemical method is versatile in the investigation of other important parameters which influence permeability of water vapor. Such versatility is not possessed by other reported radiochemical methods 16, 17, 18 or by the ASTM Standard Method.

The data presented in this paper are part of a continuing investigation. Only two types of membrane, alkyd and epoxy, were investigated. Therefore, the results obtained here do not represent the behavior of all other types of film; for these others further research is required. However, it has been demonstrated from the limited data that:

1. The rate of the moisture diffusing through a membrane varied inversely with film thickness.

2. The independence of the permeability constant from thickness is valid, but this condition tends to break down if the film is made of a material that absorbs much water or is hydrophilic in nature.

3. The diffusion rate of moisture increases with an increase of vapor pressure differential.

4. The independence of the permeability constant from vapor pressure is not true for all types of film. This deviation becomes more apparent with films which are more hydrophilic.

5. The effect of temperature on the diffusion rate and the permeability constant is anomalous in that in the temperature range of this test $(22^{\circ} \sim 50^{\circ} \text{ C})$ the expected related rise with temperature was not conclusive. The permeability constant of the less permeable membranes is more sensitive to temperature changes than those of more permeable membranes.

6. Since a straight line passes through the origin, only one experimental point is required to determine the curve of permeability versus thickness (1/d) or permeability versus vapor pressure difference (Δp). However, plots tend to deviate from the expected straight lines as the membranes become more hydrophilic in nature.

FUTURE WORK

To complete this work, effects on the water vapor permeability of

films of (1) four different pigments, (2) varied pigment concentrations, and (3) water in the liquid form will be investigated.

ACKNOWLEDGEMENT

The author wishes to express his appreciation to the following NCEL personnel; Mr. F. Nelson for developing a vapor pressure controlling device; Mr. M. Botts, for fabricating a diffusion cell; Mr. J. Mitchell for developing a computer program, and other members of the computer staff who gave much assistance on mathematical interpretation.

	Counts Per Ten Minutes					
	1	2	3	4	5	
Channel (A)	67156	67112	67181	67379	67344	
Channel (B)	66271	66703	66565	66988	66724	
Total	1334 27	133905	133746	134367	134069	
s. d. <u>2</u> /	365.27	365.93	365.71	366.56	366.15	
Random Error (%)	0.273	0.273	0.273	0.272	0.273	
Average Random Error (%)	0.273					

Table 1. Reliability of Measured Value Obtained by the Radiochemical Method. $\frac{1}{-1}$

^{1/} Unpigmented alkyd film, 2.1 mil; vapor pressure, 20 mmHg; temperature, 30°C; exposure time, 123 minutes.

 $\frac{2}{2}$ S. D. = Standard Deviation

Alkyd Film <u>1</u> / Thickness, mil	U.9	1.9	2.7	3.5
Diffusion Rate, µg/cm ² /hr	358.30	197.33	151.69	102.58
At 95% Confidence Limits	<u>+</u> 17.94	<u>+</u> 6.55	<u>+</u> 14.15	<u>+</u> 4.83
Standard Deviation	14.43	5.27	11.38	3.89
Cv, % ^{2/}	4.02	2.67	7.50	3.79

Table 2. Analysis of Water Vapor Diffusion Rate Obtained by Radiochemical Method.

 $\frac{1}{}$ Unpigmented alkyd film (TT-R-266, Type II).

 $\frac{2}{4}$ A measure of relative dispersion about the sample mean.

Alkyd Film ^{1/} Thickness, mil	0.9	1.9	2.7	3.5
Average Diffusion Rate, ug/cm ² /hr	380.38	196.32	136.80	132.48
At 95% Confidence Limit ^s	<u>+</u> 41.91	<u>+</u> 20.35	<u>+</u> 14.57	<u>+</u> 98.26
Standard Deviation	33.71	16.37	11.72	79.03
Cv, %	8.86	8.32	8,56	59.66 <u>2</u> /

Table 3. Analysis of Water Vapor Diffusion Rate Obtained by ASTM Standard Method (D1653-62).

 $\frac{1}{}$ Unpigmented alkyd film (TT-R-266, Type II).

 $\frac{2}{2}$ Did not attain a steady-state of flow for three days.

Film Thickness, Microns, mils	Diffusion Rate, µg/cm ² /hr	Permeability Constant, µg/mm/cm ² /hr/cmHg
Alkyd Film:		
114.3 (4.5) 101.6 (4.0) 88.9 (3.5) 68.5 (2.7) 48.2 (1.9) 35.5 (1.4) 25.4 (1.0) 22.8 (0.9)	67.29 79.72 102.58 151.68 197.33 236.99 265.42 358.36	3.617 3.841 5.488 5.105 4.756 4.213 3.344 4.095 Ave. 4.196
Epoxy Film:		
101.6 (4.0) 50.8 (2.0) 25.4 (1.0)	22.68 35.89 7 3 .73	1.152 0.911 0.936 Ave. 1.000

Table 4. Effect of Thickness on Permeability $\frac{1}{2}$

 $\frac{1}{v_{apor}}$ pressure, 2.0 cmHg; temperature, 30° C.

Vapor Pressure, cmHg	Diffusion Rate, µg/cm ² /hr	Permeability Constant, ug/mm/cm ² /hr/cmHg
Alkyd Film: (2.0 mil)		
2.0 2.5 3.0 3.5	114.74 176.83 205.52 300.48	2.690 3.383 3.480 4. ³ 61 Ave. 3.478
Epoxy Film: (2.0 mil)		
2.0 3.0 4.0	35.89 55.42 96.32	0.911 0.938 1.223 Ave. 1.024

Table 5. Effect of Vapor Pressure on Permeability $\frac{1}{2}$

 $\frac{1}{1}$ Temperature, 30°C.

Temperature C ^O	Diffusion Rate, µg/cm ² /hr	Permeability Constant, µg/mm/cm ² /hr/cmHg
Alkyd Film: (1.4 mil)		
27°C 30°C 35°C 40°C 45°C 50°C	229.25 230.15 238.86 230.49 217.02 237.75	4.076 4.252 4.247 4.133 3.858 4.227
	Ave. 232.29 Cv,% 5.54	Ave. 4.186 Cv,% 9.02
Epoxy Film: (2.0 mil)		
22°C 25°C 30°C 40°C 48°C	39.88 42.43 35.89 54.35 52.54 Ave. 47.00	1.136 1.078 0.938 1.313 1.464 Ave. 1.183
	Cv,% 23.54	Cv,% 22.87

Table 6. Effect of Temperature on Permeability $\frac{1}{}$

 $\frac{1}{1}$ Vapor Pressure, 20 mmHg.



J Screw

Figure 1. Diffusion Cell.



Figure 2. Permeation apparatus for vapor diffusion.



(ιή/ molg..) stef noisuffid studie/ Δίστο (γ.)



Figure 4. Effect of thickness on permeability.







たいであるというとしよう

Figure 6. Effect of temperature on permeability.

APPENDIX A

COMPUTER PROGRAM TO DETERMINE WATER VAPOR PERMEABILITY OF PAINT FILMS

27

COMPUTER PROGRAM FOR MOISTURE PERMEABILITY OF PAINT FILMS

C

+I DISKWAVPRE WATER VAPOR PERMEABILITY THROUGH PAINT FILMS DIMENSION NO(5)+A(5)+B(5)+TIME(5)+T(5)+RATIO(5)+EFF(5)+TOT(5) DIMENSION TDH(5)+TDHA(5)+PERM(5)+THICK(5)+ARFA(5)+PRES(5) DIMENSION ACTVIV(5)+TFMP(5)+DA(5)+TF(5)+S(5)+O(5)+AB(17) READ 500.41.42.43 500 FORMAT(3E15.8) 700 READ 900.4.8L 900 FORMAT(15+A2) IF (M-511.1.97 97 TYPE 719 709 FORMAT (44HUSE & MAXIMUM OF FIVE DATA CARDS-TRY AGAIN 1 GO TO 99 1 DO 11 1=1+M READ 901+NO(1)+T(1)+A(1)+R(1)+TIMF(1)+THICK(1)+AREA(1)+PRES(1)+ 1ACTVTY(1)+TEMP(1)+DA(1)+TE(1)+S(1)+O(1) 901 FORMAT (12+F4+2+2F8+2+1X+F5+0+F5+1+2F4+0+F8+0+F4+0+244+1X+244) A(T)=A(T)/T(T) 2 B(1)=B(1)/T(1) TCT(1)= A(1)+B(1) RATIO(1) = B(1)/A(1) EFF(1)=A1+A2=RATIO(1)+A3=RATIO(1)==2 TIME(I) = TIME(I)/60.0 TDH([)=TOT(])/(ACTVTY(])*FFF(])*TIME(]))*100. TDHA(I)=TDH(I)/ARFA(I) THICK(1)=THICK(1)#.0254 11 PERM(1)=(THICK(1)*TDHA(1))/PRES(1) PUNCH 701 701 FORMAT(3X,2HNO,7X,4HFILM,8X,4HFILM,3X,4HFILM,4X,5HVAPOR,6X, 13HT20,9X,4HDATE) PUNCH 702 PRESSURE .12H 702 FORMATIATH ARFA TEMP AC THICKNESS ITIVITY) PUNCH 703 ,19H (CMHG) 10 (CM)2 (C) 703 FORMAT(39H (MM) 1PM/MG1/1 DO 13 [=1.M PUNCH 903, NO(1), THICK(1), AREA(1), TEMP(1), PRES(1), ACTVIY(1), DA(1), T 1E(1) 903 FORMAT(3X, 12, 8X, F6, 4, 4X, F5, 1, 2X, F5, 1, 4X, F5, 1, 4X, F9, 1, 4X, A4, A4) 13 CONTINUE PUNCH 704 TRIAL TRIAL TR 704 FORMAT(// ,79H 11AL TRIAL TRIAL) 1TAL PUNCH 705 5) 705 FORMAT(27X,50H 1 2 3 PUNCH 904+(DA(1)+TF(1)+I=1+M) 904 FORMAT(13HSAMPLE NUMBER+7X+5(4X+A4+A4)) PUNCH 905+(TIME(I)+I=1+M) 905 FORMAT(16HTIME OF EXP(HRS) +2X+5F12+3) PUNCH 906+(A(I)+I=1+M) 906 FORMAT(14HCHANEL A (CPM), 5X, 5F12.1) PUNCH 907+(B(1)+1=1+M) 907 FORMAT(14HCHANEL B (CPM).5X.5F12.1) PUNCH 908.(TOT(I).I=1.M) 908 FORMAT(14HTOTAL N (CPM).5X.5F12.1) PUNCH 909+(RATIO(1)+1=1+M) .5X.5F12.51 909 FORMAT(14HRATIO (8/A) PUNCH 910,(EFF(1),I=1,M) 910 FORMAT(15HEFFICIENCY(0/0), 3X, 5F12.2) PUNCH 911+(TDH(I)+I=1+M) 911 FORMAT(20HT20 DIFFUSED (MG/HR)+5F12+5) PUNCH 912.(TDHA(1),1=1,M) 912 FORMAT(9X+11H(MG/HR/CM2)+5F12+5) PUNCH 913+(PERM(1)+1=1+M) 913 FORMAT(12HPERMEABILITY/1X, BHCONSTANT/1X, 19H(MG/HR/CM2/CMHG/MM), 5F1 12.8//) 99 GO TO 700 END

3400032 22 JOB 22 XEQSW	00701360	00032007(02490	00465	1196	3611	3001026	00240	200009		
-23.46		51.51		-7	.87						
211000	8102200	9108300	156.	2.0	20.	4.0	14948.	30.	3=11=6	8 FPOXY	
221000	5050200	5591000	96.	2.0	20.	4.0	14948.	30.	3=11=6	A FPOXY	
2310001	16997001	12799900	186.	2.0	2	4.0	14948.	30.	3=12=6	A FPOXY	
241000	5448700	6036600	114.	2.0	20.	4.0	14948.	30.	3=12=6	8 EPOXY	
251000	7676400	8443000	135.	2.0	20.	4.0	14948.	30.	3=12=6	8 EPOXY	
NO	FTI	M	FTU	M F	TLM	v	POR	120	h	DATE	
	TH	CKNESS	ARE	A T	EMP	Pf	RESSURF	AC	TIVITY		
		(MM)	(CM	12 (()	1	(MHG)	(()	DM/MG)		
21		0508	20.	n 3	0.0		4.0	14	948.0	3=11=6A	
22		0508	20.	0 3	0.0		4.0	14	948.0	3=11=68	
23		0508	20.1	0 3	0.0		4.0	14	948.0	3=12=68	
24		0508	20.	0 3	0.0		4.0	14	948.0	3=12=68	
25	•	0508	20.	03	0.0		4.0	14	948.0	3=12=68	
			71			TP	141	TR	1 & I	TRIAL	RTAL
				1			,		3	4	5
SAMPLE	NUMBER		3=1	1=68		3=11	•68	3=12	=68	3=12=68	3=12=68
TIME OF	EXPINES	5)	2.0	500		1.60	00	3.10	00	1.900	2.250
CHANEL	A (CPM)		810	02.2		5050	.2	1169	9.7	5448.7	7676.4
CHANEL	B (CPM)		910	08.3		559	.0	1279	9.9	6036.6	8443.0
TOTAL N	(CPM).		172	10.5		1064	.2	2449	9.6	11485.3	16119.4
RATIO (9/A1		1.13	2417		1.10	108	1.09	403	1.10789	1.09986
EFFICIE	NCY10/01)	24	50		23.0	2	23.4	47	23.94	23.67
T20 DIF	FUSED IN	AG/HR)	1.1	80743		1.80	5004	2.2	5229	1.68864	2.02449
	(MG/HF	R/CM2)	• (9037		.09	300	•13	261	.08443	.10122
PERMEAB	ILITY										
(MG/HR	/CM2/CMH	G/MM)	.001	4772	•	00118	9112	.0014	3020	.00107229	.00128555

TABLE A. SAMPLE INPUT AND OUTPUT DATA OF MOISTURE PERMEABILITY

APPENDIX B

STRAP (STEPWISE LINEAR REGRESSION ANLYSIS PROGRAM) DATA FOR PLOTTING WATER VAPOR DIFFUSION RATE VS VARIOUS PARAMETERS.

R = DIFFUSION RATE D = FILM THICKNESS INR = NATURAL LOG OF DIFFUSION PATE ΔP = VAPOR PRESSUPE GRADIENT

.

TABLE 8-1. OUTPUT FROM STRAP FOR R VS 1/D PLOTS OF FIG. 3 FOR ALKYD FILMS

.

NO. OF IND. VARIABLES 01 DEPENDENT VARIABLE NO. 01 NO. OF OBSERVATIONS 040

١

 TOLERANCE LEVEL
 .1000000-03

 STEP NO.
 ENTERING VAR.
 ERROR OF EST.
 F TO ENTER
 F VALUE

 01
 .2871615+02
 .1000000-01
 .2017B32+04

 VARIABLE NO.
 COEFFICIENT
 ERROR OF COEF.

 01
 .3150659+03
 .7013889+01

 R
 SOUARE = .9810390+00

STUDENTS T = .2023000+01

NO.	OBSERVED	FITTED	CONFIDENCE	LIMITS	RESTDUAL
001	.3566900+03	• 3500732+03	.2898792+03	•4102673+03	6616760+01
002	.3485200+03	•3500732+03	.2898792+03	•4102673+03	.1553240+01
003	.3755200+03	.3500732+03	.2898792+03	.4102673+03	2554676+02
004	·341010C+03	.3500732+03	.2898792+03	.4102673+03	.9063240+01
005	.3699700+03	.3500732+03	.28 / 792+03	4102673+03	1989676+02
006	.2215200+03	.3150659+03	.2552654+03	.3748664+03	.9354592+02
007	.3007100+03	.3150659+03	.2552654+03	.3748664+03	.1435592+02
008	.2972200+03	.3150659+03	.2552654+03	.3748664+03	.1784592+02
009	.2591300+03	.3150659+01	.2552654+03	.3748664+03	.5593592+02
010	.2485600+03	.3150659+03	.2552654+03	.3748664+03	.6650592+02
011	.2283600+03	.2250471+03	.1660768+03	.2840173+03	3312920+01
012	·2455700+03	.2250471+03	·1660768+03	.2840173+03	2052292+02
013	.2321100+03	.2250471+03	.1660768+03	·2840173+03	7062920+01
014	.2474800+03	.2250471+03	.1660768+03	.2840173+03	2243292+02
015	.2314700+03	.2250471+03	.1660768+03	.2840173+03	6422920+01
016	.1916400+03	.1658242+03	.1072534+03	.2243950+03	2581584+02
017	1948600+03	1658242+03	.1072534+03	.2243950+03	2903584+02
018	.2056700+03	.1658242+03	10.72534+03	.2243950+03	3984584+02
019	.1985100+03	.1658242+03	1072534+03	·2243950+03	3268584+02
020	1959800+03	.1658242+03	.1072534+03	·2243950+03	3015584+0?
021	1354100+03	.1166911+03	•583611h+h2	1750211+03	1871892+02
022	.1654600+03	.1166911+03	•5836110+02	+1750211+03	4876892+02
023	.1468100+03	1166911+03	.5836110+02	.1750211+03	3011892+02
024	.1578700+03	•1166911+03	•5836110+02	1750211+03	4117892+02
025	1528800+03	1166911+03	•5836110+02	1750211+03	3618892+02
026	1044900+03	·9001883+02	·3178478+02	1482529+03	1447117+02
027	9738000+02	.9001883+02	•3178478+02	1482529+03	7361168+01
028	•1007300+03	•9001883+02	.3178478+02	1482529+03	1071117+02
029	1077200+03	+9001883+02	3178478+02	1482529+03	1770117+02
030	•1026000+03	•9001883+02	.3178478+02	1482529+03	-+1258117+02
031	•9121000+02	•7876648+02	2056551+02	1369674+03	1244352+02
032	.7718000+02	.7876648+02	2056551+02	1 369674+03	.1586480+01
033	•7141000+02	•7876648+02	2056551+02	1369674+03	•7356480+01
034	.8093000+02	•7876648+02	2056551+02	•1369674+03	2163520+01
035	•7810000+02	•7876648+02	.2056551+02	•1369674+03	•6664 0+00
036	.7206000+02	.7001465+02	1183637+02	1281929+03	2045352+01
037	•6170000+02	.7001465+02	1183637+02	1281929+03	•8314648+01
038	•5863000+02	•7001465+02	1183637+02	1281929+03	113'465+02
039	•5901000+02	•7001465+02	•1183637+02	1281929+03	·1100465+02
040	•6509000+02	•7001465+02	1183637+02	1281929+03	.4924648+01

TABLE 8-2. OUTPUT FROM STRAP FOR R VS 1/D PLOTS OF FIG. 3 FOR FPOXY FILMS

NO. OF IND. VARIABLES 01 DEPENDENT VARIABLE NO. 01 NO. OF OBSERVATIONS 015

.

TOLERANCE LEVEL .100000-03

STEP NO. 01	ENTERING VAR. 01	ERROR OF EST. •5467792+01	F TO ENTER •1000000-01	F VALUE 1207737+04
	VARIABLE NO. 01	COEFF1C1ENT •7417600+02	ERROR OF COEF. .2134407+01	

R SQUARE = .9885410+00

STUDENTS T = +2145000+01

NO.	OBSERVED	FITTED	CONFIDENCE	LIMITS	RESTDUAL
001	.7353000+02	.7417600+C2	.6158567+02	.8676634+02	.6460140+00
002	.6962000+02	.7417600+02	.6158567+02	8676634+02	.4556004+01
003	.8125000+02	.7417600+02	+6158567+02	.867663'+02	7073996+01
004	.6241000+02	.7417600+02	.6158567+02	·86766? ++02	+1176600+02
005	.8188000+02	.7417600+02	+158567+02	.8676634+02	7703996+01
006	+4099000+02	.3708800+02	.2513828+02	.4903772+02	3901998+01
007	.3760000+02	.3708800+02	.2513828+02	.4903772+02	5119980+00
008	.3315000+02	.3708800+02	.2513828+02	.4903772+02	.3938002+01
009	.3507000+02	.3708800+02	.2513828+02	.4903772+02	.2018002+01
010	.3266000+02	.3708800+02	.2513828+02	.4903772+02	.4428002+01
011	.2174000+02	.1854400+02	.6759872+01	.3032813+02	3195999+01
012	.2252000+02	.1854400+02	.6759872+01	·?032813+02	3975999+01
013	.2090000+02	.1854400+02	.6759872+01	• 3032813+02	2355999+01
014	.2480000+02	1854400+02	.6759872+01	• 3032813+02	6255999+01
015	.2346000+02	.1854400+02	.6759872+01	· 3032813+02	4915999+01

TABLE 8-3. OUTPUT FROM STRAP FOR INR VS D PLOTS OF FIG. 4 FOR ALKYD FILMS

,

NO. OF OBSERVATIONS INDEPENDENT VARIABLES DEPENDENT VAPIABLE

040

NO. OF IND. VARIABLES 01 DEPENDENT VARIABLE NO. 01

MEAN VALUES

.5047275+01

\$ TD • DEVIATION
•132*784+01

• 5861 050+00

0102 -.9853865+00

CORRELATION COEFFICIENTS

TOLERANCE LEVEL .100000-03

STEP NO.	ENTERING VAR.	FRROR OF EST.	E TO ENTER	F VALUE
01	01	1011539+00	•1000000-01	·1271740+04
	VARIABLE NO.	COEFFICIENT	ERROR OF COEF.	
	01	4363473+00	1223582-01	
	PURE CONSTANT	6132688+01	- 7438208-01	

R SQUARE = .9709866+00

STUDENTS T = .2024000+01

NO.	OBSERVED	FITTED	CONFIDENCE	LIMITS	RESIDUAL
101	.5876867+01	.5739976+01	·5529002+01	.5950950+01	1368911+00
002	·5853696+11	.5739976+01	.5529002+01	• 5950950+01	1137197+00
003	•5928578+01	·5739976+01	•5529002+01	•5950950+1]	1886120+00
004	•5831912+01	.5739976+01	·5527002+01	·5950950+01	9193590-01
005	•5913422+01	•5739976+C1	•5523002+01	•5950950+01	1734460+00
006	•5400513+01	.5696341+01	54858*4+01	·5906868+01	.2958 I+00
0 0 7	• 5706146+01	•5696341+∩1	•54°581-+01	•5906863+01	98.5201-02
008	.5694473+01	·5696341+01	-5445A14+01	·5206868+01	·1258500-02
000	• 5 5 5 7 3 3 0 + 0 1	•F696341+C1	- 5485814+P1	5%^6868+^1	•1-00113+0C
010	•5515684+01	•5696341+01	• 5485814+C1	.FORSA68+C1	·1806560+00
<u>^11</u>	·5430923+01	•5521802+01	•5312781+01	•5731R23+01	• 00 17890-01
015	•5503582+01	•5521802+01	•5312781+01	• 5730 F 23+0]	1822020-01
013	•5447211+01	•5521802+01	•5312791+∩1	• 5730823+01	•7450ncn-n1
014	•5511330+01	+5521802+ 1	•5312781+~`	•5730823+01	1047250-01
015	•5444450+01	•5521802+01	5312781+01	•5730B23+01	•7735200-01
016	•5255619+01	-503629+11	• 5095P47+01	•5511417+01	.48 1000-01
017	•5272281+01	•5303629+01	•5095940+11	•5511417+ 1	• 31 34 730-01
018	• 5326273+01	•5303629+01	· 5095840+01	•5511417+1	2264430-01
019	•5290839+01	•5303629+01	• 5095840+01	• 5511417+01	1278920-01
020	•5278013+01	.5303629+01	5095840+01	•5511417+01	·2561600-01
021	<pre>.4908307+01</pre>	4954551+01	•4747205+01	5161896+01	.4624350-01
022	•5108729+01	·4954551+01	· 4747205+01	·5161896+01	154:787+CC
023	·4989139+01	.4954551+01	.4747215+01	•5161805+1	345A850-01
024	.5061772+01	2545-1+01	.4747205+01	.5161896+01	1072212+00
025	•5029653+01	.4954551+01	• 4747205+01	•5161806+11	7510260-01
026	•4649091+01	•4605473+C1	• 4396683+01	·4814263+11	4341840-01
027	•4578621+01	•4605473+01	•4396683+01	+4P14263+01	.2685210-01
028	•46124+4+C1	•4605473+01	.4396683+01	·4814263+01	6970700-02
229	.4670335+01	.4605473+01	.4396683+01	·4814263+01	7406230-01
030	•4630838+01	.4605473+01	.4396683+01	.4814263+01	2536500-01
031	•4513165+01	.4387294+01	•4176663+01	.4577735+01	1258653+00
032	.4346140+01	.4387299+01	•4176663+01	.4507935+01	.4115800-01
033	•4268438+01	.4387299+01	·4176663+01	.4597935+01	.1188613+00
034	•4393585+01	.4787299+01	•4176563+01	.4597025+01	6285300-02
035	•4357990+01	.4387299+01	•4176663+01	.4597935+01	.2930920-01
036	+427749 +CI	•4169126+01	.3955939+01	.4382312+01	1083735+00
037	.4122284+01	.41(9126+01	. 2955939+01	·4382312+01	.46P417 -01
038	+4071247+01	.4169126+01	. 3955930+01	.(182312+11	.9787910-01
039	·4077707+01	.4169126+01	. 3055530+11	.4382312+01	.9141870-01
040	·4175771+01	.4169126+01	. 39F5430+01	.4392312+01	6645300-02

TABLE 8-4. OUTPUT FROM STRAP FOR R VS AP PLOTS OF FIG. 5 FOR ALKYD FILM

NO. OF IND. VARIABLES 01 DEPENDENT VARIABLE NO. 01 NO. OF OBSERVATIONS 020

TOLERANCE LEVEL .100000-03

STEP NO.	ENTERING VAR.	ERROR OF EST.	F TO ENTER	F VALUE
01	01	•3738567+02	•1000000-01	• 5977770+03
	VARIABLE NO. 01	COFFFICIENT •7283407+02	ERPOR OF COFF. .2978962+01	

R SQUARE = .9691947+00

STUDENTS T = .2093000+01

NO.	OBSERVED	FITTED	CONFIDENCE	LIMITS	RESIDUAL
001	.7609000+02	.1456681+03	•6643253+02	·2249038+03	.6957814+02
002	.1028100+03	.1456681+03	.6643253+02	.2249038+03	4285814+02
003	.1130800+03	.1456681+03	.6643253+02	.2249038+03	.1258814+02
004	.1218300+03	.1456681+03	.6643253+02	.2249038+03	.2383814+02
005	.1212500+03	.1456681+03	.6643253+02	.2249038+03	.2441814+02
006	.1250400+03	.1820852+03	.1022995+03	·2618708+03	.5704517+02
007	.1762900+03	1820852+03	1022995+03	·2618708+03	.5795170+01
008	.1832400+03	1820852+03	1022995+03	·2618708+03	1154830+01
009	.1737100+03	.1820852+03	1022995+03	·2618708+03	8375170+01
010	1741100+03	.1820852+03	.1022995+03	.2618708+03	.7975170+01
011	.1733900+03	.2185022+03	.1380494+03	.2989550+03	.4511221+02
012	.2163600+03	.2185022+03	.1380494+03	·2989550+03	2142210+01
013	.2117300+03	.2185022+03	•1380494+03	.2989556+93	·6772710·01
014	.2056500+03	.2185022+03	•1380494+03	·2989550+03	12P5221+02
015	.2134700+03	.2185022+03	.1380494+03	.2989550+13	.5 32211+01
016	.2936600+03	.2549192+03	.1736850+03	· 3361535+12	3874076+02
017	.3077500+03	.2549192+03	•1736850+03	• 3361535+03	5283076+02
018	.3027600+03	.2549192+03	1736850+03	3361535+03	4784076+02
019	.2720700+03	.2549192+03	•1736850+03	· 3361535+03	1715076+02
020	.3261800+03	.2549192+03	.1736850+03	·3361535+03	7126076+02

.

TABLE 8-5. OUTPUT FROM STRAP FOR R VS AP PLTS OF FIG. 5 FOR EPOXY FILM

.

NO. OF IND. VARIABLES 01 DEPENDENT VARIABLE NO. 01 NO. OF OBSERVATIONS 015

TOLERANCE LEVEL .1000000-03

NO.	ENTERING VAR. 01	ERROR OF EST. •1155265+02	F TO ENTER +1000000-01	F VALUE • 5019579+03
	VARIABLE NO.	COEFFICIENT	ERROR OF COFF.	
	C1	.2149469+02	•9593951+00	

R SQUARE = .9728661+00

STUDENTS T = .2145000+01

NO.	OBSERVED	FITTED	CONFIDENCE	LIMITS	RESIDUAL
001	.4099000+02	.4298938+02	.1786948+02	+6810928+02	·1999378+01
002	.3760000+02	.4298938+02	.1786948+02	·6810928+02	.5389378+01
003	.3315000+02	.4298938+02	.1786948+02	.6810928+02	.9839378+01
004	.3507000+02	.4298938+02	.1786948+02	.6810928+02	.7919378+01
005	.3266000+02	.4298938+02	.1786948+02	·6810928+02	+1032938+02
006	.6143000+02	.6448407+02	.3894617+02	.9002197+02	.3054167+01
007	•6090000+02	.6448407+02	.3894617+02	+9002197+02	.3584067+01
008	•5611000+02	.6448407+02	.3894617+02	.9002197+02	.8374067+01
009	.5088000+02	.6448407+02	.3894617+02	.9002197+02	.1360407+02
010	•4777000+02	.6448407+02	.3894617+92	.9002197+02	.1671407+02
011	.9037000+02	.8597876+02	.5986690+02	.1120906+03	4391244+01
012	.9300000+02	.8597876+02	.5986691+02	·1120906+03	7021244+01
013	1126100+03	.8597876+02	.5986690+02	.1120906+03	2663125+02
014	.8443000+02	.8597876+02	.5986690+02	.1120906+03	.1548756+01
015	1012200+03	.8597876+02	•5986690+02	1120906+03	1524125+02

REFERENCES

1. H. H. Uhlig. The Corrosion Handbook, New York, John Wiley & Sons, Inc., 1948.

2. W. Fischer. Organic Protective Coatings, New York, Reinhold Publishing Co., 1953.

3. F. W. Shanks. Corrosion and Its Prevention, Paint Technology, Vol. 38, No. 497, 1966, pp. 351-6.

4. E. E. McSweeney. Water and Metal, Official Digest, Vol. 37, No. 485, June 1965, pp. 670-82.

5. F. LaQue. Corrosion Resistance of Metal and Alloy, 2nd Ed., ACS Monograph Series, New York, Reinhold Publishing Co., 1963, pp. 83-157.

6. R. M. Barrer. Diffusion in and Through Solid, Cambridge, Cambridge University Press, 1951.

7. A. C. Elm. Paints as Moisture Barriers, Official Digest, Vol. 19, No. 267, 1947, pp. 197-228.

8. C. A. Kumins and J. Roteman. Diffusion of Gas and Vapor Through Unpigmented Vinyl Films, Official Digest, Vol. 34, No. 445, February 1962, pp. 177-193.

9. A. S. Michaels. Water and the Barrier Film, Official Digest, Vol. 37, No. 485, June 1965, pp. 638-53.

10. P. W. T. Willmott and F. W. Billmeyer. Solubility and Diffusion of Water Vapor in Aliphatic Polyesters, Official Digest, Vol. 35, No. 464, September 1963, pp. 847-56.

11. H. G. Spencer. Effect of Chemical Composition on the Diffusion and Permeability of Water Vapor in Polymer Films, Official Digest, Vol. 37, No. 486, July 1965, pp. 757-65.

12. Fundamental of Permaselective Membrane Technology, General Electric, Burlington, 1964, pp. 1-14.

13. P. M. Doty and others. Water Vapor Permeability of Organic Film, Industrial and Engineering Chemistry, Vol. 16, No. 11, November 1944, pp. 689-90.

14. M. Pobereskin. Permeability Test for Organic Sheet Material. Battelle Memorial Institute, Columbus, Paper presented to Western Region Conference, NACE, 1966. 15. R. E. Murdock. Permeation of Paint Film by Environmental Agents, Shell Chemical Co., New Jersey, Paper presented to Western Region Conference, NACE, 1966.

16. A. L. Glass and others. A Radiochemical Investigation into the Diffusion of Ions Through Protective Film, Journal of Paint Technology, Vol. 38, No. 495, April 1966, pp. 203-9.

17. A. L. Glass and others. A Radiochemical Investigation of the Effect of Pigment on the Diffusion of Ions Through Protective Films, Journal of Paint Technology, Vol. 39, No. 511, August 1967, pp. 203-10.

18. J. H. Deterding and others. Determination of the Water Permeability of Epoxy Coating Film by a Radioactive Tracer Technique, International Congress of Marine Corrosion, Paris, 1964, pp. 275-83.

19. U. S. Naval Civil Engineering Laboratory Technical Report R-568: Measurement of Airfield Marking Paint Flexibility by E. S. Matsui and R. W. Drisko, Port Hueneme, Calif., March 1968.

20. E. T. Buch. General Applicability of the Channel Method of Measuring Liquid Scintillation Counting Efficiency, Analytical Chemistry, Vol. 35, pp. 1024-9, 1963.

21. Federal Specification IT-R-266, Type II, Resin, Alkyd Solution, September 1967.

22. S. B. Tuwiner. Diffusion and Membrane Technology. ACS Monograph Series, New York, Reinhold Publishing Co., 1962, pp. 215-36.

23. S. Glasstone. Text Book of Physical Chemistry, 2nd Ed., New York, D. VanNostrand Co., 1948, pp. 696-7.

UNCLASSIFIED

.

Security classification of Hilo, body of abstract and ind	exing annotation must be	a. U Intered when the	overall report in classified)
OHIGINA TING ACTIVITY (Corporate author)	<u> </u>	28. REPORTS	ECURITY CLASSIFICATION
Naval Civil Engineering Laboratory		Ur	nclassified
Port Hueneme, California		2h GROUP	
		1	
Water Vapor Diffusion Through Protectiv	ve Coatings. Pa	rt I. AN	Method of Measuring
Water Vapor Permeability of Coating Fil	lms by Radioisot	ope Tracei	r Technique and
Its Application			
A DESCRIPTIVE NOTES (Type of report and inclusive dates)	<u></u>		
Interim	March 1966	- April 19	068
5 AUTHOR(\$) (First name, middle initial, last name)			
E. S. Matsui			
REPORT DATE	78. TOTIL NO O	FPAGES	76. NO OF REFS
October 1968	40		23
B CONTRACT OR GRANT NO	SE ORIGINATOR	S REPORT NUM	HER(\$)
7 0011 01 01 027			
b. PROJECT NO 2-KUIL-UI-UI-UO/	TN-992		
		DT NO(51 (Any a	the number that may be and that
· .	this report)	HT NOISI (ANY D	nner numbers (nat may be assigned
d.			
0 DISTRIBUTION STATEMENT			
Each transmittal of this document outsi	de the agencies	of the U.	S. Government must
have prior approval of the U.S. Naval	Civil Engineeri	ng Laborat	tory.
IT SUPPLEMENTARY NOTES	12 SPONSORING	MILITARY ACT	
	Director	of Navy L	aboratories
3 ABSTRACT			
A method of measuring the permeabi	lity constant a	nd the dif	fusion rate of
water vapor through a polymer film by t	the radiochemica	l method i	s elaborated.
It demonstrates that the radiochemical	method, as comp	ared to th	e ASTM Standard
Method, is precise, sensitive and rapid	. The radioche	mical meth	or is also useful
in the investigation of other parameter	s which influen	ce permeab	ility of water
vapor.			
D FORM 1472 (PAGE 1)			
U INOV 45 14/3 ATAGE T	UI	WCLASSIFIE	D
N 0101-807-6801		Securit	n Changel and

CLASSIFIFD

Productive contings Noter vour Note vour	a la constante de la constante	1.174	• 4		н (1	194	р (й)
Proceedings With yours Proming Proceedings Proceeding		14 m	h. 1	6. j	<u>^'</u>	Sec. F	6.1
Witer word Distribution Presentitie	Protective continue						
	h for voue						
Presential (1): Press Proved Harra Image: Proved Harra	Distosion			ĺ	1		
Dr ^{row} 1473 Hat)	`! e isuring				l.		1
	Permati i lit				1		
	p = 1 = 20 ts						
	. chochemistr.						
					1		
					10		
					le internet		
			1				
			1				
						1	
						ļ	
			1				
DD FORM 1473 (BALK)							
	DD FORM 1473 (RALK)	×, 11 × 14.					

•

 $(1 - \Lambda - 1) = (1 - 1)$

.

١

Security Classification

SUPPLEMENTARY

INFORMATION

DEFENSE DOCUMENTATION CENTER NOTICES OF CHANGES IN CLASSIFICATION, DISTRIBUTION AND AVAILABILITY

69-21	· · ·	1. November 1967			
IDENTIFICATION	FORHER STATEMENT	NEW STATEMENT	AUTHORITY		
AD-843 7391 Naval Civil Engineering Lab., Port Hueneme, Calif. Technical nctc. Rept. no. NTEL-TR- 992 Oct C8	USGO: others to Commander, Naval Civil Engineering Lab., Port Hueneme, Calif.	No limitation	USNCEL ltr, 10 Mar 69		

r¶.