| REPORT DOCUMENTATION PAGE  |                    |                            | Form Approved OMB NO. 0704-0188 |   |                                       |  |  |
|--|--------------------|----------------------------|---------------------------------|---|---------------------------------------|--|--|
| The public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggesstions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington VA, 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to any oenalty for failing to comply with a collection of information if it does not display a currently valid OMB control number. PLEASE DO NOT RETURN YOUR FORM TO THE ABOVE ADDRESS. |                    |                            |                                 |   |                                       |  |  |
| 1. REPORT DATE (DD-MM-Y  | YYY)               | 2. REPORT TYPE             |                                 |   | 3. DATES COVERED (From - To)          |  |  |
| 28-07-2016   | ,                  | Final Report               |                                 |   | 1-May-2013 - 30-Apr-2016              |  |  |
| 4. TITLE AND SUBTITLE  |                    |                            |                                 | 5a. CON                                     | 5a. CONTRACT NUMBER                   |  |  |
| Final Report: Controlling the Efficiency of Semiconductor-TiO2   |                    |                            | W911N                           | W911NF-13-1-0101                            |                                       |  |  |
| for Sunlight-driven Technologies for Military Needs  |                    |                            | 5b. GRA                         | 5b. GRANT NUMBER                            |                                       |  |  |
|  |                    |                            |                                 | 5c. PRO                                     | 5c. PROGRAM ELEMENT NUMBER            |  |  |
|  |                    |                            |                                 | 611102                                      | 611102                                |  |  |
| 6. AUTHORS   |                    |                            |                                 | 5d. PRO                                     | 5d. PROJECT NUMBER                    |  |  |
| Ian Harrison   |                    |                            |                                 |   |                                       |  |  |
|  |                    |                            | 5e. TASI                        | 5e. TASK NUMBER                             |                                       |  |  |
|  |                    |                            |                                 | 5f. WOR                                     | K UNIT NUMBER                         |  |  |
| 7. PERFORMING ORGANIZATION NAMES AND ADDRESSES       8. PERFORMING ORGANIZATION RE         University of Virginia       NUMBER         1001 North Emmet Street       NUMBER         P. O. Box 400195       Herric Market and Comparison of the street  |                    |                            |                                 | 3. PERFORMING ORGANIZATION REPORT<br>NUMBER |                                       |  |  |
| 9 SPONSORING/MONITOR   | ZZ90<br>ING AGENCV | 4 -4195<br>MAME(S) AND ADI | DEESS                           | 1   | 0 SPONSOR/MONITOR'S ACRONYM(S)        |  |  |
| (ES)   |                    |                            | 1                               | ARO   |                                       |  |  |
| U.S. Army Research Office<br>P.O. Box 12211  |                    |                            | 1<br>N                          | 11. SPONSOR/MONITOR'S REPORT<br>NUMBER(S)   |                                       |  |  |
| Research Triangle Park, NC 27709-2211  |                    |                            | 6                               | 62064-CH.11                                 |                                       |  |  |
| 12. DISTRIBUTION AVAILIE   | BILITY STATE       | EMENT                      |                                 |   |                                       |  |  |
| Approved for Public Release; D   | istribution Unli   | mited                      |                                 |   |                                       |  |  |
| 13. SUPPLEMENTARY NOTES<br>The views, opinions and/or findings contained in this report are those of the author(s) and should not contrued as an official Department<br>of the Army position, policy or decision, unless so designated by other documentation.   |                    |                            |                                 |   |                                       |  |  |
| 14. ABSTRACT<br>How surface chemistry can modify the electronic properties of metal oxide semiconductor nanomaterials relevant<br>to improving sunlight driven military technologies was investigated. Photoluminescence was used to probe the<br>surface band-bending of TiO2 nanoparticles to help identify properties that can control the flow of charge to the<br>semiconductor surface. First, the effects of oxygen exposure on band-bending induced by both healing defects at<br>the surface and molecular chemisorption were studied. Second, probing the band-bending of the TiO2 surface under<br>the influence of gases with different electron eccentring and denoting strengths revealed that head heading at the   |                    |                            |                                 |   |                                       |  |  |
| 15. SUBJECT TERMS<br>Photoluminescence, photochemistry, photovoltaic cels, titanium dioxide, zinc oxide, carbon nanotubes  |                    |                            |                                 |   |                                       |  |  |
| 16. SECURITY CLASSIFICAT   | FION OF:           | 17. LIMITATION<br>ABSTRACT | OF 1                            | 5. NUMBEI<br>DF PAGES                       | R 19a. NAME OF RESPONSIBLE PERSON     |  |  |
| UU UU UU   | JU                 | UU                         |                                 |   | 19b. TELEPHONE NUMBER<br>434-924-3639 |  |  |

I

٦

#### **Report Title**

Final Report: Controlling the Efficiency of Semiconductor-TiO2 for Sunlight-driven Technologies for Military Needs

#### ABSTRACT

How surface chemistry can modify the electronic properties of metal oxide semiconductor nanomaterials relevant to improving sunlight driven military technologies was investigated. Photoluminescence was used to probe the surface band-bending of TiO2 nanoparticles to help identify properties that can control the flow of charge to the semiconductor surface. First, the effects of oxygen exposure on band-bending induced by both healing defects at the surface and molecular chemisorption were studied. Second, probing the band-bending of the TiO2 surface under the influence of gases with different electron accepting and donating strengths revealed that band-bending at the surface modulates electron trapping into gold nanoparticles at the surface, when present. Electron donation from the TiO2 surface to gold particles has been shown to be critical in the reactivity of Au/TiO2 nanoparticle catalysts and our ability to measure band-bending. Third, the electron mobility changes in TiO2 nanopowder decorated with conductive carbon nanotubes concluded fruitful studies on the effect of surface conductors on charge recombination. Finally, the role that free carriers and neutral donors play in producing visible emission from ZnO nanoparticles was more fully elucidated.

# Enter List of papers submitted or published that acknowledge ARO support from the start of the project to the date of this printing. List the papers, including journal references, in the following categories:

(a) Papers published in peer-reviewed journals (N/A for none)

| Received   |      | Paper  |
|------------|------|--|
| 08/18/2014 | 1.00 | Ana Stevanovic, John T. Yates. Electron Hopping through TiO2 Powder: A Study by Photoluminescence Spectroscopy,<br>The Journal of Physical Chemistry C, (11 2013): 0. doi: 10.1021/jp407765r   |
| 08/18/2014 | 2.00 | Shiliang Ma, Ana Stevanovic, John T. Yates. Effect of Gold Nanoparticles on Photoexcited Charge Carriers in Powdered TiO2-Long Range Quenching of Photoluminescence, The Journal of Physical Chemistry C, (08 2014): 0. doi: 10.1021/jp507156p   |
| 08/18/2014 | 3.00 | Zhen Zhang, John T. Yates. Band Bending in Semiconductors: Chemical and Physical Consequences at Surfaces and Interfaces, Chemical Reviews, (10 2012): 0. doi: 10.1021/cr3000626   |
| 08/18/2014 | 4.00 | John T. Yates. Electron stimulated desorption, DIET, and photochemistry at surfaces: A personal recollection,<br>The Journal of Chemical Physics, (09 2012): 0. doi: 10.1063/1.4746798   |
| 08/18/2014 | 5.00 | Petro Maksymovych, Dan C. Sorescu, Oleksandr Voznyy, John T. Yates. Hybridization of Phenylthiolate-<br>and Methylthiolate-Adatom Species at Low Coverage on the Au(111) Surface,<br>Journal of the American Chemical Society, (04 2013): 0. doi: 10.1021/ja4000905  |
| 08/26/2015 | 8.00 | Ana Stevanovic, Shiliang Ma, John T. Yates. Photoexcited Electron Hopping between TiO2 Particles-<br>Effect of Single-Walled Carbon Nanotubes,<br>The Journal of Physical Chemistry C, (10 2014): 23614. doi: 10.1021/jp508061w  |
| 08/26/2015 | 9.00 | Monica McEntee, Ana Stevanovic, Wenjie Tang, Matthew Neurock, John T. Yates. Electric Field Changes<br>on Au Nanoparticles on Semiconductor Supports – The Molecular Voltmeter and Other Methods to<br>Observe Adsorbate-Induced Charge-Transfer Effects in Au/TiO,<br>Journal of the American Chemical Society, (02 2015): 1972. doi: 10.1021/ja511982n |
| TOTAL:     |      | 7  |

Number of Papers published in peer-reviewed journals:

(b) Papers published in non-peer-reviewed journals (N/A for none)

**Received** 

Paper

TOTAL:

#### (c) Presentations

Number of Presentations: 0.00

Non Peer-Reviewed Conference Proceeding publications (other than abstracts):

Received Paper

TOTAL:

Number of Non Peer-Reviewed Conference Proceeding publications (other than abstracts):

# 

Received

Paper

TOTAL:

FTE Equivalent:

|                         |              | Books                                       |  |
|-------------------------|--------------|---|--|
| Received                | Book         |   |  |
| TOTAL:                  |              |   |  |
| <u>Received</u>         | Book Chapter |   |  |
| TOTAL:                  |              |   |  |
|                         |              | Patents Submitted                           |  |
|                         |              | Patents Awarded                             |  |
|                         |              | Awards                                      |  |
|                         |              | Graduate Students                           |  |
| <u>NAME</u><br>Shiliang | Ма           | <u>PERCENT_SUPPORTED</u> Discipline<br>1.00 |  |

| Total Number:   | 1                        |  |
|-----------------|--------------------------|--|
|                 | Names of Post Doctorates |  |
| NAME            | PERCENT_SUPPORTED        |  |
| Matthew Reish   | 1.00                     |  |
| FTE Equivalent: | 1.00                     |  |
| Total Number:   | 1                        |  |

1.00

| <u>NAME</u><br>lan Harrison<br>FTE Equivalent:<br>Total Number:   | PERCENT_SUPPORTED<br>0.09<br>0.09<br>1 | National Academy Member                           |  |  |
|---|--|---|--|--|
| Names of Under Graduate students supported  |  |   |  |  |
| NAME  | PERCENT_SUPPORTED                      |   |  |  |
| FTE Equivalent:<br>Total Number:  |  |   |  |  |
| Student Metrics<br>This section only applies to graduating undergraduates supported by this agreement in this reporting period  |  |   |  |  |
| The number of undergraduates funded by this agreement who graduated during this period: 0.00<br>The number of undergraduates funded by this agreement who graduated during this period with a degree in |  |   |  |  |
| The number of undergraduates  | science, math                          | hematics, engineering, or technology fields: 0.00 |  |  |
| the number of undergraduates  | runded by your agreement who gra       | duated during this period and will continue       |  |  |

Names of Faculty Supported

to pursue a graduate or Ph.D. degree in science, mathematics, engineering, or technology fields:..... 0.00

Number of graduating undergraduates who achieved a 3.5 GPA to 4.0 (4.0 max scale):..... 0.00

Number of graduating undergraduates funded by a DoD funded Center of Excellence grant for

Education, Research and Engineering:..... 0.00

The number of undergraduates funded by your agreement who graduated during this period and intend to work for the Department of Defense ...... 0.00

The number of undergraduates funded by your agreement who graduated during this period and will receive scholarships or fellowships for further studies in science, mathematics, engineering or technology fields: ..... 0.00

#### Names of Personnel receiving masters degrees

NAME

**Total Number:** 

## Names of personnel receiving PHDs

NAME

**Total Number:** 

## Names of other research staff

 NAME
 PERCENT\_SUPPORTED

 FTE Equivalent:
 Contraction

 Total Number:
 Contraction

Sub Contractors (DD882)

Inventions (DD882)

See Attachment

Scientific Progress

**Technology Transfer** 

# Final Report: Controlling the Efficiency of Semiconductor-TiO<sub>2</sub> for Sunlight-driven Technologies for Military Needs

#### July 2016

#### I. Foreword

During this support period we have further expanded on the theory and techniques developed previously. New instrumentation designed and built during this period further expanded the unique capabilities available in our lab. Also during this period ARO supported PhD student Ana Stevanovic graduated and found employment at the National Institute of Standards and Technology (NIST). ARO supported postdoc Matthew Reish will also move on to another Army supported position at AMRDEC, bringing surface science experience learned under this ARO project to a new project.

Sadly, during this period the project's PI, John T. Yates Jr., became ill and passed away. During an extraordinary research career Professor Yates accomplished more than can be listed here, placing him into the upper echelons of scientific accomplishment. He also inspired all those he mentored with his passion for understanding difficult scientific problems with careful experimentation and clear communication. His long and fruitful support from ARO led to many important results that will continue to further the ARO mission and make a lasting positive impact on this world.

#### II. Statement of Problems Studied

Band bending at a semiconductor surface is an important driver for making free charges available at the surface. Controlling the sign and magnitude of this band bending determines the type (hole or electron) and concentration of the charges at the surface.<sup>1</sup> These surface charges can then be used to perform oxidation or reduction reactions on surface adsorbates. These reactions have a wide range of practical applications including photoelectrochemical cells, photochemical decomposition of unwanted chemicals, and energy storage.

Under previous ARO support our group has developed the ability to use photoluminescence (PL) intensity from TiO<sub>2</sub> nanoparticles to detect the relative band bending at the TiO<sub>2</sub> surface and measure the interparticle hopping rate.<sup>2,3</sup> Over this support period we used this technique to study the effect of interparticle linkers which have been hypothesized to increase the hopping rate between particles. The two linkers studied were gold nanoparticles and single walled carbon nanotubes.

Additional applications of the ability to measure both PL intensity and IR absorbance in the study of metal oxide electronics under high vacuum and applications of the developed theories were also discovered. The use of simultaneous PL and IR spectroscopies in the study of visible emission in annealed zinc oxide have revealed a wealth of information about the mechanism of emission. Continuation of this work will focus on enhancement of the PL using the insights gained into the mechanism of the visible PL with the goal of generating low-cost and non-toxic visible phosphors of interest in lighting applications.

#### III. Summary of Important Results

# a. Effect of Gold Nanoparticles on Photoexcited Charge Carriers in Powdered TiO2–Long Range Quenching of Photoluminescence

TiO<sub>2</sub> particles were decorated with a low coverage of gold nanoparticles with intent of enhancing the interparticle charge hopping rate which can be measured by the decrease in PL over time after gold/TiO<sub>2</sub> UV exposure is halted.<sup>2,4</sup> However we found that in gold/TiO<sub>2</sub> there is a complete quenching of the TiO<sub>2</sub> defect luminescence. Figure 1 shows the development of PL over time in both neat (red) and covered with gold TiO<sub>2</sub> nanoparticles (black).



**Figure 1.** Integrated PL intensity during UV exposure of TiO<sub>2</sub> (red) and Gold/TiO<sub>2</sub> (black).

In this case resonance energy exchange between the gold plasmon and the TiO<sub>2</sub> emission can be ruled out because of the lack of plasmonic absorption in the gold/TiO<sub>2</sub> sample.<sup>5</sup> Photoluminescence quenching occurs as a result of photoexcited electron transfer from TiO<sub>2</sub> to gold nanoparticles. However, the continuous quenching of PL suggests that the electron transferred into Au must recombine with a hole in TiO<sub>2</sub> across the interface. The short-circuit with photoexcited electrons transfering to Au and electron hole recombination across the Au/TiO<sub>2</sub> interface causes the continuous quenching of PL, as shown in Figure 2.



**Figure 2.** Schematic of the short-circuit which quenches TiO<sub>2</sub> photoluminescence when the gold nanoparticles are deposited on the surface.

By identifying the surface coverage of gold we can also determine the minimum trap distance of the gold particles to completely withdraw photoexcited electrons from TiO<sub>2</sub>. Our calculation shows that Au nanoparticles can withdraw electrons from at least 4 nm beyond the Au nanoparticle boundary. This shows that gold particles on the TiO<sub>2</sub> surface have a relatively long range interaction with excited electrons and even at low coverages gold particles can effectively trap electrons and separate them from holes.

**Peer Reviewed Report of these Results:** Stevanovic, A., Ma, S. and Yates Jr, J.T., 2014. Effect of Gold Nanoparticles on Photoexcited Charge Carriers in Powdered TiO<sub>2</sub>– Long Range Quenching of Photoluminescence. *The Journal of Physical Chemistry C*, *118*(36), pp.21275-21280.

# b. Photoexcited Electron Hopping between TiO<sub>2</sub> Particles: Effect of Single-Walled Carbon Nanotubes

One design challenge in TiO<sub>2</sub> photovoltaics is the low mobility rate of charges though nanopowders which can hamper device performance.<sup>6</sup> We proposed to create interconnections between TiO<sub>2</sub> by the addition of conducting single walled carbon nanotubes (SWNTs) to the TiO<sub>2</sub> surface. The mobility of electrons in SWNT is ~10<sup>8</sup> m<sup>2</sup> V<sup>-1</sup> s<sup>-1</sup>, and this high conductivity makes SWNTs a likely candidate for increasing charge hopping rates.<sup>7</sup> In this study we mixed samples with 1, 3, and 5% carbon nanotubes by weight with P25 TiO<sub>2</sub> with an SEM micrograph of the 5% sample shown in figure 3.





When measuring the charging and discharging of PL intensity under UV exposure we found two important factors which describe the charge hopping process in the SWNT/TiO<sub>2</sub> composites. First, SWNTs exhibit electron accepting behavior as the PL intensity of SWNT/TiO<sub>2</sub> composites systematically decreases with increase of the fraction of SWNTs mixed into the TiO<sub>2</sub> powder. The fractional decrease in PL intensity is proportional to the average number of SWNT/TiO<sub>2</sub> contact points in the first-layer of TiO<sub>2</sub>. Second, the PL charging/discharging rate of all SWNT/TiO<sub>2</sub> mixtures is identical to that of pure TiO<sub>2</sub> (Figure 4), indicating that SWNTs only accept photoexcited electron from TiO<sub>2</sub> but do not transport electrons under conditions of the experiment. This is due to the effect of positively charged TiO<sub>2</sub> particles due to charge separation (i.e. electron injection into SWNTs) which immobilize the photoexcited electrons transferred to SWNTs at the interface between first-layer TiO<sub>2</sub> and SWNTs, inhibiting charge transport through SWNT channels.



**Figure 4.** Charging and discharging curves neat of SWNT intercalated TiO<sub>2</sub> nanoparticles. While the final PL intensity of different coverages varies the charging and discharging rates are the same within error.

**Peer Reviewed Report of these Results:** Stevanovic, A., Ma, S. and Yates Jr, J.T., 2014. Photoexcited Electron Hopping between TiO<sub>2</sub> Particles: Effect of Single-Walled Carbon Nanotubes. *The Journal of Physical Chemistry C*, *118*(41), pp.23614-23620.

# c. Band Bending at the Surface Affects the Potential and of Electrons in Gold Deposited on TiO<sub>2</sub>

Gold/TiO<sub>2</sub> is also an important substrate material for several important catalytic reaction including water-gas shift and CO oxidation.<sup>8</sup> The activity of the catalyst has been shown to be highly dependent on the charge state of the gold particles which is in turn influenced by band bending of the TiO<sub>2</sub> supports as shown in Figure 5.<sup>5</sup>



**Figure 5.** The band bending effect of adsorbed molecules on TiO<sub>2</sub> influence the charge state and electron potential of gold deposited on TiO<sub>2</sub>.

Recent work in our group has used CO as a reporter for the charge state of gold and we have found that the reversible adsorption of donor or acceptor molecules shifts the vibrational frequency of the adsorbed CO molecules in opposite directions.<sup>9</sup> The determination of band bending by the PL method on nano gold TiO<sub>2</sub> with same donor (alkane) and acceptor (sulfur hexafluoride) molecules was also performed to show that band bending at the TiO<sub>2</sub> surface could be used to explain the change in gold charge. The results of this study for propane and sulfur hexafluoride are shown in Figure 6. The adsorption of the donor molecule, propane, decreases the band bending as indicated by the increase in PL while for the acceptor molecule, sulfur hexafluoride, the opposite effect is noted.



Figure 6. Opposite effects of van der Waals bound donor-C<sub>3</sub>H<sub>8</sub> and acceptor-SF<sub>6</sub> molecules on the magnitude of PL intensity. (a) The results indicate that donor-C<sub>3</sub>H<sub>8</sub> molecules reduce upward band bending in n-type TiO<sub>2</sub>, causing an increase in PL intensity. (b) Conversely, acceptor-SF<sub>6</sub> molecules enhance upward band bending in n-type TiO<sub>2</sub>, causing a decrease in PL intensity.

**Peer Reviewed Report of these Results:** McEntee, M., Stevanovic, A., Tang, W., Neurock, M. and Yates Jr, J.T., 2015. Electric Field Changes on Au Nanoparticles on Semiconductor Supports–the Molecular Voltmeter and Other Methods to Observe Adsorbate-Induced Charge-Transfer Effects in Au/Tio2 Nanocatalysts. *Journal of the American Chemical Society*, *137*(5), pp.1972-1982.

#### d. The Effect of Free Charges on PL Intensity in ZnO

The development of PL and IR spectroscopy for the application to polar metal oxide electronics also helped clarify the role of free charges in the defect emission of zinc oxide. It is well known that high temperature annealing of zinc oxide can create intrinsic defects which act as recombination centers and generate highly efficient visible emission. However details of the emission mechanism in annealed zinc oxide are not well understood.<sup>10</sup>

IR spectroscopy of polar metal oxides can be used to measure the concentration of high-mobility free or polaronic electrons generated by intrinsic defects by the drude metallization of the oxide with leads to low frequency IR absorption with a characteristic power-law band shape. Much of the pioneering work on TiO<sub>2</sub> defect electron detection by IR was completed in the Yates lab and this technique gives us a unique tool for understanding the relation between intrinsic defects and PL.<sup>11</sup> Simultaneous transmission IR absorption and PL during stepwise annealing revealed that free electron concentration rises in ZnO at annealing temperature below 1000 K indicating oxygen loss.<sup>12</sup> However this free electron increase is not accompanied by a rise in PL intensity. At annealing temperatures above 1000 K the free electron concentration begins to fall with an inverse rise in the PL as shown in Figure 7.



**Figure 7.** IR background absorption (black) and integrated PL intensity (blue) during stepwise annealing of ZnO nanoparticles. The IR background signal is proportional to the free electron concentration and has an inverse relationship with the PL intensity.

Exposure of the annealed samples to hole (methanol) and electron (O<sub>2</sub>) scavengers shows that free charges have an influence on PL intensity and free electron concentration in high temperature annealed ZnO. The top section of Figure 8 shows the change in the normalized PL in vacuum and then under different pressures of methanol (black) and O<sub>2</sub> (red) and the bottom shows the change in IR absorbance during the same experiment, which is which is proportional to the free electron concentration. Initially in vacuum there is a decrease in PL intensity but when exposed to hole scavenging methanol there is strong increase in PL intensity accompanying an increase in free electron concentration. Electron scavenging O<sub>2</sub> significantly decreases the electron concentration but has only a minor effect on PL efficiency. These results suggest that free holes quench PL intensity in annealed ZnO and the removal of hole buildup likely generates more efficient PL.



**Figure 8.** Top: Normalized integrated PL in vacuum and during exposure to labeled pressures of O<sub>2</sub> (red) and methanol (black). Bottom: Differential absorbance at 1760 cm<sup>-1</sup> during exposure to UV light and charge scavengers (same conditions as top)

Rather than band bending, which plays a dominant role in PL intensity changes in TiO<sub>2</sub>, we suggest that the buildup of holes in ZnO is effective at removing the excited intermediate that leads to PL, namely the donor bound

exciton. Neutral donor bound excitons, with no available ionized states, have previously been shown to be important intermediates for visible emission in ZnO and we therefore suggest that free holes act to effectively ionize donor bound excitons and therefore remove an efficient path for the creation of visible emitting states. The insights garnered from this work suggest that passivating the surface with a hole extracting layer may serve to enhance PL efficiency. Work on ZnO particles coated in a hole-extracting ZnS layer is underway.

**Peer Reviewed Report of these Results:** Reish, M.E., Zhang, Z., Ma, S., Harrison, I. and Everitt, H.O., 2016. How Annealing and Charge Scavengers Affect Visible Emission from ZnO Nanocrystals. *The Journal of Physical Chemistry C*, *120*(9), pp.5108-5113.

#### **References:**

- 1) Zhang, Z.; Yates, J. T. Band Bending in Semiconductors: Chemical and Physical Consequences at Surfaces and Interfaces. *Chem. Rev.* **2012**, *112*, 5520–5551.
- (2) Stevanovic, A.; Yates, J. T. Electron Hopping through TiO2 Powder: A Study by Photoluminescence Spectroscopy. *J. Phys. Chem. C* **2013**, *117*, 24189–24195.
- (3) Stevanovic, A.; Büttner, M.; Zhang, Z.; Yates, J. T. Photoluminescence of TiO2: Effect of UV Light and Adsorbed Molecules on Surface Band Structure. *J. Am. Chem. Soc.* 2012, 134, 324–332.
- (4) Stevanovic, A.; Ma, S.; Yates, J. T. Effect of Gold Nanoparticles on Photoexcited Charge Carriers in Powdered TiO2-Long Range Quenching of Photoluminescence. *J. Phys. Chem. C* **2014**, just accepted manuscript.
- (5) Subramanian, V.; Wolf, E. E.; Kamat, P. V. Catalysis with TiO2/Gold Nanocomposites. Effect of Metal Particle Size on the Fermi Level Equilibration. *J. Am. Chem. Soc.* **2004**, *126*, 4943–4950.
- (6) Grätzel, M. Dye-Sensitized Solid-State Heterojunction Solar Cells. *MRS Bull.* 2005, 30, 23–27.
- (7) Dresselhaus, M. S.; Dresselhaus, G.; Saito, R. NanotubesPhysics of Carbon Nanotubes. *Carbon N. Y.* **1995**, *33*, 883–891.
- (8) Green, I. X.; Tang, W.; Neurock, M.; Yates, J. T. Spectroscopic Observation of Dual Catalytic Sites During Oxidation of CO on a Au/TiO2 Catalyst. *Sci.* 2011, 333, 736–739.
- (9) McEntee, M.; Stevanovic, A.; Tang, W.; Neurock, M.; Yates, J. T. Electric Field

Changes on Au Nanoparticles on Semiconductor Supports – The Molecular Voltmeter and Other Methods to Observe Adsorbate-Induced Charge-Transfer Effects in Au/TiO2 Nanocatalysts. *J. Am. Chem. Soc.* **2015**, *137*, 1972–1982.

- (10) Özgür, Ü.; Alivov, Y. I.; Liu, C.; Teke, A.; Reshchikov, M. A.; Doğan, S.; Avrutin, V.; Cho, S. J.; Morko, H. A Comprehensive Review of ZnO Materials and Devices. *J. Appl. Phys.* **2005**, *98*, 1–103.
- Berger, T.; Sterrer, M.; Diwald, O.; Knözinger, E.; Panayotov, D.; Thompson, T.
   L.; Yates, J. T. Light-Induced Charge Separation in Anatase TiO2 Particles. *J. Phys. Chem. B* 2005, *109*, 6061–6068.
- (12) Reish, M. E.; Zhang, Z.; Ma, S.; Harrison, I.; Everitt, H. O. How Annealing and Charge Scavengers Affect Visible Emission from ZnO Nanocrystals. *J. Phys. Chem.* C 2016, 120, 5108–5113.