

U.S. DEPARTMENT OF COMMERCE
National Technical Information Service

AD-A024 609

DESIGN MECHANICAL PROPERTIES, FRACTURE TOUGHNESS,
FATIGUE PROPERTIES, EXFOLIATION AND STRESS-CORROSION
RESISTANCE OF 7050 SHEET, PLATE, HAND FORGINGS, DIE
FORGINGS AND EXTRUSIONS

ALUMINUM COMPANY OF AMERICA

PREPARED FOR
NAVAL AIR SYSTEMS COMMAND

JULY 1975

DISCLAIMER NOTICE

THIS DOCUMENT IS BEST QUALITY PRACTICABLE. THE COPY FURNISHED TO DTIC CONTAINED A SIGNIFICANT NUMBER OF PAGES WHICH DO NOT REPRODUCE LEGIBLY.

KEEP UP TO DATE

Between the time you ordered this report—which is only one of the hundreds of thousands in the NTIS information collection available to you—and the time you are reading this message, several new reports relevant to your interests probably have entered the collection.

Subscribe to the **Weekly Government Abstracts** series that will bring you summaries of new reports as soon as they are received by NTIS from the originators of the research. The WGA's are an NTIS weekly newsletter service covering the most recent research findings in 25 areas of industrial, technological, and sociological interest—invaluable information for executives and professionals who must keep up to date.

The executive and professional information service provided by NTIS in the **Weekly Government Abstracts** newsletters will give you thorough and comprehensive coverage of government-conducted or sponsored re-

search activities. And you'll get this important information within two weeks of the time it's released by originating agencies.

WGA newsletters are computer produced and electronically photocomposed to slash the time gap between the release of a report and its availability. You can learn about technical innovations immediately—and use them in the most meaningful and productive ways possible for your organization. Please request NTIS-PR-205/PCW for more information.

The weekly newsletter series will keep you current. But *learn what you have missed in the past* by ordering a computer NTISearch of all the research reports in your area of interest, dating as far back as 1964, if you wish. Please request NTIS-PR-186/PCN for more information.

WRITE: Managing Editor
5265 Port Royal Road
Springfield, VA 22161

Keep Up To Date With SRIM

SRIM (Selected Research in Microfiche) provides you with regular, automatic distribution of the complete texts of NTIS research reports *only* in the subject areas you select. SRIM covers almost all Government research reports by subject area and/or the originating Federal or local government agency. You may subscribe by any category or subcategory of our WGA (Weekly Government Abstracts) or Government Reports Announcements and Index categories, or to the reports issued by a particular agency such as the Department of Defense, Federal Energy Administration, or Environmental Protection Agency. Other options that will give you greater selectivity are available on request.

The cost of SRIM service is only 45¢ domestic (60¢ foreign) for each complete

microfiche report. Your SRIM service begins as soon as your order is received and processed and you will receive biweekly shipments thereafter. If you wish, your service will be backdated to furnish you microfiche of reports issued earlier.

Because of contractual arrangements with several Special Technology Groups, not all NTIS reports are distributed in the SRIM program. You will receive a notice in your microfiche shipments identifying the exceptionally priced reports not available through SRIM.

A deposit account with NTIS is required before this service can be initiated. If you have specific questions concerning this service, please call (703) 451-1558, or write NTIS, attention SRIM Product Manager.

This information product distributed by

NTIS

U.S. DEPARTMENT OF COMMERCE
National Technical Information Service
5265 Port Royal Road
Springfield, Virginia 22161

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER NO0019-72-C-0512	2. GOVT ACCESSION NO.	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) DESIGN MECHANICAL PROPERTIES, FRACTURE TOUGHNESS, FATIGUE PROPERTIES, EXFOLIATION AND STRESS-CORROSION RESISTANCE OF 7050 SHEET, PLATE, HAND FORGINGS, DIE FORGINGS AND EXTRUSIONS		5. TYPE OF REPORT & PERIOD COVERED FINAL
7. AUTHOR(s) R.E. DAVIES, G.E. NORDMARK AND J.D. WALSH		6. PERFORMING ORG. REPORT NUMBER
9. PERFORMING ORGANIZATION NAME AND ADDRESS ALUMINUM COMPANY OF AMERICA ALCOA LABORATORIES ALCOA CENTER, PA 15069		8. CONTRACT OR GRANT NUMBER(s) NO0019-72-C-0512
11. CONTROLLING OFFICE NAME AND ADDRESS Department of the Navy Naval Air Systems Command, AIR-52031 Washington, DC 20360		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)		12. REPORT DATE July 1975
		13. NUMBER OF PAGES 300
		15. SECURITY CLASS. (of this report) UNCLASSIFIED
		16a. DECLASSIFICATION/DOWNGRADING SCHEDULE
16. DISTRIBUTION STATEMENT (of this Report) Approved for Public Release; Distribution Unlimited		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		
18. SUPPLEMENTARY NOTES None		
PRICES SUBJECT TO CHANGE		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number)		
7050	Die Forgings	Bearing
Aluminum	Extruded Shapes	Modulus of Elasticity
Sheet	Tensile	Stress-Strain
Plate	Compressive	Fracture Toughness
Hand Forgings	Shear	Fatigue
		Crack Propagation
		Stress-Corrosion
		Exfoliation
20. ABSTRACT (Continue on reverse side if necessary and identify by block number)		
<p>The mechanical properties, including fracture toughness and fatigue, fatigue-crack growth rates and corrosion characteristics have been determined for a total of 51 lots of 7050-T76 sheet, 7050-T73651 plate, 7050-T73652 hand forgings, 7050-T736 die forgings and 7050-T76511 extruded shapes.</p> <p>Tables of computed design mechanical properties, modulus of elasticity values, and individual stress-strain curves are presented.</p> <p>The critical stress-intensity factor, K_{IC}, was determined for samples of each lot of sheet and the plane-strain stress intensity factor, K_{Ic}, was</p>		

DD FORM 1473

1 JAN 73

EDITION OF 1 NOV 68 IS OBSOLETE
S/N 0102-016-6601

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

determined for plate, hand and die forgings and extruded shapes. The combination of strength and toughness of all products are generally comparable to or higher than those of conventional 7XXX alloys.

Axial-stress fatigue strengths were determined in ambient-air and salt-fog environments. Modified Goodman diagrams were developed from tests made in ambient air.

Generally, equivalent rates of fatigue-crack propagation were obtained for plate, hand forgings and extruded shapes. Propagation occurred significantly faster in the longitudinal direction of thick hand forgings and extruded shapes.

All products showed a high resistance to exfoliation attack and were resistant to stress-corrosion cracking when stressed in the longitudinal and long-transverse directions; for the short-transverse direction, the various products and tempers showed good resistance to SCC in line with proposed targets. SCC performance of precracked specimens from plate, die forgings and extruded shapes showed trends similar to those obtained for smooth specimens.

ADDITION FOR	
WTH	White Section <input checked="" type="checkbox"/>
DOG	Ball Section <input type="checkbox"/>
UNANNOUNCED	<input type="checkbox"/>
JUSTIFICATION	
BY	
DISTRIBUTION/AVAILABILITY CODES	
Dist.	AVAIL. and/or SPECIAL
A	

SUMMARY

The mechanical properties, including fracture toughness and fatigue, fatigue-crack growth rates and corrosion characteristics have been determined for a total of 51 lots of 7050-T76 sheet, 7050-T73651 plate, 7050-T73652 hand forgings, 7050-T736 die forgings and 7050-T76511 extruded shapes.

Tables of computed design mechanical properties, modulus of elasticity values and individual stress-strain curves are presented.

The critical stress-intensity factor, K_{IC} , was determined for samples of each lot of sheet and the plane-strain stress-intensity factor, K_{IC} , was determined for plate, hand and die forgings and extruded shapes. The combination of strength and toughness of all products are generally comparable to or higher than those of conventional 7XXX alloys.

Axial-stress fatigue strengths were determined in ambient-air and salt-fog environments. Modified Goodman diagrams were developed from tests made in ambient air.

Generally, equivalent rates of fatigue-crack propagation were obtained for plate, hand forgings and extruded shapes. Propagation occurred significantly faster in the longitudinal direction of thick hand forgings and extruded shapes.

All products showed a high resistance to exfoliation attack and were resistant to stress-corrosion cracking when stressed in the longitudinal and long-transverse directions; for the short-transverse direction, the various products and tempers showed good resistance to SCC in line with proposed targets. SCC performance of precracked specimens from plate, die forgings and extruded shapes showed trends similar to those obtained for smooth specimens.

PREFACE

This investigation was conducted by Alcoa Laboratories, Aluminum Company of America, Alcoa Center, Pennsylvania, for the Department of the Navy, Naval Air Systems Command, Washington, D.C. under NASC Contract No. N00019-72-C-0512.

This report covers work done from May 12, 1972 to November 12, 1974.

This investigation was coordinated by Mr. J. G. Kaufman. The phase covering the design mechanical properties, fracture toughness and fatigue properties (ambient air) was under the supervision of Mr. D. J. Brownhill, with Mr. R. E. Davies as project engineer. The phase covering the fatigue properties (salt-fog) and fatigue-crack propagation rates was under the supervision of Mr. R. A. Kelsey, with Mr. G. E. Nordmark as project engineer. The phase covering the exfoliation and stress-corrosion characteristics was under the supervision of Mr. D. O. Sprowls, with Mr. J. D. Walsh as project leader.

TABLE OF CONTENTS

SECTION	PAGE
I. INTRODUCTION	23
II. MATERIALS	25
III. PROCEDURE	
A. MECHANICAL PROPERTIES	26
B. FATIGUE CRACK-PROPAGATION TESTS	30
C. CORROSION CHARACTERISTICS	31
IV. RESULTS OF TESTS	33
V. DISCUSSION OF RESULTS	
A. MECHANICAL PROPERTIES	34
B. FATIGUE CRACK-PROPAGATION TESTS	43
C. CORROSION CHARACTERISTICS	46
VI. SUMMARY AND CONCLUSION	54
REFERENCES	58
APPENDIX	288

LIST OF ILLUSTRATIONS

FIGURE		PAGE
1	Etched Cross Sections of 7050-T73651 Plate, 0.500-in. Thick	62
2	Etched Cross Sections of 7050-T73651 Plate, 1.000-in. Thick	63
3	Etched Cross Sections of 7050-T73651 Plate, 2.000-in. Thick	64
4	Etched Cross Sections of 7050-T73651 Plate, 4.000-in. Thick	65
5	Etched Cross Sections of 7050-T73651 Plate, 6.000-in. Thick	66
6	Etched Cross Sections of 7050-T73652 Hand Forgings, 2 and 2-1/2-in. Thick	67
7	Etched Cross Sections of 7050-T73652 Hand Forgings, 3-1/2-in. Thick	68
8	Etched Cross Sections of 7050-T73652 Hand Forgings, 4-1/2-in. Thick	69
9	Etched Cross Sections of 7050-T73652 Hand Forgings, 5-1/2-in. Thick.	70
10	Etched Cross Section of 7050-T73652 Hand Forging, 7-1/2-in. Thick.	71
11	Etched Cross Section of 7050-T73652 Hand Forging, 7-1/2-in. Thick.	72
12	Etched Cross Section of 7050-T736 Die Forging (Die No. 2177).	73
13	Etched Cross Section of 7050-T736 Die Forging (Die No. 9078).	74
14	Etched Cross Section of 7050-T736 Die Forging (Die No. 15789)	75
15	Etched Cross Section of 7050-T736 Die Forging (Die No. 17975)	76

LIST OF ILLUSTRATIONS
(Continued)

FIGURE		PAGE
16	Etched Cross Section of 7050-T736 Die Forging (Die No. 17944)	77
17	Etched Cross Section of 7050-T736 Die Forging (Die No. 1364)	78
18	Etched Cross Section of 7050-T736 Die Forging (Die No. 8457)	79
19	Etched Cross Section of 7050-T736 Die Forging (Die No. 4736)	80
20	Etched Cross Section of 7050-T736 Die Forging (Die No. 12767)	81
21	Etched Cross Section of 7050-T736 Die Forging (Die No. 16392)	82
22	Etched Cross Sections of 7050-T76511 Extruded Shapes, 0.187, 0.402 and 0.665-in. Thick. . . .	83
23	Etched Cross Sections of 7050-T76511 Extruded Shapes, 0.841 and 1.161-in. Thick	84
24	Etched Cross Sections of 7050-T76511 Extruded Rectangles, 1.5 and 2-in. Thick	85
25	Etched Cross Section of 7050-T76511 Extruded Rectangle, 3.5x7.5 in.	86
26	Etched Cross Section of 7050-T76511 Extruded Rectangle, 4.0x8.0 in.	87
27	Etched Cross Section of 7050-T76511 Extruded Rectangle, 5.0x6.25 in.	88
28	General Dimensions of Tensile Specimens	89
29	General Dimensions of Compressive and Shear Specimens	90
30	General Dimensions of Bearing Specimens	91
31	General Dimensions of Tensile Specimens for Modulus and Stress-Strain Tests	92

LIST OF ILLUSTRATIONS
(Continued)

FIGURE		PAGE
32	General Dimensions of Center-Slotted Fracture Toughness Panels	93
33	Setups for Testing 16-in. Wide Center-Slot Fracture Toughness Specimens With Anti- Buckling Guides	94
34	Setup for Testing 16-in. Wide Center-Slot Fracture Toughness Specimens.	95
35	Compact Tension Fracture Toughness Specimen . . .	96
36	Fracture-Toughness Specimen Orientations.	97
37	Setup for Fatigue Precracking of Compact Tension Fracture Toughness Specimens.	98
38	Setup for Testing Compact Tension Fracture Toughness Specimens	99
39	General Dimensions of Smooth and Notched Sheet- Type Axial-Stress Fatigue Specimens	100
40	Dimensions of Smooth and Notched Axial-Stress Fatigue Specimens	101
41	Crack-Propagation Specimen for Sheet.	102
42	Dimensions for Compact Tension Fatigue-Crack Propagation Specimens	103
43	Environmental Chamber for Fatigue-Crack Propagation Tests of Sheet.	104
44	Compact Tension Crack-Propagation Specimen in Fatigue Machine.	105
45	Four Degrees of Severity of Exfoliation Corrosion per ASTM Standard Method of Test G34-72.	106
46	Preformed Blank and Sheet-Tensile Specimen End Loaded for Corrosion Tests.	107

LIST OF ILLUSTRATIONS
(Continued)

FIGURE		PAGE
47a	1/8-in. Diameter Tensile Specimen, Various Parts of Stressing Frame, and Final Stressed Assembly for Stress-Corrosion Tests. .	108
47b	Synchronous Loading Device Used to Stress Specimens. Stressed Assembly and One Assembled Finger-Tight Ready for Stressing Are Shown to the Left	108
48	Configuration of Double Cantilever Beam (DCB) Specimen Used for SCC Tests	109
49	Sketches Showing Location of DCB Specimens Used for SCC Tests of Die Forgings.	110
50	Representative Stress-Strain Plots Obtained With an X-Y Recorder for Determining Modulus of Elasticity	111
51	Tensile Stress-Strain Curves for 0.040-in. Thick 7050-T76 Sheet (S-428882)	112
52	Tensile and Compressive Stress-Strain Curves for 0.063-in. Thick 7050-T76 Sheet (S-411378) .	113
53	Tensile and Compressive Stress-Strain Curves for 0.090-in. Thick 7050-T76 Sheet (S-411182) .	114
54	Tensile and Compressive Stress-Strain Curves for 0.125-in. Thick 7050-T76 Sheet (S-411212) .	115
55	Tensile and Compressive Stress-Strain Curves for 0.249-in. Thick 7050-T76 Sheet (S-411309) .	116
56	Tensile and Compressive Stress-Strain Curves for 1/2-in. Thick 7050-T73651 Plate (S-411184). .	117
57	Tensile and Compressive Stress-Strain Curves for 1-in. Thick 7050-T73651 Plate (S-411185). .	118
58	Tensile and Compressive Stress-Strain Curves for 2-in. Thick 7050-T73651 Plate (S-411186). .	119

LIST OF ILLUSTRATIONS
(Continued)

FIGURE		PAGE
59	Tensile and Compressive Stress-Strain Curves for 4-in. Thick 7050-T73651 Plate (S-411187-L and LT)	120
60	Tensile and Compressive Stress-Strain Curves for 4-in. Thick 7050-T73651 Plate (S-411187-ST) .	121
61	Tensile and Compressive Stress-Strain Curves for 6-in. Thick 7050-T73651 Plate (S-411300-L and LT)	122
62	Tensile and Compressive Stress-Strain Curves for 6-in. Thick 7050-T73651 Plate (S-411300-ST) .	123
63	Tensile and Compressive Stress-Strain Curves for 2-1/2-in. Thick 7050-T73652 Hand Forging (S-411229).	124
64	Tensile and Compressive Stress-Strain Curves for 3-1/2-in. Thick 7050-T73652 Hand Forging (S-411352-L and LT)	125
65	Tensile and Compressive Stress-Strain Curves for 3-1/2-in. Thick 7050-T73652 Hand Forging (S-411352-ST)	126
66	Tensile and Compressive Stress-Strain Curves for 4-1/2-in. Thick 7050-T73652 Hand Forging (S-411230-L and LT)	127
67	Tensile and Compressive Stress-Strain Curves for 4-1/2-in. Thick 7050-T73652 Hand Forging (S-411230-ST)	128
68	Tensile and Compressive Stress-Strain Curves for 5-1/2-in. Thick 7050-T73652 Hand Forging (S-411353-L and LT)	129
69	Tensile and Compressive Stress-Strain Curves for 5-1/2-in. Thick 7050-T73652 Hand Forging (S-411353-ST)	130

LIST OF ILLUSTRATIONS
(Continued)

FIGURE		PAGE
70	Tensile and Compressive Stress-Strain Curves for 7-1/2-in. Thick 7050-T73652 Hand Forging (S-411232-L and LT)	131
71	Tensile and Compressive Stress-Strain Curves for 7-1/2-in. Thick 7050-T73652 Hand Forging (S-411232-ST)	132
72	Tensile and Compressive Stress-Strain Curves for 0.7-in. Thick 7050-T736 Die Forging, Die No. 9078 (S-411331)	133
73	Tensile and Compressive Stress-Strain Curves for 1.1-in. Thick 7050-T736 Die Forging, Die No. 15789 (S-411351)	134
74	Tensile and Compressive Stress-Strain Curves for 4.25-in. Diameter 7050-T736 Die Forging, Die No. 12767 (S-411233)	135
75	Tensile and Compressive Stress-Strain Curves for 5.5-in. Thick 7050-T736 Die Forging, Die No. 8457 (S-411332)	136
76	Tensile and Compressive Stress-Strain Curves for 6.1-in. Thick 7050-T736 Die Forging, Die No. 16392 (S-411303)	137
77	Tensile and Compressive Stress-Strain Curves for 0.187-in. Thick 7050-T76511 Extruded Shape, Die No. 86366 (S-411288)	138
78	Tensile and Compressive Stress-Strain Curves for 0.665-in. Thick 7050-T76511 Extruded Shape, Die No. 213590 (S-411290)	139
79	Tensile and Compressive Stress-Strain Curves for 1.161-in. Thick 7050-T76511 Extruded Shape, Die No. 231372 (S-411287)	140
80	Tensile and Compressive Stress-Strain Curves for 3-1/2x7-1/2-in. 7050-T76511 Extruded Rectangle (S-411285-L and LT)	141

LIST OF ILLUSTRATIONS
(Continued)

FIGURE		PAGE
81	Tensile and Compressive Stress-Strain Curves for 3-1/2x7-1/2-in. 7050-T76511 Extruded Rectangle (S-411285-ST)	142
82	Tensile and Compressive Stress-Strain Curves for 5x6-1/4-in. 7050-T76511 Extruded Rectangle (S-411286-L and LT)	143
83	Tensile and Compressive Stress-Strain Curves for 5x6-1/4-in. 7050-T76511 Extruded Rectangle (S-411286-ST)	144
84	K_C vs. Tensile Yield Strength of 0.063-in. Sheet .	145
85	Plane-Stress Fracture Toughness Data of 7050-T76 Sheet, K_C vs. Sheet Thickness.	146
86	Crack-Growth Resistance, K_R , vs. Slow-Crack Growth of 7050-T76 Sheet, 0.063-in. (L-T Orientation)	147
87	Crack-Growth Resistance, K_R , vs. Slow-Crack Growth of 7050-T76 Sheet, 0.063-in. (T-L Orientation)	148
88	Plots of Threshold Apparent and Critical Instability of 7050-T76 Sheet, 0.063-in. (L-T Orientation)	149
89	Plots of Threshold, Apparent and Critical Instability of 7050-T76 Sheet, 0.063-in. (T-L Orientation)	150
90	K_{Ic} vs. Tensile Yield Strength of 7050-T73651 Plate, Thickness: 1/2 to 6 in.	151
91	K_{Ic} vs. Tensile Yield Strength of 7050-T73652 Hand Forgings, Thickness: 2 to 7-1/2-in. . . .	152
92	K_{Ic} vs. Tensile Yield Strength of 7050-T736 Die Forgings, Thickness: 0.6 to 6.1-in. . . .	153

LIST OF ILLUSTRATIONS
(Continued)

FIGURE		PAGE
93	K_{Ic} vs. Tensile Yield Strength of 7050-T76511 Extruded Shapes, Thickness: 0.4 to 5 in.	154
94	Axial-Stress Fatigue Data for Smooth Specimens of 7050-T76 Sheet, 0.125-in. Thick.	155
95	Axial-Stress Fatigue Data for Smooth Specimens of 7050-T76 Sheet, 0.040 to 0.222-in. Thick, (Longitudinal).	156
96	Axial-Stress Fatigue Data for Smooth Specimens of 7050-T76 Sheet, 0.040 to 0.222-in. Thick (Transverse).	157
97	Axial-Stress Fatigue Data for Smooth Specimens of 7050-T76 Sheet, 0.040 to 0.222-in. Thick (Comparison with 7075 Sheet).	158
98	Axial-Stress Fatigue Data for Notched Specimens of 7050-T76 Sheet, 0.125-in. Thick.	159
99	Axial-Stress Fatigue Data for Notched Specimens of 7050-T76 Sheet, 0.040 to 0.222-in. Thick (Longitudinal).	160
100	Axial-Stress Fatigue Data for Notched Specimens of 7050-T76 Sheet, 0.040 to 0.222-in. Thick (Transverse).	161
101	Axial-Stress Fatigue Data for Notched Specimens of 7050-T76 Sheet, 0.040 to 0.249-in. Thick (Comparison with 7075-T6 Sheet)	162
102	Axial-Stress Fatigue Data for Smooth Specimens of 7050-T73651 Plate, 1-in. Thick	163
103	Axial-Stress Fatigue Data for Smooth Specimens of 7050-T73651 Plate, 1 to 6-in. Thick (Longitudinal).	164
104	Axial-Stress Fatigue Data for Smooth Specimens of 7050-T73651 Plate, 1 to 6-in. Thick, (Long-Transverse)	165

LIST OF ILLUSTRATIONS
(Continued)

FIGURE		PAGE
105	Axial-Stress Fatigue Data for Smooth Specimens of 7050-T73651 Plate, 1 to 6-in. Thick (Comparison with 7075-T7351 Plate).	166
106	Axial-Stress Fatigue Data for Smooth Specimens of 7075-T7351 and 7050-T73651 Plate, 1 to 2-in. Thick (Comparison with 7075-T73XXX Products). . .	167
107	Axial-Stress Fatigue Data for Notched Specimens of 7050-T73651 Plate, 1-in. Thick	168
108	Axial-Stress Fatigue Data for Notched Specimens of 7050-T73651 Plate, 1 to 6-in. Thick, (Longitudinal).	169
109	Axial-Stress Fatigue Data for Notched Specimens of 7050-T73651 Plate, 1 to 6-in. Thick, (Long-Transverse)	170
110	Axial-Stress Fatigue Data for Notched Specimens of 7050-T73651 Plate, 1 to 6-in. Thick (Comparison with 7075-T73XXX Products).	171
111	Axial-Stress Fatigue Data for Smooth Specimens of 7050-T73652 Hand Forgings, 2 to 7-1/2-in. Thick (R = 0.0)	172
112	Axial-Stress Fatigue Data for Smooth Specimens of 7050-T73652 Hand Forgings, 4-1/2x22x84 in. (R = +0.5 and -1.0)	173
113	Axial-Stress Fatigue Data for Smooth Specimens of 7050-T73652 Hand Forgings, 2 to 7-1/2-in. Thick (Comparison with 7XXX-T73XXX Products). . .	174
114	Axial-Stress Fatigue Data for Notched Specimens of 7050-T73652 Hand Forgings, 2 to 7-1/2-in. Thick (R = 0.0)	175
115	Axial-Stress Fatigue Data for Notched Specimens of 7050-T73652 Hand Forgings, 4-1/2x22x84 in. (R = +0.5 and -1.0)	176

LIST OF ILLUSTRATIONS
(Continued)

FIGURE		PAGE
116	Axial-Stress Fatigue Data for Notched Specimens of 7050-T73652 Hand Forgings, 2 to 7-1/2-in. Thick (Comparison with 7XXX-T73XXX Products). . .	177
117	Axial-Stress Fatigue Data for Smooth Specimens of 7050-T736 Die Forgings, 1 to 6.1-in. Thick . .	178
118	Axial-Stress Fatigue Data for Smooth Specimens of 7050-T736 Die Forgings, 1 to 6.1-in. Thick (Comparison with 7XXX-T7XX)	179
119	Axial-Stress Fatigue Data for Smooth Specimens of 7050-T736 Die Forgings, 1 to 6.1-in. Thick . .	180
120	Axial-Stress Fatigue Data for Notched Specimens of 7050-T736 Die Forgings, 1 to 6.1-in. Thick (Comparison with 7XXX-T7XX)	181
121	Axial-Stress Fatigue Data for Smooth Specimens of 7050-T76511 Extruded Shapes, 1.161-in. Thick (Die No. 231372).	182
122	Axial-Stress Fatigue Data for Smooth Specimens of 7050-T7651X Extruded Shapes, 0.187 to 5.000-in. Thick (Longitudinal).	183
123	Axial-Stress Fatigue Data for Smooth Specimens of 7050-T7651X Extruded Shapes, 0.187 to 5.000-in. Thick (Long-Transverse)	184
124	Axial-Stress Fatigue Data for Smooth Specimens of 7050-T7651X Extruded Shapes, 0.187 to 5.000-in. Thick (Comparison with 7075-T7651X) . .	185
125	Axial-Stress Fatigue Data for Notched Specimens of 7050-T7651X Extruded Shapes, 1.161-in. Thick (Die No. 231372).	186
126	Axial-Stress Fatigue Data for Notched Specimens of 7050-T7651X Extruded Shapes, 0.187 to 5.000-in. Thick (Longitudinal).	187

LIST OF ILLUSTRATIONS
(Continued)

FIGURE		PAGE
127	Axial-Stress Fatigue Data for Notched Specimens of 7050-T7651X Extruded Shapes, 0.187 to 5.000-in. Thick (Long-Transverse).	188
128	Axial-Stress Fatigue Data for Notched Specimens of 7050-T7651X Extruded Shapes, 0.187 to 5.000-in. Thick (Comparison with 7075-T7651X). . .	189
129	Modified Goodman Diagram for 7050-T76 Sheet, 0.125-in. Thick (Longitudinal and Long-Transverse, $K_t = 1$).	190
130	Modified Goodman Diagram for 7050-T76 Sheet, 0.125-in. Thick (Longitudinal and Long-Transverse, $K_t = 3$).	191
131	Modified Goodman Diagram for 7050-T73651 Plate, 1-in. Thick (Longitudinal and Long-Transverse, $K_t = 1$).	192
132	Modified Goodman Diagram for 7050-T73651 Plate, 1-in. Thick (Longitudinal and Long-Transverse, $K_t = 3$).	193
133	Modified Goodman Diagram for 7050-T73652 Hand Forging, 4-1/2x22x84-in. (Longitudinal, $K_t = 1$).	194
134	Modified Goodman Diagram for 7050-T73652 Hand Forging, 4-1/2x22x84-in. (Long-Transverse, $K_t = 1$).	195
135	Modified Goodman Diagram for 7050-T73652 Hand Forging, 4-1/2x22x84-in. (Short-Transverse, $K_t = 1$).	196
136	Modified Goodman Diagram for 7050-T73652 Hand Forging, 4-1/2x22x84-in. (Longitudinal, $K_t = 3$).	197
137	Modified Goodman Diagram for 7050-T73652 Hand Forging, 4-1/2x22x84-in. (Long-Transverse, $K_t = 3$).	198

LIST OF ILLUSTRATIONS
(Continued)

FIGURE		PAGE
138	Modified Goodman Diagram for 7050-T73652 Hand Forging, 4-1/2x22x84-in. (Short- Transverse, $K_t = 3$)	199
139	Modified Goodman Diagram for 7050-T76511 Extruded Shape, 1.161-in. Thick (Die No. 231372) (Long-Transverse, $K_t = 1$)	200
140	Modified Goodman Diagram for 7050-T76511 Extruded Shape, 1.161-in. Thick (Die No. 231372) (Long-Transverse, $K_t = 3$)	201
141	Effect of Salt Fog on Axial-Stress Fatigue Strength of 7050-T76 Sheet	202
142	Effect of Salt Fog on Axial-Stress Fatigue Strength of 7050-T73651 Plate.	203
143	Effect of Salt Fog on Axial-Stress Fatigue Strength of 7050-T73652 Hand Forgings.	204
144	Effect of Salt Fog on Axial-Stress Fatigue Strength of 7050-T7651X Extruded Shapes.	205
145	Axial-Stress Fatigue Strength of 7050 Products in Salt Fog.	206
146	Fatigue Crack-Growth Data for 0.040-in. 7050-T76 Sheet, T-L Orientation.	207
147	Fatigue Crack-Growth Data for 0.125-in. 7050-T76 Sheet, T-L Orientation.	208
148	Fatigue Crack-Growth Data for 0.125-in. 7050-T76 Sheet, L-T Orientation.	209
149	Fatigue Crack-Growth Data for 1-in. 7050-T73651 Plate, T-L Orientation	210
150	Fatigue Crack-Growth Data for 6-in. 7050-T73651 Plate, T-L Orientation	211

LIST OF ILLUSTRATIONS
(Continued)

FIGURE		PAGE
151	Fatigue Crack-Growth Data for 6-in. 7050-T73651 Plate, L-T Orientation.	212
152	Fatigue Crack-Growth Data for 6-in. 7050-T73651 Plate, S-L Orientation.	213
153	Fatigue Crack-Growth Data for 2-1/2x22-in. 7050-T73652 Hand Forging, T-L Orientation . . .	214
154	Fatigue Crack-Growth Data for 7-1/2x22-in. 7050-T73652 Hand Forging, T-L Orientation . . .	215
155	Fatigue Crack-Growth Data for 7-1/2x22-in. 7050-T73652 Hand Forging, L-T Orientation . . .	216
156	Fatigue Crack-Growth Data for 7-1/2x22-in. 7050-T73652 Hand Forging, S-L Orientation . . .	217
157	Fatigue Crack-Growth Data for 1.161-in. 7050-T76511 Extruded Shape, T-L Orientation . .	218
158	Fatigue Crack-Growth Data for 1.161-in. 7050-T76511 Extruded Shape, L-T Orientation . .	219
159	Fatigue Crack-Growth Data for 5x6-1/4-in. 7050-T76511 Extrusion, L-T Orientation.	220
160	Fatigue Crack-Growth Data for 5x6-1/4-in. 7050-T76511 Extrusion, S-L Orientation.	221
161	Photomicrographs Illustrating Minor Exfoliation Attack in Alloy 7050 Products Exposed 48 Hours to "EXCO" Test.	222
162	Photomicrographs Illustrating Severe Pitting and Auxiliary Transgranular Cracking in Longitudinal and Long-Transverse Specimens from 4-in. Thick 7050-T73651 Plate	223

LIST OF ILLUSTRATIONS
(Continued)

FIGURE		PAGE
163	Photomicrographs Illustrating the Mixed-Mode Nature of Auxiliary Cracking in Short-Transverse Specimens from 7050-T73651 Plate. . .	224
164	Photomicrographs Illustrating the Predominantly Transgranular Nature of Auxiliary Cracking in Short-Transverse Specimens from 7050-T73652 Hand Forgings.	225
165	Photomicrographs Illustrating the Predominantly Interfragmentary Nature of Auxiliary Cracking in Short-Transverse Specimens from 7050-T736 Die Forgings Exposed to Accelerated and Atmospheric Environments	226
166	Photomicrographs Illustrating the Interfragmentary Nature of Auxiliary Cracking in Short-Transverse Specimens from 7050-T76511 Extruded Shapes.	227
167	Stress-Corrosion Crack Growth of Alloy 7050 Products in 3.5% NaCl.	228
168	Illustrates Fracture Surface and Intergranular Nature of Cracking at the Tip of the Stress-Corrosion Crack in Short-Transverse (S-L) DCB Specimens from 2-in. Thick 7050-T73651 Plate.	229
169	Illustrates Fracture Surface, Crack Profile and Interfragmentary Nature of Stress-Corrosion Crack Growth in Short-Transverse (S-L) DCB Specimens from 4.001-5.000-in. Thick 7050-T736 Die Forging.	230
170	Illustrates Fracture Surfaces and Interfragmentary Nature of Stress-Corrosion Crack Growth in Short-Transverse (S-L) DCB Specimens from 7050-T7651X Extruded Shapes.	231

LIST OF ILLUSTRATIONS
(Concluded)

FIGURE		PAGE
171	Illustrates Fracture Surface, Crack Profile and Interfragmentary Nature of Stress- Corrosion Crack Growth in Short-Transverse (S-L) DCB Specimen from 2.001-4.000-in. Thick 7050-T736 Die Forging.	232
172	K_I - Rate Data for Tests of Alloy 7050 Products	233

LIST OF TABLES

TABLE		PAGE
I	Chemical Compositions of 7050-Products.	234
II	Mechanical Properties of 7050-T76 Sheet	235
III	Mechanical Properties of 7050-T73651 Plate.	236
IV	Mechanical Properties of 7050-T73652 Hand Forgings.	237
V	Mechanical Properties of 7050-T736 Die Forgings	238
VI	Mechanical Properties of 7050-T76511 Extruded Shapes	239
VII	Specified Minimum Tensile Properties for 7050 Products	240
VIII	Ratios Among the Tensile, Compressive, Shear and Bearing Properties of 7050-T76 Sheet	241
IX	Ratios Among the Tensile, Compressive, Shear and Bearing Properties of 7050-T73651 Plate.	242
X	Ratios Among the Tensile, Compressive, Shear and Bearing Properties of 7050-T73652 Hand Forgings.	243
XI	Ratios Among the Tensile, Compressive, Shear and Bearing Properties of 7050-T736 Die Forgings	244
XII	Ratios Among the Tensile, Compressive, Shear and Bearing Properties of 7050-T76511 Extruded Shapes.	245
XIII	Statistical Analyses of Ratios Among Tensile, Compressive, Shear and Bearing Properties of 7050-T76 Sheet.	246
XIV	Statistical Analyses of Ratios Among Tensile, Compressive, Shear and Bearing Properties of 7050-T73651 Plate	247
XV	Statistical Analyses of Ratios Among Tensile, Compressive, Shear and Bearing Properties of 7050-T73652 Hand Forgings	248
XVI	Statistical Analyses of Ratios Among Tensile, Compressive, Shear and Bearing Properties of 7050-T736 Die Forgings.	249

LIST OF TABLES
(Continued)

TABLE		PAGE
XVII	Statistical Analyses of Ratios Among Tensile, Compressive, Shear and Bearing Properties of 7050-T76511 Extruded Shapes.	250
XVIII	Ratios For Computing Design Mechanical Properties of 7050-T76 Sheet.	251
XIX	Ratios For Computing Design Mechanical Properties of 7050-T73651 Plate	252
XX	Ratios For Computing Design Mechanical Properties of Hand Forgings and Die Forgings.	253
XXI	Ratios For Computing Design Mechanical Properties of 7050-T76511 Extruded Shapes	254
XXII	Computed Design Mechanical Properties of 7050-T76 Sheet	255
XXIII	Computed Design Mechanical Properties of 7050-T73651 Plate.	256
XXIV	Computed Design Mechanical Properties of 7050-T73652 Hand Forgings	257
XXV	Computed Design Mechanical Properties of 7050-T736 Die Forgings.	258
XXVI	Computed Design Mechanical Properties of 7050-T76511 Extruded Shapes.	259
XXVII	Results of Tensile and Compressive Stress-Strain and Modulus of Elasticity Tests of 7050 Products	260
XXVIII	Summary of Average Modulus of Elasticity Values of 7050 Products	261
XXIX	Results of Fracture Toughness Tests of 7050-T76 Sheet	262
XXX	Results of Compact Tension Fracture Toughness Tests of 7050-T73651 Plate.	263
XXXI	Results of Compact Tension Fracture Toughness Tests of 7050-T73651 Hand Forgings.	264
XXXII	Results of Compact Tension Fracture Toughness Tests of 7050-T736 Die Forgings	265

LIST OF TABLES
(Continued)

TABLE	PAGE
XXXIII	Results of Compact Tension Fracture Toughness Tests of 7075-T76511 Extruded Shapes. 266
XXXIV	Average Axial-Stress Fatigue Strengths For Smooth and Notched Specimens Tested in Salt Fog. 267
XXXV	Rates of Fatigue-Crack Propagation In 7050 Products 268
XXXVI	Results of Accelerated Exfoliation Tests of 7050-T76 Sheet 269
XXXVII	Results of Accelerated Exfoliation Tests of 7050-T73651 Plate. 270
XXXVIII	Results of Accelerated Exfoliation Tests of 7050-T736 Die Forgings and 7050-T73652 Hand Forgings . 271
XXXIX	Results of Accelerated Exfoliation Tests of 7050-T76511 Extruded Shapes. 272
XL	Results of Accelerated SCC Tests of 7050-T76 Sheet 273
XLI	Results of Accelerated SCC Tests of 7050-T73651 Plate 274
XLII	Results of Accelerated SCC Tests of 7050-T73652 Hand Forgings 275
XLIII	Results of Accelerated SCC Tests of 7050-T736 Die Forgings. 276
XLIV	Results of Accelerated SCC Tests of 7050-T76511 Extruded Shapes 277
XLV	Status of Atmospheric SCC Tests of 7050-T76 Sheet . 278
XLVI	Status of Atmospheric SCC Tests of 7050-T73651 Plate 279
XLVII	Status of Atmospheric SCC Tests of 7050-T73652 Hand Forgings 280
XLVIII	Status of Atmospheric SCC Tests of 7050-T736 Die Forgings. 281

LIST OF TABLES
(Concluded)

TABLE		PAGE
XLIX	Status of Atmospheric SCC Tests of 7050-T76511 Extruded Shapes	282
L	Summary of Corrosion Performance of Alloy 7050 Products Relative to Anticipated Corrosion Targets	283
LI	Results of SCC Tests of Precracked Specimens From 7050-T73651 Plate	284
LII	Results of SCC Tests of Precracked Specimens From 7050-T736 Die Forgings.	285
LIII	Results of SCC Tests of Precracked Specimens From 7050-T76511 Extruded Shapes	286
LIV	Results of Tests of Ring-Loaded Short-Transverse Compact Specimens of 7050-T73651 Plate and 7050-T76511 Extruded Shapes.	287
LV	Fatigue Crack-Growth Data for 7050-T76 Sheet. . .	289
LVI	Fatigue Crack-Growth Data for 7050-T73651 Plate .	291
LVII	Fatigue Crack-Growth Data for 7050-T73652 Hand Forgings.	293
LVIII	Fatigue Crack Growth Data for 7050-T76511 Extruded Shapes.	295

SECTION I

INTRODUCTION

The aerospace industry has a need for an aluminum alloy capable of developing in thick products a combination of high strength, high resistance to stress-corrosion and good fracture toughness for advanced, reliable, high-performance aircraft and aerospace structures. It also has a need for thinner aluminum alloy products which are capable of developing good resistance to exfoliation and high toughness at high-strength levels. Established commercial alloys and tempers provide one and sometimes two of these characteristics, but the combination of all three in either thick or thin sections has heretofore not been available.

Alcoa developed alloy 7050 under NASC contracts [1-4] to fill the need for a material which had the desired combination of properties in thick sections, and later realized that in thin sections this alloy also developed levels of strength, exfoliation resistance and toughness that were superior to those of commercial aluminum alloy products.

The alloy development work revealed that the corrosion characteristics and toughness of alloy 7050 products progressively increased as yield strength decreased with overaging beyond peak strength. This correlation between yield strength and corrosion resistance was used to select tentative minimum tensile properties for various tempers of 7050 products.

Either yield strength or corrosion resistance was used as the primary property. The secondary property was obtained from the yield strength-corrosion resistance correlation. For some products and tempers corrosion resistance capability criteria were initially set. The maximum yield strengths expected to provide the desired corrosion resistance were then estimated from tensile and corrosion test data. The minimum yield strengths were then set 9 ksi below the maximum values; this spread in yield strengths is that expected based on the fabricating and heat treating practices established for the products. In other instances, the desired minimum yield strength was initially set and the maximum yield strength was made 9 ksi higher. Then the corrosion resistance capabilities were estimated from the yield strength-corrosion resistance correlation. Once the yield strengths and corrosion resistance capabilities were set, minimum tensile ultimate strengths were established from relationships of yield strength to ultimate strength for commercially established 7XXX alloy products. Minimum elongations were estimated from available data.

The purpose of this investigation was to evaluate the mechanical properties and corrosion characteristics of 7050 products produced by commercial practices in the form of (T76) sheet, (T73651) plate, (T73652) hand forgings, (T736) die forgings and (T76511) extruded shapes. In order to make effective and efficient utilization of these products, sufficient data have been evaluated to permit the development of statistically meaningful design mechanical properties for use in MIL-HDBK-5[5] and to provide sufficient confidence in their levels of fracture toughness, fatigue strength, fatigue-crack propagation rates, exfoliation and stress-corrosion resistance.

SECTION II

MATERIAL

The 7050 products tested in this investigation included eleven lots of T76 sheet and ten lots each of T73651 plate, T73652 hand forgings, T736 die forgings and T76511 extruded shapes. All lots tested were produced by commercial practices. Three samples each of hand forgings, die forgings and extruded shapes were fabricated by another producer, hereafter designated as "Producer B"; all other samples were fabricated by Alcoa, hereafter designated as "Producer A".

The chemical compositions of each sample, determined at the Alcoa Laboratories, are shown in Table I. The compositions of all samples are within the specified limits shown at the bottom of Table I.

The tensile properties of the sheet, plate, hand forgings, die forgings, and extruded shapes are shown in Tables II, III, IV, V and VI, respectively. The specified minimum tensile properties are shown in Table VII. The AMS Specifications for plate, hand forgings and die forgings are indicated in the last column of Table VII. The minimum values for sheet and extruded shapes are Alcoa's tentative values. The tensile properties of two of the hand forgings (S. Nos. 428850 and 428851) and one of the die forgings (S. No. 411392) were initially below the specified minimum values. In each instance two retests were made. As indicated in Table IV, one of the two retests of the short-transverse specimens of the 3-1/2-in. thick hand forging (S. No. 428850) failed to meet the tensile strength minimum values by 0.8 ksi. Both short-transverse tensile strengths in the retests of the die forgings (S. No. 411392) failed to meet the minimum value (Table V). These samples could not be replaced by Producer B. Also, two of the hand forgings, and five of the die forgings had yield strengths a little above the maximum values. Since the minimum and maximum tensile properties at the time of the tests were tentative and since the relationships among the tensile, compressive, shear and bearing properties would still be valid, the data were included in the analysis of ratios for establishing minimum design properties.

Etched cross sections of each sample, except sheet, are shown in Figs. 1 through 27. The microstructures of some of the samples were examined; all structures were representative of structures of commercially established 7XXX aluminum alloys. Photographs of the die forgings are shown in Figs. 12 through 21 along with the etched cross section of the respective die forgings.

SECTION III

PROCEDURE

A. Mechanical Properties

A.1. Tensile, Compressive, Shear and Bearing

All tensile, compressive, shear and bearing tests were made using the smallest suitable range of an Amsler 20,000-lb. (Type 105XBDA58), an Olsen Electromatic 30,000-lb, and an Olsen Super-L 20,000-lb or a Southwark-Tate-Emery 50,000-lb capacity Universal Testing Machine. The machines were calibrated prior to and during the investigation. The accuracy of these testing machines was always within that required by ASTM Method E4[6].

In general, the test specimens and procedures used were, where appropriate, the same as those used in previous investigations of sheet, plate, extrusions and forgings[7-12]. Single tests were made except in a few instances where initial results indicated check tests were necessary. Specimens were taken in the test directions and locations specified in ASTM B557[13]. Specimens (L and LT) from the sheet were full thickness. Longitudinal specimens from plate were from the same locations as the long-transverse specimens, and short-transverse specimens were from the center of the thickness. Specimens from hand forgings (L, LT and ST) were from the center third of the thickness and width. Longitudinal specimens from predominantly "flanged" die forgings, 0.6 to 3.1-in. thick, were located between the parting plane and the top of the flange. Short-transverse specimens were taken normal to the parting plane with the center of the test sections located at the parting plane; specimens from the thicker die forgings, 3.5 to 6.1-in. thick (or diameter) were from the central area of the cross section; locations of the longitudinal specimens from extruded shapes were as indicated in ASTM B557 and long-transverse and short-transverse specimens were from the center of the width and thickness.

Tensile tests were made in accordance with ASTM E8[14] with either 1/2-in. wide sheet-type specimens or 1/2-in. diameter tapered-seat specimens, except where it was necessary to use subsize round specimens (Fig. 28). The yield strengths were determined from autographically recorded load-strain diagrams.

Compressive tests were made in accordance with ASTM E9[15] using a subpress (Fig. 3 of ASTM E9). Specimens from sheet and extruded shapes less than 0.500-in. thick were of the type shown in Fig. 29; these specimens were supported laterally by a Montgomery-Templin Fixture (Fig. 4 of ASTM E9). Specimens from thicker products were cylindrical of the type shown in Fig. 29. The yield strengths were determined from autographically recorded load-strain diagrams.

Shear tests of each sample of sheet were made with a punch-type shear tool in which the shear strength was determined by measuring the load required to punch a 2-3/4-in. diameter circle from a 4x4-in. blank with a hardened steel punch and die. Shear tests of the other products, and also the 0.222 and 0.249-in. sheet, were made using cylindrical specimens (Fig. 29); these specimens were tested in an Amsler double-shear tool in which a 1-in. length is sheared from the center of a 3-in. long specimen, the end thirds being supported throughout their length. In the tests of longitudinal and long-transverse specimens, the loads were applied in the direction normal (ST) to the major surface of the product; in the tests of short-transverse specimens, the loads were applied in the direction parallel (L) to the major axis[16].

Bearing tests were made in accordance with ASTM E238[17] using longitudinal and, where possible, long-transverse specimens of the type shown in Fig. 30. Specimens from material equal to or less than 0.249-in. thick were full thickness, and those from thicker material were machined to 0.094-in. thick. The bearing ultimate and yield strengths were determined at edge distance of 1.5 and 2.0 times the pin diameter. The bearing yield strength was obtained by determining the load at a permanent deformation of 2 per cent of the pin diameter as indicated on an autographic load-deformation diagram. Bearing specimens were taken flatwise with the exception that those from the hand and die forgings were taken edgewise. The specimens and test fixtures were cleaned ultrasonically as prescribed in ASTM E238.

Tensile and compressive stress-strain tests, including modulus of elasticity determinations, were made of longitudinal, and when possible, long-transverse and short-transverse specimens from five samples of each product. The tests were, in general, conducted in accordance with ASTM E111[18]. The tensile specimens were of the type shown in Fig. 31 and the compressive specimens were of the types shown in Fig. 29 (sheet-type, 3/4-in. and 1/2-in. dia.).

Loads were measured with Revere Super Precision type load cells having an accuracy, traceable to the National Bureau of Standards, of 0.1 per cent of rated output. Strains were measured with Micro-Measurements Types CEA-13-062UW-350 and CEA-13-125UW-350 strain gages. These gages have a gage factor accuracy of 0.5 per cent and a resistance accuracy of 0.3 per cent. The stress and strain signals were recorded on a Mosley X-Y recorder. Overall accuracy of load measurement was 0.5 per cent of reading or 0.25 per cent of full scale, whichever was larger. Strain measurement accuracy was 0.7 per cent of reading or 0.5 per cent of full scale, whichever was larger; the accuracy of the gages was well within the requirements established for Class B1 extensometers in ASTM E83[19].

The modulus of elasticity values were determined from Tuckerman analysis plots as described in ASTM E111. The values obtained from the stress versus strain plots were used for the trial modulus values. The specimens were tested to 25 ksi, within the elastic limit of the material. The stress scales were 2.5 ksi per inch and the strain scales were 250 microinches per inch.

The aforementioned methods and equipment were then used to obtain stress-strain curves beyond the yield strength of the material; the stress scale was 10 ksi per inch and the strain scale was 2000 microinches per inch. These data were also recorded in computer storage for use in establishing typical stress-strain and tangent-modulus curves. Compressive modulus of elasticity values from zero stress to the proportional limit were determined from these data. Presently, there are insufficient production data for establishing the typical tensile properties necessary for making typical stress-strain curves.

A.2. Fracture Toughness

The critical stress-intensity factor, K_{IC} , of all the sheet samples were determined from tests of 16-in. wide center-slotted panels of the type shown in Fig. 32[20] following published guidelines[21]. The specimens were loaded monotonically in an Amsler 300,000-lb capacity testing machine, shown in the test setup in Fig. 33. Two different anti-buckling guides, shown in Fig. 34, were used. The improved type, shown at the bottom of Fig. 34, was used in the latter tests. The guides at the top of Fig. 34 were made up of four separate aluminum bars and the improved guides were made up of two bars with a 1x12-in. slot centered over the crack in the specimen; these guides had 1/8-in. thick layers of lubricated teflon between the guides and the specimen. A few samples were tested without anti-buckling guides.

The crack-opening displacement (COD) was measured over an 11.3-in. gage length. Plots of load versus COD were made using a Mosley X-Y recorder. The critical crack lengths were calculated by conversion of COD to crack length measurement through a compliance calibration. The critical stress-intensity factor, K_{IC} , was calculated at the point of instability. Crack resistance curves for 0.063-in. sheet were developed. Data for 0.063-in. sheet were established using the technique proposed by C. E. Feddersen[22].

All samples were tested with 4-in. center slots. One sample of 0.063-in. sheet was tested with various slot sizes, 1, 2, 3, 4, 5 and 6 in.; the other sample of 0.063-in. sheet was tested with 4 and 6-in. slots.

Duplicate fatigue-cracked compact tension specimens of the type shown in Fig. 35 were used to determine the plane-strain stress-intensity factor, K_{Ic} , of all the plate, hand forgings and die forgings and all but the 0.187-in. thick extruded shape. The specimen orientations, shown in Fig. 36, dimensions, notches, fatigue cracking and testing procedures were essentially in accordance with ASTM E399[23]. The specimens were fatigue cracked by axial loading ($R=+0.1$) in Krouse fatigue machines. The test setups for fatigue precracking and fracture toughness testing are shown in Figs. 37 and 38, respectively. The tests were made in a 30,000-lb capacity Olsen Electromatic testing machine, and plots of load versus COD were recorded using a Mosley X-Y recorder. Candidate values of critical plane-strain stress-intensity factor, K_Q , were calculated using the load at 5 per cent secant offset which is equivalent to about 2 per cent of crack extension. If all the validity criteria specified in ASTM Method E399 were met, the candidate value was designated as K_{Ic} .

A.3. Axial-Stress Fatigue

A.3.1 Ambient-Air Environment

Tests were made of smooth and notched axial-stress fatigue specimens of the types shown in Figs. 39 (sheet-type, thickness < 0.125 in.) and 40 (round). Generally, longitudinal and long-transverse specimens were taken from each product; specimens from die forgings were longitudinal and short-transverse and specimens from hand forgings were long-transverse except for one sample where specimens were taken in all three directions, L, LT and ST. The specimens were, in general, taken from the same locations as the tensile specimens. Tests were made at stress ratios* of $R=+0.5$, 0.0 and -1.0 for one sample each of sheet, plate, hand forgings and extruded shapes; sufficient specimens were tested in order to develop modified Goodman diagrams. Generally, at least four specimens from the other lots, including die forgings, were tested at various stress levels at a stress ratio of $R=0.0$. All tests were made in Krouse fatigue machines operating in 13.3, 25.0 or 28.8 Hz.

A.3.2 Salt-Fog Environment

Smooth and notched specimens having test sections similar to those shown in Figs. 39 and 40 were subjected to axial-stress fatigue tests ($R=0.0$) in a salt-fog environment. As indicated in Fig. 40 the notched round specimen had a notch-tip radius of 0.0005 in., $K_t \geq 12$, instead of 0.013 in., $K_t=3$, as originally intended. Specimens were taken in the long-transverse direction from two thicknesses of the sheet, plate, hand forgings and extruded shapes. During the tests in 5-kip capacity Krouse fatigue machines operating at 18.3 Hz, the test sections were subjected to a 20-second spray of a 3-1/2 per cent salt solution at 5 minute intervals.

* Stress ratio, $R = \frac{\text{minimum stress}}{\text{maximum stress}}$

B. Fatigue Crack-Propagation Tests

Fatigue-crack propagation rates for 0.040 and 0.215-in. thick sheet samples were determined using full thickness, center-notch specimens containing a 0.020-in. long EDM (electrical discharge machining) crack-starter notch, Fig. 41. Compact tension specimens, Fig. 42, were used for the plate, extrusions and hand forgings. Data were developed for each product in: (a) Dry air, (b) Humid air and (c) 3-1/2 per cent NaCl salt fog. Specimens were taken in the T-L and L-T orientations, and where possible in the S-L orientation, as shown in Fig. 36.

Center-notch specimens were tested in a 15-kip Krouse fatigue machine, Fig. 43, at a frequency of 13.3 Hz. The compact tension-type fatigue crack-propagation specimens were tested in 5-kip Krouse machines at a frequency of 18.3 Hz using fixtures similar to those shown in Fig. 44. Fatigue cracks were generally initiated at $R=0.1$ at maximum test loads used in subsequent data acquisition at $R=1/3$. The final 0.03 to 0.05 in. of "initiation" was accomplished at test loads ($R=1/3$). Visual crack-length measurements were made using low power magnification (15X) and a series of reference grid lines (0.02 in.) photographically printed on both sides of the specimen surface (Fig. 44).

Environmental control was provided by using chambers such as shown in Fig. 43. Dry air (relative humidity < 10 per cent) was obtained using dessicants; humid air (relative humidity < 90 per cent) was obtained by having a water reservoir in the chamber. The salt fog consisted of a 20 second spraying of a 3-1/2 per cent salt solution applied at 5-minute intervals.

The rate of fatigue-crack growth, da/dN , was determined from the slope of a second degree polynomial fitted through each three successive data points. The rates of crack growth were plotted as a function of $\Delta K = \frac{\Delta P \sqrt{a}}{BW}$

where a = crack length, in. (half of total crack length for center-notch specimens), Figs. 41 and 42.

B = specimen thickness, in.

W = specimen width, in. (load line to end of specimen for compact tension specimen).

P = load, kips.

$$Y, \text{ (center-notch specimen)} = 1.77 + 0.277\left(\frac{2a}{W}\right) - 0.510\left(\frac{2a}{W}\right)^2 + 2.7\left(\frac{2a}{W}\right)^3 \quad (\text{Ref. 24})$$

$$Y, \text{ (compact-tension specimen, } H/W = 0.485) = 30.96 - 195.8\left(\frac{a}{W}\right) + 730.6\left(\frac{a}{W}\right)^2 - 1186.3\left(\frac{a}{W}\right)^3 \text{ (Ref. 25)}$$

$$Y, \text{ (compact-tension specimen, } H/W = 0.6) = 29.6 - 185.5\left(\frac{a}{W}\right) + 655.7\left(\frac{a}{W}\right)^2 - 1017.0\left(\frac{a}{W}\right)^3 + 638.9\left(\frac{a}{W}\right)^4$$

C. Corrosion Characteristics

C.1. Resistance to Exfoliation

The resistance to exfoliation of the various products was evaluated by means of 2x4-in. panels machined to the T/10 and/or the T/2 planes (10 or 50 per cent of the section thickness machined from one of the fabricated surfaces) and exposed to the EXCO test per ASTM G34[26]. The EXCO test involves total immersion for a period of 48 hours in a 4M NaCl + 0.5M KNO₃ + 0.1M HNO₃ solution. In addition, selected lots of the sheet, plate and extruded products were exposed to the acidified salt spray test such as specified in MIL-A-8978, 8979 and 8980 for 7178-T76 products[27], and to the seacoast atmosphere at Point Judith, Rhode Island. Specimens exposed to the two accelerated tests were rated visually using the photographic standards contained in ASTM G34[26], Fig. 45.

C.2. Resistance to Stress-Corrosion Cracking (SCC)-Smooth Specimens

Sheet

Stress-corrosion cracking tests were conducted with two types of long-transverse specimens: a premachined tensile specimen (ASTM E8, Fig. 8), and a plastically deformed tensile specimen blank. Full thickness specimens were used for 0.040 and 0.063-in. sheet; for thicknesses greater than 0.063 in., specimens were machined on one surface to 0.063 in. and the original rolled surface was stressed in tension. Both types of specimens were stressed in duplicate, by bending in constant span-type fixtures, Fig. 46, with the tensile specimens being end-milled to a length calculated to develop a stress of 75 per cent of the measured tensile yield strength. Duplicate unstressed tensile specimens were also exposed.

Specimens were exposed to three environments: (a) 3.5 per cent NaCl by alternate immersion per Federal Test Standard 151b, Method 823[28]; (b) seacoast atmosphere at Point Judith, Rhode Island; and (c) industrial atmosphere at Alcoa Center, Pennsylvania. Atmospheric tests are scheduled for a minimum exposure of four years, but at the time this report was written, the maximum length of accrued exposure was only about 22 months.

Plate, Forgings and Extrusions

The resistance to stress-corrosion cracking of susceptible aluminum alloys and tempers is most critical in the short-transverse direction (perpendicular to and across the parting plane in the case of die forgings); consequently, the majority of tests were made on specimens oriented in that direction. Certain items were also tested in the longitudinal and long-transverse directions.

Tests were conducted with 0.125-in. diameter threaded end tensile specimens meeting the requirements of ASTM E8. Specimens were centered in the product thickness, except that for die forgings the short-transverse specimens were taken across the parting plane approximately 3/8-in. below the base of the flash.

Unstressed specimens were exposed in duplicate and stressed specimens in triplicate. All specimens were axially loaded in tension in "constant strain" type fixtures, Fig. 47a, using a synchronous loading device of the type shown in Fig. 47b. Longitudinal and long-transverse specimens were stressed at 75 per cent of the actual tensile yield strength, and short-transverse specimens were stressed at 45, 35 and 25 ksi.

The corrosive environments used were the same as those cited in the preceding section for sheet samples. Atmospheric tests of these samples had progressed for approximately 20 to 25 months at the time this report was written.

C.3. Resistance to SCC - Precracked Specimens

Stress-corrosion cracking tests of precracked specimens were conducted on plate, die forged and extruded samples with bolt-loaded double cantilever beam (DCB) specimens of the types shown in Fig. 48. Short-transverse specimens of S-L orientation were taken from the plate and extruded sections at the center of the product thickness, and specimens from the die forgings were taken just below the parting plane as shown in Fig. 49.

Duplicate specimens were precracked in tension, with a few drops of a 3.5 per cent NaCl solution being applied during the final stage of precracking. The specimens were then held for a period of 30 days in a laboratory environment with air at 80 F and 45 per cent relative humidity. A few drops of a 3.5 per cent NaCl solution were added to the crack three times during each working day, and crack growth was monitored with an ultrasonic detection device developed at these Laboratories. Pertinent stress-intensity calculations, as a function of crack opening displacement and crack length, were made using the formula developed by Hyatt[29].

SECTION IV

RESULTS OF TESTS

The results of the individual tensile, compressive, shear and bearing tests, the ratios among these test results, the statistical analyses of these ratios, the computed design values and the modulus of elasticity data are shown in Tables II through XXVIII. Tensile and compressive stress-strain curves for samples of five lots of each product are shown in Figs. 50 through 83.

The results of the tests of the 16-in. wide center-slotted panels (K_C) and the compact tension fracture toughness specimens (K_{Ic}) are shown in Tables XXIX through XXXIII and Figs. 94 through 93.

The results of the smooth and notched axial-stress fatigue tests, ambient-air environment, and modified Goodman diagrams are shown in Figs. 94 through 140; those of the smooth and notched specimens tested in a salt-fog environment are presented in Figs. 141 through 145. Either scatter bands or average curves are shown representing results of tests of comparable products of other aircraft alloys[12]. Table XXXIV lists the average corrosion-fatigue strengths at several lives for these tests, as well as those for comparable products[12].

The results of the fatigue crack-growth tests are presented in the form of da/dN versus ΔK plots in Figs. 146 through 160 and summarized in Table XXXV. The table includes rates listed for some of the tests of comparable specimens and products[12]. The raw crack-propagation data are presented in the Appendix (Tables LIV to LVII).

The results of the exfoliation tests are given in Tables XXXVI through XXXIX and Fig. 161. The results of accelerated and atmospheric stress-corrosion tests of smooth specimens are shown in Tables XL through L and Figs. 162 through 166. Results of tests of precracked specimens are shown in Tables LI through LIV and Figs. 167 through 172.

SECTION V

DISCUSSION OF RESULTS

GENERAL

The results of tests obtained in this investigation of the mechanical properties and corrosion characteristics of 7050 products provide evidence that this alloy is capable of developing the combination of high strength, high resistance to corrosion, and a high level of fracture toughness not available previously in other commercially produced aluminum alloy products. The data generally confirm that 7050 products produced by commercial practices develop the yield strength-corrosion resistance combination estimated from alloy development data. These properties, the development of design mechanical properties, the fracture toughness, and the fatigue characteristics are discussed in detail in the following sections.

A. Mechanical Properties

A.1. Tensile, Compressive, Shear and Bearing

A.1.1. Minimum and Maximum Tensile Properties

The methods used in establishing minimum and maximum tensile properties were discussed in Section I. The minimum tensile yield strengths for the various products appear reasonable with the possible exception that for certain extruded shapes it may be necessary to lower either the maximum and minimum strengths or the stress-corrosion capability based on stress-corrosion data for the 1.5x7.5-in. and similar shapes; this is discussed in detail in C2 of this section.

Analysis of subsequent tensile and stress-corrosion test results of plate and hand forgings tested for this contract and for quality control purposes indicated that the 9 ksi spread between minimum and maximum yield strengths was unnecessarily restrictive for thick sections. The stress-corrosion resistance of the thicker sections is such that higher maximum yield strengths can be tolerated. Consequently, the maximum yield strengths for 3.001 in. and thicker sections have been revised to 9 ksi higher than the minimum values of 3-in. thick plate and hand forgings.

As mentioned in Section I, the minimum tensile ultimate strengths of the 7050 products were estimated from the relationships of yield strength to ultimate strength for established commercial 7XXX alloy products. These relationships for the data obtained in this contract indicate that it may be necessary to adjust some

of the minimum tensile ultimate strengths. However, the amount of data obtained in this contract are not sufficient to justify such revisions; further supporting data from production lots are necessary before revisions can be made with any degree of confidence. For changes to be made in the minimum values for plate, hand forgings and die forgings, it would be necessary to revise AMS specifications. In the case of 7050-T73651 plate the yield-ultimate relationships for data from this contract and other plant production indicate revisions in the tensile ultimate strengths may not be necessary.

A.1.2. Design Mechanical Properties

The tensile properties used in computing the ratios among the tensile, compressive, shear and bearing properties for each product meet applicable specified minimum properties except those for some of the hand forgings and die forgings fabricated by Producer B, as noted in Section II, Materials; the ratios are shown in Tables VIII through XII.

The distribution of the ratios, number of ratios (n), mean ratios (\bar{R}), standard deviations ($\sigma_{\bar{R}}$) and the minimum ratios (Min. \bar{R}) are shown in Tables XIII through XVII. The statistical analyses of the ratio data were made in accordance with procedures outlined in Chapter 9 of MIL-HDBK-5, Guidelines for Presentation of Data[5]. A regression analysis of each group of ratios was made to determine whether the data showed a correlation with thickness; where such correlation was indicated, Min. \bar{R} values were selected which correspond with the lower limit of the confidence band around the regression line at the lower end of each respective thickness range. When no correlation was indicated, a single value of Min. \bar{R} was selected for all thicknesses. These values of Min. \bar{R} were used to establish the derived design value for the respective thickness ranges. In some instances variation in the ratios throughout the full thickness range indicated that the ratios should be broken down into sub-groups for analysis. This was done with the analysis of the bearing data for sheet, i.e., the ratios for 0.040 and 0.063-in. thick sheet and those for thicknesses greater than 0.063 in. were analyzed separately. The analyses of the shear and bearing ratios for plate were made on thicknesses equal to or less than 1.500 in. and greater than 1.500 in. The ratios for these two thickness ranges differ because of the change in the specification-test location, $T/2$ to $T/4$. This was not recognized in the previous Air Force Contract on 2014-T651, 2024-T351 and -T851, 7075-T651 and 7178-T651 plate[7]. Consequently, the Min. \bar{R} values used to develop derived minimum values presently shown in MIL-HDBK-5B, insofar as the approach to the analyses are concerned, are not comparable to those for 2124-T851[12], 7075-T7351[30] and 7050-T73651 plate.

Since no directions are shown for shear and bearing minimum design values and data were obtained for more than one direction in most products, the Students "t"-test and the "F"-test were applied to determine if there were significant differences in \bar{R} or $(\sigma \bar{R})^2$, respectively, for the different directions. Where no differences with direction were indicated, the ratios were combined for computation of the minimum ratios. The approach taken in combining ratios was to average the individual ratios for the two directions of each sample and then run the statistical analysis on the average ratios. By using this approach, the analysis was based on the number of samples (lots) tested and not the number of tests thus keeping "n" equal, or about equal, for each property of each product.

The derived Min. \bar{R} values used in computing the derived design values from the tensile properties of the respective thickness ranges of each product are summarized in Tables XVIII through XXI. The corresponding computed design values are shown in Tables XXII through XXVI. In preparing the design tables for the plate, hand forgings and die forgings the tensile properties in AMS specification 4050, 4108 and 4107, respectively, were used as basis-property "S" values. Since there are no such specifications for 7050 sheet and extruded shapes, Alcoa's tentative minimum tensile properties were used; therefore the design properties are shown as "tentative" in Tables XXII and XXVI. With the exception of extruded shapes, the derived compressive values for each direction are based on the corresponding directions of the tensile yield strengths. There are presently no long-transverse specified minimum tensile properties for extruded shapes, so all derived values are based on the longitudinal tensile properties. The shear and bearing minimum values for sheet, plate and hand forgings are based on the long-transverse tensile properties and for die forgings they are based on the longitudinal tensile properties.

The results of the tensile and compressive stress-strain tests and the modulus of elasticity tests are summarized in Table XXVII. Representative tensile stress-strain plots for determining modulus of elasticity from zero to 25 ksi are shown in Fig. 50, and tensile and compressive stress-strain curves are shown in Figs. 51 to 83. Average modulus values (Table XXVIII) for each product are as follows:

Product	Temper	Modulus, 10^3 ksi (0 to 25 ksi)	
		Tension	Compression
Sheet	T76	10.2	10.5
Plate	T73651	10.3	10.5
Hand Forgings	T73652	10.2	10.5
Die Forgings	T736	10.2	10.5
Extruded Shapes	T76511	10.3	10.6

The above values for the 7050 products are generally within 2 per cent of those of other 7XXX alloys. These average values for each product are, as with other alloys, 2 to 3 per cent higher in compression than in tension.

The long-transverse modulus values for plate, hand forgings and extruded shapes average 1 to 2 per cent higher than the corresponding longitudinal values; for the same products the short-transverse modulus values average 1 to 2 per cent lower than the long-transverse values. The longitudinal and long-transverse modulus values for sheet average about the same and for die forgings the longitudinal and short-transverse modulus values are about equal.

The proportional limit in tension is usually not much above 25 ksi for most 7XXX products, and in compression the proportional limit is appreciably higher than that in tension. Therefore, in the tests of 7050, the modulus tests in compression were run to only 25 ksi so that the stress range evaluated was the same as that in tension. However, most of the compressive stress-strain curves for 7050 showed that above 25 ksi the slope (modulus) increased noticeably up to the elastic limit. The amount of this change in slope appears to vary with grain direction and with product. However, this change in slope is directly related to the elastic limit of the product, the higher the elastic limit the greater the change in slope (modulus). In the longitudinal direction of hand forgings there is little or no increase in slope as the stress increased within the elastic range, but in the transverse directions (LT and ST) of the hand forgings and all three directions of plate, the slopes of the upper part of the elastic range average 2 per cent higher than those of the lower part (0 to 25 ksi). For sheet, die forgings and extruded shapes the differences in the slopes average about 2.5 to 3.5 per cent for the longitudinal direction and 4 to 4.5 per cent for the two transverse directions. This increase in slope is not unique for 7050; it has been observed in data for other high-strength alloys. The compressive modulus values have been adjusted upward as shown in Table XXVIII; these values are based on a stress range of zero to the elastic limit. The modulus values in the tables of design mechanical properties (Tables XXII through XXVI) have been adjusted accordingly.

A.2. Fracture Toughness

Sheet

The results of the tests of 16-in. wide center-slot fracture toughness specimens of the 7050-T76 sheet are shown in Table XXIX. On the basis of the net section stress, σ , not exceeding 0.8 times the tensile yield strength, all tests were valid.

Values of K_C versus tensile yield strength for the 0.063-in. 7050-T76 sheet are plotted in Fig. 84; data for other alloys of sheet tested without anti-buckling guides are shown for comparison. One sample of 7050-T76 sheet (411378) has yield strengths, averaging about 78 ksi, greater than and K_C values equivalent to those of 7075-T6. The second sample of 7050 (428884), has yield strengths, averaging 73 ksi, in the range of those of 7075-T6 and 7475-T61; for the L-T orientation the K_C values, with and without anti-buckling guides, are equal to or higher than those of 7475, and for the T-L orientation they are between those of 7075-T6 and 7475-T61. The larger differences in the K_C values of the two samples of 7050-T76 sheet appear to be a trade off in yield strength and toughness which is, at least partially, due to differences in Cu and Zn content (Table I).

Values of K_C versus thickness are plotted in Fig. 85 for specimens with initial slot-lengths of 4-in. The K_C values of the thick sheet average about 2/3 those of the thin sheet.

Crack-resistance data for the two samples of 0.063 in. sheet (S-411378 and 428884), tested with anti-buckling guides, (open symbols), are shown in Figs. 86 and 87 for the L-T and T-L orientations, respectively. These data characterize the resistance to fracture of the sheet during slow-crack growth. The R-curves for the two samples of sheet indicate large differences in their resistance to fracture, which can be partially attributed to the differences in the tensile yield strengths of the two samples.

The function of the anti-buckling guides in the fracture toughness tests of sheet was to prevent buckling. Buckling can lower not only the toughness, K_C , but also the resistance to slow-crack growth as demonstrated by the data for the L-T and T-L orientations (4 and 6-in. crack lengths) of the 0.063-in. sheet (S-428884) in Figs. 86 and 87, respectively.

The method recommended by C. E. Feddersen[22] for analyzing residual strength was used to establish various "damage" levels, K , from load-deformation curves obtained from tests of the 16-in. wide panels of 0.063-in. thick sheet (S-411378). The results of the evaluations of the data, assuming panels of infinite width, are presented in Figs. 88 (L-T) and 89 (T-L); the three damage levels established are: 1. "Threshold"-beginning of slow-crack growth, 2. "Apparent"-no crack growth at critical instability, and 3. "Critical"-initial crack length plus crack growth at critical instability. The data for the 0.063-in. sheet appear to fit Feddersen's analyses reasonably well, at least in the fracture-mechanics applicable range.

Plate, Hand Forgings, Die Forgings and Extruded Shapes

The results of the fracture toughness tests, K_{Ic} , are shown in Tables XXX through XXXIII. Only a few of the candidate K_Q values for plate and hand forgings are not strictly valid by all the criteria stipulated in ASTM E399. However, as indicated in the tables, most of these values are considered meaningful K_{Ic} values since they almost satisfy the validity criteria. Most of the K_{Ic} values for die forgings are invalid primarily because either the crack lengths were outside limits, crack curvatures exceeded limits or the stress intensities were too high. At times it was difficult to initiate and propagate the fatigue cracks in the die forging specimens, which accounts for the relatively high stress intensity and crack curvature. Almost one-third of the K_{Ic} values for extruded shapes were strictly invalid; most of the invalid tests were for the L-T specimens and were due to excessive yielding. Average values of valid K_{Ic} , including values considered meaningful, are as follows:

Product	Temper	K_{Ic} , ksi $\sqrt{\text{in.}}$		
		L-T (L-S)	T-L	S-L
Plate	T73651	32.2	27.8	24.2
Hand Forgings	T73652	31.9	20.9	19.0
Die Forgings	T736	31.9(37.7)	--	23.7
Extruded Shapes	T76511	31.6	23.0	18.6

K_{Ic} values versus tensile yield strengths of plate, hand forgings, die forgings and extruded shapes are plotted in Figs. 90 through 93, respectively. Both valid (solid symbols) and invalid (open symbols) fracture toughness data are shown. Generally, in Figs. 90, 91 and 93, bands are shown for conventional alloys which include data for 2014, 2024, 2219, 2618, 7075, 7079 and 7178[30]; data for 7049[12] and 7175[12] hand forgings are also represented in Fig. 91. Data for other die forgings in Fig. 92 are limited to 7075[30], 7049[12] and 7175[12]. Comparisons of 7050 with these other alloys are as follows:

Plate (Fig. 90): Generally, the K_{Ic} values for the 7050-T73651 are higher than those of conventional alloys of comparable yield strengths and thickness. The two data points (circles) within the band for the L-T orientation and the two data points (squares) within the band for the T-L orientation represent 6-in. plate while the bands for conventional alloys represent thinner plate. For the S-L orientation (triangles) all six samples of plate have K_{Ic} values above the band.

Hand Forgings (Fig. 91): The combination of toughness and strength for 7050-T73652 in the L-T orientation are about comparable to those of 7175-T736 and better than those of 7049-T73 and other conventional alloys. For the T-L and S-L orientations the combination of toughness and strength are in the same range as those of 7049-T73 and the conventional alloys, and a little lower than those of 7175-T736. The overall sizes of the 7050 forgings are generally larger than those of the other alloys.

Die Forgings (Fig. 92): The data for the L-T and S-L orientations of 7050-T736 are comparable to those of 7175 and 7049, but for the L-S orientation 7050 exhibits a higher strength-toughness combination than 7175 and 7049.

Extruded Shapes (Fig. 93): The toughness of 7050-T76511 is comparable to that of the conventional alloys while maintaining yield strengths at the higher-strength end of the range of conventional alloys.

A.3. Axial-Stress Fatigue

A.3.1. Ambient-Air Environment

The results of the axial-stress fatigue tests of smooth and notched ($K_t=3$) specimens are shown in Figs. 94 through 128. Curves have been drawn through data points for one sample each of sheet, plate, hand forgings and extruded shapes for stress ratios of +0.5, 0.0 and -1.0. For the purpose of establishing modified Goodman diagrams (Figs. 129 through 140) for these samples, the curves were adjusted slightly from those drawn through the points.

Comparisons of the fatigue data for 7050 products with curves or bands for sheet of other 7XXX alloys are as follows:

Sheet - Smooth and Notched Specimens (Figs. 97 and 101): 7050-T76 fatigue strengths are in the same range as those of single lots of 7075-T6, -T76 and -T73 sheet[30].

Plate - Smooth Specimens (Fig. 105 and 106): The band shown in Fig. 105 is for 1-1/4 to 1-3/4-in. thick 7075-T7351 plate[30]. Data for one of the samples of 1-in. thick 7050-T73651 plate (\bullet, \circ) fall a little below this band between 10^4 and 10^6 cycles, but the fatigue limits at 10^7 cycles fall just within the band. The data for the other sample of 1-in. thick plate (\blacksquare, \square) generally fall in the lower half of the band. For the 2-in. thick plate ($\blacktriangle, \triangle$) the data fall near the center of the band. No direct comparison can be made for the 4 and 6-in. plate, but their fatigue strengths are about as expected for their relatively large thicknesses. The data for the 1-in. and 2-in. 7050 plate and the data for the 1-1/4 to 1-3/4-in. plate from which the band was established for the 7075-T7351 plate are plotted in Fig. 106; also shown is the band for 7075-T73XXX products[30]. The fatigue strengths for the 2-in. 7050 plate are comparable to that of the 1-3/4-in. 7075-T7351 plate.

Plate - Notched Specimens (Fig. 110): The fatigue strengths of 7050-T73651 are within or above the band for 7075-T73XXX products[30]. The long-transverse strengths of the 7050 plate are generally higher than those for the longitudinal direction and, beyond 10^5 cycles, are equal to or higher than those for one lot of 7075-T7351 plate.

Hand Forgings - Smooth Specimens (Fig. 113): The longitudinal fatigue strengths of the 4-1/2x22x84-in. 7050-T73652 forging fall in the center and the long-transverse strengths for all five forgings fall in the lower half of the band for 7075-T73XXX products. The strengths are lower than the strengths of smaller sizes of 7175-T736 hand forgings[12], but appear to be about the same as those for 7049-T73 hand forgings[12].

Hand Forgings - Notched Specimens (Fig. 116): The data for 7050-T73652 forgings fall within or above the band for 7075-T73XXX products[30]. The strengths are in about the same range as those of 7049-T73 hand forgings[12] and a little lower than the strengths of 7175-T736 hand forgings[12].

Die Forgings - Smooth and Notched Specimens (Figs. 118 and 120): The fatigue strengths of 7050-T736 are comparable to those of 7075-T73[30], 7049-T73[12] and 7175-T736[12] die forgings.

Extruded Shapes - Smooth Specimens (Fig. 124): The fatigue strengths of 7050-T76511 shapes are about the same as those of 1.25 to 2.00-in. 7075-T7651X shapes[30]. As would be expected, the long-transverse strengths of the 3.5 and 5-in. thick shapes are lower than those of the thinner 7050 shapes; the longitudinal strengths, however, are higher than those of the thinner shapes.

Extruded Shapes - Notched Specimens (Fig. 128): The fatigue strengths of the 7050-T76511 shapes average a few ksi lower than those of the 1.43 and 2.0-in. 7075-T7651X shapes.

A study of the chemistry, fabrication practices and testing conditions has been made in an effort to explain the low fatigue strengths for the smooth specimens of the two samples of 1-in. plate (411050 and 411185) relative to the strengths of the 2-in. plate (411186). The only conclusions that could be made concerning the strength of sample 411185 was that this plate had a more recrystallized grain structure than that of the 2-in. plate. Limited evidence suggests that an unrecrystallized grain structure will be more resistant to fatigue damage than a recrystallized structure. As for the other sample of 1-in. plate (411050), which was unrecrystallized and has the lowest fatigue strengths,

the humidity at the time of testing may have been a factor; the humidity was higher when testing this sample as compared to that when the other two samples were tested. Values up to 105 grains of H_2O per pound of dry air were estimated. The same lot of 1-in. plate was tested by independent investigators where the absolute humidity values were in a range from 20 to 40 grains per pound[31]. Their results, adjusted from 0.1 to 0.0 stress ratio, were as much as 7 ksi higher than the 2-in. plate and at least 10 ksi higher than the corresponding sample of 1-in. plate (411050). These differences in strength appear too high to be attributed to differences in humidity alone; other variables such as test specimens and equipment probably contributed to the differences in fatigue properties obtained from the same lot.

A.3.2. Salt-Fog Environment

As is common in corrosion-fatigue tests, the salt-fog environment lowers the fatigue strength of all products (Table XXXIV and Figs. 141 to 145) with the effect of environment being greatest at the lower stresses where the exposure is longest and the effect of a notch is greatest. For the smooth specimens the failures of the specimens lasting more than a day (1,580,000 cycles) had their origins in corroded areas, and the lives were within the scatter band for mildly notched specimens, $K_t=3$ tested in air. The number of corrosion-fatigue tests was small, but the following trends can be noted for the various products:

7050-T76 Sheet - Smooth and Notched, $K_t=3$, Specimens (Fig. 141):

The 0.040-in. thick unnotched specimens have longer lives than the 0.125-in. thick specimens. This is in variance with the thought that comparable pits should have more effect on the thinner sheet, which was the finding for the 7475-T761 sheet[12]. The lives of notched specimens of the two sheet thicknesses are equivalent. For medium lives the fatigue results for the smooth and notched 7050-T76 specimens approximate the average curves for the 0.040-in. 7475-T761 sheet[12]. However, beyond 10^6 cycles, the 7050 specimens are affected by the environment to a greater degree.

7050-T73651 Plate - Smooth and Notched, $K_t=12$, Specimens (Fig. 142):

The corrosion-fatigue strengths of the two thicknesses of plate were equivalent. For smooth specimens of the 7050-T73651 plate, the fatigue strengths were in the same range as those of 2124-T851 plate[12] for lives up to 10^6 cycles. For notched specimens the strengths were below those of 2124-T851 plate.

7050-T73652 Hand Forgings - Smooth and Notched, $K_t=12$, Specimens (Fig. 143): No variations of corrosion-fatigue strengths with forging size were noted. The long-life fatigue strengths for the smooth 7050 specimens were lower than the average curves obtained in a previous test program for 7049-T73 and 7175-T736 hand forgings[12]. Similarly, the long-life data for the sharp-notched 7050 specimens were three to four ksi below the curve for 7049-T73 specimens.

7050-T76511 Extruded Shapes - Smooth and Notched, $K_t=12$, Specimens (Fig. 144): The corrosion fatigue lives for smooth and notched specimens of the 1.161 in. thick extruded shape were generally longer than those from 3.5x7.5-in. extruded bar.

Comparison of Products

Average curves representing the results of the tests of two sizes each of plate, forgings and extruded products are shown in Fig. 145 and summarized in Table XXXIV. Comparison with the fatigue strengths of the sheet would not be valid because of the different specimen types. The curves for the smooth specimens have somewhat different shapes but appear equivalent. However, for the notched specimens, the curve for the 7050-T73651 plate is consistently 1 to 2 ksi lower than those for the hand forgings and extruded shapes.

The failures of the smooth specimens which had lives greater than 1,000,000 cycles generally were directly related to corrosion. In most cases a corrosion pit served as the origin. However, the failure of one 0.125-in. sheet specimen started in an area of intergranular attack. There was no evidence of stress-corrosion attack.

B. Fatigue Crack-Propagation Tests

Some of the plots of crack-propagation rates show substantial scatter and overlap. Accordingly, differences in fatigue crack-growth rates of less than 50 per cent, in the summary Table XXXV, are not considered significant. There is generally good agreement between the da/dN - ΔK relationships for tests made at either low or high stress levels, with an overlapping ΔK range. The effects of orientation and environments are discussed below for the various products.

7050-T76 Sheet (Figs. 146 to 148):

- a. At the lower stress intensities the rates of fatigue crack propagation for T-L specimens of the 0.040 and 0.125-in. sheet were comparable in each atmosphere (Figs. 146 and 147). However, propagation at the higher stress intensities is somewhat slower in the thinner sheet.

- b. Equivalent propagation rates were obtained for T-L and L-T specimens (Figs. 147 and 148).
- c. The humid air doubles the rate of crack propagation over that of dry air. At the low stress intensities, propagation in the salt-fog environment is 50% faster than in humid air, but at the higher stress intensities equivalent propagation is obtained in the moist environments.
- d. The rates of propagation are comparable to those reported for 7475-T61 and T761 sheet (T-L specimens).

7050-T73651 Plate (Figs. 149 to 152):

- a. The rates of fatigue-crack propagation for T-L specimens of the 1-in. and 6-in. plate are comparable in each atmosphere (Figs. 149 and 150).
- b. The rates of propagation for the 6-in. plate (Figs. 150 to 152) do not differ greatly with specimen orientation.
- c. At the lower stress intensities, the rates of propagation in salt fog are about triple and those in humid air are about double those in dry air. At the higher stress intensity range of 12 ksi $\sqrt{\text{in.}}$ listed in Table XXXV, the rates in the two moist environments are both about double those in dry air.
- d. At the lower stress intensities, propagation rates of the 7050-T73651 specimens are slower than those reported for 2124-T851 plate in dry and humid air, but the rates are equivalent at the higher stress intensities (T-L specimens).

7050-T73652 Hand Forgings (Figs. 153 to 156):

- a. Crack propagation is generally faster for T-L specimens from the 7-1/2-in. thick forgings (Fig. 154) than for similar specimens from the 2-1/2-in. thick forgings (Fig. 153).
- b. For the 7-1/2-in. forgings at the higher stress intensities, the rates of propagation are faster for T-L and S-L specimens than for L-T specimens (Figs. 154, 156 and 155). Propagation is particularly fast for the S-L specimens at the higher stress intensities. The disparity between the resistance to crack propagation in the T-L and L-T specimens was such that the cracks of specimens LT-1 and LT-2 changed to vertical (longitudinal) propagation at a/W values of 0.55 to 0.60. Near the transition, propagation at midthickness lagged behind surface measurements rather than leading them as is

normal for specimens of this thickness. Accordingly, the width, W, of the remaining L-T specimens was reduced to produce specimens having an H/W ratio of 0.60 instead of 0.485. Comparison of the rates of propagation in Fig. 155 shows similar performance for Specimens LT-2 and LT-5 having the two H/W ratios. The rate of propagation showed a slower rate of increase as ΔK increases beyond 10 ksi $\sqrt{\text{in.}}$ for any of the longitudinal specimens.

- c. The salt-fog environment generally increases the rates of propagation significantly over those obtained in humid air, which are, in turn, 50 to 100 per cent faster than those obtained in dry air.
- d. At the higher stress intensities, propagation is faster (T-L specimens) for the 7050-T73652 forging than for the 7175-T736 forging and is comparable to 7049-T73. At low stress intensities the rates for both 7050-T73652 and 7175-T736 forgings are slower than those of 7049-T73[12].

7050-T76511 Extruded Shapes (Figs. 157 to 160):

- a. For the thinner shapes equivalent propagation is obtained in the longitudinal and long-transverse directions in the humid environments although, in dry air, propagation is somewhat slower for L-T than for T-L specimens (Figs. 157 and 158).
- b. At the higher stress intensities, the L-T specimens from the thick shapes (Fig. 159) experienced a slowing of propagation similar to that shown for the L-T specimens from the thick hand forging (Fig. 155). For those specimens having H/W = 0.485, vertical (longitudinal) propagation resulted. The data for the thinner extruded shape (Fig. 158) did not show any such trend so the rates for L-T specimens from the thinner shape are significantly faster at the higher stress intensities.
- c. Propagation is particularly fast for the S-L specimens (Fig. 160) at the higher stress intensities.
- d. The moist environments increased the propagation at lower ΔK by factors of 3 or more.

Comparison of Products

- a. In the thick extruded shapes and hand forgings, propagation at the higher stress intensities occurs significantly faster in the longitudinal direction than transverse directions; propagation is particularly fast for the S-L specimens. No such behavior was found for the plate.

- b. Generally, similar crack-propagation behavior is obtained from T-L specimens of the thinner products of the plate, hand forgings and extrusion.
- c. Except at the high stress intensities, propagation of all products in humid air and in salt fog is faster than in dry air by factors of about two and three, respectively.

C. Corrosion Characteristics

C.1. Resistance to Exfoliation

All products showed a high resistance to exfoliation in the "EXCO" immersion test. Specimens from the T736 die forgings showed no exfoliation, but minor exfoliation was detected on nearly all samples of T76 sheet, T73651 plate, T76511 extrusions and T73652 hand forgings, and these samples were rated in the E-A category, Fig. 45. One sample of T76 temper sheet was rated E-B. Fig. 161 illustrates the minor nature of the exfoliation attack in representative samples from the extruded and plate products.

Acidified salt spray tests also developed minor exfoliation of the degree E-A on selected samples of the extruded shapes and hand forgings, but no exfoliation was observed on the sheet and plate samples.

The development of minor exfoliation (degree E-A) for these materials in these aggressive accelerated test media is believed to be of no practical importance because it has been shown by outdoor tests in a seacoast atmosphere to be of little practical significance for similar products of 7075 and 7178 alloys[32,33]. It is expected that it will be shown to be equally insignificant for alloy 7050 products with the attainment of more lengthy atmospheric exposure.

At the time this report was prepared, tests of selected samples of sheet, plate and extruded shapes had progressed for a period of 23 months in the seacoast atmosphere at Point Judith, Rhode Island, with no evidence of exfoliation attack.

C.2. Resistance to Stress-Corrosion Cracking (SCC)-Smooth Specimens

Sheet (Tables XL and XLV): The sheet exhibited excellent resistance to SCC in the long-transverse direction for all thicknesses tested. No failures occurred in the accelerated tests even with the highly-stressed preformed specimens. The sheet has been equally resistant in both seacoast and industrial atmospheric tests of 606 and 660 days duration.

Plate (Tables XLI and XLVI): Longitudinal and long-transverse specimens showed good resistance to SCC. Long-time failures (101-182 days) did occur with specimens of either orientation, but microscopic examination revealed deep surface pitting and transgranular auxiliary cracking. Fig. 162, not typical of SCC.

Short-transverse specimens also showed a high resistance to SCC. No failures occurred at test stresses of 45, 35 and 25 ksi during the first 30 days of exposure, which is the period commonly used for SCC evaluations of high-strength aluminum alloys. Specimens stressed at 45 and 35 ksi did fail with continued exposure, and metallographic examination revealed pitting plus a mixture of intergranular, transgranular and mixed mode auxiliary cracking. It was concluded that fracture resulted primarily from intergranular SCC (Fig. 163).

No failures have occurred with short-transverse specimens stressed at 45, 35 and 25 ksi during exposures of 730 days in the seacoast atmosphere and 763 days in the industrial atmosphere.

Hand Forgings (Tables XLII and XLVII): Longitudinal and long-transverse specimens from hand forgings were also resistant to SCC. Failures which did occur were again associated with severe pitting and transgranular cracking not typical of SCC.

Short-transverse specimens showed a similar high resistance to SCC. No failures occurred during the first 30 days of exposure at stresses of 45, 35 and 25 ksi. Failures did occur at both 45 and 35 ksi with longer exposure, but microscopic examination of representative specimens revealed deep surface pitting and predominantly transgranular auxiliary cracking, (Fig. 164) not typical of SCC.

In seacoast atmospheric tests of 605 days duration, specimens from two of the five forgings tested have failed at a stress of 45 ksi. A single specimen has also failed at 25 ksi. Microscopic examination of these specimens showed that they resulted from severe localized corrosion and were not typical of SCC. No failures have occurred in industrial atmospheric tests of 665 days duration.

Die Forgings (Tables XLIII and XLVIII): Tests of a limited number of specimens confirmed the expected high resistance to SCC in the longitudinal direction. Failures did occur after long periods of exposure (124-182 days), but they too were not typical of SCC. No long-transverse specimens were tested.

Short-transverse specimens from the 7050-T736 die forgings showed some susceptibility to SCC in the alternate immersion test. Specimens from two of the ten forgings tested failed in 30 days or less at a stress of 45 ksi, but no failures occurred at stresses of 35 and 25 ksi during that period. With longer exposure most specimens failed at 45 ksi; numerous specimens failed at 35 ksi and two specimens failed at 25 ksi. Microscopic examination of representative test failures revealed a predominantly interfragmentary mode of auxiliary cracking indicative of SCC, Fig. 165.

After 605 days of exposure, tests in the seacoast atmosphere showed the same trends observed in the accelerated tests. SCC failures had occurred at 45 and 35 ksi with specimens from four of the ten forgings tested. In industrial atmospheric tests of 605 - 673 days duration, a single failure occurred at 45 ksi. Interfragmentary nature of auxiliary cracking in these atmospheric test failures is also shown in Fig. 165.

Extruded Shapes (Tables XLIV and XLIX): Longitudinal and long-transverse specimens showed a high resistance to SCC similar to the other products.

The short-transverse SCC performance of 7050-T76511 extruded shapes was expected to be similar to that of 7075-T76511 sections which are required to pass a 30 day test at 25 ksi. The shapes tested, with the exception of the 1.5x7.5-in. rectangular bar, performed as expected.

Short-transverse specimens from the 1.5x7.5-in. bar failed at a stress of 25 ksi in 30 days or less, and during longer exposure failures occurred at a stress of 20 ksi. The performance of this shape has also been shown to be substantially below that of other 7050 shapes in other test programs, and the results of one investigation[34] showed that this shape would have to be overaged to lower strengths than other 7050 shapes to develop the same resistance to SCC. Therefore, portions of the 1.5x7.5-in. bar were given additional aging at 325 F, and tests of short-transverse specimens from these re-aged samples showed that the material aged five additional hours at 325 F (20 hours total) demonstrated the expected resistance to SCC with only a slightly lowering of the mechanical properties. Pertinent data for this re-aged bar are listed below:

E.C. %IIACS	Longitudinal Properties			Applied Stress, ksi	SCC Data		
	TS ksi	YS ksi	El. %		F/N	Days	
40.5	83.7	77.0	13.6	55	3/3	5,	33, 34
				25	1/3	71,	2 OK 84

In seacoast atmospheric tests of 680 days duration, short-transverse specimens have shown the same trends observed in accelerated tests. SCC failures occurred at 45 and 35 ksi with each of the four sections tested, and two of the four sections failed at 25 ksi. No failures have occurred in industrial atmospheric tests of 721 days duration.

The interfragmentary character of auxiliary cracking in representative SCC test failures is shown in Fig. 166.

Summary of Exfoliation Tests and SCC Tests of Smooth Specimens

The corrosion performance of the various 7050 alloy products tested under this contract is compared with proposed corrosion targets in Table L.

In general, the various products showed the expected resistance both to exfoliation corrosion and stress-corrosion cracking. The lone exception was that the exfoliation resistance of 7050-T73651 plate was slightly less than that of 7075-T7351 plate, but the level of exfoliation in these plate samples was only of a degree E-A (ASTM G34-72), and is not considered significant.

The SCC performance of the 1.5x7.5-in. 7050-T76511 extruded shape indicated a need for a modified aging practice for sections of this type. Such modifications may result in revision of the tentative strength requirements; additional studies are currently being made under an extension of AFML Contract No. F33615-73-C-5015.

The resistance to general corrosion of these 7050 products in the highly aggressive 3.5 per cent NaCl alternate immersion environments is reflected by the reduction in tensile strength data for unstressed specimens in Tables XL through XLIV. A comparison of the 7050 hand forging data with those for similar forgings tested in a prior investigation[7] indicates that 7050 alloy is slightly less resistant to general corrosion in saline environments than other 7XXX alloys such as 7175 and 7049. The reduction in tensile strength for unstressed short-transverse specimens exposed 84 days to the 3.5 per cent NaCl alternate immersion test were as follows: 7175-T736, 14-24 per cent; 7049-T73, 24-32 per cent and 7050-T73652, 32-40 per cent. The reductions for 7050-T73651 plate approached, but were lower on the average than losses for short-transverse specimens of similar thickness plate of 2124-T851: 7050-T73651, 29-38 per cent; 2124-T851, 32-45 per cent. These data show the relative performance of small diameter specimens in a highly corrosive environment and cannot be directly related to the structural damage that might be expected with larger sections in service environments.

Stressed tension specimens that survived the 84 or 182 day alternated immersion exposure to the 3.5 per cent NaCl solution typically showed higher reductions in tensile strength than the unstressed specimens, particularly at high levels of applied stress (this was true also for the 7175-T736 and 7049-T73 forgings and for the other 7050 alloys products). A prior investigation of accelerated SCC test procedures[35] showed that such acceleration of corrosion losses under the application of stress can result from the presence of fine transgranular cracks emanating from surface pits. Such cracking is not considered to be indicative of susceptibility to SCC.

C.3. Resistance to SCC-Precracked Specimens

Tables LI through LIII list the plate, die forgings, and extruded shapes which were tested with short-transverse (S-L), tension precracked DCB specimens. Pertinent measurements and initial (K_{Ii}) and final (K_{If}) stress-intensity calculations are listed for the individual test specimens. The results of plane-strain fracture toughness tests of these materials are also shown.

Figure 167 illustrates the increase in crack length during exposure. Bands are shown to illustrate the range of results seen with various samples of each product; representative crack-growth curves for DCB specimens from 7079-T651, 7075-T651 and 7075-T7351 plate are also shown. Individual crack-growth curves for specimens from each of the 7050 products tested were shown in the tenth bi-monthly progress report.

A small amount of crack growth was noted in the specimens from the 7050-T73651 plate, slightly more than that seen in similar tests of 7075-T7351 plate, but considerably less than that incurred in tests of susceptible plate materials such as 7075-T651 and 7079-T651. Specimens from the 7050-T736 die forgings and 7050-T7651 extruded shapes experienced significantly greater amounts of crack growth than specimens from the plate. Although comparative data are not available for similar products of other alloys, it is considered significant that the greatest amount of crack growth seen in tests of either die forgings or extruded shapes was also somewhat less than that developed in the 7075-T651 and 7079-T651 plate.

Metallographic examination of representative specimens showed that the environmental crack growth in each product was the result of typical intergranular SCC. Figs. 168 through 170 illustrate the intergranular or interfragmentary nature of the SCC in the various products. No transgranular cracking was detected in the precracked specimens.

Crack-growth rate versus stress intensity data were also developed for each of the products tested. However, before considering these data, several pertinent observations must be made. Plastic bending occurred in the arms of most specimens during loading to pop-in. This bending generally was rather slight for most of the die forged and extruded specimens, and had little significant effect on the level of calculated stress-intensity; i.e., the K_{I1} values agreed well with the valid K_{Ic} values determined with compact tension specimens (Tables LII and LIII). The plasticity effects resulted in somewhat higher COD measurements for the plate samples, and the calculated stress-intensities were inordinately high (Table LI). Excessive stress-intensity values were also noted for certain die forged specimens due to the crack front deviating from the intended plane of fracture (Fig. 17); data for these die forged specimens were not utilized in the K-rate determinations.

"Plateau" velocities for the K-rate curves were determined by an arbitrary procedure to avoid the erratic shapes of crack-growth curves during the initiation of SCC, and the extraneous effect of corrosion product wedging. The total amount of crack growth in inches that occurred during the first 360 hours (15 days) was used to calculate the overall average growth rate for that period. This method was found to best represent the initial sustained crack growth which is considered to be one of the most significant features of the K-rate graphs.

The K_I rate data for the 7050 alloy products are illustrated in Fig. 172. Data for plate of alloys 7079-T651, 7075-T651 and 7075-T7351 again are shown for comparison. The data showed SCC "plateau" velocities for the products tested of:

Product	SCC Velocity, in./hr.	
	Range	Average
7050-T73651 Plate	7.5×10^{-5} to 3×10^{-4}	1.4×10^{-4}
7050-T736 Die Forgings	2.9×10^{-4} to 7.9×10^{-4}	4.5×10^{-4}
7050-T76511 Extruded Shapes	3.3×10^{-4} to 8.2×10^{-4}	5.8×10^{-4}

The data provide questionable values of K_{Ith} due to the high calculated stress intensities (non plane-strain) for the plate, and the fact that crack growth in specimens of the die forgings and extruded shapes did not reach an actual arrest due to corrosion product wedging. However, if the threshold stress

intensity is expressed as a ratio of final and initial calculated stress intensities for individual specimens

$$\frac{K_{If}}{K_{I1} \text{ (Pop-In)}}$$

the data provide estimated K_{Ith} values of:

<u>Product</u>	<u>Apparent K_{Ith}</u>
7050-T73651 Plate	81-95% K_{I1}
7050-T736 Die Forgings	58-80% K_{I1}
7050-T76511 Extruded Shapes	54-79% K_{I1}

Since the calculated K_{I1} values for the die forgings and extruded shapes showed good agreement with valid K_{Ic} values, these are considered to be reasonable approximations of K_{Ith} for those products. Although these estimated threshold stress intensities may be considered technically invalid (due to plasticity effects or curvature of the crack fronts), they are considered meaningful because there is ample evidence to show that the occurrence of SCC in aluminum alloy products does not require a plane-strain state of stress.

Supplemental Tests - Ring-Loaded Compact Tension Specimens

As a result of the experimental difficulties encountered in estimating threshold stress intensities by the "crack-arrest" procedure discussed above, a limited number of additional tests were conducted to check the apparent threshold stress intensity for a single lot of both the plate and extruded shapes by the "crack-initiation" procedure. Details of the latter procedure are given in a paper (36) presented at the 1974 Tri-Service Conference on Corrosion of Military Equipment and to be published in the proceedings of that conference.

Table LIV summarizes the results of ring-loaded SCC initiation tests of compact tension specimens (S-L orientation) from one lot of 4-in. thick plate and the 5.0x6.25-in. extruded shape. The specimens were fatigue precracked prior to loading, and the corrodent was a 3.5% NaCl solution applied dropwise three times daily except for weekends and holidays.

Applied stress intensity values were chosen to cover a range extending below the threshold values indicated by the DCB tests. Target values for specimens from the 7050-T73651 plate were therefore chosen at 98, 90, 85 and 75 per cent of the critical stress intensity. The calculated initial stress intensity (K_{Ii}) was generally higher than the target value, and the specimen loaded to the target value of 98% K_{Ic} actually exceeded the critical stress-intensity factor with attendant rapid failure. SEM examination of the fracture indicated that the failure had not been environmentally assisted. The remaining samples loaded to K_{Ii} values of 96, 88 and 79 per cent of K_{Ic} all showed small but significant amounts of crack growth which subsequent fractographic or metallographic examination showed to be intergranular and typical of SCC. The crack-growth rate was very slow in all specimens, and the specimen loaded to the K_{Ii} level of 79% K_{Ic} had not failed prior to removal from test at 3600 hours (150 days), indicating that this value of K_{Ii} was very close to the threshold stress intensity.

Specimens from the 7050-T76511 extruded section loaded to K_{Ii} values of 85, 75, 62 and 53 per cent of K_{Ic} all showed significant amounts of environmental crack growth which fractographic examination confirmed to be SCC. The SCC growth developed very slowly in the specimen loaded to 53% K_{Ic} , and failure did not occur until 2860 hours (120 days), suggesting that this specimen was loaded only slightly above the threshold stress intensity.

The apparent levels of K_{Ith} indicated by the ring load, "crack-initiation" tests are listed below together with the range of apparent K_{Ith} values estimated by the "crack-arrest" tests discussed in the previous section.

	Apparent K_{Ith}	
	Ring Load, Compact	Bolt Load, DCB
7050-T73651 Plate	78% K_{Ic}	81-95% K_{Ii}
7050-T76511 Extruded Shapes	50% K_{Ic}	54-79% K_{Ii}

There appears to be reasonable agreement between the threshold stress-intensity values estimated by the two test procedures.

SECTION VI

SUMMARY AND CONCLUSIONS

Alloy 7050, developed to have a combination of high strength, high resistance to corrosion and good fracture toughness, has been evaluated for mechanical properties and corrosion resistance from tests of T76 sheet, T73651 plate, T73652 hand forgings, T736 die forgings and T76511 extruded shapes produced by commercial practices. Based on these test results the following summary statements and conclusions have been made:

GENERAL

Commercially produced products of 7050 are capable of developing a combination of high strength, high resistance to corrosion and good fracture toughness that is more attractive than that of commercially established alloys.

A. Mechanical Properties

1. The minimum tensile yield strengths, tentatively selected on the basis of yield strength-corrosion resistance correlations, appear reasonable, with the possible exception that for certain extruded shapes it may be necessary to lower either the minimum and maximum yield strengths or the tentative stress-corrosion test capability based on the results of the corrosion tests.
2. The maximum yield strengths for plate and hand forgings greater than 3-in. in thickness have been increased on the basis of data obtained in this contract.
3. Based on yield strength-ultimate strength relationships, the minimum ultimate strengths, with the possible exception of those for plate, should be reevaluated when sufficient production data are obtained.
4. Design mechanical properties have been established using derived minimum ratios developed statistically from ratios among tensile, compressive, shear and bearing properties.
5. The modulus of elasticity values of 7050 products are generally within 2 per cent of those of other 7XXX alloys. Above 25 ksi the compressive modulus increases as the stress increases.

The average modulus values of each product are as follows:

<u>Product</u>	<u>Temper</u>	<u>0 to 25 ksi</u>		<u>0 to E.L.*</u>
		<u>Tension</u>	<u>Compression</u>	<u>Compression</u>
Sheet	T76	10.2	10.5	10.6
Plate	T73651	10.3	10.5	10.6
Hand Forgings	T73652	10.2	10.5	10.6
Die Forgings	T736	10.2	10.5	10.7
Extruded Shapes	T76511	10.3	10.6	10.7

* Stress range: 0 to elastic limit

6. Tensile and compressive stress-strain curves for five samples of each product, shown in Figs. 51 to 83, represent data suitable for use in establishing typical tensile and compressive stress-strain curves when sufficient production data are obtained to set typical tensile properties.

A.2. Fracture Toughness

1. No K_{Ic} data for tests made with anti-buckling guides are available for other sheet alloys for comparative purposes, but the strength-toughness combination indicated for 7050-T76 sheet is higher than most conventional alloys and can approach that of 7475 sheet. Tests of 0.063-in. sheet indicate that the strength and toughness levels obtained for 7050-T76 are dependent on composition.
2. Generally, 7050 plate, hand forgings, die forgings and extruded shapes exhibit a higher combination of strength and toughness, K_{Ic} , than established commercial alloys and tempers.

A.3. Axial-Stress Fatigue

1. The axial-stress fatigue strengths for smooth and notched, $K_t=3$, specimens of the 7050 products are in about the same general range as those for corresponding products of 7XXX alloys in the T7XXX tempers.
2. The fatigue strengths of 7050 plate, hand forgings and extruded shapes tested in salt fog are generally equivalent.
3. The effect of the salt-fog environment is greatest at the longer lives; at these lives the corrosion fatigue strengths of the 7050 products are somewhat lower than reported for 7475-T761 sheet, 2124-T851 plate and 7049-T73 and 7175-T736 hand forgings.

B. Fatigue-Crack Propagation

1. Similar crack propagation is generally obtained from T-L specimens of the thinner products of the plate, hand forgings and extruded shapes.
2. At the higher stress intensities, crack propagation occurs significantly faster in the longitudinal direction than in the transverse direction of the thick extruded shapes and hand forgings; no such behavior occurs in plate.
3. Propagation in humid air and in salt fog for the various products tends to be faster than in dry air by factors of about two and three, respectively.
4. The rates of propagation for T-L specimens are generally comparable to those reported earlier for tests of corresponding products of other aircraft alloys.

C. Corrosion Characteristics

1. All products showed a high order of resistance to exfoliation in the accelerated test media, generally showing either no exfoliation or only minor exfoliation (visual rating of degree E-A) which is not considered to be of practical significance in regard to service performance.
2. The sheet, plate and forged products all showed good resistance to stress-corrosion cracking, in line with the proposed targets for resistance to SCC (Table L).
3. The extruded shapes, with the exception of short-transverse specimens from the 1.5x7.5-in. rectangular bar, also demonstrated the SCC resistance expected of the product. Additional aging at 325 F (5 hours) developed the expected level of SCC resistance in the 1.5x7.5-in. rectangle with some decrease in mechanical properties.
4. Atmospheric test results have shown no SCC failures of specimens of sheet, plate and hand forgings in tests of 605 and 763 days duration. Seacoast atmospheric failures have occurred at stresses of 35 ksi with specimens from four of ten 7050-T736 die forgings tested, and at 25 ksi with specimens from two or four 7050-T76511 extruded shapes. In the industrial atmosphere only one specimen of a die forging has failed at 45 ksi.

5. Tests of precracked DCB specimens from the plate, die forgings and extruded shapes showed the same general trends seen with tests of smooth specimens, and would result in a similar ranking of the three products. Analyses of the crack-growth data resulted in the following estimates of average SCC "plateau" velocities and K_{Ith} .

Product	Crack Velocity <u>in./hr.</u>	K_{Ith} <u>%K_{I1}</u>	Ring-Loaded Compact
			K_{Ith} <u>%K_{Ic}</u>
7050-T73651 Plate	1×10^{-4}	81-95	78
7050-T736 Die Forgings	5×10^{-4}	58-80	--
7050-T76511 Extruded Shapes	6×10^{-4}	54-79	50

REFERENCES

1. J. T. Staley, "Investigation to Improve the Stress-Corrosion Resistance of Aluminum Aircraft Alloys Through Alloy Additions and Specialized Heat Treatment," Final Report under Naval Air Systems Command Contract N00019-68-C-0146, February 1969.
2. J. T. Staley, "Investigation to Develop a High-Strength, Stress-Corrosion Resistant Aluminum Aircraft Alloy," Final Report under Naval Air Systems Command Contract N00019-69-C-0292, January 1970.
3. J. T. Staley, "Investigation to Develop a High-Strength, Stress-Corrosion Resistant Naval Aircraft Alloy," Final Report under Naval Air Systems Command Contract N00019-70-C-0118, November 1970.
4. J. T. Staley, "Further Development of Aluminum Alloy X7050", Final Report under Naval Air Systems Command Contract N00019-71-C-0131, May 1972.
5. Military Standardization Handbook, Metallic Materials and Elements for Aerospace Vehicle Structures, Volume 1, September 1, 1971.
6. "Standard Methods of Verification of Testing Machines, E4-72", 1973 Book of ASTM Standards, Part 31.
7. G. W. Stickley and D. J. Brownhill, "Mechanical Properties of Stress-Relieved Stretched Aluminum Alloy Plate", Technical Report AFML-TDR-64-105, May 1964.
8. J. G. Kaufman, G. E. Nordmark and B. W. Lifka, "Fracture Toughness, Fatigue and Corrosion Characteristics of 7075-T651, 7075-T7351 and 7079-T651 Aluminum Alloys", Technical Report AFML-TR-65-170, May 1965.
9. J. G. Kaufman, G. E. Nordmark and B. W. Lifka, "Fracture Toughness, Fatigue and Corrosion Characteristics of 2020-T651, 2024-T851, 2219-T851 and 7001-T75 Aluminum Alloys", Technical Report AFML-TR-66-291, September 1966.

10. D. J. Brownhill, R. E. Davies and D. O. Sprowls, "Mechanical Properties, Including Fracture Toughness and Fatigue, and Resistance to Stress Corrosion Cracking, of Stress-Relieved Stretched Aluminum Alloy Extrusions", Technical Report AFML-TR-68-34, February 1968.
11. D. J. Brownhill, C. F. Babilon, G. E. Nordmark and D. O. Sprowls, "Mechanical Properties Including Fracture Toughness and Fatigue, Corrosion Characteristics and Fatigue Crack Propagation Rates of Stress-Relieved Aluminum Alloy Hand Forgings", Technical Report AFML-TR-70-10, February 1970.
12. C. F. Babilon, R. H. Wygonik, G. E. Nordmark and B. W. Lifka, "Mechanical Properties, Fracture Toughness, Fatigue, Environmental Fatigue Crack Growth Rates and Corrosion Characteristics of High Toughness Aluminum Alloy Forgings, Sheet and Plate", Technical Report AFML-TR-73-83, April 1973.
13. "Standard Methods of Tension Testing Wrought and Cast Aluminum and Magnesium Alloy Products, B557-73", 1974 Book of ASTM Standards, Part 7.
14. "Standard Methods of Tension Testing of Metallic Materials, E8-69", 1973 Book of ASTM Standards, Part 31.
15. "Standard Methods of Compression Testing of Metallic Materials, E9-70", 1973 Book of ASTM Standards, Part 31.
16. R. E. Davies and J. G. Kaufman, "Effects of Test Method and Specimen Orientation on Shear Strengths of Aluminum Alloys", ASTM Proceedings, Vol. 64, 1964, pp. 999-1010.
17. "Standard Method for Pin-Type Bearing Test of Metallic Materials, E238-68", 1973 Book of ASTM Standards, Part 31.
18. "Standard Method for Determination of Young's Modulus at Room Temperature, E111-61", 1973 Book of ASTM Standards, Part 31.
19. "Standard Method of Verification and Classification of Extensometers, E83-67", 1973 Book of ASTM Standards, Part 31.
20. J. G. Kaufman and A. H. Knoll, "Kahn-Type Tear Tests and Crack Toughness of Aluminum Sheet," Materials Research and Standards, Vol. 4, No. 4, April 1964, pp. 151-155.

21. "Fracture Testing of High Strength Sheet Materials", ASTM Bulletin No. 243, January 1960, p. 29; also No. 244, February 1960, p. 18.
22. C. E. Feddersen, "Evaluation and Prediction of the Residual Strength of Center-Cracked Tension Panels," Battelle Memorial Institute, Columbus, Ohio (presented at the ASTM Annual Meeting, Toronto, Canada, June 1970).
23. "Standard Method of Test for Plane-Strain Fracture Toughness of Metallic Materials, E399-72", 1973 Book of ASTM Standards, Part 31.
24. W. F. Brown, Jr. and J. E. Srawley, "Plane Strain Crack Toughness Testing of High Strength Metallic Materials", ASTM STP No. 410, 1967.
25. W. G. Clark, Jr., ASTM E24.4, "Fatigue Crack Growth Rate Testing Round Robin Program", Task Group Progress Report No. 3, May 14, 1971.
26. "Standard Method of Test for Exfoliation Corrosion Susceptibility in 7XXX Series Copper-Containing Aluminum Alloys (EXCO Tests)", G34-72, 1973 Book of ASTM Standards, Part 31.
27. B. W. Lifka and D. O. Sprowls, "An Improved Exfoliation Test for Aluminum Alloys," Corrosion, Vol. 22, No. 1, 1966, pp. 7-15.
28. "Federal Test Method Standard No. 151b", November 1967.
29. M. V. Hyatt, "Use of Precracked Specimens in Stress-Corrosion Testing of High-Strength Aluminum Alloy", Corrosion, Vol. 26, No. 11, November 1970, pp 487-503.
30. Unpublished Data, Alcoa Laboratories.
31. R. E. Jones and K. A. Fudge, "Engineering Design Data For Aluminum Alloy 7050-T73651 Plate", Technical Report AFML-TR-73-269, November 1973.
32. D. O. Sprowls and B. W. Lifka, "Relationship of Accelerated Test Methods for Exfoliation Resistance in 7XXX Series With Exposure to a Seacoast Atmosphere", Corrosion in Natural Environments, ASTM STP558, 1974.

33. D. O. Sprowls, T. J. Summerson and F. E. Loftin, "Exfoliation Corrosion Testing of 7075 and 7178 Aluminum Alloys - Interim Report on Atmospheric Exposure Tests", Corrosion in Natural Environments, ASTM STP558, 1974.
34. "Production of Extrusions From Aluminum Alloy 7050", AFML Contract No. F33615-73-C-5015, Interim Engineering Progress Report, December 14, 1973.
35. Lifka, B. W., Sprowls, D. O. and Kelsey, R. A., "Investigation of Smooth Specimen SCC Test Procedures-Variations in Environment, Specimen Size, Stressing Frame, and Stress State," Final Report of Government Contract NAS 8-21487 - Part II, August 1972.
36. J. G. Kaufman, J. W. Coursen and D. O. Sprowls, "An Automated Method for Evaluating Resistance to Stress-Corrosion Cracking with Ring-Loaded Precracked Specimens."

000000
000000



Fig. 1 Etched Cross Sections of 7050-T73651 Plate,
0.500-in. Thick.

Fig. 1



Fig. 2 Etched Cross Sections of 7050-T73651 Plate,
1.000-in. Thick.

Fig. 2

00000002
00000000




Fig. 3 Etched Cross Section of 7050-T73651 Plate,
2.000-in. Thick.

0000804
0000805



Fig. 4 Etched Cross Sections of 7050-T73651 Plate,
4.000-in. Thick.

Fig. 4


000000
000000




Fig. 5 Etched Cross Sections of 7050-T73651 Plate,
6.000-in. Thick.

Fig. 5

00000000
00000000



2 x 8 x 72 in.



2-1/2 x 22 x 60 in.
Fig. 6 Etched Cross Sections of 7050-T73652 Hand Forgings

Fig. 6

0000075
0000075



3-1/2 x 22 x 84 in.



3-1/2 x 14 x 74 in.

Fig. 7 Etched Cross Sections of '050-T73652 Hand Forgings

Fig. 7



4-1/2 x 22 x 84 in.




4-1/2 x 22 x 84 in.

Fig. 8 Etched Cross Sections of 7050-T73652 Hand Forgings



5-1/2 x 22 x 60 in.



5-1/2 x 22 x 45 in.


Fig. 9 Etched Cross Sections of 7050-T73652 Hand Forgings



7-1/2 x 22 x 42 in.

Fig. 10 Etched Cross Section of 7050-T73652 Hand Forging

Fig. 10



7-1/2 x 22 x 42 in.

Fig. 11 Etched Cross Section of 7050-T73652 Hand Forging

Fig. 11




Fig. 12 Etched Cross Section of 7050-T736 Die Forging
(Die No. 2177)

000004
000005

Fig. 12




Fig. 13 Etched Cross Section of 7050-T736 Die Forging (Die No. 9078)

0000000
0000000



Fig. 14 Etched Cross Section of 7050-T736 Die Forging (Die No. 15789)




Fig. 15 Etched Cross Section of 7050-T736 Die Forging (Die No. 17975)

tion
mens




Fig. 16 Etched Cross Section of 7050-T736 Die Forging (Die No. 17944)



Fig. 17 Etched Cross Section of 7050-T736 Die Forging (Die No. 1364)

0002259
0009873




Fig. 18 Etched Cross Section of 7050-T736 Die Forging (Die No. 8457)




FIG. 19 Etched Cross Section of 7050-T736 Die Forging (Die No. 4736)

0002903
0004867




Fig. 20 Etched Cross Section of 7050-T736 Die Forging (Die No. 12767)

Fig. 20


00000000
00000000



Fig. 21 Etched Cross Section of 7050-T736 Die Forging (Die No. 16392)



0.187-in. Thick x 22.56-in. Wide (Die No. 86366)




0.402-in. Thick x 16.56-in. Wide (Die No. 191282)




0.665-in. Thick x 16.9-in. Wide (Die No. 213592)

Fig. 22 Etched Cross Sections of 7050-T76511 Extruded Shapes




0.841-in. Thick x 17.18-in. Wide (Die No. 53717)




1.161-in. Thick x 17.35 in. Wide (Die No. 231372)

Fig. 23 Etched Cross Sections of 7050-T76511 Extruded Shapes



1.5-in. Thick x 7.5-in. Wide



2-in. Thick x 8-in. Wide

Fig. 24 Etched Cross Sections of 7050-T76511 Extruded Shapes





Fig. 25 Etched Cross Section of 7050-T76511
Extruded Rectangle, 3.5 x 7.5 in.

0006311




411280

Fig. 26 Etched Cross Section of 7050-T76511
Extruded Rectangle, 4.0 x 8.0 in.


Fig. 26



Fig. 27 Etched Cross Section of 7050-T76511
Extruded Rectangle, 5.0 x 6.25 in.




SHEET-TYPE SPECIMEN



Diameter, in.		Gage Length, in.	Reduced-Section Length, in.	Diameter, (D) in.
$d1$	$d2$			
0.500 ± 0.005	$d1 \pm 0.005$	2.0	3-1/8	3/4
0.357 ± 0.004	$d1 \pm 0.004$	1.4	2-15/64	17/32
0.250 ± 0.003	$d1 \pm 0.003$	1.0	1-9/16	3/8
0.160 ± 0.002	$d1 \pm 0.002$	0.64	1	15/64
0.125 ± 0.001	$d1 \pm 0.001$	0.50	25/32	3/16

ROUND SPECIMENS

Fig. 28 General Dimensions of Tensile Specimens



* Strain-gage length for specimens used in stress-strain tests: 0.062-in.

SHEET-TYPE COMPRESSIVE SPECIMEN*




ROUND COMPRESSIVE SPECIMEN	
Nominal Diameter, in.	Diameter, (D) in.
3/8	0.3730
	0.3720
1/4	0.2490
	0.2480
3/16	0.1865
	0.1855

ROUND SHEAR SPECIMEN


Fig. 29 General Dimensions of Compressive and Shear Specimens

Fig. 29



Specimen Thickness, (T) in.	Pin Hole Diameter, (D) in.	Specimen Width, (W) in.
0.125 to 0.249	0.500	2.0
0.090 to 0.094	0.375	1.5
0.063	0.250	1.5
0.040	0.160	1.0

Fig. 30 General Dimensions of Bearing Specimens



Diameter, in.	Strain-Gage Length, in.		Reduced-Section Length, in.
	D1	D2	
0.500 ± 0.003	3/4	0.062, 0.125	3
0.438 ± 0.003	5/8	0.062	2-7/8
0.438 ± 0.003	5/8	0.062	1-7/8
0.375 ± 0.003	9/16	0.062	2-3/4
0.357 ± 0.003	9/16	0.062	2-3/4
0.312 ± 0.002	1/2	0.062	1-5/8

ROUND SPECIMENS

Fig. 31 General Dimensions of Tensile Specimens
For Modulus and Stress-Strain Tests




Fig. 32 General Dimensions of Center-Slotted
Fracture Toughness Panels

Fig. 32

Reproduced from
best available copy.




Fig. 33 Setup for Testing 16-in. Wide Center-Slot Fracture Toughness Specimens

Fig. 33



Anti-buckling Guide and Strain Gages



Improved Anti-Buckling Guide

Fig. 34 Setups for Testing 16-in. Wide Center-Slot
Fracture Toughness Specimens With
Anti-buckling Guides.

0005142
0000057

Fig. 34




Fig. 36 FRACTURE-TOUGHNESS SPECIMEN ORIENTATIONS

Fig. 36



Fig. 37 Setup for Fatigue Precracking of
Compact Tension Fracture Toughness Specimens

Fig. 37






Fig. 38 Setup for Testing Compact Tension Fracture Toughness Specimens

PGD0083

Fig. 38



SMOOTH SPECIMEN*




NOTCHED SPECIMEN* (K_t = 3)


* Thickness ≤ 0.125 in.

Fig. 39 General Dimensions of Smooth and Notched Sheet-Type Axial-Stress Fatigue Specimens

Fig. 39



SMOOTH SPECIMEN



Notch-Tip Radius, R_t
 †Ambient Air *Salt Fog
 $R_t = 0.013$ $R_t \leq 0.0005$
 $K_t = 3$ $K_t \geq 12$

NOTCHED SPECIMEN

Note: All dimensions
in inches

Fig. 40 Dimensions of Smooth and Notched
Axial-Stress Fatigue Specimens

Fig. 40





Fig. 41 Crack Propagation Specimen for Sheet



a = crack length

Special Dimensions - Inches

B	2H	W	A	D	d	W_1	H/W
1.00	3.72	3.805	1.650	0.75	1.151	4.80	0.485
1.00	3.72	3.100	1.650	0.75	1.151	4.10	0.6

Fig. 42 Dimensions for Compact Tension Fatigue Crack-Propagation Specimen

Fig. 42



Fig. 43 Environmental Chamber for Fatigue-Crack Propagation
Tests of Sheet.

7210059

Fig. 43




Fig. 44 Compact Tension Crack Propagation Specimen in Fatigue Machine

Fig. 44




Fig. 45 - Four Degrees of Severity of Exfoliation Corrosion
Per ASTM Standard Method Test G34-72.




Fig. 46 - Preformed Blank and Sheet Tensile Specimen End Loaded
For Corrosion Tests.



Mag: 1/2X

Fig. 47a 1/8-in. Diameter Tensile Specimen, Various Parts of the Stressing Frame and Final Stressed Assembly for Stress Corrosion Tests.



Mag: 1/5X

Fig. 47b Synchronous Loading Device Used to Stress Specimens. Stressed Assembly and One Assembled Finger Tight Ready For Stressing Are Shown to the Left.

PEB024
PAW075

Fig. 47a
Fig. 47b




Fig. 48 Configuration of Double Cantilever Beam (DCB) Specimen Used for SCC Tests

Fig. 48




Fig. 49 Sketches Showing Location of DCB Specimens Used for SCC Tests of Dile Potting

Fig. 49




Fig. 50 Representative Stress-Strain Plots Obtained with an X-Y Recorder For Determining Modulus of Elasticity

Fig. 50




Fig. 51




Fig. 52 Tensile and Compressive Stress-Strain Curves
for 0.063-in. Thick 7050-T76 Sheet (S-411378)

Fig. 52




Fig. 5j Tensile and Compressive Stress-Strain Curves
for 0.090-in. Thick 7050-T76 Sheet (S-411182)

Fig. 53




Fig. 54 Tensile and Compressive Stress-Strain Curves for 0.125-in. Thick 7050-T76 Sheet (S-411212)

Fig. 54




Fig. 55 Tensile and Compressive Stress-Strain Curves
for 0.249-in. Thick 7050-T76 Sheet (S-411909)

Fig. 55




Fig. 56 Tensile and Compressive Stress-Strain Curves for 1/2-in. Thick 7050-T73651 Plate (S-411104)

Fig. 56




Fig. 57 Tensile and Compressive Stress-Strain Curves for 1-in. Thick 7050-T73651 Plate (S-41115)

Fig. 57




Fig. 58 Tensile and Compressive Stress-Strain Curves
for 2-in. Thick 7050-T73651 Plate (S-411186)

Fig. 58




Fig. 59




Fig. 60




Fig. 61 Tensile and Compressive Stress-Strain Curves for 6-in. Thick 7050-T73651 Plate (S-411300)

Fig. 61




Fig. 62 Tensile and Compressive Stress-Strain Curves for 6-in. Thick 7050-T73651 Plate (S-411300)

Fig. 62




Fig. 63 Tensile and Compressive Stress-Strain Curves for 2-1/2-in. Thick 7050-F7J52 Hand Forging (S-311229)

Fig. 63




Fig. 64 Tensile and Compressive Stress-Strain Curves
for 3-1/2-in. Thick 7050-F73652 Hand Forging (S-311352)

Fig. 64




Fig. 65




Fig. 66 Tensile and Compressive Stress-Strain Curves (S-411230)
for 4-1/2-in. Thick 7050-T7352 Aluminum Forging

Fig. 66




Fig. 67




Fig. 68




Fig. 69




Fig. 70




Fig. 71




Fig. 72 Tensile and Compressive Stress-Strain Curves for 0.1-in. Thick 7050-F736 AlSi Purglas. Doc No. 9078 (8-31133)

Fig. 72




Fig. 73 Tensile and Compressive Stress-Strain Curves for 1.1-in. Thick 7050-F736 Dia Forging. Dia No. 15709 (2-411351)

Fig. 73




Fig. 74 Tensile and Compressive Stress-Strain Curves for 7050-T736 Die Forging, Die No. 12767 (S-411233)

Fig. 74




Fig. 75
Tensile and Compressive Stress-Strain Curves
for 5.5-in. Thick 7050-T736 Al-Li Forging,
Die No. 8457 (S-411332)

Fig. 75




Fig. 76




Fig. 77 Tensile and Compressive Stress-Strain Curves
For 0.187-in. Thick 7050-776511 Extruded Shape,
Dir. No. 66366 (S-11128)

Fig. 77




Fig. 78




Fig. 79




Fig. 80 Tensile and Compressive Stress-Strain Curves for 3-1/2x1-1/2-in. 7050-T76511 Extruded Rectangle (S-All285)




Fig. 81




Fig. 82 Tensile and Compressive Stress-Strain Curves for 5052-H14-Al. 1050-77551 Extended Rectangle (S-411286)

Fig. 82




Fig. 83




Fig. 84 K_c vs. Tensile Yield Strength of 0.063-in. Sheet

Fig. 84




Fig. 85

Fig. 85




Fig. 86

Fig. 86





Fig. 87


Fig. 87



Plots of Threshold, Apparent
and Critical Instability of
7050-T76 Sheet, 0.063-in.
16-in. Wide Panels
L-T Orientation
(MASC Contract No.
W00019-72-C-0512)

Fig. 88

Fig. 88



Plots of Threshold, Apparent
and Critical Instability of
7050-T76 Sheet, 0.063-in.
16-in. Wide Panels
T-L Orientation
(MASC Contract No.
H00019-72-C-0512)

Fig. 89

Fig. 89




Fig. 90 K_{Ic} Vs. Tensile Yield Strength of
7050-T73551 Plate, Thickness: 1/2 to 6 in.

Fig. 90




Fig. 91 $K_t C$ Vs. Tensile Yield Strength of
7050-T73652 Band Forgings,
Thickness: 2 to 7-1/2 In.

Fig. 91




Fig. 92 K_{Ic} Vs. Tensile Yield Strength of 7050-T736 Die Forgings, Thickness: 0.6 to 6.1 in.

Fig. 92




Fig. 93 K_{Ic} Vs. Tensile Yield Strength of
 7050-T76511 Extruded Shapes
 Thickness: 0.4 to 5 in.

Fig. 93




Fig. 94

Fig. 94





Fig. 95

Fig. 95






Fig. 97




Fig. 98




Fig. 100




Fig. 101

Fig. 101




Fig. 102

Fig. 102




Fig. 103




Fig. 104

Fig. 104




Fig. 105

Fig. 105




Fig. 106




Fig. 107





Fig. 108





-172-



Fig. 112




Fig. 113

Fig. 113




Fig. 115




Fig. 116

Fig. 116




Fig. 117




Fig. 119




Fig. 120




Fig. 121




Fig. 122

Fig. 122




Fig. 123

Fig. 123




Fig. 12a

Axial-Stress Fatigue Data
for Matched Specimens of
7050-T7651X Extruded Bar-25
1.161 in. Thick (Die 231372)

(KASC Contract No.
W00019-72-C-0512)
M.T. No. 061272-A

Part No. REP. Rev. 1.0.2.2f. Date: 11-11-72





FIG. 225




Fig. 125





Fig. 127

Fig. 127



Plg. 128




Fig. 129

Fig. 129




Fig. 131

Fig. 131




Fig. 132

Fig. 133




Fig. 133

Fig. 133




Fig. 134




Fig. 135

Fig. 135




Fig. 136

Fig. 136




Fig. 137

Fig. 137




Fig. 139

Fig. 139





Fig. 140

Fig. 140






Fig. 142

Fig. 142




Fig. 145

Fig. 145




Fig. 146 **FATIGUE CRACK-GROWTH DATA FOR
 0.040-IN. 7050-T76 SHEET.
 T-L ORIENTATION**

Fig. 146




Fig. 147 FATIGUE CRACK-GROWTH DATA FOR
0.125-IN. 7050-T76 SHEET.
T-L ORIENTATION

Fig. 147




FIG. 148 FATIGUE CRACK-GROWTH DATA FOR
 0.125-IN. 7050-T76 SHEET.
 L-T ORIENTATION

Fig. 148




Fig. 149 **FATIGUE CRACK-GROWTH DATA FOR
1-IN. 7050-T73651 PLATE.
T-L ORIENTATION**

Fig. 149




Fig. 150 **FATIGUE CRACK-GROWTH DATA FOR
6-IN. 7050-T73651 PLATE.
T-L ORIENTATION**

Fig. 150




Fig. 151 **FATIGUE CRACK-GROWTH DATA FOR
6-IN. 7050-T73651 PLATE.
L-T ORIENTATION**

Fig. 151




Fig. 152 FATIGUE CRACK-GROWTH DATA FOR
6-IN. 7050-T73651 PLATE.
S-L ORIENTATION

Fig. 152




Fig. 153 **FATIGUE CRACK-GROWTH DATA FOR
 2-1/2 x 22-IN. 7050-T73652 HAND
 FORGING T-L ORIENTATION**

Fig. 153




Fig. 154 **FATIGUE CRACK-GROWTH DATA FOR
7-1/2 x 22-IN. 7050-T73652 HAND
FORGING. T-L ORIENTATION**

Fig. 154




Fig. 155 FATIGUE CRACK-GROWTH DATA FOR
7-1/2 x 22-IN. 7050-T73652 HAND
FORGING. L-T ORIENTATION

Fig. 155




Fig. 156 **FATIGUE CRACK-GROWTH DATA FOR
7-1/2 x 22-IN. 7050-T73652 HAND
FORGING. S-L ORIENTATION**

Fig. 156




Fig. 157 **FATIGUE CRACK-GROWTH DATA FOR
1.161-IN. 7050-T76511 EXTRUDED SHAPE.
T-L ORIENTATION**

Fig. 157




Fig. 158 **FATIGUE CRACK-GROWTH DATA FOR
1.161-IN. 7050-T76511 EXTRUDED SHAPE.
L-T ORIENTATION**

Fig. 158




FIG. 159 **FATIGUE CRACK-GROWTH DATA FOR
 5 x 6-1/4-IN. 7050-T76511 EXTRUSION
 L-T ORIENTATION**

Fig. 159





Fig. 160 **FATIGUE CRACK-GROWTH DATA FOR
5 x 6-1/4 -IN. 7050-T76511 EXTRUSION
S-L ORIENTATION**

Fig. 160



S. No. 411290-A

Mag. 225X

Longitudinal Section at T/10 Plane of 0.665-in. Thick
7050-T76511 Extruded Section.



S. No. 411186-A

Mag. 225X

Longitudinal Section at T/10 Plane of 2.00-in. Thick
7050-T73651 Plate

Fig. 161 Photomicrographs Illustrating Minor Exfoliation Attack
in Alloy 7050 Products Exposed 48 Hours to "EXCO" Test.
Note the corrosion is primarily an undermining pitting
type of attack.

Fig. 161



S. No. 411187-L5

Mag. 100X

Longitudinal Specimen

Stressed 75% Y.S. - Failed 153 Days



S. No. 411187-T3

Mag. 100X

Long-Transverse Specimen

Stressed 75% Y.S. - Failed 112 Days

Fig. 162 Photomicrographs Illustrating Severe Pitting and Auxiliary Transgranular Cracking in Longitudinal and Long-Transverse Specimens from 4" Thick 7050-T73651 Plate. Corrosion and Cracking are Typical of that Seen with All Plate Samples.



S. No. 410778-N5

Mag. 100X

2-in. Thick

Stressed 45 ksi - Failed 76 Days



S. No. 411187-N4

Mag. 100X


4-in. Thick

Stressed 45 ksi - Failed 73 Days

Fig. 163 Photomicrographs Illustrating the Mixed-Mode Nature of Auxiliary Cracking in Short-Transverse Specimens From 7050-T73651 Plate.




S. No. 411354-N5 Mag. 75X



Mag. 400X

2 x 8-in. Forging, Stressed 45 ksi - Failed 82 Days



S. No. 411353-N5 Mag. 75X



Mag. 400X

5.5 x 22-in. Forging, Stressed 45 ksi - Failed 71 Days

Fig. 164 Photomicrographs Illustrating the Predominantly Transgranular Nature of Auxiliary Cracking in Short-Transverse Specimens From 7050-T73652 Hand Forgings

Fig. 164



S. No. 411332-N7 Mag. 75X



S. No. 411233-N3 Mag. 75X

Stressed 35 ksi - Failed 53 Days Stressed 45 ksi - Failed 42 Days
3.5% NaCl Alternate Immersion



S. No. 411332-N25 Mag. 75X
Stressed 45 ksi - Failed 139 Days
Seacoast Atmosphere



S. No. 411233-N15 Mag. 75X
Stressed 45 ksi - Failed 329 Days
Industrial Atmosphere

Fig. 165 Photomicrographs Illustrating the Predominantly Interfragmentary Nature of Auxiliary Cracking in Short-Transverse Specimens from 7050-T736 Die Forgings Exposed to Accelerated and Atmospheric Environments.



S. No. 411284-N11 Mag. 75X



Mag. 225X

1.5 x 7.5-in. Rectangle, Stressed 25 ksi - Failed 10 Days



S. No. 411285-N3 Mag. 75X



Mag. 225X

3.5 x 7.5-in. Rectangle, Stressed 45 ksi - Failed 12 Days

Fig. 166 Photomicrographs Illustrating the Interfragmentary Nature of Auxiliary Cracking in Short-Transverse Specimens from 7050-T76511 Extruded Shapes.

DCB SPECIMENS(S-L)BOLT LOADED TO POP-IN
WET THREE TIMES DAILY




Fig. 167 Stress-Corrosion Crack Growth of Alloy 7050 Products in 3.5% NaCl

Fig. 167



SCC

Mag. 1.8X



Mag. 100X




Mag. 225X


S. No. 410778

Fig. 168 Illustrates Fracture Surface and Intergranular Nature of Cracking at the Tip of the Stress - Corrosion Crack in Short-Transverse (S-L) DCB Specimens from 2-in. Thick 7050-T73651 Plate.

Fig. 168



Mag. 1.6X




Mag. 7.5X

S. No. 411233

Mag. 225X

Fig. 169 Illustrates Fracture Surface, Crack Profile and Interfragmentary Nature of Stress-Corrosion Crack Growth in Short-Transverse (S-L) DCB Specimens from 4.001 - 5.000-in. Thick 7050-T736 Die Forging.

Fig. 169



SCC

Mag. 1.8X



SCC

Mag. 1.8X



Mag. 225X
S. No. 411287
1.161-in. Thick Section



Mag. 225X
S. No. 411286
5-in. Thick Section

Fig. 170 Illustrates Fracture Surfaces and Interfragmentary Nature of Stress-Corrosion Crack Growth in Short-Transverse (S-L) DCB Specimens from 7050-T76511 Extruded Shapes.

Fig. 170



SCC

Mag. 1.6X



Mag. 75X



Mag. 225X

S. No. 411392

Fig. 171 Illustrates Fracture Surface, Crack Profile and Interfragmentary Nature of Stress-Corrosion Crack Growth in Short-Transverse (S-L) DCB Specimen from 2.001 - 4.000-in. Thick 7050-T736 Die Forging.

Fig. 171




Fig. 172 K_I - Rate data for tests of alloy 7050 products.

Fig. 172

TABLE I
CHEMICAL COMPOSITIONS OF 7050-PRODUCTS
(NASC Contract No. W00019-72-C-0512)

Thickness or Size, in. (Die No.)	AL Sample No.	Element, per cent									
		SI	FE	CU	MN	MG	UP	NI	ZN	TI	BP
7050-T76 Sheet											
0.040	428882	0.06	0.08	2.11	0.00	2.09	0.00	0.00	6.15	0.08	0.10
0.040	428883	0.06	0.10	2.03	0.01	2.18	0.01	0.00	6.00	0.08	0.10
0.060	411776	0.06	0.08	2.97	0.00	2.28	0.01	0.00	6.29	0.08	0.11
0.080	428884	0.06	0.08	2.15	0.00	2.13	0.00	0.00	5.88	0.08	0.10
0.090	411182	0.06	0.13	2.50	0.00	2.25	0.01	0.01	6.38	0.04	0.11
0.090	411183	0.07	0.11	2.28	0.01	2.25	0.02	0.01	6.19	0.04	0.11
0.120	411212	0.06	0.14	2.50	0.00	2.29	0.01	0.01	6.16	0.04	0.11
0.120	411213	0.07	0.12	2.25	0.01	2.30	0.02	0.01	6.27	0.04	0.10
0.187	411730	0.09	0.12	2.05	0.00	2.44	0.00	0.00	5.71	0.03	0.11
0.232	418020	0.06	0.08	2.97	0.01	2.27	0.01	0.00	6.46	0.02	0.10
0.249	411309	0.07	0.10	2.15	0.01	2.16	0.02	0.01	6.24	0.03	0.10
7050-T73651 Plate											
0.500	411772	0.06	0.09	2.21	0.00	2.06	0.00	0.00	6.10	0.01	0.10
0.500	411784	0.06	0.10	2.26	0.00	2.32	0.01	0.01	6.54	0.02	0.10
1.000	411050	0.06	0.07	2.47	0.01	2.19	0.01	0.00	6.50	0.02	0.10
1.000	411185	0.06	0.15	2.57	0.00	2.30	0.01	0.01	6.35	0.04	0.11
2.000	410778	0.06	0.10	2.09	0.00	2.27	0.04	0.00	6.00	0.03	0.11
2.000	411186	0.06	0.10	2.19	0.00	2.26	0.01	0.01	6.27	0.02	0.10
4.000	410777	0.06	0.08	2.21	0.00	2.34	0.02	0.00	6.12	0.03	0.12
4.000	411187	0.06	0.11	2.13	0.01	2.22	0.02	0.01	6.29	0.03	0.10
6.000	411300	0.07	0.11	2.21	0.01	2.22	0.02	0.01	6.05	0.04	0.11
6.000	411330	0.07	0.11	2.32	0.01	2.27	0.01	0.00	6.19	0.04	0.10
7050-T73652 Hand Forgings											
2x8x72*	411354	0.06	0.12	2.04	0.01	2.12	0.00	0.01	6.63	0.01	0.13
2-1/2x22x60	411229	0.06	0.12	2.29	0.00	2.29	0.00	0.00	6.22	0.01	0.10
3-1/2x22x64	411352	0.07	0.12	2.07	0.00	2.08	0.00	0.00	5.95	0.03	0.10
4-1/2x14x72*	428850	0.10	0.10	2.27	0.01	2.46	0.00	0.00	6.11	0.08	0.10
4-1/2x22x64	411250	0.05	0.11	2.21	0.00	2.32	0.00	0.00	6.13	0.03	0.10
4-1/2x22x60	411302	0.07	0.11	2.17	0.00	2.19	0.00	0.01	6.09	0.03	0.09
4-1/2x22x60	411353	0.07	0.12	2.09	0.00	2.09	0.00	0.00	5.90	0.03	0.10
4-1/2x22x45*	428851	0.10	0.10	2.26	0.01	2.44	0.00	0.00	6.08	0.02	0.10
7-1/2x22x42	411231	0.05	0.11	2.28	0.00	2.38	0.00	0.00	6.28	0.02	0.10
7-1/2x22x42	411232	0.07	0.12	2.21	0.01	2.25	0.00	0.00	6.21	0.02	0.10
7050-T736 Die Forgings											
<1.000(2177)*	411243	0.08	0.13	2.47	0.01	2.53	0.03	0.01	6.53	0.02	0.12
<1.000(9078)	411331	0.05	0.10	2.10	0.00	2.28	0.00	0.00	6.10	0.02	0.09
1.001-2.000(15789)	411351	0.06	0.12	2.24	0.00	2.23	0.00	0.00	6.14	0.01	0.10
1.001-2.000(15775)	411281	0.06	0.13	2.24	0.00	2.25	0.00	0.01	6.11	0.02	0.10
1.001-2.000(17345)	411297	0.05	0.12	2.24	0.00	2.17	0.00	0.00	5.96	0.01	0.10
2.001-4.000(1364)*	411392	0.06	0.12	2.09	0.01	2.16	0.00	0.01	6.49	0.01	0.12
3.001-4.000(8457)	411352	0.06	0.10	2.18	0.00	2.40	0.00	0.00	6.31	0.02	0.10
4.001-5.000(4736)*	411244	0.08	0.12	2.43	0.01	2.53	0.03	0.01	6.40	0.02	0.12
4.001-5.000(12787)	411233	0.06	0.12	2.29	0.00	2.30	0.00	0.01	6.26	0.01	0.10
6.000-7.000(16392)	411305	0.05	0.11	2.24	0.00	2.36	0.00	0.01	6.18	0.02	0.09
7050-T76511 Extruded Shapes											
0.187(86366)	411288	0.05	0.10	2.16	0.00	2.37	0.00	0.01	6.32	0.02	0.09
0.402(191282)	411289	0.05	0.10	2.18	0.00	2.38	0.00	0.00	6.23	0.02	0.09
0.665(213592)	411290	0.07	0.10	2.29	0.01	2.17	0.00	0.00	5.98	0.02	0.10
0.841(57717)*	411552	0.10	0.10	2.28	0.01	2.51	0.00	0.00	6.17	0.02	0.10
1.161(251372)	411287	0.07	0.11	2.34	0.01	2.28	0.00	0.01	6.20	0.02	0.10
1-1/2x7-1/2	411284	0.05	0.11	2.21	0.00	2.42	0.00	0.00	6.28	0.02	0.09
2x6*	411270	0.05	0.15	2.00	0.03	1.96	0.03	0.01	6.53	0.00	0.13
3-1/2x7-1/2	411505	0.08	0.11	2.20	0.00	2.45	0.00	0.01	6.48	0.02	0.09
4x8*	411290	0.08	0.15	2.07	0.04	1.95	0.02	0.01	6.62	0.00	0.13
5x6-1/4	411286	0.06	0.11	2.20	0.00	2.46	0.00	0.01	6.49	0.02	0.09
Composition Limits**											
		0.12	0.15	2.0-2.6	0.10	1.9-2.6	0.04	--	5.7-6.7	0.06	0.08-0.15
Nominal Composition*		--	--	2.3	--	2.25	--	--	6.2	--	0.12

* Producer B, all others Producer A.

† Maximum unless A range is shown.

* Registration Record of Aluminum Association Alloy Designations and Chemical Composition Limits of Wrought Aluminum Alloys, May 1, 1973.

TABLE II
MECHANICAL PROPERTIES OF 7050-T76 SHEET
(NASC Contract No. N00019-72-C-0512)

Sample Thickness, in.	Specimen Number	Specimen Direction	Tensile Strength, ksi	Tensile Yield Strength,* ksi	Elong. in 2 in., % ⁴⁰	Compressive Yield Strength,* ksi	Shear Strength, ksi	Bearing Strength, ksi e/70d1.5	Bearing Yield Strength, ksi e/70d1.5
(Flat-Plate Specimens)									
0.040	428882	L LT	79.6 81.6	73.2 73.5	10.0 10.0	71.2 78.0	49.0 [†]	124.5 126.2	101.9 100.0
0.040	428985	L LT	79.7 81.0	73.4 73.1	9.0 9.0	73.5 78.4	49.4 [†]	122.8 123.2	101.8 101.8
0.063	411378	L LT	83.0 84.3	77.7 78.2	10.5 10.0	77.1 82.2	50.4 [†]	126.0 126.9	102.9 103.2
0.063	428984	L LT	79.2 80.6	73.3 73.0	10.5 10.5	73.9 77.3	47.9 [†]	125.0 125.0	103.8 101.2
0.090	411182	L LT	84.5 85.9	78.9 77.0	11.0 11.0	78.9 83.6	51.2 [†]	131.3 131.5	112.1 113.6
0.090	411183	L LT	83.8 82.4	78.3 75.5	11.0 11.0	78.9 81.0	50.0 [†]	131.3 129.4	111.2 110.5
0.125	411212	L LT	85.6 85.7	79.6 77.9	11.0 11.5	79.3 83.4	49.7 [†]	131.5 130.7	110.7 111.2
0.125	411213	L LT	85.1 85.0	78.7 77.2	11.0 11.5	77.8 82.8	50.2 [†]	130.3 131.1	109.4 112.5
0.125	413150	L LT	81.1 83.3	75.0 74.5	11.0 11.5	74.8 80.4	49.8 [†]	131.4 132.4	112.2 113.5
0.222	415020	L LT	83.4 84.5	76.4 76.3	11.0 11.0	81.2 84.1	54.0 49.7 [†] 53.2	134.0 129.1	117.2 111.9
0.249	411309	L LT	83.2 83.5	80.2 78.4	12.5 13.0	80.3 84.0	49.7 49.8 [†] 51.9	132.9 132.0	111.3 111.4
Tentative Minimum Properties									
0.040-0.249		L LT	78 78	71 69	8 8	-- --	-- --	-- --	-- --

* Offset equals 0.2 per cent.

† L - Longitudinal; LT - Long-Transverse

‡ Punch-type shear specimens; L and LT shear strengths for 0.222 and 0.249-in. sheet are from tests of cylindrical specimens made in an Amesler double-shear tool.

§ Specimens cleaned ultrasonically; yield strength offset equals 2 per cent of pin diameter.

TABLE III

MECHANICAL PROPERTIES OF 7050-T7351 PLATE
(BASC Contract No. 00019-72-C-0512)

Sample Thickness, Number In.	Specimen Location	Specimen Direction*	Tensile Strength, ksi	Tensile Yield Strength, ksi	Elong. in 2 in., or %	Compressive Yield Strength, ksi	Shear Strength, ksi	Bearing Strength, ksi (Flatwise Specimens)	Bearing Yield Strength, ksi (Flatwise Specimens)
0.500	411372	T/2 L	75.9 75.3	66.1 65.7	15.7 15.7	65.3 67.9	45.0 45.6	109.8 111.8	99.2 90.8
0.500	411184	T/2 L	76.2 76.5	66.9 67.2	15.0 14.5	66.2 69.8	45.0 44.7	115.4 114.2	95.4 91.9
1.000	411185	T/2 L	74.9 75.1	65.4 65.4	13.0 12.0	64.7 68.5	44.2 45.5	114.1 113.5	95.1 92.7
1.000	411050	T/2 L	79.9 79.0	70.8 70.0	13.5 12.0	71.1 73.1	45.5 45.5	112.1 118.0	94.7 96.2
2.000	411186	T/4 T/2	75.3 75.5 72.9	65.9 65.7 61.5	12.5 11.0 7.8	64.7 68.9 68.2	46.5 46.5 44.7	116.4 117.4	95.4 97.5
2.000	410778	T/4 T/2	75.2 75.9 70.9	65.7 65.5 62.2	13.0 11.5 4.9	64.4 69.3 68.2	46.7 46.1 44.6	116.8 115.9	96.6 98.2
4.000	410777	T/4 T/2	74.0 75.6 72.9	65.3 64.4 60.9	12.0 11.0 6.4	61.9 68.0 68.3	46.9 46.7 45.6	116.5 115.3	98.0 97.5
4.000	411187	T/4 T/2	72.0 73.3 69.9	62.7 63.2 59.7	11.0 10.0 7.1	61.4 67.0 65.2	45.5 45.0 41.9	115.1 114.2	95.0 94.7
6.000	411300	T/4 T/2	69.7 70.5 67.7	60.9 58.1 56.8	9.5 7.5 5.0	58.0 63.1 63.3	45.2 45.1 42.5	107.7 110.3	92.2 92.9
6.000	411350	T/4 T/2	73.0 72.2 68.7	64.3 62.1 59.3	9.0 8.0 5.5	60.2 60.1 68.5	46.9 46.7 42.5	112.6 114.6	97.1 96.6
Minimum Properties									
0.250-2.000		L LT	71 72	63 65	8 6	—	—	—	—
2.001-4.000		L LT ST	69 70 68	60 60 56	9 2	—	—	—	—
5.001-6.000		L LT ST	66 67 63	56 56 53	8 5 2	—	—	—	—

* Offset equals 0.2 per cent.

† T - Thickness; T/4 - Midway between center and surface; T/2 - Center

‡ L - Longitudinal; LT - Long-transverse; ST - Short-transverse

§ Specimens cleaned ultrasonically; yield strength-offset equals 2 per cent of pin diameter.

TABLE IV
MECHANICAL PROPERTIES OF T030-T73000 BOND FORMERS
(RASC Contract No. DD0019-70-0-0512)

Sample No.	Lot	Specimen Direction, ¹ in.	Tensile Strength, ksi	Tensile Yield Strength, ² ksi	Elong in 2 in. or 40, %	Compressive Yield Strength, ³ ksi	Char- py Strength, ksi	Starting Strength, ⁴ ksi		Starting Yield Strength, ⁵ ksi	
								0/90°	0/0°	0/90°	0/0°
								(Average Results)			
2-1/2" x 1/2" x 1/8"	A11300	L	78.0 76.0	72.0 69.0	8.0 7.0	71.0 70.0	48.0 47.0	118.0 117.0	120.0 119.0	100.0 100.0	
2-1/2" x 1/2" x 1/8"	A11300	L	78.0 76.0	72.0 69.0	8.0 7.0	71.0 70.0	48.0 47.0	118.0 117.0	120.0 119.0	100.0 100.0	
3-1/2" x 1/2" x 1/8"	A00050	L	78.0 76.0	72.0 69.0	8.0 7.0	71.0 70.0	48.0 47.0	118.0 117.0	120.0 119.0	100.0 100.0	
3-1/2" x 1/2" x 1/8"	A11300	L	78.0 76.0	72.0 69.0	8.0 7.0	71.0 70.0	48.0 47.0	118.0 117.0	120.0 119.0	100.0 100.0	
4-1/2" x 1/2" x 1/8"	A11300	L	78.0 76.0	72.0 69.0	8.0 7.0	71.0 70.0	48.0 47.0	118.0 117.0	120.0 119.0	100.0 100.0	
4-1/2" x 1/2" x 1/8"	A11300	L	78.0 76.0	72.0 69.0	8.0 7.0	71.0 70.0	48.0 47.0	118.0 117.0	120.0 119.0	100.0 100.0	
5-1/2" x 1/2" x 1/8"	A00051	L	78.0 76.0	72.0 69.0	8.0 7.0	71.0 70.0	48.0 47.0	118.0 117.0	120.0 119.0	100.0 100.0	
5-1/2" x 1/2" x 1/8"	A11300	L	78.0 76.0	72.0 69.0	8.0 7.0	71.0 70.0	48.0 47.0	118.0 117.0	120.0 119.0	100.0 100.0	
7-1/2" x 1/2" x 1/8"	A11301	L	78.0 76.0	72.0 69.0	8.0 7.0	71.0 70.0	48.0 47.0	118.0 117.0	120.0 119.0	100.0 100.0	
7-1/2" x 1/2" x 1/8"	A11302	L	78.0 76.0	72.0 69.0	8.0 7.0	71.0 70.0	48.0 47.0	118.0 117.0	120.0 119.0	100.0 100.0	
Minimum Properties											
Up to 2.000		L	72	62	8						
2.001-3.000		L	72	62	8						
3.001-4.000		L	72	62	8						
4.001-5.000		L	72	62	8						
5.001-6.000		L	72	62	8						
6.001-7.000		L	72	62	8						
7.001-8.000		L	72	62	8						

1. Stress equal to 0.2 per cent.
2. Specimen tested either center (HLL) or edge (HLL) of thickness and width.
3. L = longitudinal; T = transverse; BT = shear-transverse.
4. Minimum elongation (average); yield strength - stress equal to one percent of pin diameter.
5. Minimum of two tests; tensile strength from initial test; below minimum value (60.9 ksi).
6. Average of two tests; yield strength from initial test. One of the tensile strength from tests below minimum value (60.9 ksi).
7. Average of two tests; tensile and yield strengths of initial tests below minimum values.

TABLE V
MECHANICAL PROPERTIES OF 7050-T76 DIS SPECIMENS
(MIL-STD-883C Contract No. 60019-72-C-0512)

Approximate Thickness in.	Sample Number	Dir No.	Specimen Direction†	Tensile Strength, ksi	Tensile Yield Strength, ksi	Elong. in 2 in. or 40, %	Compressive Yield Strength, ksi	Shear Strength, ksi	Bearing Strength, ksi 87054.5 (Machine Specimens)	Bearing Yield Strength, ksi 87054.5
0.600	411243	2177	L ST	80.2 73.8	75.4 64.5	13.6 8.0	76.9 65.1	45.6 47.4	113.6 —	96.6 —
0.7	411321	9078	L ST	79.9 73.1	72.9 63.5	13.6 9.0	75.1 67.5	45.4 —	112.1 —	92.4 —
1.1	411351	15769	L ST	76.0 75.2	69.1 68.1	8.5 7.5	72.0 70.7	47.9 47.0	113.9 —	97.7 —
1.25	411281	17975	L ST	75.6 75.3	68.0 66.7	14.0 7.0	71.3 70.8	48.0 44.5	113.4 —	101.4 —
1.95	411297	17944	L ST	76.7 74.5	68.8 67.0	14.5 8.5	76.1 71.0	49.8 48.2	118.4 —	101.1 —
3.1**	411392	1364	L ST	73.7 65.6††	64.7 58.9	14.0 3.5††	69.4 65.8	47.6 41.3	97.7 —	89.7 —
3.5	411328	8457	L ST	77.4 75.7	70.2 68.3	12.0 7.1	74.3 71.9	49.6 48.5	105.0 —	92.0 —
4.00 dia.**	411244	4736	L ST	77.4 71.3	69.0 65.8	12.0 5.0	73.1 66.7	48.3 45.8	101.7 —	89.0 —
4.25 dia.	411233	12767	L ST	75.6 74.4	69.3 68.5	14.0 7.1	72.3 69.5	48.3 46.7	117.7 —	107.9 —
5.5	411324	2457	L ST	76.6 74.0	68.5 68.5	11.0 8.0	73.8 68.7	46.8 44.5	107.4 —	91.2 —
6.1	411303	16392	L ST	72.3 72.9	63.2 65.7	8.5 4.0	70.7 67.1	48.1 44.2	104.8 —	99.0 —
Up to 2.000			L ST	72 68	62 58	7 5	— —	— —	— —	— —
2.001-4.000			L ST	71 67	61 56	7 4	— —	— —	— —	— —
4.001-5.000			L ST	70 66	60 54	7 5	— —	— —	— —	— —
5.001-6.000			L ST	70 66	59 54	7 5	— —	— —	— —	— —

* Offset equals 0.2 per cent.
† Longitudinal, ST-Short-Transverse
‡ Specimens checked ultrasonically; field strength - offset equals 2 per cent of pin diameter.
§ Specimens checked ultrasonically; field strength - offset equals 2 per cent of pin diameter.
** Below tensile strength; average results of three tests.

TABLE VI
MECHANICAL PROPERTIES OF 7050-T76(1) EXTRUDED BARS
(MIL Contract No. DDONS-72-C-0512)

Specimen Thickness or Dia., in.	Number	Des No.	Location	Specimen Direction	Tensile Strength, ksi	Tensile Yield Strength, ksi	Elong. in 2 in., %	Compressive Yield Strength, ksi	Shear Strength, ksi	Bearing Strength, ksi (7050-T76(1) Specimens)	Bearing Yield Strength, ksi (7050-T76(1) Specimens)
0.187	411288	86366	W/A	L	85.1	75.9	10.0	81.9	87.4	122.1	121.5
0.402	411289	191382	W/A	L	85.4	76.6	14.0	76.2	89.4	125.2	121.5
0.665	411290	213592	W/A	L	85.4	75.0	10.0	81.5	89.4	126.8	121.5
0.841**	411291	213592	W/A	L	85.4	75.0	10.0	81.5	89.4	126.8	121.5
0.841**	411292	213592	W/A	L	85.4	75.0	10.0	81.5	89.4	126.8	121.5
1.161	411297	231272	W/A	L	85.4	75.0	10.0	81.5	89.4	126.8	121.5
1.547.5	411284	11	W/A	L	85.4	75.0	10.0	81.5	89.4	126.8	121.5
2.046.0**	411279	11	W/A	L	85.4	75.0	10.0	81.5	89.4	126.8	121.5
3.547.5	411285	11	W/A	L	85.4	75.0	10.0	81.5	89.4	126.8	121.5
4.046.0**	411280	11	W/A	L	85.4	75.0	10.0	81.5	89.4	126.8	121.5
5.046.25	411286	11	W/A	L	85.4	75.0	10.0	81.5	89.4	126.8	121.5

Specimen Minimum Properties	
Up to 0.249 (Area = 20 in. ²)	78
0.250-0.499 (Area = 20 in. ²)	81
0.500-1.499 (Area = 20 in. ²)	81
1.500-2.999 (Area = 20 in. ²)	81

* Offset equals 0.2 per cent.
 † T-thickness, W-width
 ‡ L-Longitudinal, LR-Long Transverse, ST-Short Transverse
 § Specimens cleaned ultrasonically; yield strength - offset equals 2 per cent of pin diameter.
 ¶ Rectangles
 ** Specimens taken near edge of width; location not comparable to those of other shapes.
 †† Data not included for J-terminating radius.

TABLE VII

SPECIFIED ALUMINUM TENSILE PROPERTIES FOR 7050 PRODUCTS
(MSC Contract No. 80019-72-C-0512)

Product	Temper	Thickness, in.	Longitudinal			Long Transverse			Short Transverse			Specification
			Ultimate Strength, ksi	Yield Strength,* ksi	Elongation In 2 in. or AD, %	Ultimate Strength, ksi	Yield Strength,* ksi	Elongation In 2 in. or AD, %	Ultimate Strength, ksi	Yield Strength,* ksi	Elongation In 2 in. or AD, %	
Sheet	T76	0.040-0.241	78	71	8	72	69	8	--	--	--	None
Plate	T73651	0.250-2.000	71	63	9	72	63	6	--	--	--	AMS 4050
		2.001-3.000	71	63	9	72	63	6	66	59	2	
		3.001-4.000	69	60	9	70	60	6	66	56	2	
		4.001-5.000	67	58	9	68	58	5	64	54	2	
Sand Forgings	T73652	5.001-6.000	66	56	8	67	56	5	63	53	2	AMS 4106
		6.001-7.000	66	56	8	67	56	5	63	53	2	
		7.001-8.000	67	57	9	66	52	4	64	50	3	
		8.001-9.000	67	57	9	66	52	4	64	50	3	
		9.001-10.000	67	57	9	66	52	4	64	50	3	
		10.001-11.000	67	57	9	66	52	4	64	50	3	
Die Forgings	T736	0.250-2.000	72	62	9	71	60	5	67	55	4	AMS 4107
		2.001-3.000	71	61	9	70	59	5	67	55	4	
		3.001-4.000	70	60	9	69	58	4	66	54	3	
		4.001-5.000	69	59	9	68	56	4	65	53	3	
Extruded Shapes	T76511	5.001-6.000	68	58	9	67	54	4	65	53	3	None
		6.001-7.000	67	57	9	66	52	4	64	50	3	
		7.001-8.000	67	57	9	66	52	4	64	50	3	
		8.001-9.000	67	57	9	66	52	4	64	50	3	
Extruded Shapes	T76511	9.001-10.000	67	57	9	66	52	4	64	50	3	None
		10.001-11.000	67	57	9	66	52	4	64	50	3	
		11.001-12.000	67	57	9	66	52	4	64	50	3	
		12.001-13.000	67	57	9	66	52	4	64	50	3	

* Offset equals 0.2 per cent.

† Values apply to specimens with axes deviating more than 15 degrees from parallel to forging flow lines.

TABLE VIII

Sample Thickness, In.	CYS (L) TYS (L)	CYS (LT) TYS (LT)	SUS (°) TUS (LT)	SUS (LALT) TUS (LT)	EUS (L) / TUS (LT) e/D=1.5 e/D=2.0		EUS (L) / TYS (LT) e/D=1.5 e/D=2.0		EUS (LT) / TUS (LT) e/D=1.5 e/D=2.0		EYS (LT) / TYS (LT) e/D=1.5 e/D=2.0		
					(Platewise Specimens)		(Platewise Specimens)		(Platewise Specimens)		(Platewise Specimens)		
0.040	42882	0.973	1.061	0.600	--	1.527	1.945	1.386	1.559	1.547	1.902	1.361	1.641
0.040	42895	1.001	1.073	0.612	--	1.516	2.009	1.393	1.611	1.521	1.935	1.393	1.596
0.063	411378	0.992	1.051	0.596	--	1.495	1.968	1.316	1.545	1.505	1.992	1.320	1.528
0.063	42884	1.008	1.059	0.594	--	1.551	2.012	1.422	1.670	1.551	2.016	1.386	1.670
0.090	411192	1.000	1.086	0.610	--	1.589	2.067	1.456	1.657	1.589	2.061	1.475	1.736
0.090	411183	1.008	1.073	0.607	--	1.593	2.049	1.473	1.656	1.570	2.075	1.464	1.715
0.125	411212	0.996	1.071	0.594	--	1.571	2.020	1.421	1.560	1.562	2.031	1.427	1.630
0.125	411213	0.989	1.073	0.605	--	1.570	2.036	1.417	1.591	1.580	2.023	1.457	1.622
0.187	413150	1.024	1.079	0.598	--	1.577	2.029	1.506	1.734	1.589	2.029	1.525	1.775
0.222	416020	1.034	1.074	0.587	0.638, 0.629	1.584	2.017	1.498	1.608	1.526	2.021	1.429	1.672
0.249	411309	1.001	1.071	0.596	0.595, 0.622	1.592	2.029	1.420	1.583	1.581	2.025	1.423	1.622

Punch-type shear tests.

* Punch-type shear tests.

Tests of cylindrical specimens.

Note: Bearing specimens cleaned ultrasonically.

TABLE IX
RATIOS AMONG THE TENSILE, COMPRESSIVE, SHEAR AND BEARING PROPERTIES
OF 7050-T73651 PLATE
(NASC Contract No. N00019-72-C-0512)

Sample Thickness in.	Sample Number	CYS(L) TYS(L)	CYS(LT) TYS(LT)	CYS(ST) TYS(ST)	SUS(L) TUS(LT)	SUS(LT) TUS(LT)	BUS(L)/TUS(LT) e/D=1.5 e/D=2.0	BYS(L)/TYS(LT) e/D=1.5 e/D=2.0	BUS(LT)/TUS(LT) e/D=1.5 e/D=2.0	BYS(LT)/TYS(LT) e/D=1.5 e/D=2.0
							(Flatwise Specimens)			(Flatwise Specimens)
0.500	411372	0.988	1.033	--	0.598	0.579	1.459 1.930	1.358 1.638	1.482 1.899	1.379 1.662
0.500	411184	0.990	1.039	--	0.588	0.584	1.508 1.907	1.390 1.653	1.493 1.939	1.368 1.652
1.030	411185	0.989	1.047	--	0.589	0.579	1.519 1.920	1.424 1.633	1.512 1.973	1.417 1.712
1.000	411050	1.004	1.044	--	0.576	0.573	1.419 1.913	1.353 1.576	1.494 1.906	1.374 1.606
2.000	411186	0.982	1.049	1.109	0.616	0.616	1.542 1.992	1.454 1.694	1.555 2.034	1.485 1.775
2.000	410778	0.980	1.058	1.064	0.615	0.607	1.539 1.966	1.475 1.655	1.527 1.962	1.499 1.695
4.000	410777	0.946	1.056	1.122	0.620	0.618	1.541 1.952	1.522 1.707	1.525 1.966	1.514 1.734
4.000	411187	0.964	1.060	1.092	0.621	0.614	1.570 2.008	1.503 1.742	1.558 2.012	1.498 1.777
6.000	411300	0.952	1.068	1.109	0.641	0.642	1.528 1.972	1.560 1.827	1.565 2.017	1.572 1.844
6.000	411330	0.936	1.074	1.121	0.641	0.633	1.538 1.977	1.564 1.810	1.557 2.015	1.556 1.845

* For 0.500 and 1.000 in. plate and ST direction of 2.000 to 6.000 in. plate specimens located at center of thickness.
For L and LT directions of 2.000 to 6.000-in. plate specimens located midway between center and surface of plate.

Note: Bearing specimens cleaned ultrasonically.

TABLE X
RATIOS AMONG THE TENSILE, COMPRESSIVE, SHEAR AND BEARING PROPERTIES
OF 7050-T7352 HAND FORGINGS
(WASC Contract No. W00019-72-C-0512)

Sample Size, In.	Number	$\frac{CTS(L)}{TYS(L)}$	$\frac{CTS(ST)}{TYS(ST)}$	$\frac{SUS(L)}{TUS(L)}$	$\frac{SUS(ST)}{TUS(ST)}$	$\frac{BUS(L)}{TUS(L)} \frac{e}{D-1.5} \frac{e}{D-2.0}$ (Reference Specimens)	$\frac{BYS(L)}{TYS(L)} \frac{e}{D-1.5} \frac{e}{D-2.0}$ (Reference Specimens)	$\frac{BUS(L)}{TUS(L)} \frac{e}{D-1.5} \frac{e}{D-2.0}$ (Reference Specimens)	$\frac{BYS(L)}{TYS(L)} \frac{e}{D-1.5} \frac{e}{D-2.0}$ (Reference Specimens)
2x8x72*	411354	1.061	1.072	0.618	0.603	1.428	1.981	1.519	1.990
2-1/2x22x60	411229	0.999	1.053	0.573	0.573	1.394	1.831	1.484	1.916
3-1/2x14x72*	428850	1.062	1.081	0.603	0.598	1.427	1.952	1.418	1.856
3-1/2x22x84	411352	1.033	1.111	0.624	0.634	1.334	1.826	1.403	1.879
4-1/2x22x84	411230	1.024	1.105	0.594	0.584	1.385	1.850	1.445	1.803
4-1/2x22x84	411302	1.021	1.145	0.621	0.611	1.418	1.924	1.504	1.923
5-1/2x22x45*	428851	1.058†	0.981†	0.620	0.617	1.525	1.949	1.484	1.968
5-1/2x22x60	411353	1.017	1.098	0.606	0.613	1.393	1.774	1.419	1.945
7-1/2x22x42	411231	1.033	1.077	0.626	0.599	1.439	1.918	1.420	1.777
7-1/2x22x42	411232	1.020	1.096	0.597	0.606	1.442	1.899	1.461	1.870
* Producer B, all others Producer A.									
† Average of two tests.									

Note: Bearing specimens cleaned ultrasonically.

TABLE II
RATIOS AMONG THE TENSILE, COMPRESSIVE, SHEAR AND BEARING PROPERTIES
OF 7050-T736 DIE FORGINGS
(NASC Contract No. M00019-72-C-0512)

Sample Thickness, in.	Sample Number	Die Number	$\frac{CYS(L)}{TYS(L)}$	$\frac{CYS(ST)}{TYS(ST)}$	$\frac{SUS(L)}{TUS(L)}$	$\frac{SUS(ST)}{TUS(ST)}$	$\frac{BUS(L)}{TUS(L)} \frac{e/D=1.5}{e/D=2.0}$	$\frac{BYS(L)}{TYS(L)} \frac{e/D=1.5}{e/D=2.0}$ (Edgewise Specimens)
0.6*	411243	2177	1.020	1.056	0.554	0.577	1.382	1.805
0.7	411331	9078	1.030	1.063	0.568	0.568	1.493	1.775
1.1	411351	15789	1.042	1.038	0.630	0.618	1.499	1.955
1.25	411281	17975	1.048	1.061	0.635	0.589	1.500	1.993
1.95	411297	17944	1.106	1.060	0.649	0.628	1.544	1.941
3.1*	411392	1364	1.073	1.083	0.592	0.560	1.326	1.821
3.5	411332B	8457	1.058	1.053	0.589	0.572	1.357	1.814
4.02*	411244	4736	1.059	1.049	0.572	0.563	1.314	1.757
4.25	411233	12767	1.043	1.045	0.639	0.604	1.557	2.040
5.5	411332A	8457	1.063	1.003	0.611	0.581	1.402	1.821
6.1	411303	16392	1.119	1.021	0.665	0.611	1.450	1.900
								1.566
								1.853

* Producer B; all others Producer A.

Note: Bearing specimens cleaned ultrasonically.

TABLE II

• **Producer B; all others Producer A.**

Note: Bearing specimens cleaned ultrasonically.

STATISTICAL ASPECTS OF DIFFUSION THROUGH COMPRESSIVE SOLID AND MELTING

(SASC Contract No. W00019-72-C-0512)
 FURNISHING OF 10,000-170-1-100

[illegible]

• Peach-type stone? ☐ Yes. ☐ No.

† Levene's F test showed no significant difference between the average ratings

for L and LT directions and "V" - test showed no significant difference in variability for the L and LT directions.

* 0.040 and 0.063-in. thick sheet; analyzed separately from thicker sheet.

insufficient data for analyses of data from tests cylindrical specimens.

^{††} Regression analysis showed significant relationship with thickness. Values shown is σ_0/\sqrt{n} .

100

1

五、

442 443

Confronted with the results of the 1977-78 survey, the authors conclude that the 1979-80 survey was not a significant improvement in the 1977-78 survey. The authors conclude that the 1979-80 survey was not a significant improvement in the 1977-78 survey.

11

TABLE XVI

STATISTICAL ANALYSES OF RATIOS AMONG TENSILE, COMPRESSIVE, SHEAR AND BEARING PROPERTIES
OF 7050-T7-S DIE FORDINGS
(MASC Contract No. W00019-72-C-0512)

Ratio Cell	CTS(L) TSS(L)	CTS(ST) TSS(ST)	Ratio Cell	STS(L) TSS(L)	STS(ST) TSS(ST)	STS(L-ST) TSS(L)	$\sigma/D = 1.5$		$\sigma/D = 2.0$	
				Ratio Cell	Ratio TSS(L)	Ratio TSS(L)	Ratio Cell	Ratio TSS(L)	Ratio Cell	Ratio TSS(L)
1.12	1		0.67	1.55	1	1.57	1	2.04	1	1.85
1.11			0.66	1.56		1.56		2.03		1.84
1.10			0.65	1.54		1.55		2.02		1.83
1.09			0.64	1.53		1.54		2.01		1.82
1.08	1		0.63	1.52		1.53		2.00		1.81
1.07	3		0.62	1.51		1.52		1.99	1	1.80
1.06	4		0.61	1.50	2	1.51	2	1.98		1.79
1.05	3		0.60	1.49	1	1.50		1.96	1	1.78
1.04	1		0.59	1.48		1.49		1.95		1.77
1.03	1		0.58	1.47		1.48		1.94	1	1.76
1.02	1		0.57	1.46	2	1.47		1.93		1.75
1.01	1		0.56	1.45	2	1.46		1.92		1.74
1.00	1		0.55	1.44	1	1.45		1.91		1.73
				1.43		1.44		1.90	1	1.72
				1.42		1.43		1.89		1.71
				1.41		1.42		1.88		1.70
				1.40		1.41	2	1.87		1.69
				1.39		1.40		1.86		1.68
				1.38		1.39	1	1.85		1.67
				1.37		1.38		1.84		1.66
				1.36		1.37	1	1.83		1.65
				1.35		1.36		1.82	2	1.64
				1.34		1.35		1.81	2	1.63
				1.33		1.34	1	1.80		1.62
				1.32		1.33		1.79		1.61
				1.31		1.32	1	1.78		1.60
								1.77	1	1.59
								1.76	1	1.58
										1.57
										1.56
										1.55
										1.54
										1.53
										1.52
										1.51
										1.50
										1.49
	11	11			11	11	11	11	11	11
R	1.560	1.048						1.875		1.621
ST	.02569 ^{††}	.01787 ^{††}						.09534		.11546
Min. R	1.015-	1.047-						1.823		1.557
	1.058	1.007								

[†] L and ST ratios averaged. Students t-test showed no significant difference between the average ratios for L and ST directions and P-test showed no significant difference in variability for the L and ST directions.

^{††} Regression analysis showed significant relationship with thickness. Value shown in σ_e/\bar{x} .

TABLE XVIII

RATIOS FOR COMPUTING
DESIGN MECHANICAL PROPERTIES
OF 7050-T76 SHEET

Ratio	Thickness, in.	
	0.040- 0.089	0.090- 0.187
$F_{cy} (L)/F_{ty} (L)$	0.980	0.990
$F_{cy} (LT)/F_{ty} (LT)$	1.065	1.065
$F_{su}/F_{tu} (LT)$	0.598*	0.591*
$F_{bru}/F_{tu} (LT)$ e/D=1.5 e/D=2.0	1.501 1.928	1.577 1.024
$F_{bry}/F_{ty} (LT)$ e/D=1.5 e/D=2.0	1.327 1.538	1.433 1.610

* Based on punch-type shear-test data.

TABLE X'X

RATIOS FOR COMPUTING DESIGN MECHANICAL PROPERTIES
OF 7050-T73651 PLATE

Ratio	Thickness, in.									
	0.250- 0.499	0.500- 1.000	1.001- 1.500	1.501- 2.000	2.001- 3.000	3.001- 4.000	4.001- 5.000	5.001- 6.000		
$F_{cy}(L)/F_{ty}(L)$	0.987	0.983	0.979	0.974	0.964	0.955	0.943	0.932		
$F_{cy}(LT)/F_{ty}(LT)$	1.033	1.036	1.040	1.043	1.046	1.051	1.057	1.061		
$F_{cy}(ST)/F_{ty}(ST)$	-	-	-	-	1.061	1.075	1.086	1.087		
$F_{su}/F_{tu}(LT)$	0.577	0.569	0.562	0.601	0.604	0.609	0.619	0.625		
$F_{bru}/F_{tu}(LT)$ e/D=1.5 e/D=2.0	1.454 1.904	1.454 1.904	1.454 1.904	1.536 1.971	1.536 1.971	1.536 1.971	1.536 1.971	1.536 1.971		
$F_{bry}/F_{ty}(LT)$ e/D=1.5 e/D=2.0	1.352 1.600	1.352 1.600	1.352 1.600	1.448 1.633	1.459 1.654	1.485 1.697	1.507 1.733	1.526 1.758		

TABLE XI
RATIOS FOR COMPUTING DESIGN MECHANICAL PROPERTIES
OF HAND FORGINGS AND DIE FORGINGS

HAND FORGINGS		DIE FORGINGS					
Ratio	Thickness, in. 2-8.000	Ratio		Thickness, in.			
$F_{cy} (L)/F_{ty} (L)$	1.020	$F_{cy} (L)/F_{ty} (L)$		1.001-2.000	2.001-3.000	3.001-4.000	4.001-5.000
$F_{cy} (LT)/F_{ty} (LT)$	1.077	$F_{cy} (T)/F_{ty} (T)$		1.000	2.000	3.000	4.000
$F_{cy} (ST)/F_{ty} (ST)$	1.114			1.016	1.022	1.036	1.047
$F_{su}/F_{tu} (LT)$	0.591	$F_{su}/F_{tu} (L)$		0.583	0.583	0.583	0.583
$F_{bru}/F_{tu} (LT)$ $e/D=1.5$ $e/D=2.0$	1.415 1.854	$F_{bru}/F_{ty} (L)$ $e/D=1.5$ $e/D=2.0$		1.384	1.384	1.384	1.384
$F_{bry}/F_{ty} (LT)$ $e/D=1.5$ $e/D=2.0$	1.414 1.668	$F_{bry}/F_{ty} (L)$ $e/D=1.5$ $e/D=2.0$		1.623	1.832	1.832	1.832
				1.326	1.326	1.326	1.326
				1.557	1.557	1.557	1.557

TABLE XXI

RATIOS FOR COMPUTING DESIGN MECHANICAL PROPERTIES
OF 7050-T76511 EXTRUDED SHAPES

Ratio	Thickness, in.													
	0.249	0.250- 0.499	0.500- 0.749	0.750- 0.999	1.000- 1.499	1.500- 1.999	2.000- 2.499	2.500- 2.999	3.000- 3.999	4.000- 4.999				
$F_{tu} (LT)/F_{tu} (L)$	0.992	0.987	0.981	0.975	0.963	0.951	0.938	0.924	0.898	0.870				
$F_{ty} (LT)/F_{ty} (L)$	0.983	0.977	0.972	0.967	0.955	0.943	0.931	0.917	0.889	0.861				
$F_{cy} (L)/F_{cy} (L)$	1.017	1.017	1.017	1.017	1.017	1.015	1.012	1.007	0.997	0.986				
$F_{cy} (LT)/F_{ty} (L)$	1.030	1.027	1.022	1.018	1.009	0.999	0.988	0.976	0.951	0.925				
F_{su}/F_{tu}	0.557	0.557	0.556	0.556	0.554	0.551	0.547	0.543	0.534	0.523				
$F_{tru}/F_{tu} (L)$ $e/D=1.5$ $e/D=2.0$	1.477 1.913	1.462 1.908	1.467 1.903	1.462 1.897	1.453 1.883	1.440 1.869	1.425 1.852	1.409 1.832	1.373 1.791	1.335 1.748				
$F_{bry}/F_{ty} (L)$ $e/D=1.5$ $e/D=2.0$	1.374 1.608	1.369 1.601	1.364 1.593	1.359 1.585	1.348 1.569	1.334 1.550	1.318 1.527	1.301 1.504	1.262 1.451	1.222 1.395				

TABLE XXII
Computed Design Mechanical Properties
of 7050-T76 Sheet

ALLOY SPECIFICATION				
FORM		Sheet		
TEMPER		T76		
CROSS-SECTIONAL AREA, in ²				
THICKNESS, in.	{	0.040-	0.090-	0.188-
		0.089	0.187	0.249
BASIS		Tentative		
MECHANICAL PROPERTIES				
F _{tu} , ksi	L	78	78	78
	LT	78	78	78
F _{ty} , ksi	L	71	71	71
	LT	69	69	69
F _{cy} , ksi	L	69	70	71
	LT	73	73	73
F _{su} , ksi		46	46	45
F _{bcu} , ksi	e/D=1.5	117	123	123
	e/D=2.0	150	158	158
F _{bry} , ksi	e/D=1.5	93	99	99
	e/D=2.0	106	111	111
e, per cent	L	8	8	8
	LT	8	8	8
E, 10 ³ ksi		10.2		
E _a , 10 ³ ksi		10.6		
G, 10 ³ ksi		3.9		

TABLE XXIII

Computed Design Mechanical Properties of 7050-T73651 Plate

ALLOY SPECIFICATION		AMS 7050							
FORM		Plate							
TEMPER		T73651							
CROSS-SECTIONAL AREA, in ²									
THICKNESS, in.	{	0.250-	0.500-	1.001-	1.501-	2.001-	3.001-	4.001-	5.001-
		0.499	1.000	1.500	2.000	3.000	4.000	5.000	6.000
BASIS		S	S	S	S	S	S	S	S
MECHANICAL PROPERTIES									
F_{tu} , ksi	L	71	71	71	71	71	69	67	66
	LT	72	72	72	72	72	70	68	67
	ST	--	--	--	--	68	66	64	63
F_{ty} , ksi	L	63	63	63	63	63	60	58	56
	LT	63	63	63	63	63	60	58	56
	ST	--	--	--	--	59	56	54	53
F_{cy} , ksi	L	62	62	61	61	60	57	54	52
	LT	65	65	65	65	66	63	61	59
	ST	--	--	--	--	62	60	58	57
F_{su} , ksi		41	41	40	43	43	42	42	42
F_{bru} , ksi	e/D=1.5	104	104	104	110	110	107	104	103
	e/D=2.0	137	137	137	142	142	138	134	132
F_{brv} , ksi	e/D=1.5	85	85	85	91	91	89	87	85
	e/D=2.0	101	101	101	103	103	102	100	98
e, per cent	L	9	9	9	9	9	9	9	8
	LT	6	6	6	6	6	6	5	5
	ST	--	--	--	--	2	2	2	2
E , 10 ³ ksi		10.3							
E_c , 10 ³ ksi		10.6							
G , 10 ³ ksi		3.9							

TABLE XXIV
Computed Design Mechanical Properties of 7050-T73652 Hand Forgings

ALLOY SPECIFICATION		AMS 4108						
FORM		Hand Forgings						
TEMPER		T73652						
CROSS-SECTIONAL AREA, in ²								
THICKNESS, in.	{	2.001-	3.001-	4.001-	5.001-	6.001-	7.001-	
		2.000	3.000	4.000	5.000	6.001	7.001	8.001
BASIS		S	S	S	S	S	S	S
MECHANICAL PROPERTIES								
F _{tu} , ksi	L	72	72	71	70	69	68	67
	LT	71	70	70	69	68	67	66
	ST	--	67	67	66	66	65	64
F _{ty} , ksi	L	63	62	61	60	59	58	57
	LT	61	60	59	58	56	54	52
	ST	--	55	55	54	53	51	50
F _{cy} , ksi	L	64	63	62	61	60	59	58
	LT	65	64	63	62	60	58	56
	ST	--	61	61	60	59	57	55
F _{su} , ksi		42	41	41	41	40	39	39
F _{bru} , ksi	e/D=1.5	100	99	99	97	96	95	93
	e/D=2.0	131	130	130	128	126	124	122
F _{bry} , ksi	e/D=1.5	86	85	83	82	79	76	73
	e/D=2.0	101	100	98	96	93	90	86
e, per cent	L	9	9	9	9	9	9	9
	LT	5	5	5	4	4	4	4
	ST	--	4	4	3	3	3	3
E, 10 ³ ksi		10.2						
E _c , 10 ³ ksi		10.6						
G, 10 ³ ksi		3.9						

TABLE XXV

Computed Design Mechanical Properties of 7050-T736 Die Forgings

ALLOY SPECIFICATION		AMS 4107					
FORM		Die Forgings					
TEMPER		T736					
CROSS-SECTIONAL AREA, in ²							
THICKNESS, in.	{		1.001-	2.001-	3.001-	4.001-	5.001-
		21.000	2.000	3.000	4.000	5.000	6.000
BASIS		S	S	S	S	S	S
MECHANICAL PROPERTIES							
F _{tu} , ksi	L	72	72	71	71	70	70
	T	68	69	67	67	66	66
F _{ty} , ksi	L	62	62	61	61	60	59
	T	56	56	55	55	54	54
F _{cy} , ksi	L	63	63	63	63	63	62
	T	58	58	57	56	55	54
F _{su} , ksi		40	40	41	41	41	41
F _{bru} , ksi	e/D=1.5	99	99	98	98	97	97
	e/D=2.0	131	131	129	129	127	127
F _{bry} , ksi	e/D=1.5	83	83	81	81	79	78
	e/D=2.0	97	96	95	95	93	92
e, per cent	L	7	7	7	7	7	7
	T	5	5	4	4	3	3
E, 10 ³ ksi		10.7					
E _c , 10 ³ ksi		10.7					
G, 10 ³ ksi		5.9					

TABLE XXVI

Computed Design Mechanical Properties of 7050-T76511 Extruded Shapes

ALLOY SPECIFICATION									
FORM		Extruded Shapes							
TEMPER		T76511							
CROSS-SECTIONAL AREA, in ²		220							
THICKNESS, in.	{		0.250-	0.500-	0.750-	1.000-	1.500-	2.000-	2.500-
		0.249	0.499	0.749	0.999	1.499	1.999	2.499	2.999
BASIS		Tentative							
MECHANICAL PROPERTIES									
F _{tu} , ksi	L	78	81	81	81	81	81	81	81
	LT	77	80	79	79	78	77	76	75
F _{ty} , ksi	L	70	73	72	72	72	72	72	72
	LT	69	71	70	69	69	68	67	66
F _{cy} , ksi	L	71	74	73	73	73	73	73	72
	LT	72	75	73	73	72	72	71	70
F _{su} , ksi		43	45	45	45	45	44	44	44
F _{brv} , ksi	e/D=1.5	115	119	119	118	117	116	115	114
	e/D=2.0	149	154	154	153	152	151	150	148
F _{brv} , ksi	e/D=1.5	96	100	98	98	97	96	95	93
	e/D=2.0	112	117	114	114	113	111	110	108
e, per cent	L	7	7	7	7	7	7	7	7
	LT	--	--	--	--	--	--	--	--
E, 10 ³ ksi		10.3							
E _c , 10 ³ ksi		10.7							
G, 10 ³ ksi		3.0							

TABLE XVIII

RESULTS OF TENSILE AND COMPRESSIVE STRESS-STRAIN AND
MODULUS OF ELASTICITY TESTS OF 7050 ALUMINUM
STRESS RANGE: 0 TO 100 KSI
(BASC Contract No. 60019-72-C-0512)

Product	Temp. °F.	Sample Thickness, in.	Longitudinal			Long-Transverse			Short-Transverse		
			Yield Strength,* ksi	Modulus, 10 ³ ksi	Yield Strength,* ksi	Modulus, 10 ³ ksi	Yield Strength,* ksi	Modulus, 10 ³ ksi	Yield Strength,* ksi	Modulus, 10 ³ ksi	Yield Strength,* ksi
Cast	77	C.040	72.9	10.21	73.3	10.15	73.3	10.15	73.3	10.15	73.3
		A11378	77.9	10.32	76.2	10.17	76.2	10.17	76.2	10.17	76.2
		A11382	81.1	10.35	77.4	10.43	77.4	10.43	77.4	10.43	77.4
		C.125	79.3	10.12	79.0	10.16	79.0	10.16	79.0	10.16	79.0
		A11309	80.0	10.03	79.9	10.35	79.9	10.35	79.9	10.35	79.9
Plate	77	AVG.		10.19		10.53		10.20		10.54	
		C.500	65.1	10.19	66.4	10.50	66.4	10.50	66.4	10.50	66.4
		A11184	65.4	10.38	65.2	10.36	65.2	10.36	65.2	10.36	65.2
		A11185	63.7	10.30	61.7	10.45	61.7	10.45	61.7	10.45	61.7
		A11189	60.9	10.13	58.4	10.51	58.4	10.51	58.4	10.51	58.4
Hard Forgings	77	AVG.		10.22		10.49		10.33		10.65	
		A11229	65.7	10.05	66.0	10.44	66.0	10.44	66.0	10.44	66.0
		A11352	68.5	10.14	71.5	10.52	71.5	10.52	71.5	10.52	71.5
		A11230	59.6	10.13	62.9	10.42	62.9	10.42	62.9	10.42	62.9
		A11353	69.5	10.15	72.6	10.43	72.6	10.43	72.6	10.43	72.6
Tie Forgings	77	AVG.		10.11		10.31		10.32		10.59	
		A11331	69.2	10.12	72.7	10.42	72.7	10.42	72.7	10.42	72.7
		A11351	66.2	10.51	71.1	10.71	71.1	10.71	71.1	10.71	71.1
		A11233	69.2	9.96	71.6	10.35	71.6	10.35	71.6	10.35	71.6
		A11332	69.7	10.32	73.3	10.46	73.3	10.46	73.3	10.46	73.3
Extruded Shapes	77	AVG.		10.19		10.53		10.25		10.70	
		A11288	78.1	1.37	76.7	10.76	76.7	10.76	76.7	10.76	76.7
		A11290	76.1	10.10	79.2	10.44	79.2	10.44	79.2	10.44	79.2
		A11287	80.1	9.98	78.2	10.40	78.2	10.40	78.2	10.40	78.2
		A11285	82.1	10.39	83.7	10.67	83.7	10.67	83.7	10.67	83.7

* Offset equals 0.2 per cent.

* During initial tests and retests specimens buckled before reaching 0.2 per cent offset.

* Compressive modulus of elasticity values are 1 to 2 per cent higher when computed within a stress range of zero to the elastic limit based on stress-strain tests to the yield stress. Average values shown in Tables of Computed Design Mechanical Properties (VIII) through (XVI) have been adjusted as shown in Table XVIII.

TABLE XXVIII
SUMMARY OF AVERAGE MODULUS OF ELASTICITY VALUES OF 7050 PRODUCTS
(NASC Contract No. W00019-72-C-0512)

Product	Temper	Average Modulus of Elasticity Values, 10 ³ ksi						Average for all Directions*	
		Tension (0 to 25 ksi)			Compression (0 to 25 ksi)			Tension	Compression
		Longitudinal	Transverse	Short-Transverse	Longitudinal	Long-Transverse	Short-Transverse		
Sheet	T76	10.19	10.20	--	10.53	10.54	--	10.2	10.5
Plate	T73651	10.22	10.33	10.06	10.49	10.65	10.50	10.3	10.5
Hard Forgings	T73652	10.12	10.28	10.13	10.42	10.63	10.53	10.2	10.5
Die Forgings	T736	10.19	--	10.15	10.53	--	10.52	10.2	10.5
Extruded Shapes	T76511	10.24	10.41	10.14	10.57	10.70	10.53	10.3	10.6

* Values weighted and rounded to nearest 100 ksi.

* Stress range: 0 to E.L. (elastic limit).

* Values are 1 to 3 per cent higher than those for stress range of 0 to 25 ksi. There are the values shown in Tables XXVII through XXIX.

TABLE XIV
RESULTS OF COMPRESSION PLATING TESTS SERIES OF 7050-T7451 PLATES
(BASC Contract No. 60010-70-0-0012)

Sample No.	Thick- ness, in.	Longitudinal (L-F)			Transverse (T-T)			Short-Transverse (S-S)		
		Thick- ness, in.	Section Location	Crack Length, in.	Thick- ness, in.	Section Location	Crack Length, in.	Thick- ness, in.	Section Location	Crack Length, in.
0.500	0.1277	61.1	Pull Thru	1.00	61.7	Pull Thru	0.55	61.5	7/2	0.75
1.000	0.1228	61.9	Pull Thru	1.00	61.2	Pull Thru	0.55	61.5	7/2	0.75
1.000	0.1228	61.4	Pull Thru	1.00	61.4	Pull Thru	0.55	61.5	7/2	0.75
2.000	0.1196	70.2	Pull Thru	1.00	70.0	Pull Thru	0.55	61.5	7/2	0.75
3.000	0.1138	61.9	Pull Thru	1.00	61.7	Pull Thru	0.55	61.5	7/2	0.75
4.000	0.1077	61.7	Pull Thru	1.00	61.5	Pull Thru	0.55	61.5	7/2	0.75
5.000	0.1107	61.7	Pull Thru	1.00	61.4	Pull Thru	0.55	61.5	7/2	0.75
6.000	0.1130	61.9	Pull Thru	1.00	61.2	Pull Thru	0.55	61.5	7/2	0.75
7.000	0.1130	61.7	Pull Thru	1.00	61.1	Pull Thru	0.55	61.5	7/2	0.75

Crack length 0.2 per cent.
a. Thick-ness, in. is given for the following reasons (letters in parentheses indicate K₁ values considered significant).
b. Section cut thick enough, 2.5 (100/10) is greater than section thickness.
c. Section cut thick enough, 2.5 (100/10) is greater than crack length.
d. Section cut thick enough, 2.5 (100/10) is greater than crack length.

TABLE VIII

RESULTS OF COMBUSTION-FATIGUE FRACTURE TESTS OF 7050-T7355 HAD PUNCHES
(MSC Contract No. D0019-72-C-0512)

Specimen No.	Load-Displacement (1-2)				Load-Displacement (2-3)				Short-Displacement (2-4)			
	Yield Strength, ksi	Crack Length, in.	$2.5 \left(\frac{K_I}{S_y} \right)^2$	K_I ksi/in.	Yield Strength, ksi	Crack Length, in.	$2.5 \left(\frac{K_I}{S_y} \right)^2$	K_I ksi/in.	Yield Strength, ksi	Crack Length, in.	$2.5 \left(\frac{K_I}{S_y} \right)^2$	K_I ksi/in.
2-1-7222260	72.6	1.50 1.50 Avg	0.37 0.33	28.0 26.2 27.1	71.3	1.50 1.50 Avg	0.17 0.18	18.3 18.3 18.8	67.6	0.75 0.75 Avg	0.19 0.15	18.7 18.6 18.6
2-1-7222260	67.3	1.50 1.50 Avg	0.47 0.46	29.3 29.2 29.4	65.5	1.50 1.50 Avg	0.40 0.43	26.2 26.2 26.7	61.3	1.00 1.00 Avg	0.23 0.22	18.5 18.5 18.5
2-1-7222260	61.1	1.50 1.50 Avg	0.78 0.79	33.2 33.8 33.5	60.2	1.50 1.50 Avg	0.32 0.32	21.9 21.7 21.8	56.5	1.50 1.50 Avg	0.30 0.29	18.4 18.3 18.4
2-1-7222260	70.0	1.50 1.50 Avg	0.47 0.46	30.2 30.2 30.2	66.0	1.50 1.50 Avg	0.36 0.39	22.7 22.7 22.6	64.4	1.50 1.50 Avg	0.27 0.26	21.1 21.1 21.2
2-1-7222260	61.2	1.50 1.50 Avg	0.58 0.50	30.3 30.3 30.6	59.3	1.50 1.50 Avg	0.31 0.32	20.9 21.2 21.0	61.1	1.50 1.50 Avg	0.19 0.20	16.8 16.8 16.8
2-1-7222260	62.1	1.50 1.50 Avg	0.82 0.82	37.7 35.5 36.6	60.2	1.50 1.50 Avg	0.33 0.28	21.9 20.0 20.3	57.3	1.50 1.50 Avg	0.33 0.31	26.4 26.4 26.4
2-1-7222260	60.0	1.50 1.50 Avg	0.59 0.61	31.5 30.8 31.2	62.5	1.50 1.50 Avg	0.28 0.29	21.1 21.3 21.2	57.1	1.50 1.50 Avg	0.28 0.27	18.3 18.3 18.3
2-1-7222260	66.8	1.50 1.50 Avg	0.56 0.56	34.0 33.2 33.6	66.2	1.50 1.50 Avg	0.22 0.21	19.7 19.0 19.4	62.1	1.50 1.50 Avg	0.27 0.23	20.8 20.8 20.8
2-1-7222260	60.9	1.50 1.50 Avg	0.76 0.65	33.7 32.0 32.8	60.9	1.50 1.50 Avg	0.25 0.25	19.2 19.2 19.2	57.6	1.50 1.50 Avg	0.24 0.24	18.0 18.0 18.0
2-1-7222260	61.9	1.50 1.50 Avg	0.76 0.66	33.7 32.0 32.8	62.7	1.50 1.50 Avg	0.25 0.23	18.4 17.9 18.4	58.1	1.50 1.50 Avg	0.21 0.20	25.0 25.0 25.0

* Offset equal to 0.2 per cent.
† Yield K_I values except as noted for the following reasons (letters in parenthesis indicate K_I values considered meaningful):
a - Residual yield strength was not determined; 40 and 0.5%
b - Residual yield strength was not determined; 40 and 0.5%
c - Residual yield strength was not determined; 40 and 0.5%
d - Residual yield strength was not determined; 40 and 0.5%
e - Residual yield strength was not determined; 40 and 0.5%
f - Residual yield strength was not determined; 40 and 0.5%
g - Residual yield strength was not determined; 40 and 0.5%
h - Residual yield strength was not determined; 40 and 0.5%
i - Residual yield strength was not determined; 40 and 0.5%
j - Residual yield strength was not determined; 40 and 0.5%
k - Residual yield strength was not determined; 40 and 0.5%
l - Residual yield strength was not determined; 40 and 0.5%
m - Residual yield strength was not determined; 40 and 0.5%
n - Residual yield strength was not determined; 40 and 0.5%
o - Residual yield strength was not determined; 40 and 0.5%
p - Residual yield strength was not determined; 40 and 0.5%
q - Residual yield strength was not determined; 40 and 0.5%
r - Residual yield strength was not determined; 40 and 0.5%
s - Residual yield strength was not determined; 40 and 0.5%
t - Residual yield strength was not determined; 40 and 0.5%
u - Residual yield strength was not determined; 40 and 0.5%
v - Residual yield strength was not determined; 40 and 0.5%
w - Residual yield strength was not determined; 40 and 0.5%
x - Residual yield strength was not determined; 40 and 0.5%
y - Residual yield strength was not determined; 40 and 0.5%
z - Residual yield strength was not determined; 40 and 0.5%

NOTE: Specimens loaded in center third of thickness and width of loading.

May 2000

Net equals 1.2 per cent.

Effect equals 1.2 per cent.

a. Life values except as noted for the following reasons:

1. Specimen not thick enough 2.5 (1/2) is greater than

2. Specimen yielding before crack extension.

3. Fatigue-crack front traverse exceeding allowed amount.

4. Stress-Intensity as too high.

5. Producer B, others Producer A

TABLE XXXIV

AVERAGE AXIAL-STRESS FATIGUE STRENGTHS FOR SMOOTH AND NOTCHED SPECIMENS TESTED IN SALT FOG
 $R = 0.0$, Transverse Specimens
 (NASC Contract No. N00019-72-C-0512)

Alloy	Product	Thickness or Size, in.	Fatigue Strength for Failure at Indicated Number of Cycles					
			Smooth Specimens		Notched Specimens (a)			
			10^5	2×10^6	10^7	10^5	2×10^6	10^7
7050-T76	Sheet	0.040	31	20	--	18	11	7.5
7475-T761	Sheet	0.040	28	20	--	16	11	9.5
7050-T76	Sheet	0.125	29	17	--	17	10	7.5
7475-T761	Sheet	0.125	36	26	--	18	13	--
7050-T73651	Plate	1.0 and 4.0	40	19	13	11	6	5
2124-T851	Plate	2.0 and 4.5	37	22	20	14	10	8
7050-T73652	Hand forging	2-1/2x22 and 5-1/2x22	45	18	13	13	7	6
7049-T73	Hand forging	4x16 and 5x20	42	25	--	14	11	11
7175-T73b	Hand forging	4x16 and 5x20	42	25	--	12	--	--
7050-T76511	Extruded shape	1.161 and 3.5x7.5	47	19	13	15	8	7

(a) Sheet: $K_t = 3$; plate, Hand Forging and Extruded Shape: $K_t \geq 12$

TABLE XXIV

RATES OF FATIGUE-CRACK PROPAGATION IN 7050 PRODUCTS
Constant Load Tests

(NASC Contract No. N00019-72-C-0512)

Alloy and Temper	Product	Thickness or Size, in.	Sample No.	Orientation in Figs.	Data Shown in Figs.	da/dN at Indicated ΔK (a)					
						Dry Air		Humid Air		Salt Fog	
						7	12	7	12	7	12
7050-T73	Sheet (b)	0.040	428385	T-L	146	3.5	13	7.0	28	29.5	40
		0.125	411212	T-L	147	4.6	24	9.0	50	12	58
	Sheet (c)	0.125	411212	L-T	148	4.7	23	8.5	53	13	53
	Sheet (d)	0.125	--	T-L	(d)	3.5	20	5.5	32	12	65
7050-T7352	Sheet	0.125	--	T-L	(d)	4.0	20	8.5	48	14	75
	Plate (c)	1	411185	T-L	149	1.9	19	4.2	24	6.5	45
		6	411300	T-L	150	1.4	14	2.6	28	4.0	30
		6	411300	L-T	151	1.2	14	2.6	20	5.0	28
7050-T7351	Plate (c)	6	411300	S-L	152	1.5	11	2.6	28	4.0	32
		4.5	--	T-L	(d)	2.5	12	4.0	25	3.0	28
7050-T73652	Hand Forging (c)	2-1/2x22	411229	T-L	153	0.9	19	1.5	26	9.0	46
		7-1/2x22	411232	T-L	154	2.8	100	4.4	140	9.0	150
		7-1/2x22	411232	L-T	155	1.2	5	3.8	10	5.5	22
		7-1/2x22	411232	S-L	156	1.9	>200	5.0	>300	5.5	>400
7050-T7356	Hand Forging (c)	5x20	411232	T-L	(d)	4.0	140	10	160		
	Hand Forging	5x20	--	T-L	(d)	3.5	24	7.0	40	8.0	36
7050-T73511	Extruded Shape (c)	1.161	411287	T-L	157	2.0	12	5.9	30	7.0	42
		1.161	411287	L-T	158	1.0	9	4.5	30	11	44
		5x6-1/4	411286	L-T	159	1.4	5	5.5	22	5.5	28
		5x6-1/4	411286	S-L	160	1.7	>100	6.0	>300	9.0	290

(a) ksi $\sqrt{\text{in.}}$

(b) Center notch specimen

(c) Compact specimen

(d) Ref. 12

TABLE XXXVI
RESULTS OF ACCELERATED EXFOLIATION TESTS OF 7050-T76 SHEET
(MSC CONTRACT NO. M0019-72-G-0512)

Sample Thickness, In.	Number	Long Transverse Y.S. (ksi)	Electrical Conductivity % IACS*	Visual Degree of Exfoliation†	
				7/10 Plane	7/10 Plane
0.040	428882**	73.5	39.4	None	None
0.040	428985	73.1	39.5	None	None
0.063	428884	73.0	38.5	None	None
0.063	411378#	78.2	38.7	A	None
0.090	411182#	77.0	38.6	A	None
0.090	411183	75.5	38.2	A	None
0.125	411212	77.9	37.9	A	None
0.125	411213#	77.2	37.7	A	None
0.222	416020	78.3	37.7	A	None
0.249	411309#	78.4	35.5	B	None

* Conductivity measurements made on T/10 surface.

† Ratings based upon ASTM standards for exfoliation (Designation: G34-72), with A thru D categories; D being the most severe.

T/10 panel from this item exposed in the sea-coast atmosphere 7/30/73.

** T/10 panel from this item exposed in the sea-coast atmosphere 4/29/74.

TABLE XXXVII
RESULTS OF ACCELERATED EXFOLIATION TESTS OF 7050-T73651 PLATE
(NASC CONTRACT NO. N00019-72-C-10312)

Sample Thickness, In.	Sample Number	Long Transverse Y.S., (ksi)	Electrical Conductivity % IACS*	Visual Degree of Exfoliation†			
				T/10 Plane	T/2 Plane	T/10 Plane	T/2 Plane
0.500	411372	65.7	42.7	A	A	--	--
0.500	411194#	67.2	41.1	A	A	None	None
1.000	411185#	65.4	41.9	A	A	None	None
1.000	411050	70.0	41.1	A	A	--	--
2.000	411186#	65.7	42.2	A	A	None	None
2.000	41077C	65.5	40.8	A	A	--	--
4.000	410777#	64.4	40.9	A	A	None	None
4.000	411187	63.2	41.1	A	A	--	--
6.000	411300	59.1	41.1	A	A	--	--
6.000	411330#	62.1	40.9	A	A	None	None

* Conductivity measurements made on T/2 surface.

+ Ratings based upon ASTM standards for exfoliation (Designation: G34-72), with A thru D categories; D being the most severe.

T/10 and T/2 panels from this item exposed in the seacoast atmosphere 8/1/73.

TABLE XXVIII

RESULTS OF ACCELERATED EXFOLIATION TESTS OF 7050-T736 DIE FORGINGS AND 7050-T73652
HAND FORGINGS
(NASC CONTRACT NO. N00019-72-C-0512)

Sample Thickness Range Or Dimensions, In.	Sample		Longitudinal Y.S. (ksi)	Electrical Conductivity, % IACS*	Visual Degree of Exfoliation	
	Number	Die Number			T/10 Plane	T/2 Plane
<u>7050-T736 Die Forgings</u>						
< 1.000**	411243	2177	75.4	41.2	--	None
< 1.000	411331	9078	72.9	41.8	--	None
1.001 - 2.000	411351	15789	69.1	41.3	--	None
1.001 - 2.000	411281	17975	68.0	40.9	--	None
1.001 - 2.000	411297	17944	68.8	40.7	--	None
2.001 - 4.000**	411392	1364	64.7	40.5	--	None
3.001 - 4.000	411332	8457	70.2	41.4	--	None
4.001 - 5.000**	411244	4736	69.0	41.4	--	None
4.001 - 5.000	411233	12767	69.3	41.5	--	None
6.000 - 7.000	411303	16392	63.2	41.3	--	None
<u>7050-T73652 Hand Forgings</u>						
2.5 x 22	411229	--	67.3	42.2	A	A
7.5 x 22	411231	--	60.9	42.3	A	A

* Conductivity measurements made on T/2 surface.

+ Ratings based upon ASTM standards for exfoliation (Designation: G34-72), with A thru D categories; D being the most severe.

** Producer B, all others from Producer A.

TABLE XXXIX

RESULTS OF ACCELERATED EXFOLIATION TESTS OF 7050-T76511 EXTRUDED SHAPES
NASA CONTRACT NO. D00019-72-C-0512)

Sample Thickness or Size In.	Sample Number	Longitudinal Y.S. (ksi)	Electrical Conductivity % IACS *	Visual Degree of Exfoliation†			
				EXFO		ASTM BASIS	
				T/10 Plane	T/2 Plane	T/10 Plane	T/2 Plane
0.187	411288	75.9	39.7	A	A	--	--
0.402	411289	75.6	39.0	A	A	--	--
0.665	411290#	78.2	39.2	A	A	None	A
0.841**	411552#	75.2	38.2	A	A	A	A
1.161	411287	76.4	40.2	A	A	--	--
1.5 x 7.5	411284#	78.4	39.7	A	A	A	A
2.0 x 8.0 **	411279	75.6	39.5	A	A	--	--
3.5 x 7.5	411285#	80.5	39.5	A	A	A	A
4.0 x 8.0 **	411280#	79.7	39.4	A	A	A	None
5 x 6.25	411286	82.3	39.3	A	A	--	--

* Conductivity measurements made on T/2 surface.

+ Ratings based upon ASTM standards for exfoliation (Designation: G34-72), with A thru D categories; D being the most severe.

T/10 and T/2 panels from this item exposed in the seacoast atmosphere 8/1/73 or

** Producer B, all others from Producer A.

TABLE XL
RESULTS OF ACCELERATED SCC TESTS OF 7050-T76 SHEET
(NASC CONTRACT NO. W00019-72-C-0512)

Sample Thickness, In.	Sample Number	Electrical Conductivity, % IACS *	Tensile Properties TS ksi	Per Cent Loss in Tensile Strength Unstressed	Stress-Corrosion Cracking Data		
					75% Y.S. F/N ⁺	Days	Days
0.040	428882	39.4	81.6 73.5 10.0		0/2	OK 112	0/2 OK 146
0.063	411378	38.7	84.3 78.2 10.0	26	0/2	OK 182	0/2 OK 182
0.090	411182	38.6	83.9 77.0 11.0	24	0/2	OK 182	0/2 OK 182
0.125	411213	37.7	83.0 77.2 11.5	23	0/2	OK 182	0/2 OK 182
0.249	411309	35.5	83.5 78.4 13.0	33	0/2	OK 182	0/2 OK 182

Note: Test specimens: Long-transverse sheet tensile and preforms, 0.040 and 0.063-In. gauges tests of full thickness, other gauges machined on one surface to 0.063 in. and rolled surface stressed in tension.

Test environment: 3.5% NaCl - Alternate Immersion per Federal Method 823. Maximum test duration 182 days.

* Conductivity measurements made on T/2 surface.

+ F/N denotes number of specimens failed over number of specimens exposed.

TABLE XII

RESULTS OF ACCELERATED SOC TESTS OF 7050-T7351 PLATE
(NASC CONTRACT NO. DD010-72-5-512)

Sample No.	Electrical Conductivity, % IACS*	Test Division	Tensile Properties T.S., T.S., Y.S., Y.S., Elong., Elong.	Percent Loss in Tensile Strength Derived From T.S., Y.S., Elong., Elong.	Stress-Corrosion Cracking Data			
					7050-T7351 Y.S., Y.S., Elong., Elong.	7050-T7351 Y.S., Y.S., Elong., Elong.	7050-T7351 Y.S., Y.S., Elong., Elong.	7050-T7351 Y.S., Y.S., Elong., Elong.
0.500	42.7	L	75.9 66.1 15.7	27	71	--	0/3	0/3
		IT	75.3 65.7 15.7	32	99	--	2/3	182, 182 (100, 100)
0.500	41.9	L	76.5 66.9 15.0	27	78	--	1/3	182, 2- 0/102
		IT	76.5 67.2 14.5	31	--	--	3/3	101 182, 182
2.000	42.2	ST	72.9 61.5 7.8	31	--	67	66	52
		ST	70.9 62.2 4.9	29	--	--	67	44
4.000	40.9	L	74.0 65.3 12.0	36	--	--	3/3	118 148, 182
		IT	75.6 64.4 11.0	34	81	--	0/3	0/3
4.000	41.1	L	72.0 65.7 11.0	33	76	--	2/3	153, 2- 0/102
		IT	73.3 65.2 10.0	37	--	--	3/3	112 129, 182
4.000	41.1	L	69.9 59.7 7.1	34	--	70	62	46
		IT	69.9 59.7 7.1	34	--	70	62	46

Note: 0.125-in. diameter tensile specimens exposed to 3.5% NaCl-Alternate Immersion per Federal Method B23. Marine test duration 84 days for short-transverse (ST) and 182 days for longitudinal (L) and long-transverse (IT) specimens.

* Conductivity measurements made on T/2 surface.

+ F/N denotes number of specimens failed over number of specimens exposed.

TABLE XXX
RESULTS OF ACCELERATED SCC TESTS OF 7050-T7352 HARD FIBERS
(P/Ns: CONDUCT 80, 80018-72-0-0512)

Sample Dimensions, In.	Electrical Conductivity § 1A29 *	Test Direction	Tensile Properties TS YS		Per Cent Loss in Tensile Strength					Stress-Corrosion Cracking Data								
			ksi	ksi	§ 1E1, ksi	§ 1E2, ksi	§ 1E3, ksi	§ 1E4, ksi	§ 1E5, ksi	72 hr TS YS	168 hr TS YS	25 hr TS YS	72 hr TS YS	168 hr TS YS	25 hr TS YS			
2 x 6 **	411354	ST	78.7	67.6	4.7	35	--	--	56	43	--	--	3/3	75.82, 84	1/3	82.2- 84	0/3	OK 84
2.5 x 22	411229	L	75.7	67.3	10.5	35	72	--	--	--	--	2/3	182.182, OK 182	--	--	--	--	--
		LT	75.9	55.5	13.0	37	63	--	--	--	--	1/3	160 (2 OK 152)	--	--	--	--	
		ST	74.3	51.3	10.0	32	--	--	54	43	--	--	3/3	53.73, 70	2/3	52.80, 1-OK 84	0/3	OK 84
4.5 x 22	411302	L	72.2	63.2	11.5	35	70	--	--	--	--	0/3	OK 182	--	--	--	--	--
		LT	70.1	59.3	10.5	44	--	--	--	--	--	3/3	181.184, 182	--	--	--	--	--
		ST	71.5	61.1	7.1	40	--	56	43	--	--	0/3	OK 84	1/3	42.2- OK 84	0/3	OK 84	
5.5 x 22	411353	ST	73.4	62.1	6.0	34	--	--	35	--	--	3/3	71.82, 84	0/3	OK 84	0/3	OK 84	
7.5 x 22	411231	L	71.0	60.9	13.0	35	57	--	--	--	--	1/3	182.12, OK 182	--	--	--	--	--
		LT	70.9	60.9	5.5	50	--	--	--	--	--	3/3	66.69, 69	--	--	--	--	--
		ST	69.5	57.8	5.0	35	--	56	43	--	--	1/3	84.2- OK 84	0/3	OK 84	0/3	OK 84	

Note: 0.125 in. diameter tensile specimens exposed to 3.5% NaCl - Alternate Immersion per Federal Method B23. Maximum test duration 84 days for short-transverse (ST) and 182 days for longitudinal (L) and long-transverse (LT) specimens.

* Conductivity measurements made on T/2 surface.

+ P/N denotes the number of specimens failed over number of specimens exposed.

** Producer B, all others from Producer A.

TABLE XIII
RESULTS OF ACCELERATED SO₂ TESTS OF 7050-7736 INS FURNISHING
(NBS CONTRACT NO. 5701G-77-5-012)

Tensile Specimen Designation	Elastic Limit, ksi	Tensile Strength, ksi	Elongation, %	Per Cent Loss In Tensile Strength, %	Specimens Surviving in Corrosion Test			
					25	50	75	100
(1.000)**	2177	73.8	64.5	8.0	31	56	42	—
(1.000)	9076	73.1	63.5	9.0	36	65	50	—
1.001-2.000	15769	76.0	69.1	8.5	30	—	3/3	129, 143, 170
1.001-2.000	17975	75.2	68.1	7.5	30	—	50	40
1.001-2.000	17975	75.3	66.7	7.0	33	—	—	45
1.001-2.000	17944	74.5	68.0	6.5	28	—	56	36
2.001-4.000**	1369	65.6	58.9	3.5	26	—	72	52
2.001-4.000	8457	75.7	68.3	7.1	35	—	—	49
4.001-5.000**	4796	71.3	63.6	5.0	30	—	55	54
4.001-5.000	12767	75.6	69.3	14.0	36	—	—	3/3
6.001-7.000	16392	74.4	66.5	7.1	32	—	—	42
		72.9	65.7	4.0	42	—	—	50

Note: 0.125 in. diameter tensile specimens exposed to 3.5% SO₂ - Alternate Immersion per Federal Method B93. Maximum test duration 60 days for short-transverse (ST) and 182 days for longitudinal (L) specimens.

* Conductivity measurements made on 7/2 surface.

- P/N denotes the number of specimens failed over number of specimens exposed.

** Producer 2, all others from Producer 1.

RESULTS OF ACCELERATED SCC TESTS OF 7050-T6511 EXTRUDED SHAPES
(MIL-STD-883C METHOD 201.10, E-1018-72-5-0512)

Sample Thickness or Size, In.	Electrical Conductivity % IACS	Test Direction	Tensile Properties TS ksi	Per Cent Loss in Tensile Strength		Stress-Corrosion Cracking Data					
				Unstressed	Stressed	TS, ksi	TS, ksi	TS, ksi	TS, ksi	TS, ksi	TS, ksi
0.402	39.0	L	83.8	75.6	14.0	33	--	--	3/3	67,182, 182	--
		LT	83.4	73.0	10.0	35	--	--	3/3	74,104, 162	--
0.665	39.2	L	85.4	78.2	14.3	34	--	--	3/3	87,174, 182	--
		LT	84.1	76.9	12.9	37	--	--	3/3	70, 85, 90	--
0.941**	38.2	L	82.8	75.2	11.3	34	--	--	3/3	94,107, 147	--
		LT	81.6	74.1	11.0	33	--	--	3/3	80,87, 91	--
1.5 x 7.5	39.7	ST	82.3	59.8	8.0	43	--	--	--	3/3	4,4,4 3/3 3,3,3 10,45,66**
2.0 x 8.0**	39.5	ST	76.0	66.7	6.0	35	--	69	--	3/3	38,49, 3/3 56,62, 1/3 71, 2 53 71
3.5 x 7.5	39.5	L	86.6	50.5	11.3	34	--	--	3/3	83,86, 116	--
1.0 x 8.0**	39.4	LT	80.3	74.1	7.0	34	--	--	3/3	82,60, 63	--
		ST	79.9	70.9	2.9	42	--	52	--	3/3	12,14, 2/3 28,39, 1/3 77, 2 14 50
		ST	75.1	68.9	2.9	36	--	49 41	--	3/3	45,60, 1/3 73, 2-0/3 84 70 84

Note: 0.125-in. diameter tensile specimens exposed to 3.5% NaCl - Alternate Immersion per Federal Method 823. Maximum test duration 84 days for short-transverse (ST) and 182 days for longitudinal (L) and long transverse (LT) aged bars.

- * Conductivity measurements made on 1/2 surface.
- ** Indicates the number of specimens failed over number of specimens exposed.
- ** Specimens 1, all of one size produced 1.

Secondary test results for specimens stressed at 15, 20 and 25 ksi:

Stress, ksi	TS, ksi	TS, ksi	TS, ksi
15	5/4	3/3	5/4
20	5/4	5/4	5/4
25	5/4	5/4	5/4

TABLE XLV

STATUS OF ATMOSPHERIC SCC TESTS OF 7050-T76 SHEET
(NASC Contract No. N00019-72-C-0512)

Sample Thickness In.	Number	Stress-Corrosion Cracking Data			
		75% Y.S.		Preforms	
		F/N+	Days	F/N+	Days
<u>Seacoast Atmosphere</u>					
0.040	428882	0/2	OK - 354	0/2	OK - 417
0.063	411378	0/2	OK - 606	0/2	OK - 606
0.090	411182	0/2	OK - 606	0/2	OK - 606
0.125	411213	0/2	OK - 606	0/2	OK - 606
0.249	411309	0/2	OK - 606	0/2	OK - 606
<u>Industrial Atmosphere</u>					
0.040	428882	0/2	OK - 373	0/2	OK - 430
0.063	411378	0/2	OK - 660	0/2	OK - 660
0.090	411182	0/2	OK - 660	0/2	OK - 660
0.125	411213	0/2	OK - 660	0/2	OK - 660
0.249	411309	0/2	OK - 660	0/2	OK - 660

Note: Test Specimens: Long-transverse sheet tensile and preforms, 0.040 and 0.063 in. gauges tested full thickness, other gauges machined on one surface to 0.063 in. and rolled surface stressed in tension.

+ F/N denotes number of specimens failed over number exposed.

TABLE XLVI

STATUS OF ATMOSPHERIC SCC TESTS OF 7050-T73651 PLATE
(NASC Contract No. NC0019-72-C-0512)

Sample Thickness in.		Stress-Corrosion Cracking Data					
		45 ksi		35 ksi		25 ksi	
		F/N+	Days	F/N	Days	F/N	Days
<u>Seacoast Atmosphere</u>							
2.0	411186	0/3	OK - 730	0/3	OK - 730	0/3	OK - 730
2.0	410778	0/3	OK - 730	0/3	OK - 730	0/3	OK - 730
4.0	410777	0/3	OK - 730	0/3	OK - 730	0/3	OK - 730
4.0	411187	0/3	OK - 730	0/3	OK - 730	0/3	OK - 730
<u>Industrial Atmosphere</u>							
2.0	411186	0/3	OK - 763	0/3	OK - 763	0/3	OK - 763
2.0	410778	0/3	OK - 763	0/3	OK - 763	0/3	OK - 763
4.0	410777	0/3	OK - 763	0/3	OK - 763	0/3	OK - 763
4.0	411187	0/3	OK - 763	0/3	OK - 763	0/3	OK - 763

Note: 0.125 in. diameter short-transverse tensile specimens.

+ F/N denotes number of specimens failed over number exposed.

TABLE XLVII.

STATUS OF ATMOSPHERIC SCC TESTS OF 7050-T73652 HAND FORGINGS
(NASC Contract No. N00019-72-C-0512)

Sample Dimensions In.	Number	Stress-Corrosion Cracking Data					
		45 ksi		35 ksi		25 ksi	
		F/N+	Days	F/N	Days	F/N	Days
<u>Seacoast Atmosphere</u>							
2 x 8**	411354	2/3	360, 360, (1-OK-605)	0/3	OK - 605	1/3	360 (2-OK-605)
2.5 x 22	411229	0/3	OK - 605	0/3	OK - 605	0/3	OK - 605
4.5 x 22	411302	0/3	OK - 605	0/3	OK - 605	0/3	OK - 605
5.5 x 22	411353	1/3	539, (2-OK-605)	0/3	OK - 605	0/3	OK - 605
7.5 x 22	411231	0/3	OK - 605	0/3	OK - 605	0/3	OK - 605
<u>Industrial Atmosphere</u>							
2 x 8**	411354	0/3	OK - 665	0/3	OK - 665	0/3	OK - 665
2.5 x 22	411229	0/3	OK - 665	0/3	OK - 665	0/3	OK - 665
4.5 x 22	411302	0/3	OK - 665	0/3	OK - 665	0/3	OK - 665
5.5 x 22	411353	0/3	OK - 665	0/3	OK - 665	0/3	OK - 665
7.5 x 22	411231	0/3	OK - 665	0/3	OK - 665	0/3	OK - 665

Note: 0.125 in. diameter short-transverse tensile bars.

+ F/N denotes number of specimens failed over number exposed.

** Producer B; all others from Producer A.

TABLE XLVIII
STATUS OF ATMOSPHERIC SCC TESTS OF 7050-T736 DIE FORGINGS
(NASC Contract No. N00019-72-C-0512)

Sample		Stress-Corrosion Cracking Data					
Thickness Range, In.	Number	45 ksi		35 ksi		25 ksi	
		F/N*	Days	F/N	Days	F/N	Days
<u>Seacoast Atmosphere</u>							
<1.000**	411243	0/3	OK - 605	0/3	OK - 605	0/3	OK - 605
<1.000	411331	0/3	OK - 605	0/3	OK - 605	0/3	OK - 605
1.001-2.000	411351	0/3	OK - 605	0/3	OK - 605	0/3	OK - 605
1.001-2.000	411281	1/3	139, (2-OK-605)	1/3	271, (2-OK-605)	0/3	OK - 605
1.001-2.000	411297	0/2	OK - 605	0/3	OK - 605	0/3	OK - 605
2.001-4.000**	411392	0/3	OK - 605	0/3	OK - 605	0/3	OK - 605
2.001-4.000	411332	3/3	139,139,139	2/3	139,360, (1-OK-605)	0/3	OK - 605
4.001-5.000**	411244	0/3	OK - 605	0/3	OK - 605	0/3	OK - 605
4.001-5.000	411233	3/3	139,139,185	3/3	271,360,360	0/3	OK - 605
6.001-7.000	411303	3/3	139,139,139	3/3	139,139,360	0/3	OK - 605
<u>Industrial Atmosphere</u>							
<1.000**	411243	0/3	OK - 673	0/3	OK - 673	0/3	OK - 673
<1.000	411331	0/3	OK - 673	0/3	OK - 673	0/3	OK - 673
1.001-2.000	411351	0/3	OK - 605	0/3	OK - 605	0/3	OK - 605
1.001-2.000	411281	0/3	OK - 673	0/3	OK - 673	0/3	OK - 673
1.001-2.000	411297	0/3	OK - 673	0/3	OK - 673	0/3	OK - 673
2.001-4.000**	411392	0/3	OK - 605	0/3	OK - 605	0/3	OK - 605
2.001-4.000	411332	0/3	OK - 673	0/3	OK - 673	0/3	OK - 673
4.001-5.000**	411244	0/3	OK - 605	0/3	OK - 605	0/3	OK - 605
4.001-5.000	411233	1/3	329, (2-OK-673)	0/3	OK - 673	0/3	OK - 673
6.001-7.000	411303	0/3	OK - 673	0/3	OK - 673	0/3	OK - 673

Note: 0.125 in. diameter short-transverse tensile specimens.

* F/N denotes number of specimens failed over number exposed.

** Producer B; all others from Producer A.

TABLE XLIX

STATUS OF ATMOSPHERIC SCC TESTS OF 7050-T76511 EXTRUDED SHAPES
(NASC Contract No. N00019-72-C-0512)

Sample Dimensions, In.	Number	Stress-Corrosion Cracking Data					
		45 ksi		35 ksi		25 ksi	
		F/N+	Days	F/N	Days	F/N	Days
<u>Seacoast Atmosphere</u>							
1.5 x 7.5	411284	3/3	75,75,75	3/3	75,75,75	2/3	75,445, (1-OK-680)
2.0 x 8.0**	411279	3/3	75,359,445	1/3	445, (2-OK-680)	0/3	OK - 680
3.5 x 7.5	411285	3/3	75,75,75	3/3	75,75,359	1/3	224, (2-OK-680)
4.0 x 8.0**	411280	3/3	224,224,224	3/3	224,224,359	0/3	OK - 680
<u>Industrial Atmosphere</u>							
1.5 x 7.5	411284	0/3	OK- 721	0/3	OK - 721	0/3	OK - 721
2.0 x 8.0**	411279	0/3	OK - 721	0/3	OK - 721	0/3	OK - 721
3.5 x 7.5	411285	0/3	OK - 721	0/3	OK - 721	0/3	OK - 721
4.0 x 8.0**	411280	0/3	OK - 721	0/3	OK - 721	0/3	OK - 721

Note: 0.125 in. diameter short-transverse tensile bars.

+ F/N denotes number of specimens failed over number exposed.

** Producer B; all others from Producer A.

TABLE I

SUMMARY OF CORROSION PERFORMANCE OF ALLOY 7050 PRODUCTS RELATIVE TO
ANTICIPATED CORROSION TARGETS*
(NASC Contract No. N00019-72-C-0512)

Product	Temper	No. Lots #	Thick. Range, In.	Corrosion Targets- Resistance		Met. Target?	
				SCC	Exfoliation	SCC	Exfoliation
Sheet	T76	5	0.040-0.249	7075-T76	7075-T76	Yes	Yes
Plate	T7351	6	0.500-4.000	< 7075-T7351 > 7075-T7651	7075-T7351	Yes	No**
Hand Forgings	T7352	5	2.000-7.500	7175-T736	7175-T736	Yes	Yes
Die Forgings	T736	10	< 1.000-7.000	7175-T736	7175-T736	Yes	Yes
Extrusions	T76511	7	0.402-4.000	7075-T76511	7075-T76511	Yes++	Yes

* Anticipated performance per Alcoa Green Letter: Alcoa Alloy 7050, (4-73).

+ Principal corrosion target boxed; when no corrosion target is boxed, the primary target for the product was some other characteristic such as tensile properties.

Designates number of lots SCC tested with smooth specimens. Exfoliation tests conducted on all lots of each product but hand forgings. Two lots tested for latter.

** Exfoliation was degree F-A; 7075-T7351 showed no exfoliation.

++ One section required additional aging at ATC.

TABLE LI

RESULTS OF SCC TESTS OF PRECASTED SPECIMENS FROM 7050-77551 PLANS
(SEE CONTRACT NO. DAH10-72-1-0112)

Thickness, In.	Specimen Number	Test Specimen	C.O.D., In.	Crack Length, In.		Environmental Crack Growth, In.	Stress-Intensity Calculated		Plane-Strain Fracture Toughness
				Initial	Final		K _I , ksi $\sqrt{\text{in.}}$	K _{II} , ksi $\sqrt{\text{in.}}$	
1.000	411185	SL1	0.029	0.803	0.951	0.058	29.7	26.8	---
		SL2	0.031	0.860	0.942	0.062	31.9	25.8	
2.000	411186	SL1	0.033	0.842	1.029	0.087	30.9	27.2	23.3
		SL2	0.031	0.858	0.937	0.079	33.0	29.2	
2.000	410778	SL1	0.030	0.806	0.975	0.123	34.8	28.4	25.6
		SL2	0.031	0.878	0.956	0.078	32.0	28.4	
4.000	410777	SL1	0.031	0.774	0.839	0.064	32.0	34.2	25.4
		SL2	0.031	0.694	0.968	0.071	33.1	29.6	
4.000	411187	SL1	0.030	0.766	0.846	0.080	37.3	32.6	23.6
		SL2	0.029	0.839	0.876	0.037	31.9	30.1	
6.000	411300	SL1	0.030	0.838	0.874	0.036	32.0	31.2	24.7
		SL2	0.028	0.852	0.860	0.028	31.1	29.7	

Note: Test Specimen: Short-transverse (SCL) double cantilever beam bolt loaded to pay-18.
Test Environment: Air at 80°F, 45% R.H. plus 3.5% NaCl droplets three times a day for 30 days.

* Includes both the mechanical precrack and the environmental crack growth.

TABLE LII

RESULTS OF SCC TESTS OF PRECRACKED SPECIMENS FROM 7050-T76 HIR FORGINGS
(BASE DATA OF DR. BUNN-27-1-1512)

Thickness, in.	Sample Number	Mo. No.	Test Specimen	C.O.D., inches	Crack Length, inches		Environmental Crack Growth, inches	Stress-Intensity Calculations		Plane- Strain Fracture Threshold K_{Ic} , ksi $\sqrt{in.}$
					Initial	Final		K_{Ic} , ksi $\sqrt{in.}$	K_{Ic} , ksi $\sqrt{in.}$	
1.001 - 2.000	411351	15705	SL1	0.027	0.898	1.115	0.217	27.0	19.8	26.0
			SL2	0.025	0.949	1.122	0.175	23.1	18.1	
1.001 - 2.000	411361	17975	SL1	0.022	0.693*	0.771*	0.132	33.2	26.2	24.2
			SL2	0.020	0.713	0.866	0.149	27.0	21.0	
2.001 - 4.000**	411392	1964	SL1	0.021	0.819	0.966	0.147	25.8	19.0	23.5
			SL2	0.026	0.884	0.786	0.102	37.4	31.2	
2.001 - 4.000	411332	3457	SL1	0.013	0.732	1.023	0.231	21.4	14.9	23.2†
			SL2	0.020	0.876	1.100	0.224	20.7	14.9	
4.001 - 5.000	411233	12767	SL1	0.023	0.901	1.302	0.401	22.9	13.3	23.2†
			SL2	0.019	0.843	1.212	0.369	20.7	12.3	
6.001 - 7.000	411303	16392	SL1	0.020	0.894	1.205	0.301	20.1	13.0	21.2
			SL2	0.021	0.865	1.213	0.330	21.5	13.5	

Note: Test Specimen: Short-transverse (S-T) double cantilever beam bolt loaded to pop-in.
Test Environment: Air at 80°F, 45% R.H. plus 3.5% NaCl droplets three times a day for 30 days.

* Includes both the mechanical precrack and the environmental crack growth.

+ Crack front showed considerable deviation from intended plane of fracture.

† Did not meet ASTM criteria for valid K_{Ic} values.

** Producers B, all others from Producer A.

TABLE LIII

RESULTS OF SCC TESTS OF PRECRACKED SPECIMENS FROM 709-776311 EXPOSED SAMPLES
(NASC CONTRACT NO. DDAG-72-0-0512)

Thickness or Size, in.	Sample Number	Test Specimen	C.O.D. in.	Crack Length, in. (in.)	Crack Length, in. (in.)	Environmental Crack Growth, in.	Stress-Intensity Factor, K_{Ic}		Plane-Strain Fracture Toughness, K_{Ic} ksi $\sqrt{in.}$
							ksi $\sqrt{in.}$	ksi $\sqrt{in.}$	
1.161	411287	SL1 SL2	0.022 0.020	0.888 0.885	1.231 1.231	0.217 0.331	22.4 22.5	13.9 13.9	---
1.5 x 7.5	411288	SL1 SL2	0.020 0.021	0.838 0.820	1.260 1.255	0.421 0.435	22.0 23.8	12.2 12.9	22.2
2.0 x 8.0 **	411279	SL1 SL2	0.015 0.020	0.838 0.858	1.010 1.016	0.172 0.158	20.9 21.3	16.1 16.8	18.2
3.5 x 7.5	411295	SL1 SL2	0.017 0.016	0.846 0.818	1.186 1.150	0.340 0.332	18.5 18.2	11.4 11.2	16.4
4.0 x 8.0 **	411280	SL1 SL2	0.017 0.018	0.809 0.810	1.004 1.027	0.195 0.217	19.6 20.8	14.5 14.9	18.2
5 x 6.25	411286	SL1 SL2	0.018 0.018	0.874 0.840	1.129 1.106	0.237 0.268	19.3 19.7	12.9 13.5	18.0

Notes: Test Specimen: Short-tensile (S-L) double cantilever beam bolt loaded to pop-in.
Test Environment: Air at 50°F, 45° R.H., plus 3.5% NaCl droplets three times a day for 30 days.

* Includes both the mechanical precrack and the environmental crack growth.

** Producer B, all others from Producer A.

Table LIV

RESULTS OF TESTS OF RING LOADED SHORT TRANSVERSE COMPACT SPECIMENS
OF 7050-T73651 PLATE AND 7050-T76511 EXTRUDED SHAPES

Specimen Number	Initial Values				Values at Fracture								
	Target		Calculated (b)		Estimated		Calculated (b)		Time to Failure hrs.				
	Crack Length in. (a)	Load lb.	K_{Ii} ksi- $\sqrt{\text{in.}}$	K_{IC}	Crack Length in. (c)	K_{If} ksi- $\sqrt{\text{in.}}$	Crack Length in.	Load lb.					
										K_{If} ksi- $\sqrt{\text{in.}}$			
7050-T73651 Plate (S. No. 410777)													
S-L-1	1.005	3660	25.0	98	1.062 (d)	3650	27.4 (d)	1.060	27.2	1.089 (d)	3650	28.5 (d)	120
S-L-2	1.010	3330	22.9	90	1.048	3350	24.3	1.250	33.9	1.237	3200	33.0	1704
S-L-3	1.010	3140	21.6	85	1.034	3140	22.4	1.250	31.9	1.211	3010	29.4	3120
S-L-4	1.000	2790	19.0	75	1.038	2790	20.1	----	----	1.178 (e)	2710 (e)	24.9 (e)	3600
7050-T76511 Extruded Shape (S. No. 411286)													
S-L-1	1.000	2120	14.4	80	1.038	2130	15.3	1.096	16.6	1.115	2110	17.2	120
S-L-2	1.005	1850	12.6	70	1.078	1850	14.2	1.310	21.0	1.328	1730	21.9	540
S-L-3	1.005	1570	10.8	60	1.030	1570	11.2	1.323	18.3	1.333	1450	18.7	822
S-L-4	1.000	1325	9.0	50	1.034	1330	9.5	1.405	17.6	1.405	1145	19.8	2860

(a) Initial crack lengths were averages of measurements on both sides of specimen.

(b) Calculated values based on measurements of loads and crack opening displacements.

(c) Final crack lengths measured on fracture surfaces.

(d) Relatively high calculated values may be due to plastic deformation during loading.

(e) Test terminated before specimen failed.

APPENDIX

FATIGUE CRACK-GROWTH DATA FOR 7050-T76 SHEET
Constant Load Tests, Stress Ratio = +1/3
NASC Contract N00019-72-C-0512

[illegible]

Notes: CN = Center Notch Specimen, Fig. 41
Crack lengths are average readings on front and back surface. Total notch length includes machined flaw of 0.20.
T = Specimen thickness

Reproduced from
best available copy.

FATIGUE CRACK-GROWTH DATA FOR 7050-T76 SHEET
Constant Load Tests, Stress Ratio = 1/3
NASC Contract N00019-72-C-0512

[illegible]

Notes: CN = Center Notch Specimen, Fig. 41
Crack lengths are average readings on front and back surface. Total notch length includes machined flaw of 0.20.
T = specimen thickness.

FATIGUE CRACK-GROWTH DATA FOR 7050-T73651 PLATE
Constant Load Tests, Stress Ratio = +1/3
NASC Contract N00019-72-C-0512

[illegible][illegible][illegible]

T = Specimen thickness.

FATIGUE CRACK-GROWTH DATA FOR 7050-T73651 PLATE
Constant Load Tests, Stress Ratio = +1/3
NASC Contract N00014-72-C-0512

Notes: CT = Compact tension crack growth specimen,
Fig. 42.
Crack lengths measured from load line.

T = Specimen thickness.

FATIGUE CRACK-GROWTH DATA FOR 7050-T73652 HAND FORGING
Constant Load Tests, Stress Ratio = +1/3
NASC Contract N00019-72-C-0512

Notes: CT = Compact tension crack growth specimen, Fig. 42.
Crack lengths measured from load line.

-293-

Table LVII(conc.)

PATIENCE CRACK-GROWTH DATA FOR 7050-T73652 HAND FORGING
Constant Load Tests, Stress Ratio = $\pm 1/3$
NASC Contract N00019-72-C-0512

STRESS RATIO = $\pm 1/3$ - CONSTANT LOAD TESTS									
Specimen	Crack Length	Crack Length	Crack Length	Crack Length	Crack Length	Crack Length	Crack Length	Crack Length	Crack Length
1	2	3	4	5	6	7	8	9	10
11	12	13	14	15	16	17	18	19	20
21	22	23	24	25	26	27	28	29	30
31	32	33	34	35	36	37	38	39	40
41	42	43	44	45	46	47	48	49	50
51	52	53	54	55	56	57	58	59	60
61	62	63	64	65	66	67	68	69	70
71	72	73	74	75	76	77	78	79	80
81	82	83	84	85	86	87	88	89	90
91	92	93	94	95	96	97	98	99	100

Notes: CT = Compact tension crack growth specimen, Fig. 42.
Crack lengths measured from load line.
T = Specimen thickness.

Reproduced from
best available copy.

FATIGUE CRACK-GROWTH DATA FOR 7050-T76511 EXTRUDED SHAPES
Constant Load Tests, Stress Ratio = +1/3
NASC Contract N00019-72-C-0512

Notes: CT = Compact Tension Crack Growth Specimen, Fig. 42.
Crack lengths measured from load line.
T = specimen thickness.

-295-

FATIGUE CRACK-GROWTH DATA FOR 7050-T76511 EXTRUDED SHAPES
Constant Load Tests, Stress Ratio = +1/3
NASC Contract N00019-72-C-0512

Notes: CT = Compact Tension Crack Growth Specimen, Fig. 42.
Crack lengths measured from load line.
T = specimen thickness.

Reproduced from
best available copy.