

AD-A040 013




ARMY INST OF DENTAL RESEARCH WASHINGTON D C
SEALING QUALITY OF A TEMPORARY FILLING MATERIAL.(U)
MAY 77 R T WEBBER, C E DEL RIO, J M BRADY

F/G 6/5


UNCLASSIFIED

NL

| OF |
AD
A040 013



END
DATE
FILMED
6-77



REPORT DOCUMENTATION PAGE

READ INSTRUCTIONS BEFORE COMPLETING FORM

ADA 040013

1. REPORT NUMBER	2. GOVT ACCESSION NO.	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) Sealing Quality of a Temporary Filling Material,		5. TYPE OF REPORT & PERIOD COVERED 9 Repts. for Sep 75 - May 77
7. AUTHOR(s) Raymond T. Webber, Carlos E. del RIO, John M. Brady and Ronald O. Segall		6. PERFORMING ORG. REPORT NUMBER
9. PERFORMING ORGANIZATION NAME AND ADDRESS US Army Institute of Dental Research Walter Reed Army Medical Center Washington, DC 20012		8. CONTRACT OR GRANT NUMBER(s)
11. CONTROLLING OFFICE NAME AND ADDRESS US Army Medical Research and Development Command ATTN: (SGRD-RP) Washington, DC 20012		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS Program Element 62110A Project No. 3A162110A825 Task Area No. 90 Work Unit No. 117
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)		12. REPORT DATE 10 May 1977
		13. NUMBER OF PAGES 15
		15. SECURITY CLASS. (of this report) UNCLASSIFIED
		15a. DECLASSIFICATION/DOWNGRADING SCHEDULE
16. DISTRIBUTION STATEMENT (of this Report) This document has been approved for public release and sale; its distribution is unlimited.		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		
18. SUPPLEMENTARY NOTES		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) Endodontic access cavities, obturated, Cavit, leakage, methylene blue, sealing, temporary, filling, material		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) Access cavities obturated with Cavit were tested for leakage with methylene blue. A thickness of 3.5 mm of Cavit was needed to prevent leakage.		

1316

16

11

12 17 p.

DDC
MAY 31 1977
C

AD NO. BDC FILE COPY

038 670

mt

SEALING QUALITY OF A TEMPORARY
FILLING MATERIAL

*RAYMOND T. WEBBER, DDS, MS
 **CARLOS E. del RIO, DDS, BS
 ***JOHN M. BRADY, DDS, MSPH
 ****RONALD O. SEGALL, DMD, MS

REGISTRATION No.	
NTIS	White Section <input checked="" type="checkbox"/>
ARC	Buff Section <input type="checkbox"/>
UNANNOUNCED	<input type="checkbox"/>
JUSTIFICATION	
BY	
DISTRIBUTION/AVAILABILITY CODES	
Dist.	AVAIL. and/or SPECIAL
A	

- MAJ, DC Endodontic Resident, US Army Institute of Dental Research,
Walter Reed Army Medical Center, Washington, DC 20012
- COL, DC Chief, Division of Clinical Research; Director, Endodontic
Residency, US Army Institute of Dental Research, Walter
Reed Army Medical Center, Washington, DC 20012
- COL, DC Chief, Department of Biophysics, US Army Institute of Dental
Research, Walter Reed Army Medical Center, Washington, DC 20012
- MAJ, DC Endodontic Resident, US Army Institute of Dental Research,
Walter Reed Army Medical Center, Washington, DC 20012

ABSTRACT

Access cavities obturated with Cavit were tested for leakage with methylene blue. A thickness of 3.5 mm of Cavit was needed to prevent leakage.

The function of a temporary filling material in endodontics is twofold: first, to prevent the saliva with its microorganisms from gaining entrance into the root canal, thus preventing infection or re-infection; second, to prevent medicaments placed into the pulp chamber from escaping into the oral cavity, thereby preserving the effectiveness of the intracanal medication and preventing any chemical burn to the oral mucosa. If these criteria are to be met, the sealing qualities of a temporary filling material are of primary importance in endodontic therapy.^{1,2,3 & 4}

Many studies have been made related to the sealing qualities of various temporary filling materials used in restorative dentistry but few studies have dealt specifically with their use in endodontics.⁵⁻¹⁸

Glass capillary tubes were used by Grossman to study zinc oxide-eugenol, zinc oxyphosphate, and gutta percha. In this study zinc oxide-eugenol showed no leakage. This quality was attributed to its property of expansion on contact with moisture.

Zinc oxyphosphate cement was the least effective with gutta percha having an intermediate position.¹⁹ Massler confirmed the previous findings and added that zinc oxide-eugenol and amalgam fillings presented the most effective marginal sealing qualities.²⁰

Neither zinc oxide-eugenol nor Cavit*, a zinc oxide and polyvinyl preparation, permitted bacterial penetration in the studies of Parris

*Premier, Philadelphia, Pa.

and Kapsimalis. Zinc oxide-eugenol did not show leakage at room temperature but leaked in five out of ten access cavities subjected to temperature changes. Cavit maintained a leak-proof seal both at room and at thermal temperatures ranging from 60°C to 4°C.^{21,22}

The coefficient of linear expansion for Cavit was almost double that of zinc oxide-eugenol which explains its effectiveness as a temporary sealing material.²³ The compressive strength of Cavit has been estimated to be approximately half that of zinc oxide-eugenol, thus showing a lack of marginal strength.²³ For this reason, and to prevent absorption of saliva from the oral cavity and medicaments from the access cavity, the bulk of the restoration is an important factor if Cavit is going to be used as a temporary filling material.

There are other variables besides the temporary sealing material that can cause leakage. Improper access cavity preparation can leave fractured enamel walls to produce a marginal gap up to ten microns.^{24,26} Poor adaptation to cavity walls, debris between cavity wall and temporary restorations, and deterioration of the temporary filling material may lead to marginal seal failure.^{24,25}

The use of a double seal has been advocated to improve the sealing quality of the temporary restorations. This second seal of gutta percha aids only in the support of the outer seal, Cavit or zinc oxide-eugenol, against occlusal stresses. It does not improve the sealing quality of the temporary filling.^{3,27}

Patients undergoing endodontic treatment at our clinic occasionally complained of a foul taste or a burning sensation. This is evidence

of an inadequate seal even though leakage is not apparent on visual examination.²⁸ For the above reason this study was designed to evaluate the thickness of Cavit necessary to achieve an appropriate seal.

Methods and Materials Part I

Forty extracted human molar teeth were selected for their occlusal integrity and stored until their use in water. Endodontic access cavity preparations were performed. The pulp chamber content was removed but no attempt was made to remove material from the root canal.

The teeth were immersed six times in melted wax up to the cemento-enamel junction to produce an impermeable coating on the roots. A dry cotton pellet was placed in half of the specimens and, in the other half, a cotton pellet was moistened in camphorated parachlorophenol, compressed to dryness and placed in the chamber. Care was exercised so that no cotton fibers were left attached to the cavity wall to serve as a wick and that at least 5 mm. of space was left to allow adequate space for the temporary restoration of Cavit.

After the insertion, the Cavit temporary filling was blotted with a wet cotton ball and the teeth were immersed in a solution of 10 cc of 10% methylene blue* in water filtered through a 50 millimicron filter. The teeth remained in the solution at 37°C for forty-eight hours. No effort was made in this experiment to simulate the viscosity of saliva which Grossman determined would help prevent leakage.¹⁹

The teeth were removed from the dye solution, washed with water and examined for integrity of the wax protective coating. When any dye was

*Stock methylene blue is 1.4 gm of methylene blue to 95% alcohol per 100 cc.

detected on the root surface of the tooth, that tooth was discarded and another test-specimen used.

Each specimen was fractured mesio-distally and the cotton pellet examined for dye discoloration, the temporary filling material for dye penetration and the filling-tooth interface for dye penetration (Figure 1). The penetration of the dye was measured with a vernier calpier and recorded.

PART II

Five maxillary central incisors were selected with complete occlusal integrity and stored in water until their use. Standard endodontic access cavity preparations were performed. A dry cotton pellet was placed in the chamber and Cavit was condensed into the access cavity. Care was exercised so that no cotton fibers were left attached to the cavity wall to serve as a wick and that at least 5 mm. of space was left to allow adequate space for the temporary restorative material. After the insertion, the Cavit temporary filling was blotted with a wet cotton ball to accelerate the setting.

The roots were cut at the cervical line and the crowns were fixed to aluminum stubs, coated with carbon and examined in a scanning electron microscope*.

Results Part I

The results of the dye penetration measurements are presented in the table. The penetration of the dye into the mass of Cavit was the same as the penetration of the Cavit-tooth interphase. There was an apparent

*Model AMR 1000, Advanced Metal Research Corporation, Bedford, MA

difference in penetration depending upon the presence or absence of medication beneath the Cavit. This mean penetration of the dye was 2.65 mm. in the medicated cavity and 2.51 mm. in the non-medicated cavity. The results were statistically analysed using the student "t" test and the results were not statistically significant (Table I). The range of penetration varied from 2.5 to 3.2 mm. when both medicated and non-medicated cavities were combined.

Part II

Examination under the scanning electron microscope revealed good adaptation of the Cavit to the access cavity wall (Figure 3) in most of the peripheral area but there were crevices ranging from 37 μ m to 63 μ m (Figure 4) in some regions.

The surface of the Cavit appears particulate except for one crystallin-like area containing a powdery material high in calcium content and rod-like structures with a high content of zinc (Figures 2 & 5).

Discussion

There are two areas of interest in the study of temporary sealers; the integrity of the tooth-filling interphase and the permeability of the material itself. The penetration of the dye in the tooth-filling interphase was the same as the permeability into the material, strongly suggesting that the leakage potential of Cavit is due to its hydroscopic properties. Our conclusions point out that in order to improve the inter-visit seal, a filling thickness of at least 3.5 mm. of Cavit should be used. This tends to parallel Fogel's study.²⁹

Examination with the SEM showed that the constituent materials of Cavit had not been thoroughly mixed probably adding to the permeability.

The crevices found between the access cavity wall and the Cavit could be dehydration artifacts in preparation of the specimen.

During the pilot phase of this investigation, intermediate restorative material (IRM)* was used according to the manufacturer's direction. It was observed that setting was prevented within the one millimeter of material adjacent to the cotton containing camphorated parachlorophenol and the authors do not recommend its use with this medicament. The pilot study showed no difference in penetration of dye between teeth that were doubly or singly scaled. Penetration appears to be solely dependent on the thickness of the Cavit.³⁰

Summary

Endodontic access cavities were prepared in forty extracted human teeth. The access cavities were obturated with Cavit and tested for leakage with methylene blue. The data suggested that at least a 3.5 mm. thickness of Cavit should be used in order to prevent leakage. Examination under the scanning electron microscope showed areas in which the constituents of Cavit were improperly mixed which may lead to increase penetration.

REQUESTS FOR REPRINTS TO:

COL Carlos E. del RIO
Director, Endodontic Residency
Chief, Division of Clinical Research
US Army Institute of Dental Research
Walter Reed Army Medical Center
Washington, DC 20012

*Caulk, Division of Dentsply International, Milford, Delaware

- Figure 1. Mesio-distal section of specimen with Cavit (1), cotton (2) and apical margin of dye penetration (*).
- Figure 2. Electron micrograph of Cavit temporary filling. Note areas of good marginal adaptation (a), crevices (b) to access cavity wall and area of defective mix (c). (20X)
- Figure 3. Higher magnification of area "a" showing good marginal adaptation. (200X)
- Figure 4. Higher magnification of area "b" showing marginal crevis. (200X)
- Figure 5. Higher magnification of area "c" showing powdery material (Ca) and rod-like structures (Zn). (950X)

TABLE I

Millimeters of Dye Penetration

	Medicated	Non-medicated
	2.4	2.2
	2.4	2.5
	2.9	2.7
	3.0	2.7
	3.1	2.6
	3.1	2.6
	2.6	2.5
	3.2	3.0
	2.6	2.2
	2.6	2.8
	2.3	2.5
	2.6	2.5
	2.1	2.5
	2.2	2.7
	3.0	2.3
	2.5	2.4
	2.9	2.5
	2.5	2.4
	2.5	2.4
	2.5	2.2
	<hr/>	<hr/>
MEANS	2.65	2.51

df = 38
 p < .20
 t = 1.64

Bibliography

1. Weine, F. S.: Endodontic Therapy, ed.2, St. Louis, 1976, The C. V. Mosby Company, pp. 234-236.
2. Stewart, G. G.: Rationale Root Canal Medication, Dent. Clin. North Am., pp. 823-834, November, 1957.
3. Bucher, J. F.: Endodontics, ed. 4, Bethesda, 1969, Naval Dental School, p. 59.
4. Tagger, M. and Tagger, E.: Marginal Leakage of Dyes of "Cavident," a Temporary Filling Material Used in Endodontics, Israel J. D. Medicine, 18:14-22, 1969
5. Armstrong, W. D. and Simon, W. J.: Penetration of Radiocalcium at the Margins of Filling Materials: A Preliminary Report, J.A.D.A., 43:684-686, 1951.
6. Kapsimalis, P.: Sealing Properties of Endodontic Filling Materials Using Radioactive Polar and Nonpolar Isotopes, Oral Surg., 22:386-393, 1966.
7. Phillips, R.: Recent Improvements in Dental Materials That the Operative Dentist Should Know, J.A.D.A., 73:84-90, 1966.
8. Nelson, R. J., Wolcott, R. and Paffenburger, G. G.: Fluid Exchange at the Margins of Dental Restorations, J.A.D.A., 44:238-295, 1952.
9. Braver, G. M.: Cements Containing O-ethoxybenzoic Acid (EBA), Dental Material Research, U. S. Dept. of Commerce, pp. 101-111, July, 1972.
10. Christen, A. G. and Mitchell, D. F.: A Fluorescent Dye Method For Demonstrating Leakage Around Dental Restorations, J. Dent. Res., 45:1485-1492, 1966.

11. Hirsch, L. and Weineb, M. M.: Marginal Fit of Direct Acrylic Restorations, J.A.D.A., 56:12-13, 1958.
12. Granath, L. E. and Svensson, A.: Studies of Microleakage With Restorative Materials: A New Air Pressure Method, Scand. J. Dent. Res. 78:353-366, 1970.
13. Fisher, D. W., Shillinburg, H. T., Jr. and Dewhirst, R. B.: Indirect Temporary Restorations, J.A.D.A. 82:160-163, 1971.
14. Abadic, F. R.: Plastic Stopping - Its Multiple Uses, J. Prosth. Dent., 24:103-107, 1970.
15. Gilson, T. D. and Myer, G. D.: Clinical Studies of Dental Cements, II Further Investigation of Two Zinc Oxide-Eugenol Cements for Temporary Restorations, J. Dent. Res., 48:366-367, 1969.
16. Crusten, S. and Mitchell, D.: Fluorescent Dye Method For Demonstrating Leakage Around Dental Restorations, J. Dent. Res., 45:1485-1492, 1966.
17. Swartz, M. L. and Phillips, R. V.: In Vitro Studies of Marginal Leakage of Restorative Materials, J.A.D.A., 62:141-151, 1961.
18. Anderson, J. and Myers, G.: Physical Properties of Some Zinc Oxide-Eugenol Cements, J. Dent. Res., 45:379-387, 1966.
19. Grossman, L. I.: Study of Temporary Fillings As Hermetic Sealing Agents, J. Dent. Res. 18:67-71, 1939.
20. Massler, M. and Ostrovsky, A.: Sealing Qualities of Various Filling Materials, J. Dent. Child., 21:223-224, 1954.

21. Parris, L. and Kapsimalis, P.: The Effect of Temperature Change on the Sealing Properties of Temporary Filling Materials, Part I, Oral Surg., 13:982-989, 1960.
22. Parris, L., Kapsimalis, P., Cobe, H., and Evans, R.: The Effect of Temperature Change on the Sealing Properties of Temporary Filling Materials, Part II, Oral Surg., 17:771-778, 1964.
23. Wilderman, F. H., Eames, W. B., Serene, T. P.: The Physical and Biologic Properties of Cavit, J.A.D.A., 82:378-382, 1971.
24. Going, R. D.: Microleakage Around Dental Restorations: A Summary and Review, J.A.D.A. 84:1349-1357, 1972.
25. Seltzer, S.: The Penetration of Microorganisms Between the Tooth and Direct Resin Fillings, J.A.D.A. 51:560-566, 1955.
26. Roydhouse, R. H. and Weiss, M.E.: Penetration Around the Margin of Restorations: Review and Experiment, J. Canadian Den. Ass. 33: 680-689, 1967.
27. Grossman, L. I.: Endodontic Practice, ed. 8, Philadelphia, 1974, Lea and Febiger, pp. 260-262.
28. DeWald, E. J.: Evaluation of Material and Techniques Used for Sealing Endodontic Preparations, Thesis, Kimbrough Army Hospital, Fort Meade, 1973.
29. Fogel, B.B.: A Comparative Study of Five Materials for Use in Filling Root Canal Spaces, Oral Surg., 43:284-299, 1977.
30. Weber R.: The Sealing Qualities of Temporary Filling Materials Used in Endodontic Procedures, Thesis, U. S. Army Institute of Dental Research, Washington, 1974.



FIGURE 1



FIGURE 2






FIGURE 5