

ADA 043970

13


AD

TECHNICAL REPORT ARLCB-TR-77035

EVALUATION OF 155MM M199 TUBE FORGING PRODUCERS

J. Passmore

July 1977



AMCMS No. 3210.16.0015

Pron No. M7-5-P4850-01-M7-M7

DDC
RECEIVED
SEP 12 1977
B

APPROVED FOR PUBLIC RELEASE; DISTRIBUTION UNLIMITED

AD No. _____
DDC FILE COPY

DISCLAIMER

The findings in this report are not to be construed as an official Department of the Army position unless so designated by other authorized documents.

The use of trade name(s) and/or manufacturer(s) in this report does not constitute an official indorsement or approval.

DISPOSITION

Destroy this report when it is no longer needed. Do not return it to the originator.

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER ARLCB-TR-77035	2. GOVT ACCESSION NO.	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) EVALUATION OF 155MM M199 TUBE FORGING PRODUCERS	5. TYPE OF REPORT & PERIOD COVERED	
7. AUTHOR(s) J. Passmore	6. PERFORMING ORG. REPORT NUMBER	
9. PERFORMING ORGANIZATION NAME AND ADDRESS Benet Weapons Laboratory Watervliet Arsenal, Watervliet, N.Y. 12189 DRDAR-LCB-TL	8. CONTRACT OR GRANT NUMBER(s)	
11. CONTROLLING OFFICE NAME AND ADDRESS US Army Armament Research and Development Command Large Caliber Weapon System Laboratory Dover, New Jersey 07801	10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS AMCMS No. 3210.16.0015 PRON No. M7-5-P4850-01-M7-M7	
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office) <i>12 21p.</i>	12. REPORT DATE <i>11 July 1977</i>	
	13. NUMBER OF PAGES 21	
	15. SECURITY CLASS. (of this report) UNCLASSIFIED	
16. DISTRIBUTION STATEMENT (of this Report) Approved for public release; distribution unlimited.		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report) DDC RECEIVED SEP 12 1977 RECEIVED B		
18. SUPPLEMENTARY NOTES		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) Cannon Tubes Forging Steel		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) Two 155mm M199 howitzer tube forgings, produced by different vendors, were destructively tested to determine the quality of each vendor's forgings. Vendor A's forging did not meet military specifications in all cases; several RA values were below specification. Vendor B's forging was found to be acceptable, exceeding the requirements of the specifications in all cases.		

TABLE OF CONTENTS

	<u>Page</u>
Introduction	1
Procedure	1
Results and Discussion	2
Conclusions	4

LIST OF TABLES

1. Mechanical Properties - Vendor A	6
2. Mechanical Properties - Vendor B	8
3. Chemical Analyses	10

LIST OF ILLUSTRATIONS

1. Location of Test Discs	11
2. Location of Transverse Specimens	12
3. Mechanical Properties - Vendor A (YS and %RA)	13
4. Mechanical Properties - Vendor A (C_V)	14
5. Mechanical Properties - Vendor B (YS and %RA)	15
6. Mechanical Properties - Vendor B (C_V)	16
7. Typical Microstructure - Tempered Martensite (Magnification - 1000X)	17

ACCESSION for	
NTIS	White Section <input checked="" type="checkbox"/>
DDC	Buff Section <input type="checkbox"/>
UNANNOUNCED	<input type="checkbox"/>
JUSTIFICATION	
BY	
DISTRIBUTION AVAILABILITY CODES	
DI	SPECIAL
A	

INTRODUCTION

The 155mm howitzer, M199, is one of the newest weapons to be manufactured at the Watervliet Arsenal. Full production of this tube will be starting shortly, and as a result of this planned production, vendors will be asked to submit bids for the furnishing of XM199 gun tube forgings.

An investigation to determine a vendor's ability to produce an acceptable tube forging was undertaken. To determine each vendor's ability to produce an acceptable tube forging, each prospective vendor was asked to supply one XM199 gun tube forging for qualification tests. These tests would determine if the vendor could meet the material requirements required by the specification and, also, would determine the uniformity of the material's properties.

Bids were requested from prospective vendors of gun tube forgings for the production of a single gun tube forging. Two vendors responded and each provided one tube forging for test purposes.

PROCEDURE

Each forging was sectioned along its length by taking test discs located perpendicular to the tube's axis. From each test disc, four (4) tensile and four (4) Charpy specimens were taken to determine the mechanical properties at that point in the tube. Two different specimen orientations

were tested, transverse and longitudinal, the longitudinal specimens being parallel to the axis or bore of the tube. Locations of the test discs and transverse specimens in each disc are shown in Figures 1 and 2.

Chemical analyses were performed upon the Charpy specimens exhibiting the lowest impact strength for each transverse disc to determine if there were any significant segregation. Metallography was also performed on random pieces of material obtained from each forging to determine the microstructure of that forging.

RESULTS AND DISCUSSION

The results of the mechanical tests, the vendors' test data, and the chemical analyses are tabulated in Tables 1 - 3. A graphical presentation of the results for the mechanical tests are given in Figures 3-6. Each graph presents the minimum and/or maximum values as determined by the appropriate specification¹, the mechanical properties found as a result of testing each vendor's forging, and the physical location of the disc in the tube. Mechanical properties are graphically presented for three (3) values only, the highest value, the average value, and the lowest value from each disc.

1. MIL-S-46119A(MR) dated 7 March 1973.

For Vendor A, the average transverse yield strength at the breech end of the tube was 172.6 ksi and progressively decreased to an average yield strength of 169.3 ksi at the muzzle end. The largest variance within a specific disc was 6 ksi for Disc H. The transverse reduction in area (%RA) varied from a disc averaging 42.8% to a disc averaging only 27.0% for a variance of 15.8% along the length of the tube with no pattern attributed to the position in the tube forging. Even within one disc, Disc C, %RA varied 22.6% between specimens. Three (3) of the twenty-four (24) transverse specimens did not meet the military requirement of 25% RA minimum. The minimum value was 23.2%. Impact properties of the tube were fairly uniform along the length of the tube with the lowest value being a marginal 16.8 ft-lb and the highest value being 23.4 ft-lb. Based upon a sample of this vendor's records of current M185 gun tube forging production, the marginal impact strengths and low RA's were found to be not unusual occurrences.

For Vendor B, the average transverse yield strength varied from a low of 171.4 ksi to a high of 176.9 ksi with the largest variance within a single disc being 6 ksi for Disc F. The average %RA of the gun tube showed excellent uniformity along the tube's length, with a spread

of only 4.2% in average RA. The largest variation within a single disc was 7.5% for Disc J. Average transverse impact properties were consistently above 26 ft-lb with a high average of 33.9 ft-lb for Disc D.

Vendor A's data showed good agreement with the test results except for the impact properties, where 50% of the test results were lower than the lowest impact strength reported by this vendor. Vendor B's data showed excellent agreement with the test data for all properties.

The chemical analyses taken from each tube were uniform along the length of both forgings. Both vendors' forgings showed a microstructure consisting of tempered martensite, Figures 7 and 8.

CONCLUSIONS

Vendor A's forging had good yield strengths, marginal impact strengths, and %RA's which varied widely with location in the forging. Three (3) of the twenty-four (24) %RA's did not meet the minimum requirements set by military specifications. The marginal impact strengths and low %RA's were found to be not unusual occurrences for this vendor.

Vendor B's forgings had, on an average, higher yield strengths, impact strengths, and %RA's than Vendor A's forging. Not only were Vendor B's RA's higher than Vendor A's RA's, but they were more uniform. As a result of tests,

Vendor B's M199 forging met the appropriate military specifications in all cases.

While these tests were not meant to approve or disapprove a vendor, they do indicate that Vendor B is capable of producing a high quality tube, while Vendor A shows a potential for supplying tubes with lower ductility than required.

TABLE 1. MECHANICAL PROPERTIES - VENDOR A

DISC LOCATION	0.1% YS (KSI)	RA (%)	CVN (FT-LB)
Requirement	160/180	25	15
A	169.6 169.3 168.7	35.4 33.6 31.4	21.2 19.3 17.0
B*	169.3 168.3 167.8	63.2 61.5 60.4	37.8 36.7 34.8
C	170.2 169.0 167.8	40.3 30.6 23.7	21.3 19.0 17.6
D	171.7 170.3 168.4	46.2 42.8 37.7	23.4 22.3 21.3
E*	170.8 169.4 167.8	61.6 60.3 58.3	38.0 37.7 37.3
F	172.9 171.3 170.8	38.5 33.4 26.6	19.5 18.9 17.7
G	173.8 173.0 171.7	31.8 27.0 23.2	21.0 19.9 18.7
H*	172.0 169.7 166.0	63.2 61.3 58.7	37.0 35.6 33.7
J	173.8 172.6 170.8	35.8 30.6 23.7	19.0 17.8 16.8

TABLE 1. MECHANICAL PROPERTIES - VENDOR A (cont)

DISC LOCATION	0.1% YS (KSI)	RA (%)	CVN (FT-LB)
Requirement	160/180	25	15
Vendor (Breech)	170.5 168.9 168.1	35.0 32.5 27.5	33.0 25.4 22.0
Vendor (Muzzle)	172.1 170.1 168.5	32.8 28.6 25.4	21.0 20.2 19.5

*Denotes longitudinal specimens

NOTE: Values given represent high, average, and low values for each disc.

TABLE 2. MECHANICAL PROPERTIES - VENDOR B

DISC LOCATION	0.1% YS (KSI)	RA (%)	CVN (FT-LB)
Requirement	160/180	25	15
A	176.5 175.6 174.8	45.4 42.1 39.8	28.0 26.2 24.8
B*	176.5 175.5 174.1	60.0 58.0 57.2	42.3 39.7 33.6
C	172.0 171.4 170.8	47.8 43.7 41.2	31.6 31.0 30.0
D	174.7 174.3 173.2	47.0 44.4 41.6	36.0 33.9 32.7
E*	176.2 174.5 171.7	59.2 58.3 57.5	43.5 42.3 41.8
F	178.0 175.9 172.0	43.6 41.9 40.3	32.0 29.6 28.0
G	177.1 176.9 176.8	48.3 46.1 43.6	31.2 30.5 30.0
H*	174.7 174.0 173.2	61.6 60.4 58.3	45.0 43.4 42.0
J	176.8 175.0 173.2	47.8 43.2 40.3	27.5 27.0 26.3

TABLE 2. MECHANICAL PROPERTIES - VENDOR B (cont)

DISC LOCATION	0.1% YS (KSI)	RA (%)	CVN (FT-LB)
Requirement	160/180	25	15
Vendor	173.0	46.5	29.5
(Breech)	171.9	44.2	28.7
	170.5	40.7	28.0
Vendor	172.2	45.7	29.5
(Muzzle)	171.7	45.5	28.6
	170.5	45.3	27.0

*Denotes longitudinal specimens

NOTE: Values given represent high, average,
and low values for each disc.

TABLE 3. CHEMICAL ANALYSES*

	<u>C</u>	<u>Mn</u>	<u>P</u>	<u>S</u>	<u>Si</u>	<u>Ni</u>	<u>Cr</u>	<u>Mo</u>	<u>V</u>
Vendor A	.34	.47	.013	.004	.11	2.94	1.01	.44	.09
Disc A	.34	.51	.006	.008	.12	2.96	1.01	.46	.09
C	.33	.55	.005	.005	.13	2.72	1.01	.46	.09
D	.33	.51	.006	.006	.12	2.82	1.01	.46	.09
F	.34	.50	.006	.012	.12	2.85	1.01	.46	.09
G	.34	.52	.010	.014	.12	2.85	1.01	.46	.09
J	.33	.51	.007	.008	.12	2.87	1.01	.46	.09
Vendor B	.32	.59	.008	.007	.19	2.43	.97	.54	.13
Disc A	.34	.67	.007	.008	.25	2.43	.99	.60	.13
C	.31	.67	.008	.007	.25	2.48	1.00	.60	.13
D	.31	.67	.007	.004	.25	2.51	1.00	.60	.13
F	.32	.63	.007	.007	.24	2.50	1.00	.59	.13
G	.32	.65	.007	.004	.24	2.47	.99	.58	.13
J	.34	.65	.007	.006	.25	2.53	1.00	.60	.13

*NOTE: All values are expressed in weight percent.




Figure 1. Location of test discs.





Figure 2. Location of transverse specimens.



DISTANCE FROM BREECH END

Figure 3. Mechanical properties - Vendor A




Figure 4. Mechanical properties - Vendor A




Figure 5. Mechanical properties - Vendor B






Figure 6. Mechanical properties - Vendor B



Vendor A



Vendor B

Figure 7. Typical microstructure - tempered martensite (magnification = 1000X).

WATERVLIET ARSENAL INTERNAL DISTRIBUTION LIST

May 1976

	<u>No. of Copies</u>
COMMANDER	1
DIRECTOR, BENET WEAPONS LABORATORY	1
DIRECTOR, DEVELOPMENT ENGINEERING DIRECTORATE	1
ATTN: RD-AT	1
RD-MR	1
RD-PE	1
RD-RM	1
RD-SE	1
RD-SP	1
DIRECTOR, ENGINEERING SUPPORT DIRECTORATE	1
DIRECTOR, RESEARCH DIRECTORATE	2
ATTN: RR-AM	1
RR-C	1
RR-ME	1
RR-PS	1
TECHNICAL LIBRARY	5
TECHNICAL PUBLICATIONS & EDITING BRANCH	2
DIRECTOR, OPERATIONS DIRECTORATE	1
DIRECTOR, PROCUREMENT DIRECTORATE	1
DIRECTOR, PRODUCT ASSURANCE DIRECTORATE	1
PATENT ADVISORS	1

EXTERNAL DISTRIBUTION LIST

December 1976

1 copy to each

OFC OF THE DIR. OF DEFENSE R&E
ATTN: ASST DIRECTOR MATERIALS
THE PENTAGON
WASHINGTON, D.C. 20315

CDR
US ARMY TANK-AUTMV COMD
ATTN: AMDTA-UL
AMSTA-RKM MAT LAB
WARREN, MICHIGAN 48090

CDR
PICATINNY ARSENAL
ATTN: SARPA-TS-S
SARPA-VP3 (PLASTICS
TECH EVAL CEN)
DOVER, NJ 07801

CDR
FRANKFORD ARSENAL
ATTN: SARFA
PHILADELPHIA, PA 19137

DIRECTOR
US ARMY BALLISTIC RSCH LABS
ATTN: AMXBR-LB
ABERDEEN PROVING GROUND
MARYLAND 21005

CDR
US ARMY RSCH OFC (DURHAM)
BOX CM, DUKE STATION
ATTN: RDRD-IPL
DURHAM, NC 27706

CDR
WEST POINT MIL ACADEMY
ATTN: CHMN, MECH ENGR DEPT
WEST POINT, NY 10996

CDR
HQ, US ARMY AVN SCH
ATTN: OFC OF THE LIBRARIAN
FT RUCKER, ALABAMA 36362

CDR
US ARMY ARMT COMD
ATTN: AMSAR-PPW-IR
AMSAR-RD
AMSAR-RDG
ROCK ISLAND, IL 61201

CDR
US ARMY ARMT COMD
FLD SVC DIV
ARMCOM ARMT SYS OFC
ATTN: AMSAR-ASF
ROCK ISLAND, IL 61201

CDR
US ARMY ELCT COMD
FT MONMOUTH, NJ 07703

CDR
REDSTONE ARSENAL
ATTN: AMSMI-RRS
AMSMI-RSM
ALABAMA 35809

CDR
ROCK ISLAND ARSENAL
ATTN: SARRI-RDD
ROCK ISLAND, IL 61202

CDR
US ARMY FGN SCIENCE & TECH CEN
ATTN: AMXST-SD
220 7TH STREET N.E.
CHARLOTTESVILLE, VA 22901

DIRECTOR
US ARMY PDN EQ. AGENCY
ATTN: AMXPE-MT
ROCK ISLAND, IL 61201

EXTERNAL DISTRIBUTION LIST (Cont)

1 copy to each

CDR
US NAVAL WPNS LAB
CHIEF, MAT SCIENCE DIV
ATTN: MR. D. MALYEVAC
DAHLGREN, VA 22448

DIRECTOR
NAVAL RSCH LAB
ATTN: DIR. MECH DIV
WASHINGTON, D.C. 20375

DIRECTOR
NAVAL RSCH LAB
CODE 26-27 (DOCU LIB.)
WASHINGTON, D.C. 20375

NASA SCIENTIFIC & TECH INFO FAC
PO BOX 8757, ATTN: ACQ BR
BALTIMORE/WASHINGTON INTL AIRPORT
MARYLAND 21240

DEFENSE METALS INFO CEN
BATTELLE INSTITUTE
505 KING AVE
COLUMBUS, OHIO 43201

MANUEL E. PRADO / G. STISSER
LAWRENCE LIVERMORE LAB
PO BOX 808
LIVERMORE, CA 94550

DR. ROBERT QUATTRONE
CHIEF, MAT BR
US ARMY R&S GROUP, EUR
BOX 65, FPO N.Y. 09510

2 copies to each

CDR
US ARMY MOB EQUIP RSCH & DEV COMD
ATTN: TECH DOCU CEN
FT BELVOIR, VA 22060

CDR
US ARMY MAT RSCH AGCY
ATTN: AMXMR - TECH INFO CEN
WATERTOWN, MASS 02172

CDR
WRIGHT-PATTERSON AFB
ATTN: AFML/MXA
OHIO 45433

CDR
REDSTONE ARSENAL
ATTN: DOCU & TECH INFO BR
ALABAMA 35809

12 copies

CDR
DEFENSE DOCU CEN
ATTN: DDC-TCA
CAMERON STATION
ALEXANDRIA, VA 22314

NOTE: PLEASE NOTIFY CDR, WATERVLIET ARSENAL, ATTN: SARWV-RT-TP,
WATERVLIET, N.Y. 12189, IF ANY CHANGE IS REQUIRED TO THE ABOVE.