





NRL Memorandum Report 4026

# Testing and Evaluation of Potential Hazards from a Teflon Impregnated Packing

J. J. DECORPO AND J. R. HOLTZCLAW

Chemical Diagnostics Branch Chemistry Division

AND

R. C. CLARK

Fuels and Combustion Branch Chemistry Division

July 2, 1979

DDC FILE COPY

~

**DA07142** 



DDC JUL 20 1979 TL SILV A

19 024

NAVAL RESEARCH LABORATORY Washington, D.C.

Approved for public release; distribution unlimited.

79

REPORT DOCUMENTATION PAGE	READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER 2. GOVT ACCESSION NO	0. 3. RECIPIENT'S CATALOG NUMBER
NRL Memorandum Report 4026	1
A. TITLE (and Subjille)	STAR OF ASPARE PERIOD COVERED
TEOTING AND EVALUATION OF POTENTIAL HAZARDS	Interim report one continuing
FROM A TEEL ON IMPRECIATED PACKING	LNRL problem Y
FROM A TEFLON IMPREGNATED FACKING	6. PERFORMING ORG. REPORT NUMBER
and the second	
7. AUTHORCO	S. CONTRACT OR GRANT NUMBER(.)
J. J. DeCorpo, J. R. Holtzclaw and R. C. Clark	
A REPEARING ORGANIZATION NAME AND ADDRESS	10. PROGRAM ELEMENT PROJECT TASK
Naval December I shoretony	AREA & WORK UNIT NUMBERS
Washington DC 20375	65197A - 065872
Washington, DC 20070	NRL Problem C07-02D, 2A
11. CONTROLLING OFFICE NAME AND ADDRESS	12. REPORT DATE
Naval Ship Engineering Center	July 2, 1979
Washington, DC 20362 (Code 6153)	13. NUMPER OF PAGES
	30
14. MONITORING AGENCY NAME & ADDRESS(II different from Controlling Office)	15. SECURITY CLASS. (of this report)
all = 1 HA MALAN	UNCLASSIFIED
112, JUL 11/ (12) 31 P'/	SCHEDULE
Made Marin	
Approved for public release; distribution unlimited.	rom Report)
Approved for public release; distribution unlimited.	rom Report)
Approved for public release; distribution unlimited. 17. DISTRIBUTION STATEMENT (of the observed in Block 2D, 11 different to III NRL - MR 4026 19. SUPPLEMENTARY NOTES	rom Report)
Approved for public release; distribution unlimited. 17. DISTRIBUTION STATEMENT (at the observect entered in Block 20, 11 different in WRL - MR 4026 18. SUPPLEMENTARY NOTES 19. KEY WORDS (Continue on reverse elde 11 necessary and identity by block number	rom Report)
Approved for public release; distribution unlimited. 17. DISTRIBUTION STATEMENT (of the observaci entered in Block 20, 11 different in IIIIIIIIIIIIIIIIIIIIIIIIIIIIIIIIIIII	rom Report)
Approved for public release; distribution unlimited. 17. DISTRIBUTION STATEMENT (of the observed in Block 20, 11 different for INRL - MR HB26 18. SUPPLEMENTARY NOTES 19. KEY WORDS (Continue on reverse side if necessary and identify by block number Teflon Submarine Atmosphare	rom Report)
Approved for public release; distribution unlimited. 17. DISTRIBUTION STATEMENT (of the observed in Block 20, 11 different for WRL-MR-4026 19. SUPPLEMENTARY NOTES 19. KEY WORDS (Continue on reverse side if necessary and identify by block number Teflon Submarine Atmosphere Seal	roan Report)
Approved for public release; distribution unlimited. 17. DISTRIBUTION STATEMENT (of the observed in Block 20, 11 different for WRL-MR-4026 19. SUPPLEMENTARY NOTES 19. KEY WORDS (Continue on reverse side if necessary and identify by block number Teflon Submarine Atmosphere Seal	roa Report)
Approved for public release; distribution unlimited. 17. DISTRIBUTION STATEMENT (at the obstract entered in Block 20, it different in WRL - MR 4026 19. KEY WORDS (Continue on reverse side if necessary and identify by block number Teflon Submarine Atmosphere Seal 20. Nest RACT (Continue on reverse side if necessary and identify by block number Seal	rom Report) r)
Approved for public release; distribution unlimited. 17. OISTRIBUTION STATEMENT (at the obstract entered in Block 20, 11 different in WRL - MR 4026 19. KEY WORDS (Continue on reverse side if necessary and identify by block number Tefion Submarine Atmosphere Seal 20. Natract (Continue on reverse side if necessary and identify by block number A Tefion impregnated, asbestos yarn packing material is bu	rom Report)
Approved for public release; distribution unlimited. 17. OISTRIBUTION STATEMENT (at the obstract entered in Block 20, 11 different in WRL - MR 4026 19. KEY WORDS (Continue on reverse side 11 necessary and identify by block number Teflon Submarine Atmosphere Seal 20. Nest RACT (Continue on reverse side 11 necessary and identify by block number A Teflon impregnated, asbestos yarn packing material is be main feed and other water pumps. The Naval Research Labor	rom Report) ") eing considered for use in submarine's ratory was tasked to evaluate the
Approved for public release; distribution unlimited. 17. OISTRIBUTION STATEMENT (at the obstract entered in Block 20, 11 different in WRL-MRHB26 19. KEY WORDS (Continue on reverse elde 11 necessary and identify by block number Teflon Submarine Atmosphere Seal 20. Nest RACT (Continue on reverse elde 11 necessary and identify by block number A Teflon impregnated, asbestos yarn packing material is be main feed and other water pumps. The Naval Research Labor potential hazard under the most severe conditions as well as m	") eing considered for use in submarine's ratory was tasked to evaluate the nore typical operating conditions.
Approved for public release; distribution unlimited. 17. OISTRIBUTION STATEMENT (at the obstract entered in Block 20, 11 different in WRL-MRMR4026 19. KEY WORDS (Continue on reverse elde 11 necessary and identify by block number Teflon Submarine Atmosphere Seal 20. Nest RACT (Continue on reverse elde 11 necessary and identify by block number A Teflon impregnated, asbestos yarn packing material is be main feed and other water pumps. The Naval Research Labor potential hazard under the most severe conditions as well as m Air and lubricating water samples were collected during simula	") eing considered for use in submarine's ratory was tasked to evaluate the nore typical operating conditions.
Approved for public release; distribution unlimited. 17. OISTRIBUTION STATEMENT (at the obstract entered in Block 20, 11 different in WRL-MRMR4026 19. KEY WORDS (Continue on reverse elde 11 necessary and identify by block number Teflon Submarine Atmosphere Seal 20. Nest RACT (Continue on reverse elde 11 necessary and identify by block number A Teflon impregnated, asbestos yarn packing material is be main feed and other water pumps. The Naval Research Labor potential hazard under the most severe conditions as well as m Air and lubricating water samples were collected during simula Brown Inc. and analyzed for Teflon decomposition products a	") eing considered for use in submarine's ratory was tasked to evaluate the nore typical operating conditions. ation runs conducted at Dayton T. and asbestos fiber content. Additiona
Approved for public release; distribution unlimited. 17. OISTRIBUTION STATEMENT (at the obstract entered in Block 20, 11 different in WRL-MRMR4026 19. KEY WORDS (Continue on reverse elde 11 necessary and identify by block number Teflon Submarine Atmosphere Seal 20. Nest RACT (Continue on reverse elde 11 necessary and identify by block number A Teflon impregnated, asbestos yarn packing material is be main feed and other water pumps. The Naval Research Labor potential hazard under the most severe conditions as well as m Air and lubricating water samples were collected during simula Brown Inc. and analyzed for Teflon decomposition products a pyrolysis and g.c. mass spectroscopic tests were conducted at 1	") eing considered for use in submarine's atory was tasked to evaluate the hore typical operating conditions. ation runs conducted at Dayton T. and asbestos fiber content. Additiona NRI. to identify and profile the
Approved for public release; distribution unlimited. 17. OISTRIBUTION STATEMENT (at the obstract entered in Block 20, 11 different in WRL-MRMR4026 19. KEY WORDS (Continue on reverse elde 11 necessary and identify by block number Teflon Submarine Atmosphere Seal 20. Nest RACT (Continue on reverse elde 11 necessary and identify by block number A Teflon impregnated, asbestos yarn packing material is be main feed and other water pumps. The Naval Research Labor potential hazard under the most severe conditions as well as m Air and lubricating water samples were collected during simula Brown Inc. and analyzed for Teflon decomposition products a pyrolysis and g.c. mass spectroscopic tests were conducted at 1	") eing considered for use in submarine's ratory was tasked to evaluate the nore typical operating conditions. ation runs conducted at Dayton T. and asbestos fiber content. Additiona NRL to identify and profile the (Continues)
Approved for public release; distribution unlimited. 17. OISTRIBUTION STATEMENT (of the observed entered in Block 20, 11 different in WRL-MRMRH026 18. SUPPLEMENTARY NOTES 19. KEY WORDS (Continue on reverse side if necessary and identify by block number Teflon Submarine Atmosphere Seal 20. Nest RACT (Continue on reverse side if necessary and identify by block number Main feed and other water pumps. The Naval Research Labor potential hazard under the most severe conditions as well as m Air and lubricating water samples were collected during simula Brown Inc. and analyzed for Teflon decomposition products a pyrolysis and g.c. mass spectroscopic tests were conducted at 1	rom Report)
Approved for public release; distribution unlimited. 17. DISTRIBUTION STATEMENT (at the observact entered in Block 20, if different in IMARE ARE ARE ARE ARE ARE ARE ARE ARE ARE	rom Report) rom Report) reing considered for use in submarine's ratory was tasked to evaluate the more typical operating conditions. ation runs conducted at Dayton T. and asbestos fiber content. Additional NRL to identify and profile the (Continues)

#### SECURITY CLASSIFICATION OF THIS PAGE (When Date Entered)

#### 20. Abstract (Continued)

contaminants outgassing from the packing material as a function of temperature.

→ Under normal operating conditions, no significant amounts of hydrocarbons, fluorides, perfluorocarbons, and asbestos were discharged into the atmosphere or the lubricating, water stream. A trace amount of fluoride ion detected in the water samples can be attributed to a polyfluorinated surfactant identified during the g.c. - mass spectroscopic analysis.

Under severe or "dry" operating conditions, some hydrocarbons, HF, fluorocarbons, and asbestos are discharged into the atmosphere. The observed hydrocarbons are easily absorbed by the charcoal filters, readily oxidized to  $CO_2/H_2O$  by the catalytic burners, and should be essentially removed from the machinery space in 30 minutes with normal air exchange. However, the hydrocarbon concentration may reach 400 ppm in the vicinity of the pump, and the hydrocarbons have a characteristic unpleasant odor.

The concentration of asbestos, HF, perfluorocyclopropane, and perfluoroethylene released under the conditions of the test and expanded into the machinery space of SSN 688 are below the currently established NIOSH standards.

The most toxic decomposition product of Teflon, perfluoroisobutylene, can be produced in dangerous quantities only with simultaneous failure of the water lubricating system, the air handling system and with manual tightening of the packing. The likelihood of the triple failure occurring was assessed to be negligible.

SECURITY CLASSIFICATION OF THIS PAGE(When Date Entered)

### TABLE OF CONTENTS

I.	INTRODUCTION	. 1
11.	REACTIVITY OF PACKING MATERIALS	. 1
111.	PACKING TESTS CONDUCTED AT DAYTON T. BROWN, INC.	. 2
IV.	SAMPLING AND ANALYSIS DURING DRY OPERATION	5
v.	SAMPLING AND ANALYSIS DURING WET OPERATION	6
vī.	TEMPERATURE ANALYSIS DURING TEST OPERATIONS	. 7
VII.	IDENTIFICATION OF VAPOR PHASE PRODUCTS	. 7
VIII.	CONCLUSIONS	8
IX.	REFERENCES	11

Access	lon For
NTIS	I IMAGE
DEC TH	B
(In running)	unced
1	tention
4 41 ( M.S.	2 States and a state of the states of the st
1-	a construction of the second se
	hast ton!
	and the second se
I we U	UPITITA CODES
	Limit and/or
	Availa and
Dist	aportan
1	
VI	
n	
11.	and the second

#### TESTING AND EVALUATION OF POTENTIAL HAZARDS FROM A TEFLON IMPREGNATED PACKING

#### I. INTRODUCTION

A Teflon impregnated packing is being considered as a replacement for packings currently used on submarine's main and other water pumps. Produced under Military Specification MIL-P-24377 (Ships), the proposed packing material consists of chrysotile asbestos yarn with reinforcing fibers that are impregnated with virgin PTFE (polytetrafluoroethylene), and surface coated with refined white petrolatum. Under normal operating conditions the packing is lubricated with a small stream of water. However, during pump startup, or either as a result of pump failure or operator error, the possibility exists of operation with a "dry" packing. During "dry" operating conditions, the petrolatum and Teflon may thermally decompose and evolve toxic gases which would enter the enclosed atmosphere of the submarine. In addition, asbestos fibers may be released into the atmosphere and the lubricating water stream at a level which could be hazardous to personnel. The Naval Research Laboratory (reference (1)) was tasked to evaluate the potential environmental hazard under the most severe conditions as well as more typical operating conditions.

### II. REACTIVITY OF PACKING MATERIALS

Petroleum products can be cracked at temperatures exceeding 400°C to produce lighter hydrocarbons (reference (2)). However, at lower temperatures (<200°C), the low boiling petrolatum coating on the packing will begin to vaporize and decomposition of the less stable hydrocarbons may initiate. The specific hydrocarbon gases Note: Manuscript submitted May 2, 1979.

evolved from the packing depend upon the petrolatum chemical composition and the reaction conditions; in general, however, hydrocarbons in the petrolatum are relatively nontoxic.

Teflon (PTFE) will decompose at elevated temperatures (>400°C) by a reverse mechanism of the polymerization to form perfluoroethylene (PFE) (reference (3)). Perfluoroethylene can then react with oxygen and water in the atmosphere to produce carbonyl fluoride and hydrogen fluoride. At temperatures >500°C, PTFE will decompose to perfluorocyclopropane (PFCP) and perfluoroisobutylene (PFIB) in addition to perfluoroethylene. The degree of toxicity (reference (3), (4)) of these decomposition products is given below:

	Approximate lethal concentration (4-hour exposure)
perfluoroethylene	40,000 ppm
perfluorocyclopropane	non-toxic
perfluorisobutylene	0.5 ppm
hydrogen fluoride	200 ppm (Threshold Limit Value

III. PACKING TESTS CONDUCTED AT DAYTON T. BROWN, INC.

A report (reference (5)) outlines the packing tests conducted at Dayton T. Brown, Inc. which simulated both severe and normal shipboard operations. The test stand and packing housing were constructed so that one set of packing would be tested at a time and in a manner to simulate a SSN 688 class ships' main feed pump stuffing box (see figures 1,2).

The shaft sleeve, shaft sleeve nut, packing gland, and packing were actually SSN 688 class ship's main feed pump parts, purchased new for use in these tests. Packing temperature was monitored continually at three locations: the innermost ring, the center, and the outermost packing ring. Air and water leakage rates across the packing were measured with a flowmeter and a graduated cylinder, respectively. Figures 3-6 depict the test stand and detail the interior of the stuffing box with packing and packing gland in place.

For each test, the shaft was brought up to the designated speed and the packing gland tightened until the desired leakage rate was achieved. During the course of each test, the packing gland was readjusted, when necessary, to maintain the desired leakage rate. Each test ran for 2 hours or until the packing failed, whichever occurred first.

Severe operating conditions were simulated by running the packing without a lubricating water stream ("dry") while injecting air at 50 psig and 60°F into the rear of the stuffing box. The tests were carried out at shaft speeds of 3600, 1800, and 600 RPM with zero or 2 liters/minutes of air leakage past the packing. Air leaking past the packing was continually monitored for toxic materials and concentrated for subsequent laboratory trace analysis at NRL.

During zero leakage tests, the packing would occasionally seize the pump shaft, resulting in very high peak packing

temperature. However, this action was immediately followed by high air leakage rates and subsequent cooling of the packing. As a result, the peak temperatures were held for only a few seconds. Elevated packing temperatures could be maintained only by constant manual adjustment of the packing.

The packing shown in Figure 7 is typical of those used in severe operation testing. As can be seen, the interior surface of the packing has been badly burned and all that remains is the asbestos yarn. The petrolatum was vaporized or decomposed, and the bulk of the Teflon probably removed as fine particulates. The accumulation of waxy dust in the stuffing box is shown in Figure 8.

Simulation of more typical conditions consisted of injecting water at 160°F and 100 psig into the rear of the stuffing box. As was the case for the air tests, the shaft was operated at 3600, 1800, and 600 RPM under zero leakage and 8-16 drops/ minute leakage rates. At the completion of each test run, water samples were collected by NRL for subsequent fluoride ion and asbestos content analysis.

Packing used in the "wet" zero leak tests had to be constantly adjusted to maintain zero leakage. In addition, moderate peak packing temperatures were observed. As a result, some scorching of the packing took place. A typical packing is shown in Figure 9. Damage to the packing material was much less severe than that experienced in the air tests.

Tests with water leakage rates of 8-16 drops/minutes gave more favorable results. Leakage rates were relatively easy to maintain and the problems with high packing temperatures and scorching did not occur. The test conditions produced negligible damage to the packing material (Figure 10).

IV. SAMPLING AND ANALYSIS DURING DRY OPERATION

The sampling configuration is shown in Figure (1). Particulates in the gas sample stream were collected on a  $0.8_{\mu}$  polycarbonate filter while gaseous hydrocarbons and Teflon decomposition products were monitored with a Wilks Model 80 Infrared Analyzer. Lithium hydroxide traps were used to collect hydrogen fluoride in the gas stream. The flow rate through the sample system was held at two liters per minute by a critical orifice incorporated in the sampling pump.

During dry test operations, the major portion of the material outgassing from the packing consisted of gaseous hydrocarbons and condensed hydrocarbons in the form of an aerosol cloud. After approximately five-ten minutes of operation, the amount of outgassing hydrocarbons dropped significantly. Unfortunately, the level of hydrocarbons was still high enough to prevent on-site detection of low levels of Teflon decomposition products.

Hydrogen fluoride collected on the lithium hydroxide traps was removed using standard analytical procedures and measured

with a fluoride specific electrode. Blank samples of the distilled water used in this analysis and in the "wet" runs gave a fluoride ion background of 0.64 ppm/gal. The small amount of HF detected in the lithium hydroxide traps (Table 1) can be attributed to hydrolysis of a polyfluorinated surfactant (see Section VII), since Teflon does not decompose until it reaches ~450°C. Under the most severe conditions of prolonged "dry" operation (high shaft RPM's coupled with a lack of compartment air exchange), the highest HF concentration in the machinery space of a 688 class boat should not exceed 1 PPM. The current TLV for HF is 3 PPM (reference (4)).

Particulate samples collected on the polycarbonate filter were analyzed for asbestos content by electron microscopy. The measured atmospheric asbestos levels resulting from the packing material (Table 2) were well below the current accepted NIOSH standards (reference (6)).

#### V. SAMPLING AND ANALYSIS DURING WET OPERATION

The test stand and water circulation system used to simulate normal operating conditions is outlined in Figure 2. Water samples were taken from the circulation system at the conclusion of each test run and analyzed at NRL for asbestos fiber and HF concentration. Particulates were filtered from the water samples and burned in a muffle furnace leaving only the asbestos fibers which were examined under polarized light with an optical microscope. The asbestos content of the water was found to be too low

to be accurately measured (Table 2). Hydrogen fluoride contamination of the water sample was measured with a fluoride specific electrode and found to be insignificant (Table 3). As in the case of the air samples, the detected HF can be attributed to hydrolysis of the fluorocarbon surfactant. No hydrocarbons, asbestos, or perfluorocarbons were observed to be released into the atmosphere.

#### VI. TEMPERATURE ANALYSIS DURING TEST OPERATIONS

Packing temperature near the shaft was continually monitored during the simulation tests. During dry operation, packing temperature averaged 200-315°C (400-600°F) with peak temperatures of  $\sim$ 480°C (900°F). Packing temperatures during wet operation averaged 99-104°C (210-220°F) and never exceeded  $\sim$ 144°C (300°F). Peak temperatures were reached for a period of less than 30 seconds in tests ranging from 10-120 minutes. The observed packing temperatures are summarized in Table (4). VII. IDENTIFICATION OF VAPOR PHASE PRODUCTS

Identification of the packing outgassing products was carried out at NRL. Sections of packing and stainless steel chips were heated in a closed quartz tube to the temperatures observed in test runs conducted at Dayton T. Brown, Inc. Gas samples were taken at the typical packing temperatures and analyzed by g.c.-mass spectroscopic techniques. The composition of the gas sample was found to be dependent upon heating time, temperature, and the presence of catalytic surfaces (stainless steel). In general, heating of the packing at 130°C

(266°F) produced a small amount of a straight chain fluorocarbon (Figure 11), while packing temperatures of ~200-300°C (392-572°F) produced gas mixtures consisting of branched and straight chain paraffins, acetaldehyde, methyl furans, carbon monoxide, and other partially oxidized hydrocarbons (Figure 12). The straight chain fluorocarbon is thought to serve as a surfactant in the packing manufacturing process. Teflon decomposition products were observed, via infrared spectroscopy, only when packing temperature reached 450-600°C (842-1112°F). Table 5 summarizes the observed composition of the outgassing products as a function of temperature.

#### VIII. CONCLUSIONS

Tests at Dayton T. Brown, Inc., subsequent laboratory analysis of the air and water samples, and laboratory characterization of the proposed packing allow several conclusions to be made.

Significant amounts of hydrocarbons, fluorides, perfluorocarbons, and asbestos, are not discharged into the atmosphere or bilge when the proposed packing is used under normal, "wet", operating conditions. The slow rate of HF production will result in less than 0.01 gram of HF being added to the bilge in 90 days of continuous operation. In addition, HF production is caused by hydrolysis of the polyfluorinated surfactant, not Teflon decomposition. Furthermore, the trace amount of asbestos discharged into the bilge is coated with petrolatum which will

inhibit release of the fibers into the atmosphere.

Varying amounts of hydrocarbons, HF, fluorocarbons, and asbestos are discharged into the atmosphere when the proposed packing is used under abnormal or "dry" conditions.

The hydrocarbons released into the atmosphere during "dry" operation come from the petrolatum on the packing. After approximately 10 minutes of operation, all the petrolatum at the packing shaft interface is gone, and the atmospheric hydrocarbon concentration in the vincinity of the pump may reach as high as 400 ppm (based on  $C_6$ ). This exceeds the BUMED 90 day exposure limit for total hydrocarbons (reference (7)), although a one hour exposure limit has not been established. The observed hydrocarbons are easily absorbed by the charcoal filters and readily oxidized to CO2/H2O by the catalytic burners. These hydrocarbons have, however, a characteristic, unpleasant ordor. As graphically illustrated in Figure 13, the hydrocarbons should be essentially removed from the machinery space in 30 minutes. The hydrocarbon concentration was estimated by assuming dry operation, normal compartment air exchange, and dispersion of the hydrocarbons throughout the volume of the machinery space.

The concentrations of HF and asbestos released under the conditions of the test and expanded into the machinery space of an SSN 688 class boat are below the currently accepted NIOSH standards (references (4) and (6)). After thirty minutes of continuous "dry" operation and no compartment air exchange, the concentration of

perfluoroethylene and perfluorocyclopropane in the machinery space will be less than 1 ppm. There are no currently accepted exposure levels for perfluoroethylene and perfluorocyclopropane, however, the ALC (approximate lethal concentration, 4 hour exposure) is 40,000 ppm for perfluoroethylene (reference (3)) and perfluoroalkanes such as perfluorocyclopropane exhiit very low toxicity (reference (3)).

The most toxic decomposition product of Teflon, perfluoroisobutylene (PFIB), requires special attention since an exposure to 0.5 ppm for four hours can be fatal (reference (3)). PFIB was observed in the laboratory tests only when the packing temperature exceeded 900°F, and was not observed during on site testing at Dayton T. Brown, Inc. when the packing reached 900°F for approximately 30 seconds in 30 minutes of dry operation. Based on the temperature measurements obtained during tests at Dayton T. Brown, prolonged "dry" operation at high shaft speeds would be needed to produce the temperature required to generate PFIB. Three failures are required to produce the conditions necessary for production of dangerous levels of PFIB. Failure of the water lubricating system and the air handling system would have to occur, and the packing would have to be manually tightened, simultaneously, during "dry" operation. The likelihood of the triple failure occurring was assessed to be negligible (reference (8)). Momentary "dry" operation does not generate the packing temperature necessary to produce dangerous levels of PFIB.

#### REFERENCES

- 1. NAVSEA Ltr PMS 301:BJM 9503, Ser 507, 28 June 78.
- 2. Organic Chemistry, R. T. Morrison and R. N. Boyd (Allyn and Bacon, Inc.) Boston (1973).
- 3. Organic Fluorine Chemistry, W. A. Sheppard and C. M. Sharts (W. A. Benjamin, Inc.) N. Y., N. Y. (1969).
- Registry of Toxic Effects of Chemical Substances, 1976 Edition, H. E. Christensen and T. L. Luginbyhl, eds., HEW, Public Health Services, Rockville, MD.
- 5. Dayton T. Brown, Inc. Test Report, Document No. DTB26R78-2415.
- Dangerous Properties of Industrial Materials, 4th Edition, N. I. Sox (Van Nostrand Reinhold Co.), N. Y., N. Y. (1975)
- Nuclear Powered Submarine Atmosphere Control Manual, NAVSEA 0938-011-9010, Revision B.
- Meeting between NRL (6110), NAVSEA (PMS 301, 393, 396-08) and NAVSEC (6151, 6153), 17 January 1979.

### ACKNOWLEDGMENT

The authors would like to thank Mr. M. L. Hartranft, NAVSEC, Code 6153, and Mr. R. Ufer of Dayton T. Brown, Inc. for their assistance at the Dayton T. Brown test site and for information and photographs included in this report.

# Dry Operation HF Conc - Air Run

Tes	<u>t</u> #	RPM	Estimate of HF Conc in Machinery Air Space (No exchange or Loss) ± 50%	Run	Time
1	(Garlock)	3600	.01 PPM	10	minutes
1A	(John Crane)	3600	.5	40	minutes
2	(Garlock)	1800	1.5	88	minutes
3	(John Crane)	600	.01	25	minutes
7	(Garlock)	3600	1.0	13	minutes
8	(Garlock)	1800	0.5	76	minutes
9	(Garlock)	600	0.5	120	minutes

Measured Asbestos

# Observation

Wet Operation

Trace in Water\*

Dry Operation

Trace\*

\* <1000/M<sup>3</sup>

HF Conc. - Water Run (Normal Conditions)

Tes	t #	RPM	Grams [HF]/Min in Water	Run Time
4	(Garlock)	3600	$5 \times 10^{-7}$	94 minutes
5	(John Crane)	1800	$4 \times 10^{-7}$	120 minutes
10	(Garlock)	3600	$4 \times 10^{-7}$	120 minutes
12	(Garlock)	600	$2 \times 10^{-7}$	120 minutes

Measured Temperatures During Simulation Tests

Dry Operation - Average - 400-600°F (200-315°C) Peak - ~900°F (480°C)

Wet Operation - Average - 210-220°F (99-104°C) Peak - <300°F (149°C)

# Gaseous Products of Packing in Air

### At Various Temperatures

Temperature

1

# Products

>100°C	Water
20°C-130°C	Straight Chain Fluorocarbon (Surfactant)
200°C-350°C	Straight Chain Hydrocarbons, Acetaldehyde, Dimethylbutane, Methylfuran, Dimethylfuran, and Furfural
>450°C	Tetrafluoroethylene, Carbonyl- fluoride, HF (Hydrogen Fluoride) Perfluorocyclopropane
>500°C	Perfluoroisobutylene plus the above fluorinated compounds



Fig. 1 - Dry operation test configuration



Fig. 2 - "Wet" operation test configuration



Fig. 3 - Dayton T. Brown test stand





Fig. 5 – Interior of stuffing box - packing gland



Fig. 6 - Interior of stuffing box - packing installed



Fig. 7 – Dry operation, zero leakage, 3600 RPM



Fig. 8 – Packing residue deposited on interior of stuffing box during dry operation



Fig. 9 – Wet operation, zero leakage, 3600 RPM



Fig. 10 - Wet operation, 8-16 drops per minute leakage, 1800 RPM





