

AD-A096 127

PRINCETON UNIV N J DEPT OF CHEMICAL ENGINEERING

F/G 11/9

THE TIME-TEMPERATURE-TRANSFORMATION (TTT) STATE DIAGRAM AND ITS--ETC(U)

FEB 81 J K GILLHAM

N00014-76-C-0200

UNCLASSIFIED

TR-22

NL

1/9
AD-A096 127

END

DATE

FEB 81

DTIC

AD A096127

LEVEL II

(13)

OFFICE OF NAVAL RESEARCH

Contract N00014-76-C-0200

Task No. NR 356-504

TECHNICAL REPORT NO. 22

DTIC
ELECTE
MAR 10 1981

THE TIME-TEMPERATURE-TRANSFORMATION (TTT)
STATE DIAGRAM AND ITS ROLE IN DETERMINING
STRUCTURE/PROPERTY RELATIONSHIPS
IN THERMOSETTING SYSTEMS

by

J. K. Gillham

Prepared for publication in American Chemical Society,
Preprints, Division of Organic Coatings and Plastics
Chemistry, Atlanta, Georgia, March 1981.

Princeton University
Polymer Materials Program
Department of Chemical Engineering
Princeton, NJ 08544

February 1981

Reproduction in whole or in part is permitted for
any purpose of the United States Government

This document has been approved for public release
and sale; its distribution is unlimited

Principal Investigator
J. K. Gillham
609/452-4694

DDC FILE COPY

81 3 9 083

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER Technical Report #22	2. GOVT ACCESSION NO. AD-A096 127	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) (6) The Time-Temperature-Transformation (TTT) State Diagram and its Role in Determining Structure/Property Relationships in Thermosetting Systems.	5. TYPE OF REPORT & PERIOD COVERED Feb. 1980 - Feb. 1981	
7. AUTHOR(s) (10) J. K. Gillham	8. CONTRACT OR GRANT NUMBER(s) (15) N00014-76-C-0200	
9. PERFORMING ORGANIZATION NAME AND ADDRESS Polymer Materials Program Department of Chemical Engineering Princeton University, Princeton, NJ 08544	10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS Task No. NR 356-504	
11. CONTROLLING OFFICE NAME AND ADDRESS Office of Naval Research 800 North Quincy St. Arlington, VA 22217	12. REPORT DATE (11) February 1981	13. NUMBER OF PAGES 11 (12) 171
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office) (9) Technical Rept. Feb 80 - Feb 81	15. SECURITY CLASS. (of this report) 15a. DECLASSIFICATION/DOWNGRADING SCHEDULE	
16. DISTRIBUTION STATEMENT (of this Report) Approved for Public Release; Distribution Unlimited.		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		
18. SUPPLEMENTARY NOTES		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) Torsion Pendulum Transitions Torsional Braid Analysis Rubber-modified thermosets Cure Epoxies		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) A generalized time-temperature-transformation (TTT) state diagram for the thermosetting process is presented in which the four physical states encountered (i.e., liquid, rubber, ungelled glass and gelled glass) are related to the time and temperature of cure. Gelation and vitrification, as a consequence of quenching morphological development and chemical conversion respectively, are discussed with respect to control of material properties.		

THE TIME-TEMPERATURE-TRANSFORMATION (TTT) STATE DIAGRAM
AND ITS ROLE IN DETERMINING STRUCTURE/PROPERTY RELATIONSHIPS
IN THERMOSETTING SYSTEMS

J. K. Gillham
*Polymer Materials Program
Department of Chemical Engineering
Princeton University
Princeton, New Jersey 08544*

ABSTRACT

A generalized time-temperature-transformation (TTT) state diagram for the thermosetting process is presented in which the four physical states encountered (i.e., liquid, rubber, ungelled glass and gelled glass) are related to the time and temperature of cure. Gelation and vitrification, as a consequence of quenching morphological development and chemical conversion respectively, are discussed with respect to control of material properties.

TIME-TEMPERATURE-TRANSFORMATION (TTT) STATE DIAGRAMS

Recent research (1-5) has indicated that a Time-Temperature-Transformation diagram (analogous to the TTT diagrams that have been employed for many years in metallurgical processing) may be used to provide an intellectual framework within which an understanding of the physical properties of thermosetting matrices may be achieved.

Figure 1a (3) shows a generalized TTT diagram obtained from isothermal experiments for a typical thermosetting process that does not involve phase separation. It displays the four distinct material states (liquid, elastomer, ungelled glass and gelled glass) that are encountered during cure. Three critical temperatures are also displayed on the diagram. These are $T_{g\infty}$, the

maximum glass transition temperature of the fully cured system, $_{gel}T_g$, the isothermal temperature at which gelation and vitrification occur simultaneously, and $_{resin}T_g$, the glass transition temperature of the reactants.

When a thermosetting material is cured isothermally above $T_{g\infty}$, the liquid gels to form an elastomer but it will not vitrify in the absence of degradation. (Vitrification due to degradation is shown in Fig. 1). An isothermal cure at an intermediate temperature between $_{gel}T_g$ and $T_{g\infty}$ will cause the material first to gel and then to vitrify. If chemical reactions are quenched by vitrification it follows that the glass transition temperature will then equal the temperature of cure and that such a material will not be fully cured. At temperatures below $_{gel}T_g$ but above $_{resin}T_g$ the viscous curing liquid can vitrify simply by an increase of molecular weight and, if chemical reactions are quenched by vitrification, the material need not gel.

It is immediately apparent that structure-property relationships will only be meaningful if the material is fully reacted. This is generally only possible by curing above $T_{g\infty}$.

As indicated in Fig. 1 the time to vitrify passes through a minimum between $_{gel}T_g$ and $T_{g\infty}$. This behavior reflects the competition between the increased rate constant for reaction and the increasing chemical conversion required to achieve vitrification as the temperature is increased. Also, as indicated in Fig. 1, the time to vitrify passes through a maximum between $_{resin}T_g$ and $_{gel}T_g$. This behavior reflects the competition between the temperature and time dependence of viscosity of the reacting system.

The cure TTT diagram of Fig. 1a can be extended (see Fig. 1b) to include two phase systems such as the rubber-modified thermosets used to

improve the toughness of glassy state thermosets. The curing of such rubber-modified systems may involve a change from an initially homogeneous solution to a heterogeneous morphology with dispersed rubber. Figure 1b includes the locus of the visual onset of phase separation. Gelation may arrest the development of the rubber second phase and therefore procedures which alter the time and temperature to gelation can be used to control the material properties. Control of the time-temperature history of the material during cure is a method of achieving the desired degree of phase separation, but a knowledge of the TTT diagram is prerequisite for such a procedure. Since the nucleation and growth of the rubber phase involves a balance between nucleus formation and matter transport, the degree of phase separation achieved in an isothermal process would be expected to show a maximum at a temperature between that for which thermodynamics favors the solubility of the rubber in the matrix and the $T_{g, \text{resin}}$ of the matrix (6). Careful control of the cure temperature will also permit the size and number of particles per unit volume of the dispersed rubber phase to be modified and hence have a strong effect on the mechanical properties. Evidence has been presented (6,7) to show that improved material toughness arises in rubber-modified systems in which part of the rubber is phase-separated and part is trapped "in solution" in the matrix. The path taken on the TTT diagram must therefore be chosen so as to balance the distribution of the rubber between the two phases.

A continuous Heating Transformation (CHT) State Diagram (not shown) which is analogous to the isothermally obtained TTT state diagram can be obtained experimentally from a series of temperature scans at different rates from below the glass transition temperature of the reactants ($T_{g, \text{resin}}$) to above $T_{g, \infty}$. A typical scan for a homogeneous reactive system will reveal in

sequence: relaxations in the glassy state, resin T_g , gelation, vitrification, revitrification and (in the presence of some types of degradation) revitrification. After vitrification on cure, in these scans, the glass transition temperature will in principle equal the instantaneous scanning temperature until the rate of chemical reaction is not sufficient to overcome the increased segmental mobility of the developing network, at which temperature the material will devitrify.

TORSIONAL BRAID ANALYSIS (TBA) - A METHOD FOR CONSTRUCTING TTT & CHT STATE DIAGRAMS

An automated, free-hanging, freely decaying torsion pendulum has been developed (1,8) which permits monitoring of the changes which occur throughout cure by using a support (e.g. braid) impregnated with the reactive system (TBA).

The TTT diagram (Fig. 1a) can be generated by measuring times to gel and to vitrify at a series of isothermal temperatures. These transformation times have been obtained using TBA from measurements of peaks in the mechanical damping as a function of time which correspond to points of inflection in the rigidity curves. Complementary CHT diagrams have been generated by scanning the temperature range from below the glass transition temperature of the reactant mixture, resin T_g , to above $T_{g\infty}$ at a series of constant heating rates.

Details of procedures and results on structure-property relationships of thermosetting systems are provided in recent publications (1-12).


An advantage of a freely suspended torsion pendulum specimen over forced systems is its sensitivity which is the consequence of the free end.

This has led to the revelation of fine details in the dynamic mechanical spectra which suggest, for example, that gelation is a multistep process (4,10,11).

EFFECT OF EXTENT OF CURE ON MATERIAL BEHAVIOR

In principle, cure at a temperature T_{cure} which is below $T_{g\infty}$ will lead to the glass transition temperature $T_g = T_{\text{cure}}$. Post-cure above $T_{g\infty}$ will lead to $T_g = T_{g\infty}$. An epoxy was cured according to the manufacturer's specifications and yielded the thermomechanical TBA behavior "before post-cure" shown in Fig. 2 (which lists experimental details and a summary of transitions). It is apparent that the cure cycle was not sufficient to have $T_g = T_{\text{cure}}$. Post-cure resulted in significant increase in T_g as well as change in the viscoelastic behavior (e.g., the damping behavior) below the glass transition. In particular, a small but significant decrease in the rigidity (i.e. modulus if no dimensional changes occur on post-cure) occurred in the glassy state at, for example 0°C (0mV, Fig. 2) in consequence of the post-cure. This is a result of the non-equilibrium nature of the glassy state. Cooling at the same rate through a glass transition leads to a supercooled liquid which is further from equilibrium at, e.g. 0°C, the higher the T_g .

Consider (Fig. 3) two specimens (1 and 2), one cured above $T_{g\infty}$ at temperature ${}_2T_{\text{cure}}$, the other cured below $T_{g\infty}$ at temperature ${}_1T_{\text{cure}}$. Specimen 1 vitrified on cure to give a glass transition equal to the temperature of cure. Specimen 2 reacted completely to give the maximum glass transition temperature ($T_{g\infty}$). In the hypothetical absence of further reaction above temperature ${}_1T_{\text{cure}}$ the specific volume of the specimen cured at the lower temperature will be higher at ${}_2T_{\text{cure}}$ than that cured at ${}_2T_{\text{cure}}$ (due to lower crosslink density and more unreacted ends). The



diagram, Fig. 3 (13), shows that cooling of the more completely reacted material (at equal rates) results in a higher T_g and indicates how a higher specific volume^{may} result in the glassy state. The fundamental reason is that the material with the higher T_g is further from equilibrium at e.g. room temperature (RT).

The higher free volume at RT of the more highly crosslinked material is held responsible for its lower density and lower modulus at RT and greater water absorption on immersion at RT (5,13).

EFFECT OF GELATION ON MATERIAL PROPERTIES IN TWO-PHASE SYSTEMS

The influence of gelation time on morphology is made evident by comparison of the thermomechanical TBA behavior of a rubber-modified epoxy cured without (Fig. 4a) and with (Fig. 4b) catalyst (12). The glass transition temperature of the rubber is much more dominant in the sample cured without catalyst. This suggests that the extent of phase separation depends on the time available for phase separation which is limited by the process of gelation. The higher glass transition temperature of the epoxy for the sample cured with the longer gelation time also suggests more complete separation of the two phases.

REFERENCES

1. J. K. Gillham, Polym. Eng. Sci., 19, 676 (1979).
2. A. F. Lewis, M. J. Doyle and J. K. Gillham, Polym. Eng. Sci., 19, 683 (1979).
3. J. K. Gillham, SPE, Proceedings, ANTEC Meeting, N.Y. (1980) 268.
4. J. B. Enns, J. K. Gillham, and M. J. Doyle, ACS, Prep., Div. Org. Coat. Plast. Chem., 43, 669 (1980).
5. M. J. Doyle, J. K. Gillham, S. J. Washburn and C. A. McPherson, ACS, Prepr., Div. Org. Coat. Plast. Chem., 43, 677 (1980).

6. L. T. Manzione, J. K. Gillham and C. A. McPherson, J. Appl. Polym. Sci., 26, 889 (1981).
7. L. T. Manzione, J. K. Gillham and C. A. McPherson, J. Appl. Poly. Sci., 26, 907 (1981).
8. J. K. Gillham, Am. Inst. Chem. Eng. Journal, 20, 1066 (1974).
9. N. S. Schneider, J. F. Sprouse, G. L. Hagnauer and J. K. Gillham, Polym. Eng. Sci., 19, 304 (1979).
10. J. K. Gillham, Polym. Eng. Sci., 19, 319 (1979).
11. J. K. Gillham, ACS Symp. Series, Resins for Aerospace, 132, Ch. 26, 1980.
12. J. K. Gillham, C. A. Glandt and C. A. McPherson, in Chemistry and Properties of Crosslinked Polymers, Acad. Press, NY 1977, p. 491.
13. S. J. Washburn, Senior Thesis, Dept. Chem. Eng., Princeton Univ., May 1980.

ACKNOWLEDGMENT

Partial support by the Chemistry Branch of the Office of Naval Research is acknowledged.

FIGURE CAPTIONS

- Fig. 1. Schematic Time-Temperature-Transformation (TTT) diagrams obtained isothermally for the curing process. a) A thermosetting system not involving phase separation. b) A thermosetting system in which a rubber phase may separate during cure. The visual onset of phase separation (the "cloud point") is indicated. (T_g is the maximum temperature for phase separation to occur prior to gelation.)
- Fig. 2. Thermomechanical behavior (TBA) of an epoxy after recommended cure and after post-cure. Note the decreased rigidity at 0°C (0mV) after post-cure.
- Fig. 3. Schematic: Specific volume versus temperature in the absence of chemical reaction. Cured at temperature $1T_{cure}$: dashed line. Cured at temperature $2T_{cure}$: solid line. Note the higher specific volume at room temperature (RT) of the more highly reacted system.
- Fig. 4. Thermomechanical behavior (TBA) of an epoxy-rubber system following identical time-temperature cure paths. a) Zero parts per hundred of catalyst. b) 0.5 parts per hundred of catalyst.




Fig. 1a




Fig. 1b




Figure 2




Fig. 3




Fig. 4a




Fig. 4b

TECHNICAL REPORT DISTRIBUTION LIST, GEN

	<u>No. Copies</u>		<u>No. Copies</u>
Office of Naval Research Attn: Code 472 800 North Quincy Street Arlington, Virginia 22217	2	U.S. Army Research Office Attn: CRD-AA-IP P.O. Box 1211 Research Triangle Park, N.C. 27709	1
ONR Branch Office Attn: Dr. George Sandoz 536 S. Clark Street Chicago, Illinois 60605	1	Naval Ocean Systems Center Attn: Mr. Joe McCartney San Diego, California 92152	1
ONR Area Office Attn: Scientific Dept. 715 Broadway New York, New York 10003	1	Naval Weapons Center Attn: Dr. A. B. Amster, Chemistry Division China Lake, California 93555	1
ONR Western Regional Office 1030 East Green Street Pasadena, California 91106	1	Naval Civil Engineering Laboratory Attn: Dr. R. W. Drisko Port Hueneme, California 93401	1
ONR Eastern/Central Regional Office Attn: Dr. L. H. Peebles Building 114, Section D 666 Summer Street Boston, Massachusetts 02210	1	Department of Physics & Chemistry Naval Postgraduate School Monterey, California 93940	1
Director, Naval Research Laboratory Attn: Code 6100 Washington, D.C. 20390	1	Dr. A. L. Slafkosky Scientific Advisor Commandant of the Marine Corps (Code RD-1) Washington, D.C. 20380	1
The Assistant Secretary of the Navy (RE&S) Department of the Navy Room 4E736, Pentagon Washington, D.C. 20350	1	Office of Naval Research Attn: Dr. Richard S. Miller 800 N. Quincy Street Arlington, Virginia 22217	1
Commander, Naval Air Systems Command Attn: Code 310C (H. Rosenwasser) Department of the Navy Washington, D.C. 20360	1	Naval Ship Research and Development Center Attn: Dr. G. Bosmajian, Applied Chemistry Division Annapolis, Maryland 21401	1
Defense Technical Information Center Building 5, Cameron Station Alexandria, Virginia 22314	12	Naval Ocean Systems Center Attn: Dr. S. Yamamoto, Marine Sciences Division San Diego, California 91232	1
Dr. Fred Saalfeld Chemistry Division, Code 6100 Naval Research Laboratory Washington, D.C. 20375	1	Mr. John Boyle Materials Branch Naval Ship Engineering Center Philadelphia, Pennsylvania 19112	1

TECHNICAL REPORT DISTRIBUTION LIST, GENNo.
Copies

Dr. Rudolph J. Marcus
Office of Naval Research
Scientific Liaison Group
American Embassy
APO San Francisco 96503

1

Mr. James Kelley
DTNSRDC Code 2803
Annapolis, Maryland 21402

1

TECHNICAL REPORT DISTRIBUTION LIST, 356A

	<u>No. Copies</u>		<u>No. Copies</u>
Dr. Stephen H. Carr Department of Materials Science Northwestern University Evanston, Illinois 60201	1	Picatinny Arsenal Attn: A. M. Anzalone, Building 3401 SMUPA-FR-M-D Dover, New Jersey 07801	1
Dr. M. Broadhurst Bulk Properties Section National Bureau of Standards U.S. Department of Commerce Washington, D.C. 20234	2	Dr. J. K. Gillham Department of Chemistry Princeton University Princeton, New Jersey 08540	1
Professor G. Whitesides Department of Chemistry Massachusetts Institute of Technology Cambridge, Massachusetts 02139	1	Douglas Aircraft Co. Attn: Technical Library Cl 290/36-84 AUTO-Sutton 3855 Lakewood Boulevard Long Beach, California 90846	1
Professor J. Wang Department of Chemistry University of Utah Salt Lake City, Utah 84112	1	Dr. E. Baer Department of Macromolecular Science Case Western Reserve University Cleveland, Ohio 44106	1
Dr. V. Stannett Department of Chemical Engineering North Carolina State University Raleigh, North Carolina 27607	1	Dr. K. D. Pae Department of Mechanics and Materials Science Rutgers University New Brunswick, New Jersey 08903	1
Dr. D. R. Uhlmann Department of Metallurgy and Material Science Massachusetts Institute of Technology Cambridge, Massachusetts 02139	1	NASA-Lewis Research Center Attn: Dr. T. T. Serofini, MS-49-1 21000 Brookpark Road Cleveland, Ohio 44135	1
Naval Surface Weapons Center Attn: Dr. J. M. Augl, Dr. B. Hartman White Oak Silver Spring, Maryland 20910	1	Dr. Charles H. Sherman Code TD 121 Naval Underwater Systems Center New London, Connecticut	1
Dr. G. Goodman Globe Union Incorporated 5757 North Green Bay Avenue Milwaukee, Wisconsin 53201	1	Dr. William Risen Department of Chemistry Brown University Providence, Rhode Island 02192	1
Professor Hatsuo Ishida Department of Macromolecular Science Case-Western Reserve University Cleveland, Ohio 44106	1	Dr. Alan Gent Department of Physics University of Akron Akron, Ohio 44304	1

TECHNICAL REPORT DISTRIBUTION LIST, 356A

	<u>No.</u> <u>Copies</u>		<u>No.</u> <u>Copies</u>
Mr. Robert W. Jones Advanced Projects Manager Hughes Aircraft Company Mail Station D 132 Culver City, California 90230	1	Dr. T. J. Reinhart, Jr., Chief Composite and Fibrous Materials Branch Nonmetallic Materials Division Department of the Air Force Air Force Materials Laboratory (AFSC) Wright-Patterson AFB, Ohio 45433	1
Dr. C. Giori IIT Research Institute 10 West 35 Street Chicago, Illinois 60616	1	Dr. J. Lando Department of Macromolecular Science Case Western Reserve University Cleveland, Ohio 44106	1
Dr. M. Litt Department of Macromolecular Science Case Western Reserve University Cleveland, Ohio 44106	1	Dr. J. White Chemical and Metallurgical Engineering University of Tennessee Knoxville, Tennessee 37916	1
Dr. R. S. Roe Department of of Materials Science and Metallurgical Engineering University of Cincinnati Cincinnati, Ohio 45221	1	Dr. J. A. Manson Materials Research Center Lehigh University Bethlehem, Pennsylvania 18015	1
Dr. Robert E. Cohen Chemical Engineering Department Massachusetts Institute of Technology Cambridge, Massachusetts 02139	1	Dr. R. F. Helmreich Contract RD&E Dow Chemical Co. Midland, Michigan 48640	1
Dr. T. P. Conlon, Jr., Code 3622 Sandia Laboratories Sandia Corporation Albuquerque, New Mexico	1	Dr. R. S. Porter Department of Polymer Science and Engineering University of Massachusetts Amherst, Massachusetts 01002	1
Dr. Martin Kaufmann, Head Materials Research Branch, Code 4542 Naval Weapons Center China Lake, California 93555	1	Professor Garth Wilkes Department of Chemical Engineering Virginia Polytechnic Institute and State University Blacksburg, Virginia 24061	1
Professor S. Senturia Department of Electrical Engineering Massachusetts Institute of Technology Cambridge, Massachusetts 02139	1	Dr. Kurt Baum Fluorochem Inc. 6233 North Irwindale Avenue Azusa, California 91702	1
		Professor C. S. Paik Sung Department of Materials Sciences and Engineering Room 8-109 Massachusetts Institute of Technology Cambridge, Massachusetts 02139	1

