

AD-A125 048

NUMERICAL ANALYSIS IN FRACTURE MECHANICS(U) WASHINGTON
UNIV SEATTLE DEPT OF MECHANICAL ENGINEERING
A S KOBAYASHI 20 JAN 83 UWA/DME/TR-83/45

1/1

UNCLASSIFIED

N00014-76-C-0060


F/G 20/11

NL

END

FILMED

DTIC



MICROCOPY RESOLUTION TEST CHART
NATIONAL BUREAU OF STANDARDS-1963-A

13

AD A125048

OFFICE OF NAVAL RESEARCH
CONTRACT N00014-76-0060 NR 064-478

Technical Report No.
UWA/DME/TR-83/45

NUMERICAL ANALYSIS IN FRACTURE
MECHANICS

by

A. S. Kobayashi

January 1983


DTIC FILE COPY

The research reported in this technical report was made possible through support extended to the Department of Mechanical Engineering, University of Washington, by the Office of Naval Research under contract N00014-76-C-0060 NR 064-478. Reproduction in whole or in part is permitted for any purpose of the United States Government.

Department of Mechanical
Engineering
College of Engineering
University of Washington




This document has been approved
for public release and sale; its
distribution is unlimited.



A

83 02 023 190



NUMERICAL ANALYSIS IN FRACTURE MECHANICS

A. S. Kobayashi

Department of Mechanical Engineering, University of Washington
Seattle, Washington, USA 98195

ABSTRACT

Recent developments in four numerical techniques in structural mechanics, which are used to extract fracture parameters for linear elastic, nonlinear and dynamic fracture mechanics, are reviewed. Primary emphasis is placed on the finite element methods for determining two- and three-dimensional (2-D and 3-D) stress intensity factors in linear elastic fracture mechanics. Crack opening displacements (COD) and J-integrals for 2-D, stable crack growth, ductile fracture, and use of elastic finite element method in its generation mode for obtaining dynamic elastic fracture parameters are discussed. The second topic is the finite difference method for analyzing the elasto-dynamic and elastic-plastic dynamic states in fracturing 2- and 3-D problems. The use of a super finite difference code to study dynamic ductile fracture using the void growth and coalescence model is discussed. The third topic is the boundary element method which has evolved into a practical tool for numerical analysis in 3-D linear elastic fracture mechanics. The final topic is the updated alternating technique, which was merged with a 3-D finite element code and together with a break-through in its analytical formulation, has become a cost-effective numerical technique in solving part and complete elliptical crack problems in 3-D linear elastic fracture mechanics. Comparisons between the J-integral of a 3-point bend specimen, the stress intensity factor for a surface flaw specimen and the dynamic stress intensity factor of a fracturing dynamic tear test specimen obtained by various investigators are made.

INTRODUCTION

Successful applications of linear elastic fracture mechanics (LEFM) in numerous postmortem analyses of failures in aerospace structures of the early 60's and its expanded role in design synthesis in the 70's required precise knowledge of the stress intensity factors associated with cracks. Such stress intensity factors of two-dimensional (2-D) and three-dimensional (3-D) cracks, which are subjected to complex loading conditions can only be obtained through numerical techniques. As a result, numerical analysis of fracture mechanics problems became the most active branche of structural mechanics in the 1970's [1]. One of the first numerical solutions in fracture problems, however, is the finite difference elastic-plastic result of Jacobs in 1950 [2] which was followed by others in the 1960's [3 - 5]. Swedlow et al [6], on the other

hand, used finite element method to study a similar problem. In essence, these numerical results on the elasto-plastic states in cracked plates were ahead of their time since no plausible ductile fracture criterion was available in the early 1960's.

During this period of soul searching, other specialized numerical techniques, which were specially designed to compute mode I (opening mode) SIF in 2-D crack problems, emerged. Such techniques include extensive studies using the boundary collocation method [7], series expansion of a complex mapping function [8] and the method of Laurent series expansion [9]. The numerical solutions, which were generated by these special techniques, are still valid today and are listed in stress intensity factor handbooks and are liberally quoted in literature as well. These techniques, however, failed to generate subsequent supporters and thus will not be discussed in this paper.

In contrast, the overwhelming popularity of finite element method together with the growing acceptance of linear elastic fracture mechanics in structural mechanics in the late 1960's provided the impetus for an orderly development in the use of finite element method for determining stress intensity factors for 2-D linear elastic fracture mechanics [10]. The explosive developments in finite element method approaches to linear elastic fracture mechanics and also to nonlinear as well as dynamic fracture mechanics of the 1970's are documented in several review papers and special conference proceedings [1, 11 - 16]. Limited reviews of available linear elastic fracture mechanics computer software for fracture mechanics are given in References [17, 18].

Review papers covering the other three topics of finite difference method, boundary element method and alternating technique are few and scarce. The boundary element method, however, has attracted a large core of users and its applications to fracture mechanics have been presented at numerous conferences.

The purpose of this paper is to review the above four numerical techniques in fracture mechanics, with particular emphasis on development of finite element method following the period covered in Reference [1].

FINITE ELEMENT METHOD

The above mentioned popularity in the use of finite element method in every aspect of fracture mechanics has resulted in technical papers too numerous to be included in this review. Thorough reviews on the applications of finite element techniques to 2-D static and quasi-static problems in fracture mechanics through the 1970's have appeared in References [1, 11 - 15]. The historical and important developments of this era will not be repeated as this paper will concentrate on the 3-D static and 2-D nonlinear and dynamic analyses which emerged during and after this period.

A. 3-D Static LEFM Singularity Element

Although 3-D finite element method codes are available commercially, the mode I stress intensity factor for a seemingly simple surface flaw in a uniaxial tension plate requires inordinate amount of computer time. The densely packed 3-D constant strain quadrilaterals along the curved crack front [19]

for proper modeling of the $1/\sqrt{r}$ stress singularity results in an inefficient use of computer time. Although crack opening displacements (COD) was used to improve the accuracy of mode I stress intensity factor, K_I , the accuracy of such brute force computation remains in doubt. The 3-D counterpart [20] of the virtual crack extension method [21] attempted to increase, by computing the local strain energy change for small crack tip displacements in conventional displacement elements, the solution accuracy without excessive number of finite elements.

a. Singularity Element

Computational efficiency can also be improved by incorporating the $1/\sqrt{r}$ strain singularity in the displacement elements. Raju and Newman [22] used such singularity element and reduced the effect of interelement displacement discontinuity by surrounding the crack tip with two layers of "square-root" elements. A series of nodal forces adjacent to the crack tip was then used to compute K_I . The multitude of 3-D problems analyzed by this procedure include the surface flaw problems [23] in pressurized cylinders.

b. Collapsed Quarter-Point Isoparametric Element

The popularity [1] of Barsoum's collapsed quarter-point isoparametric element [24] is due to its simplicity in execution which does not require special subroutines to available 3-D finite element method codes. These elements have the correct $1/\sqrt{r}$ singularity and together with proper stress intensity factor extraction procedure, will yield stress intensity factor of sufficient accuracy along the crack front. While many use the crack opening displacement procedures or the crack-tip stress formula to compute the stress intensity factor in 3-D problems, few procedures are developed specifically for 3-D applications. In the following, two such procedures are described.

Ingraffea [26] has shown that for collapsed 20-node isoparametric elements surrounding the crack front of Figure 1, the three modes of stress intensity factors can be written in terms of the mapped curvilinear coordinates of ξ , η and ζ as

$$K_I = \frac{E}{4(1-\nu^2)} \sqrt{\frac{\pi}{2L_1}} \left[2v_B - v_C + 2v_E - v_F + v_D - 2v_{B'} + v_{C'} - 2v_{E'} \right. \\ \left. + v_{F'} - v_{D'} + \frac{1}{2}\eta(-4v_B + v_C + 4v_E - v_F + 4v_{B'} - v_{C'} - 4v_{E'} + v_{F'}) \right. \\ \left. + \frac{1}{2}\eta^2 (v_F + v_C - 2v_D - v_{F'} - v_{C'} + 2v_{D'}) \right] \quad (1)$$




Fig. (1) - Quarter-point Wedge Elements

$$\begin{aligned}
 K_{II} = \frac{E}{4(1-\nu^2)} \sqrt{\frac{\pi}{2L_1}} & \left[2u_B - u_C + 2u_E - u_F + u_D - 2u_{B'} + u_{C'} - 2u_{E'} \right. \\
 & + u_{F'} - u_{D'} + \frac{1}{2}\eta(-4u_B + u_C + 4u_E - u_F + 4u_{B'} - u_{C'} - 4u_{E'} + u_{F'}) \\
 & \left. + \frac{1}{2}\eta^2 (u_F + u_C - 2u_D - u_{F'} - u_{C'} + 2u_{D'}) \right] \quad (2)
 \end{aligned}$$

$$\begin{aligned}
K_{III} = & \frac{E}{4(1+\nu)} \sqrt{\frac{\pi}{2L_1}} \left[2w_B - w_C + 2w_E - w_F + w_D - 2w_{B'} + w_{C'} - 2w_{E'} \right. \\
& + w_{F'} - w_{D'} + \frac{1}{2}\eta(1-4w_B + w_C + 4w_E - w_F + 4w_{B'} - w_{C'} - 4w_{E'} + w_{F'}) \\
& \left. + \frac{1}{2}\eta^2 (w_F + w_C - 2w_D - w_{F'} - w_{C'} + 2w_{D'}) \right] \quad (3)
\end{aligned}$$

where E and ν are the modulus of elasticity and Poisson's ratio, respectively. The three stress intensity factors at η distance along the crack front can be computed by the crack surface displacements of u , v and w on the collapsed element face of $\xi = -1$. In terms of the physical distance along the z coordinate

$$\eta = - (2z/L_2 + 1) \quad (4)$$

where L_2 is the element length along the crack front as shown in Figure 1. The quadratic variation in displacement field in the original 20-node element also results in a quadratic variation in stress intensity factor along each crack front element.

The accuracy of the stress intensity factor extraction procedure is demonstrated by analyzing the embedded elliptical crack problem solved analytically by Green and Sneddon [27]. Because of symmetry, one-eighth of an elliptical crack in a cube composed of 23 elements and 141 nodes was analyzed using SAP IV [28]. The maximum errors in the numerical results, when compared against the theoretical results [27], were 5% and 7% for a circular crack and an elliptical crack with an aspect ratio of 1.5, respectively. At the tip of the minor axis where the SIF is maximum in the elliptical crack, the error was 2%.

c. Finite Element Hybrid Method

Since a review on the use of finite element hybrid method in fracture mechanics appeared in Reference [1], substantial progress has been made in improving its computational efficiency. Hybrid formulation is now restricted to finite elements surrounding the crack front with the crack-tip singularity being preserved through assumed $1/\sqrt{r}$ stress or $\sqrt{r}$ displacement field. Computational efficiency is achieved by the general purpose finite element code which models the bulk of the boundary value problem. The effect of inter-element discontinuity between the singular and conventional elements is minimized through the hybrid formulation. For 2-D problems, the hybrid method can be formulated such that one element, which has the assumed $1/\sqrt{r}$ singularity and also an assumed compatible boundary displacements, completely encompasses the

crack tip [29]. For 3-D problems, the crack front becomes one of the boundaries of the several hybrid elements which surround the crack tip. The assumed stress hybrid method is based on an assumed equilibrating stress field, which contains the proper crack-tip singularity, and on independently assumed boundary displacements [30]. In terms of the local coordinates of n , z and t , the singular stress and corresponding displacements fields are represented as

$$\begin{pmatrix} \sigma_n \\ \sigma_z \\ \sigma_t \\ \tau_{nz} \\ \tau_{zt} \\ \tau_{nt} \end{pmatrix} = \frac{1}{\sqrt{2\pi r}} \left[K_I \begin{pmatrix} \cos \frac{\theta}{2} (1 - \sin \frac{\theta}{2} \sin \frac{3\theta}{2}) \\ \cos \frac{\theta}{2} (1 + \sin \frac{\theta}{2} \sin \frac{3\theta}{2}) \\ 2\nu \cos \frac{\theta}{2} \\ \sin \frac{\theta}{2} \cos \frac{\theta}{2} \cos \frac{3\theta}{2} \end{pmatrix} + K_{II} \begin{pmatrix} -\sin \frac{\theta}{2} (2 + \cos \frac{\theta}{2} \cos \frac{3\theta}{2}) \\ \sin \frac{\theta}{2} \cos \frac{\theta}{2} \cos \frac{3\theta}{2} \\ -2\nu \sin \frac{\theta}{2} \\ \cos \frac{\theta}{2} (1 - \sin \frac{\theta}{2} \sin \frac{3\theta}{2}) \end{pmatrix} \right. \\ \left. K_{III} \begin{pmatrix} \cos \frac{\theta}{2} \\ -\sin \frac{\theta}{2} \end{pmatrix} \right] \quad (5)$$

$$\begin{pmatrix} u_n \\ u_z \\ u_t \end{pmatrix} = \frac{1}{G} \frac{\sqrt{2r}}{\pi} \left[\frac{K_I}{8} \begin{pmatrix} (5-8\nu) \cos \frac{\theta}{2} - \cos \frac{3\theta}{2} \\ (7-8\nu) \sin \frac{\theta}{2} - \sin \frac{3\theta}{2} \end{pmatrix} + \frac{K_{II}}{8} \begin{pmatrix} (9-8\nu) \sin \frac{\theta}{2} + \sin \frac{3\theta}{2} \\ (-3+8\nu) \cos \frac{\theta}{2} - \cos \frac{3\theta}{2} \end{pmatrix} \right. \\ \left. K_{III} \sin \frac{\theta}{2} \right] \quad (6)$$

where r and θ are the local polar coordinates in the plane normal to the crack front. While 2-D finite element method codes can incorporate higher order terms in r , such as the constant, $\sqrt{r}$, r ... terms [31], corresponding series forms of equations (3) and (4) are not available. The assumed stress in the crack tip hybrid element is thus represented as

$$\sigma_{ij} = \sum_m P_{s_{ijm}} (1/\sqrt{r}, \theta) K_m + \sum_n P_{r_{ijn}} (x, y, z) \beta_n \quad (7)$$

where the first term of the above is equation (4) and the second term is a

regular polynomial of x , y and z . For a traction free crack, this second term must satisfy the homogeneous equilibrium equations and the traction free boundary conditions on the crack surface. The assumed element boundary displacements contain equation (7) for all element boundaries which intersect with the crack front and satisfy inter-element compatibility. When these hybrid elements are merged into a general purpose 3-D code, equation (7) will introduce as unknowns, the three stress intensity factors of K_m ($m=1,2$ or 3) in addition to the unknown generalized nodal displacement of $\tilde{q}_m$ as

$$\begin{bmatrix} \tilde{K}_{rr} & \tilde{K}_{rs} \\ \tilde{K}_{rs}^T & \tilde{K}_{ss} \end{bmatrix} \begin{Bmatrix} \tilde{q} \\ \tilde{K}_m \end{Bmatrix} = \begin{Bmatrix} Q \\ \tilde{Q} \end{Bmatrix}$$

(8)

$\tilde{q}$ and K_m are thus obtained by solving equation (8).

Pian and Moriya [32] used a twelve node, assumed stress hybrid, half element, as shown in Figure 2, to determine the distribution of stress




Fig. (2) Three-Dimensional Hybrid Elements

intensity factor along a semi-circular surface crack in a tension specimen. Because of four way symmetry, only one quadrant of the specimen was analyzed with 284 nodes and 852 degrees of freedom. The numerical results, when compared with Smith's results [33] obtained by the alternating technique, were

within 12% at the free surface and coincided at the maximum crack depth.

The assumed displacement hybrid method is based on an assumed displacement field, which includes equation (6) with K_m , and independently assumed element boundary displacements and boundary tractions. The general format of the final element equation is identical to equation (8) where K_m is treated also as three unknowns along the the crack front.

Atluri and Katherisean [34] used static condensation to produce a 20 node quadratic isoparametric super-element, as shown in Figure 3, based on the




Fig. (3) Super Singular Element

assumed displacement hybrid method. Using this super-element in a general 3-D finite element code, they analyzed the surface flaw problem with 280 finite elements and 4815 degrees of freedom. The results are discussed in the last section entitled "Benchmark Solutions" of this paper.

B. 2-D Nonlinear Singularity Element

Since the early use [6] of constant strain elements for elastic-plastic finite element method analysis of 2-D fracture problems, this simple element is still used today with success, primarily due to the moderate or lack of stress singularity at the plastically yielded crack tip. Kanninen et al [35] used such finite element method code in both its generation and application modes to study stable crack growth and instability of A533-B steel and 2219-T87 aluminum, center cracked and compact specimens. Loadline displacement and crack length measurements were input into generation-mode calculations and the applied load among others were output for evaluation. Figure 4 shows the computed and measured applied load versus loadline displacement relation of the steel compact specimen. Other uses of the conventional element include




Fig. (4) Load-displacement Curve for A533B Steel CT Specimens

the updated Lagrangian finite-deformation, finite-element analysis by McMeeking and Parks [36] who studied the influence of crack-tip blunting on the J-based characterization of the crack tip region.

For a material with a strain hardening index of n , the strain field of the dominant singularity at the crack tip under deformation theory of plasticity is [37, 38]

$$\sigma_{ij} = \sigma_0 \left(\frac{EJ}{\sigma_0^2 r} \right)^{1/(n+1)} \bar{\sigma}_{ij}(\theta, n) \quad (9)$$

$$\sigma_{ij} = \frac{\sigma_0}{E} \left(\frac{EJ}{\sigma_0^2 r} \right)^{n/(n+1)} \bar{\epsilon}_{ij}(\theta, n) \quad (10)$$

where J is the J-integral as per Rice [39], $\bar{\sigma}_{ij}$ and $\bar{\epsilon}_{ij}$ are functions of θ and n , and σ_0 is the yield stress.

Early uses of the above singular stress and strain fields include that of Hilton [40] who used deformation theory of plasticity to study ductile crack initiation under monotonically increasing load. Shih [40], on the other hand, constructed a circular crack tip element with the dominant stress and strain singularities and studied the changes in elastic-plastic boundaries with variations in n values under small scale yielding. Atluri et al [42] incorporated the above stress and strain singularities into the hybrid-displacement




Fig. (5) Translation of Singular Element

finite elements surrounding the crack tip. The virtual work equation for an incremental crack growth, Δa , as shown in Figure 5, was used to simulate crack closure and opening under a cyclic loading condition with a single overload as shown in Figure 6. The penalty function and superposition method used by Yagawa et al [43] is similar in formulation where the penalty coefficients are stiffness coefficients which optimize the potential function under nonlinear constraints.

For an ideally plastic material, $n = \infty$ in equations (9) and (10) yield $\sigma_{11} = \sigma_0$ and ϵ_{11} with an $1/r$ singularity. Barsoum [44] showed that the same triangular quarter-point element [24] of elastic analysis will possess the $1/r$ strain singularity when the condensed crack tip nodes are allowed to slide. Shih et al [45] used this quarter point element to model crack tip blunting and growth. As shown in Figure 7, crack-tip blunting is modeled by separating the condensed crack tip nodes and crack extension is modeled by sequential shifting of the crack tip node. The crack tip opening displacement (CTOA) and crack tip displacement can be determined directly from Figure 7(c).




Fig. (6) Crack Closure and Opening Stress under Single Overload




Fig. (7) Crack Tip Blunting and Growth

C. 3-D Non-linear Singularity Element

The singularity element used in 3-D elastic-plastic analysis of cracks apparently is limited to Barsoum's triangular quarter-point element. Although this element contains only a $1/r$ singularity, Benzley [46] showed heuristically that when used with a stress-strain relation governed by a power hardening law, this element provided the correct singular states of strain and stress interior of the element. deLorenzi [47] used 556 of such 20-noded isoparametric elements in an 8300 degree-of-freedom system to study the elastic-plastic behavior of a surface flaw in the beltline region of a pressurized reactor vessel. The semi-elliptical crack front was surrounded with triangular quarter-point elements and a Ramberg-Osgood power hardening law for stress-strain relation was used. COD at the symmetry plane, as shown in Figure 8, demonstrated the need for a 3-D elastic-plastic analysis since the plane strain (2-D) approximation clearly overestimated the severity of the flaw.




Fig. (8) COD of a Surface Flaw

D. 2-D Dynamic Singularity Element

Dynamic fracture analysis has also been conducted successfully with conventional elements during the past five years. Such analysis include the extensive code verifications by Kobayashi et al [48, 49] and the recent work by Jung et al [50]. Accuracy of such simplified finite element method codes can be improved by using a proper crack node release mechanism which was the subject of considerable debate in the late 1970's [51 - 53]. This writer's experiences, however, indicate that the simple node release mechanism of linearly decreasing crack-tip nodal force yield dynamic stress intensity factor which are in good agreement with those obtained by photoelasticity [54]. Yagawa et al [55], on the otherhand, represented the crack surface traction, acting on the extending crack surface, as a Lagrange multiplier, and optimized the dissipated surface energy during crack extension.

While singularity elements in dynamic finite element method was used earlier by Anderson et al [56] and Aoki et al [57], the most successful use of such element is by Atluri et al who incorporated the $1/\sqrt{r}$ singularity in the displacement hybrid crack tip element [58, 59]. Figure 9 shows the Atluri's




Fig. (9) Dynamic Crack Growth Using a Singularity Element

singularity element, which moves with the crack tip and retains its shape, and the continually distorting regular elements surrounding the crack tip. Periodic mesh readjustment is necessary with crack extension when this procedure is used. Similar approach without the distorting regular elements

was used by Gunther et al [60]. Figure 10 shows good agreement between the numerically generated dynamic stress intensity factor by Atluri et al and the theoretical solution by Broberg [61].




Fig. (10) Dynamic Stress Intensity Factor of Broberg Crack

Literature is void with 3-D dynamic finite element analysis, due in part to the enormity in computational requirements, but also due to the lack of definitive experimental observations on 3-D dynamic crack extension. Such dynamic crack extension history is necessary to execute a dynamic finite element code in its generation mode. 3-D dynamic analysis by the propagation mode, on the otherhand, requires apriori a 3-D dynamic crack propagation law which is equally missing at this time.

FINITE DIFFERENCE METHOD

As mentioned in the Introduction, finite difference method predates the now popular finite element codes in its application to fracture problems. Subsequent development of the finite difference codes were taken over by weapon researchers and re-emerged as vastly superior general purpose codes which

could solve 3-D problems ranging from dynamic plasticity to gas dynamics. For example, the HEMP 3-D code [62] is an explicit finite difference code which does not require large computer storage. Crack tip singularity is thus handled by swamping the crack region with large number of zones and no known attempt has been made to incorporate crack tip singularities into the computation. Such simplified model results in enormous computer time which normally cannot be executed outside of special laboratories. The code can also handle ductile fracture with relative ease due to the reduced severity in stress singularity.

A. Static Analysis

Historically, the available general purpose finite difference codes were designed to solve complex dynamic problems and thus no static finite difference programs for analyzing static fracture problems exist to date. In an overkill attempt to demonstrate the versatility of such supercodes, Chen [63] showed that the static stress intensity factor can be obtained from a simple average of the stress waves set up in the crack-tip region when high artificial viscosity is inserted to damp out the stress waves in the 3-D supercodes. A similar converge scheme using dynamic relaxation was used by Shmueli et al [64] to obtain the static SIF in a finite thickness, central crack tension plate.




Fig. (11) Dynamic Stress Intensity Factor in an Impulse Loaded Plate

B. Dynamic Analysis

For elastic analysis, a simple extrapolation scheme is used to extract stress intensity factors from the numerically determined crack tip stresses

[63]. Figure 11 shows the dynamic stress intensity factor in a center cracked plate subjected to sudden tension loading. Also shown for comparison is Baker's solution [65] for a pressurized semi-infinite crack which suddenly appeared in an infinite plate. Complex fracture problems, such as an internally or externally surface flawed cylinder subjected to sudden pressurization has also been solved [66] by the HEMP code. The advantage of such supercode, however, lies in its ability to analyze elastic-plastic dynamic fracture problems, such as a notched bar subjected to sudden tensile loading [66, 67] and a Charpy V-notched specimen [68]. In these ductile fracture analyses, a void growth and coalescence criterion [68] was used to predict the onset and propagation of a ductile crack.

Special purpose finite difference codes have been used to analyze dynamic fracture problems but the earlier analyses [70, 71] did not focus on viable dynamic fracture parameters, primarily due to the undeveloped state of science in dynamic fracture at that time. Finite difference method was used by Popelar et al [72] to study the dynamic elastic response of an internally cracked cylinder subjected to impulse loading. The dynamic stress intensity factor was determined by the energy release rate calculated from the displacements at the nodes in the vicinity of the propagating crack tip. Shmueli et al [73] incorporated a moving substructure, as shown in Figure 12 with the proper $1/\sqrt{r}$




Fig. (12) Stationary and Moving Grid

singularity in their finite difference program. One half reduction in computing time in static analysis and improved accuracy in energy release rate computation in dynamic analysis are claimed. As a straightforward application of a dynamic finite difference shell code, Emery et al [74] studied the axial

cracking of a pressurized crack with coupled depressurization calculation. This analysis was extended to large scale yielding with critical CTOA as a dynamic fracture criterion [75].

BOUNDARY ELEMENT METHOD

While the boundary element method, which was earlier referred to as the boundary integral equation method, as a stress analysis tool dates back to the mid 1960's [76], its application towards solving fracture mechanics problems was pioneered by Cruse [77, 78] in the early 1970's. Boundary equation method requires only the discretization of the boundary of the structure in contrast to the domain discretization required by finite element method. Thus boundary equation method is not suitable for analyzing elastic-plastic and elasto-dynamic fracture problems although some recent work [79, 80] suggests that such use of boundary equation method may not be far. On the other hand, the reduced system of equation makes it suitable for solving 3-D linear elastic fracture mechanics problems although it yields a fully populated, nonsymmetric system of equations. Also, for an extending crack, boundary equation method requires only the recomputation of nodes along the crack surface while finite element method requires complete remeshing around the original and extended crack. Recent applications of boundary element method to fracture mechanics has been reviewed by Cruse [81].

A. 2-D Boundary Element Method

Since boundary element method emerged as a numerical tool during the period of successful application of 2-D finite element method to elasto-static problems in linear elastic fracture mechanics, its use in 2-D linear elastic fracture mechanics did not grow until a special Green's function approach [78, 82] was developed. Utilizing the elastic Green's function for an infinite plate with a crack and an interior point load, the stress intensity factors can be represented by the following set of path independent integrals enclosing a crack tip as

$$(K_I, K_{II}) = - \int_B R_i^{I,II}(z_Q) u_i(Q) ds + \int_B L_i^{I,II}(z_Q) t_i(Q) ds \quad (11)$$

where $u_i(Q)$ and $t_i(Q)$ refer to the displacements and surface tractions at boundary point Q . Details of functional, $R_i^{I,II}$ and $L_i^{I,II}$, are given in [83]. By taking advantage of symmetry, Cruse used only seven boundary points to obtain K_I for a central crack fracture specimen with 6.4 CPU seconds.

Blandford et al [84] eliminated the complex arithmetic involved in the above by using traction singular quarter-point boundary elements along each side of the crack tip. The procedure is the boundary element method counterpart of Barsoum's finite element method procedure [24] where the midpoint in

the isoparametric quadratic boundary element is shifted to the quarter point. This totally numerical procedure eliminates the non-uniqueness of flat crack modeling [82] and the matrix singularity problem [85]. Atkinson et al [86] used the path-independent F_I and M integrals [87] to determine K_{III} in an edge cracked square torsion bar with a quadratically varying shear modulus.

B. 3-D Boundary Element Method

Since the first applications of boundary element method to 3-D linear elastic fracture mechanics in the early 1970's [85], significant improvements has been made in the computational algorithm. The use of quadratic isoparametric boundary element elements with quarter point nodes [89] provided accurate COD's which were used to extract the K_I values. Recent solutions to 3-D linear elastic fracture mechanics include the surface flaw solutions in a tension plate [90] and in a pressurized cylinder [91] by Hellot et al and crack growth studies of surface flaw by Cruse [92].

ALTERNATING TECHNIQUE

Application of the alternating technique to 3-D linear elastic fracture mechanics was first introduced by Smith et al [93] who solved the semi-circular surface flaw problem. The procedure was extended to an elliptical crack by Shah et al [94] who determined K_I of an embedded elliptical crack near a free surface. Later, Smith et al [95] extended the solution procedure to K_{II} and K_{III} determination of an elliptical crack. The alternating techniques of those days were relatively inaccurate due to the limited curve fitting capabilities of the third order polynomial of the elliptical crack pressure and of the modeling of the surrounding finite geometry. A major breakthrough in the latter was made by Browning et al [96] and Kullgren et al [97] who used a 3-D finite element code to model the surrounding finite geometry. Grandt [98] and Barrachin et al [99] used this procedure to analyze surface flaw problems and in particular, the well studied surface flaw at a hole.

Another significant improvement was made with the derivation of the complete analytical solution [100] for an embedded elliptical crack in an infinite solid and subjected to modes I, II and III crack tip deformation. Nishioka et al used twelve terms of a fifth order polynomial of this analytical solution together with a standard 3-D finite element code to analyze among other, the surface flaw problem [101] and the internally and externally flawed pressurized cylinders [102]. Figure 13 shows the reduction in residual stress with alternating cycles of iteration for analyzing an externally flawed pressurized cylinder. Figure 14 shows the resultant stress intensity factor which is compared with those of [103, 104]. The finite element method portion of this alternating technique used 96 20-noded isoparametric elements with 1815 degrees of freedom and the total CPU time was about 1000 seconds with a CYBER 74.




Fig. 13 Residual Stress on Crack Surface




Fig. (14) Stress Intensity Factors for an Outer Surface Flaw in a Pressurized Cylinder

BENCHMARK SOLUTIONS

In most cases, numerical techniques are validated by comparing the numerical results with known theoretical solutions. By nature, these theoretical problems in fracture mechanics are simple in geometry and uncomplicated in loading and thus agreement between the numerical and theoretical solutions are bound to be good. Theoretical solutions for more realistic fracture problems do not exist and a consensus between various numerical solutions does not guarantee their correctness. Lacking other means of comparative study, benchmark solutions which are well defined boundary and initial value problems, are used to eliminate any ambiguity in problem definition and to assure that all numerical solutions relate to the same problem. Three such benchmark problems are discussed in the following.

A. 2-D Elastic-Plastic Crack Problem

In 1975, ASTM Committee E24.01.09 undertook a task to compare numerical solutions to elastic-plastic plane strain problems. A three-point fracture toughness test specimen with a uniaxial stress-strain relation of A533B steel was analyzed by 10 respondents and the edited and assembled solutions were presented by Wilson [105]. Figure 15 shows the average J-value, which was




Fig. (15) J versus Applied Load

computed over several integration paths by each investigator, with increasing applied load. While substantial progress has been made in the elastic-plastic codes in the ensuing six years, the wide differences in the results obtained in the late 1970's are still indicative of the lack of consensus for valid 2-D elastic-plastic codes as well as for basic physical laws, such as the constitutive relations under plastic flow under severe strain gradients.

B. 3-D LEFM Problem

The surface flaw problem is an outgrowth of a 1976 workshop at Battelle Columbus Laboratories at which time several 3-D benchmark problems were designated for numerical analysis. The numerical results for the semi-elliptical, surface flaw plates in tension and bending were subsequently assembled and edited by McGowan [106]. Figure 16 shows the normalized stress intensity factors by six investigators where moderate differences are seen.




Fig. (16) Stress Intensity Factor for a Surface-Flawed Tension Plate

C. 2-D Dynamic Crack Problem

While no formal benchmark problem in 2-D dynamic fracture was ever designated for round robin studies, an informal comparative study was made between the investigators at the Georgia Institute of Technology, Battelle Columbus Laboratories and the University of Washington. Dynamic crack propagation in an A533B steel, dynamic tear test (DTT) specimen was analyzed by generation calculation using the crack velocity data provided in [107]. Figure 17 shows the dynamic SIF computed by the three investigators. All three elastic results are in good agreement with each other.




Fig. (17) Dynamic Stress Intensity Factor of a Dynamic Tear Test Specimen

CONCLUDING REMARKS

The concluding remarks in this paper could have been taken from Reference [1] since the four cited and the numerous uncited numerical techniques in fracture mechanics continue to develop at equal or even higher pace since Reference [1] was written. Also, the efficiency in numerical techniques continues to improve despite the rapid increase in the complexity of the problems studied.

Despite this explosive rate of development, coordinated efforts to evaluate the old as well as new numerical codes through benchmark problems are scarce. In order to properly assess the numerous codes available today, an international effort in code verification is badly needed at this time.

ACKNOWLEDGEMENT

The effort in compiling this survey paper was supported by an ONR Contract No. N00014-76-C-0000 NR 064-478. The author acknowledges the support and encouragement of Dr. Y. Rajapakse, ONR. Special gratitude is due to Professor S. N. Atluri, Georgia Institute of Technology for reading this manuscript and providing valuable comments and to Dr. T. A. Cruse, United Technologies, Pratt and Whitney Aircraft for providing literature on the boundary element method.

REFERENCES

- [1] Gallagher, Richard H., "A Review of Finite Element Techniques in Fracture Mechanics", Numerical Methods in Fracture Mechanics, Proc. of the 1st Int. Conf., ed. by A. R. Luxmoore and D. R. J. Owens, Univ. College Swansea, p. 1, Jan. 1978.
- [2] Jacobs, J. A., "Relaxation Methods Applied to Problems of Plastic Flow I, Notched Bar Under Tension", Phil. Mag., 41, p. 47, 1950.
- [3] Stimpson, L. D. and Eaton, D. M., "The Extent of Elastic-Plastic Yielding at the Crack Point of an Externally Notched Plane Stress Tensile Specimen, Guggenheim Aero. Lab. of Cal. Inst. of Tech. Rept. SM 60-10, June 1960.
- [4] Roberts, E. Jr. and Mendelson, A., "Analysis of Plastic Thermal Stresses and Strains in Finite Thin Plate of Strain Hardening Material", NASA TN D-2206, Oct. 1964.
- [5] Kobayashi, A. S., Woo, S. and Shah, R. C. "Plane-Stress, Elastic-Plastic States in the Vicinity of Crack Tips", NASA CR-772, April 1967.
- [6] Swedlow, J. L., Williams, M. L. and Yang, W. H., "Elasto-Plastic Stresses and Strains in Cracked Plates", Proc. of Int. Conf. on Fracture I, Sendai, Japan, p. 259, 1966.
- [7] Gross, B., Srawley, J. E. and Brown, W. F., "Stress Intensity Factors for a Single-Edge-Notch Tension Specimen by Boundary Collocation of Stress Function", NASA TN D-2395, August 1964.
- [8] Bowie, O. L., "Solutions of plane crack problems by mapping technique", Mechanics of fracture I, Methods of analysis and solutions of crack problems, ed. G. C. Sih, Noordhoff Int., p. B1, 1972.
- [9] Isida, M., "Method of Laurent series expansion for internal crack", Mechanics of fracture I, Methods of analysis and solutions of crack problems, ed. G. C. Sih, Noordhoff Int., p. 56, 1972.
- [10] Kobayashi, A. S., Maiden, D., Simon, B. and Iida, S., "Application of the Method of Finite Element Analysis to Two-Dimensional Problems in Fracture Mechanics", ASME Paper 69 WA-PVP-12, Nov. 1972.
- [11] Gallagher, R. H., "Survey and Evaluation of the Finite Element Method in Linear Fracture Mechanics Analysis", Proc. of the 1st Int. Conf. on

Structural Mechanics in Reactor Technology, 6, Part L, p. 637, Sept. 1972.

- [12] The Surface Crack: Physical Problems and Computational Solutions, ed. by J. L. Swedlow, ASME, 1972.
- [13] Rice, J. R. and Tracey, D. M., "Computational Fracture Mechanics", Numerical and Computer Methods in Structural Mechanics, ed. by S. J. Penses, Academic Press, p. 555, 1973.
- [14] Pian, T. H. H., "Crack Elements", Proc. of World Congress on Finite Element Methods in Structural Mechanics, Robinson and Associates, Dorset, England, 1, p. F.1, 1975.
- [15] Computational Fracture Mechanics, ed. by E. F. Rybicki and S. E. Benzley, ASME, 1975.
- [16] Nonlinear and Dynamic Fracture Mechanics, ed. by N. Perrone and S. Atluri, ASME AMD, Vol. 35, 1979.
- [17] Mackerle, J. and Fredriksson, B., "Fracture Mechanics", Structural Mechanics Software Series, III, ed. by N. Perrone and W. Pilkey, Univ. Press of Virginia, p. 205, 1980.
- [18] Kobayashi, A., "Fracture Mechanics", Structural Mechanics Software Series, IV, ed. by N. Perrone and W. Pilkey, Univ. Press of Virginia, p. 85, 1982.
- [19] Miyamoto, H., Shiratori, M. and Miyoshi, T., "Analysis of Stress and Strain Distribution at the crack Tip by Finite Element Method", Recent Advances in Matrix Methods of Structural Analysis and Design, ed. by J. T. Oden, Univ. of Alabama Press, 1971.
- [20] Blackburn, W. S. and Hellen, T. K., "Determination of Stress Intensity Factors for Battelle Benchmark Geometries", Central Electricity Generating Board, Berkeley Nuclear Laboratories Report RD/B/N4512, Feb. 1979.
- [21] Hellen, T. K. and Blackburn, W. S., "The calculation of stress intensity factors for combined tensile and shear loading", Int. J. of Fracture, 11, p. 605, 1975.
- [22] Raju, I. S. and Newman, J. C., "Three-Dimensional Finite-Element Analysis of Finite-Thickness Fracture Specimens", NASA TN D-8414, May 1977.
- [23] Raju, I. S. and Newman, J. C., "Stress-Intensity Factors for Internal and External Surface Cracks in Cylindrical Vessels", ASME J. of Pressure Vessel Technology, 104, p. 293, 1982.
- [24] Barsoum, R. S., "On the use of finite isoparametric finite elements in linear fracture mechanics", Int. J. Numerical Methods in Engng., 10, p. 25, 1976.

- [25] Yamada, Y., Hirakawa, T., Nishiguichi, I. and Okamura, H., "Nonlinear Analysis by Finite Element and a Microcomputer System Development", Proc. of Int. Conf. on Computer Application in Civil Engrg., Univ. of Roorkee, India, 1979.
- [26] Ingraffea, A. R. and Manu, C., "Stress-Intensity Factor Computation in Three Dimensions with Quarter-Point Elements", to be published in Int. J. for Numerical Methods in Engineering,
- [27] Green, A. E. and Sneddon, I. N., "The Distribution of Stress in the Neighborhood of a Flat Elliptical Crack in an Elastic Solid", Proc. of the Cambridge Philosophical Soc., 46, p. 159, 1950.
- [28] Bathe, K. J., Wilson, E. L. and Peterson, F. E., "SAP IV. Structural Analysis Program for Static and Dynamic Response of Linear Systems", Report No. EERC73-11, Earthquake Engrg. Res. Ctr., Univ. of Cal. at Berkeley, June 1973 revised April 1974.
- [29] Tong, P., Pian, T. H. H. and Lasry, S., "A Hybrid Finite-Element Approach to Crack Problems with Singularity", Int. J. of Fracture, 7, p. 297, 1975.
- [30] Pian, T.H.H., Tong, P. and Luk, C. H., "Elastic Crack Analysis by a Finite Element Method", Proc. of 3rd Conf. on Matrix Methods in Structural Mechanics, Wright-Patterson Air Force Base AFFDL TR-71-160, p. 661, 1971.
- [31] Tracey, D. M. and Cook, T. S., "Analysis of Power Type Singularities Using Finite Elements", Int. J. of Numerical Methods in Engrg., 11, p. 1225, 1977.
- [32] Pian, T. H. H. and Moriya, K., "Three-Dimensional Fracture Analysis by Assumed Stress Hybrid Elements", Numerical Methods in Fracture Mechanics, Proc. of 1st Int. Conf., ed. by A. R. Luxmoore and D. R. J. Owen, Univ. College Swansea, p. 364, 1977.
- [33] Smith, F. W. and Alavi, M. J., "Stress Intensity Factors for a Penny-Shaped Crack in Half Space", J. of Engrg. Fracture Mechanics, 3, p. 241, 1971.
- [34] Atluri, S. N. and Kathiresan, K., "Stress Analysis of Typical Flaws in Aerospace Structural Components Using Three-Dimensional Hybrid Displacement Finite Element Method", AIAA Paper 78-513, Proc. of AIAA-ASME 19th SDM Conf., p. 340, 1978.
- [35] Kanninen, M. F., Rybicki, E.F., Stonesifer, R. B., Broek, D., Rosenfield, A. R., Marschall, C. W. and Hahn, G. T., "Elastic-Plastic Fracture Mechanics for Two-dimensional Stable Crack Growth and Instability Problems", Elastic-Plastic Fracture, ed. by J. D. Landes, J. A. Begley and G. A. Clarke, ASTM STP 668, p. 121, 1979.
- [36] McMeeking, R. M. and Parks, D. M., "On Criteria for J-Dominance of Crack-Tip Fields in Large-Scale Yielding", Elastic-Plastic Fracture, ed. by J. D. Landes, J. A. Begley and G. A. Clarke, ASTM STP 668, p. 175,

1979.

- [37] Hutchinson, J. W., "Singular Behavior at the End of a Tensile Crack in a Hardening Material", J. of Mechanics and Physics of Solids, 16, p. 13, 1968.
- [38] Rice, J. R. and Rosengren, G. F., "Plane Strain Deformation Near a Crack Tip in a Power-Law Hardening Material", J. of Mechanics and Physics of Solids, 16, p. 1, 1968.
- [39] Rice, J. R., "A Path Independent Integral and the Approximate Analysis of Strain Concentration by Notches and Cracks", J. of Applied Mechanics, Trans. of ASME, 90, Series E, p. 379, 1968.
- [40] Hilton, P. D., "Elastic-Plastic Analysis for Cracked Members", ASME J. of Pressure Vessel Technology, 89, p. 47, 1976.
- [41] Shih, C. F., "Small-Scale Yielding Analysis of Mixed Mode Plane-Strain Crack Problems", Fracture Analysis, ASTM STP 560, p. 187, August 1974.
- [42] Atluri, S. N., Nakagaki, M. and Kathiresan, K., "Hybrid-finite element analysis of Some Nonlinear and 3-dimensional Problems of Engineering Fracture Mechanics", Computers and Structures, 12, p.511, 1980.
- [43] Yagawa, G., Aizawa, T. and Ando, Y., "Crack Analysis of Power Hardening Materials Using a Penalty Function and Superposition Method", Fracture Mechanics, 12th Symposium, ed. by P. C. Paris, ASTM STP 700, p. 439, 1980.
- [44] Barsoum, R., "Triangular Quarter-Point Elements as Elastic and Perfectly-Plastic Crack Tip Elements", Int. J. for Numerical Methods in Engineering, 11, p. 85, 1977.
- [45] Shih, C. F., deLorenzi, H. G., and Andrews, W. R., "Studies on Crack Initiation and Stable Crack Growth", Elastic-Plastic Fracture, ed. by J. D. Landes, J. A. Begley and G. A. Clarke, ASTM STP 668, p. 65, 1979.
- [46] Benzley, S., "Nonlinear Calculations With a Quadratic Quarter-point Crack Tip Element", Int. J. of Fracture, 12, p. 477, 1976.
- [47] deLorenzi, H. G., "Elastic-Plastic Analysis of the Maximum Postulated Flaw in the Beltline Region of a Reactor", ASME J. of Pressure Vessel Technology, 104, p. 278, 1982.
- [48] Kobayashi, A. S., "Dynamic Fracture Analysis by Dynamic Finite Element Method - Generation and Propagation Analyses", Nonlinear and Dynamic Fracture Mechanics, ed. by N. Perrone and S. N. Atluri, ASME AMD - Vol. 35, p.19, 1979.
- [49] Hodulak, L., Kobayashi, A. S. and Emery, A.F., "A Critical Examination of a Numerical Fracture Dynamic Code", Fracture Mechanics, 12th Conf., ASTM STP 700, p. 174, 1980.

- [50] Jung, J., Ahmad, J., Kanninen, M. F. and Popelar, C. H. "Finite Element Analysis of Dynamic Crack Propagation", presented at Failure Prevention and Reliability Conf., Hartford, CO, Sept. 20-23, 1981.
- [51] Keegstra, P. N. R., Head, J. L., and Turner, C. E., "A Transient Finite Element Analysis of Unstable Crack Propagation in Some 2-Dimensional Geometries", Proc. of 4th Int. Conf. on Fracture, Univ. of Waterloo Press, 3, p. 515, 1977.
- [52] Malluck, J. F. and King, W. W., "Fast Fracture Simulated by a Finite Element Analysis Which Accounts for Crack Tip Energy Dissipation", Proc. of 4th Int. Conf. on Fracture, Univ. of Waterloo Press, 3, p. 648, 1977.
- [53] Rydholm, G., Fredricksson, B. and Nilsson, F., "Numerical Investigation of Rapid Crack Propagation", Proc. of 4th Int. Conf. on Fracture, 3, p. 660, 1977.
- [54] Kobayashi, A. S., Seo, K., Jou, J. Y. and Urabe, Y., "A Dynamic Analysis of Modified Compact-tension Specimens Using Homalite-100 and Polycarbonate Plates", Experimental Mechanics, 20, p. 73, 1980.
- [55] Yagawa, G., Sakai, Y. and Ando, Y., "Analysis of a Rapidly Propagating Crack Using Finite Elements", Fast Fracture and Crack Arrest, ed. by G. T. Hahn and M. F. Kanninen, ASTM STP 627, p. 9, 1977.
- [56] Anderson, J. M. and King, W. W., "Singularity-Element Simulation of Crack Propagation", Fast Fracture and Crack Arrest, ed. by G. T. Hahn and M. F. Kanninen, ASTM STP 627, p. 123, 1977.
- [57] Aoki, S., Kishimoto, K. Kondo, H. and Sakata, M., "Elastodynamic Analysis Crack by Finite Element Method using Singular Element", Int. J. of Fracture, 14, p. 59, 1978.
- [58] Atluri, S. N., Nishioka, T. and Nakagaki, M., "Numerical Modeling of Dynamic and Nonlinear Crack Propagation in Finite Bodies", Nonlinear and Dynamic Fracture Mechanics, ed. by N. Perrone and S. Atluri, ASME AMD - Vol. 35, p. 37, 1979.
- [59] Nishioka, T. and Atluri, S. N., "Numerical Modeling of Dynamic Crack Propagation in Finite Bodies by Moving Singular Elements: Part I - Formulation, Part II - Results", ASME J. of Applied Mechanics, 102, p. 570 and p. 577, 1980.
- [60] Gunther, C. K., Hossaple, K. A. and Kobayashi, A. S., "Finite Element Analysis of Cracking Bodies", AIAA J., 19, p. 789, 1981.
- [61] Broberg, K. B., "The Propagation of a Brittle Crack", Arkiv For Fysik, 18, 1960.
- [62] Wilkins, M. L., Blum, R. E., Cronshagen, E. and Grantham, P., "A Method for Computer Simulation of Problems in Solid Mechanics and Gas Dynamics in Three Dimensions and Time", Lawrence Livermore Lab. Rept. UCRL-51524, 1974.

- [63] Chen, Y. M. and Wilkins, M. L., "Fracture Analysis With a Three-Dimensional Time-Dependent Computer Program", Lawrence Livermore Lab. Rept. UCRL-75703, 1974.
- [64] Shmueli, M. and Alterman, Z. S., "A Three Dimensional Numerical Analysis of Stress Distribution in the Vicinity of a Crack Tip", Israel J. of Technology, 9, p. 523, 1971.
- [65] Baker, B. R., "Dynamic Stresses created by a Moving Crack", J. of Applied Mechanics, Trans. of ASME, 29, p. 449, 1962.
- [66] Wilkins, M. L., "Fracture Studies With Two- and Three-Dimensional Computer Simulation Programs", Fracture Mechanics and Technology, II, ed. by G. C. Sih and C. L. Chow, Sijthoff and Noordhoff Int. Pub., p. 965, 1977.
- [67] Wilkins, M. L. and Streit, R. D., "Computer Simulation of Ductile Fracture", Nonlinear and Dynamic Fracture Mechanics, ed. by N. Perrone and S. N. Atluri, ASME AMD - Vol. 35, p. 67, 1979.
- [68] Norris, D. E., Reaugh, J. E., Moran, b. and Quinones, D. F., "Computer Model for Ductile Fracture: Applications to the Charpy V-Notch Test", Electric Power Research Institute, EPRI NP-961, 1979.
- [69] McClintock, F. A., "Plasticity Aspects of Fracture", Fracture, A Treatise, III, ed. by H. Liebowitz, Academic Press, p.47, 1975.
- [70] Hanson. M. E. and Sanford, A. R., "A Two-Dimensional Source Function for a Dynamic Brittle Bilateral Tensile Crack", Bulletin of Seismological ociety of America, 60, p. 1209, 1970.
- [71] Stoeckl, H. and Auer, F., "Dynamic behavior of a tensile crack: Finite difference simulation of fracture experiments", Int. J. of Fracture, 12, p. 345, 1976.
- [72] Popelar, C. H., Gehlen, P. C. and Kanninen, M. F., " Dynamic Crack Propagation in Precracked Cykindrical Vessels Subjected to Shock Loading", ASME J. of Pressure Vessel Technology, 103, p. 155, 1981.
- [73] Shmueli, M. and Perl, M, "A Semi-moving Grid Based Finite Difference Scheme (The SMF2D Code) for Proper Simulation of Crack Propagation", Int. J. of Fracture, 14, p. 205, 1978.
- [74] Emery, A. F., Love, W. J. and Kobayashi, A. S., "Fracture In Straight Pipes Under Large Deflection Condition, Part I - Structural Deformation and Part II - Pipe Pressure", ASME J. of Pressure Vessel Technology, 99, p. 122, 1977.
- [75] Emery, A. F., W. J. Love and Kobayashi, A. S., "Dynamic Propagation of Circumferential Cracks in Two Pipes with Large-scale Yielding", ASME J. of Pressure Vessel Technology, 102, p.28, 1980.
- [76] Rizzo, F. J., "An Integral Equation Approach to Boundary Value Problems of Classical Elastostatics", Quart. of Appl. Mech., 25, p. 83, 1967.

- [77] Cruse, T. A. and Van Buren, W., "Three-dimensional Elastic Stress Analysis of a Fracture Specimen With an Edge Crack", Int. J. of Fracture Mechanics, 7, p.1, 1971.
- [78] Cruse, T. A., "Boundary-Integral Equation Fracture Mechanics Analysis", Boundary-Integral Equation Method: Computational Applications in Applied Mechanics, ed. by T. A. Cruse and F. J. Rizzo, ASME AMD - Vol. 11, p. 31, 1975.
- [79] Danson, D. J., "A Boundary Element Formulation of Problems in Linear Isotropic Elasticity with Body Forces", Boundary Element Methods, Proc. of 3rd Int. Seminar, ed. by C. A. Brebbia, Springer-Verlag, p. 105, 1981.
- [80] Telles, J. C. F. and Brebbia, C. A., "New Developments in Elastoplastic Analysis", Boundary Element Methods, Proc. of 3rd Int. Seminar, ed. by C. A. Brebbia, Springer-Verlag, p. 350, 1981.
- [81] Cruse, T. A., "Two- and Three-Dimensional Problems of Fracture Mechanics", Developments in Boundary Element Methods - 1, ed. by P. K. Banerjee and R. Butterfield, Applied Science Publishers, p. 97, 1980.
- [82] Cruse, T. A., "Two-dimensional BIE Fracture Mechanics Analysis", Applied Math. Modelling, 2, p.287, 1978.
- [83] Synder, M. D and Cruse, T. A., "Boundary-Integral Analysis of Cracked Anisotropic Plates", Int'l. J. of Fracture, 11, p.359, 1975.
- [84] Blandford, G. E., Ingraffea, A. R. and Liggett, J. A. "Two-Dimensional Stress Intensity Factor Computations Using the Boundary Element Method, Int. J. for Numerical Methods in Engrg., 17, p. 387, 1981.
- [85] Cruse, T. A., "Numerical Evaluation of Elastic Stress Intensity Factors by The Boundary-Integral Equation Method", The Surface Crack: Physical and Computational Solutions, ed. by J. L. Swedlow, ASME , p. 153, 1972.
- [86] Atkinson, C., Xanthis, L. S. and Bernal, M. J. M., "Boundary Integral Equation Crack-Tip Analysis and Applications to Elastic Media with Spatially Varying Elastic Properties", Computer Methods in Applied Mechanics and Engrg., 29, p. 35, 1981.
- [87] Knowles, J. K. and Sternberg, E., "On a Class of Conservation Laws in Linearized and Finite Elastostatics", Arch. of Rational Mechanics and Analysis, 44, p. 187, 1972.
- [88] Cruse, T. A. and Meyers, G. J., "Three Dimensional Fracture Mechanics Analysis", J. of Structural Div., ASCE, 103 (ST2), p. 309, 1977.
- [89] Lachat, J. C. and Watson, J. O., "Effective Numerical Treatment of Boundary Integral Equations: A Formulation for Three-Dimensional Elastostatics", Int. J. for Numerical Methods in Engrg., 10, p. 991, 1976.
- [90] Helliot, J., Labbens, R. and Pellissier-Tanon, A., "Benchmark Problem

No. 1 - Semi-Elliptical Surface Crack - Results of Computation", Int'l. J. of Fracture, 15, p. R197, 1979.

- [91] Hellot, R., Labbens, R. and Pellissier-Tanon, A., "Semi-Elliptical Cracks in a Cylinder Subjected to Stress Gradients", Fracture Mechanics, ed. by C. W. Smith, ASTM STP 677, p. 341, 1979.
- [92] Cruse, T. A., Meyers, G. J. and Wilson, R. B., "Fatigue Growth of Surface Cracks", Flaw Growth and Fracture, ed. by J. M. Barsom, ASTM STP 631, p. 174, 1977.
- [93] Smith, F. W., Emery, A. F. and Kobayashi, A. S., "Stress Intensity Factors for SEMI-Circular Cracks, Part 2 - Semi-Infinite Solid, J. of Applied Mechanics, Trans. of ASME, 89, p. 953, 1967.
- [94] Shah, R. C. and Kobayashi, A. S., "Stress Intensity Factors for an Elliptical Crack Approaching the Surface of Semi-Infinite Solid", Int. J. of Fracture, 9, p. 133, 1973.
- [95] Smith, F. W. and Sorensen, D. R., "The Elliptical Crack Subjected to Nonuniform Shear Loading", J. of Applied Mechanics, Trans. of ASME, 94, p. 502, 1974.
- [96] Browning, W. M. and Smith, F. W., "An Analysis for Complex Three-Dimensional Crack Problems", Proc. of the 8th Southeastern Conf. on Theoretical and Applied Mechanics, Blacksburg, 1976.
- [97] Kullgren, T. E., Smith, F. W. and Ganong, G. P., "Quarter Elliptical Crack Elliptical Cracks Emanating from Holes in Plates", ASME J. of Engrg. Materials and Technology, 100, p. 144, 1978.
- [98] Grandt, A. F., "Crack Face Pressure Loading of Semi-elliptical Cracks Located Along the Bore of a Hole", Engrg. Fracture Mechanics, 14, p. 843, 1981.
- [99] Barrachin, B., Bhandari, S., Lahouratate, M., Sartha, M. H. and Kobayashi, A. S., "Stress Intensity Factors for Complex Cracked Structures under Arbitrary Loading", Proc. of 4th Int. Conf. on Pressure Vessel Technology, C26/80, p. 149, 1980.
- [100] Vijayakumar, K. and Atluri, S. N., "An Embedded Elliptical Flaw in an Infinite Solid Subject to Arbitrary Crack-Face Traction, ASME J. of Applied Mechanics, 103, p. 88, 1981.
- [101] Nishioka, T. and Atluri, S. M., "Analytical Solution for Embedded Elliptical Crack and Finite Element Alternating Method for Elliptical Surface Cracks, Subjected to Arbitrary Loadings", Engrg. Fracture Mechanics, p. 247, 1983.
- [102] Nishioka, T. and Atluri, S. N., "Analysis of Surface Flaw in Pressure Vessels by a New 3-Dimensional Alternating Method", ASME J. of Pressure Vessel Technology, 104, p. 299, 1982.
- [103] Atluri, S. N. and Kathiresan, K., "3-D Analysis of Surface Flaws in

Thick-Walled Reactor Pressure-Vessels Using Displacement-Hybrid Finite Element Method", Nuclear Engrg. and Design, 51, p. 163, 1980.

- [104] Miyazaki, N., Watanabe, T. and Yagawa, G., "Calculation of Stress Intensity Factors of Surface Cracks in Complex Structures: Application of Efficient Computer Program EPSA-J1", Trans. of the 6th Int. Conf. on Structural Mechanics in Reactor Technology, G 10/1, Paris, 1981.
- [105] Wilson, W. K., "A Comparison of Finite Element Solutions for an Elastic-Plastic Crack Problem", Int. J. of Fracture, 14, p. R95, 1978.
- [106] "A Critical Evaluation of Numerical Solutions to the 'Benchmark' Surface Flaw Problem", ed. by J. J. McGowan, Soc. for Exp. Stress Analysis, 1980.
- [107] Kanninen, M. F., Gehlen, P. C., Barnes, C. R., Hoagland, R. C. and Hahn, G. T., "Dynamic Crack Propagation Under Impact Loading", Nonlinear and Dynamic Fracture Mechanics, ed. by N. Perrone and S. N. Atluri, ASME AMD, Vol. 35, p. 85, 1979.

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER UWA/DME/TR-83/45	2. GOVT ACCESSION NO. ADA125048	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) Numerical Analysis in Fracture Mechanics		5. TYPE OF REPORT & PERIOD COVERED Technical Report
7. AUTHOR(s) A. S. Kobayashi		6. PERFORMING ORG. REPORT NUMBER UWA/DME/TR-82/44
9. PERFORMING ORGANIZATION NAME AND ADDRESS Dept. of Mechanical Engineering FU-10 University of Washington Seattle, WA 98195		8. CONTRACT OR GRANT NUMBER(s) N00014-76-C-0060
11. CONTROLLING OFFICE NAME AND ADDRESS Office of Naval Research Arlington, VA 22217		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS NR 064-478
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)		12. REPORT DATE January 20, 1983
		13. NUMBER OF PAGES 31
		15. SECURITY CLASS. (of this report) unclassified
		15a. DECLASSIFICATION/DOWNGRADING SCHEDULE
16. DISTRIBUTION STATEMENT (of this Report) Unlimited		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		
18. SUPPLEMENTARY NOTES		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) static fracture, dynamic fracture, linear elastic fracture mechanics, boundary element method, alternating technique, stress intensity factors, finite difference method, non-linear fracture mechanics, finite element method		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) Recent developments in four numerical techniques in structural mechanics, which are used to extract fracture parameters for linear elastic, nonlinear and dynamic fracture mechanics, are reviewed. Primary emphasis is placed on the finite element methods for determining two- and three-dimensional (2-D and 3-D) stress intensity factors in linear elastic fracture mechanics. Crack opening displacements (COD) and J-integrals for 2-D, stable crack growth, -continued next page-		

DD FORM 1 JAN 73 1473

EDITION OF 1 NOV 65 IS OBSOLETE
S/N 0102-014-6601UNCLASSIFIED
SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE(When Data Entered)

-block #20, Abstract, continued-

ductile fracture, and use of elastic finite element method in its generation mode for obtaining dynamic elastic fracture parameters are discussed. The second topic is the finite difference method for analyzing the elasto-dynamic and elastic-plastic dynamic states in fracturing 2- and 3-D problems. The use of a super finite difference code to study dynamic ductile fracture using the void growth and coalescence model is discussed. The third topic is the boundary element method which has evolved into a practical tool for numerical analysis in 3-D linear elastic fracture mechanics. The final topic is the updated alternating technique, which was merged with a 3-D finite element code and together with a break-through in its analytical formulation, has become a cost-effective numerical technique in solving part and complete elliptical crack problems in 3-D linear elastic fracture mechanics. Comparisons between the J-integral of a 3-point bend specimen, the stress intensity factor for a surface flaw specimen and the dynamic stress intensity factor of a fracturing dynamic tear test specimen obtained by various investigators are made.

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE(When Data Entered)

**Part 1 - Government
Administrative and Liaison Activities**

Office of Naval Research
Department of the Navy
Arlington, VA 22217
Attn: Code 474 (2)
471
200

Director
Office of Naval Research
Branch Office
666 Summer Street
Boston, MA 02210

Director
Office of Naval Research
Branch Office
536 South Clark Street
Chicago, IL 60605

Director
Office of Naval Research
Branch Office
1030 East Green Street
Pasadena, CA 91106

Naval Research Laboratory (6)
Code 2627
Washington, D.C. 20375

Defense Documentation Center (12)
Cameron Station
Alexandria, Virginia 22314

Navy

Undersea Explosion Research Division
Naval Ship Research and Development
Center
Norfolk Naval Shipyard
Portsmouth, VA 23709
Attn: Dr. E. Palmer, Code 177

Navy (Con't.)

Naval Research Laboratory
Washington, D.C. 20375
Attn: Code 8400
8410
8430
8440
8300
8390
8380

David W. Taylor Naval Ship Research
and Development Center
Annapolis, MD 21402
Attn: Code 2740
28
281

Naval Weapons Center
China Lake, CA 93555
Attn: Code 4062
4520

Commanding Officer
Naval Civil Engineering Laboratory
Code L31
Port Hueneme, CA 93041

Naval Surface Weapons Center
White Oak
Silver Spring, MD 20910
Attn: Code R-10
G-402
K-82

Technical Director
Naval Ocean Systems Center
San Diego, CA 92152

Navy Underwater Sound
Reference Division
Naval Research Laboratory
P.O. Box 8337
Orlando, FL 32806

Navy (Con't.)

Chief of Naval Operations
Department of the Navy
Washington, D.C. 20350
Attn: Code 07-008
Strategic Systems Project Office
Department of the Navy
Washington, D.C. 20376
Attn: NSP-300

Naval Air Systems Command
Department of the Navy
Washington, D.C. 20361
Attn: Code 5302 (Aerospace and Structures)
604 (Technical Library)
320B (Structures)

Naval Air Development Center
Harrisburg, PA 17174
Attn: Aerospace Mechanics
Code 606

U.S. Naval Academy
Engineering Department
Annapolis, MD 21402

Naval Facilities Engineering Command
200 Stovall Street
Alexandria, VA 22332
Attn: Code 03 (Research & Development)
04B
045
14114 (Technical Library)

Naval Sea Systems Command
Department of the Navy
Washington, D.C. 20362
Attn: Code 05H
312
322
323
05H
32H

Navy (Con't.)

Commander and Director
David W. Taylor Naval Ship
Research and Development Center
Bethesda, MD 20084
Attn: Code 042

17
172
173
174
1800
1844
012.2
1900
1901
1945
1960
1962

Naval Underwater Systems Center
Newport, RI 02840
Attn: Dr. R. Trainor

Naval Surface Weapons Center
Dahlgren Laboratory
Dahlgren, VA 22448
Attn: Code 004
G20

Technical Director
Navy Island Naval Shipyard
Vallejo, CA 94592

U.S. Naval Postgraduate School
Library
Code 0384
Monterey, CA 93940

Webb Institute of Naval Architecture
Attn: Librarian
Crescent Beach Road, Glen Cove
Long Island, NY 11542

Army

Commanding Officer (2)
U.S. Army Research Office
P.O. Box 12211
Research Triangle Park, NC 27709
Attn: Mr. J. J. Murray, CRD-AA-1P

Army (Con't.)

Watervliet Arsenal
MAGOS Research Center
Watervliet, NY 12189
Attn: Director of Research

U.S. Army Materials and Mechanics
Research Center
Watertown, MA 02172
Attn: Dr. R. Shan, DR10M-T

U.S. Army Missile Research and
Development Center
Redstone Scientific Information
Center
Chief, Document Section
Redstone Arsenal, AL 35809

Army Research and Development
Center
Fort Belvoir, VA 22040

NASA

National Aeronautics and Space
Administration
Structures Research Division
Langley Research Center
Langley Station
Hampton, VA 23365

National Aeronautics and Space
Administration
Associate Administrator for Advanced
Washington, D.C. 20546

Air Force

Wright-Patterson Air Force Base
Dayton, OH 45433
Attn: AFPHL (PB)

(PB)
(PB)
(PB)
AFPHL (HBN)

Air Force (Con't.)

Chief Applied Mechanics Group
U.S. Air Force Institute of Technology
Wright-Patterson Air Force Base
Dayton, OH 45433

Chief, Civil Engineering Branch
WLRC, Research Division
Air Force Weapons Laboratory
Kirtland Air Force Base
Albuquerque, NM 87117

Air Force Office of Scientific Research
Bolling Air Force Base
Washington, D.C. 20332
Attn: Mechanics Division

Department of the Air Force
Air University Library
Maxwell Air Force Base
Montgomery, AL 36112

Other Government Activities

Commandant
Chief, Testing and Development Division
U.S. Coast Guard
1300 E Street, NW
Washington, D.C. 20226

Technical Director
Marine Corps Development
and Education Command
Quantico, VA 22134

Director Defense Research
and Engineering
Technical Library
Room 3C128
The Pentagon
Washington, D.C. 20301

Other Government Activities (Con't.)

Dr. M. Guss
National Science Foundation
Environmental Research Division
Washington, D.C. 20550

Library of Congress
Science and Technology Division
Washington, D.C. 20540

Director
Defense Nuclear Agency
Washington, D.C. 20305
Attn: SPSS

Mr. Jerome Perah
Staff Specialist for Materials
and Structures
OUSD&E, The Pentagon
Room 3D1089
Washington, D.C. 20301

Chief, Airframe and Equipment Branch
FS-120
Office of Flight Standards
Federal Aviation Agency
Washington, D.C. 20533

National Academy of Sciences
National Research Council
Ship Hull Research Committee
2101 Constitution Avenue
Washington, D.C. 20418
Attn: Mr. A. R. Lytle

National Science Foundation
Engineering Mechanics Section
Division of Engineering
Washington, D.C. 20550

Picatinny Arsenal
Plastics Technical Evaluation Center
Attn: Technical Information Section
Dover, NJ 07810

Maritime Administration
Office of Maritime Technology
14th and Constitution Ave., NW
Washington, D.C. 20230

**PART 2 - Contractors and other Technical
Collaborators****Universities**

Dr. J. Tinsley Oden
University of Texas at Austin
345 Engineering Science Building
Austin, TX 78712

Professor Julius Miklowitz
California Institute of Technology
Division of Engineering
and Applied Sciences
Pasadena, CA 91109

Dr. Harold Liebowitz, Dean
School of Engineering and
Applied Science
George Washington University
Washington, D.C. 20052

Professor Eli Sternberg
California Institute of Technology
Division of Engineering and
Applied Sciences
Pasadena, CA 91109

Professor Paul M. Naghd
University of California
Department of Mechanical Engineering
Berkeley, CA 94720

Professor A. J. Durelli
Oakland University
School of Engineering
Rochester, MD 48063

Professor F. L. DiMaggio
Columbia University
Department of Civil Engineering
New York, NY 10027

Professor Norman Jones
The University of Liverpool
Department of Mechanical Engineering
P.O. Box 147
Brownlow Hill
Liverpool L69 3BE
England

Professor E. J. Stodrayk
Pennsylvania State University
Applied Research Laboratory
Department of Physics
State College, PA 16801

Universities (Con't.)

Professor J. E. Egan
Polytechnic Institute of New York
Department of Mechanical and
Aerospace Engineering
333 Jay Street
Brooklyn, NY 11201

Prof. E. A. Schapery
Texas A&M University
Department of Civil Engineering
College Station, TX 77843

Professor Walter D. Pilkey
University of Virginia
Research Laboratories for the
Engineering Sciences and
Applied Sciences
Charlottesville, VA 22901

Professor K. D. Willmert
Clarkson College of Technology
Department of Mechanical Engineering
Potsdam, NY 13676

Dr. Walter E. Baizer
Texas A&M University
Aerospace Engineering Department
College Station, TX 77843

Dr. Hussein A. Kameel
University of Arizona
Department of Aerospace and
Mechanical Engineering
Tucson, AZ 85721

Dr. S. J. Fenves
Carnegie-Mellon University
Department of Civil Engineering
Scholar Park
Pittsburgh, PA 15213

Dr. Ronald L. Huston
Department of Engineering Analysis
University of Cincinnati
Cincinnati, OH 45221

Universities (Con't.)

Professor G. C. M. Sakh
Lehigh University
Institute of Fracture and
Solid Mechanics
Bethlehem, PA 18015

Professor Albert S. Kobayashi
University of Washington
Department of Mechanical Engineering
Seattle, WA 98105

Professor Daniel Frederick
Virginia Polytechnic Institute and
State University
Department of Engineering Mechanics
Blacksburg, VA 24061

Professor A. C. Eringen
Princeton University
Department of Aerospace and
Mechanical Sciences
Princeton, NJ 08540

Professor E. W. Lee
Stanford University
Division of Engineering Mechanics
Stanford, CA 94305

Professor Albert I. King
Wayne State University
Biomechanics Research Center
Detroit, MI 48202

Dr. V. E. Hodgson
Wayne State University
School of Medicine
Detroit, MI 48202

Dean R. A.oley
Northwestern University
Department of Civil Engineering
Evanston, IL 60201

Universities (Con't.)

Professor P. G. Hodge, Jr.
University of Minnesota
Department of Aerospace Engineering
and Mechanics
Minneapolis, MN 55455

Dr. D. C. Drucker
University of Illinois
Dean of Engineering
Urbana, IL 61801

Professor M. J. Newman
University of Illinois
Department of Civil Engineering
Urbana, IL 61803

Professor E. Reissner
University of California, San Diego
Department of Applied Mechanics
La Jolla, CA 92037

Professor William A. Nash
University of Massachusetts
Department of Mechanics and
Aerospace Engineering
Amherst, MA 01002

Professor G. Herrmann
Stanford University
Department of Applied Mechanics
Stanford, CA 94305

Professor J. D. Achenbach
Northwestern University
Department of Civil Engineering
Evanston, IL 60201

Professor S. B. Dong
University of California
Department of Mechanics
Los Angeles, CA 90024

Professor Burt Paul
University of Pennsylvania
Towne School of Civil and
Mechanical Engineering
Philadelphia, PA 19104

Universities (Con't.)

Professor H. W. Liu
Syracuse University
Department of Chemical Engineering
and Metallurgy
Syracuse, NY 13210

Professor S. Rodner
Technion R&D Foundation
Haifa, Israel

Professor Warner Goldsmith
University of California
Department of Mechanical Engineering
Berkeley, CA 94720

Professor R. S. Rivlin
Lehigh University
Center for Application
of Mathematics
Bethlehem, PA 18015

Professor F. A. Coszarella
State University of New York at
Buffalo
Division of Interdisciplinary Studies
Karr Parker Engineering Building
Chemistry Road
Buffalo, NY 14214

Professor Joseph L. Rose
Drexel University
Department of Mechanical Engineering
and Mechanics
Philadelphia, PA 19104

Professor B. K. Donaldson
University of Maryland
Aerospace Engineering Department
College Park, MD 20742

Professor Joseph A. Clark
Catholic University of America
Department of Mechanical Engineering
Washington, D.C. 20064

Universities (Con't.)

Dr. Samuel B. Bittorf
University of California
School of Engineering
and Applied Science
Los Angeles, CA 90024

Professor Isaac Fried
Boston University
Department of Mathematics
Boston, MA 02215

Professor E. Krampl
Aeronautical Polytechnic Institute
Division of Engineering
Engineering Mechanics
Troy, NY 12181

Dr. Jack E. Vinson
University of Delaware
Department of Mechanical and Aerospace
Engineering and the Center for
Composite Materials
Newark, DE 19711

Dr. J. Duffy
Brown University
Division of Engineering
Providence, RI 02912

Dr. J. L. Dundas
Carnegie-Mellon University
Department of Mechanical Engineering
Pittsburgh, PA 15213

Dr. V. E. Varadan
Ohio State University Research Foundation
Department of Engineering Mechanics
Columbus, OH 43210

Dr. E. Machin
University of Pennsylvania
Department of Metallurgy and
Materials Science
College of Engineering and
Applied Science
Philadelphia, PA 19104

Universities (Con't.)

Dr. Jackson C. S. Yang
University of Maryland
Department of Mechanical Engineering
College Park, MD 20742

Professor T. Y. Chang
University of Akron
Department of Civil Engineering
Akron, OH 44325

Professor Charles W. Bert
University of Oklahoma
School of Aerospace, Mechanical,
and Nuclear Engineering
Norman, OK 73019

Professor Satyn N. Atluri
Georgia Institute of Technology
School of Engineering and
Mechanics
Atlanta, GA 30332

Professor Graham F. Carey
University of Texas at Austin
Department of Aerospace Engineering
and Engineering Mechanics
Austin, TX 78712

Dr. S. S. Wang
University of Illinois
Department of Theoretical and
Applied Mechanics
Urbana, IL 61801

Industry and Research Institutes

Dr. Norman Hobbs
Kaman Aerospace
Division of Kaman
Science Corporation
Burlington, MA 01803

Argonne National Laboratory
Library Services Department
9700 South Cass Avenue
Argonne, IL 60440

Industry and Research Institutes (Con't.)

Dr. H. C. Junger
Cambridge Acoustical Associates
34 Rindge Avenue Extension
Cambridge, MA 02140

Dr. V. Godino
General Dynamics Corporation
Electric Boat Division
Groton, CT 06340

Dr. J. E. Greenespan
J. G. Engineering Research Associates
3031 Menlo Drive
Baltimore, MD 21215

Navport News Shipbuilding and
Dry Dock Company
Library
Navport News, VA 23601

Dr. W. F. Bozich
McDonnell Douglas Corporation
5301 Bolan Avenue
Huntington Beach, CA 92647

Dr. H. N. Abramson
Southwest Research Institute
8500 Culebra Road
San Antonio, TX 78284

Dr. R. C. DeHart
Southwest Research Institute
8500 Culebra Road
San Antonio, TX 78284

Dr. M. L. Baron
Weidinger Associates
110 East 59th Street
New York, NY 10022

Dr. T. L. Geers
Lockheed Missiles and Space Company
3231 Hanover Street
Palo Alto, CA 94304

Mr. William Caywood
Applied Physics Laboratory
Johns Hopkins Road
Laurel, MD 20810

Industry and Research Institutes (Con't.)

Dr. Robert E. Dunham
Pacific Technology
P.O. Box 148
Del Mar, CA 92014

Dr. M. F. Kanninen
Battelle Columbus Laboratories
505 King Avenue
Columbus, OH 43201

Dr. A. A. Hochrein
Deedean Associates, Inc.
Springlake Research Road
15110 Frederick Road
Woodbine, MD 21797

Dr. James W. Jones
Swanson Service Corporation
P.O. Box 5415
Huntington Beach, CA 92646

Dr. Robert E. Nickell
Applied Science and Technology
3346 North Torrey Pines Court
Suite 220
La Jolla, CA 92037

Dr. Kevin Thomas
Westinghouse Electric Corp.
Advanced Reactors Division
P.O. Box 158
Madison, PA 15663

Dr. Bernard Shaffer
Polytechnic Institute of New York
Dept. of Mechanical and Aerospace
Engineering
333 Jay Street
Brooklyn, NY 11021