

MEMORANDUM REPORT ARLCB-MR-83036

**COLD ROTARY FORGING
OF A THIN-WALLED RIFLED TUBE**

BOAZ AVITZUR

OCTOBER 1983



**US ARMY ARMAMENT RESEARCH AND DEVELOPMENT CENTER
LARGE CALIBER WEAPON SYSTEMS LABORATORY
BENET WEAPONS LABORATORY
WATERVLIET N.Y. 12189**

APPROVED FOR PUBLIC RELEASE; DISTRIBUTION UNLIMITED

DTIC QUALITY INSPECTED 3

DISCLAIMER

The findings in this report are not to be construed as an official Department of the Army position unless so designated by other authorized documents.


The use of trade name(s) and/or manufacture(s) does not constitute an official indorsement or approval.

DISPOSITION

Destroy this report when it is no longer needed. Do not return it to the originator.

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER ARLCB-MR-83036	2. GOVT ACCESSION NO.	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) COLD ROTARY FORGING OF A THIN-WALLED RIFLED TUBE		5. TYPE OF REPORT & PERIOD COVERED Final
		6. PERFORMING ORG. REPORT NUMBER
7. AUTHOR(s) Boaz Avitzur		8. CONTRACT OR GRANT NUMBER(s)
9. PERFORMING ORGANIZATION NAME AND ADDRESS US Army Armament Research & Development Center Benet Weapons Laboratory, DRSMC-LCB-TL Watervliet, NY 12189		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS
11. CONTROLLING OFFICE NAME AND ADDRESS US Army Armament Research & Development Center Large Caliber Weapon Systems Laboratory Dover, NJ 07801		12. REPORT DATE October 1983
		13. NUMBER OF PAGES 9
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)		15. SECURITY CLASS. (of this report) UNCLASSIFIED
		15a. DECLASSIFICATION/DOWNGRADING SCHEDULE
16. DISTRIBUTION STATEMENT (of this Report) Approved for public release; distribution unlimited.		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		
18. SUPPLEMENTARY NOTES		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) Artillery Cold Working Forge (Presses) Forging (Radial) (Rotary) Gun Barrels Steel		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) In Technical Report WVT-TR-75054 on cold rotary forging of rifling into a thin-wall gun tube, it was stated that the yield strength of the forged material increased in the longitudinal direction, while a recoverable loss was observed in the tangential (hoop) direction. A recently obtained metallographic study of the same material suggests a potential improvement in fatigue life and/or fracture toughness of the material, attained in that earlier work but overlooked at the time.		

SECURITY CLASSIFICATION OF THIS PAGE(When Data Entered)



SECURITY CLASSIFICATION OF THIS PAGE(When Data Entered)

TABLE OF CONTENTS

	<u>Page</u>
INTRODUCTION	1
DISCUSSION	1
CONCLUSIONS	3
REFERENCES	4

LIST OF ILLUSTRATIONS

1(a). Broached Rifling in 105 mm Gun Tube Transverse (20X).	5
1(b). Broached Rifling in 105 mm Gun Tube Transverse (100X, 500X). Metallurgical Imperfection at the Root of the Land.	6
2. Forged Rifling in 105 mm Gun Tube Transverse (20X).	7
3. Forged Rifling in 105 mm Gun Tube Longitudinal (20X).	8

INTRODUCTION

Campione, Liuzzi, and Heiser, in Technical Report WVT-TR-75054¹ described a preliminary study of introducing rifling into a thin-wall gun tube while simultaneously rotary forging the outer surface. This was achieved through the use of a rifled mandrel at the inside of the tube during the forging operation. As a way of reducing manufacturing costs, they emphasized finish forming the internal rifled configuration, thereby eliminating the subsequent machining operation. The effect of this forging process on the mechanical properties and residual stresses of the material being used was also described.

DISCUSSION

Dimensionally the results showed a slight departure in the forged tube's I.D. (at the grooves as well as at the lands) as compared to the mandrel. This was anticipated and was justifiably attributed to material spring-back. The authors also encountered a departure in the forged tube's land width from that of the mandrel's groove, and likewise attributed it to material spring-back. Material spring-back is limited to $\epsilon = \sigma_e/E$, where $\sigma_e \equiv$ material's elastic limit and $E \equiv$ material's Modulus of Elasticity. In the case at hand, with material yield strength not exceeding 160,000 psi this would amount to a maximum spring-back of 0.53 percent, whereas the reported departure in land width varies between 5 percent and 10.6 percent. It is suggested here that

¹Alfred A. Campione, Leonard Liuzzi, and Francis A. Heiser, "Cold Rotary Forging," Watervliet Arsenal Technical Report WVT-TR-75059, Watervliet, NY, September 1975.

the reduced land width results from axial flow of the material through helical grooves during forging. The axial flow causes land width to narrow through deformation or wear on one side. This suggestion is supported by the roughly linear correlation between the amount of deformation reduction and percent loss in land width. Nevertheless, once the mechanism is known, we can conclude that with further work the stringent dimensional requirement can be achieved.

An increase in yield strength after forging was noticed in the axial direction. In the tangential (hoop) direction, Campione et al¹ reported reduction in yield strength after deformation. However, these losses in yield strength in the hoop direction were recovered after heat-treatment. They also reported that a closer examination of the rifling grooves revealed no longitudinal score marks, tears or gouges, which are commonly found in rifling grooves that are produced by conventional machining methods such as solid rifling broaches and individual rifling cutting. They presumed that the surface stress concentration may be reduced substantially. These surface stress concentrations are limited to an extremely thin layer at the surface. This investigator believes that of greater importance is the difference in texture structure at and below the surface. In the broached rifling the prebroaching texture structure, if any, is being cut through, with metallurgical irregularities sometimes being normal to the surface (see Figure 1). These are often nucleation sights for fatigue failure. Because in the

¹Alfred A. Campione, Leonard Liuzzi, and Francis A. Heiser, "Cold Rotary Forging," Watervliet Arsenal Technical Report WVT-TR-75059, Watervliet, NY, September 1975.


forged tube (Figure 2) the texture structure is parallel to the surface, it is less prone to fatigue failure nucleation. Tensile and impact tests were made on machined specimens where the surface texture referred to here was removed. Accordingly, a potential advantage thereof did not receive its deserved attention. However, it has been reported that the service life for the small caliber tubes was extended when they were rotary forged. Texturizing due to the rotary swage operation in the longitudinal direction, both at the land and under the groove, is shown in Figure 3.

CONCLUSIONS

One may conclude that plastically deforming the rifling while simultaneously rotary forging the tube is limited to thin-wall tubes and that its economical advantage over post-deformation broaching is in reducing the manufacturing cost. However, even if the tube's wall thickness is a limiting factor in incorporating the rifling with rotary forging, there are other methods for plastically deforming the rifling into the tube. These methods are not confined to thin-wall tubes. One should not overlook the benefits of improved fatigue life and/or fracture toughness, which may lead to longer service life, reduced tube weight, and/or increased propelling pressure with all of its consequences.


REFERENCES

1. Alfred A. Campione, Leondard Liuzzi, and Frances A. Heiser, "Cold Rotary Forging," Watervliet Arsenal Technical Report WVT-TR-75059, Watervliet, NY, September 1975.




**BROACHED RIFLING IN 105mm GUN TUBE
TRANSVERSE, 20 X**

FIGURE 1(a)




**BROACHED RIFLING IN 105mm GUN TUBE
TRANSVERSE, METALLURGICAL IMPERFECTION
AT THE ROOT OF THE LAND**

FIGURE 1(b)



FORGED RIFLING IN 105mm GUN TUBE
TRANSVERSE, 20 X

FIGURE 2



FORGED RIFLING
IN 105mm GUN TUBE
LONGITUDINAL, 20X



THROUGH GROOVE

THROUGH LAND

FIGURE 3

TECHNICAL REPORT INTERNAL DISTRIBUTION LIST

	<u>NO. OF COPIES</u>
CHIEF, DEVELOPMENT ENGINEERING BRANCH	
ATTN: DRSMC-LCB-D	1
-DP	1
-DR	1
-DS (SYSTEMS)	1
-DS (ICAS GROUP)	1
-DC	1
CHIEF, ENGINEERING SUPPORT BRANCH	
ATTN: DRSMC-LCB-S	1
-SE	1
CHIEF, RESEARCH BRANCH	
ATTN: DRSMC-LCB-R	2
-R (ELLEN FOGARTY)	1
-RA	1
-RM	1
-RP	1
-RT	1
TECHNICAL LIBRARY	5
ATTN: DRSMC-LCB-TL	
TECHNICAL PUBLICATIONS & EDITING UNIT	2
ATTN: DRSMC-LCB-TL	
DIRECTOR, OPERATIONS DIRECTORATE	1
DIRECTOR, PROCUREMENT DIRECTORATE	1
DIRECTOR, PRODUCT ASSURANCE DIRECTORATE	1

NOTE: PLEASE NOTIFY DIRECTOR, BENET WEAPONS LABORATORY, ATTN: DRSMC-LCB-TL,
OF ANY ADDRESS CHANGES.

TECHNICAL REPORT EXTERNAL DISTRIBUTION LIST

	<u>NO. OF COPIES</u>		<u>NO. OF COPIES</u>
ASST SEC OF THE ARMY RESEARCH & DEVELOPMENT ATTN: DEP FOR SCI & TECH THE PENTAGON WASHINGTON, D.C. 20315	1	COMMANDER US ARMY AMCCOM ATTN: DRSMC-LEP-L(R) ROCK ISLAND, IL 61299	1
COMMANDER DEFENSE TECHNICAL INFO CENTER ATTN: DTIC-DDA CAMERON STATION ALEXANDRIA, VA 22314	12	COMMANDER ROCK ISLAND ARSENAL ATTN: SMCRI-ENM (MAT SCI DIV) ROCK ISLAND, IL 61299	1
COMMANDER US ARMY MAT DEV & READ COMD ATTN: DRCDE-SG 5001 EISENHOWER AVE ALEXANDRIA, VA 22333	1	DIRECTOR US ARMY INDUSTRIAL BASE ENG ACTV ATTN: DRXIB-M ROCK ISLAND, IL 61299	1
COMMANDER ARMAMENT RES & DEV CTR US ARMY AMCCOM ATTN: DRSMC-LC(D) DRSMC-LCE(D) DRSMC-LCM(D) (BLDG 321) DRSMC-LCS(D) DRSMC-LCU(D) DRSMC-LCW(D) DRSMC-SCM-O (PLASTICS TECH EVAL CTR, BLDG. 351N) DRSMC-TSS(D) (STINFO) DOVER, NJ 07801	1 1 1 1 1 1 1 1 2	COMMANDER US ARMY TANK-AUTMV R&D COMD ATTN: TECH LIB - DRSTA-TSL WARREN, MI 48090 COMMANDER US ARMY TANK-AUTMV COMD ATTN: DRSTA-RC WARREN, MI 48090 COMMANDER US MILITARY ACADEMY ATTN: CHMN, MECH ENGR DEPT WEST POINT, NY 10996 US ARMY MISSILE COMD REDSTONE SCIENTIFIC INFO CTR ATTN: DOCUMENTS SECT, BLDG. 4484 REDSTONE ARSENAL, AL 35898	1 2
DIRECTOR BALLISTICS RESEARCH LABORATORY ARMAMENT RESEARCH & DEV CTR US ARMY AMCCOM ATTN: DRSMC-TSB-S (STINFO) ABERDEEN PROVING GROUND, MD 21005	1	COMMANDER US ARMY FGN SCIENCE & TECH CTR ATTN: DRXST-SD 220 7TH STREET, N.E. CHARLOTTESVILLE, VA 22901	1
MATERIEL SYSTEMS ANALYSIS ACTV ATTN: DRSXY-MP ABERDEEN PROVING GROUND, MD 21005	1		

NOTE: PLEASE NOTIFY COMMANDER, ARMAMENT RESEARCH AND DEVELOPMENT CENTER,
US ARMY AMCCOM, ATTN: BENET WEAPONS LABORATORY, DRSMC-LCB-TL,
WATERVLIET, NY 12189, OF ANY ADDRESS CHANGES.

TECHNICAL REPORT EXTERNAL DISTRIBUTION LIST (CONT'D)

	<u>NO. OF COPIES</u>		<u>NO. OF COPIES</u>
COMMANDER US ARMY MATERIALS & MECHANICS RESEARCH CENTER ATTN: TECH LIB - DRXMR-PL WATERTOWN, MA 01272	2	DIRECTOR US NAVAL RESEARCH LAB ATTN: DIR, MECH DIV CODE 26-27, (DOC LIB) WASHINGTON, D.C. 20375	1 1
COMMANDER US ARMY RESEARCH OFFICE ATTN: CHIEF, IPO P.O. BOX 12211 RESEARCH TRIANGLE PARK, NC 27709	1	COMMANDER AIR FORCE ARMAMENT LABORATORY ATTN: AFATL/DLJ AFATL/DLJG EGLIN AFB, FL 32542	1 1
COMMANDER US ARMY HARRY DIAMOND LAB ATTN: TECH LIB 2800 POWDER MILL ROAD ADELPHIA, MD 20783	1	METALS & CERAMICS INFO CTR BATTELLE COLUMBUS LAB 505 KING AVENUE COLUMBUS, OH 43201	1
COMMANDER NAVAL SURFACE WEAPONS CTR ATTN: TECHNICAL LIBRARY CODE X212 DAHLGREN, VA 22448	1		

NOTE: PLEASE NOTIFY COMMANDER, ARMAMENT RESEARCH AND DEVELOPMENT CENTER,
US ARMY AMCCOM, ATTN: BENET WEAPONS LABORATORY, DRSMC-LCB-TL,
WATERVLIET, NY 12189, OF ANY ADDRESS CHANGES.

READER EVALUATION

Please take a few minutes to complete the questionnaire below and return to us at the following address: Commander, Armament Research and Development Center, U.S. Army AMCCOM, ATTN: Technical Publications, DRSMC-LCB-TL, Watervliet, NY 12189.

1. Benet Weapons Lab. Report Number _____

2. Please evaluate this publication (check off one or more as applicable).

	Yes	No
Information Relevant	_____	_____
Information Technically Satisfactory	_____	_____
Format Easy to Use	_____	_____
Overall, Useful to My Work	_____	_____
Other Comments	_____	

3. Has the report helped you in your own areas of interest? (i.e. preventing duplication of effort in the same or related fields, savings of time, or money). _____

4. How is the report being used? (Source of ideas for new or improved designs. Latest information on current state of the art, etc.). _____

5. How do you think this type of report could be changed or revised to improve readability, usability? _____

6. Would you like to communicate directly with the author of the report regarding subject matter or topics not covered in the report? If so please fill in the following information.

Name: _____

Telephone Number: _____

Organization Address: _____