

AD-A145 860

INFRARED SPECTROSCOPY STUDY OF THE SP-250 EPOXY RESIN
SYSTEM(U) ARMY MATERIALS AND MECHANICS RESEARCH CENTER
WATERTOWN MA R E SACHER ET AL. JUL 84 AMRC-TR-84-29


1/1

UNCLASSIFIED

F/G 7/3

NL

							END						
							FORM						
							FILE						



MICROCOPY RESOLUTION TEST CHART
NATIONAL BUREAU OF STANDARDS-1963-A

12

AMMRC TR 84-29

AD

AD-A145 860

INFRARED SPECTROSCOPY STUDY OF THE SP-250 EPOXY RESIN SYSTEM

ROBERT E. SACHER and BERNARD R. LaLIBERTE
POLYMER RESEARCH DIVISION

July 1984

Approved for public release; distribution unlimited.

ARMY MATERIALS AND MECHANICS RESEARCH CENTER
Watertown, Massachusetts 02172-0001

DTIC
ELECTE
SEP 24 1984

B

DTIC FILE COPY

84 09 20 009

The findings in this report are not to be construed as an official Department of the Army position, unless so designated by other authorized documents.

Mention of any trade names or manufacturers in this report shall not be construed as advertising nor as an official indorsement or approval of such products or companies by the United States Government.

DISPOSITION INSTRUCTIONS

Destroy this report when it is no longer needed.
Do not return it to the originator.

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

DD FORM 1473 EDITION OF 1 NOV 68 IS OBSOLETE

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

Block No. 20

ABSTRACT

→ The various epoxides which are part of the SP-250 formulation (3M Company, St. Paul, Minnesota) were treated to three different curing procedures. In this study, the epoxides and the epoxy blends were individually cured with dicyandiamide (Dicy) and Monuron, respectively, and in combination (Dicy/Monuron). The acceleration of the Dicy-containing epoxy resin cure is linked to the formation of cyclic 2-oxazolidone. The characteristic nature of the carbonyl band of these cyclic derivatives prompted us to monitor the hardening process by infrared spectroscopy. The cure conversion was evaluated to be the highest for the EPON 828 + Dicy/Monuron and ECN 1273/ EPON 828 + Dicy/Monuron systems. The epoxide + accelerator reaction affording 2-oxazolidone was found to be the greatest in the active diluent + Monuron system. Regarding neat EPON 828, the presence of Dicy significantly enhanced the formation of 2-oxazolidone.

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

CONTENTS

	Page
INTRODUCTION.	1
EXPERIMENTAL.	1
DISCUSSION AND RESULTS.	1
CONCLUSION.	4
APPENDIX.	5

S **DTIC**
ELECTE
SEP 24 1984
B

Accession For	
NTIS GRA&I	☒
DTIC TAB	☐
Unannounced	☐
Justification	
By	
Distribution/	
Availability Codes	
Dist	Avail and/or Special
A-1	

INTRODUCTION

The various epoxy combinations in the SP-250 system were recently examined by differential scanning calorimetry (DSC) under dynamic conditions. The results of this study¹ and the military aspects of the epoxy system such as the usage in helicopter blades necessitated further investigation of 3M's formulation. Consequently, the same mixtures prepared for the previous study were reexamined by infrared spectroscopy (IR).


EXPERIMENTAL

The preparation of mixtures used in this study has been described.¹ For this IR investigation, the mixtures containing Monuron were cured at 130°C and those consisting of dicyandiamide and having "no Monuron" were hardened at 200°C. The curing time for all systems was two hours.

The preparation of samples for IR examination involved two different techniques. Solid materials were measured as potassium bromide (KBr) wafers and slurries were analyzed as thin films on KBr salt plates. The IR spectra were recorded on a Digilab FTS-10M Fourier transform infrared spectrometer. Each spectrum consisted of 120 co-added interferometric scans at 4-cm⁻¹ resolution. All uncured specimens were measured from 4000 cm⁻¹ to 400 cm⁻¹.

DISCUSSION AND RESULTS

The accelerated cure of dicyandiamide (Dicy)-containing epoxy resins is a complicated process and the cure mechanism was elucidated in this laboratory.²⁻⁴ The low temperature Dicy cure is dependent on the fact that the trisubstituted urea accelerator (Monuron) first reacts with the oxirane ring to form a matrix which is partially composed of cyclic 2-oxazolidones as indicated below:



Although the by-product, dimethylamine, is able to readily react with the epoxy functionally, the amine plays a more important role in the hardening process. This amine

1. LaLIBERTE, B. R., and SACHER, R. E. *The Dicyandiamide Cure of SP-250 Epoxy Resin Accelerated by Monuron*. Army Materials and Mechanics Research Center, AMMRC TR 83-17, April 1983.
2. LaLIBERTE, B. R., SACHER, R. E., and BORNSTEIN, J. *Acceleration of the Epoxy Resin-Dicyandiamide Cure Cycle by Trisubstituted Ureas*. Army Materials and Mechanics Research Center, AMMRC TR 81-30, June 1981.
3. LaLIBERTE, B. R. *The Reaction of Diuron With Epoxy Groups*. Army Materials and Mechanics Research Center, AMMRC TN 79-1, January 1979.
4. BORNSTEIN, J., LaLIBERTE, B. R., and SACHER, R. E. *The Formation of Cyclic 2-Oxazolidones With Respect to the Acceleration of the Dicyandiamide Cure of Epoxy Resins*. Army Materials and Mechanics Research Center, AMMRC TN 82-2, June 1982.

does, in fact, increase the reactivity of Dicy. It has been proposed⁵ that dimethylamine has a strong proclivity to remove a proton from Dicy, thus, enhancing the nucleophilic nature of the hardening agent (Dicy). This would account for the increased reactivity of Dicy.

The SP-250 resin is a mixture of three very different types of epoxy materials. The SP-250 formulation is summarized as to reflect a distribution of Monuron and Dicy on the basis of weight percent for each epoxide as shown in Table 1 below:

Table 1.

Epoxide	Epoxide (wt. %)	Dicy (wt. %)	Monuron (wt. %)
ECN 1273 (Ciba Geigy)	45.8	3.88	1.96
EPON 828 (Shell)	38.1	3.23	1.63
Active Diluent	4.7	0.40	0.20
	88.6	7.51	3.79

ECN 1273 is a low melting polymeric material having an epoxy novalac structure. EPON 828 comes in a liquid form and this mixture has a considerable amount of diglycidyl ether of bisphenol-A. The active diluent is described as a liquid flexibilizer having one epoxy group per molecule.

Infrared analysis of the curing behavior of the blends depicted in Tables 2 and 3 was performed using three different IR frequencies. These bands include the 1510 cm^{-1} (phenyl C=C semicircle stretch), the 915 cm^{-1} (the oxirane ring deformation), and the 1745 cm^{-1} frequency (carbonyl stretch which is characteristic of 2-oxazolidone derivatives). The results of the analysis are listed in Tables 2 and 3.

The maximum cure conversion which yielded the lowest 915 cm^{-1} to 1510 cm^{-1} ratio was found to be the EPON 828/Monuron/Dicy system which is also associated with the highest ratio of oxazolidone regarding the epoxy band. These results were somewhat anticipated based on predictions contained in our recent study.¹ The speculations resulted from the introduction of scanning rates having the dimensions of temperature per time. These values are believed to be a measure of the rapidity in which a mixture will achieve about 50% of its hardening cycle. Also, the ECN 1273/EPON 828/Monuron/Dicy system, 0.032 cm^{-1} , and the ECN 1273/EPON 828/Monuron system, 0.043 cm^{-1} , yielded high epoxy conversion. The active diluent system itself with Dicy and/or Monuron does not cure that well. The lack of cure is illustrated with the values of 0.182 cm^{-1} to 0.195 cm^{-1} and with the ratio of 910 cm^{-1} to 1510 cm^{-1} . These results are understandable because of the monofunctional characteristic of the active diluent which would not favor the formation of a high molecular weight product. However, the active diluent/Monuron mixture afforded the greatest 2-oxazolidone formation. Based on the previous predications,¹ this observation was not much of a surprise.

The EPON 828 system cures better than the ECN 1273 mixture and this is illustrated in Table 2. Copies of the infrared scans used in compiling the data in Tables 2 and 3 are incorporated in the Appendix.

5. LaLIBERTE, B. R., and BORNSTEIN, J. *Mechanism of Monuron-Accelerated Dicyandiamide Cure of Epoxy Resins*. Army Materials and Mechanics Research Center, AMMRC TR 81-34, July 1981.

Table 2. INFRARED ANALYSES OF CURING BEHAVIOR

Sample Identification	Ratio of 910 cm^{-1} to 1510 cm^{-1}
EPON 828 + DICY (uncured)	0.246
EPON 828 + DICY (cured)	0.173
EPON 828 + MON (uncured)	0.416
EPON 828 + MON (cured)	0.212
EPON 828 + MON + DICY (uncured)	0.313
EPON 828 + MON + DICY (cured)	0.013
ECN 1273 + DICY (uncured)	0.636
ECN 1273 + DICY (cured)	0.186
ECN 1273 + MON (uncured)	0.310
ECN 1273 + MON (cured)	0.588
ECN 1273 + MON + DICY (uncured)	0.777
ECN 1273 + MON + DICY (cured)	0.195
DILUENT + DICY (uncured)	0.315
DILUENT + DICY (cured)	0.245
DILUENT + MON (uncured)	0.307
DILUENT + MON (cured)	0.195
DILUENT + MON + DICY (uncured)	0.505
DILUENT + MON + DICY (cured)	0.182
EPON 828 + ECN 1273 + DICY (uncured)	0.350
EPON 828 + ECN 1273 + DICY (cured)	0.236
EPON 828 + ECN 1273 + MON (uncured)	0.398
EPON 828 + ECN 1273 + MON (cured)	0.043
EPON 828 + ECN 1273 + MON + DICY (uncured)	0.400
EPON 828 + ECN 1273 + MON + DICY (cured)	0.032
EPON 828 + DILUENT + DICY (uncured)	0.313
EPON 828 + DILUENT + DICY (cured)	0.114
EPON 828 + DILUENT + MON (uncured)	0.225
EPON 828 + DILUENT + MON (cured)	0.198
EPON 828 + DILUENT + MON + DICY (uncured)	0.862
EPON 828 + DILUENT + MON + DICY (cured)	0.570
ECN 1273 + DILUENT + DICY (uncured)	0.581
ECN 1273 + DILUENT + DICY (cured)	0.158
ECN 1273 + DILUENT + MON (uncured)	0.548
ECN 1273 + DILUENT + MON (cured)	0.375
ECN 1273 + DILUENT + MON + DICY (uncured)	0.771
ECN 1273 + DILUENT + MON + DICY (cured)	0.129

Table 3. INFRARED ANALYSIS OF 2-OXAZOLIDONE FORMATION

Sample Identification	Ratio of 1745 cm^{-1} to 910 cm^{-1}
EPON 828 + MON (uncured)	0
EPON 828 + MON (cured)	0.666
EPON 828 + MON + DICY (uncured)	0
EPON 828 + MON + DICY (cured)	6.0
DILUENT + MON (uncured)	0
DILUENT + MON (cured)	0.888
DILUENT + MON + DICY (uncured)	0
DILUENT + MON + DICY (cured)	1.1
EPON 828 + DILUENT + MON (uncured)	0
EPON 828 + DILUENT + MON (cured)	0.807
EPON 828 + DILUENT + MON + DICY (uncured)	0
EPON 828 + DILUENT + MON + DICY (cured)	0.200

CONCLUSION

This manuscript is an initial study on the application of infrared spectroscopy as an analytical tool for the study of the curing process of epoxy-based systems. In this study, two specific vibrational frequencies were utilized to follow the cure. The epoxy frequency was normalized to the phenyl C=C semicircle stretch at 1510 cm^{-1} which is considered to be inert in the course of the hardening process. The carbonyl frequency was found to increase in the presence of Dicy and this band was normalized to the epoxy absorbance.

For a better understanding of the cure mechanism, the various SP-250 mixtures should be cured in the IR spectrometer with respect to temperature and time.

Further work is ongoing in the evaluation of the extent of cure with respect to chemistry. This work includes the following considerations:


A. The evaluation of other inert frequencies for normalization such as the 1600 cm^{-1} , phenyl C=C quadrant stretch, and the 830 cm^{-1} , p-substitution frequency. The 1240 cm^{-1} bond phenyl-O-C stretch is also being studied as a normalizing frequency.

B. The use of the region from 3600 cm^{-1} to 3200 cm^{-1} (formation of alcohols during the amide reaction), 2400 cm^{-1} to 2000 cm^{-1} (C-N stretch characteristic of dicyandiamide), and the 1200 cm^{-1} to 900 cm^{-1} may be employed as a measure of cross-linking.


C. The formation of C-N linkages between the epoxy system and the Dicy hardener are part of the cure process. These linkages are difficult to detect by IR analysis but are pertinent to the cure cycle. Investigations of this type have commenced and will continue in the future.

A DSC paper is being prepared which involves the isothermal analysis of the SP-250 mixtures. The results of this study added technical substance to our scanning rates.¹ Likewise, this IR investigation indicates that the rates are worthy of a theoretical consideration.


APPENDIX




DIGLYCIDYLETHER OF BISPHENOL A (DGEBA) MONOMER




ECN 1273 RESIN KBR PELLET




DICYANDIAMIDE 97% KBR PELLET




MONURON KBR PELLET




33.1% EPON 828, 3.23% DICY UNCURED THIN FILM




33.1% EPON 828, 3.23% DICY CURED @ 180 C FOR 2 HRS. THIN FILM




EPON 828, 1.63% MONURON UNCURED THIN FILM




38.1% EPON 828, 3.23% DICY, 1.63% MONURON UNCURED




38.1% EPON 828 , 3.23% DICY, 1.63% MONURON CURED KBR




ECN1273 3.88% DICY UNCURED KBR PELLET




ECN 1273 3.88% DICY (CURED)




ECN1273 1.96% MONURON UNCURED KBR PELLET




ECN1273 1.96% MONURON (CURED)




ECN 3.88% DICY, 1.96% MONURON UNCURED KBR PELLET




ECN 1273 3.88% DICY 1.96% MONURON (CURED)




CARDOLITE 513(4.7%), DICY(0.4%) UNCURED THIN FILM




CARDOLITE S13(4.7%), DICY(0.4%) CURED @ 180 C FOR 2 HRS.




CARDOLITE S13 + MONURON UNCURED THIN FILM




CARDOLITE 513 + MONURON CURED @ 130°C FOR 2 HRS.





CARDOLITE 513 (4.7%), MONURON (0.2%), DICY (0.4%) UNCURED






CARDOLITE 513 (4.7%), DICY (0.4%) CURED @ 180 C FOR 2 HRS. THIN FILM




CARDOLITE 513 (4.7%), MONURON (0.2%), DICY (0.4%) CURED @ 130C 2 HRS.










EPON 828,ECN 1273,MONURON(3.59%),DICY(7.11%) UNCURED TF




EPON 828,ECN 1273,MONURON(3.59%),DICY(7.11%) CURED 2 HRS. @ 130 C KE








EPON 828(38.1%),CARDOLITE(4.7%),MONURON(9.83%) UNCURED THIN FILM




EPON 828(38.1%),CARDOLITE 513(4.7%),MONURON(1.83%) CURED 2 HRS. @ 130








EGN1273 DICY CARDOLITE 513 UNCURED




EGN 1273 CARDOLITE 513 DICY CURED 180 C 2 HRS.





ECN 1273,CARDOLITE S13 MONURON,DICY UNCURED



ECN 1273 CARDOLITE S13 DICY MONURON CURED 130 C 2 HRS.

DISTRIBUTION LIST

No. of Copies	To
1	Office of the Under Secretary of Defense for Research and Engineering, The Pentagon, Washington, DC 20301
12	Commander, Defense Technical Information Center, Cameron Station, Building 5, 5010 Duke Street, Alexandria, VA 22314
1	Metals and Ceramics Information Center, Battelle Columbus Laboratories, 505 King Avenue, Columbus, OH 43201
	Commander, Army Research Office, P.O. Box 12211, Research Triangle Park, NC 27709
1	ATTN: Information Processing Office
	Commander, U.S. Army Materiel Command, 5001 Eisenhower Avenue, Alexandria, VA 22333
1	ATTN: DRCLD
	Commander, U.S. Army Electronics Research and Development Command, Fort Monmouth, NJ 07703
1	ATTN: DELSD-L
1	DELS-D-E
	Commander, U.S. Army Armament, Munitions and Chemical Command, Dover, NJ 07801
2	ATTN: Technical Library
1	DRDAR-SCM, J. D. Corrie
	Commander, U.S. Army Natick Research and Development Center, Natick, MA 01760
1	ATTN: Technical Library
	Commander, U.S. Army Missile Command, Redstone Arsenal, AL 35898
1	ATTN: DRSMI-TB, Redstone Scientific Information Center
	Commander, U.S. Army Foreign Science and Technology Center, 220 7th Street, N. E., Charlottesville, VA 22901
1	ATTN: Military Tech, Mr. Marley
	Director, Eustis Directorate, U.S. Army Air Mobility Research and Development Laboratory, Fort Eustis, VA 23604
1	ATTN: DAVDL-E-MOS (AVRADCOM), Mr. J. Robinson
	Naval Research Laboratory, Washington, DC 20375
1	ATTN: Dr. C. I. Chang - Code 5830
1	Dr. Chet Poranski - Code 6110
1	Dr. William Moniz, Chemistry Division - Code 6120
	Chief of Naval Research, Arlington, VA 22217
1	ATTN: Code 471
1	Edward J. Morrissey, AFWAL/MLTE, Wright-Patterson Air Force Base, OH 45433

No. of
Copies

To

Commander, U.S. Air Force Wright Aeronautical Laboratories,
Wright-Patterson Air Force Base, OH 45433

- 1 ATTN: AFWAL/MLC
- 1 AFWAL/MLLP, D. M. Forney, Jr.
- 1 AFWAL/MLBC, Stanley Schulman
- 1 AFWAL/MLBC, Dr. T. Helminiak
- 1 AFWAL/MLBP, Dr. R. Van Deusen

National Aeronautics and Space Administration, Washington, DC 20546

- 1 ATTN: Mr. G. C. Deutsch - Code RW

National Aeronautics and Space Administration, Marshall Space Flight Center,
Huntsville, AL 35812

- 1 ATTN: R. J. Schwinghammer, EH01, Director, M&P Lab
- 1 Mr. W. A. Wilson, EH41, Building 4612

National Aeronautics and Space Administration, Langley Research Center,
Hampton, VA 23365

- 1 ATTN: Dr. Philip R. Young
- 1 Dr. Paul Hergenrother

- 1 Committee on Marine Structures, Marine Board, National Research Council,
2101 Constitution Ave., N. W., Washington, DC 20418

- 1 Dr. David H. Kaelbe, Arroyo Computer Center, 730 Blue Oak Avenue,
Thousand Oaks, CA 91320

- 1 Richard J. Hinrichs, NARMCO Materials, Inc., 600 W. Victoria Street,
Costa Mesa, CA 92627

DuPont Instruments, Quillen Building, Concord Plaza, Wilmington, DE 19898

- 1 ATTN: George Dallas

Lockheed Missiles and Space Company, Inc., Dept. 47-01, Building 150,
P.O. Box 504, Sunnyvale, CA 94088

- 1 ATTN: Deborah Hadad

Lockheed California Company, B/229, PH2, Dept. 74-71, P.O. Box 551,
Burbank, CA 91520

- 1 ATTN: Don Crozier

Hercules, Inc., Box 98, Magna, UT 84044

- 1 ATTN: R. E. Hoffman

Boeing Commercial Airplane Company, Seattle, WA 98008

- 1 ATTN: Judy S. Chen, M.S. 73-43

Grumman Aerospace Corporation, Bethpage, NY 11714

- 1 ATTN: Robert Holden

No. of
Copies

To

Rockwell Science Center, 1049 Camino Dos Rios, P.O. Box 1085,
Thousand Oaks, CA 91360
1 ATTN: Paul Dynes

Northrop Corporation, Hawthorne, CA 90250
1 ATTN: David Crabtree

McDonnell Douglas Corporation, McDonnell Aircraft Company, P.O. Box 516,
St. Louis, MO 63166
1 ATTN: J. F. Carpenter
1 Terry Bartels

McDonnell Douglas Corporation, Huntington Beach, CA 92646
1 ATTN: Paul Scherer

Reliable Manufacturing, Inc., 10910 Talbert Avenue, Fountain Valley, CA 92708
1 ATTN: Derril Steele

Westinghouse Electric Company, Research and Development Center, Beulah Road,
Pittsburgh, PA 15235
1 ATTN: Dr. Zal Sanjana

Ministry of Defense, Non-Metallic Materials Branch, Waltham Abbey, Essex, England
1 ATTN: Dr. Anthony Davis, Procurement Executive

Union Carbide Corporation, Nuclear Division, Y-12 Plant, Oak Ridge, TN 37830
1 ATTN: J. M. Mills, Jr., Information Control Office

Director, Army Materials and Mechanics Research Center, Watertown, MA 02172
2 ATTN: DRXMR-PL
2 Authors

Army Materials and Mechanics Research Center,
Watertown, Massachusetts 02172
INFRARED SPECTROSCOPY STUDY OF THE SP-250
EPOXY RESIN SYSTEM -
Robert E. Sacher and Bernard R. Laliberte
Technical Report AMMRC TR 84-29, July 1984, 26 pp -
illus-tables, D/A Project 11162105AH84

AD
UNCLASSIFIED
UNLIMITED DISTRIBUTION
Key Words
Epoxy resins
Curing agents
Monuron

The various epoxides which are part of the SP-250 formulation (3M Company, St. Paul, Minnesota) were treated to three different curing procedures. In this study, the epoxides and the epoxy blends were individually cured with dicyandiamide (Dicy) and Monuron, respectively, and in combination (Dicy/Monuron). The acceleration of the Dicy-containing epoxy resin cure is linked to the formation of cyclic 2-oxazolidone. The characteristic nature of the carbonyl band of these cyclic derivatives prompted us to monitor the hardening process by infrared spectroscopy. The cure conversion was evaluated to be the highest for the EPON 828 + Dicy/Monuron and ECN 1273/EPON 828 + Dicy/Monuron systems. The epoxide $\pm$ accelerator reaction affording 2-oxazolidone was found to be the greatest in the active diluent + Monuron system. Regarding neat EPON 828, the presence of Dicy significantly enhanced the formation of 2-oxazolidone.

Army Materials and Mechanics Research Center,
Watertown, Massachusetts 02172
INFRARED SPECTROSCOPY STUDY OF THE SP-250
EPOXY RESIN SYSTEM -
Robert E. Sacher and Bernard R. Laliberte
Technical Report AMMRC TR 84-29, July 1984, 26 pp -
illus-tables, D/A Project 11162105AH84

AD
UNCLASSIFIED
UNLIMITED DISTRIBUTION
Key Words
Epoxy resins
Curing agents
Monuron

The various epoxides which are part of the SP-250 formulation (3M Company, St. Paul, Minnesota) were treated to three different curing procedures. In this study, the epoxides and the epoxy blends were individually cured with dicyandiamide (Dicy) and Monuron, respectively, and in combination (Dicy/Monuron). The acceleration of the Dicy-containing epoxy resin cure is linked to the formation of cyclic 2-oxazolidone. The characteristic nature of the carbonyl band of these cyclic derivatives prompted us to monitor the hardening process by infrared spectroscopy. The cure conversion was evaluated to be the highest for the EPON 828 + Dicy/Monuron and ECN 1273/EPON 828 + Dicy/Monuron systems. The epoxide $\pm$ accelerator reaction affording 2-oxazolidone was found to be the greatest in the active diluent + Monuron system. Regarding neat EPON 828, the presence of Dicy significantly enhanced the formation of 2-oxazolidone.

Army Materials and Mechanics Research Center,
Watertown, Massachusetts 02172
INFRARED SPECTROSCOPY STUDY OF THE SP-250
EPOXY RESIN SYSTEM -
Robert E. Sacher and Bernard R. Laliberte
Technical Report AMMRC TR 84-29, July 1984, 26 pp -
illus-tables, D/A Project 11162105AH84

AD
UNCLASSIFIED
UNLIMITED DISTRIBUTION
Key Words
Epoxy resins
Curing agents
Monuron

The various epoxides which are part of the SP-250 formulation (3M Company, St. Paul, Minnesota) were treated to three different curing procedures. In this study, the epoxides and the epoxy blends were individually cured with dicyandiamide (Dicy) and Monuron, respectively, and in combination (Dicy/Monuron). The acceleration of the Dicy-containing epoxy resin cure is linked to the formation of cyclic 2-oxazolidone. The characteristic nature of the carbonyl band of these cyclic derivatives prompted us to monitor the hardening process by infrared spectroscopy. The cure conversion was evaluated to be the highest for the EPON 828 + Dicy/Monuron and ECN 1273/EPON 828 + Dicy/Monuron systems. The epoxide $\pm$ accelerator reaction affording 2-oxazolidone was found to be the greatest in the active diluent + Monuron system. Regarding neat EPON 828, the presence of Dicy significantly enhanced the formation of 2-oxazolidone.

Army Materials and Mechanics Research Center,
Watertown, Massachusetts 02172
INFRARED SPECTROSCOPY STUDY OF THE SP-250
EPOXY RESIN SYSTEM -
Robert E. Sacher and Bernard R. Laliberte
Technical Report AMMRC TR 84-29, July 1984, 26 pp -
illus-tables, D/A Project 11162105AH84

AD
UNCLASSIFIED
UNLIMITED DISTRIBUTION
Key Words
Epoxy resins
Curing agents
Monuron

The various epoxides which are part of the SP-250 formulation (3M Company, St. Paul, Minnesota) were treated to three different curing procedures. In this study, the epoxides and the epoxy blends were individually cured with dicyandiamide (Dicy) and Monuron, respectively, and in combination (Dicy/Monuron). The acceleration of the Dicy-containing epoxy resin cure is linked to the formation of cyclic 2-oxazolidone. The characteristic nature of the carbonyl band of these cyclic derivatives prompted us to monitor the hardening process by infrared spectroscopy. The cure conversion was evaluated to be the highest for the EPON 828 + Dicy/Monuron and ECN 1273/EPON 828 + Dicy/Monuron systems. The epoxide $\pm$ accelerator reaction affording 2-oxazolidone was found to be the greatest in the active diluent + Monuron system. Regarding neat EPON 828, the presence of Dicy significantly enhanced the formation of 2-oxazolidone.