

AD-A159 161 BURNING TIME AND SIZE OF ALUMINUM MAGNESIUM ZIRCONIUM
TANTALUM AND PYROFU. (U) NAVAL POSTGRADUATE SCHOOL
MONTEREY CA J KOL ET AL. JUL 85 NPS67-85-003CR

AD-A159 161 BURNING TIME AND SIZE OF ALUMINUM MAGNESIUM ZIRCONIUM
TANTALUM AND PYROFU. (U) NAVAL POSTGRADUATE SCHOOL
MONTEREY CA J KOL ET AL. JUL 85 NPS67-85-003CR

AD-A159 161 BURNING TIME AND SIZE OF ALUMINUM MAGNESIUM ZIRCONIUM 1/1


UNCLASSIFIED F/G 21/2

UNCLASSIFIED F/G 21/2

UNCLASSIFIED

[illegible]

END
FILMED
STC



MICROCOPY RESOLUTION TEST CHART
NATIONAL BUREAU OF STANDARDS-1963-A

2

NPS67-85-003CR

AD-A159 161

NAVAL POSTGRADUATE SCHOOL

Monterey, California



CONTRACTOR REPORT

BURNING TIME AND SIZE OF ALUMINUM, MAGNESIUM,
ZIRCONIUM, TANTALUM, AND PYROFUZE PARTICLES
BURNING IN STEAM

Yair Chozev and Jacob Kol

July 1985

DTIC
ELECTE
SEP 13 1985
D

Approved for public release; distribution unlimited.

Prepared for: Naval Surface Weapons Center
White Oak Laboratories
Silver Springs, MD 20910

DTIC FILE COPY

NAVAL POSTGRADUATE SCHOOL
Monterey, California

RADM R. H. Shumaker
Superintendent

D. A. Schrady
Provost


The work reported herein was carried out for the Naval Postgraduate School by Mr. Jacob Kol under Contract N62271-84-M-3357 and Mr. Yair Chozev under Contract N62271-84-M-3055. The work presented in this report is in support of "Underwater Shaped Charges" sponsored by the Naval Surface Weapons Center. The work provides experimental results for burning time and size of aluminum, magnesium, zirconium, tantalum and pyrofuze particles in steam. The project at the Naval Postgraduate School is under the cognizance of Distinguished Professor A. E. Fuhs who is principal investigator.

Reproduction of all or part of this report is authorized.

Prepared by:



MR. YAIR CHOZEV
Research Contractor




MR. JACOB KOL
Research Contractor

Reviewed by:



ALLEN E. FUHS
Distinguished Professor



M. F. PLATZER
Chairman, Department of Aeronautics

Released by:



J. N. DYER
Dean of Science and Engineering

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER NPS67-85-003CR	2. GOVT ACCESSION NO. AD-A159161	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) Burning Time and Size of Aluminum, Magnesium, Zirconium, Tantalum, and Pyrofuze Particles Burning in Steam		5. TYPE OF REPORT & PERIOD COVERED Contractor's Report November 1984-March 1985
7. AUTHOR(s) Jacob Kol and Yair Chozev		6. PERFORMING ORG. REPORT NUMBER
9. PERFORMING ORGANIZATION NAME AND ADDRESS Naval Postgraduate School Monterey, CA 93943-5100		8. CONTRACT OR GRANT NUMBER(s) N62271-84-M-3357 N62271-84-M-3055
11. CONTROLLING OFFICE NAME AND ADDRESS		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office) Naval Postgraduate School Monterey, CA 93943-5100		12. REPORT DATE July 1985
		13. NUMBER OF PAGES 31
		15. SECURITY CLASS. (of this report) UNCLASSIFIED
		16a. DECLASSIFICATION/DOWNGRADING SCHEDULE
16. DISTRIBUTION STATEMENT (of this Report) Approved for public release; distribution unlimited.		Accession For NTIS GRA&I DTIC TAB Unannounced Justification
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		By Distribution/ Availability Codes
18. SUPPLEMENTARY NOTES		Avail and/or Dist Special A-1
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) Combustion of Metal, Burning of Metal, Combustion in Steam, Burning in Steam, Aluminum, Pyrofuze, Magnesium, Tantalum, Titanium, Zirconium, Burning Time.		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) Wires of various metals were exploded in a steam atmosphere. The metals investigated were aluminum, magnesium, tantalum, zirconium, and pyrofuze. Exploding wires generated numerous hot, small particles. Using photography, the burning time and particle sizes were measured. Typical results are as follows: 125 $\pm$ 25 micron diameter aluminum burns in 3.8 $\pm$.75 ms; 175 $\pm$ 35 micron diameter magnesium burns in 3.8 $\pm$.75 ms; 125 $\pm$ 25 micron diameter zirconium in 25 to 31 ms; 125 $\pm$ 25 micron diameter tantalum in 24 to 50 ms;		

DD FORM 1 JAN 73 1473

EDITION OF 1 NOV 65 IS OBSOLETE
S/N 0102-LF-014-6601

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

and 125 ± 25 micron pyrofuze in 30 to 50 ms. The atmosphere was pure saturated steam at approximately 20 psig.

S/N 0102- LF-014-6601

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

TABLE OF CONTENTS

	<u>Page</u>
I. INTRODUCTION	1
II. EXPERIMENTAL	3
A. Experimental Procedure	3
B. High Speed Light Chopper	3
C. The Quenching Technique for Particle Size Measurement	5
III. RESULTS	6
A. Burning Time Measurement	6
B. Distribution Functions of Burning Time	6
C. Distribution Functions of Particle Size	16
D. Summary of Results of Burning Time and Particle Size	18
IV. DISCUSSION	19
V. REFERENCES	21

LIST OF TABLES

	<u>Page</u>
1. Burning Time Measurement	7
2. Summary of Results	18

LIST OF FIGURES

1. Photography with High Speed Chopper	4
2. The Quenching Technique Configuration for Particle Quenching	5
3. Burning Time Measurement of Aluminum Particles	10
4. Burning Time Measurement of Magnesium Particles	11
5. Burning Time Measurement of Zirconium Particles	12
6. Burning Time Measurement of Tantalum Particles	13
7. Burning Time Measurement of Pyrofuze Particles	14
8. Distribution Functions of Burning Time for Al, Mg, Zr, Ta and Pyrofuze	15
9. Distribution Functions of Particle Size for Al, Mg, Zr, Ta and Pyrofuze	17

ABSTRACT + OF-

Wires of various metals were exploded in a steam atmosphere. The metals investigated were aluminum, magnesium, tantalum, zirconium, and pyrofuze. Exploding wires generated numerous hot, small particles. Using photography, the burning time and particle sizes were measured. Typical results are as follows: 125 $\pm$ 25 micron diameter aluminum burns in 3.8 $\pm$.75 ms; 175 $\pm$ 35 micron diameter magnesium burns in 3.8 $\pm$.75 ms; 125 $\pm$ 25 micron diameter zirconium in 25 to 31 ms; 125 $\pm$ 25 micron diameter tantalum in 24 to 50 ms; and 125 $\pm$ 25 micron pyrofuze in 30 to 50 ms. The atmosphere was pure

saturated steam at approximately 20 psig. Originator supplied
Keywords: 'include:'

ACKNOWLEDGEMENT

The authors acknowledge the valuable help, cooperation and guidance of Professor Allen E. Fuhs during this work.

I. INTRODUCTION

The energy released by metals burning in steam has several important applications including torpedo propulsion, nuclear reactor safety, underwater vehicles, underwater ordnance, etc.

This report continues the studies that were performed by Hallenbeck [1] and Kol, Fuhs and Berger [2] which are related to underwater shaped charge investigations.

Investigation of burning time of aluminum, magnesium, tantalum, zirconium and pyrofuze particles in steam were rarely found in the literature.

Leibowitz et. al., [3] ignited aluminum particles of diameter of 360 μm in water and steam by laser beam and measured the burning-time of the reacting particles. In the cases of low amount of reaction ($T=25^\circ\text{C}$, $P=0.03$ ATM where T and P are the water temperature and pressure, respectively) the burning-time was 5 to 10 ms. In the cases of complete reaction ($T=100^\circ\text{C}$, 181°C and $P=1, 10$ ATM respectively) long burning times of 213 ms were measured. The amount of reaction is according to amount of alumina formation.

Cassel et. al., [4] measured the burning time of magnesium particles at atmospheric pressure with O_2 , air, premixed $20_2 + 8 \text{ Ar}$ and $20_2 + 8\text{He}$ at 1200K ambient temperature and found that 120 μm particles burned 16.8 ms in air, 15.75 ms in $20_2 + 8 \text{ Ar}$ and 11.5 m in $20_2 + 8\text{He}$. The burning-time in O_2 was one tenth that in air.

Pruchukho et. al., [5] measured the burning time of magnesium particles in diameter from 34 to 184 μm and in ambient temperature of 1800°C . For the particles of 90 μm at 1 ATM in water vapor, the burning time of 1 ms was obtained while in mixture of 35% H_2O and 65% N_2 at 1 ATM and ambient temperature from 1050°C to 1150°C , the burning time was 2 ms. For particles of 180 μm the burning time was 16 ms in the same mixture.

Ozerov et. al., [6] measured the burning time for aluminum and magnesium in 1800°C water vapor. The burning time in 1 ATM for 120 μm aluminum particles was 18 ms and for 165 μm magnesium particles was 12 ms. The burning time of 148 μm aluminum particles in 3 ATM was 30.5 ms.

Nelson et. al., [7] measured the burning time of 525 μm zirconium particles in mixtures of O_2 , He/O_2 and Ar/O_2 at 0.82 ATM and found 200 ms for 65% He + 35% O_2 and even longer burning time for 65% Ar + 35% O_2 .

Harrison [8] measured burning velocities of zirconium wires of 1 and 0.5 mm diameter in atmospheric pressure and mixtures of air and oxygen and found burning time longer than magnesium.

Data for burning time was not found for tantalum and pyrofuze particles. This report summarizes the burning time measurements and particle size measurements for aluminum, magnesium, zirconium, tantalum and pyrofuze burning in steam.

II. EXPERIMENTAL

A. Experimental Procedure

The experiments were conducted in pressure vessel which consisted of a twelve inch high stainless steel cylinder, 10.75 inches diameter with four evenly spaced, 5 inch diameter observation ports welded into its circumference. One inch thick. Schlieren quality, borosilicate crown glass (BK-7) was installed in each port. Two Watlow Band Heaters were used to heat the apparatus to operating temperature and four additional Watlow Heaters were mounted on observation ports in order to prevent steam condensation during experiments. An Omega model 157 Digital Controller was used for temperature stabilization. The experiments were conducted in pressure range of 20 to 35 psi and steam temperature of 180°C. Thermocouples were mounted in different locations inside the chamber to measure the internal temperature.

The aluminum, magnesium, tantalum, zirconium and pyrofuze particles were generated by the exploding wire technique. The 5 cm length wire was mounted between two holders and the ignition energy transferred to the wire.

Particle burning time was measured using Pentax 35 mm still camera equipped with high speed light chopper (see Figure 1). Kodak Ektachrome 200 ASA film, 400 ASA TRI-X PAN film and Polaroid 40 ASA film were used for photography of the time events along particle tracks.

B. High Speed Light Chopper

The light chopper was assembled from an Universal Electric Company motor and a 8 inch diameter balanced disc. The motor speed after loading was 6500 RPM, and the chopping frequency was increased by using fifteen 1 inch diameter holes around the circumference of the disc. The on-off ratio of the chopping was designed to be 67 percent on time and 33 percent off-time. The chopping time is calculated as follows:

$$T_1 \text{ chopping} = \frac{60}{6500 \times 15} = 0.62 \text{ [ms]} \text{ (for 15 holes)}$$

$$T_2 \text{ chopping} = \frac{60}{6500 \times 12} = 0.77 \text{ [ms]} \text{ (for 12 holes)}$$

where T_1 and T_2 are the chopper periods for 15 and 12 holes respectively.




Figure 1. Photography with High Speed Chopper

a. High Speed Light Chopper

b. 35 mm Pentax Camera

C. The Quenching Technique for Particle Size Measurement

The diameter of the particles was measured by comparing the quenched particles to standard wires. The quenching technique for the burning particles is shown in Figure 2.




Figure 2. The Quenching Technique Configuration for Particle Quenching

- a. Particle angular filter made of teflon plate
- b. An aluminum foil impact suppressor
- c. The aluminum foil holders
- d. Stainless steel collector plate (smeared with silicon grease).

The aluminum foil was assembled at a distance 29 ± 0.5 mm below the wire while the plate was assembled 35 ± 0.5 mm below the wire.

III. RESULTS

A. Burning Time Measurement

The experimental conditions of burning time measurements are summarized in Table 1. In the following tests, the 55 mm focal length lens was used. Representative photographs of burning time experiments are shown in Figure 3 through Figure 7.

B. Distribution Functions of Burning Time

The distribution functions of burning time results of aluminum, zirconium, magnesium, tantalum and pyrofuze particles are shown in Figure 8. The burning time of aluminum particles is less than 27 ms where the maximum of the distribution function is for 3.75 ms. The burning time of magnesium particles is less than 14 ms, and the maximum of the distribution function is 3.75 ms.

The burning time of zirconium particles is from 6.5 to 39.5 ms and the maximum of the distribution function is from 25 to 30 ms. The burning time for tantalum particles is longer than that of zirconium particles and is from 9.5 to 91 ms. The distribution function is quite uniform where the maximum is from 24 to 28 ms. The burning time of pyrofuze particles is from 12 to 97 ms and the maximum of an almost uniform distribution function is from 30 to 50 ms. The total number of the particles tracks that were analyzed for different metals were as follows: 40 tracks of aluminum, 22 tracks of pyrofuze, 21 tracks of magnesium and zirconium and 18 tracks of tantalum.

TABLE 1 Burning Time Measurement

TEST NUMBER	METAL	FILM [ASA]	f NUMBER	PRES. [PSI]	TEMP. [F]	*BURNING TIME [ms]	*FLAME ZONE WIDTH [mm]
1	Aluminum	40	2.4	25	380	N/A	N/A
2	Aluminum	40	2.8	27.5	365	6.1,3.1	2.15,1.3
3	Aluminum	40	2.8	22.5	360	8.5	2.8
16	Aluminum	200	5.6	22	370	N/A	N/A
17	Aluminum	200	5.6	27	390	N/A	N/A
18	Aluminum	200	5.6	39	380	N/A	N/A
19	Aluminum	200	5.6	20	390	3.6,3.6,3.05,4.3, 4.9,13.4,15.9,4.3	.78,.78,.61,.26,.78,1.04 1.04,.78
36	Aluminum	200	5.6	34	380	6.7,10.4,6.7,>15	0.95,0.95,.78,1.56
37	Aluminum	400	8	21	360	7.7,6.2,5.4,3.9,6.9	.73,.66,.66,.55,.66
38	Aluminum	400	8	20	360	14.6,2.7,27,10.8, 3.9	.6,1.11,1.02,0.6,.37
39	Aluminum	400	8	22	390	3.9,15.4,7.7,3.9,5.4,7.7 10.8,5.4,4.6,3.9,4.6	0.56,1.02,.74,.28,.28, .65,.83,.47,.37,.55,.46
40	Aluminum	400	8	20	380	N/A	N/A
54	Aluminum	400	8	22	340	4.6,2.3,3.1,3.5	.49,.39,.29,.29
4	Magnesium	40	2.4	21	400	7.9,3.7,3.7,2.4	3.2,1.5,2.6,1.7
5	Magnesium	40	2.4	27.5	370	7.3,2.4	3.4,5.2,6
6	Magnesium	40	2.8	25	400	7.3,3.1	3,1.7
7	Magnesium	40	2.8	23	400	N/A	N/A
20	Magnesium	200	5.6	20	390	N/A	N/A
21	Magnesium	200	5.6	17	380	4.3,3.7,3.1	.78,.69,.69
22	Magnesium	200	5.6	20	370	7.3,6.1,9.8	.78,1.04,1.12
23	Magnesium	200	5.6	27	380	6.1,2.4	0.86,0.78
41	Magnesium	400	8	22	370	N/A	N/A
42	Magnesium	400	8	20	400	N/A	N/A
43	Magnesium	400	8	24	390	4.6	.7
55	Magnesium	400	8	20	380	N/A	N/A
56	Magnesium	400	8	22	350	3.1,2.3,3.9,13.9,6.93, 3.1	.53,.65,.75,0.74,0.68, 0.41

TABLE 1 (CONTINUED)

TEST NUMBER	METAL	FILM [ASA]	f NUMBER	PRES. [PSI]	TEMP. [F]	*BURNING TIME [ms]	*FLAME ZONE WIDTH [mm]
8	Zirconium	40	9.5	27	400	23.8	0.43
9	Zirconium	40	8	35	400	N/A	N/A
24	Zirconium	200	16	33	400	33.6, 27.5, 31.7, 31.7, 20.1, 20.7, 24.4	.6, .43, .51, 0.6, .48, .34, .43
25	Zirconium	200	16 + ND 0.3	28	400	9.2, 17.1, 34.2	.34, .25, .6
26	Zirconium	200	16 + ND 0.3	22	400	N/A	N/A
27	Zirconium	200	16 + ND 0.3	21	390	N/A	N/A
44	Zirconium	400	16 + ND 0.3	36	380	N/A	N/A
45	Zirconium	400	16 + ND 0.3	21	390	23.9, 6.2	.18, .18
46	Zirconium	400	16 + ND 0.3	34	400	40, 31.5, 15.4	.26, .26, .18
47	Zirconium	400	16 + ND 0.3	20	390	N/A	N/A
48	Zirconium	400	16 + ND 0.3	30	380	12.3	.18
57	Zirconium	400	16 + ND 0.3	24	370	21.6, 10.8, 8.5, 12.3	0.22, .18, .13, .18
58	Zirconium	400	16 + ND 0.3	27	390	N/A	N/A
10	Tantalum	40	8	27.5	400	>55	0.66
11	Tantalum	40	8	26	400	N/A	N/A
12	Tantalum	40	9.5	22	400	43, 24	0.66, 0.5
13	Tantalum	40	9.5	32	360	N/A	N/A
28	Tantalum	200	16 + 0.3 ND	28	400	26.2, 33.6, 26.8, 55, 91.5	.3, .39, .35, .69, .47
29	Tantalum	200	16 + 0.3 ND	27	390	42.7, 30.5, 85.4, 11.6, 9.2, 22.6, 36.6	.26, .3, 0.5, .17, 1.3, .37, .26
30	Tantalum	200	16 + 0.3 ND	50	350	26.8, 13.4	.43, .26
31	Tantalum	200	16 + 0.3 ND	34	370	18.3	.17
32	Tantalum	200	16 + 0.3 ND	29	360	N/A	N/A
33	Tantalum	200	16 + 0.3 ND	33	390	N/A	N/A
49	Tantalum	400	16 + 0.3 ND	32	400	N/A	N/A
50	Tantalum	400	16 + 0.3 ND	21	360	N/A	N/A
59	Tantalum	400	16 + 0.3 ND	24	390	N/A	N/A

TABLE 1 (CONTINUED)

TEST NUMBER	METAL	FILM [ASA]	f NUMBER	PRES. [PSI]	TEMP. [F]	*BURNING TIME [ms]	*FLAME ZONE WIDTH [mm]
14	Pyrofuz	40	9.5	21	350	18.3,12.4,19.2	.33,0.17,0.39
15	Pyrofuz	40	8	33	400	93,49,30,56,49	0.82,0.63,.66,.4,0.66
34	Pyrofuz	200	16 + 0.3 ND	22	390	24.4,42.7,53.1,48.8,79.3 42.7	.86,.78,.78,.44,.78,.6
35	Pyrofuz	200	10	40	370	30.5,45.8,15.9,97.6,67, 70.2,51.9,67	.43,.78,.43,.78,.52,.43, .52,.69
51	Pyrofuz	400	16 + 0.3 ND	46	350	N/A	N/A
52	Pyrofuz	400	16 + 0.3 ND	22	390	N/A	N/A
53	Pyrofuz	400	16 + 0.3 ND	21	390	N/A	N/A

* Each burning time was measured until onset of the supercooling event.



Figure 3. Burning Time Measurement of Aluminum Particles



Figure 4. Burning Time Measurement of Magnesium Particles




Figure 5. Burning Time Measurement of Zirconium Particles



Figure 6. Burning Time Measurement of Tantalum Particles



Figure 7. Burning Time Measurement of Pyrofuze Particles




Figure 8. Distribution Functions of Burning Time for Al, Mg, Zr, Ta and Pyrofuze (see Table 1).

C. Distribution Functions of Particle Size

The distribution functions of particle sizes of aluminum, magnesium, zirconium, tantalum and pyrofuze as were measured by the quenching technique are shown in Figure 9. The locations of the maxima of the various distribution functions is similar, from 0.125 to 0.175 mm, but the tails are different. For aluminum and magnesium the distribution functions have distinct maxima and the greatest particles are about 0.55 mm. The distribution functions of tantalum and pyrofuze have a long tails extending to a size of 1.85 mm. The distribution function of zirconium is about the same as for aluminum and magnesium.




Figure 9. Distribution Functions of Particle Diameter for Al, Mg, Zr, Ta and Pyrofuze (The same conditions as in Table 1).

D. Summary of Results of Burning Time and Particle Size

The summary of results of burning time and particle size measurements is shown in Table 2.

METAL	BURNING TIME LIMITS [ms]	*t _{MPV} [ms]	PARTICLE SIZE LIMITS [μm]	*D _{MPV} [μm]
Aluminum	2-28	3.75 ± .75	75 - 550	125 ± 25
Magnesium	2-14	3.75 ± .75	75 - 550	175 ± 35
Zirconium	6.5-39.5	25 - 31 ± 1.5	75 - 450	125 ± 25
Tantalum	9.5-91	24 - 50 ± 1.5	75 - 1850	125 ± 25
Pyrofuze	12-97	30 - 50 ± 1.5	75 - 1850	125 ± 25

Table 2 Summary of Results

*MPV - Most Probable Value

IV. DISCUSSION

The distribution functions of burning time of aluminum and magnesium have a distinct maximum for 3.75 ms. The longest burning time for aluminum was 26.5 ms and the longest burning time for magnesium was 14 ms.

Prachukho et. al., [5] measured burning time of 1 ms for 90 μm magnesium particles in water vapor, pressure of 1 ATM and at ambient temperature of 1800°C. Considering our different experimental conditions (about 175 μm particles and pressure of 1.5-2 ATM) and the fact that the burning time increases with the pressure and particle size we can conclude agreement with our results (burning time of 3.75 ms). Ozerov et. al., [6] measured burning time of 18 ms in water-vapor for 120 μm aluminum particles and burning time of 12 ms for 165 μm magnesium particles in Prachukho's conditions and apparatus. These results are slightly longer than our burning time results but are longer than Prachukho's results as well.

The distribution functions of burning time for zirconium, tantalum and pyrofuze are more uniformly distributed over longer burning times than that of aluminum and magnesium, especially those of tantalum and pyrofuze where burning times as long as 95 ms were found. Published literature related to tantalum and pyrofuze burning time was not found. Harrison [8] reported the same qualitative results about zirconium burning time. He suggested that in zirconium there is surface burning of the molten metal instead of burning taking place in the vapor phase in magnesium (and aluminum). We believe that we have the same behavior for tantalum and pyrofuze combustion in steam.

Nelson et. al., [7] and Leibovitz et. al., [3] measured burning time of bigger zirconium and aluminum particles, respectively, by laser heating and found much longer burning times in excess of 200 ms. We believe that the different

heating technique and different particle size were responsible for such a long burning times.

Comparing the distribution functions of burning time to distribution functions of particle size, though measured in two following sets of experiments because of obvious reasons, one can conclude a statistical proportion between burning time and particle size. We believe that for zirconium, tantalum and pyrofuze particles there are missing data for burning times shorter than 8 ms due to using small apertures during the experiments. The apertures were determined according to the exposure range of the films, from one side, and the relatively intense illumination from big burning particles from the other side.

V. REFERENCES

1. A. E. Hallenbeck, Jr., "Preliminary Investigation of Aluminum Combustion in Air and Steam," Thesis, Naval Postgraduate School, March 1983.
2. J. Kol, A. E. Fuhs and M. Berger, "Experimental Investigation of Aluminum Combustion in Steam," Twent, Third AIAA Aerospace Sciences Meeting, AIAA 85-0323, January 1985.
3. L. Leibowitz and L. W. Mishler, "A Study of Aluminum Water Reactions by Laser Heating," Journal of Nuclear Materials 23 (1967), pp. 173-182, North Holland Publishing Company, Amsterdam.
4. H. M. Cassel and I. Liebman, "Combustion of Magnesium Particles", Combustion and Flame, Vol. 6, pp. 153-156, March 1962.
5. V. P. Prachukho, E. S. Ozerov and A. A. Yurinov, "Burning of Magnesium Particles in Water Vapor," Fizika Goreniya i Vzryva, Vol. 7, No. 2, pp. 232-236, April-June 1971.
6. E. S. Ozerov and A. A. Yurinov, "Combustion of Particles of Aluminum-Magnesium Alloys in Water Vapor," Fizika Goreniya i Vzryva, Vol. 13, No. 5, pp. 913-915, 1977.
7. L. S. Nelson, D. E. Rosner, S. L. Kurzius and H. S. Levine "Combustion of Zirconium Droplets in Oxygen/Rare Gas Mixtures-Kinetics and Mechanism," 12th Symposium on Combustion, pp. 59-68, 1969.
8. P. L. Harrison, "The Combustion of Titanium and Zirconium," Seventh (International) Symposium on Combustion, pp. 913-918, Butterworth's Scientific Publications, London, 1959.

DISTRIBUTION LIST

	No. Copies
1. Defense Technical Information Center Cameron Station Alexandria, Virginia 22314	2
2. Library, Code 0142 Naval Postgraduate School Monterey, California 93943	2
3. Department Chairman, Code 67 Department of Aeronautics Naval Postgraduate School Monterey, California 93943	1
4. Distinguished Professor Allen E. Fuhs Code 67Fu Naval Postgraduate School Monterey, California 93943	2
5. Mr. Donald E. Phillips, Code R10A White Oak Laboratory Naval Surface Weapons Center Silver Springs, Maryland 20910	3
6. Dr. Franklin D. Hains, Code R14 White Oak Laboratory Naval Surface Weapons Center Silver Springs, Maryland 20910	1
7. Mr. Wayne K. Reed, Code R14 White Oak Laboratory Naval Surface Weapons Center Silver Springs, Maryland 20910	1
8. Information Services Division, Code X20 White Oak Laboratory Naval Surface Weapons Center Dahlgren, Virginia 22448	1
9. Mr. George Daniello White Oak Laboratory Naval Surface Weapons Center Silver Springs, Maryland 20910	1
10. Captain Robert M. Wellborn, Jr., Director Mark 50 Torpedo Office Naval Sea Systems Command Washington, DC 20360	1

11. Mr. Francis J. Romano, SEA 63R3 1
Naval Sea Systems Command
Washington, DC 20360
12. Dr. William Sykes, Code 175 1
David W. Taylor Naval Ship Research
and Development Center
Bethesda, Maryland 20084
13. Mr. Raymond P. Gogolewski 1
Defense Advanced Research Project Agency
1400 Wilson Boulevard
Arlington, Virginia 22209
14. Mr. Charles Beatty 1
Naval Undersea Center
San Diego, California 92132
15. Professor Forman Williams 1
Princeton University
Princeton, New Jersey 08540
16. LCDR Amos E. Hallenbeck, Jr. 2
3293 Edinburgh Drive
Virginia Beach, Virginia 23452
17. Jonathan L. Minner 1
Naval Surface Weapons Center
Dahlgren, Virginia 22448
18. Zernow Technical Services 1
Attn: Louis Zernow
425 West Bonita
San Dimas, California 91773
19. Dr. Louis Baker, Jr. 1
Argonne National Laboratories
9700 South Cass Avenue
Building 207
Argonne, Illinois 60439
20. Professor Irvin Glassman 1
Department of Mechanical and
Aeronautical Engineering
Princeton University
Princeton, New Jersey 08540
21. R. G. S. Sewell 1
Code 3835
Naval Weapons Center
China Lake, California 93555

22. R. R. Durrell 1
Code R12
Naval Surface Weapons Center
Silver Springs, Maryland 20910
23. LT Jerome Buck 1
USS Goldsborough (DDG-20)
FPO, San Francisco 96666
24. LT John Strott 1
USS Radford (DD-968)
FPO, New York 09586
25. D. R. Kennedy Associates, Inc. 1
4940 El Camino Real, Suite 209
Post Office Box 4003
Mountain View, California 94040
26. Mr. J. M. McNerney 1
Battelle
Columbus Laboratories
505 King Avenue
Columbus, Ohio 43201
27. Dr. G. E. Jensen 1
Chemical Systems Division
United Technology Corporation
Post Office Box 358
Sunnyvale, California 94086
28. Dr. Edward G. Liska 1
Mark 50 Torpedo Office
Naval Sea Systems Command
Washington, DC 20360
29. Mr. Mati Berger 1
Ministry of Defense
P.O. Box 2250
Haifa, Israel
30. Mr. Jacob Kol (88) 1
Ministry of Defense
P.O. Box 2250
Haifa, Israel
31. Professor C. K. Law 1
Department of Mechanical Engineering
University of California at Davis
Davis, CA 95616
32. Mr. Yair Chozev 1
Ministry of Defense
P.O. Box 2250
Haifa, Israel

- | | | |
|-----|--|---|
| 33. | Professor A. Gany
Department of Aeronautical Engineering
Technion
Haifa, Israel | 1 |
| 34. | Dr. Norman Hubele
Mail Stop 1301-R
GPSD
2801 E. Washington
Phoenix, AZ 85034 | 1 |
| 35. | Professor Paul Dimotakis
California Institute of Technology
301-46
Pasadena, CA 91125 | 1 |
| 36. | Research Administration Office
Code 012A
Naval Postgraduate School
Monterey, CA 93943 | 1 |

END

FILMED

10-85

DTIC