

NO 4158 676

METAL CONTACTS ON SEMICONDUCTORS(U) UNIVERSITY COLL
CARDIFF (WALES) R H WILLIAMS 30 APR 86
DAJA45-84-C-0028


171

UNCLASSIFIED

F/G 20/3

NL





DTIC FILE COPY

(2)

METAL CONTACTS ON SEMICONDUCTORS

AD-A195 676

Principal Investigator: Professor R H Williams
 Contractor: University College, Cardiff
 Contract Number: DAJA 45-84-C-0028
 4th Periodic Report: 1st November 1985 - 30th April 1986

The research reported in this document has been made possible through the support and sponsorship of the US Government through its US Army Research and Standardization Group (Europe). ~~This report is intended only for the internal management use of the contractor and the US Government.~~

DTIC
 ELECTE
 JUN 07 1988
 S D



Accession For	
NTIS CRA&I	☒
DTIC TAB	☐
Unannounced	☐
Justification	
By <i>per form 50</i>	
Distribution	
Availability Codes	
Dist	Avail and/or Special
A-1	

DISTRIBUTION STATEMENT A

Approved for public release
 Distribution Unlimited

88 5 17 054

FOURTH INTERIM REPORT

A detailed study has been made of the methods that are used to estimate the magnitude of the Schottky barrier height at metal/semiconductor interfaces. The results of this study have clearly demonstrated that the conventional procedures for extracting the barrier height from a measurement of a diodes I-V characteristics often provide an underestimate. Therefore a new method has been developed for analysing the I-V characteristics. The method correctly takes into account the effects of the recombination generation current, the voltage dependence of the barrier height and the effect of a large series resistance. The barrier height is obtained using a graphical method which utilizes both the forward and reverse biased characteristics. The method has been tested using a recently designed automatic data acquisition system. As a result, the element of subjectivity which is often involved in barrier height measurements has been substantially reduced.

In addition a detailed study has been made of the voltage dependence of the recombination current. In particular the dependence of the recombination currents on the recombination centre spatial and energy distributions. A graphical procedure has been developed for testing the quality of a metal - semiconductor interface and it is envisaged that the technique could be used on a routine basis to test the quality of interfaces fabricated by MBE or MOCVD.

U

Detailed microscopic studies of a number of metals with GaAs and InP clean and oxidised surfaces have also been carried out using photoelectron spectroscopy. These interactions are being related to the Schottky barrier heights measured by I-V and C-V methods. The stability of these contacts as a function of time and temperature is also being probed.

In October 1985, Alistair McLean, the Research Assistant on the grant moved on to another post. We have now appointed Dietrich Zahn to this position and he commenced duties on March 1st, 1986. He is an expert in using Raman spectroscopy to study interfaces and we are setting up to carry out such experiments in our own laboratories. This technique is potentially extremely valuable to study buried surfaces and interfaces.

END

DATED

FILM

8-88
STIC