

AD-A202 955

ORGANIC CHEMISTRY IN TWO DIMENSIONS:
SURFACE-FUNCTIONALIZED POLYMERS AND SELF-ASSEMBLED MONOLAYER FILMSGeorge M. Whitesides* and Gregory S. Ferguson
Department of Chemistry
Harvard University
Cambridge MA 02138

Technical Report No. 9 (September 1988)

Interim Technical Report
(Chemtracts 1988, 1, 171-187)PREPARED FOR DEFENSE ADVANCED RESEARCH PROJECTS AGENCY
1400 Wilson Boulevard
Arlington VA 22209DEPARTMENT OF THE NAVY
Office of Naval Research, Code 1130P
800 North Quincy Street
Arlington VA 22217-5000ARPA Order No.: NR 356-856
Contract No.: N00014-85-K-0898
Effective Date: 85 September 01
Expiration Date: 88 August 31Principal Investigator: George M. Whitesides
(617) 495-9430

The views and conclusions in this document are those of the authors and should not be interpreted as necessarily representing the official policies, either expressed or implied, of the Defense Advanced Research Projects Agency or the U.S. Government.

DTIC
ELECTE
S DEC 07 1988 D
C
E

This document has been approved
for public release and sales in
distribution is unlimited.

88 12 7 047

REPORT DOCUMENTATION PAGE

1a. REPORT SECURITY CLASSIFICATION Unclassified			1b. RESTRICTIVE MARKINGS			
2a. SECURITY CLASSIFICATION AUTHORITY			3. DISTRIBUTION/AVAILABILITY OF REPORT Approved for public release; distribution unlimited			
2b. DECLASSIFICATION/DOWNGRADING SCHEDULE						
4. PERFORMING ORGANIZATION REPORT NUMBER(S) Technical Report 9			5. MONITORING ORGANIZATION REPORT NUMBER(S)			
6a. NAME OF PERFORMING ORGANIZATION Harvard University		6c. OFFICE SYMBOL (If applicable)		7a. NAME OF MONITORING ORGANIZATION Office of Naval Research		
6c. ADDRESS (City, State, and ZIP Code) Office of Sponsored Research Holyoke Center, Fourth Floor Cambridge MA 02138-4993			7b. ADDRESS (City, State, and ZIP Code) Code III30P 800 North Quincy Street Arlington VA 22217-5000			
8a. NAME OF FUNDING/SPONSORING ORGANIZATION ONR/DARPA		8b. OFFICE SYMBOL (If applicable)		9. PROCUREMENT INSTRUMENT IDENTIFICATION NUMBER		
8c. ADDRESS (City, State, and ZIP Code) 800 North Quincy Street Arlington VA 22217-5000			10. SOURCE OF FUNDING NUMBERS			
			PROGRAM ELEMENT NO. 85-K-0898	PROJECT NO. NR 356-856	TASK NO.	WORK UNIT ACCESSION NO.
11. TITLE (Include Security Classification) Organic Chemistry in Two Dimensions: Surface-Functionalized Polymers and Self-Assembled Monolayer Films						
12. PERSONAL AUTHOR(S) George M. Whitesides and Gregory S. Ferguson						
13a. TYPE OF REPORT Interim		13b. TIME COVERED FROM TO		14. DATE OF REPORT (Year, Month, Day) September 1988		
15. PAGE COUNT						
16. SUPPLEMENTARY NOTATION						
17. COSATI CODES			18. SUBJECT TERMS (Continue on reverse if necessary and identify by block number)			
FIELD	GROUP	SUB-GROUP	Self-Assembly, Monolayer, Surface Functionalization, Polymers, Wetting, Interface, Gold, Films. (mg)			
19. ABSTRACT (Continue on reverse if necessary and identify by block number)						
Organic chemistry is largely derived from studies of the reactivity and properties of molecules in homogeneous solution, and much of the intuition of organic chemists is based on the behavior of molecules in solution. Surfaces and interfaces (that is, quasi two-dimensional assemblies of molecules or functional groups) provide environments that can be quite different from those of solutions, and chemical intuition derived from solution is often wrong when applied to processes occurring at surfaces. The central focus of our program in organic surface chemistry is on new science: that is, understanding and controlling the phenomena characteristic of surfaces, interfaces, and thin films. A charm of surface chemistry is, however, its ability to combine new science with relevance to a wide range of technological problems, and we hope to contribute to these applied areas as well.						
20. DISTRIBUTION/AVAILABILITY OF ABSTRACT ☒ UNCLASSIFIED/UNLIMITED ☐ SAME AS RPT. ☐ DTIC USERS			21. ABSTRACT SECURITY CLASSIFICATION			
22a. NAME OF RESPONSIBLE INDIVIDUAL Joanne Milliken			22b. TELEPHONE (Include Area Code)		22c. OFFICE SYMBOL	

19. Abstract (cont'd)

Underlying our program in surface chemistry is a broad interest in the properties of organic surfaces as components of materials. In particular, we hope to develop the ability to rationalize and predict the macroscopic properties of surfaces -- wetting, adhesion, friction -- by knowing their microscopic, molecular-level structures. The issue of structure/property relationships in solids lies at the base of much of the current research in areas such as materials science, condensed matter and device physics, and polymer physical chemistry. Surface science spans these fields, and is currently a research area of particularly great activity. The appeal of surface chemistry as an avenue into detailed understanding of the relations between microscopic and macroscopic properties of matter is that interfaces are more accessible to analysis and more easily modified by synthesis than are the interiors of solids.

Organic chemistry has played a surprisingly small role in interfacial science. Although organic chemistry offers, in principal, the ability to introduce a wide range of functional and structural groups into surfaces, in practice it has been difficult to, much less design and synthesize, ordered two-dimensional arrays of organic moieties. We have taken a physical-organic approach to the study of organic interfacial chemistry: we formulate a hypothesis relating molecular-scale structure to macroscopic property, synthesize and characterize interfaces having structures appropriate to testing that hypothesis, measure the properties of interest, and interpret the information concerning structure and properties in terms of the original hypothesis. The physical-organic paradigm for the study of complex patterns of structure and reactivity is fundamentally a qualitative one, often relying more on analogy than on numerical calculations based on fundamental theory. It has, however, provided one of the most durable and useful methods of understanding complicated systems. Physical-organic chemistry counts among its many successes the correlation of organic structures with reactivities in solution, the rationalization of areas such as photochemistry and catalysis, and the inference of the properties and structures of reactive intermediates; we believe it will also be immensely valuable in understanding surfaces.

Accession For	
NTIS GRA&I	☒
DTIC TAB	☐
Unannounced	☐
Justification	
By	
Distribution/	
Availability Codes	
Dist	Avail and/or Special
A-1	20



ORGANIC CHEMISTRY IN TWO DIMENSIONS: SURFACE-FUNCTIONALIZED POLYMERS AND SELF-ASSEMBLED MONOLAYER FILMS¹

George M. Whitesides and Gregory S. Ferguson,² Harvard University

Organic chemistry is largely derived from studies of the reactivity and properties of molecules in homogeneous solution, and much of the intuition of organic chemists is based on the behavior of molecules in solution. Surfaces and interfaces³ (that is, quasi two-dimensional assemblies of molecules or functional groups) provide environments that can be quite different from those of solutions, and chemical intuition derived from solution is often wrong when applied to processes occurring at surfaces. The central focus of our program in organic surface chemistry is on new science: that is, understanding and controlling the phenomena characteristic of surfaces, interfaces, and thin films. A charm of surface chemistry is, however, its ability to combine new science with relevance to a wide range of technological problems,^{4,5} and we hope to contribute to these applied areas as well.⁶

Underlying our program in surface chemistry is a broad interest in the properties of organic surfaces as components of materials. In particular, we hope to develop the ability to rationalize and predict the *macroscopic* properties of surfaces—wetting, adhesion, friction—by knowing their *microscopic*, molecular-level structures. The issue of structure/property relationships in solids lies at the base of much of the current research in areas such as materials science, condensed matter and device physics, and polymer physical chemistry. Surface science spans these fields and is currently a research area of particularly great activity.^{5,7-26} The appeal of surface chemistry as an avenue into detailed understanding of the relations between microscopic and macroscopic properties of matter is that interfaces are more accessible to analysis and more easily modified by synthesis than are the interiors of solids.


Organic chemistry has played a surprisingly small role in interfacial science.²⁷ Although organic chemistry offers, in principal, the ability to introduce a wide range of functional and structural groups into surfaces, in practice it has been difficult to rationalize, much less design and synthesize, ordered two-dimensional arrays of organic moieties.²⁸ We have taken a physical-organic approach to the study of organic interfacial chemistry: We *formulate a hypothesis re-*

CHEMTRACTS—ORGANIC CHEMISTRY 1:171-187 (1988)
0895-4445/88/\$4.00 © 1988 Chemtracts

lating molecular-scale structure to macroscopic property, *synthesize and characterize interfaces* having structures appropriate to testing that hypothesis, *measure the properties* of interest, and *interpret the information* concerning structure and properties in terms of the original hypothesis. The physical-organic paradigm for the study of complex patterns of structure and reactivity is fundamentally a qualitative one, often relying more on analogy than on numerical calculations based on fundamental theory. It has, however, provided one of the most durable and useful methods of understanding complicated systems. Physical-organic chemistry counts among its many successes the correlation of organic structures with reactivities in solution, the rationalization of areas such as photochemistry and catalysis, and the inference of the properties and structures of reactive intermediates;²⁹ we believe it will also be immensely valuable in understanding surfaces.

SYNTHESIS OF SURFACES AND INTERFACES

We have relied on two separate types of experimental systems in our studies (Scheme 1):




1. Surface-Functionalized Organic Polymers, Especially "Polyethylene Carboxylic Acid" (PE-CO₂H). These systems are prepared by oxidizing polyethylene (PE) films with chromic acid and using the carboxylic acid groups introduced onto the surface as the starting point for more elaborate chemical modification (Scheme 1).³⁰⁻³⁶ The chromic acid oxidation has the advantages of restraining the functionality to a very thin (less than 10 Å in depth) layer along the surface contour of the polymer and of generating a set of functionalities limited to carboxylic acids and ketones and/or aldehydes. PE-CO₂H is convenient to prepare and study and is an excellent material for exploratory studies. It also provides an entry into the examination of properties repre-

sentative of a "real" material. It is, however, a complex, microscopically heterogeneous and structurally ill-defined material.³⁷

2. Self-Assembled Adsorbed Monolayer Films.^{38,39} We and others have focused on two classes of monolayers: organosulfur compounds (especially organic thiols) adsorbed on gold,^{35,40-48} and alkyl siloxane monolayers prepared by reaction of alkyl trichlorosilanes with surfaces containing hydroxyl groups and/or adsorbed water.⁴⁹⁻⁵² Both of these systems, and others related to them, are excellent models for interpreting the characteristics of PE-CO₂H and its derivatives. Immersion of a silicon wafer coated with a thin film (~1000 Å) of evaporated gold in a solution of a fatty thiol for 1 hour at room temperature results in the formation of a highly ordered, quasicrystalline monolayer of fatty thiol attached to the gold surface by sulfur-gold coordination (Scheme 1). The essential processes occurring during the adsorption and organization of the thiol on the gold surface are still incompletely understood, but they are certainly related to the familiar, if complex, coordination chemistry of thiols and gold(0) or gold(I).^{53,54}

One of the most attractive features of organic chemistry is the wide variation in the structure of organic molecules that can be produced through synthesis. A challenge to our program in organic surface chemistry has been to bring these synthetic techniques to bear on two separate classes of problems in surface chemistry: first, the introduction of small fragments having desired functionality onto surfaces through chemical reaction; second, the preparation/assembly of these fragments in extended macroscopic arrays with control over position and orientation. The two approaches we have followed—one leading to PE-CO₂H and its derivatives, and the other to self-assembled organic monolayers—are quite different. The former introduces functional groups onto a preformed heterogeneous material (Scheme 2). This procedure is convenient and experimentally relevant to a broad range of polymer technologies, but it requires the study and analysis of materials that are intrinsically structurally ill-defined. The latter prepares well-defined, appropriately func-



tionalized molecules, which are then allowed to self-assemble on a reactive surface and form highly ordered two-dimensional structures. Self-assembly will, we believe, become a mainstay of ordered monolayer formation,^{5,55} and will eventually prove invaluable in rational strategies for modification of the properties of interfaces. Preparing these systems is, however, experimentally more complex than generating functionalized polymer surfaces.

CHARACTERIZATION OF SURFACES

We have used the usual array of spectroscopic techniques to characterize surfaces: attenuated total reflectance-infrared (ATR-IR) and polarized infrared external reflective spectroscopy (PIERS), X-ray photoelectron spectroscopy (XPS), electron spin resonance (ESR), fluorescence, electron microscopy, and ellipsometry are all useful (Table). We have, however, also

Table. Selected Methods for Analysis of Surfaces and Interfaces


Technique	Application and Depth Sensed
Scanning tunneling microscopy (STM)	Individual atomic positions on surfaces
Low-angle X-ray scattering	Electron density map of the surface of very flat solids
Electron microscopy (SEM, TEM); electron diffraction	Surface morphology and degree of crystalline order
Contact angle (H ₂ O)	Polarity of top ~10 Å
X-ray photoelectron spectroscopy; (XPS); auger spectroscopy	Atomic and chemical composition of top ~50 Å
Ellipsometry	Determination of film thickness with a resolution of 2 Å
Attenuated total reflectance-infrared (ATR-IR)	Vibrational analysis of top ~1000 Å
Polarized infrared external reflective spectroscopy (PIERS)	
Rutherford backscattering (RBS)	
	Atomic composition as a function of depth with resolution of hundreds of Å
Fluorescence spectroscopy	Assay for density of functionality after covalent attachment of fluorescent probes
Electron spin resonance (ESR) spectroscopy	Location and mobility of paramagnetic centers (e.g., TMPO) in interfaces

been able to apply to problems in the physical-organic chemistry of surfaces two techniques for characterization that are less familiar to the spectroscopic community. The first is the measurement and interpretation of liquid-solid contact angles. This technique has proven to be the most surface-sensitive and most convenient (if not the most easily interpreted) method that we have available to characterize organic interfaces.^{30-35,40,41} It is especially useful in characterizing the solid-water interface. The second technique involves studies of chemical reactivity at interfaces. This approach is especially useful when applied using simple, high-yield reactions that are well understood in homogeneous, liquid phase chemistry. Ionization and esterification of carboxylic acids and saponification of carboxylic acid esters are especially diagnostic.³⁴

The combination of measurement of contact angle with studies of ionization of functional groups has resulted in a technique we call "contact angle titration": that is, study of the variation in the contact angle with the pH of the

aqueous drop (Scheme 3). This technique increases the information derived from the measurement of contact angles. Traditional approaches to studying contact angle generate only two numbers (the advancing contact angle θ_a and the receding contact angle θ_r).⁵⁶ Receding contact angles are presently very difficult to interpret. Efforts to characterize complex, heterogeneous interfaces using only advancing contact angles are unlikely to be very broadly useful. By measuring contact angle *as a function of pH*, however, one can often infer the existence, environment, and nature of ionizable groups present at the interface.

Contact angle titration is based on the observation of variations in contact angle with pH at surfaces containing ionizable groups.⁵⁵ This variation plau-




Scheme 3. Dependence of θ_a on pH for surface-functionalized polyethylene film. *Top:* Using unbuffered aqueous solutions. Buffers: ($\square$) 0.1 M phosphate buffer; ($\circ$) all others (0.05 M), pH 1, 0.1 N HCl; pH 2, maleic acid; pH 3, tartaric acid; pH 4, succinic acid; pH 5, acetic acid; pH 6, maleic acid; pH 7 and 8, HEPES; pH 9 and 10, CHES; pH 11, triethylamine; pH 12, phosphate; pH 13, 0.1 N NaOH. The crosshatched and labeled "assorted buffers" at pH 8 include data for phosphates MOPS, HEPES, TAPS, TRIS, and triethanolamine.

sibly reflects ionization of the functional group: The charged form of an acid or base is more hydrophilic than the uncharged form, and the contact angle with water is lower. Although this simple explanation is fundamentally correct, and the technique is a very useful one in comparing acidities, its simplicity hides a number of complexities.^{32,33}

One interesting aspect of contact angle titration concerns the intuitive concept of the "quantity" of a functional group present at an interface. Our initial intuition concerning surface functional group chemistry was that, in most systems likely to be studied experimentally, the number of functional groups present on a representative area of surface would be small compared with the quantity of a reagent present in the volume of solution used in experiments on that surface. This belief is largely incorrect for measurements of contact angles: The number of functional groups present at high density on a surface is comparable to that present in solutions used for contact angle titration in unbuffered systems. The difference between the titration curves obtained using buffered and unbuffered solutions (Scheme 3) exemplifies the phenomenon.³²

Explanation of this observation helps to clarify the concept of "concentration" in a heterogeneous system consisting of a surface and a contacting liquid phase. We consider the spreading of an aqueous drop at an interface to be determined in part by the extent of ionization of the functionality present at that interface. Let us examine the "concentration" of this functionality in a system consisting of a 1- μ l drop in contact with a derivatized polyethylene surface (a 1- μ l drop typically covers an area of ~ 1 mm²). The density of functional groups on the surface can be in the order of 6×10^{14} /cm² for a surface with typical roughness;³³ at this density, the concentration of reagent in solution in the contacting drop required to react stoichiometrically with that functionality is ~ 0.1 mM.³⁷ For an unbuffered aqueous solution and a monoprotic acid/base reaction, a concentration of acid or base > 0.1 mM (i.e., pH < 4 or pH > 10) is thus required to achieve a stoichiometric reaction. Clearly, the difference in contact angle titration curves obtained using buffered and unbuffered solutions is due to surface functionality that is itself sufficiently concentrated in the system comprising surface and drop to buffer the pH of the aqueous solution in the range pH 5–9. Thus, the qualitative idea that a monolayer of organic functionality is insignificantly small in quantity compared with the functionality present in solution is incorrect, if one is concerned with small volumes of solution.

A second interesting issue concerns the detailed interpretation of the contact angle titration curves. In particular, we ask how should the solid–liquid interfacial free energy γ_{SL} be related to the functional groups present on the surface? The fundamental relation connecting the contact angle to interfacial free energy terms is Young's equation (Eq. 1).³⁸



$$\cos \theta = \frac{\gamma_{SV} - \gamma_{SL}}{\gamma_{LV}} \quad (1)$$

For aqueous solutions constituted with appropriate buffers, the liquid-vapor interfacial free energy γ_{LV} is the same as that for pure water. Variations in interfacial free energies are thus related to the observed value of θ primarily by the terms γ_{SV} and γ_{SL} . These terms, in turn, depend on a number of factors: the type, density, and distribution of functional groups present at the solid-vapor (liquid) interface; their extent of ionization; the roughness of the surface; the relative humidity of the vapor.

As a first approximation, we have proposed that the interfacial free energy can be expressed as a linear combination of functional group contributions, multiplied by the normalized fraction β_i of these groups on the surface^{32,34} (Eq. 2). The parameters $\gamma_{i,SL}$ and $\gamma_{i,SV}$ reflect intrinsic

$$\gamma_{SL} = \sum_i \beta_i \gamma_{i,SL} \quad (2a)$$

$$\gamma_{SV} = \sum_i \beta_i \gamma_{i,SV} \quad (2b)$$

hydrophilicity and group size or area. Comparisons of infrared spectroscopic data with contact angles indicate that this type of analysis is approximately




Figure. Schematic representation of an ideal (top left) and real (top right, bottom) drop of liquid (L) in contact with a solid (S) and vapor (V) with contact angle θ . The symbols in the upper right picture represent (○) water molecules, (Δ) dissolved solutes (phosphate, buffer salts), ($\diamond$, $\ominus$) polar surface groups (CO_2H , CO_2^- , $\text{C}=\text{O}$, ...), ($\blacksquare$) nonpolar surface groups (CH_2 , CH_3 , ...). A lip of liquid (bottom; not drawn to scale), the "precursor film," extends microns beyond the edge of the drop in certain circumstances.

correct for PE-CO₂H and some of its acidic derivatives,³² but that interactions between groups, and perhaps interfacial heterogeneity, make the problem more complex than can be described completely using this simple approach.³⁵ An understanding of these interactions and complexities remains to be established.

A third important issue is the meaning of hysteresis in the measurement of contact angles. For derivatives of PE-CO₂H, θ_a appears to provide a simple, semiquantitatively interpretable measure of interfacial group character and density. Contact angles are, however, a simple parameter derived from observations of a complex reality (Figure). Advancing and receding contact angles differ on many surfaces, and all the derivatives of PE-CO₂H (particularly polar derivatives) display very large hystereses in their contact angles: θ_r is frequently 0 even for systems having fairly large values of θ_a . Large hysteresis is usually interpreted to indicate a heterogeneous system far from thermodynamic equilibrium.³⁹ Yet analyses of θ_a based on Young's equation, an equation assuming thermodynamic equilibrium, seem to give interpretable and reasonable results. It is not clear how one should treat a system that is not at thermodynamic equilibrium, but for which physical measurements correlate with those expected based on physical-organic analogies to processes occurring at equilibrium in solution.


RESULTS

Both functionalized polyethylene and its derivatives, and self-assembled monolayer films, provide systems with which to examine reactions occurring at interfaces and to test hypotheses concerning structure/reactivity and structure/property relationships. In so doing, we find that many of the results we obtain can be rationalized by analogy to phenomena in solution (often with characteristic differences that can be interpreted to compare and contrast the environments provided by homogeneous solutions and interfaces). We also frequently encounter unexpected phenomena, which suggest that any models of organic reactivity at interfaces, based exclusively on analogies with solution, are not complete. The studies that follow provide examples.

Surface Acidities. Scheme 3 indicates that carboxylic acids and many, but not all, amines show inflections in plots of θ_a vs the pH of the drop used in measuring the contact angle.^{32,35} Assuming that the midpoint of the inflection corresponds to half-ionization of the functional group (an assumption supported by independent ATR-IR measurements on carboxylic acid surfaces),³² we infer that acidities of functional groups at an interface and in solution are very different. For example, the value of pH for a solution in contact with a surface required to achieve half-ionization of the carboxylic acid groups at that surface can be as high as 12. What is the origin of this very large apparent decrease in acidity of carboxylic acids (and corresponding increase in the apparent acidity of ammonium ions)? We believe that the origin of these shifts can ultimately be attributed to the locally low dielectric constant at the polyethylene-water interface,^{32,35,40} but rationalization of these anomalous values of pK_a is not yet complete.


Relations between Functional Group Hydrophilicity and Wettability of Interfaces. We assumed at the outset of our studies that more hydrophilic interfacial groups (as measured by some convenient parameter such as the Hansch π parameter⁴¹) would lead to more wettable surfaces. In fact, experimental observations relating wettability to functional group hydrophilicity

differ significantly from those expected (Scheme 4). As the value of π for the functional group on the surface decreases, θ_a also decreases, but only up to a point. Beyond that point, further increases in functional group hydrophilicity result in no further increase in wettability: that is, the hydrophilicity of the surface "saturates."³⁵ We postulate that the origin of this effect lies in condensation of water vapor at polar solid-vapor interfaces (Scheme 5). Nonpolar interfaces condense relatively little water. All of our experiments involving contact angles with water are carried out at 100% relative humidity in order to assure that the system is as close to thermodynamic equilibrium as possible. Polar functional groups at interfaces are undoubtedly associated with hydrating water adsorbed from the vapor phase. We postulate that, beyond a certain value of the Hansch π parameter, the polar surface functional groups become completely surrounded by condensed, hydrating water, producing a solid-vapor interface whose polarity is essentially independent of the underlying functional group. Under these circumstances, the wettability of the surface is determined primarily by the area fraction of the surface converted to polar functionality, and then hydrated by condensed water.



These observations and interpretations imply the existence of a thin, condensed water film on polar surfaces. The nature of this film, and especially the relation of its structure to that of bulk water, remains an important and complex problem.

The Range of Interactions Determining Wetting. Scheme 4 displays an astonishing observation: Although a surface incorporating amides (PE-CONH₂) is relatively hydrophilic, the analogous primary amide PE-CONHC₃H₇ is more hydrophobic than unfunctionalized polyethylene. Some of the apparent hy-




Scheme 5. Schematic illustration of the degree of hydration of a functional group P at the solid-vapor interface. When P is nonpolar, the equilibrium lies to the left; when P is polar, it lies to the right.


drophobicity of PE-CONHC₃H₇, and its analogs undoubtedly reflects the microscopic roughness of the surface of these materials (generated during the oxidative surface functionalization). Nonetheless, we find that it takes only a small hydrophilic or hydrophobic group to determine the wettability of a surface. Furthermore, a small hydrophobic group is capable of completely masking an underlying, intrinsically hydrophilic core functionality. Thus, for example, replacement of a terminal CH₃ group in one of the well-defined, self-assembled monolayer systems by a CH₂OH group changes the monolayer from being very hydrophobic to very hydrophilic,⁴¹ and reacylation of the terminal hydroxyl (CH₂OCOR) once again makes it very hydrophobic. The interactions that determine macroscopic wettability are, apparently, very short in range.¹⁰ We believe, in fact, that measurement of contact angle is the most surface-sensitive technique presently available for examining the solid-liquid interface. The great advantages of wetting as a probe of surface structure (relative, for example, to XPS) are that its measurement is very simple, convenient, and inexpensive, and that it is intrinsically applicable to the solid-liquid interface and to heterogeneous, noncrystalline surfaces. Its disadvantages are that contact angle measurements are information poor, that they require a liquid-solid interface, and that their physical basis is complex and still incompletely understood.

Designed Interfaces. The materials PE-CO-X are convenient but heterogeneous. The best characterized and structurally best defined organic interfaces now available are those formed by adsorbing long-chain alkyl thiols on gold, or by allowing long-chain alkyl trichlorosilanes to react with surface hydroxyl groups and adsorbed water present on the surface of glass or silica. Both of these systems have the alkyl groups in completely *trans*-extended conformations, provided that the terminal functional group is relatively small. For organic thiols on gold, the chains are tilted ~30° from the normal to the metal surface;^{42,45} for alkyl siloxanes on silicon/silicon dioxide, they are approximately perpendicular to the substrate surface (Scheme 6).⁵⁰ Transmission electron microscopy indicates that the thiol/gold system has at least microcrystalline order in the plane of the monolayer.⁴²

These ordered monolayer systems permit an exquisite degree of control over structure and dimensionality at the interface. As one example, consider a monolayer formed by adsorption of HS(CH₂)₁₉OH on gold. Formation of such a monolayer is experimentally very straightforward: one simply dips the gold-coated substrate into a solution of the α,ω -thioalcohol in a solvent such as acetonitrile for 1 hour at room temperature, withdraws it, and washes it briefly. At the conclusion of this procedure, the entire accessible surface of



Scheme 6. Schematic illustration of conformation and packing order in monolayers of organic thiols on gold and alkyl siloxanes on silicon/silicon dioxide. The monolayer is composed of three important regions: the head groups (portion binding to solid substrate), the polymethylene chains (for formation of van der Waals surface), and the tail groups (terminal functionality that determines the character of the solid-liquid and solid-vapor interfaces).



Scheme 7. Stylized illustrations of monolayer structures.⁴¹ Proposed structures of (A) pure monolayer of $\text{HS}(\text{CH}_2)_{19}\text{OH}$; (B) monolayer composed of 50% $\text{HS}(\text{CH}_2)_{19}\text{OH}$ and 50% $\text{HS}(\text{CH}_2)_{11}\text{OH}$; (C) pure monolayer of $\text{HS}(\text{CH}_2)_{11}\text{OH}$. Structures we believe do not occur in the systems studied here: (D) disordered monolayer and (E) monolayer containing a mixture of components and showing phase separation into islands.

the gold is covered with a uniform monolayer 23 Å thick, and the exposed surface is a densely packed monolayer of hydroxyl groups. The thickness of the monolayer is easily controlled at the scale of angstroms by varying the number of methylene groups in the thiol chain; the surface properties are independently controllable through variations in the terminal functional group. If mixtures of two different terminally functionalized thiols are used, monolayers can be made having the two mixed on the surface (Scheme 7).

CURRENT PROBLEMS

The physical-organic chemistry of surfaces promises to provide new materials based on rational synthetic modification of surfaces and interfaces, new analytical methods with which to characterize surfaces, and deeper levels of understanding of familiar processes such as dissolution, wetting, adsorption, and adhesion occurring at interfaces and in solutions. The phenomena being observed are, however, usually more complex than those occurring in homogeneous solution, and are, consequently, still incompletely understood at even the simplest levels. The field presents a number of fascinating fundamental problems in interfacial chemistry, among which we place the following:

1. **Molecular-Level Order.** How should the order in these systems be defined and measured? One advantage of a two-dimensional system is that it is, in principle, less complex structurally than a three-dimensional system: The components of a two-dimensional system are by definition restricted to a plane rather than free to translate and rotate in three dimensions. In practice, however, the problem of defining order in surface-functionalized polymers and self-assembled monolayers remains very complex. All of these systems are, in reality, only quasi two-dimensional. Materials such as functionalized polyethylene are obviously microscopically rough and heterogeneous and have functionality distributed nonuniformly in a thin interfacial layer. Contact of these systems with a liquid phase may result in interfacial swelling and reconstruction. Self-assembled monolayers are better defined structurally, but even with these systems, subtle issues of order in the plane of the monolayer, at the gold-monolayer and monolayer-liquid interfaces and between adjacent organic molecules require the development of new analytical techniques and new criteria for order.
2. **Kinetics vs Thermodynamics.** The extent to which any of the systems currently studied are at thermodynamic equilibrium, and the influence of departures from equilibrium on their behavior, is almost completely uncertain at present.
3. **Wetting.** Despite interesting and provocative theoretical contributions to the theory of wetting in certain idealized systems,^{9,62-78} there is no usefully detailed theory of wetting relevant to real, microscopically heterogeneous surfaces. The current rationalization of hysteresis in the measurement of contact angles is especially unsatisfactory. Detailed examination of hysteresis, both theoretically and experimentally would be particularly useful, because hysteresis appears to be very sensitive to order; an understanding of the relation between interfacial structure and hysteresis might provide a new avenue of approach to this important subject.
4. **Molecular Design of Monolayers.** Essentially all work so far carried out with self-assembled monolayers has focused on derivatives of fatty

acids. These systems have the two virtues that they are easy to manipulate synthetically and that they do, for whatever reason, form well-ordered monolayers. They are, however, not stable at even modestly elevated temperatures and have no strong intermolecular interactions contributing to order in the plane of the monolayer or to thermal or oxidative stability. It is important to develop molecular structures other than fatty acids that form ordered, stable two-dimensional sheet structures.

CONCLUSIONS

Organic chemistry at interfaces is a field offering major opportunities for both the conduct of basic science and the development of new technology. It also provides, through the synthesis of extended functionalized interfaces, a bridge between the science of isolated molecules and the science and technology of materials. Since chemical reactivity and wettability provide what we believe will prove to be invaluable probes of interfacial structure for organic systems, these systems are particularly attractive for studies aimed at understanding the characteristics of solid-liquid interfaces.

Surface-functionalized polymers (of which the best developed is PE-CO₂H) are proving to be convenient systems with which to conduct exploratory work. They are easily prepared and manipulated, and because they present solid-vapor interfaces that have low surface free energies, they are relatively resistant to contamination by atmospheric contaminants. Further, since they are physically robust, surface-modified polymers can be used to examine complex materials problems such as biocompatibility,^{79,80} adhesion,³¹ gas permeation,³² friction,³³ and the influence of bending, stretching,³⁴ and surface reconstruction³⁵ on interfacial properties.

Self-assembled monolayers will, we believe, prove to be the ultimate cornerstone of the basic science in organic surface chemistry. They will certainly also find technological application in areas such as promotion of adhesion, inhibition of corrosion, and control of friction, and they may prove important in the production of sensors and microelectronic devices. The remarkable ease with which very complex monolayer structures can be assembled from molecules of very modest complexity will be invaluable in studying the properties of organized molecular assemblies. The best defined of these systems is presently obtained by adsorption of ω -functionalized fatty thiols on gold, although organosilicon compounds on silicon dioxide and glass may ultimately prove equally ordered. Alkyl thiols on gold have as their major advantage the compatibility of the thiol moiety with a wide range of organic functional groups, and the fact that these systems lead to highly ordered monolayers. Silanes on silica are more economical, better adapted to the formation of multilayer structures, and more robust structurally.

Given the astonishing sensitivity of wettability to local surface structure, its study should provide a range of important new types of information about interfaces, especially solid-liquid interfaces. Designing and interpreting these experiments will require a physical-organic approach—the systems being studied are too complex to be defined using conventional, spectroscopy-based physical chemistry. Because wetting is directly relevant to a broad range of technological problems, these studies should be exceptionally valuable in applications. The experimental techniques required to study wetting are very simple. Surface science based on studies of wettability should thus be accessible even to those without routine access to the instrumentation of high-

vacuum physics. A more realistic theoretical basis for wetting is desperately needed. Current treatments do not deal adequately with subjects such as molecular-scale heterogeneity, hysteresis, deviations from thermodynamic equilibrium, and the nature of the interactions between solids and liquids.

ACKNOWLEDGMENTS

The research carried out in our group has been the result of skilled experimentation and of thoughtful and creative design and interpretation by a number of individuals, including Jim Rasmussen, Randy Holmes-Farley, Tom McCarthy, Colin Bain, Barry Troughton, Paul Laibinis, Hans Biebuyck, Lou Strong, Stephen Wasserman, and Louis M. Scarmoutzos. We are also grateful to our colleagues Peter Pershan (Division of Applied Science, Harvard), Ralph Nuzzo (AT&T Bell Laboratories), and Mark Wrighton (MIT) for important contributions to our understanding of surfaces.

REFERENCES AND NOTES

1. The work described in this paper was supported in part by the Office of Naval Research and the Defense Advanced Research Projects Agency, and by the NSF through grants to GMW (CHE 85-08702) and to the Harvard Materials Research Laboratory (DMR 86-14003).
2. NIH Postdoctoral Fellow, 1988-1989.
3. The words "surface" and "interface" have clearly defined meanings only in the context of an ideal system, a liquid and vapor in contact with a smooth, homogeneous solid. In the real systems discussed here (especially functionalized polyethylene films), these words should be understood as indicating the more complicated notion of an "interphase region," which incorporates the complexities (roughness, inhomogeneity, surface reconstruction and swelling, etc.) inevitably encountered.
4. Armstrong, J.A., Whitesides, G.M. *Chem. Eng. News*, 1986, 64, 22; *Research Briefings 1986*, National Academy of Science: Washington, DC, 1986; *Proc. Natl. Acad. Sci. USA*, 1987, 84, 4665.
5. Swalen, J.D., Allara, D.L., Andrade, J.D., Chandross, E.A., Garoff, S., Israelachvili, J., McCarthy, T.J., Murray, R., Pease, R.F., Rabolt, J.F., Wynne, K.J., Yu, H. *Langmuir* 1987, 3, 932.
6. Holmes-Farley, S.R., Troughton, E.B., Whitesides, G.M., unpublished results.
7. Golovchenko, J.A. *Science*, 1986, 232, 48; Tromp, R.M., Hamers, R.J., Demuth, J.E. *Science*, 1986, 234, 304; Noonan, J.R., Davis, H.L. *ibid.*, 310; Madey, T.E. *ibid.*, 316; Engel, T. *ibid.*, 327; Celotta, R.J., Pierce, D.T. *ibid.*, 333; Comizzoli, R.B., Frankenthal, R.P., Milner, P.C., Sinclair, J.D. *ibid.*, 340.
8. Somorjai, G. *Chemistry in Two Dimensions: Surfaces*, Cornell University Press: Ithaca, New York, 1981; Gaines, G.L. *Insoluble Monolayers at Liquid-Gas Interfaces*; Interscience: New York, 1966.
9. Adamson, A.W. *Physical Chemistry of Surfaces*; John Wiley & Sons: New York, 1982.
10. Israelachvili, J. *Intermolecular and Surface Forces*; Academic: London, 1985.
11. Israelachvili, J. *Proc. Natl. Acad. Sci. U.S.A.* 1987, 84, 4722; Israelachvili, J. *Acc. Chem. Res.*, 1987, 20, 415, and references therein.
12. Garoff, S. *Proc. Natl. Acad. Sci. U.S.A.* 1987, 84, 4729, and references therein.
13. Rabolt, J.F. *MRS Bulletin*, 1987, November 16/December 31, 39.
14. Dubois, L.H., Zegarski, B.R., Nuzzo, R. G. *Proc. Natl. Acad. Sci. U.S.A.* 1987, 84, 4739.
15. Adams, N.K. *Adv. Chem. Ser.*, 1964, No. 43, 52; Adamson, A.W., Ling, I. *Adv. Chem. Ser.*, 1964, No. 43, 57.
16. Ishida, H. *Rubber Chem. Tech. Rev.*, 1987, 60, 497; Debe, M.K. *Prog. Surf. Sci.*, 1987, 24, 1.

17. Dierker, S.B., Murray, C.A., Lefrange, J.D., Schlotter, N.E. *Chem. Phys. Lett.*, **1987**, *137*, 453; Rabe, J.P., Swalen, J.D., Rabolt, J.F. *J. Chem. Phys.*, **1987**, *86*, 1601; Rabolt, J.F., Burns, F.C., Schlotter, N.E., Swalen, J.D. *J. Chem. Phys.*, **1983**, *78*, 946; Rothberg, L., Higashi, G.S., Allara, D.L., Garoff, S. *Chem. Phys. Lett.*, **1987**, *133*, 67.
18. Langmuir, I. *J. Am. Chem. Soc.*, **1917**, *39*, 1848; Blodgett, K.B. *J. Am. Chem. Soc.* **1935**, *57*, 1007; Blodgett, K.B., Langmuir, I. *Phys. Rev.* **1937**, *51*, 964; for more recent reviews of Langmuir-Blodgett systems, see: Blinov, L.M. *Russian Chem. Rev.* **1983**, *52*, 713; Roberts, G.G. *Adv. Phys.* **1985**, *34*, 475; Proceedings of the Second International Conference on Langmuir-Blodgett Films, in *Thin Solid Films*, **1985**, vols. 132, 133, 134.
19. Sugi, M. *J. Mol. Electronics*, **1985**, *1*, 3.
20. Allara, D.L., Nuzzo, R.G., *Langmuir* **1985**, *1*, 45, 52.
21. Hubbard, A.T. *Acc. Chem. Res.* **1980**, *13*, 177.
22. Soriaga, M.P., Stickney, J.L., Hubbard, A.T. *J. Mol. Catal.* **1983**, *21*, 211.
23. Bard, A.J. *J. Chem. Ed.* **1983**, *60*, 302.
24. Faulkner, L.R. *Chem. Eng. News* **1984**, *62*, 28.
25. Li, T.T.-T., Liu, H.Y., Weaver, M.J. *J. Am. Chem. Soc.* **1984**, *106*, 1233; Li, T.T.-T., Weaver, M.J. *J. Am. Chem. Soc.* **1984**, *106*, 6107.
26. Mori, K., Watanabe, A., Muroi, A., Nakamura, Y. *J. Polymer Sci.: Part A: Polymer Chem.* **1987**, *25*, 2893.
27. Fendler, J.H. *Chem. Rev.*, **1987**, *87*, 877; Ringsdorf, H., Schlarb, B., Venzmer, J. *Angew. Chem. Int. Ed. Eng.* **1988**, *27*, 113.
28. Lahav, M., Addadi, L., Leiserowitz, L. *Proc. Natl. Acad. Sci. U.S.A.* **1987**, *84*, 4737, and references therein.
29. Lowry, T.H., Richardson, K.S. *Mechanism and Theory in Organic Chemistry*, 3rd ed., Harper and Row: New York, 1987.
30. Rasmussen, J.R., Stedronsky, E.R., Whitesides, G.M. *J. Am. Chem. Soc.* **1977**, *99*, 4736.
31. Rasmussen, J.R., Bergbreiter, D.E., Whitesides, G.M. *J. Am. Chem. Soc.* **1977**, *99*, 4746.
32. Holmes-Farley, S.R., Reamey, R.H., McCarthy, T.J., Deutch, J., Whitesides, G.M. *Langmuir* **1985**, *1*, 725.
33. Holmes-Farley, S.R., Whitesides, G.M. *Langmuir* **1986**, *2*, 266.
34. Holmes-Farley, S.R., Whitesides, G.M. *Langmuir* **1987**, *3*, 62.
35. Holmes-Farley, S.R., Bain, C.D., Whitesides, G.M. *Langmuir*, in press, 1988.
36. For a similar procedure on polypropylene, see Lee, K.-W., McCarthy, T.J. *Macromolecules* **1988**, *21*, 309.
37. The surface region of PE-CO₂H is rough on both the molecular and macroscopic scales. It is an ill-defined combination of carboxylic acids, ketones and/or aldehydes, and methylene groups. Whether heterogeneity exists on a larger scale of length, owing to uneven functionalization between crystalline and amorphous regions, is unknown. The surface region swells to varying degrees, depending on the contacting solvent, and reconstructs on heating below the melting point.
38. Bigelow, W.C., Pickett, D.L., Zisman, W.A. *J. Colloid Sci.* **1946**, *1*, 513.
39. Zisman, W.A. *Adv. Chem. Ser.* **1964**, *43*, 1.
40. Troughton, E.B., Bain, C.D., Whitesides, G.M., Nuzzo, R.G., Allara, D.L., Porter, M.D. *Langmuir* **1988**, *4*, 365.
41. Bain, C.D., Whitesides, G.M. *Science* **1988**, *240*, 62.
42. Strong, L., Whitesides, G.M. *Langmuir*, in press, 1988.
43. Nuzzo, R.G., Fusco, F., Allara, D.L. *J. Am. Chem. Soc.*, **1987**, *109*, 2358; Nuzzo, R.G., Allara, D.L. *J. Am. Chem. Soc.*, **1983**, *105*, 4481.
44. Nuzzo, R.G., Zegarski, B.R., Dubois, L.H. *J. Am. Chem. Soc.* **1987**, *109*, 733.

45. Porter, M.D., Bright, T.B., Allara, D.L., Chidsey, C.F.D. *J. Am. Chem. Soc.* **1987**, *109*, 3559.
46. Sundgren, J.E., Bodoe, P., Invarsson, B., Lundstroem, I.J. *J. Colloid Interface Sci.* **1986**, *113*, 530.
47. Finklea, H.O., Avery, S., Lynch, M., Furtch, T. *Langmuir* **1987**, *3*, 409.
48. Diem, T., Czajka, B., Weber, B., Regen, S.L. *J. Am. Chem. Soc.* **1986**, *108*, 6094.
49. Haller, I. *J. Am. Chem. Soc.* **1978**, *100*, 8050.
50. Sagiv, J. *J. Am. Chem. Soc.* **1980**, *102*, 92; Gun, J., Iscovici, R., Sagiv, J. *J. Colloid Interface Sci.* **1984**, *101*, 201; Netzer, L., Iscovici, R., Sagiv, J. *Thin Solid Films* **1982**, *99*, 235; Maoz, R., Sagiv, J. *J. Colloid Interface Sci.* **1984**, *100*, 465; Gun, J., Sagiv, J. *J. Colloid Interface Sci.* **1986**, *112*, 457; Pomerantz, M., Segmuller, A., Netzer, L., Sagiv, J. *Thin Solid Films* **1985**, *132*, 153; Cohen, S.R., Naaman, R., Sagiv, J. *J. Phys. Chem.* **1986**, *90*, 3054.
51. Finklea, H.O., Robinson, L.R., Blackburn, A., Richter, B., Allara, D., Bright, T. *Langmuir* **1986**, *2*, 239.
52. Tillman, N., Ulman, A., Schildkraut, J.S., Penner, T.L. *J. Am. Chem. Soc.*, in press, 1988.
53. Puddephatt, R.J. *Chemistry of Gold*, Elsevier: Amsterdam, 1978; Blower, P.J., Dilworth, J.R. *Coord. Chem. Rev.* **1985**, *65*, 121; Schmidbaur, H. *Angew. Chem. Int. Ed. Eng.* **1976**, *15*, 728. Al-Sa'ady, A.K.H., Moss, K., McAuliffe, C.A., Parish, R.V. *J. Chem. Soc. Dalton Trans.* **1984**, 1609.
54. Messmer, R.P. In Rhodin, T.N., Ertl, G., eds., *The Nature of the Surface Chemical Bond*, North-Holland: Amsterdam, 1979; Meutterties, E.L., Rhodin, T.N., Band, E., Bracker, C.F., Pretzer, W.R. *Chem. Rev.* **1979**, *79*, 91; Hoffmann, R. *Rev. Mod. Phys.*, in press, 1988.
55. The alternative method for the assembly of ordered monolayers, attributed to Langmuir and Blodgett, is a useful complement to self-assembly processes. See references 5 and 18.
56. An advancing contact angle is defined by the tangent where a spreading drop meets the surface; a receding contact angle is defined by the tangent formed as the drop is retracted. In practice, however, these angles are measured on stationary drops. For discussions, see Neumann, A.W., Good, R.J. In Good, R.J., Stromberg, R.R. eds., *Surface and Colloid Science*, vol. 11. Plenum: New York, 1979, pp. 31-47 and Reference 9.
57. This argument is equally valid for the gold monolayer systems, since the estimated surface density of functionality in those systems is of the same order of magnitude ($\sim 4-5 \times 10^{14}/\text{cm}^2$) as the derivatized polyethylene surfaces. See References 35 and 43.
58. Young, T. *Phil. Trans. Roy. Soc.* **1805**, *95*, 65.
59. For instance, see Good, R.J. In (Good, R.J., Stromberg, R.R., eds., *Surface and Colloid Science*, vol. 11, Plenum: New York, 1979, pp. 1-13.
60. Honig, B.H., Hubbel, W.L., Flewelling, R.F. *Ann. Rev. Biophys. Biophys. Chem.* **1986**, *15*, 163.
61. Hansch, C., Rockwell, S.D., Jow, P.Y.C., Leo, A., Steller, E.E. *J. Med. Chem.* **1977**, *20*, 304; Hansch, C., Leo, A., Unger, S.H., Kim, K.H., Nikaitani, D., Lien, E.J. *J. Med. Chem.* **1973**, *16*, 1207; Hansch, C., Leo, A. *Substituent Constants for Correlation Analysis in Chemistry and Biology*, Wiley: New York, 1979.
62. Vold, R.D., Vold, M.J. *Colloid and Interface Chemistry*, Addison-Wesley: Reading, MA, 1983.
63. Jaycock, M.J., Parfitt, G.D. *Chemistry of Interfaces*, Wiley: New York, 1981.
64. Good, R.J., Stromberg, R.R. *Surfaces and Colloid Science*, vol. 2. Plenum: New York, 1979.
65. de Gennes, P.G. *Rev. Mod. Phys.* **1985**, *57*, 827.
66. Joanny, J.F., de Gennes, P.G. *J. Chem. Phys.* **1984**, *81*, 552.

67. Kaelble, D.H. *Physical Chemistry of Adhesion*; Wiley-Interscience: New York, 1971, p. 170.
68. Gould, R.F., ed. *Adv. Chem. Ser.* 1964, 43.
69. Schwartz, L.W., Garoff, S. *Langmuir* 1985, 1, 219.
70. Schwartz, L.W., Garoff, S. *J. Coll. Int. Sci.* 1985, 106, 422.
71. Cherry, B.W. *Polymer Surfaces*, Cambridge University Press: Cambridge, UK, 1981.
72. Woodruff, D.P. *The Solid-Liquid Interface*; Cambridge University Press: Cambridge, UK, 1973.
73. Fortes, M.A. *J. Chem. Soc., Faraday Trans. 1* 1982, 78, 101.
74. Malev, V.V., Gribanova, E.V. *Dokl. Akad. Navk. SSSR* 1983, 272, 413.
75. Wolfram, E., Faust, R. *Anales Universitatis Scientiarum Budapest* 1980, 151.
76. Baszkin, A., Ter-Minassian-Saraga, L. *J. Coll. Int. Sci.* 1973, 43, 190.
77. Pomeau, Y., Vannimenus, J. *J. Coll. Int. Sci.* 1985, 104, 477.
78. Andrade, J.D., Smith, L.M., Gregonis, D.E. In Andrade, J.D., ed., *Surface and Interfacial Aspects of Biomedical Polymers*, vol. 1. Plenum: New York, 1985.
79. Ratner, B.D. In "Biomaterials: Interfacial Phenomena and Applications." Cooper, S.L., Peppas, N.A., eds., *Advances in Chemistry*, 199. American Chemical Society: Washington DC, 1982, chap. 2, pp. 9-23.
80. Durrani, A.A., Chapman, D. In Feast, W.J., Munro, H.S., eds., *Polymer Surfaces and Interfaces*, Wiley: Chichester, UK, 1987, chap. 10; Lundstrom, I., Ivarsson, B., Jonsson, U., Elwing, H. *Ibid.*, chap. 11.
81. Wu, S. *Polymer Interface and Adhesion*, Dekker: New York, 1982; Clark, D.T., Feast, W.J. *Polymer Surfaces*; Wiley: Chichester, UK 1977; Zisman, W.A. In Skeist, I., ed., *Handbook of Adhesives*, Van Nostrand: New York, 1977, Chap. 3.
82. Comyn, J., ed., *Polymer Permeability*, Elsevier: London, 1985.
83. Bowden, F.P., Tabor, D. *The Friction and Lubrication of Solids*, Part II, Oxford University Press: London, 1964.
84. Holmes-Farley, S.R., Reamey, R.H., McCarthy, T.J., Whitesides, G.M., unpublished results.
85. Scarmoutzos, L.M., Holmes-Farley, S.R., McCarthy, T.J., Whitesides, G.M., unpublished results.

CONTRACT DATA REQUIREMENTS LIST
INSTRUCTIONS FOR DISTRIBUTION
ARPA/ONR

MINIMUM DISTRIBUTION OF TECHNICAL REPORTS

<u>ADDRESSEE</u>	<u>DODAAD CODE</u>	<u>NUMBER OF COPIES</u>	
		<u>UNCLASSIFIED/UNLIMITED</u>	<u>UNCLASSIFIED/LIMITED AND CLASSIFIED</u>
Director, Advanced Research Projects Agency 1400 Wilson Boulevard Arlington, Virginia 22209 ATTN: Program Management	EX1241	2	2
Scientific Officer	N00014	3	3
Administrative Contracting Officer	N66016	1	1
Director, Naval Research Laboratory, ATTN: Code 1627 Washington, D. C. 20375	N00173	6	1
Defense Technical Information Center Bldg. 5, Cameron Station Alexandria, Virginia 22314	S47031	12	2

One (1) copy of each technical report resulting from work performed in the area of tactical technology shall be sent to:

TACTEC	<u>DODAAD CODE</u>
Battelle Memorial Institute	79986
505 King Avenue	
Columbus, Ohio 43201	

MINIMUM DISTRIBUTION OF REPORTS WHICH ARE NOT TECHNICAL REPORTS

<u>ADDRESSEE</u>	<u>DODAAD CODE</u>	<u>NUMBER OF COPIES</u>	
		<u>UNCLASSIFIED/UNLIMITED</u>	<u>UNCLASSIFIED/LIMITED AND CLASSIFIED</u>
Director, Advanced Research Projects Agency 1400 Wilson Boulevard Arlington, Virginia 22209 ATTN: Program Management	EX1241	2	2
Scientific Officer	N00014	3	3
Administrative Contracting Officer	N66016	1	1

If the Scientific Officer directs, the Contractor shall make additional distribution of technical reports and such other reports as may be specified by the Scientific Officer in accordance with a supplemental distribution list provided by the Scientific Officer.

ABSTRACTS DISTRIBUTION LIST, 356B

Professor T. Marks
Department of Chemistry
Northwestern University
Evanston, Illinois 60201

Dr. Kurt Baum
Fluorochem, Inc.
680 S. Ayon Avenue
Azusa, California 91702

Dr. Ulrich W. Suter
Department of Chemical and Engineering
Massachusetts Institute of Technologies
Room E19-628
Cambridge, MA 02139-4309

Dr. William Bailey
Department of Chemistry
University of Maryland
College Park, Maryland 20742

Dr. J.C.H. Chien
Department of Polymer Science and
Engineering
University of Massachusetts
Amherst, MA 01003

~~Professor G. Whitesides~~
~~Department of Chemistry~~
~~Harvard University~~
Cambridge, Massachusetts 02138

Dr. K. Paciorek
Ultrasystems, Inc.
P.O. Box 19605
Irvine, California 92715

Dr. Ronald Archer
Department of Chemistry
University of Massachusetts
Amherst, Massachusetts 01002

Professor D. Seyferth
Department of Chemistry
Massachusetts Institute of Technology
Cambridge, Massachusetts 02139

Professor J. Moore
Department of Chemistry
Rensselaer Polytechnic Institute
Troy, New York 12181

Dr. V. Percec
Department of Macromolecular
Science
Case Western Reserve University
Cleveland, Ohio 44106

Dr. Gregory Girolami
Department of Chemistry
University of Illinois
Urbana-Champaign, IL 61801

Dr. Ted Walton
Chemistry Division
Code 6120
Naval Research Lab
Washington D.C. 20375-5000

Professor Warren T. Ford
Department of Chemistry
Oklahoma State University
Stillwater, OK 74078

Professor H. K. Hall, Jr.
Department of Chemistry
The University Arizona
Tucson, Arizona 85721

Dr. Fred Wudl
Department of Chemistry
University of California
Santa Barbara, CA 93106

Professor Kris Matjaszewski
Department of Chemistry
Carnegie-Mellon University
4400 Fifth Avenue
Pittsburgh, PA 15213

Professor Richard Schrock
Department of Chemistry
Massachusetts Institute of Technology
Cambridge, MA 02139

ABSTRACTS DISTRIBUTION LIST, 356B

Professor A. G. MacDiarmid
Department of Chemistry
University of Pennsylvania
Philadelphia, Pennsylvania 19174

Dr. E. Fischer, Code 2853
Naval Ship Research and
Development Center
Annapolis, Maryland 21402

Professor H. Allcock
Department of Chemistry
Pennsylvania State University
University Park, Pennsylvania 16802

Professor R. Lenz
Department of Chemistry
University of Massachusetts
Amherst, Massachusetts 01002

Professor G. Wnek
Department of Chemistry
Rensselaer Polytechnic Institute
Troy, NY 12181

Professor C. Allen
Department of Chemistry
University of Vermont
Burlington, Vermont 05401

Dr. Ivan Caplan
DTNSRDC
Code 0125
Annapolis, MD 21401

Dr. R. Miller
Almaden Research Center
650 Harry Road K918801
San Jose, CA 95120

Dr. William B. Moniz
Chemistry Division
Naval Research Laboratory
Washington, D.C. 20375-5000

Dr. Richard M. Laine
SRI International
333 Ravenswood Avenue
Menlo Park, California 94025

Dr. L. Buckley
Naval Air Development Center
Code 6063
Warminster, Pennsylvania 18974

Dr. James McGrath
Department of Chemistry
Virginia Polytechnic Institute
Blacksburg, Virginia 24061

Dr. Geoffrey Lindsay
Chemistry Division
Naval Weapons Center
China Lake, California 93555

Professor J. Salamone
Department of Chemistry
University of Lowell
Lowell, Massachusetts 01854

Dr. J. Griffith
Naval Research Laboratory
Chemistry Section, Code 6120
Washington, D. C. 20375-5000

Professor T. Katz
Department of Chemistry
Columbia University
New York, New York 10027

Dr. Christopher K. Ober
Department of Materials Science
and Engineering
Cornell University
Ithaca, New York 14853-1501