OFFICE OF NAVAL RESEARCH CONTRACT NOOO 14-89-J-1849 R & T Code 4134005

Technical report No. 11

PREPARATION AND CHARACTERIZATION OF DISPERSED "COBALT OXIDE" SUPPORTED ON Y-A1203

by

C-S. Bai, S. Soled, K. Dwight and A. Wold

Prepared for Publication in

JOURNAL OF SOLID STATE CHEMISTRY



December 21, 1990

Brown University Department of Chemistry Providence, rhode Island 02912

Reproduction in whole or in part is permitted for any purpose of the United States Government.

This document has been approved for public release and sale; its distribution is unlimited.

AD-A231 269

	REPORT DOCU	MENTATION	PAGE			
1a REPORT SECURITY CLASSIFICATION unclassified		16 RESTRICTIVE	MARKINGS			
24 SECURITY CLASSIFICATION AUTHORITY		3 DISTRIBUTION	AVAILABILITY	OF REPO	RT	
26 DECLASSIFICATION / DOWNGRADING SCHEDL	JLE	DISTRIBUTIO	APPROVED FOR PUBLIC RELEASE DISTRIBUTION UNLIMITED			
4 PERFORMING ORGANIZATION REPORT NUMBE	ER(S)	5. MONITORING ORGANIZATION REPORT NUMBER(S)				
Report No. 11		NOOO 14-89-J-1849				
6a. NAME OF PERFORMING ORGANIZATION BROWN UNIVERSITY	6b OFFICE SYMBOL (If applicable)	7a. NAME OF MONITORING ORGANIZATION			······	
AARON WOLD		OFFICE OF NAVAL RESEARCH				
6C. ADDRESS (Gty, State, and ZIP Code) DEPARTMENT OF CHEMISTRY Box H		76. ADDRESS (Cit	ty, State, and 2	IP Code)		
BROWN UNIVERSITY		DR. MARK R	DSS			
PROVIDENCE, RI 02912		Arlington	icy St. VA 22217			
8a. NAME OF FUNDING/SPONSORING ORGANIZATION	8b. OFFICE SYMBOL (If applicable)	9. PROCUREMENT INSTRUMENT IDENTIFICATION NUMBER			MBER	
Bc ADDRESS (City, State, and ZIP Code)		10 SOURCE OF		BERS		
		PROGRAM ELEMENT NO.	PROJECT	TASK NO		WORK UNIT
C-S. Bai, S. Soled, K. Dwi 13a. TYPE OF REPORT 13b. TIME C FROM	ght and A. Wold OVERED	14 DATE OF REPO	DRT (Year, Mont	th, Day) G 12	15 PAGE	COUNT
C-S. Bai, S. Soled, K. Dwi 13a. TYPE OF REPORT 13b. TIME C CCMMCH 13b. TIME C FROM 16 SUPPLEMENTARY NOTATION Prepared for publication 17. CUSATI CODES FIELD GROUP SUB-GROUP	ght and A. Wold OVERED TO in Journal of St 18. SUBJECT TERMS	14 DATE OF REPO Dec olid State Ci Continue on revers	DRT (Year, Mont シント」 トロ nemistry e if necessary a	th, Day) G ひ and identi	15 PAGE	COUNT k number)
C-S. Bai, S. Soled, K. Dwi 13a. TYPE OF REPORT 13b. TIME OF 13b. TIME OF 17b. COSATI CODES FIELD GROUP 14b.	ght and A. Wold OVERED TO in Journal of St 18. SUBJECT TERMS (	14 DATE OF REPO Dec olid State Ci Continue on revers	DRT (Year, Mont L 1 19 nemistry e if necessary a	ih, Day) 9 D and identi	15 PAGE	COUNT k number)
C-S. Bai, S. Soled, K. Dwi 13a. TYPE OF REPORT 13b. TIME OF REPORT 13b. TIME C 13b. TIME C 13b. TIME C FROM 16 SUPPLEMENTARY NOTATION Prepared for publication 17. COSATI CODES FIELD GROUP SUB-GROUP SUB-GROUP Samples of "cobalt oxide" supp precursors. The samples were reduction, and measurement of with those of bulk Co <sub>3</sub> O <sub>4</sub> and C of preparation.	ght and A. Wold OVERED TO in Journal of Si 18. SUBJECT TERMS and identify by block iorted on gamma-J characterized by magnetic suscep OA12O4 and the o	14 DATE OF REPO Deco olid State Ci (Continue on revers Al <sub>2</sub> O <sub>3</sub> were pr y x-ray analy tibility. Th observed diff	DRT (Year, Mont - 21; 19 nemistry e if necessary of repared from vsis, temponetry heir proper ferences wo	n, Day) g U and identi om a va erature rties w ere rel	15 PAGE fy by block ariety de progra were con lated to	COUNT k number) of ammed mpared o the method
C-S. Bai, S. Soled, K. Dwi 13a. TYPE OF REPORT 13b. TIME OF 13b. TIME	ght and A. Wold OVERED TO in Journal of So 18. SUBJECT TERMS ( and identify by block forted on gamma- characterized b) magnetic suscep oAl <sub>2</sub> O <sub>4</sub> and the o	14 DATE OF REPO Dec olid State Ci (Continue on revers Al203 were pr y x-ray analy tibility. Th obsgrved diff	PRT (Year, Mont 	th, Day) GD and identi OM a Va erature rties v ere rel	15 PAGE	COUNT k number) of ammed mpared o the method
C-S. Bai, S. Soled, K. Dwi 13a. TYPE OF REPORT 13b. TIME OF REPORT 13b. TIME OF 13b. TIME OF 14b. TIME OF 15b. TIME OF 15	ght and A. Wold OVERED TO in Journal of Si 18. SUBJECT TERMS ( and identify by block in and identify by block orted on gamma	14 DATE OF REPO Dec olid State Ci (Continue on revers number) Al <sub>2</sub> O <sub>3</sub> were pr y x-ray analy tibility. The obsgrved diff	DRT (Year, Mont 	th, Day) 9 D and identi om a va erature rties w ere rel	15 PAGE ( fy by block ariety ( e progra were con lated to	COUNT k number) of ammed mpared o the method

# PREPARATION AND CHARACTERIZATION OF

ł

DISPERSED "COBALT OXIDE" SUPPORTED ON  $\gamma\text{-Al}_2\text{O}_3$ 

C-S. Bai, S. Soled\*, K. Dwight and A. Wold Department of Chemistry, Brown University

Providence, Rhode Island 02912

\*Exxon Research & Engineering Annandale, New Jersey 08801



OB FOF
RALI
B 11
meed 🗌
Leation
ويران متناب والمروج والمنابع ومراجع والمنابع
butlon/
ability Codes
WALL ADA/OF
Special
1

# Abstract

Samples of "cobalt oxide" supported on  $Y-Al_2O_3$  were prepared from a variety of precursors. The samples were characterized by x-ray analysis, temperature programmed reduction, and measurement of magnetic susceptibility. Their properties were compared with those of bulk  $Co_3O_4$  and  $CoAl_2O_4$  and the observed differences were related to the method of preparation.



÷

### Introduction

The nature of cobalt catalysts supported on  $\gamma - \lambda l_2 O_3$  has been the subject of many investigations (1-17). Most of these studies were concerned with the role of cobalt in hydrocracking processes and tried to provide an understanding of hydrodesulfurization of fossil fuels. During the final heat treatment in the preparation of these catalysts, cobalt ions diffuse into the  $\gamma - \lambda l_2 O_3$  structure and can occupy octahedral or tetrahedral sites. In most studies (1-17) it was reported that a dispersed " $\delta$ -phase" predominates when the cobalt loading is less than 2%. This phase consists of Co(II) ions and shows many of the chemical features of bulk  $Co\lambda l_2 O_4$ . This phase contains "non-reducible" cobalt. A second  $\beta$ -phase occurs at higher cobalt loading, and consists of Co<sub>1</sub>O<sub>4</sub> crystallites which can be reduced easily.

In almost all of the above studies, the precursor used to prepare the  $\gamma$ -Al<sub>2</sub>O<sub>3</sub> supported cobalt samples was an aqueous solution of cobalt nitrate. However, the literature does not include any systematic study of the influences of the precursor compound or the pH of the precursor solution on the dispersion of cobalt on  $\gamma$ -Al<sub>2</sub>O<sub>3</sub>. In the present study, various precursors are used to prepare  $\gamma - \lambda l_2 O_3$ samples containing "cobalt oxide." Each precursor is dissolved in an aqueous solution at a known pH. X-ray analysis, temperature programmed reduction studies and magnetic susceptibility measurements are used to characterize the composition and properties of each supported cobalt oxide sample.

# **Experimental**

Preparation of samples. Bulk  $Co_3O_4$  was prepared by the decomposition of  $Co(NO_3)_2 \cdot 6H_2O$  (Mallinckrodt) at 450°C for 24 hours.  $CoAl_2O_4$  was synthesized by dissolving appropriate weights of  $Co(NO_3)_2 \cdot 6H_2O$  and  $Al(NO_3)_3 \cdot 9H_2O$  (Allied Chemical) in water, evaporating to dryness, followed by careful decomposition of the product at 450°C. The resulting mixed oxides were heated in air at 950°C for 24 hours. CoO was prepared by heating  $CoCO_3$  (Allied Chemical) at 1000°C in an argon atmosphere for 24 hours. The  $Y-Al_2O_3$  was prepared by heating boehmite at 500°C in air for 24 hours. Boehmite (Y-AlOOH) was prepared hydrothermally according to the procedure of A. B. Kiss (18).

Samples of cobalt oxide containing 11.29 weight percent cobalt supported on Y-Al<sub>2</sub>O<sub>3</sub> were prepared from various cobalt precursors, namely, cobalt

ιŀ

acetate, cobalt nitrate, cobalt citrate and cobalt acetylacetonate. The latter two compounds were prepared in this laboratory. Analyses for the actual compositions of  $Co(NO_3)_2 \cdot 6H_2O$  and  $Co(C_2H_3O_2)_2 \cdot 4H_2O$  were performed by heating representative samples in air to 500°C and obtaining the weight loss. Corrected values reduced the compositions of cobalt dispersed on Y-A1203 samples from a nominal 11.38 weight percent cobalt to 11.29 weight percent. The products  $Co_3O_4$ , CoO and  $CoAl_2O_4$  were confirmed by x-ray analysis, temperature programmed reduction and magnetic susceptibility measurements; the phase Y-Al<sub>2</sub>O<sub>3</sub> was confirmed by x-ray diffraction analysis. An aqueous solution of each cobalt precursor was prepared and the pH was adjusted with acid. The acid was usually chosen to have the same anion as the precursor (see Table 1). Y-Al<sub>2</sub>O<sub>3</sub> was impregnated with the precursor solution, dried on a hot plate, and then heated in a drying oven at 230°C for 24 hours. The final heat treatment was carried out at 450°C for 24 hours.

Characterization of samples. X-ray powder diffraction analyses of the samples were obtained using a Philips diffractometer and monochromatic high intensity  $CuK\alpha_1$  radiation ( $\lambda = 1.5405$  Å). The diffraction patterns were taken in the range of  $12^\circ < 2\theta < 72^\circ$  with a scan rate of  $1^\circ 2\theta/\min$  and a chart speed of 30 in/hr.

Magnetic susceptibility was measured with a Faraday balance at a field strength of 10.4 kOe from liquid nitrogen temperature to 700 K. Honda-Owens (field dependency) measurements (susceptibility vs 1/H) were also made at room temperature and liquid nitrogen temperature, and all magnetic susceptibility data were corrected for core diamagnetism.

Temperature programmed reduction (TPR) measurements were taken using a Cahn system 113 thermal balance. The samples impregnated on Y-Al<sub>2</sub>O<sub>3</sub> were preheated in air at 400°C for 4 hours to remove most of the residual water before reduction. However, to correct for all of the residual water, a sample of Y-Al<sub>2</sub>O<sub>3</sub> was heated in dry air to 950°C and its weight loss was used to correct the initial sample weights. This correction amounted to approximately one third of the total weight loss of a fully reduced sample of  $\gamma-Al_2O_3$ impregnated with 11.29 weight percent cobalt. The samples were cooled down to room temperature and were then heated at 60°C/hr from room temperature to 950°C in a purified  $Ar/H_2$  (85/15) atmosphere; the rate of gas flow was 60 ml/min. The samples were maintained at 950°C for 4 hours in order to ensure constant weight. Two samples, i.e.  $CoAl_2O_4$  and the cobalt oxide, dispersed on

Y-Al<sub>2</sub>O<sub>3</sub>, which was prepared from a cobalt acetate precursor at pH 2.7, were heated in pure hydrogen at 950°C until  $\sim$  99% of the cobalt was reduced to cobalt metal.

## **Results and Discussion**

The bulk standard,  $Co_3O_4$ , was prepared by the decomposition of  $Co(NO_3)_2 \cdot 6H_2O$  at 450°C in air for 24 hours. X-ray diffraction analysis of the product confirmed the presence of  $Co_3O_4$ . Temperature programmed reduction of the product was carried out under an atmosphere of  $Ar/H_2(85/15)$  from room temperature to 950°C. For the standard  $Co_3O_4$  sample, reduction commenced at 220°C and was complete at 320°C. The observed weight loss of 26.6 percent is consistent with a calculated value of 26.5 weight percent for the reduction of  $Co_3O_4$  to cobalt metal. These results are in agreement with those previously reported in the literature (19).

However, bulk  $CoAl_2O_4$  showed no appreciable reduction in an  $Ar/H_2(85/15)$ atmosphere when heated up to 320°C. The product was then heated from 320°C to 950°C and maintained in the reducing atmosphere at 950°C for a total of four hours in order to achieve constant weight. The observed weight loss of 8.37 percent corresponds to 92.5 percent of the calculated value for the reducible cobalt present. Reduction of  $CoAl_2O_4$  in a pure hydrogen atmosphere at 950°C resulted in the reduction of 98.7 percent of the total reducible cobalt (see Table 2), because of the greater reducing power of pure hydrogen compared with that of  $Ar/F_4(85/15)$ .

X-ray analysis of the reduction products formed from bulk  $CoAl_2O_4$ , which had been reduced at a maximum temperature of 950°C, indicated the presence of metallic cubic cobalt, and  $\alpha$ -Al<sub>2</sub>O<sub>3</sub>. These results are consistent with the temperature programmed reduction data given in Table 2.

The sample of "cobalt oxide" supported on  $Y-Al_2O_3$ , prepared from the cobalt nitrate precursor at pH = 2.7, contained 11.29 weight percent of cobalt. This sample when formed at 450°C was identified by x-ray analysis as  $Co_3O_4 + Y-Al_2O_3$  (see Table 3). Magnetic susceptibility data (Table 4) confirmed the presence of the oxide  $Co_3O_4$ . This sample was reduced in an atmosphere of  $Ar/H_2$  (85/15) and at 320°C the observed weight loss of 0.97% co.responds to the calculated value for the reduction of all the Co(III) to Co(II) (Table 2). There was no evidence of free cobalt metal in the product. From magnetic susceptibility measurements of the product reduced at 320°C, the moment of the cobalt, namely 4.2 BM, corresponded to the value for Co(II) in a tetrahedral environment (20).

From Table 2 it can be seen that the additional weight loss between 320-950°C was 2.69 percent, which is 91% of the value calculated for the complete reduction of all the cobalt(II). The cobalt reduced in this temperatur range is referred to as "fixed cobalt(II) in a tetrahedral oxide environment." This cobalt species is similar in its property towards reduction to the cobalt(II) in CoAl<sub>2</sub>O<sub>4</sub>.

The sample of cobalt oxide supported on  $Y-Al_2O_3$  prepared from the nitrate precursor at pH = 5.6 showed little change from that prepared at pH = 2.7. Undoubtedly, the formation of a considerable quantity of  $Co_3O_4$  is a result of the partial oxidation of Co(II) by the nitrate ion, particularly during decomposition of the nitrate precursor.

For the samples prepared from cobalt acetate as a precursor at pH = 2.7, the TPR results shown in Table 2 indicate that most of the cobalt oxide is fixed and only a small quantity of  $Co_3O_4$  is present in the final product. The x-ray results confirmed these observations. When the pH of the cobalt acetate was raised to 5.6, there was an observed increase in the  $Co_3O_4$  content and a corresponding reduction in the amount of initial "fixed cobalt."

Ĺ

The magnetic susceptibility measurements are summarized in Table 4. The susceptibilities for bulk samples of  $Co_3O_4$  and  $CoAl_2O_4$  were determined to be 2.8 BM/mol Co and 4.2 BM/mol Co, respectively. The values for  $\mu$ , given in Table 4, for the products obtained from the decomposition of the acetate, acetylacetonate and citrate precursors are consistent with the relative quantity of fixed cobalt present in the sample, as obtained by TPR studies (Table 2).

For the products obtained from the nitrate precursor there appears to be a discrepancy between the susceptibility data مسd the TPR results. The س values indicate that almost all of the cobalt is present as  $Co_3O_4$ , whereas the TPR results show the apparent formation of a large amount of fixed cobalt oxide during the initial stage of the reduction process. Fig. 1 characterizes the reduction of bulk  $Co_3O_4$  and 11.29 weight percent cobalt on  $Y-Al_2O_3$  (from the nitrate precursor at pH = 2.7) in an oscillating magnetic field. The observed change in weight, therefore, measures the relative quantity of metallic cobalt formed during the reduction process. It can be seen that whereas bulk  $Co_3O_4$  reduces immediately to cobalt metal at 290°C, the supported samples produce no metallic cobalt until 420°C. This indicates that the initial stage of the reduction process involves the reduction of

cobalt(III) to cobalt(II) which behaves then as tetrahedral cobalt in an oxide environment. Hence, for all of the supported cobalt samples reduced between 220-320°C, the reduction process can be represented as a change of Co(III) to Co(II).

#### Acknowledgments

This research has been partially supported by the Office of Naval Research and by the National Science Foundation, Contract No. DMR 880-3184.

#### References

1. F. E. Massoth, "Advances in Catalysis," Vol. 27, P. 265, Academic Press, New York, 1978.

2. M. Lo Jacono, A. Cimino, and G. C. A. Schuit, *Gazz. Chim. Ital.*, <u>103</u>, 1281 (1973).

3. J. R. Tomlinson, R. O. Keeling, G. T. Rymer, and J. M. Bridges, "Actes du 2me Congr. Int. Catal." p. 1831. Editions Technip. Paris, 1961.

4. J. H. Ashley, and P. C. H. Mitchell, J. Chem. Soc. A, 2730 (1969).

5. H. Ueda, and N. Todo, J. Catal., 27, 281 (1972).

6. M. Lo Jacono, J. L. Verbeek, and G. C. A. Schuit, J. Catal., <u>29</u>, 463 (1973).

7. P. Ratnasamy, A. V. Ramaswamy, K. Banerjee, D. K. Sharma, and N. Ray, J. Catal., <u>38</u>, 19 (1975).

11

8. J. Grimbolt, J. P. Bonnelle, and J. P. Beaufils, *J. Electron. Spectrosc.* Relat. Phenom., <u>8</u>, 437 (1976).

9. R. I. Declerck-Grimée, P. Caresson, R. M. Friedman, and J. J. Fripiat, J. Phys. Chem., <u>83</u>, 885 (1978).

10. H. Topsøe, B. S. Clausen, N. Burriesci, R. Candia, and S. Mørup, in "Preparation of Catalysts, II" (B. Delmon, P. Grange, P.A. Jacobs and G. Poncelet, Eds.), p. 479. Elsevier, Amsterdam, 1979.

•

11. A. Lycourghiotis, C. Defossé, F. Delannay, J. LeMaitre, and B. Delmon, J. Chem. Soc. Faraday Trans. 1, 76, 1677 (1980).

12. R. B. Greegor, F. W. Lytle, R. L. Chin, and D. M. Hercules, J. Phys. Chem., <u>85</u>, 1232 (1981).

13. K. S. Chung, and F. E. Massoth, J. Catal., <u>64</u>, 320 (1980).

14. R. L. Chin, and D. M. Hercules, J. Phys. Chem., 86, 360 (1982).

15. K. S. Chung, and F. E. Massoth, J. Catal., <u>64</u>, 332 (1980).

16. N. Y. Topsøe, and H. Topsøe, J. Catal., <u>75</u>, 354 (1982).

17. P. Arnoldy, and J. A. Moulign, J. Catal., <u>93</u>, 38 (1985).

18. A. B. Kiss, G. Keresztuny, and L. Farkas, Spectrochimica Acta, <u>36A</u>, 653 (1980).

19. P. Wu, R. Kershaw, K. Dwight, and A. Wold, *Mat. Res. Bull.*, <u>23</u>, 475 (1988).

20. P. Cossee, "Magnetic Properties of Cobalt in  $Co_3O_4$  and Other Oxides." Ph.D. Thesis, University of Leiden, Holland, 1956.

# Figure Caption Sheet

Fig. 1. Variation of weight with application of a magnetic field as a function of temperature for supported "cobalt oxide" prepared from a cobalt nitrate precursor compared with bulk  $Co_3O_4$ .

ι

ŗ

:



(pm) agnodl JdpiaW sitangoM

# Table 1

Precursors and pH Used To Impregnate the Support  $Y-Al_2O_3$ With 11.29 Weight Percent Cobalt\*

Precursor Used	Acid to Adjust pH	pH of Solution
<u></u>		
Acetate	HAC	2.7
Acetate	HAC	5.6
Acetylacetonate	HAC	1.9
Citrate	Citric Acid	1.9
Nitrate	hno <sub>3</sub>	2.7
Nitrate	hno <sub>3</sub>	5.6

\* Wt% cobalt defined as 100 x wt(Co)/[wt(Co)+wt(Al<sub>2</sub>O<sub>3</sub>)]

1

# Table 2

## Temperature Programmed Reduction Data

	Weight Loss (%)			
	320°C	950°C	950°C	
Samples	Ar/H <sub>2</sub>	Ar/H <sub>2</sub>	pure H <sub>2</sub>	
COAl <sub>2</sub> 04	0	8.37	8.92(a)	
Acetate pH = 2.7	0.03	2.72	2.91(b)	
pH = 5.6	0.55	2.76		
Acetylacetonate pH = 1.9	0.03	2.67		
Citrate pH = 1.9	0.06	2.69		
Nitrate pH = 2.7	0.97	2.69		
pH = 5.6	0.97	2.69		

for 11.29 Wt% Cobalt\* for Various Precursors Supported on Y-Al<sub>2</sub>O<sub>3</sub>

:

\* Wt% cobalt defined as 100 x wt(Co)/[wt(Co)+wt(Al<sub>2</sub>O<sub>3</sub>)]

(a) 98.7% of the value calculated for complete reduction

(b) 98% of the value calculated for complete reduction

# Table 3

Phases Formed by 11.29 Wt% Cobalt\* from Various Precursors

Decomposition (°C) 450	Phases
<b>4</b> 50	Y-81-0-
<b>4</b> 50	Y-11-0-
	1 1203
450	$Co_{3}O_{4} + Y-Al_{2}O_{3}$
450	Y-A1203
450	Y-A1203
450	$Co_{3}O_{4} + Y-Al_{2}O_{3}$
450	$Co_{3}O_{4} + \gamma - Al_{2}O_{3}$
	450 450 450

Dispersed and Decomposed on  $\ensuremath{\,\mathrm{Y-Al}_20_3}$ 

.

\* Wt% cobalt defined as 100 x wt(Co)/[wt(Co)+wt(Al<sub>2</sub>O<sub>3</sub>)]

Table	4
-------	---

6

ś

Magnetic Susceptibility Data for 11.29 Wt% Cobalt\*

Samples	ש(BM)/mol Co	θ (K)
Co <sub>3</sub> 0 <sub>4</sub>	2.8	-112
CoAl <sub>2</sub> 04	4.2	- 94
Acetate precursor		
pH = 2.7	4.2	- 45
pH = 5.6	3.7	- 47
Acetylacetonate precursor		
pH = 1.9	4.2	- 38
Citrate precursor		
pH = 1.9	3.9	- 44
Nitrate precursor		
pH = 2.7	2.9	- 69
pH = 5.6	2.9	- 66

From Various Precursors Supported on  $Y-Al_2O_3$ 

\* Wt% cobalt defined as 100 x wt(Co)/[wt(Co)+wt(Al<sub>2</sub>O<sub>3</sub>)]